



US 20160068937A1

(19) **United States**(12) **Patent Application Publication**
Nakajima et al.(10) **Pub. No.: US 2016/0068937 A1**(43) **Pub. Date: Mar. 10, 2016**(54) **HIGH-STRENGTH HOT-ROLLED STEEL
SHEET AND METHOD FOR PRODUCING
THE SAME (AS AMENDED)***C22C 38/08* (2006.01)*C22C 38/06* (2006.01)*C22C 38/04* (2006.01)*C22C 38/02* (2006.01)(71) Applicant: **JFE STEEL CORPORATION**, Tokyo
(JP)*C22C 38/00* (2006.01)*B32B 15/01* (2006.01)*C23C 2/40* (2006.01)(72) Inventors: **Katsumi Nakajima**, Tokyo (JP);
Kazuhiko Yamazaki, Tokyo (JP);
Chikara Kami, Tokyo (JP)(52) **U.S. Cl.**CPC . *C22C 38/58* (2013.01); *C23C 2/40* (2013.01);*C23C 2/02* (2013.01); *C21D 6/004* (2013.01);*C21D 6/005* (2013.01); *C21D 6/008* (2013.01);*C21D 8/0205* (2013.01); *C21D 8/0226*(2013.01); *C22C 38/50* (2013.01); *C22C 38/46*(2013.01); *C22C 38/44* (2013.01); *C22C 38/38*(2013.01); *C22C 38/32* (2013.01); *C22C 38/28*(2013.01); *C22C 38/24* (2013.01); *C22C 38/16*(2013.01); *C22C 38/14* (2013.01); *C22C 38/12*(2013.01); *C22C 38/08* (2013.01); *C22C 38/06*(2013.01); *C22C 38/04* (2013.01); *C22C 38/02*(2013.01); *C22C 38/008* (2013.01); *C22C**38/005* (2013.01); *C22C 38/002* (2013.01);*C22C 38/001* (2013.01); *B32B 15/013*

(2013.01)

(73) Assignee: **JFE STEEL CORPORATION**, Tokyo
(JP)(21) Appl. No.: **14/784,450**(22) PCT Filed: **Mar. 17, 2014**(86) PCT No.: **PCT/JP2014/001508**

§ 371 (c)(1),

(2) Date: **Oct. 14, 2015**(30) **Foreign Application Priority Data**

Apr. 15, 2013 (JP) 2013-084446

Apr. 15, 2013 (JP) 2013-084447

Publication Classification(51) **Int. Cl.***C22C 38/58* (2006.01)*C23C 2/02* (2006.01)*C21D 6/00* (2006.01)*C21D 8/02* (2006.01)*C22C 38/50* (2006.01)*C22C 38/46* (2006.01)*C22C 38/44* (2006.01)*C22C 38/38* (2006.01)*C22C 38/32* (2006.01)*C22C 38/28* (2006.01)*C22C 38/24* (2006.01)*C22C 38/16* (2006.01)*C22C 38/14* (2006.01)*C22C 38/12* (2006.01)

(57)

ABSTRACT

A steel slab having a composition containing C: more than 0.07% and 0.2% or less, Si: 2.0% or less, Mn: 1.0% to 3.0%, Al: 0.1% or less, Ti: 0.05% to 0.3%, and V: 0.05% to 0.3% on a mass percent basis is heated to 1100° C. or more and is subjected to rough rolling and finish rolling. In the finish rolling, the total rolling reduction of two final passes is 30% or more, and the finish rolling temperature ranges from (A_{r3} transformation temperature) to (A_{r3} transformation temperature+120° C.). Cooling is started within 2 seconds after the finish rolling. Coiling is performed at an average cooling rate of 40° C./s or more at a coiling temperature in the range of 300° C. to 500° C. The resulting high-strength hot-rolled steel sheet has a microstructure in which a bainite phase constitutes more than 90% by volume, the average lath interval of bainite is 0.45 μ m or less, and the ratio of Fe-based carbide precipitated in bainite lath to all Fe-based carbide is 10% or more, has a high tensile strength of 900 MPa or more, and has significantly improved punchability in mass production.

HIGH-STRENGTH HOT-ROLLED STEEL SHEET AND METHOD FOR PRODUCING THE SAME (AS AMENDED)

TECHNICAL FIELD

[0001] The present invention relates to a high-strength hot-rolled steel sheet suitable for, for example, structural parts, such as members and frames, and underbody parts, such as suspensions, of automobile bodies, as well as automotive body components, such as truck frame parts. In particular, the present invention relates to improvement of punchability during mass production (hereinafter also referred to as punchability in mass production).

BACKGROUND ART

[0002] In recent years, from a global environmental conservation standpoint, there has been a strong demand for improved vehicle fuel efficiency. Thus, high-strength steel sheets are actively utilized as automotive body components in order to reduce the weight of automobile bodies. High-strength steel sheets are utilized not only in automobile structural parts but also in underbody parts and truck frame parts. In general, higher-strength steel sheets have lower workability. In particular, because automotive parts are formed by intense processing, steel sheets used as automotive body component materials are strongly required to have high strength and good workability.

[0003] To address such demands, for example, Patent Literature 1 describes a high-strength hot-rolled steel sheet having a composition containing, on a mass percent basis, C: 0.05% to 0.15%, Si: 1.50% or less, Mn: 0.5% to 2.5%, P: 0.035% or less, S: 0.01% or less, Al: 0.020% to 0.15%, and Ti: 0.05% to 0.2%, wherein the high-strength hot-rolled steel sheet has a microstructure containing 60% to 95% by volume bainite and solute-strengthened or precipitation-strengthened ferrite or ferrite and martensite and has good hole expansion formability, which is shown by a fracture transition temperature of 0° C. or less in a Charpy impact test. In a technique described in Patent Literature 1, after hot rolling, a steel sheet is cooled to a temperature in the range of 400° C. to 550° C. at an average cooling rate of 30° C./s or more, is coiled, and is cooled to a temperature of 300° C. or less at a cooling rate in the range of 50° C./h to 400° C./h. Patent Literature 1 states that such a process can prevent diffusion of P in grain boundaries, decrease the fracture transition temperature to 0° C. or less, improve toughness, and improve hole expansion formability.

[0004] Among automotive body components, truck frame parts and underbody parts are particularly frequently bored in order to join parts or reduce their weight or in order for a subsequent burring process or bore expanding process. In general, such boring is performed by punching from the perspective of productivity. Thus, improved punchability is often strongly required.

[0005] However, the technique described in Patent Literature 1 only prevents the intergranular segregation of P and improves hole expansion formability. Patent Literature 1 does not describe stamping workability. It is difficult to believe that the prevention of segregation of P in grain boundaries can directly improve punched surface properties and contribute to improved stamping workability.

[0006] With respect to improvement of stamping workability, for example, Patent Literature 2 proposes a high-strength

hot-rolled steel sheet having a composition containing, on a mass percent basis, C: 0.01% to 0.07%, N: 0.005% or less, S: 0.005% or less, Ti: 0.03% to 0.2%, and B: 0.0002% to 0.002%, having a microstructure containing ferrite or bainitic ferrite as a main phase and a hard second phase and cementite, the hard second phase and cementite having an area fraction of 3% or less, and having good stamping workability. It is stated that a technique described in Patent Literature 2 can retain B in a solid solution state and thereby prevent defects in punched surfaces. In the technologies described in Patent Literature 2, ferrite or bainitic ferrite is the largest area phase, and the hard second phase, which adversely affects hole expandability, is limited to 3% or less.

[0007] Patent Literature 3 proposes a high-strength hot-rolled steel sheet having a tensile strength of 780 MPa or more and good punchability. The high-strength hot-rolled steel sheet has a composition containing, on a mass percent basis, C: 0.05% to 0.15%, Si: 0.1% to 1.5%, Mn: 1% to 2%, P: 0.03% or less, S: 0.003% or less, Al: 0.01% to 0.08%, Ti: 0.05% to 0.15%, and N: 0.005% or less and has a bainite phase having an area fraction of more than 95%. The average particle size of the bainite microstructure at a quarter thickness in the depth direction is 5 μ m or less in a vertical cross section parallel to the rolling direction and 4 μ m or less in a vertical cross section perpendicular to the rolling direction. A region having a thickness of $\frac{1}{10}$ of the sheet thickness at a central position in the thickness direction contains 7 or less crystal grains having an aspect ratio of 5 or more each spreading in the rolling direction. The technologies described in Patent Literature 3 is intended to improve punchability by decreasing the average particle size of bainite and by decreasing the number of spreading grains in a central region in the thickness direction.

CITATION LIST

Patent Literature

[0008] PTL 1: Japanese Patent No. 3889766 (Japanese Unexamined Patent Application Publication No. 2006-274318)

[0009] PTL 2: Japanese Unexamined Patent Application Publication No. 2004-315857

[0010] PTL 3: Japanese Unexamined Patent Application Publication No. 2012-62562

SUMMARY OF INVENTION

Technical Problem

[0011] There are no particular specifications for evaluating the punchability of steel sheets. The punchability of steel sheets has been evaluated by using a method and conditions similar to those for boring before a hole-enlarging test according to a hole-enlarging test method specified in the Japan Iron and Steel Federation standard (JFS T1001). More specifically, in many cases, an approximately 100 mm $\times$ 100 mm blank sheet is taken from a steel sheet in a laboratory. Then a 10-mm ϕ hole is punched in the blank sheet with a cylindrical punch (10 mm ϕ) having no wear damage while the clearance condition of 12% $\pm$ 1% of the thickness (thickness: 2 mm or more) is strictly satisfied and while the blank sheet is uniformly and firmly held. And then, the punchability of the steel sheet is evaluated by observing the fracture surface at an end face of the punched hole.

[0012] However, even steel sheets, particularly high-strength steel sheets, having good punchability as evaluated by such a method often have poor boring during stamping in mass production of parts.

[0013] In the technologies described in Patent Literature 2 and Patent Literature 3, the punchability of steel sheets is evaluated by punching a 10 mm ϕ hole at a clearance corresponding to 17% to 23% of the thickness or 10% to 20% of the thickness, which is different from the punching clearance specified in JFS T1001. However, even high-strength steel sheets produced as steel sheets having good punchability by the technologies described in Patent Literature 2 and Patent Literature 3 often have poor boring during stamping in mass production and do not necessarily have good punchability in mass production. Thus, the quality of steel sheets must be further improved.

[0014] The present invention aims to solve such problems of the related art and to provide a high-strength hot-rolled steel sheet having high strength and excellent punchability in mass production of parts and a method for producing the high-strength hot-rolled steel sheet.

Solution to Problem

[0015] In order to achieve the objects, the present inventors studied various factors that can affect punchability in mass production of high-strength hot-rolled steel sheets.

[0016] As a result, the present inventors first found a large difference between punchability evaluated by a method conforming to a known standard and punchability in mass production of actual parts. Also in actual mass production of parts, the punching clearance is adjusted at a timing of a die change. However, it is very difficult to completely adjust and manage the punching clearance within proper condition ranges, and therefore the clearance change generally happens caused by the circumferential position on a punched hole. Furthermore, punches have chipping and wear during mass production, and it is almost impossible to completely maintain and manage punches. This results in varying punching conditions. Furthermore, in mass production of actual parts, in addition to variations in punching clearance described above, depending on the part shape and the manufacturing process, boring by stamping is sometimes required in the middle of a mass production process. The present inventors have come to realize that in such a case, the punching direction may become oblique rather than vertical, or it is difficult to center a hole, and the sheet clamping conditions may deteriorate. Unlike stamping in laboratories, stamping in mass production is punching under very severe conditions and is subjected to various process variations as described above. The present inventors found that even steel sheets having good punchability as determined by punchability evaluation in laboratories in conformity with such a standard therefore often have poor boring during stamping in mass production of parts.

[0017] Considering such stamping conditions in mass production, the present inventors further studied a method for evaluating punchability in mass production. As a result, the present inventors first found that the punched hole diameter and the sheet clamping conditions as well as variations in punching clearance greatly influence the appearances of punched surfaces in stamping in mass production. As a result of further studies, the present inventors found that the best method for evaluating punchability in mass production includes using a 50-mm ϕ punching punch of a flat-bottomed

type, determining the hole diameter of a die such that the punching clearance is 30%, placing a spacer on the punching die, placing a blank sheet on the spacer, holding the blank sheet with a blank holder, and punching the blank sheet.

[0018] The present inventors intensively studied the effects of the steel sheet structure on punchability in mass production by this evaluation method. As a result, the present inventors found that size-controlling of a bainite phase for decreasing the size of the bainite phase alone is not enough to achieve the desired punchability in mass production, and additional microstructure controlling (elaboration or evolution of microstructure controlling) is required. As a result of further studies, the present inventors found that the microstructure unit that controls punchability in mass production is not only a macroscopic bainite microstructure but also the intervals of its lower microstructure, that is, bainite lath and carbide precipitation behavior.

[0019] The present inventors further studied and found that the punchability in mass production of a high-strength hot-rolled steel sheet is effectively and significantly improved by adjusting the rolling reduction and finishing temperature of finish rolling as well as the cooling timing and cooling rate control after the finish rolling within appropriate ranges, by forming a steel sheet microstructure composed mainly of a bainite phase, by decreasing the intervals of the lower microstructure bainite lath, and by causing iron based carbide to be precipitated in bainite lath grains, in addition to adjustment of the slab heating temperature.

[0020] The present invention has been accomplished on the basis of these findings after further consideration. The following is the gist of the present invention.

[0021] (1) A high-strength hot-rolled steel sheet having good punchability in mass production, the high-strength hot-rolled steel sheet having a composition and a microstructure,

[0022] the composition containing, on a mass percent basis, C: more than 0.07% and 0.2% or less, Si: 2.0% or less, Mn: 1.0% to 3.0%, P: 0.05% or less, S: 0.005% or less, Al: 0.1% or less, N: 0.01% or less, Ti: 0.05% to 0.3%, V: 0.05% to 0.3%, and the balance being Fe and incidental impurities, wherein

[0023] the microstructure comprising a bainite of more than 90% by volume, the bainite having an average lath interval of 0.45 μ m or less, and Fe-based carbide precipitated in bainite lath grains having a ratio of 10% or more by number to all Fe-based carbide.

[0024] (2) The high-strength hot-rolled steel sheet according to (1), wherein the composition further contains at least one selected from Nb: 0.005% to 0.2% and B: 0.0002% to 0.0030% on a mass percent basis.

[0025] (3) The high-strength hot-rolled steel sheet according to (1) or (2), wherein the composition further contains at least one selected from Cu: 0.005% to 0.3%, Ni: 0.005% to 0.3%, and Sn: 0.005% to 0.3% on a mass percent basis.

[0026] (4) The high-strength hot-rolled steel sheet according to any one of (1) to (3), wherein the composition further contains at least one selected from Mo: 0.002% to 0.3% and Cr: 0.002% to 0.3% on a mass percent basis.

[0027] (5) The high-strength hot-rolled steel sheet according to any one of (1) to (4), wherein the composition further contains at least one selected from Ca: 0.0002% to 0.004% and REM: 0.0002% to 0.004% on a mass percent basis.

[0028] (6) A hot-dip galvanized steel sheet having a hot-dip galvanizing layer or alloyed hot-dip galvanizing layer on a surface of the high-strength hot-rolled steel sheet according to any one of (1) to (5).

[0029] (7) A method for producing a high-strength hot-rolled steel sheet having good punchability in mass production, including: heating a steel slab and subjecting the steel slab to hot rolling having rough rolling and finish rolling to form a hot-rolled steel sheet, wherein the steel slab contains, on a mass percent basis, C: more than 0.07% and 0.2% or less, Si: 2.0% or less, Mn: 1.0% to 3.0%, P: 0.05% or less, S: 0.005% or less, Al: 0.1% or less, N: 0.01% or less, Ti: 0.05% to 0.3%, V: 0.05% to 0.3%, and the balance being Fe and incidental impurities, wherein the hot rolling includes heating the steel slab to 1100° C. or more, a total rolling reduction of two final passes in the finish rolling being 30% or more, a finish-rolling finishing temperature being in a range of (A_{r3} transformation temperature) to (A_{r3} transformation temperature+120° C.), starting cooling within 2 seconds after the finish rolling, cooling the hot-rolled steel sheet to a coiling temperature at an average cooling rate of 40° C./s or more, and coiling the hot-rolled steel sheet at a coiling temperature: 300° C. to 500° C.

[0030] (8) The method for producing a high-strength hot-rolled steel sheet according to (7), wherein the composition further contains at least one selected from Nb: 0.005% to 0.2% and B: 0.0002% to 0.0030% on a mass percent basis.

[0031] (9) The method for producing a high-strength hot-rolled steel sheet according to (7) or (8), wherein the composition further contains at least one selected from Cu: 0.005% to 0.3%, Ni: 0.005% to 0.3%, and Sn: 0.005% to 0.3% on a mass percent basis.

[0032] (10) The method for producing a high-strength hot-rolled steel sheet according to any one of (7) to (9), wherein the composition further contains at least one selected from Mo: 0.002% to 0.3% and Cr: 0.002% to 0.3% on a mass percent basis.

[0033] (11) The method for producing a high-strength hot-rolled steel sheet according to any one of (8) to (10), wherein the composition further contains at least one selected from Ca: 0.0002% to 0.004% and REM: 0.0002% to 0.004% on a mass percent basis.

[0034] (12) A method for producing a hot-dip galvanized steel sheet, including: pickling a high-strength hot-rolled steel sheet produced by the method for producing a high-strength hot-rolled steel sheet according to any one of (7) and (11), and subjecting the high-strength hot-rolled steel sheet to annealing and plating treatment to form a coated steel sheet, wherein the annealing is performed at a soaking temperature of 730° C. or less, and the plating treatment after the annealing includes passing the high-strength hot-rolled steel sheet through a hot-dip galvanizing bath to form a hot-dip galvanizing layer on a surface of the high-strength hot-rolled steel sheet and optionally subjecting the high-strength hot-rolled steel sheet to alloying treatment for alloying the hot-dip galvanizing layer.

[0035] (13) A high-strength hot-rolled steel sheet having good punchability in mass production and having a composition containing, on a mass percent basis, C: 0.05% to 0.15%, Si: 1.5% or less, Mn: 1.0% to 2.0%, P: 0.05% or less, S: 0.005% or less, Al: 0.1% or less, N: 0.01% or less, Ti: 0.05% to 0.2%, and the balance being Fe and incidental impurities, wherein the high-strength hot-rolled steel sheet has a microstructure comprising a bainite of more than 92% by volume, the bainite having an average lath interval of 0.6 μ m or less, and Fe-based carbide precipitated in bainite lath grains having a ratio of 10% or more by number to all Fe-based carbide.

[0036] (14) The high-strength hot-rolled steel sheet according to (13), wherein the composition further contains at least one selected from Nb: 0.005% to 0.2% and B: 0.0002% to 0.0030% on a mass percent basis.

[0037] (15) The high-strength hot-rolled steel sheet according to (13) or (14), wherein the composition further contains at least one selected from Cu: 0.005% to 0.3%, Ni: 0.005% to 0.3%, and Sn: 0.005% to 0.3% on a mass percent basis.

[0038] (16) The high-strength hot-rolled steel sheet according to any one of (13) to (15), wherein the composition further contains at least one selected from Mo: 0.002% to 0.3% and Cr: 0.002% to 0.3% on a mass percent basis.

[0039] (17) The high-strength hot-rolled steel sheet according to any one of (13) to (16), wherein the composition further contains at least one selected from Ca: 0.0002% to 0.004% and REM: 0.0002% to 0.004% on a mass percent basis.

[0040] (18) A hot-dip galvanized steel sheet having a hot-dip galvanizing layer or alloyed hot-dip galvanizing layer on a surface of the high-strength hot-rolled steel sheet according to any one of (13) to (17).

[0041] (19) A method for producing a high-strength hot-rolled steel sheet having good punchability in mass production, the method including: heating a steel slab and subjecting the steel slab to hot rolling having rough rolling and finish rolling to form a hot-rolled steel sheet, wherein the steel slab contains, on a mass percent basis, C: 0.05% to 0.15%, Si: 1.5% or less, Mn: 1.0% to 2.0%, P: 0.05% or less, S: 0.005% or less, Al: 0.1% or less, N: 0.01% or less, Ti: 0.05% to 0.2%, and the balance being Fe and incidental impurities, wherein the hot rolling includes heating the steel slab to 1100° C. or more, a total rolling reduction of two final passes in the finish rolling being 30% or more, a finish-rolling finishing temperature being in a range of (A_{r3} transformation temperature) to (A_{r3} transformation temperature+120° C.), starting cooling within 2 seconds after the finish rolling, cooling the hot-rolled steel sheet to a coiling temperature at an average cooling rate of 50° C./s or more, and coiling the hot-rolled steel sheet at a coiling temperature: 300° C. to 500° C.

[0042] (20) The method for producing a high-strength hot-rolled steel sheet according to (19), wherein the composition further contains at least one selected from Nb: 0.005% to 0.2% and B: 0.0002% to 0.0030% on a mass percent basis.

[0043] (21) The method for producing a high-strength hot-rolled steel sheet according to (19) or (20), wherein the composition further contains at least one selected from Cu: 0.005% to 0.3%, Ni: 0.005% to 0.3%, and Sn: 0.005% to 0.3% on a mass percent basis.

[0044] (22) The method for producing a high-strength hot-rolled steel sheet according to any one of (19) to (21), wherein the composition further contains at least one selected from Mo: 0.002% to 0.3% and Cr: 0.002% to 0.3% on a mass percent basis.

[0045] (23) The method for producing a high-strength hot-rolled steel sheet according to any one of (19) to (22), wherein the composition further contains at least selected from Ca: 0.0002% to 0.004% and REM: 0.0002% to 0.004% on a mass percent basis.

[0046] (24) A method for producing a hot-dip galvanized steel sheet, including: pickling a high-strength hot-rolled steel sheet produced by the method for producing a high-strength hot-rolled steel sheet according to any one of (19) and (23), and subjecting the high-strength hot-rolled steel sheet to annealing and plating treatment to form a coated steel sheet having a coated layer on a surface thereof, wherein the

annealing is performed at a soaking temperature of 730° C. or less, and the plating treatment after the annealing includes passing the high-strength hot-rolled steel sheet through a hot-dip galvanizing bath to form a hot-dip galvanizing layer on a surface of the hot-rolled steel sheet and optionally subjecting the high-strength hot-rolled steel sheet to alloying treatment for alloying the hot-dip galvanizing layer.

[0047] (1) to (12) correspond to a first embodiment described below, and (13) to (24) correspond to a second embodiment described below.

Advantageous Effects of Invention

[0048] In accordance with the present invention, a high-strength hot-rolled, steel sheet that withstands severe stamping in mass production of parts and has good punchability in mass production can be easily produced as materials for automotive parts and the like. Thus, the present invention has industrially significant advantages. A high-strength hot-rolled steel sheet according to the present invention is suitable for truck frame parts and structural parts, such as members and frames, and underbody parts, such as suspensions, of automobile bodies in automobiles. The present invention effectively contributes to weight reduction of parts.

DESCRIPTION OF EMBODIMENTS

First Embodiment

[0049] The reason for limiting the compositions of a high-strength hot-rolled steel sheet according to a first embodiment will be described below. Unless otherwise specified, “%” refers to “% by mass”. The term “high-strength” in the embodiment refers to a tensile strength TS of 900 MPa or more.

C: More than 0.07% and 0.2% or Less

[0050] C is an element that effectively contributes to increase the strength of steel sheets and is a useful element that promotes bainite transformation and contributes to the formation of a bainite phase. An adequate C content results in increased carbide in bainite lath grains and improved punchability in mass production. These effects require a C content of more than 0.07%. An excessive C content of more than 0.2% results in poor workability and weldability. Thus, the C content is limited to more than 0.07% and 0.2% or less, preferably 0.079% or more, more preferably 0.10% or more, and preferably 0.19% or less.

Si: 2.0% or Less

[0051] Si is an element that increases the strength of steel sheets by solute strengthening and contributes to improved ductility of steel sheets. It is desirable that the Si content be 0.05% or more to produce these effects. However, an excessive Si content results in an increased transformation temperature and decreased formation of a bainite phase. A Si content of more than 2.0% results in marked Si type complex oxide invasion of crystal grain boundaries of a surface layer while a steel slab is heated, and the Si type complex oxide is difficult to remove by frequent descaling during hot rolling, thus resulting in poor appearances of punched surfaces during stamping in mass production of steel sheets and poor punchability in mass production. Thus, the Si content is limited to 2.0% or more, preferably 1.5% or less, more preferably 1.0% or less.

Mn: 1.0% to 3.0%

[0052] Mn is an effective element that contributes to increase the strength of steel sheets by solute strengthening and transformation strengthening. Furthermore, Mn functions to decrease the transformation temperature and decrease the size of bainite lath. These effects require a Mn content of 1.0% or more. However, an excessive Mn content of more than 3.0% results in significant center segregation and very poor workability. Thus, Mn is limited to the range of 1.0% to 3.0%, preferably 1.4% to 2.6%.

P: 0.05% or Less

[0053] P is an element that functions to increase the strength of steel sheets by solid solution. A high P content tends to result in segregation in grain boundaries and may adversely affect workability. Thus, it is desirable to minimize the P content. A P content up to 0.05% is allowable. Preferably, the P content is 0.03% or less.

S: 0.005% or Less

[0054] S forms sulfides. In particular, coarse sulfides reduce the ductility and workability of steel sheets. Thus, it is desirable to minimize the S content. A S content up to 0.005% is allowable. Thus, the S content is limited to 0.005% or less, preferably 0.003% or less, more preferably 0.0015% or less.

Al: 0.1% or Less

[0055] Al is an important element that functions as a deoxidizing agent for steel. It is desirable that the Al content be 0.01% or more to produce this effect. However, an Al content of more than 0.1% results in low castability and results in low surface quality and workability due to a large amount of residual inclusions (oxide) in steel. Thus, the Al content is limited to 0.1% or less, preferably 0.06% or less.

N: 0.01% or Less

[0056] N binds to a nitride-forming element and precipitates as a nitride, thereby contributing to a decreased size of crystal grains. However, a N content of more than 0.01% is responsible for low hot ductility and very poor burring formability due to the formation of a large amount of nitride. Thus, it is desirable to minimize the N content. A N content up to 0.01% is allowable. Thus, the N content is limited to 0.01% or less, preferably 0.006% or less, more preferably 0.004% or less.

Ti: 0.05% to 0.3%

[0057] Ti is one of the most important elements in the present invention. Ti tends to form a carbonitride and decreases the size of austenite (γ) grains before transformation, thereby contributing to decreased lath intervals of bainite after transformation. Furthermore, Ti increases carbide (carbonitride) in fine bainite lath grains, contributes to increased strength by precipitation strengthening, increases void forming sites in stamping, and contributes to improved punchability in mass production. These effects require a Ti content of 0.05% or more. However, an excessive Ti content of more than 0.3% results in very large rolling force, thereby making rolling operation difficult, or results in excessively coarse precipitates, thereby reducing workability. Thus, the Ti content is limited to the range of 0.05% to 0.3%, preferably 0.07% to 0.25%, more preferably 0.07% to 0.23%.

V: 0.05% to 0.3%

[0058] V functions to improve a strength-elongation balance and a strength-hole expandability balance and is one of the most important elements in the present invention. V also functions to decrease the lath intervals of bainite, thereby decreasing the occurrence intervals of micro voids in punching, facilitating linking between voids, and improving punchability in mass production. V also functions to decrease precipitation of coarse Fe-based carbide, thereby improving edge face properties in punching. These effects require a V content of 0.05% or more. An excessive V content of more than 0.3% cannot lead to further improvements of these effects, thus increasing production costs and resulting in economic disadvantages. Thus, the V content is limited to the range of 0.05% to 0.3%, preferably 0.07% or more, more preferably 0.22% or more, and preferably 0.28% or less, more preferably 0.26% or less.

[0059] These components are basic components. In the present invention, in addition to this basic composition, the following optional elements may be contained, if necessary: one or two selected from Nb: 0.005% to 0.2% and B: 0.0002% to 0.0030%, and/or one or two or more selected from Cu: 0.005% to 0.3%, Ni: 0.005% to 0.3%, and Sn: 0.005% to 0.3%, and/or one or two selected from Mo: 0.002% to 0.3% and Cr: 0.002% to 0.3%, and/or one or two selected from Ca: 0.0002% to 0.004% and REM: 0.0002% to 0.004%.

[0060] At least one selected from Nb: 0.005% to 0.2% and B: 0.0002% to 0.0030%

[0061] Nb and B are elements that contribute to improved punchability in mass production. If necessary, one or both of Nb and B may be contained.

[0062] Nb contributes to a finer microstructure and finely-dispersed carbide by the formation of precipitates (carbonitride), thereby decreasing the occurrence intervals of micro voids in punching and improving punchability in mass production. These effects preferably require a Nb content of 0.005% or more. However, an excessive Nb content of more than 0.2% results in coarse precipitates, poor workability, and increased production costs. Thus, if Nb is contained, the Nb content is preferably limited to the range of 0.005% to 0.2%, more preferably 0.005% to 0.15%.

[0063] B decreases the lath intervals of bainite and thereby contributes to improved punchability in mass production. These effects preferably require a B content of 0.0002% or more. However, an excessive B content of more than 0.0030% results in poor workability. Thus, if B is contained, the B content is preferably limited to the range of 0.0002% to 0.0030%, more preferably 0.0003% to 0.0020%.

At Least One Selected from Cu: 0.005% to 0.3%, Ni: 0.005% to 0.3%, and Sn: 0.005% to 0.3%

[0064] Cu, Ni, and Sn are elements that contribute to increased strength by solute strengthening. If necessary, one or two or more of Cu, Ni, and Sn may be contained. It is desirable to contain Cu: 0.005% or more, Ni: 0.005% or more, and/or Sn: 0.005% or more to produce the effect. However, a Cu content of more than 0.3%, a Ni content of more than 0.3%, and/or a Sn content of more than 0.3% results in poor hot workability and may result in surface layer cracking during hot rolling. Thus, if Cu, Ni, and/or Sn are contained, each of the Cu content, the Ni content, and the Sn content is preferably limited to the range of 0.005% to 0.3%, more preferably 0.005% to 0.2%.

At Least One Selected from Mo: 0.002% to 0.3% and Cr: 0.002% to 0.3%

[0065] Mo and Cr are elements that tend to form carbide (precipitates) and contribute to improved punchability in mass production by the formation of the precipitates. Mo and Cr are also elements that contribute to improved hardenability. Mo and Cr are also elements that contribute to finer bainite lath by decreasing the bainite transformation temperature. One or both of Mo and Cr may be contained, if necessary. It is desirable to contain Mo: 0.002% or more and/or Cr: 0.002% or more to produce these effects. However, an excessive Mo content of more than 0.3% and/or an excessive Cr content of more than 0.3% results in increased production costs and economic disadvantages. Thus, if Mo and/or Cr is contained, each of the Mo content and the Cr content is preferably limited to the range of 0.002% to 0.3%, more preferably 0.002% to 0.2%.

At Least One Selected from Ca: 0.0002% to 0.004% and REM: 0.0002% to 0.004%

[0066] Ca and REM are elements that effectively contribute to improved workability by morphology control of inclusions. If necessary, one or both of Ca and REM may be contained. It is desirable to contain Ca: 0.0002% or more and/or REM: 0.0002% or more to produce the effect. However, a Ca content of more than 0.004% and/or a REM content of more than 0.004% results in an increased amount of inclusions in steel and poor workability. Thus, if Ca and/or REM is contained, each of the Ca content and the REM content is preferably limited to the range of 0.0002% to 0.004%, more preferably 0.0002% to 0.003%.

[0067] The balance other than the components described above includes Fe and incidental impurities.

[0068] The reason for limiting the microstructure of a high-strength hot-rolled steel sheet according to the present invention will be described below.

[0069] A high-strength hot-rolled steel sheet according to the present invention has a microstructure in which a bainite phase constitutes more than 90% by volume, the average lath interval of bainite is 0.45 μm or less, and the ratio of Fe-based carbide precipitated in bainite lath grains to all Fe-based carbide is 10% or more.

[0070] In order to achieve the desired punchability in mass production, it is important that a bainite phase should constitute more than 90%, preferably more than 92%, more preferably more than 94%, by volume of the steel sheet structure, as described above.

[0071] The bainite phase is a mixed microstructure of ferrite and Fe-based carbide. In such a microstructure composed mainly of the bainite phase alone, an interface between ferrite and Fe-based carbide acts as a starting point for the formation of micro voids during punching. Thus, such a microstructure is advantageous to both appropriate formation of micro voids and subsequent void linking.

[0072] In the present invention, the intervals of bainite lath, which is the lower microstructure of the bainite phase, are 0.45 μm or less. This is based on the finding that a smaller bainite phase and a finer lower microstructure (decreased lath intervals of bainite) are important in achieving the desired punchability in mass production. When the lath intervals of bainite are more than 0.45 μm , the desired punchability in mass production cannot be achieved. Thus, the lath intervals of bainite are limited to 0.45 μm or less, preferably 0.40 μm or less, more preferably 0.35 μm or less. A second phase other than the bainite phase (the remainder) includes one or more of martensite, retained austenite, ferrite, and pearlite.

[0073] In the present invention, in order to achieve the desired punchability in mass production, the bainite phase in the microstructure contains carbide formed therein, and the ratio of Fe-based carbide precipitated in ferrite grains to all precipitated Fe-based carbide in the microstructure is 10% or more by number. When the ratio of Fe-based carbide precipitated in ferrite grains to all precipitated Fe-based carbide is less than 10% by number, the desired punchability in mass production cannot be achieved. Thus, the ratio of Fe-based carbide precipitated in grains to all Fe-based carbide is limited to 10% or more, preferably 15% or more, more preferably 20% or more, by number.

[0074] A preferred method for producing a high-strength hot-rolled steel sheet according to the present invention will be described below.

[0075] In the present invention, a steel slab having the composition described above is heated and is subjected to hot rolling composed of rough rolling and finish rolling to form a hot-rolled steel sheet.

[0076] A method for producing a steel slab is not particularly limited. Molten steel having the composition described above is formed by a common melting method, for example, in a converter, an electric furnace, or an induction furnace, and, if necessary, is subjected to secondary refining in vacuum degassing equipment, and is formed into a steel slab having predetermined dimensions by a common casting method, such as by continuous casting. An ingot making and blooming method may also be used without problems. The steel slab may be a thin slab having a thickness of approximately 30 mm. In the case of a thin slab, rough rolling may be omitted.

[0077] In the present invention, an electro-magnetic stirrer (EMS) or intentional bulging soft reduction casting (IBSR) may be used to reduce segregation of steel components during continuous casting. Electro-magnetic stirrer treatment can form equiaxed crystals at half the thickness of a sheet and reduce segregation. Intentional bulging soft reduction casting can prevent the flow of molten steel in an unsolidified portion of a continuous cast slab and reduce segregation at half the thickness of a sheet. At least one of these segregation reduction treatments can be used to improve good punchability characteristic of the present invention and improve elongation among the tensile properties described below.

[0078] A steel slab is heated to a heating temperature of 1100° C. or more and is subjected to hot rolling.

Steel Slab Heating Temperature: 1100° C. or More

[0079] In the present invention, precipitates in a slab must be redissolved. Thus, a steel slab is heated to a heating temperature of 1100° C. or more. A heating temperature of less than 1100° C. results in insufficient redissolution of precipitates, and a desired precipitate distribution cannot be achieved in a subsequent process. The heating temperature is preferably 1150° C. or more. An excessively high heating temperature results in coarse crystal grains and consequently coarse bainite lath. Thus, it is desirable that the heating temperature of a steel slab be limited to 1300° C. or less.

[0080] A heated steel slab is subjected to hot rolling composed of rough rolling and finish rolling to form a hot-rolled steel sheet. The rough rolling may be performed under any conditions where a desired sheet bar size can be achieved.

[0081] The rough rolling is followed by finish rolling. The conditions for the finish rolling are very important for the formation of a desired bainite lath microstructure.

Total Rolling Reduction of Two Final Passes in Finish Rolling: 30% or More

[0082] Formation of a desired bainite lath microstructure requires bainite transformation of austenite (γ) having sufficiently accumulated strain. Thus, in the present invention, the total rolling reduction of two final passes in finish rolling is limited. When the total rolling reduction of two final passes in finish rolling is less than 30%, strain is insufficiently accumulated in γ , and a desired bainite lath microstructure cannot be formed after transformation. Thus, the total rolling reduction of two final passes in finish rolling is limited to 30% or more, preferably 40% or more, more preferably 50% or more.

Finish-Rolling Finishing Temperature: (A_{r3} Transformation Temperature) to (A_{r3} Transformation Temperature+120° C.)

[0083] Finish-rolling finishing temperature control is also important for bainite transformation of austenite (γ) having sufficiently accumulated strain. When the finish-rolling finishing temperature is less than the A_{r3} transformation temperature, it is difficult to form the desired microstructure, that is, the microstructure composed mainly of a bainite phase alone. When the finish-rolling finishing temperature is higher than (A_{r3} transformation temperature+120° C.), it is difficult to form a fine bainite phase. Thus, the finish-rolling finishing temperature is limited to (A_{r3} transformation temperature) to (A_{r3} transformation temperature+120° C.), preferably (A_{r3} transformation temperature) to (A_{r3} transformation temperature+80° C.). The finish-rolling finishing temperature herein refers to a surface temperature. The term " A_{r3} transformation temperature", as used herein, refers to a transformation temperature determined from a changing point in a thermal expansion curve obtained by cooling at a cooling rate of 1° C./s after processing with a Formastor testing machine (Thermecmaster-Z).

[0084] After the finish rolling, cooling is performed. The cooling conditions are also very important for the formation of a desired microstructure.

Cooling Start: Within 2 Seconds after Finish Rolling

[0085] In order to form a desired bainite lath microstructure by bainite transformation of γ (austenite) having sufficiently accumulated strain, cooling must be started within 2 seconds after finish rolling. When cooling is started more than 2 seconds after finish rolling, recovery of γ and recrystallization occur, and the number of nuclei for bainite transformation decreases. Thus, the desired bainite lath microstructure cannot be formed. Thus, cooling is started within 2 seconds, preferably 1.5 seconds, more preferably 1 second, after finish rolling.

Average Cooling Rate: 40° C./s or More

[0086] When the average cooling rate from the finish-rolling finishing temperature to the cooling stop temperature is less than 40° C./s, pro-eutectoid ferrite is precipitated, making it difficult to form the microstructure in which a bainite phase constitutes more than 90% by volume and that has the desired lath intervals of bainite. Thus, the average cooling rate of cooling after finish rolling is limited to 40° C./s or more, preferably 50° C./s or more, more preferably 60° C./s or more. The upper limit of the cooling rate depends on the capacity of cooling facilities and is preferably approximately 150° C./s or less in terms of the shape of steel sheets. In the present invention, control of the cooling rate after finish rolling as described above and single-stage cooling to the cooling

stop temperature as described below are among the requirements for the formation of the microstructure characteristic of the present invention.

Cooling Stop Temperature: 300° C. To 500° C.

[0087] In the present invention, coiling is performed immediately after cooling stop. Thus, the coiling temperature is the same as the cooling stop temperature. When the cooling stop temperature (coiling temperature) is less than 300° C. or more than 500° C., the lath intervals of bainite and the Fe-based carbide distribution cannot be controlled within desired optimum ranges. Thus, the cooling stop temperature (coiling temperature) is limited to the range of 300° C. to 500° C., preferably 350° C. to 500° C.

[0088] After coiling, scales on the surface may be removed by pickling according to routine procedures. After pickling treatment, a hot-rolled steel sheet may be subjected to temper rolling. After pickling treatment or temper rolling, a hot-rolled steel sheet may be annealed at a soaking temperature of 730° C. or less and may be passed through a hot-dip galvanizing bath to form a galvanized layer on the surface thereof, thereby producing a hot-dip galvanized steel sheet. When the soaking temperature for annealing treatment is more than 730° C., bainite is tempered, making it difficult to form the microstructure in which a bainite phase constitutes more than 90% by volume and that has the desired lath intervals of bainite. Thus, the soaking temperature for annealing treatment is 730° C. or less. Although the lower limit of the annealing temperature is not particularly limited, the soaking temperature for annealing treatment is preferably 600° C. or more in terms of adhesion between a hot-dip galvanizing layer and a base steel sheet. After immersed in the hot-dip galvanizing bath, the galvanized layer may be subjected to alloying treatment to produce a galvannealed steel sheet.

[0089] The resulting hot-rolled steel sheet may be used to produce a coated steel sheet, such as an electrogalvanized steel sheet, as well as a hot-dip galvanized steel sheet.

[0090] A high-strength hot-rolled steel sheet according to the present invention will be described below with examples.

Example 1

[0091] A steel slab having a composition listed in Table 1 was subjected to heating, finish rolling, and cooling after rolling listed in Table 2 to produce a hot-rolled steel sheet. In continuous casting, hot-rolled steel sheets other than a hot-rolled steel sheet No. 1' of steel A1 in Tables 1 to 3 described below were subjected to an electro-magnetic stirrer (EMS) to reduce segregation of components of the steel. Table 1 also lists the A_{r3} transformation temperature of each steel slab determined from a thermal expansion curve. After pickling, some of the hot-rolled steel sheets were passed through a continuous hot-dip galvanizing line and were subjected to annealing treatment under the conditions listed in Table 2 and hot-dip galvanizing treatment to produce hot-dip galvanized steel sheets (GI). In the hot-dip galvanizing treatment, each of the hot-rolled steel sheets subjected to the annealing treatment was immersed in a galvanizing bath (0.1% by mass Al—Zn) at 480° C., and 45 g/m² of a hot-dip galvanized layer was formed on each side of the steel sheet. After the hot-dip galvanizing treatment, some of the hot-rolled steel sheets were subjected to alloying treatment to produce galvannealed steel sheets (GA). The alloying treatment temperature was 520° C.

[0092] Test specimens were taken from the hot-rolled steel sheets (including coated steel sheets) and were subjected to microstructure observation, a tensile test, and a punchability-in-mass-production test. The test methods were as follows:

(1) Microstructure Observation

[0093] Test specimens for microstructure observation were taken from the hot-rolled steel sheets (coated steel sheets). A vertical cross section (L cross section) of each test specimen parallel to the rolling direction was polished and was etched with a 3% nital solution to expose a microstructure. The microstructure in the L cross section at a quarter thickness in the depth direction was observed with a scanning electron microscope (magnification: 3000 times). Ten visual fields of the microstructure were photographed. Phases other than a bainite phase were separated by image analysis to determine the percentage of the phases other than bainite and calculate the area percentage of the bainite phase. The area percentage calculated in this manner was considered to be the volume percentage of the bainite phase.

[0094] Samples for a thin film were taken from the hot-rolled steel sheets (coated steel sheets) at a quarter thickness in the depth direction and were subjected to mechanical polishing and electropolishing to prepare thin film specimens. The microstructure of each thin film specimen was observed with a transmission electron microscope (magnification: approximately 30000). Ten visual fields of the microstructure were photographed. The lath intervals of bainite were measured and were averaged to determine the lath intervals of bainite of each hot-rolled steel sheet.

[0095] Test specimens for microstructure observation were taken from the hot-rolled steel sheets (coated steel sheets). A vertical cross section (L cross section) of each test specimen parallel to the rolling direction was polished and was etched with a 3% nital solution to expose a microstructure. A replica sample at a quarter thickness in the depth direction was prepared. The microstructure of the replica sample was observed with a transmission electron microscope (magnification: approximately 30000 times). Ten visual fields of the microstructure were photographed. The number of Fe precipitates was measured in each precipitation site (at a grain boundary and within a grain) in the microstructure photographs, thereby calculating the ratio of the number of Fe precipitates in bainite lath grains to the number of all Fe precipitates. Fe precipitates were identified by the shape of the precipitates and by energy dispersive X-ray (EDX) analysis.

[0096] It was confirmed that substantially the same microstructure was also observed in a central portion in the thickness direction.

(2) Tensile Test

[0097] Three JIS No. 5 tensile test pieces were taken from each of the hot-rolled steel sheets (coated steel sheets) such that the tensile direction was perpendicular to the rolling direction. The test pieces were subjected to a tensile test according to JIS Z 2241. The cross head speed was 10 mm/min. The averages of tensile properties (tensile strength TS and elongation El) were considered to be the tensile properties of the steel sheets.

(3) Punchability-in-Mass-Production Test

[0098] A blank sheet (size: 150×150 mm) was taken from each of the hot-rolled steel sheets (coated steel sheets). A

50-mm ϕ punching punch of a flat-bottomed type was used. The hole diameter of a die was determined such that the punching clearance was 30%. A spacer was placed on the punching die. A blank sheet was placed on the spacer and was held with a blank holder. A hole was then punched in the blank sheet. After punching, the fracture surface condition of the punched surface was observed around the entire perimeter of the punched hole with a scanning electron microscope (magnification: 100 times) and was checked for cracking, chip-

ping, a brittle fracture surface, a secondary shear surface, and cross section roughness. Punchability in mass production was rated as follows: fracture surfaces free of cracking, chipping, a brittle fracture surface, a secondary shear surface, and cross section roughness were rated as good (circle); fracture surfaces having cross section roughness were rated as fair (triangle); and the other fracture surfaces were rated as poor (x).

[0099] Table 3 shows the results.

TABLE 1

Steel No.	Chemical composition (mass %)												Transformation		
	C	Si	Mn	P	S	Al	N	Ti	V	Nb, B	Cu, Ni, Sn	Mo, Cr	Ca, REM	temperature A _{r3} (° C.)	Remarks
A1	0.079	0.17	1.66	0.047	0.0029	0.044	0.0034	0.078	0.259	Nb: 0.008	—	—	Ca: 0.0013	894	Suitable example
B1	0.102	0.75	1.11	0.023	0.0004	0.019	0.0042	0.159	0.097	B: 0.0011	—	—	—	911	Suitable example
C1	0.123	1.42	2.38	0.007	0.0019	0.038	0.0021	0.109	0.179	Nb: 0.004	Sn: 0.04	—	—	886	Suitable example
D1	0.141	0.69	1.99	0.011	0.0005	0.033	0.0033	0.118	0.198	—	—	—	—	863	Suitable example
E1	0.159	0.41	1.59	0.013	0.0009	0.044	0.0027	0.133	0.223	—	—	—	—	859	Suitable example
F1	0.108	0.08	1.72	0.027	0.0014	0.024	0.0062	0.124	0.147	—	Ni: 0.22	Cr: 0.09, Mo: 0.03	REM: 0.0025	864	Suitable example
G1	0.116	0.75	1.89	0.005	0.0004	0.066	0.0011	0.069	0.288	—	B: 0.0004	Cr: 0.03	—	871	Suitable example
H1	0.137	0.27	2.47	0.011	0.0009	0.042	0.0048	0.168	0.129	—	—	Mo: 0.09	—	831	Suitable example
I1	0.185	0.01	2.57	0.017	0.0011	0.046	0.0037	0.138	0.226	Nb: 0.014	—	—	—	808	Suitable example
J1	0.088	0.04	2.83	0.009	0.0038	0.039	0.0024	0.252	0.059	—	Cu: 0.04, Ni: 0.08	—	—	823	Suitable example
K1	0.068	0.08	0.94	0.013	0.0011	0.049	0.0048	0.143	0.213	—	—	—	—	891	Comparative example
L1	0.104	0.03	1.84	0.011	0.0028	0.058	0.0053	0.044	0.258	—	—	—	—	848	Comparative example
M1	0.095	1.39	1.13	0.023	0.0025	0.033	0.0028	0.128	0.050	—	—	—	Ca: 0.0025	942	Suitable example
N1	0.114	0.76	1.26	0.019	0.0009	0.055	0.0039	0.068	0.009	Nb: 0.009	—	—	—	901	Comparative example

TABLE 2

		Hot-rolling conditions				Cooling conditions		Coiling	Hot-dip galvanizing		
		Sheet		Finish-rolling	Total rolling	Cooling	Average	conditions	treatment		
Hot-rolled steel sheet No.	Steel No.	thick-ness mm	Heating temperature (° C.)	finishing temperature (° C.)	reduction of two final passes (%)	start time (s)	cooling rate* (° C./s)	Coiling temperature (° C.)	Annealing temperature (° C.)	Alloying treatment	Remarks
1	A1	2.9	1180	905	35	1.3	65	425	—	—	Example
1'	A1	2.9	1180	900	35	1.4	60	425	—	—	Example
2	B1	2.6	1290	950	40	0.9	80	450	—	—	Example
3	B1	2.0	1290	915	45	0.8	90	440	605	—	Example
4	B1	2.6	1290	920	45	1.3	80	480	785	—	Comparative example
5	B1	2.6	1290	915	50	2.5	55	385	—	—	Comparative example
6	C1	4.0	1220	890	35	1.4	60	430	—	—	Example
7	D1	2.6	1250	920	60	0.8	100	400	—	—	Example
8	D1	2.0	1250	840	45	1.4	125	420	—	—	Comparative example
9	D1	2.6	1250	880	20	1.7	95	495	—	—	Comparative example

TABLE 2-continued

Hot-rolled steel sheet No.	Steel No.	Hot-rolling conditions				Cooling conditions		Coiling conditions	Hot-dip galvanizing		
		Sheet	Heating temperature (° C.)	Finish-rolling	Total rolling	Cooling start time (s)	Average		Annealing temperature (° C.)	Alloying treatment	Remarks
		thick- ness mm		finishing temperature (° C.)	reduction of two final passes (%)		cooling rate* (° C./s)	Coiling temperature (° C.)			
10	E1	3.6	1260	900	55	0.6	90	415	680	Yes	Example
<u>11</u>	E1	3.6	1260	910	50	1.4	<u>25</u>	440	645	—	Comparative example
<u>12</u>	E1	2.6	1260	930	50	1.8	80	<u>275</u>	—	—	Comparative example
13	F1	3.6	1260	870	30	1.9	40	495	—	—	Example
14	G1	2.0	1200	940	40	1.2	145	400	—	—	Example
15	H1	4.0	1290	850	40	0.7	50	355	—	—	Example
16	I1	2.6	1280	920	35	1.6	125	325	—	—	Example
17	J1	2.0	1290	900	50	1.1	75	405	725	—	Example
<u>18</u>	<u>K1</u>	3.6	1290	895	55	1.9	60	490	—	—	Comparative example
<u>19</u>	<u>L1</u>	3.6	1250	900	40	1.4	90	480	705	—	Comparative example
<u>20</u>	M1	3.6	1250	945	45	1.1	45	<u>530</u>	—	—	Comparative example
<u>21</u>	<u>N1</u>	3.6	1280	905	50	1.7	55	410	—	—	Comparative example

*Average cooling rate from finish-rolling finishing temperature to coiling temperature

TABLE 3

		Structure**			Tensile properties		Punchability in	
Hot-rolled steel sheet No.	Steel No.	Bainite fraction (vol %)	Lath interval of bainite (μm)	Ratio of Fe- based carbide in grains* (%)	Tensile strength TS (MPa)	Elongation El (%)	mass production Evaluation of punched surface	Remarks
1	A1	91	0.37	11.6	903	20	○	Example
1'	A1	92	0.36	11.5	905	18	Δ	Example
2	B1	94	0.28	15.9	985	17	○	Example
3	B1	93	0.25	13.3	982	16	○	Example
4	B1	72	1.25	12.4	954	8	x	Comparative example
5	B1	94	0.88	10.0	985	13	x	Comparative example
6	C1	95	0.33	15.2	991	17	○	Example
7	D1	98	0.26	20.2	996	19	○	Example
8	D1	63	0.65	6.3	986	11	x	Comparative example
9	D1	82	0.93	5.1	971	12	x	Comparative example
10	E1	97	0.23	23.1	1008	19	○	Example
11	E1	68	0.55	12.8	997	10	x	Comparative example
12	E1	81	0.21	2.1	1010	11	x	Comparative example
13	F1	90.5	0.44	28.5	956	16	○	Example
14	G1	93	0.19	18.8	1005	15	○	Example
15	H1	95	0.15	13.4	1106	14	○	Example
16	I1	96	0.11	10.3	1183	13	○	Example
17	J1	94	0.39	15.8	922	19	○	Example
18	K1	83	0.94	16.5	934	11	x	Comparative example
19	L1	98	0.56	5.4	886	12	x	Comparative example
20	M1	93	0.78	8.8	981	13	x	Comparative example
21	N1	97	0.47	6.7	984	14	x	Comparative example

*Number ratio of Fe-based carbide in grains to all Fe-based carbide

**Measurement at quarter thickness

[0100] The hot-rolled steel sheets (coated steel sheets) according to the examples had a high tensile strength TS of 900 MPa or more and good punchability in mass production. In contrast, the comparative examples outside the scope of the present invention had poor punchability in mass production.

Second Embodiment

[0101] The reason for limiting the compositions of a high-strength hot-rolled steel sheet according to a second embodiment will be described below. Unless otherwise specified, “%” refers to “% by mass”. The term “high-strength” in the second embodiment refers to a tensile strength TS in the range of 700 to 900 MPa.

C: 0.05% to 0.15%

[0102] C is an element that effectively contributes to increase the strength of steel sheets and is a useful element that promotes bainite transformation and contributes to the formation of a bainite phase. An adequate C content results in increased carbide in bainite lath grains and improved punchability in mass production. These effects require a C content of 0.05% or more. An excessive C content of more than 0.15% results in poor workability and weldability. Thus, the C content is limited to the range of 0.05% to 0.15%, preferably 0.071% or more, more preferably 0.080% or more, and 0.14% or less.

Si: 1.5% or Less

[0103] Si is an element that increases the strength of steel sheets by solute strengthening and contributes to improved ductility of steel sheets. It is desirable that the Si content be 0.05% or more to produce these effects. However, an excessive Si content of more than 1.5% results in an increased transformation temperature and decreased formation of a bainite phase. Thus, the Si content is limited to 1.5% or less, preferably 1.0% or less.

Mn: 1.0% to 2.0%

[0104] Mn is an effective element that contributes to increase the strength of steel sheets by solute strengthening and transformation strengthening. Furthermore, Mn functions to decrease the transformation temperature and decrease the size of bainite lath. These effects require a Mn content of 1.0% or more. However, a Mn content of more than 2.0% results in significant center segregation and very poor workability. Thus, the Mn content is limited to the range of 1.0% to 2.0%, preferably 1.2% to 1.9%.

P: 0.05% or Less

[0105] P is an element that functions to increase the strength of steel sheets by solid solution. A high P content tends to result in segregation in grain boundaries and may adversely affect workability. Thus, it is desirable to minimize the P content. A P content up to 0.05% is allowable. Preferably, the P content is 0.03% or less.

S: 0.005% or Less

[0106] S forms sulfides. In particular, coarse sulfides reduce the ductility and workability of steel sheets. Thus, it is desirable to minimize the S content. A S content up to 0.005% is allowable. Thus, the S content is limited to 0.005% or less, preferably 0.003% or less, more preferably 0.0015% or less.

Al: 0.1% or Less

[0107] Al is an important element that functions as a deoxidizing agent for steel. It is desirable that the Al content be 0.01% or more to produce this effect. However, an Al content of more than 0.1% results in low castability and results in low surface quality and workability due to a large amount of residual inclusions (oxide) in steel. Thus, the Al content is limited to 0.1% or less, preferably 0.06% or less.

N: 0.01% or Less

[0108] N binds to a nitride-forming element and precipitates as a nitride, thereby contributing to a decreased size of crystal grains. However, a N content of more than 0.01% is responsible for low hot ductility and very poor burring formability due to the formation of a large amount of nitride. Thus, it is desirable to minimize the N content. AN content up to 0.01% is allowable. Thus, the N content is limited to 0.01% or less, preferably 0.006% or less, more preferably 0.004% or less.

Ti: 0.05% to 0.2%

[0109] Ti is one of the most important elements in the present invention. Ti tends to form a carbonitride and decreases the size of austenite (γ) grains before transformation, thereby contributing to decreased lath intervals of bainite after transformation. Furthermore, Ti increases carbide (carbonitride) in fine bainite lath grains, contributes to increased strength by precipitation strengthening, acts as a void forming site and increases voids in stamping, and contributes to improved punchability in mass production. These effects require a Ti content of 0.05% or more. However, an excessive Ti content of more than 0.2% results in very large rolling force, thereby making rolling operation difficult, or results in excessively coarse precipitates, thereby reducing workability. Thus, the Ti content is limited to the range of 0.05% to 0.2%, preferably 0.065% to 0.125%, more preferably 0.065% to 0.10%.

[0110] These components are basic components. In the present invention, in addition to this basic composition, the following optional elements may be contained, if necessary: one or two selected from Nb: 0.005% to 0.2% and B: 0.0002% to 0.0030%, and/or one or two or more selected from Cu: 0.005% to 0.3%, Ni: 0.005% to 0.3%, and Sn: 0.005% to 0.3%, and/or one or two selected from Mo: 0.002% to 0.3% and Cr: 0.002% to 0.3%, and/or one or two selected from Ca: 0.0002% to 0.004% and REM: 0.0002% to 0.004%.

One or Two Selected from Nb: 0.005% to 0.2% and B: 0.0002% to 0.0030%

[0111] Nb and B are elements that contribute to improved punchability in mass production. If necessary, one or both of Nb and B may be contained.

[0112] Nb contributes to a finer microstructure and finely-dispersed carbide by the formation of precipitates (carbonitride), thereby decreasing the occurrence intervals of micro voids in stamping and improving punchability in mass production. These effects preferably require a Nb content of 0.005% or more. However, an excessive Nb content of more than 0.2% results in coarse precipitates, poor workability, and increased production costs. Thus, if Nb is contained, the Nb content is preferably limited to the range of 0.005% to 0.2%, more preferably 0.005% to 0.15%.

[0113] B decreases the lath intervals of bainite and thereby contributes to improved punchability in mass production.

These effects preferably require a B content of 0.0002% or more. However, an excessive B content of more than 0.0030% results in poor workability. Thus, if B is contained, the B content is preferably limited to the range of 0.0002% to 0.0030%, more preferably 0.0003% to 0.0020%.

At Least One Selected from Cu: 0.005% to 0.3%, Ni: 0.005% to 0.3%, and Sn: 0.005% to 0.3%

[0114] Cu, Ni, and Sn are elements that contribute to increased strength by solute strengthening. If necessary, one or two or more of Cu, Ni, and Sn may be contained. It is desirable to contain Cu: 0.005% or more, Ni: 0.005% or more, and/or Sn: 0.005% or more to produce the effect. However, a Cu content of more than 0.3%, a Ni content of more than 0.3%, and/or a Sn content of more than 0.3% results in poor hot workability and may result in surface layer cracking during hot rolling. Thus, if Cu, Ni, and/or Sn are contained, each of the Cu content, the Ni content, and the Sn content is preferably limited to the range of 0.005% to 0.3%, more preferably 0.005% to 0.2%.

At Least One Selected from Mo: 0.002% to 0.3% and Cr: 0.002% to 0.3%

[0115] Mo and Cr are elements that tend to form carbide (precipitates) and contribute to improved punchability in mass production by the formation of the precipitates. Mo and Cr are also elements that contribute to improved hardenability. Mo and Cr are also elements that contribute to finer bainite lath by decreasing the bainite transformation temperature. One or both of Mo and Cr may be contained, if necessary. It is desirable to contain Mo: 0.002% or more and/or Cr: 0.002% or more to produce these effects. However, an excessive Mo content of more than 0.3% and/or an excessive Cr content of more than 0.3% results in increased production costs and economic disadvantages. Thus, if Mo and/or Cr is contained, each of the Mo content and the Cr content is preferably limited to the range of 0.002% to 0.3%, more preferably 0.002% to 0.2%.

At Least One Selected from Ca: 0.0002% to 0.004% and REM: 0.0002% to 0.004%

[0116] Ca and REM are elements that effectively contribute to improved workability by morphology control of inclusions. If necessary, one or both of Ca and REM may be contained. It is desirable to contain Ca: 0.0002% or more and/or REM: 0.0002% or more to produce the effect. However, a Ca content of more than 0.004% and/or a REM content of more than 0.004% results in an increased amount of inclusions in steel and poor workability. Thus, if Ca and/or REM is contained, each of the Ca content and the REM content is preferably limited to the range of 0.0002% to 0.004%, more preferably 0.0002% to 0.003%.

[0117] The balance other than the components described above includes Fe and incidental impurities.

[0118] The reason for limiting the microstructure of a high-strength hot-rolled steel sheet according to the present invention will be described below.

[0119] A high-strength hot-rolled steel sheet according to the second embodiment has a microstructure in which a bainite phase constitutes more than 92% by volume, the average lath interval of bainite is 0.60 μm or less, and the ratio of Fe-based carbide precipitated in bainite lath grains to all Fe-based carbide is 10% or more by number.

[0120] In order to achieve the desired punchability in mass production, it is important that a bainite phase should constitute more than 92%, preferably more than 94%, by volume of the steel sheet structure, as described above. The remainder

other than the bainite phase includes one or more of a ferrite phase, a martensite phase, a retained austenite phase, and pearlite. The martensite phase and the retained austenite phase are harder and more brittle than the main phase bainite and impair punchability in mass production. Thus, the martensite phase and the retained austenite phase preferably constitute less than 1% by volume in total. Although retained austenite is not hard, retained austenite becomes martensite by strain-induced transformation during punching. Thus, like martensite, retained austenite adversely affects punchability. The bainite phase is a mixed microstructure of ferrite and Fe-based carbide. In such a microstructure composed mainly of the bainite phase alone, an interface between ferrite and Fe-based carbide acts as a starting point for the formation of micro voids during stamping. Thus, such a microstructure is advantageous to both appropriate formation of micro voids and subsequent void linking.

[0121] In the present invention, the intervals of bainite lath, which is the lower microstructure of the bainite phase, are 0.60 μm or less. This is based on the findings that the microstructure factor that controls punchability in mass production is not the size of the bainite phase but the lower microstructure bainite lath and that a decrease in lath intervals of bainite is important in improving punchability in mass production. When the lath intervals of bainite are more than 0.60 μm , the desired punchability in mass production cannot be achieved. Thus, the lath intervals of bainite are limited to 0.60 μm or less, preferably 0.50 μm or less, more preferably 0.45 μm or less.

[0122] A hot-rolled steel sheet according to the present invention has a microstructure that is composed mainly of the bainite phase alone. The bainite phase contains precipitated carbide (Fe-based carbide). The ratio of Fe-based carbide precipitated in bainite lath grains to all precipitated Fe-based carbide is 10% or more by number. Control of carbide (Fe-based carbide) precipitation sites is important in improving punchability in mass production. When the ratio of Fe-based carbide precipitated in bainite lath grains to all precipitated Fe-based carbide is less than 10% by number, the desired good punchability in mass production cannot be achieved. Thus, the ratio of Fe-based carbide precipitated in bainite lath grains to all precipitated Fe-based carbide is limited to 10% or more, preferably 15% or more, more preferably 20% or more, by number.

[0123] A preferred method for producing a high-strength hot-rolled steel sheet according to the present invention will be described below.

[0124] In the present invention, a steel slab having the composition described above is heated and is subjected to hot rolling composed of rough rolling and finish rolling to form a hot-rolled steel sheet.

[0125] A method for producing a steel slab is not particularly limited. Molten steel having the composition described above is formed by a common melting method, for example, in a converter, an electric furnace, or an induction furnace, and, if necessary, is subjected to secondary refining in vacuum degassing equipment, and is formed into a steel slab having predetermined dimensions by a common casting method, such as by continuous casting. An ingot making and blooming method may also be used without problems. The steel slab may be a thin slab having a thickness of approximately 30 mm. In the case of a thin slab, rough rolling may be omitted.

[0126] In the present invention, an electro-magnetic stirrer (EMS) or intentional bulging soft reduction casting (IBSR) may be used to reduce segregation of steel components during continuous casting. Electro-magnetic stirrer treatment can form equiaxed crystals at half the thickness of a sheet and reduce segregation. Intentional bulging soft reduction casting can prevent the flow of molten steel in an unsolidified portion of a continuous cast slab and reduce segregation at half the thickness of a sheet. At least one of these segregation reduction treatments can be used to achieve good punchability characteristic of the present invention and improve elongation among the tensile properties described below.

[0127] A steel slab having the composition described above is heated to a heating temperature of 1100° C. or more and is subjected to hot rolling.

Steel Slab Heating Temperature: 1100° C. or More

[0128] In the present invention, precipitates in a slab must be redissolved. Thus, a steel slab is heated to a heating temperature of 1100° C. or more. A heating temperature of less than 1100° C. results in insufficient redissolution of precipitates, and a desired precipitate distribution cannot be achieved in a subsequent process. The heating temperature is preferably 1150° C. or more. An excessively high heating temperature of more than 1300° C. results in coarse crystal grains and consequently coarse bainite lath. Thus, it is desirable that the heating temperature of a steel slab be limited to 1300° C. or less.

[0129] A heated steel slab is subjected to hot rolling having rough rolling and finish rolling to form a hot-rolled steel sheet. The rough rolling may be performed under any conditions where a desired sheet bar size can be achieved.

[0130] The rough rolling is followed by finish rolling. The conditions for the finish rolling are very important for the formation of a desired bainite lath microstructure.

Total Rolling Reduction of Two Final Passes in Finish Rolling: 30% or More

[0131] Formation of a desired bainite lath microstructure requires bainite transformation of austenite (γ) having sufficiently accumulated strain. Thus, in the present invention, the total rolling reduction of two final passes in finish rolling is limited to 30% or more. When the total rolling reduction of two final passes in finish rolling is less than 30%, strain is insufficiently accumulated in γ , and a desired bainite lath microstructure cannot be formed after transformation. Thus, the total rolling reduction of two final passes in finish rolling is limited to 30% or more, preferably 40% or more, more preferably 50% or more.

Finish-Rolling Finishing Temperature: (A_{r3} Transformation Temperature) to (A_{r3} Transformation Temperature+120° C.)

[0132] Finish-rolling finishing temperature control is also important for bainite transformation of austenite (γ) having sufficiently accumulated strain. When the finish-rolling finishing temperature is less than the A_{r3} transformation temperature, it is difficult to form the desired microstructure, that is, the microstructure composed mainly of a bainite phase alone. When the finish-rolling finishing temperature is higher than (A_{r3} transformation temperature+120° C.), it is difficult to form a fine bainite phase. Thus, the finish-rolling finishing temperature is limited to (A_{r3} transformation temperature) to (A_{r3} transformation temperature+120° C.), preferably (A_{r3}

transformation temperature) to (A_{r3} transformation temperature+80° C.). The finish-rolling finishing temperature herein refers to a surface temperature. The term " A_{r3} transformation temperature", as used herein, refers to a transformation temperature determined from a changing point in a thermal expansion curve obtained by cooling at a cooling rate of 1° C./s after processing with a Formastor testing machine.

[0133] After the finish rolling, cooling is performed. The cooling conditions are also very important for the formation of a desired microstructure.

Cooling Start: Within 2 Seconds after Finish Rolling

[0134] In order to form a desired bainite lath microstructure by bainite transformation of γ having sufficiently accumulated strain, cooling must be started within 2 seconds after finish rolling. When cooling is started more than 2 seconds after finish rolling, recovery of γ and recrystallization occur, and the number of nuclei for bainite transformation decreases. Thus, desired lath intervals of bainite cannot be formed. Thus, cooling is started within 2 seconds, preferably 1.5 seconds, more preferably 1 second, after finish rolling.

Average Cooling Rate: 50° C./s or More

[0135] When the average cooling rate from the finish-rolling finishing temperature to the cooling stop temperature is less than 50° C./s, pro-eutectoid ferrite is precipitated, and it is difficult to form the microstructure in which a bainite phase constitutes more than 92% by volume and that has the desired lath intervals of bainite. Thus, the average cooling rate of cooling after finish rolling is limited to 50° C./s or more, preferably 60° C./s or more, more preferably 70° C./s or more. The upper limit of the cooling rate depends on the capacity of cooling facilities and is preferably limited to approximately 150° C./s in terms of the shape of steel sheets. In the present invention, control of the cooling rate after finish rolling as described above and single-stage cooling to the cooling stop temperature as described below are among the requirements for the formation of the microstructure characteristic of the present invention.

Cooling Stop Temperature: 300° C. To 500° C.

[0136] In the present invention, coiling is performed immediately after cooling stop. Thus, the coiling temperature is the same as the cooling stop temperature. When the cooling stop temperature (coiling temperature) is less than 300° C. or more than 500° C., the lath intervals of bainite and the Fe-based carbide distribution cannot be controlled within desired optimum ranges. Thus, the cooling stop temperature (coiling temperature) is limited to the range of 300° C. to 500° C., preferably 350° C. to 500° C., more preferably 400° C. to 500° C.

[0137] In the present invention, an electro-magnetic stirrer (EMS) or intentional bulging soft reduction casting (IBSR) may be used to reduce segregation of steel components during continuous casting. Electro-magnetic stirrer treatment can form equiaxed crystals at half the thickness of a sheet and reduce segregation. Intentional bulging soft reduction casting can prevent the flow of molten steel in an unsolidified portion of a continuous cast slab and reduce segregation at half the thickness of a sheet. At least one of these segregation reduction treatments can be used to achieve good punchability characteristic of the present invention and improve elongation among the tensile properties described below.

[0138] After coiling, scales on the surface may be removed by pickling according to routine procedures. After pickling treatment, a hot-rolled steel sheet may be subjected to temper rolling. After pickling treatment or temper rolling, a hot-rolled steel sheet may be subjected to annealing at a soaking temperature of 730° C. or less and plating treatment in a common hot-dip galvanizing line. The plating treatment may be a treatment for forming a galvanized layer on a surface in a hot-dip galvanizing bath. The galvanized layer may be subjected to alloying treatment to produce a galvanized steel sheet. When the soaking temperature for annealing treatment is more than 730° C., bainite is tempered, making it difficult to form the microstructure in which a bainite phase constitutes more than 92% by volume and that has the desired lath intervals of bainite. Thus, the soaking temperature for annealing treatment is 730° C. or less. Although the lower limit of the soaking temperature for annealing treatment is not particularly limited, the soaking temperature for annealing treatment is preferably 590° C. or more in terms of adhesion between a hot-dip galvanizing layer and a base steel sheet. After immersed in the hot-dip galvanizing bath, the galvanized layer may be subjected to alloying treatment to produce a galvanized steel sheet.

[0139] The resulting hot-rolled steel sheet may be used to produce a coated steel sheet, such as an electrogalvanized steel sheet, as well as a hot-dip galvanized steel sheet.

[0140] A high-strength hot-rolled steel sheet according to the present invention will be described below with examples.

Example 2

[0141] A steel slab having a composition listed in Table 4 was subjected to heating, finish rolling, and cooling after rolling listed in Table 5 to produce a hot-rolled steel sheet. Table 4 also lists the A_{c3} transformation temperature of each steel slab determined from a thermal expansion curve. In continuous casting, hot-rolled steel sheets other than a hot-rolled steel sheet No. 1' of steel A2 in Tables 4 to 6 described below were subjected to an electro-magnetic stirrer (EMS) to reduce segregation of components of the steel. After pickling, some of the hot-rolled steel sheets were passed through a continuous hot-dip galvanizing line and were subjected to annealing treatment under the conditions listed in Table 5 and hot-dip galvanizing treatment to produce hot-dip galvanized steel sheets (GI). In the hot-dip galvanizing treatment, each of the hot-rolled steel sheets subjected to the annealing treatment was immersed in a galvanizing bath (0.1% Al—Zn) at 480° C., and 45 g/m² of a hot-dip galvanized layer was formed on each side of the steel sheet. After the hot-dip galvanizing treatment, some of the hot-rolled steel sheets were subjected to alloying treatment to produce galvanized steel sheets (GA). The alloying treatment temperature was 520° C.

[0142] Test specimens were taken from the hot-rolled steel sheets (including coated steel sheets) and were subjected to microstructure observation, a tensile test, and a punchability-in-mass-production test. The test methods were as follows:

(1) Microstructure Observation

[0143] Test specimens for microstructure observation were taken from the hot-rolled steel sheets (coated steel sheets). A vertical cross section (L cross section) of each test specimen parallel to the rolling direction was polished and was etched with a 3% nital solution to expose a microstructure. The microstructure in the L cross section at a quarter thickness in

the depth direction was observed with a scanning electron microscope (magnification: 3000 times). Ten visual fields of the microstructure were photographed. Phases other than a bainite phase were separated by image analysis to determine the percentage of the phases other than bainite and calculate the area percentage of the bainite phase. The area percentage calculated in this manner was considered to be the volume percentage of the bainite phase.

[0144] Samples for a thin film were taken from the hot-rolled steel sheets (coated steel sheets) at a quarter thickness in the depth direction and were subjected to mechanical polishing and electropolishing to prepare thin film specimens. The microstructure of each thin film specimen was observed with a transmission electron microscope (magnification: approximately 30000). Ten visual fields of the microstructure were photographed. The lath intervals of bainite were measured in the microstructure photographs and were averaged to determine the lath intervals of bainite of each hot-rolled steel sheet.

[0145] Test specimens for microstructure observation were taken from the hot-rolled steel sheets (coated steel sheets). A vertical cross section (L cross section) of each test specimen parallel to the rolling direction was polished and was etched with a 3% nital solution to expose a microstructure. A replica sample at a quarter thickness in the depth direction was prepared. The microstructure of the replica sample was observed with a transmission electron microscope (magnification: approximately 30000 times). Ten visual fields of the microstructure were photographed. Fe-based carbide was counted in each precipitation site (at a grain boundary and within a grain) in the microstructure photographs, thereby calculating the ratio of the number of Fe precipitates in bainite lath to the number of all Fe precipitates. Fe-based carbide (precipitates) was identified by the shape of the precipitates and by EDX analysis.

[0146] It was confirmed that substantially the same microstructure was also observed in a central portion in the thickness direction.

(2) Tensile Test

[0147] Three JIS No. 5 tensile test pieces were taken from each of the hot-rolled steel sheets (coated steel sheets) such that the tensile direction was perpendicular to the rolling direction. The test pieces were subjected to a tensile test according to JIS Z 2241. The cross head speed was 10 mm/min. The averages of tensile properties (tensile strength TS and elongation EI) were considered to be the tensile properties of the steel sheets.

(3) Punchability-in-Mass-Production Test

[0148] A blank sheet (size: 150×150 mm) was taken from each of the hot-rolled steel sheets (coated steel sheets). A 50-mmφ punching punch of a flat-bottomed type was used. The hole diameter of a die was determined such that the punching clearance was 30%. A spacer was placed on the punching die. A blank sheet was placed on the spacer and was held with a blank holder. A hole was then punched in the blank sheet. After punching, the fracture surface condition of the punched surface was observed around the entire perimeter of the punched hole with a scanning electron microscope (magnification: 100 times) and was checked for cracking, chipping, a brittle fracture surface, a secondary shear surface, and cross section roughness. Punchability in mass production was

rated as follows: fracture surfaces free of cracking, chipping, a brittle fracture surface, a secondary shear surface, and cross section roughness were rated as good (circle); fracture sur-

faces having cross section roughness were rated as fair (triangle); and the other fracture surfaces were rated as poor (x). [0149] Table 6 shows the results.

TABLE 4

Steel No.	Chemical composition (mass %)										Transformation		Remarks
	C	Si	Mn	P	S	Al	N	Nb, Ti	Cu, Ni, Sn	Mo, Cr	Ca, REM	temperature A _{r3} (° C.)	
A2	0.059	0.15	1.71	0.047	0.0034	0.044	0.0034	0.095 Nb: 0.01	—	—	Ca: 0.0011	879	Suitable example
B2	0.071	0.76	1.93	0.023	0.0004	0.015	0.0042	0.088 B: 0.0012	—	—	REM: 0.0005	878	Suitable example
C2	0.076	1.39	1.95	0.007	0.0014	0.038	0.0021	0.059 Nb: 0.006	Sn: 0.05	—	—	893	Suitable example
D2	0.081	0.73	1.34	0.011	0.0005	0.033	0.0033	0.099 —	—	—	—	882	Suitable example
E2	0.092	0.61	1.48	0.013	0.0009	0.039	0.0027	0.104 —	—	—	—	870	Suitable example
F2	0.097	0.09	1.27	0.029	0.0027	0.024	0.0062	0.064 —	Ni: 0.18	Cr: 0.08, Mo: 0.04	—	863	Suitable example
G2	0.104	0.92	1.11	0.005	0.0004	0.066	0.0011	0.124 B: 0.0004	—	Cr: 0.03	—	886	Suitable example
H2	0.113	0.27	1.67	0.011	0.0009	0.042	0.0048	0.097 —	—	Mo: 0.08	—	841	Suitable example
I2	0.124	0.19	1.83	0.019	0.0011	0.033	0.0037	0.155 Nb: 0.013	—	—	—	835	Suitable example
J2	0.141	0.04	1.89	0.009	0.0038	0.041	0.0024	0.191 —	Cu: 0.03, Ni: 0.09	—	—	815	Suitable example
K2	0.061	1.15	1.99	0.012	0.0027	0.055	0.0039	0.081 —	Cu: 0.008, Ni: 0.015	—	—	890	Suitable example
L2	0.071	0.64	1.39	0.009	0.0005	0.029	0.0032	0.109 —	—	—	—	879	Suitable example
<u>M2</u>	0.073	0.08	<u>0.94</u>	0.013	0.0011	0.049	0.0048	0.077 —	—	—	—	869	Comparative example
<u>N2</u>	0.104	0.03	1.91	0.011	0.0028	0.058	0.0053	<u>0.044</u>	—	—	—	826	Comparative example
<u>O2</u>	<u>0.044</u>	0.56	1.26	0.022	0.0017	0.047	0.0046	0.058 V: 0.007, Nb: 0.009	—	—	—	898	Comparative example

TABLE 5

		Hot-rolling conditions				Cooling conditions		Coiling	Hot-dip galvanizing		
		Sheet		Finish-rolling	Total rolling	Cooling	Average	conditions	treatment		
Hot-rolled steel sheet No.	Steel No.	thick-ness mm	Heating temperature (° C.)	finishing temperature (° C.)	reduction of two final passes (%)	start time (s)	cooling rate* (° C./s)	Coiling temperature (° C.)	Annealing temperature (° C.)	Alloying treatment	Remarks
1	A2	2.9	1180	915	40	1.3	70	435	—	—	Example
1'	A2	2.9	1180	910	40	1.2	70	440	—	—	Example
2	B2	2.6	1250	950	30	0.9	80	475	—	—	Example
3	B2	2.0	1250	920	40	0.7	90	450	600	—	Example
<u>4</u>	B2	2.6	1250	920	40	1.4	80	490	<u>775</u>	—	Comparative example
<u>5</u>	B2	2.6	1250	910	45	<u>2.7</u>	55	395	—	—	Comparative example
6	C2	4.0	1200	900	40	1.4	65	440	—	—	Example
7	D2	2.6	1240	925	55	0.7	100	410	—	—	Example
<u>8</u>	D2	2.0	1240	<u>840</u>	40	1.4	125	430	—	—	Comparative example
<u>9</u>	D2	2.6	1240	880	<u>20</u>	1.7	95	495	—	—	Comparative example

TABLE 5-continued

		Hot-rolling conditions				Cooling conditions		Coiling	Hot-dip galvanizing		
		Sheet		Finish-rolling	Total rolling	Cooling	Average	conditions	treatment		
Hot-rolled steel sheet No.	Steel No.	thick-ness mm	Heating temperature (° C.)	finishing temperature (° C.)	reduction of two final passes (%)	start time (s)	cooling rate* (° C./s)	Coiling temperature (° C.)	Annealing temperature (° C.)	Alloying treatment	Remarks
10	E2	3.6	1260	905	60	0.5	95	425	690	Yes	Example
<u>11</u>	E2	3.6	1260	910	45	1.3	<u>25</u>	450	635	—	Comparative example
<u>12</u>	E2	2.6	1260	930	40	1.9	80	<u>280</u>	—	—	Comparative example
13	F2	3.6	1250	875	30	1.9	50	495	—	—	Example
14	G2	2.0	1200	940	40	1.3	145	410	—	—	Example
15	H2	4.0	1260	860	35	0.7	55	365	—	—	Example
16	I2	2.6	1280	920	35	1.6	125	345	—	—	Example
17	J2	2.0	1290	905	50	1.1	75	415	725	—	Example
<u>18</u>	K2	3.6	1260	895	<u>25</u>	1.7	85	460	—	—	Comparative example
<u>19</u>	L2	3.6	1275	900	<u>20</u>	<u>2.8</u>	105	430	—	—	Comparative example
<u>20</u>	<u>M2</u>	3.6	1250	900	40	1.5	55	495	—	—	Comparative example
<u>21</u>	<u>N2</u>	3.6	1280	885	55	1.7	50	465	—	—	Comparative example
22	<u>O2</u>	3.6	1240	950	35	1.4	60	440	720	—	Comparative example

*Average cooling rate from finish-rolling finishing temperature to coiling temperature

TABLE 6

		Structure**			Tensile properties		Punchability in		
Hot-rolled steel sheet No.	Steel No.	Bainite fraction (vol %)	Lath interval of bainite (μm)	Ratio of Fe- based carbide in grains* (%)	Tensile strength TS (MPa)	Elongation El (%)	mass production Evaluation of punched surface	Remarks	
1	A2	93	0.49	11.1	710	26	○	Example	
1'	A2	91	0.50	11.4	712	24	Δ	Example	
2	B2	93	0.43	15.9	733	25	○	Example	
3	B2	93	0.40	12.3	741	24	○	Example	
4	B2	72	1.41	11.4	750	15	x	Comparative example	
5	B2	93	1.03	9.0	744	14	x	Comparative example	
6	C2	94	0.45	15.0	758	26	○	Example	
7	D2	97	0.39	15.5	808	24	○	Example	
8	D2	63	0.80	7.3	798	14	x	Comparative example	
9	D2	82	1.08	6.1	795	13	x	Comparative example	
10	E2	98	0.34	15.3	813	26	○	Example	
11	E2	68	0.70	12.8	809	14	x	Comparative example	
12	E2	81	0.41	3.1	801	13	x	Comparative example	
13	F2	93	0.58	20.5	797	21	○	Example	
14	G2	93	0.36	16.7	826	20	○	Example	
15	H2	96	0.33	15.2	853	20	○	Example	
16	I2	97	0.29	10.2	889	19	○	Example	
17	J2	93	0.44	15.1	894	19	○	Example	
18	K2	82	0.78	8.5	768	15	x	Comparative example	
19	L2	90	0.69	9.1	771	14	x	Comparative example	
20	M2	66	0.93	4.4	678	13	x	Comparative example	
21	N2	78	0.88	5.8	689	12	x	Comparative example	
22	O2	63	1.27	3.9	671	11	x	Comparative example	

*Number ratio of Fe-based carbide in grains to all Fe-based carbide

**Measurement at quarter thickness

[0150] The hot-rolled steel sheets (coated steel sheets) according to the examples had a high tensile strength TS of 700 MPa or more and good punchability in mass production. In contrast, the comparative examples outside the scope of the present invention had poor punchability in mass production.

1. A high-strength hot-rolled steel sheet having a composition and a microstructure, the composition containing, on a mass percent basis,

C: more than 0.07% and 0.2% or less, Si: 2.0% or less, Mn: 1.0% to 3.0%, P: 0.05% or less, S: 0.005% or less, Al: 0.1% or less, N: 0.01% or less, Ti: 0.05% to 0.3%, V: 0.05% to 0.3%, and

the balance being Fe and incidental impurities,

the microstructure comprising a bainite of more than 90% by volume, the bainite having an average lath interval of 0.45 μm or less, and Fe-based carbide precipitated in bainite lath grains having a ratio of 10% or more by number to all Fe-based carbide.

2. The high-strength hot-rolled steel sheet according to claim 1, wherein the composition further contains at least one selected from Nb: 0.005% to 0.2% and B: 0.0002% to 0.0030% on a mass percent basis.

3. The high-strength hot-rolled steel sheet according to claim 1, wherein the composition further contains at least one selected from Cu: 0.005% to 0.3%, Ni: 0.005% to 0.3%, and Sn: 0.005% to 0.3% on a mass percent basis.

4. The high-strength hot-rolled steel sheet according to claim 1, wherein the composition further contains at least one selected from Mo: 0.002% to 0.3% and Cr: 0.002% to 0.3% on a mass percent basis.

5. The high-strength hot-rolled steel sheet according to claim 1, wherein the composition further contains at least one selected from Ca: 0.0002% to 0.004% and REM: 0.0002% to 0.004% on a mass percent basis.

6. A hot-dip galvanized steel sheet, having a hot-dip galvanizing layer or alloyed hot-dip galvanizing layer on a surface of the high-strength hot-rolled steel sheet according to claim 1.

7. A method for producing a high-strength hot-rolled steel sheet, comprising:

heating a steel slab and subjecting the steel slab to hot rolling having rough rolling and finish rolling to form a hot-rolled steel sheet,

wherein the steel slab has a composition containing, on a mass percent basis,

C: more than 0.07% and 0.2% or less, Si: 2.0% or less, Mn: 1.0% to 3.0%, P: 0.05% or less, S: 0.005% or less, Al: 0.1% or less, N: 0.01% or less, Ti: 0.05% to 0.3%, V: 0.05% to 0.3%, and

the balance being Fe and incidental impurities,

wherein the hot rolling includes heating the steel slab to 1100° C. or more, a total rolling reduction of two final passes in the finish rolling being 30% or more, a finish-rolling finishing temperature being in a range of (A_{r3} transformation temperature) to (A_{r3} transformation temperature+120° C.), starting cooling within 2 seconds after the finish rolling, cooling the hot-rolled steel sheet to a coiling temperature at an average cooling rate of 40° C./s or more, and coiling the hot-rolled steel sheet at a coiling temperature: 300° C. to 500° C.

8. The method for producing a high-strength hot-rolled steel sheet according to claim 7, wherein the composition

further contains at least one selected from Nb: 0.005% to 0.2% and B: 0.0002% to 0.0030% on a mass percent basis.

9. The method for producing a high-strength hot-rolled steel sheet according to claim 7, wherein the composition further contains at least one selected from Cu: 0.005% to 0.3%, Ni: 0.005% to 0.3%, and Sn: 0.005% to 0.3% on a mass percent basis.

10. The method for producing a high-strength hot-rolled steel sheet according to claim 7, wherein the composition further contains at least one selected from Mo: 0.002% to 0.3% and Cr: 0.002% to 0.3% on a mass percent basis.

11. The method for producing a high-strength hot-rolled steel sheet according to claim 7, wherein the composition further contains at least one selected from Ca: 0.0002% to 0.004% and REM: 0.0002% to 0.004% on a mass percent basis.

12. A method for producing a hot-dip galvanized steel sheet, comprising:

pickling a high-strength hot-rolled steel sheet produced by the method for producing a high-strength hot-rolled steel sheet according to claim 7, and subjecting the high-strength hot-rolled steel sheet to annealing and plating treatment to form a coated steel sheet,

wherein the annealing is performed at a soaking temperature of 730° C. or less, and the plating treatment after the annealing includes passing the high-strength hot-rolled steel sheet through a hot-dip galvanizing bath to form a hot-dip galvanizing layer on a surface of the high-strength hot-rolled steel sheet and optionally subjecting the high-strength hot-rolled steel sheet to alloying treatment for alloying the hot-dip galvanizing layer.

13. A high-strength hot-rolled steel sheet having a composition containing, on a mass percent basis,

C: 0.05% to 0.15%, Si: 1.5% or less, Mn: 1.0% to 2.0%, P: 0.05% or less, S: 0.005% or less, Al: 0.1% or less, N: 0.01% or less, Ti: 0.05% to 0.2%, and

the balance being Fe and incidental impurities,

wherein the high-strength hot-rolled steel sheet has a microstructure comprising a bainite of more than 92% by volume, the bainite having an average lath interval of 0.60 μm or less, and Fe-based carbide precipitated in bainite lath grains having a ratio of 10% or more by number to all Fe-based carbide.

14. The high-strength hot-rolled steel sheet according to claim 13, wherein the composition further contains at least one selected from Nb: 0.005% to 0.2% and B: 0.0002% to 0.0030% on a mass percent basis.

15. The high-strength hot-rolled steel sheet according to claim 13, wherein the composition further contains at least one selected from Cu: 0.005% to 0.3%, Ni: 0.005% to 0.3%, and Sn: 0.005% to 0.3% on a mass percent basis.

16. The high-strength hot-rolled steel sheet according to claim 13, wherein the composition further contains at least one selected from Mo: 0.002% to 0.3% and Cr: 0.002% to 0.3% on a mass percent basis.

17. The high-strength hot-rolled steel sheet according to claim 13, wherein the composition further contains at least one selected from Ca: 0.0002% to 0.004% and REM: 0.0002% to 0.004% on a mass percent basis.

18. A hot-dip galvanized steel sheet, having a hot-dip galvanizing layer or alloyed hot-dip galvanizing layer on a surface of the high-strength hot-rolled steel sheet according to claim 13.

19. A method for producing a high-strength hot-rolled steel sheet, comprising:

heating a steel slab and subjecting the steel slab to hot rolling having rough rolling and finish rolling to form a hot-rolled steel sheet,

wherein the steel slab contains, on a mass percent basis,

C: 0.05% to 0.15%, Si: 1.5% or less,

Mn: 1.0% to 2.0%, P: 0.05% or less,

S: 0.005% or less, Al: 0.1% or less,

N: 0.01% or less, Ti: 0.05% to 0.2%, and

the balance being Fe and incidental impurities,

wherein the hot rolling includes heating the steel slab to 1100° C. or more, a total rolling reduction of two final passes in the finish rolling being 30% or more, a finish-rolling finishing temperature being in a range of (Ar3 transformation temperature) to (Ar3 transformation temperature+120° C.), starting cooling within 2 seconds after the finish rolling, cooling the hot-rolled steel sheet to a coiling temperature at an average cooling rate of 50° C./s or more, and coiling the hot-rolled steel sheet at a coiling temperature: 300° C. to 500° C.

20. The method for producing a high-strength hot-rolled steel sheet according to claim **19**, wherein the composition further contains at least one from Nb: 0.005% to 0.2% and B: 0.0002% to 0.0030% on a mass percent basis.

21. The method for producing a high-strength hot-rolled steel sheet according to claim **19**, wherein the composition

further contains at least one selected from Cu: 0.005% to 0.3%, Ni: 0.005% to 0.3%, and Sn: 0.005% to 0.3% on a mass percent basis.

22. The method for producing a high-strength hot-rolled steel sheet according to claim **19**, wherein the composition further contains at least one selected from Mo: 0.002% to 0.3% and Cr: 0.002% to 0.3% on a mass percent basis.

23. The method for producing a high-strength hot-rolled steel sheet according to claim **19**, wherein the composition further contains at least one selected from Ca: 0.0002% to 0.004% and REM: 0.0002% to 0.004% on a mass percent basis.

24. A method for producing a hot-dip galvanized steel sheet, comprising:

pickling a high-strength hot-rolled steel sheet produced by the method for producing a high-strength hot-rolled steel sheet according to claim **19**, and subjecting the high-strength hot-rolled steel sheet to annealing and plating treatment to form a coated steel sheet having a coated layer on a surface thereof;

wherein the annealing is performed at a soaking temperature of 730° C. or less, and the plating treatment after the annealing includes passing the high-strength hot-rolled steel sheet through a hot-dip galvanizing bath to form a hot-dip galvanizing layer on a surface of the hot-rolled steel sheet and optionally subjecting the high-strength hot-rolled steel sheet to alloying treatment for alloying the hot-dip galvanizing layer.

* * * * *