



- (51) International Patent Classification:
B01J 27/32 (2006.01)
- (21) International Application Number:
PCT/US2014/012166
- (22) International Filing Date:
20 January 2014 (20.01.2014)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
61/757,768 29 January 2013 (29.01.2013) US
- (71) Applicant: **ARKEMA INC.** [US/US]; 900 First Avenue,
King of Prussia, Pennsylvania 19406 (US).
- (72) Inventors: **SYVRET, Robert G.**; 1156 Clearwood Drive,
Allentown, Pennsylvania 18103 (US). **JANNEY, Patrick K.**; 609 Haverford Road, Ridley Park, Pennsylvania 19078
(US). **SESHADRI, Sri R.**; 46 Paddock Way, Holland,
Pennsylvania 18966 (US).
- (74) Agents: **BOYD, Steven D.** et al.; ARKEMA INC., 900
First Avenue, King of Prussia, Pennsylvania 19406 (US).

(81) Designated States (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) Title: ACTIVATION AND REGENERATION OF FLUORINATION CATALYSTS

(57) Abstract: A fluorination catalyst such as a chromium oxide-based fluorination catalyst may be activated or reactivated by contacting the catalyst with a source of reactive fluorine, for example nitrogen trifluoride (NF₃) or fluorine (F₂). Fluorinated compounds may be prepared by the gas phase reaction of hydrogen fluoride (HF) with various substrates such as chlorinated compounds. A number of metal oxide-based catalysts have been developed for this purpose.



ACTIVATION AND REGENERATION OF FLUORINATION CATALYSTS

FIELD OF THE INVENTION

The invention relates to methods for activating and regenerating catalysts used to
5 fluorinate substrates such as chlorinated compounds using hydrogen fluoride.

BACKGROUND OF THE INVENTION

Fluorinated compounds may be prepared by the gas phase reaction of hydrogen
fluoride (HF) with various substrates such as chlorinated compounds. A number of metal
10 oxide-based catalysts have been developed for this purpose. However, such catalysts
typically lose activity with prolonged use. Additionally, inactive catalyst precursors often
must be activated in order to prepare such fluorination catalysts.

Various methods for activating and reactivating metal oxide-based fluorination
catalysts, as well as methods for extending the useful life of such catalysts, have been
15 investigated. However, these methods are known to possess certain disadvantages. For
example, oxygen (O₂) may be co-fed continuously or intermittently during the fluorination
reaction or during reactivation for the purpose of oxidizing and removing carbonaceous
deposits, which tend to inhibit catalyst activity, from the catalyst surface. However, water
and carbon dioxide typically are produced as by-products. The water generated may itself
20 damage and deactivate the catalyst due to phase changes triggered by the repeated addition
and loss of water from the catalyst. The presence of water in the reactor system may also
lead to corrosion or erosion of fluorination equipment.

Accordingly, the development of improved, effective procedures for both activating
and reactivating catalysts for use in fluorination reactions which avoid the generation of
25 water would be of interest.

SUMMARY OF THE INVENTION

One aspect of the invention provides a method of reactivating a spent or depleted
fluorination catalyst (in particular, a metal oxide-based fluorination catalyst such as a
30 chromium oxide-based fluorination catalyst), comprising contacting the spent or depleted
fluorination catalyst with an agent that is a source of reactive fluorine such as NF₃ or F₂. The
fluorination catalyst may have been used to catalyze the fluorination of a chlorinated

compound such as a chloroolefin or chloroalkane using HF. The contacting may be carried out in a gas (vapor) phase at a temperature of about 100°C to about 400°C, for example.

Another aspect of the invention furnishes a fluorination process, alternately comprising reaction stages and regeneration stages, wherein the reaction stages comprise reacting a compound with HF in a gas phase in the presence of a fluorination catalyst to produce a fluorinated compound and the regeneration stages comprise contacting the fluorination catalyst with an agent that is a source of reactive fluorine such as NF₃ or F₂. Such a process may additionally comprise a preliminary activation stage which comprises contacting a fluorination catalyst precursor with an agent that is a source of reactive fluorinesuch as NF₃ or F₂.

A method of activating a fluorination catalyst is additionally supplied by the invention, comprising contacting a fluorination catalyst precursor with an agent that is a source of reactive fluorine such as NF₃ or F₂. The contacting may, for example, be carried in a gas phase at a temperature of about 100°C to about 400°C.

The activation and reactivation processes of the present invention may be carried out *in situ* (i.e., the catalyst may be activated or reactivated while in place in the equipment used for fluorination of a substrate) or *ex situ* (i.e., the catalyst may be activated or reactivated in accordance with the invention in equipment other than the fluorination equipment and subsequently transferred to the fluorination equipment).

DETAILED DESCRIPTION OF THE INVENTION

Activation/Reactivation Agents

The present invention utilizes a source of reactive fluorine such as nitrogen trifluoride (NF₃) or fluorine (F₂) or mixtures thereof as an agent for activating and/or reactivating fluorination catalysts. Such agents are fluorine-containing substances other than HF which are capable of supplying fluorine in a form which reacts with the catalyst so as to increase or restore its catalytic activity. Other useful agents for such purposes may include, for example, interhalogens (e.g., ClF, ClF₃, ClF₅, BrF₃, BrF₅, IF₅, and IF₇); hypofluorites (e.g., CF₃OF); fluorinated peroxides such as CF₃OO CF₃, as well as other fluoride and oxide fluoride compounds such as OF₂, O₂F₂, N₂F₂, N₂F₄, SF₄, SOF₄, SOF₂, XeF₂, XeF₄, XeF₆, KrF₂, FNO, FNO₂, and FClO₃.

The catalyst activation/reactivation agent may be admixed with one or more other substances as it is contacted with the catalyst precursor or deactivated catalyst. For example, the agent(s) which serve as a source of reactive fluorine may be present in combination with one or more of HF, HCl, chlorocarbons, fluorocarbons, O₂, N₂, CO, CO₂ and the like. Particular examples of such admixtures include, but are not limited to: HF + NF₃; HF + HCl + NF₃; HF + chlorocarbons + NF₃; and O₂ + NF₃. Such admixtures may be obtained as a result of recycling the stream containing the activation/reactivation agent after the agent is passed over or through the catalyst.

Fluorination reaction

In the fluorination reaction of the invention, a substrate such as a chlorinated compound is converted to a fluorinated compound through a reaction with hydrogen fluoride (HF) in the presence of a metal oxide-based catalyst. Where the substrate is a halogenated compound such as a chlorinated compound, the substrate may undergo a halogen exchange reaction catalyzed by the metal oxide-based catalyst (e.g., F is substituted for Cl). The "chlorinated compound" can be any molecule having at least one chlorine atom, and the "fluorinated compound" can be any molecule having at least one fluorine atom. The fluorination reaction may involve a reaction other than a halogen exchange reaction. For example, a fluorine atom may be substituted (exchanged) for a hydrogen atom on the substrate.

In one embodiment of the invention, the chlorinated compound is a C1 to C8 alkane or alkene compound, which may be linear or branched, having one or more substituents selected from F, Cl, I and Br, with at least one of the substituents being Cl. Mixtures of such chlorinated compounds may also be used. The fluorinated compound may be a C1 to C8 alkane or alkene compound, which may be linear or branched, having one or more substituents selected from F, Cl, I and Br, at least one of the substituents being F. Mixtures of such fluorinated compounds may be produced.

In one particular embodiment, the chlorinated compound is a C3 alkane or alkene compound having one or more substituents selected from F, Cl, I and Br, at least one of the substituents being Cl; and the fluorinated compound is a C3 alkene compound having one or more substituents selected from F, Cl, I and Br, at least one of the substituents being F. Alternatively, the chlorinated compound can be a C4 alkane or alkene compound having one or more substituents selected from F, Cl, I and Br, at least one of the substituents being Cl;

and the fluorinated compound is a C4 alkene compound having one or more substituents selected from F, Cl, I and Br, at least one of the substituents being F. According to one embodiment, the fluorinated compound is a hydrofluorolefin (and thus has no chlorine substituent). Typically, during the reaction at least one Cl substituent in the chlorinated compound is replaced by an F substituent.

The conversion of the chlorinated compound to the fluorinated compound may comprise direct conversion (i.e. in a single reaction step or under essentially one set of reaction conditions) or indirect conversion (i.e., through two or more reaction steps or using more than one single set of reaction conditions).

Illustrative fluorination reactions in accordance with the invention include the following:

2-chloro-3,3,3-trifluoro-1-propene (HFCO-1233xf) to 2,3,3,3-tetrafluoro-1-propene (HFO-1234yf);

1,1,1,2,3-pentachloropropane (HCC-240db) to 2,3,3,3-tetrafluoro-1-propene (HFO-1234yf);

1,1,2,2,3- pentachloropropane (HCC-240aa) to 2,3,3,3-tetrafluoro-1-propene (HFO-1234yf);

2,3-dichloro-1,1,1-trifluoropropane (HCFC-243db) to 2,3,3,3- tetrafluoro-1-propene (HFO-1234yf);

1,1,2,3 tetrachloro-1-propene (HCO-1230xa) to 2,3,3,3-tetrafluoro-1-propene (HFO-1234yf);

2,3,3,3 tetrachloro-1-propene (HCO-1230xf) to 2,3,3,3-tetrafluoro-1-propene (HFO-1234yf);

1,1,1,2,3-pentachloropropane (HCC-240db) to 2-chloro-3,3,3-trifluoro-1-propene (HFCO-1233xf);

1,1,2,2,3-pentachloropropane (HCC-240aa) to 2-chloro-3,3,3-trifluoro-1-propene (HFCO-1233xf);

2,3-dichloro-1,1,1 -trifluoropropane (HCFC-243db) to 2-chloro-3,3,3-trifluoro-1 -propene (HFCO-1233xf);

1,1,2,3 tetrachloro-1-propene (HCO-1230xa) to 2-chloro-3,3,3- trifluoro-1-propene (HFCO-1233xf);

2,3,3,3 tetrachloro-1-propene (HCO-1230xf) to 2-chloro-3,3,3- trifluoro-1-propene (HFCO-1233xf).

The fluorination reaction can be carried out with an HF molar ratio of HF to compound to be fluorinated typically from 3:1 to 150:1 , at a contact time from 6 to 100 s and a pressure from atmospheric pressure to 20 bars. The catalyst bed temperature can be, for example, from 100 to 450 °C.

Catalyst

The fluorination catalyst used in the present invention can be supported or unsupported. It can be, for example, a catalyst based on a metal including a transition metal oxide or a derivative thereof. In one embodiment, the catalyst is a chromium oxide-based catalyst. Suitable catalysts include, but are not limited to, metal oxide-based bulk and supported catalysts, including doped and undoped catalysts. A catalyst precursor to be activated in accordance with one aspect of the invention may be any metal oxide (e.g., corresponding to the general empirical formula M_xO_y , wherein x is 1-2 and y is selected such that the valency of M is satisfied). The metal M may be, for example, a first or second row transition metal. Once activated, the catalyst may be a metal oxide fluoride corresponding to the general empirical formula $M_xO_yF_z$, wherein x is 1-2 and y and z are selected such that the valency of M is satisfied. When M is chromium (Cr), the valency of M is typically 3-6.

The metal in the catalyst is converted to metal derivatives during activation (or regeneration), including oxides, halides or oxide halides. The metals in the catalyst are typically present in the form of metal oxides, oxychlorides, chlorides, chlorofluorides, oxychlorofluorides, oxyfluorides or fluorides. Thus, when the fluorination catalyst is a chromium oxide-based catalyst, the catalyst typically contains an oxide, oxide halide (for example, an oxyfluoride) and/or halide of chromium (for example, a fluoride of chromium).

A particularly suitable catalyst for use in the present invention is a high surface area unsupported chromium oxide-based catalyst. However, supported chromium oxide-based catalysts are also suitable for use.

The catalyst can optionally contain a low level of one or more co-catalysts (sometimes referred to as dopants) such as Co, Zn, Mn, Mg, V, Mo, Te, Nb, Sb, Ta, P, Ni, Ca, Sr, Ba, Na, K, Rb, Cs, Cd, Hg, Cu, Ag, Au, Pd, Pt, W, Ti, Zr, and/or Hf.

In one embodiment of the invention, the fluorination catalyst is an unsupported chromium catalyst which can optionally contain low levels of one or more co-catalysts

selected from cobalt, nickel, zinc or manganese, prepared by processes known in the art, such as impregnation, mixed powder, co-precipitation and the like.

The amount of co-catalyst, when present, can be varied between 1 to 10 wt%, e.g., between 1 to 5 wt%. The co-catalyst can be added to the catalyst by processes known in the art such as adsorption from an aqueous or organic solution, followed by solvent evaporation.

The catalyst precursor, before activation, may be subjected to a drying step, such as a step which comprises passing a drying gas, such as nitrogen, over the catalyst precursor. The drying step can be carried out at a pressure of from atmospheric pressure up to 20 bars, for example. The temperature of the catalyst precursor during the drying step can range from room temperature up to 400 °C, e.g., from about 175 °C to about 275 °C with a volumetric flow rate of the activating agent corresponding to a contact time in the catalyst bed of from about 1 to 100 s, e.g., from about 10 to 40 s, for an activation duration of from about 0.5 to 50 hours, e.g., between 1 to 5 hours. After the drying step, the catalyst precursor needs to be activated (i.e., converted to a substance having high catalytic activity for the fluorination of a substrate such as a chlorinated compound using HF).

Activation of the catalyst

The present inventors have found that the activation of the above catalysts using an agent that is a source of reactive fluorine such as NF_3 and/or F_2 makes it possible to significantly improve the efficiency of the fluorination process. The activation process may comprise activating the catalyst precursor using at least one activating agent. The temperature of this activation step can range from about 100 to about 500 °C, e.g., from about 300 to about 400 °C, with a volumetric flow rate of the activating agent corresponding to a contact time in the catalyst bed of from about 1 to about 200 s, for an activation duration of from about 10 to about 300 hours.

The above activation processes can be carried out at a pressure of from atmospheric pressure up to about 20 bars. The activating agent can be fed to the system with an inert gas such as nitrogen. The proportion of activating agent can range from about 1 to 100 mole% of the mixture. In one embodiment, NF_3 is employed as the activating agent and is contacted with the catalyst precursor in pure or essentially pure form (i.e., NF_3 comprises from 90 to 100 mole% of the gas contacted with the catalyst precursor).

Regeneration (reactivation) of the catalyst

The present inventors have also found that the efficiency of the fluorination reaction tends to decrease over time, but that it can be increased again up to, and even above, the initial efficiency, by subjecting the catalyst to regeneration stages wherein it is contacted with an agent that is a source of reactive fluorine such as NF_3 or F_2 , in a similar way as during the initial activation stage. The temperature during the regeneration step can range from about 100 to about 500 °C, with a contact time of from about 1 to about 200 s, for about 1 to about 200 hours. The regeneration step can be carried out at a pressure from atmospheric pressure to about 20 bars. The reactivating agent can be fed to the system with an inert gas such as nitrogen. The proportion of reactivating agent can range from about 1 to about 100 mole% of the mixture. In one embodiment, NF_3 is employed as the reactivating agent and is contacted with the spent catalyst in pure or essentially pure form (i.e., NF_3 comprises from 90 to 100 mole% of the gas contacted with the spent catalyst).

When reaction stages alternate with regeneration stages, the duration of each reaction stage can be from 50 to 2000 hours, e.g., from 200 to 1000 hours, and the duration of each regeneration stage can be from 1 to 200 hours, e.g., from 2 to 20 hours.

EXAMPLES**Example 1: Activation with Pure NF_3**

Pellets of chromium oxide (Cr_2O_3) doped with Zn were crushed and sieved to uniform particle size of 8 to 20 mesh. A 1" o.d. tubular reactor was loaded with a bed containing 46 cc (40.65 g = 268 mmol) of the sized catalyst precursor. The bed was heated to 225 °C and flushed with dry N_2 for 2.5 hours to facilitate removal of volatiles. The bed was then heated to 350 °C and pure NF_3 was flowed through the bed at approximately 5 sccm for 24 hours.

After the specified time, NF_3 flow was terminated and replaced by 100 sccm dry N_2 . Nitrogen was flowed for approximately 72 hours. After the specified time, N_2 was replaced by a reactant mixture consisting of HF, air, and 3,3,3-trifluoro-2-chloropropene, ($\text{CF}_3\text{C}(\text{Cl})=\text{CH}_2$, hereafter called 1233xf), flowing at ambient pressure with a contact time of 20 seconds through the catalyst bed heated to 350 °C. The mixture contained reactants in the molar ratio $\text{HF}:\text{1233xf}:\text{O}_2 = 20:1:0.2$.

The product exiting the reactor was passed through a caustic scrubber and analyzed subsequently online by gas chromatography (GC). Initial conversion of 1233xf was

approximately 56% with steady-state selectivity of 73% 2,3,3,3-tetrafluoropropene (hereafter called 1234yf) and 23% 1,1,1,3,3-pentafluoropropane (hereafter called 245cb). The reactant mixture was flowed continuously for approximately 100 hours after which the reactant mixture was replaced by N₂ for a period of 10 days. Following the 10 day purge with N₂, the reactant mixture was resumed as before and continued for an additional 250 hours. During these 250 hours the conversion declined slowly from approximately 50% to a steady-state value of 23%. Selectivity remained at 73% 1234yf and 23% 245cb. After this 250 hour reaction period the catalyst was deemed “deactivated” as it was at its lowest 1233xf conversion rate. The catalyst bed was held at 350 °C and purged with N₂ for 4 days before being used in Example 2.

Example 2: Reactivation of Deactivated Catalyst with Pure NF₃

The deactivated catalyst remaining at the end of Example 1 was reactivated with pure NF₃ as follows. Pure NF₃ was flowed at approximately 5 sccm through the depleted bed for 22 hours at 350 °C. During the reactivation with NF₃ an exotherm was observed in the bed during the initial few hours. In addition, volatile products of the reactivation process were observed by online GC analysis only during the first 293 minutes of activation, after which just NF₃ was observed flowing from the bed.

Following the 22 hour reactivation period, the pure NF₃ flow was replaced by a reactant mixture similar to that described in Example 1 (HF:1233xf:O₂ = 20:1:0.2), flowing at ambient pressure with a contact time of 20 seconds through the catalyst bed heated to 350 °C.

The product exiting the reactor was passed through a caustic scrubber and analyzed online by gas chromatography (GC). Initial conversion of 1233xf was approximately 60% with steady-state selectivity of 70% 1234yf and 28% 245cb. The reactant mixture was flowed continuously for approximately 100 hours after which the reactant mixture was replaced by N₂ for a period of 3 days.

Example 3: Activation Using NF₃ Followed by Air

Pellets of chromium oxide (Cr₂O₃) doped with Zn were crushed and sieved to uniform particle size of 8 to 20 mesh. A 1” o.d. tubular reactor was loaded with a bed containing 100 cc (94.9 g = 624 mmol) of the sized catalyst precursor. The bed was heated to 275 °C and flushed with pure N₂ for 72 hours to facilitate removal of volatiles. The flow of pure N₂ was

replaced with a mixture containing 5 sccm pure NF_3 and 100 sccm pure N_2 and this flow was continued for approximately 24 hours. The bed temperature was then raised to 350 °C and pure NF_3 was added at 5 sccm until approximately 642 mmol total NF_3 had been added. Following the addition of NF_3 , air was added at 25 sccm for a period of 4 days at 350 °C and at ambient pressure. After the specified time the flow of air was replaced by a reactant mixture similar to that described in Example 1 with the exception that 4% O_2 was used ($\text{HF}:1233\text{xf}:\text{O}_2 = 20:1:0.04$). The reactant mixture was flowed continuously at 1 bar absolute pressure with a contact time of 20 seconds through the catalyst bed heated to 350 °C.

The product exiting the reactor was passed through a caustic scrubber and analyzed subsequently online by gas chromatography (GC). Initial conversion of 1233xf was approximately 58% with steady-state selectivity during the first 90 hours of reaction of 73% 1234yf and 25% 245cb. The reactant mixture was flowed continuously for approximately 90 hours after which the reactant mixture was replaced by air for a period of 10 days. Following the 10 day reactivation with air, the reactant mixture was resumed as before and continued for an additional 260 hours. During the 260 hour reaction period the conversion declined slowly from approximately 65% to about 30% while the selectivities varied from 33% to 50% for 1234yf and from 62% to 47% for 245cb. Following the 260 hour reaction period the reactant mixture was replaced by air for a 3 day reactivation. Following reactivation, feeding of the reactant mixture was resumed as before and continued for an additional 400 hours. During the 400 hour reaction period the conversion declined slowly from approximately 65% to about 35% while the selectivities varied from 35% to 40% for 1234yf and from 62% to 57% for 245cb. Following the 400 hour reaction period the experiment was terminated.

Example 4: Attempted Activation Using Air and NF_3

Pellets of chromium oxide (Cr_2O_3) doped with Zn were crushed and sieved to uniform particle size of 8 to 20 mesh. A 1" o.d. tubular reactor was loaded with a bed containing 23 cc (20.74 g = 140 mmol) of the sized catalyst precursor. The bed was heated to 325 °C and flushed with pure air for 3 hours to facilitate removal of volatiles. The flow of pure air was replaced with a mixture containing 5 sccm pure NF_3 and 75 sccm pure air; however, an exotherm was observed so the flows were reduced to 0.5 sccm pure NF_3 and 7.5 sccm pure air. The bed pressure was increased from ambient to approximately 37 psig. The mixture of NF_3 and air was continued until approximately 500 mmol NF_3 had been added. After the

specified time, the flow of NF_3 and air was replaced by a reactant mixture similar to that described in Example 1 ($\text{HF}:\text{1233xf}:\text{O}_2 = 20:1:0.2$), flowing at 3.5 bar absolute pressure with a contact time of 20 seconds through the catalyst bed heated to 350 °C.

The product exiting the reactor was passed through a caustic scrubber and analyzed subsequently online by gas chromatography (GC); however, it was determined that little if any 1233xf was converted to products. At this point, the reactant mixture was replaced for a short period by NF_3 followed by air followed by a flow of air that was continued for 4 days. After the specified time, the air was replaced with the reactant mixture; however, the 1233xf conversion was < 10% and as such, the catalyst was deemed “not activated.”

Example 5: Activation Under Pressure Using NF_3 Followed by Air

Pellets of chromium oxide (Cr_2O_3) doped with Zn were crushed and sieved to uniform particle size of 8 to 20 mesh. A 1” o.d. tubular reactor was loaded with a bed containing 46 cc (40.11 g = 264 mmol) of the sized catalyst precursor. The bed was heated to 200 °C and flushed with pure N_2 to facilitate removal of volatiles. The flow of N_2 was replaced with a mixture at ambient pressure containing, initially, 5 sccm pure NF_3 and 20 sccm N_2 which was replaced ultimately with pure NF_3 flowing at 5 sccm and at 3.5 bar absolute pressure for the duration of the NF_3 addition. In total, about 10 mol% excess NF_3 was used. After the addition of NF_3 was terminated, pure air was flowed at 350 °C and 3.5 bar absolute pressure for a period of 6 days. After the specified time the flow of air was replaced by a reactant mixture similar to that described in Example 1 ($\text{HF}:\text{1233xf}:\text{O}_2 = 20:1:0.2$), flowing at 3.5 bar absolute pressure with a contact time of 20 seconds through the catalyst bed heated to 350 °C.

The product exiting the reactor was passed through a caustic scrubber and analyzed subsequently online by gas chromatography (GC). Initial conversion of 1233xf was approximately 36% but declined steadily over the course of the first 70 hours to a final value <10%. The steady-state selectivities reached during the first 70 hours of reaction were 65% 1234yf and 25% 245cb. The reactant mixture was flowed continuously for approximately 70 hours after which the reactant mixture was replaced by air for a period of 3 days. Following the 3 day reactivation attempt with air, feeding of the reactant mixture was resumed as before; however, the conversion declined rapidly from about 30% to about 10% over a period

of about 50 hours and thus the catalyst was deemed not adequately activated and the experiment was terminated.

What is claimed is:

1. A method of reactivating a spent or depleted fluorination catalyst, comprising contacting the spent or depleted fluorination catalyst with an agent that is a source of reactive fluorine.
2. The method of claim 1, wherein the agent is selected from the group consisting of NF_3 , F_2 , interhalogens, hypofluorites, fluorinated peroxides, OF_2 , O_2F_2 , N_2F_2 , N_2F_4 , SF_4 , SOF_4 , SOF_2 , XeF_2 , XeF_4 , XeF_6 , KrF_2 , FNO , FNO_2 , FCIO_3 , and mixtures thereof.
3. The method of claim 1, wherein the agent is selected from the group consisting of NF_3 and F_2 .
4. The method of claim 1, wherein the fluorination catalyst is a bulk (unsupported) or supported metal oxide-based fluorination catalyst.
5. The method of claim 1, wherein the fluorination catalyst is a bulk (unsupported) or supported chromium oxide-based fluorination catalyst.
6. The method of claim 1, wherein the fluorination catalyst has been used to catalyze the fluorination of a chloroolefin or chloroalkane using HF .
7. The method of claim 1, wherein the contacting is carried in a gas phase at a temperature of about 100°C to about 500°C .
8. A fluorination process, alternately comprising reaction stages and regeneration stages, wherein the reaction stages comprise reacting a compound with HF in gas phase in the presence of a fluorination catalyst to produce a fluorinated compound and the regeneration stages comprise contacting the fluorination catalyst with an agent that is a source of reactive fluorine.
9. The method of claim 8, wherein the agent is selected from the group consisting of NF_3 , F_2 , interhalogens, hypofluorites, fluorinated peroxides, OF_2 , O_2F_2 , N_2F_2 , N_2F_4 , SF_4 , SOF_4 , SOF_2 , XeF_2 , XeF_4 , XeF_6 , KrF_2 , FNO , FNO_2 , FCIO_3 , and mixtures thereof.
10. The method of claim 8, wherein the agent is selected from the group consisting of NF_3 and F_2 .
11. The fluorination process of claim 8, wherein the fluorination catalyst is a bulk (unsupported) or supported metal oxide-based fluorination catalyst.

12. The fluorination process of claim 8, wherein the fluorination catalyst is a bulk (unsupported) or supported chromium oxide-based fluorination catalyst.
13. The fluorination process of claim 8, additionally comprising a preliminary activation stage which comprises contacting a fluorination catalyst precursor with an agent that is a source of reactive fluorine.
14. A method of activating a fluorination catalyst, comprising contacting a fluorination catalyst precursor with an agent that is a source of reactive fluorine.
15. The method of claim 14, wherein the agent is selected from the group consisting of NF_3 , F_2 , interhalogens, hypofluorites, fluorinated peroxides, OF_2 , O_2F_2 , N_2F_2 , N_2F_4 , SF_4 , SOF_4 , SOF_2 , XeF_2 , XeF_4 , XeF_6 , KrF_2 , FNO , FNO_2 , FCIO_3 , and mixtures thereof.
16. The method of claim 14, wherein the agent is selected from the group consisting of NF_3 and F_2 .
17. The method of claim 14, wherein the fluorination catalyst precursor is comprised of a bulk (unsupported) or supported metal oxide.
18. The method of claim 14, wherein the fluorination catalyst precursor is comprised of bulk (unsupported) or supported chromium oxide.
19. The method of claim 14, wherein the contacting is carried in a gas phase at a temperature of about 100°C to about 500°C .

INTERNATIONAL SEARCH REPORT

147012100 28-04-2014
International application No.

PCT/US2014/012166

A. CLASSIFICATION OF SUBJECT MATTER

IPC(8) - B01J 27/32 (2014.01)

USPC - 502/36

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC(8) - B01J 23/90, 23/92, 27/28, 27/32, 38/46 (2014.01)

USPC - 502/36, 37; 570/168, 169

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched
CPC - B01J 23/92, 38/44, 38/46; C07C 17/206 (2014.02)

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

Orbit, Google Patents, Google Scholar

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5,227,350 A (SCOTT et al) 13 July 1993 (13.07.1993) entire document	1, 4-8, 11-14, 17-19
Y		2, 3, 9, 10, 15, 16
Y	US 2010/0210883 A1 (MUKHOPADHYAY et al) 19 August 2010 (19.08.2010) entire document	2, 3, 9, 10, 15, 16

☐ Further documents are listed in the continuation of Box C.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

10 April 2014

Date of mailing of the international search report

28 APR 2014

Name and mailing address of the ISA/US

Mail Stop PCT, Attn: ISA/US, Commissioner for Patents
P.O. Box 1450, Alexandria, Virginia 22313-1450

Facsimile No. 571-273-3201

Authorized officer:

Blaine R. Copenheaver

PCT Helpdesk: 571-272-4300

PCT OSP: 571-272-7774