

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
9 September 2011 (09.09.2011)

(10) International Publication Number
WO 2011/109699 A1

(51) International Patent Classification:

B32B 5/18 (2006.01) *C08J 9/00* (2006.01)
B32B 5/20 (2006.01) *B62D 29/00* (2006.01)
B32B 27/38 (2006.01)

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(21) International Application Number:

PCT/US2011/027166

(22) International Filing Date:

4 March 2011 (04.03.2011)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

61/310,580 4 March 2010 (04.03.2010) US

(71) Applicant (for all designated States except US): **ZEPHYROS, INC.** [US/US]; 160 Mclean Drive, Romeo, MI 48065 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **CHMIELEWSKI, Craig** [US/US]; 11117 Wilshire Drive, Shelby Township, MI 48315 (US). **MADAUS, Brandon** [US/US]; 70196 Beebe Street, Richmond, MI 48062 (US).

(74) Agent: **PURSLEY, Kristen, L.**; Dobrusin & Thennisch PC, 29 W. Lawrence Street, Suite 210, Pontiac, MI 48342 (US).

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) Title: STRUCTURAL COMPOSITE LAMINATE




Fig - 1

(57) Abstract: A method for a prevention and/or treatment of dysmenorrhea or amelioration of a symptom thereof in a subject, comprising administering to said subject an effective amount of a compound of formula I:

Filed Via EFS at USPTO.gov on 3.04.2011
Attorney Docket No. 1001.335WO

STRUCTURAL COMPOSITE LAMINATE

CLAIM OF PRIORITY

[0001] The present application claims the benefit of the filing date of U.S. Provisional Application No. 61/310,580 (filed March 4, 2010), the entirety of the contents of that application being hereby expressly incorporated by reference.

FIELD OF THE INVENTION

[0002] The present invention relates generally to laminate structures for sealing, baffling and structural reinforcement. More specifically, the present invention relates to laminate structures including structural foam and carrier materials.

BACKGROUND OF THE INVENTION

[0003] Structural reinforcement of vehicle cavities is commonly achieved by molding polymeric carriers into specific shapes that reflect the contours of the cavity requiring reinforcement, and locating expandable foam materials onto certain surfaces of the carriers. Thus, each carrier must be customized to a particular shape which requires the formation and use of multiple molds and further requires injection molding processes that are both time-consuming and costly. Many carriers require overmolding or multi-shot injection molding in order be formed in the correct shape and with sufficient density for reinforcing purposes. In attempts to reduce the cost and effort associated with manufacture of the carriers, attempts have been made to provide expandable foam materials without the inclusion of a carrier, as structural foams. The benefit is that that the size and shape of the structural foam can be quickly modified and customized to any necessary shape. Unfortunately, without a carrier, the strength of the reinforcement member that includes only the structural foam is reduced. Further, without a carrier it is difficult to control the expansion of the structural foam. It is thus desirable to provide a reinforcing structure that has the customization benefits of a structural foam alone, but still provides the requisite strength for cavity reinforcement. It is further desirable that the carrier add minimal weight and cost to the resulting structure, but still provide improved strength and

reinforcement ability than would be realized from either the structural foam or the carrier alone.

SUMMARY OF THE INVENTION

[0004] The present invention meets some or all of the above needs by providing a composite laminate structure having a reinforcement layer and structural foam so that the bond formed between the reinforcement layer and structural foam provides strength that exceeds that of either the structural foam or reinforcement layer alone. The present invention is directed toward a method of forming a composite laminate for providing sealing, baffling or reinforcement to a structure by providing a reinforcement layer and locating an epoxy-based expandable structural foam thereon. The reinforcement layer may have a surface tension of at least about 35 dynes/cm. The surface tensions of the structural foam and reinforcement layer are within about 15 dynes/cm of one another. The surface tensions of the reinforcement layer and structural foam provide sufficient wetting for load transfer from the structural foam to the reinforcement layer to increase the tensile strength of the composite laminate and to increase the lap shear strength of the composite laminate.

[0005] The present invention is further directed toward a composite laminate for providing sealing, baffling or reinforcement to a structure that includes a reinforcement layer and an epoxy-based expandable structural foam. The reinforcement layer may have a surface tension of at least about 35 dynes/cm. The epoxy-based expandable structural foam material is located onto the reinforcement layer to form the composite laminate. The surface tensions of the structural foam and reinforcement layer are within about 15 dynes/cm of one another so that adhesion between the structural foam and reinforcement layer is improved.

[0006] The present invention is also directed toward a method of forming a composite laminate by providing a polymeric reinforcement layer and locating an epoxy-based expandable structural foam material onto the reinforcement layer by a co-extrusion process to form the composite laminate. The composite laminate is then exposed to a temperature greater than 150°C. The reinforcement layer has a surface tension of at least about 35 dynes/cm and may include at least one chemical functional group free to react, such as a carboxylic acid or a primary or secondary

amine. The structural foam may include an epoxy resin, an epoxy/elastomer adduct including about 1:3 to 3:1 parts of epoxy to elastomer, and a core/shell polymer impact modifier. The epoxy resin may form a covalent bond with the reinforcement, such as with the carboxylic acid or amine of the reinforcement layer, upon exposure to temperatures greater than 150°C. The covalent bond allows for load transfer from the structural foam to the reinforcement layer to increase the tensile strength of the composite laminate.

[0007] The composite laminate includes improved physical properties over existing structures and materials for use in the sealing, baffling and reinforcement of cavities. These improved physical properties may include but are not limited to increased vertical rise, improved lap shear strength, increased tensile and flexural properties and increased T-Peel strength as compared to the use of structural foams alone. The structures of the present invention may also have improved storage and transport stability and improved shelf-life. The structures disclosed herein may also allow for customization of the size, shape and foam expansion direction of the structures in that the carrier is easily manipulated. In addition, the presence of the carrier allows for improved control over the expansion of the structural foam as compared to uses of structural foam alone.

BRIEF DESCRIPTION OF THE DRAWINGS

[0008] Fig. 1 is a cross-sectional view of an illustrative laminate structure in accordance with the present teachings.

[0009] Fig. 2 shows a graphic representation of the vertical rise of structural foams A, B, C, and D shown with and without a reinforcement layer.

[0010] Fig. 3 shows a graphic representation of the lap shear strength of structural foams A, B, C, and D shown with and without a reinforcement layer.

[0011] Fig. 4 shows a graphic representation of the flexural strength of structural foams A, B, C, and D shown with and without a reinforcement layer.

[0012] Fig. 5 shows a graphic representation of the flexural modulus of structural foams A, B, C, and D shown with and without a reinforcement layer.

[0013] Fig. 6 shows a graphic representation of the flexural testing load displacement curves for structural foam A, shown with and without a reinforcement layer.

[0014] Fig. 7 shows a graphic representation of the flexural testing load displacement curves for structural foam B, shown with and without a reinforcement layer.

[0015] Fig. 8 shows a graphic representation of the flexural testing load displacement curves for structural foam C, shown with and without a reinforcement layer.

[0016] Fig. 9 shows a graphic representation of the flexural testing load displacement curves for structural foam D, shown with and without a reinforcement layer.

DETAILED DESCRIPTION

[0017] In general, the teachings herein provide for a laminate structure that includes at least a reinforcement layer and a structural foam material located thereon. As an example, Fig. 1 shows a composite laminate having a reinforcement layer 10 and a structural foam layers 12 located on both surfaces of the reinforcement layer. The reinforcement layer provides a support mechanism for the structural foam material whereby a bond is formed between the reinforcement layer and the structural foam so that load transfer occurs from the structural foam to the reinforcement layer. The surface tensions of both the reinforcement layer and the structural foam may be similar (e.g., matched) so that the bond between the reinforcement layer and structural foam is strengthened. The strengthened bond between the reinforcement layer and the structural foam results in the laminate having one or more of improved peel strength, improved tensile properties, improved lap shear properties, improved compression properties, increased vertical rise, and improved flexural properties.

[0018] The bond between the reinforcement layer and structural foam may be formed by a variety of processes. As an example, the surface tension of the reinforcement layer and the surface tension of the structural foam may be matched so that bonding between the reinforcement layer and structural foam is improved. Improved bonding is observed as ease of wetting increases. The exceptional mechanical and structural properties exhibited by the present invention require increased adhesion of the structural foam to the reinforcement layer so that load placed on the resulting composite laminate can be transferred from the adhesive to the reinforcement layer to support part of or substantially all of the load. Thus, one technique relied upon to ensure improved adhesion is through matching the surface tensions of the adhesive and the reinforcement layer so that wetting is improved.

[0019] In order to achieve the improved bond strength between the structural foam and reinforcement layer, the surface tension of both the reinforcement layer and the structural foam may be at least about 35 dynes/cm. The surface tension of both the reinforcement layer and structural foam may be less than about 80 dynes/cm. In the event that the surface tension of the reinforcement layer falls below 35 dynes/cm, the reinforcement layer may be treated to increase its surface tension. Even when the surface tension of the reinforcement layer is at or above 35 dynes/cm, the reinforcement layer may still be treated to modify its surface tension to match the surface tension of the structural foam. Methods for treating the reinforcement layer to modify its surface tension are described herein. As an example, the structural foam may include an epoxy resin that provides for a surface tension of about 47 dynes/cm. Thus, for improved bond strength with the structural foam, the reinforcement layer has a surface tension of at least about 38 dynes/cm, but preferably at least about 42 dynes/cm, or greater.

[0020] The structural foam preferably includes an epoxy resin. Epoxy resin is used herein to mean any of the conventional dimeric, oligomeric or polymeric epoxy materials containing at least one epoxy functional group. The epoxy resin may be a bisphenol-A epoxy resin. The epoxy resin may comprise from about 2% to about 80% by weight of the structural foam. The epoxy resin may comprise from about 10% to about 30% by weight of the structural foam. The epoxy resin may comprise at least about 10% by weight of the structural foam. The epoxy resin may comprise less than about 30% by weight of the structural foam. The epoxy resin may be a liquid or a solid epoxy resin or may be a combination of liquid and solid epoxy resins.

[0021] The structural foam may also include an epoxy/elastomer adduct. More specifically, the adduct is composed substantially entirely (i.e., at least 70%, 80%, 90% or more) of one or more adducts that are solid at a temperature of 23 °C. The adduct may comprise from about 5% to about 80% by weight of the structural foam. The adduct may comprise at least about 5% by weight of the structural foam. The adduct may comprise at least about 10% by weight of the structural foam. The adduct may comprise less than about 70% by weight of the structural foam. The adduct may comprise less than about 30% by weight of the structural foam. The adduct itself generally includes about 1:5 to 5:1 parts of epoxy to elastomer, and more preferably about 1:3 to 3:1 parts or epoxy to elastomer. Exemplary elastomers

include, without limitation, natural rubber, styrene-butadiene rubber, polyisoprene, polyisobutylene, polybutadiene, isoprene-butadiene copolymer, neoprene, nitrile rubber (e.g., a butyl nitrile, such as carboxy-terminated butyl nitrile (CTBN)), butyl rubber, polysulfide elastomer, acrylic elastomer, acrylonitrile elastomers, silicone rubber, polysiloxanes, polyester rubber, diisocyanate-linked condensation elastomer, EPDM (ethylene-propylene diene rubbers), chlorosulphonated polyethylene, fluorinated hydrocarbons and the like. Examples of additional or alternative epoxy/elastomer or other adducts suitable for use in the present invention are disclosed in U.S. Patent Publication 2004/0204551, which is incorporated herein by reference for all purposes. As a specific example, the structural foam may include from about 5% to about 20% by weight CTBN/epoxy adduct.

[0022] The structural foam may also include an impact modifier. The impact modifier may comprise at least about 4% by weight of the structural foam. The impact modifier may comprise at least about 10% by weight of the structural foam. The impact modifier may comprise at least about 17% by weight of the structural foam. The impact modifier may comprise less than about 40% by weight of the structural foam. The impact modifier may comprise from about 2% to about 60% by weight of the structural foam.

[0023] The impact modifier may include at least one core/shell polymer. As used herein, the term core/shell polymer describes an impact modifier wherein a substantial portion (e.g., greater than 30%, 50%, 70% or more by weight) thereof is comprised of a first polymeric material (i.e., the first or core material) that is substantially entirely encapsulated by a second polymeric material (i.e., the second or shell material). The first and second polymeric materials, as used herein, can be comprised of one, two, three or more polymers that are combined and/or reacted together (e.g., sequentially polymerized) or may be part of separate or same core/shell systems. The first polymeric material, the second polymeric material or both of the core/shell impact modifier include or are substantially entirely composed of (e.g., at least 70%, 80%, 90% or more by weight) one or more thermoplastics. Exemplary thermoplastics include, without limitation, styrenics, acrylonitriles, acrylates, acetates, polyamides, polyethylenes or the like. It may be desirable for the glass transition temperature of the first or core polymeric material to be below 23 °C

while the glass temperature of the second or shell polymeric material to be above 23 °C, although not required.

[0024] Examples of useful core-shell graft copolymers are those where hard containing compounds, such as styrene, acrylonitrile or methyl methacrylate, are grafted onto cores made from polymers of soft or elastomeric containing compounds such as butadiene or butyl acrylate. U.S. Pat. No. 3,985,703, which is herein incorporated by reference, describes useful core-shell polymers, the cores of which are made from butyl acrylate but can be based on ethyl isobutyl, 2-ethylhexyl or other alkyl acrylates or mixtures thereof. The core polymer, may also include other copolymerizable containing compounds, such as styrene, vinyl acetate, methyl methacrylate, butadiene, isoprene, or the like. The shell portion may be polymerized from methyl methacrylate and optionally other alkyl methacrylates, such as ethyl, butyl, or mixtures thereof methacrylates. Examples of core-shell graft copolymers include, but are not limited to, "MBS" (methacrylate-butadiene-styrene) polymers, which are made by polymerizing methyl methacrylate in the presence of polybutadiene or a polybutadiene copolymer rubber. The MBS graft copolymer resin generally has a styrene butadiene rubber core and a shell of acrylic polymer or copolymer. Examples of other useful core-shell graft copolymer resins include, ABS (acrylonitrile-butadiene-styrene), MABS (methacrylate-acrylonitrile-butadiene-styrene), ASA (acrylate-styrene-acrylonitrile), all acrylics, SA EPDM (styrene-acrylonitrile grafted onto elastomeric backbones of ethylene-propylene diene monomer), MAS (methacrylic-acrylic rubber styrene), and the like and mixtures thereof.

[0025] The structural foam may also include one or more additional polymer and/or copolymer materials, such as thermoplastics, elastomers, plastomers, combinations thereof or the like. Polymers that might be appropriately incorporated into the structural foam include halogenated polymers, polycarbonates, polyketones, urethanes, polyesters, silanes, sulfones, allyls, olefins, styrenes, acrylates, methacrylates, epoxies, silicones, phenolics, rubbers, polyphenylene oxides, terphthalates, acetates (e.g., EVA), acrylates, methacrylates (e.g., ethylene methyl acrylate polymer) or mixtures thereof. Other potential polymeric materials may be or may include, without limitation, polyolefin (e.g., polyethylene, polypropylene) polystyrene, polyacrylate, poly(ethylene oxide), poly(ethyleneimine), polyester.

polyurethane, polysiloxane, polyether, polyphosphazine, polyamide, polyimide, polyisobutylene, polyacrylonitrile, poly(vinyl chloride), poly(methyl methacrylate), poly(vinyl acetate), poly(vinylidene chloride), polytetrafluoroethylene, polyisoprene, polyacrylamide, polyacrylic acid, polymethacrylate.

[0026] As a specific example, the structural foam may include at least about 2% but less than about 15% of a thermoplastic polyether. The structural foam may include at least about 10% by weight polyvinyl chloride. The structural foam may include less than about 30% by weight polyvinyl chloride. The structural foam may include at least about 0.1% by weight and less than about 5% by weight polyethylene oxide. The structural foam may include at least about 1% by weight of an ethylene copolymer (which may be and EVA or EMA copolymer). The structural foam may include at least about 15% by weight of an ethylene copolymer. The structural foam may include less than about 40% by weight of an ethylene copolymer. The structural foam may include at least about 5% by weight acrylonitrile. The structural foam may include at least about 20% by weight acrylonitrile. The structural foam may include less than about 50% by weight acrylonitrile.

[0027] The structural foam may also include a variety of blowing agents, curing agents and fillers. Examples of suitable blowing agents include azodicarbonamide, dinitrosopentamethylenetetramine, 4,4'-oxy-bis-(benzenesulphonylhydrazide), trihydrazinotriazine and N, N'-dimethyl-N,N'-dinitrosoterephthalamide. An accelerator for the blowing agents may also be provided in the activatable material. Various accelerators may be used to increase the rate at which the blowing agents form inert gasses. One preferred blowing agent accelerator is a metal salt, or is an oxide, e.g. a metal oxide, such as zinc oxide. Other preferred accelerators include modified and unmodified thiazoles or imidazoles.

[0028] Examples of suitable curing agents include materials selected from aliphatic or aromatic amines or their respective adducts, amidoamines, polyamides, cycloaliphatic amines, anhydrides, polycarboxylic polyesters, isocyanates, phenol-based resins (e.g., phenol or cresol novolak resins, copolymers such as those of phenol terpene, polyvinyl phenol, or bisphenol-A formaldehyde copolymers, bishydroxyphenyl alkanes or the like), or mixtures thereof. Particular preferred curing agents include modified and unmodified polyamines or polyamides such as triethylenetetramine, diethylenetriamine tetraethylenepentamine, cyanoguanidine,

dicyandiamides and the like. An accelerator for the curing agents (e.g., a modified or unmodified urea such as methylene diphenyl bis urea, an imidazole or a combination thereof) may also be provided for preparing the structural foam.

[0029] Examples of suitable fillers include silica, diatomaceous earth, glass, clay (e.g., including nanoclay), talc, pigments, colorants, glass beads or bubbles, glass, carbon or ceramic fibers, nylon or polyamide fibers (e.g., Kevlar), antioxidants, and the like. Such fillers, particularly clays, can assist the activatable material in leveling itself during flow of the material. The clays that may be used as fillers may include clays from the kaolinite, illite, chlorite, smectite or sepiolite groups, which may be calcined. Examples of suitable fillers include, without limitation, talc, vermiculite, pyrophyllite, saucinite, saponite, nontronite, montmorillonite or mixtures thereof. The clays may also include minor amounts of other ingredients such as carbonates, feldspars, micas and quartz. The fillers may also include ammonium chlorides such as dimethyl ammonium chloride and dimethyl benzyl ammonium chloride. Titanium dioxide might also be employed. One or more mineral or stone type fillers such as calcium carbonate, sodium carbonate or the like may be used as fillers. In another preferred embodiment, silicate minerals such as mica may be used as fillers. Preferably the filler includes a material that is generally non-reactive with the other components present in the activatable material. While the fillers may generally be present within the activatable material to take up space at a relatively low weight, it is contemplated that the fillers may also impart properties such as strength and impact resistance to the activatable material.

[0030] Examples of materials that may be included as the structural foam include those disclosed in U.S. Patent Nos. 7,892,396 and 7,125,461; and U.S. Application Nos. 2004/0204551; 2007/0090560; 2007/0101679; 2008/0060742; and 2009/0269547, which are incorporated by reference herein for all purposes.

[0031] The reinforcement layer includes any substantially solid material having the requisite capability to bond to the structural foam. As previously mentioned, the surface tension of the reinforcement layer is preferably at or above 35 dynes/cm and is also matched (e.g., similar to) the surface tension of the structural foam. Materials having surface tensions below this threshold (or considerably higher than that of the structural foam) may also be utilized as the reinforcement layer, but must first be treated to modify the surface tension of the material.

[0032] Polymeric materials may be used as the reinforcement layer. Certain polymeric materials have surface tension values that correspond with the surface tension of the epoxy-based materials generally utilized for the structural foam. Examples of polymeric materials that may be used as the reinforcement layer (with no treatment steps to modify surface tension) may include, but are not limited to acetals (about 47 dynes/cm), acrylics (about 41 dynes/cm), polyamides (about 41 dynes/cm), polycarbonates (about 46 dynes/cm), thermoplastic or cured thermoset epoxies (about 46 dynes/cm), polyethylene terephthalate (about 43 dynes/cm), polyimides (about 40 dynes/cm), polysulfones (about 41 dynes/cm), polyvinyl chlorides (about 39 dynes/cm) and phenolics (about 52 dynes/cm). Polyamides and polyethylene terephthalate (PET film) are two preferred materials for the reinforcement layer.


[0033] The reinforcement layer may include metal materials such as aluminum, steel, magnesium, tin, iron, nickel, copper, titanium or the like. The reinforcement layer may be a combination of different metal materials.

[0034] Those materials that have critical surface tensions which fall below 38 dynes/cm, may still be used as a reinforcement layer for this invention if they can be modified to meet the surface tension requirement. Three common methods for modifying the surface tension of a substrate are: (1) applying a liquid primer (including the use of strong acids and/or bases); (2) corona discharge; and (3) flaming with a petroleum based gas and air mixture. These methods typically succeed by oxidizing the surface of the substrate, thus raising its surface tension.

[0035] Another mechanism that ensures improved adhesion between the structural foam and the reinforcement layer is covalent bonding. Covalent bonding occurs via a chemical reaction between the reinforcement layer and structural foam. The composite laminate may require exposure to elevated temperatures (e.g., temperatures exceeding 150°C) in order for the covalent bonds to form. Thus, during manufacture of the composite laminate (e.g., during a co-extrusion process), temperatures are not typically elevated to levels required for covalent bonds to form. However, the covalent bonds may form during a vehicle paint bake cycle when a vehicle is exposed to such elevated temperatures.

[0036] In addition to appropriate time and temperature exposure, a chemical reaction leading to covalent bonds requires appropriate chemical matches between the

structural foam and reinforcement layer. The structural foam itself is a multi-component compound whose active ingredients include epoxy resins of various molecular weights. The epoxy resins may be based on diglycidyl ether of bisphenol A (DGBA) and their general chemical structure can be represented by:




[0037] The functional components of the epoxy resins are the epoxide group (e.g., an oxirane ring), which reside at the ends of the epoxy resin molecules. Epoxy resins residing in the structural foam adhesive have epoxy equivalent weights in the range of 170 to 6000 g/eq, but more likely in the range of 170 to 2000 g/eq and most ideally in the range of 180 to 1000 g/eq. Therefore, in order to form a bond between a structural foam and the reinforcement layer, the reinforcement layer must contain chemical functional groups which will react with epoxy resins. Examples of chemical functional groups which will react with epoxides include hydroxyl, carboxylic acid, amine, isocyanate and anhydride groups. Many thermoplastics contain one or more of these groups, especially if they have been constructed through condensation polymerizations. Examples of condensation thermoplastics are polyamides, polyesters, polycarbonates and polyurethanes.

[0038] The reinforcement layer may comprise a thermoplastic film that contains the chemical functional group which may result in covalent chemical bonds following a final bake cycle of the composite laminate. Films available commercially are commonly made from condensation polymers, such as polyesters (e.g. Mylar), polyamides (Nylons) and polycarbonates.

[0039] In the event that a polyester film is utilized as the reinforcement layer, a polyester/epoxy bond may be formed. When the composite laminate's reinforcing layer is a polyester such as polyethylene terephthalate, chemical reactions necessary to form the covalent bonds may take place upon exposure to elevated temperatures. In general, polyester resins are high molecular weight condensation polymers which are chain terminated with both carboxylic acid and alcohol chemical functionality.

[0040] As an example, polyesters that are commonly converted in to film are polyethylene terephthalate (PET) and polybutylene terephthalate (PBT). In both


cases the polymers are end-capped with both an alcohol and carboxylic acid. The reaction of the epoxide group with a carboxylic acid on the end of a polyester, such as polyethylene terephthalate (shown below as "PET"), proceeds via:



The reaction of the epoxide group with an alcohol on the end of a polyester, such as polyethylene terephthalate (shown below as "PET"), proceeds via:



[0041] Similar to the epoxide/polyester reactions shown above, the composite laminate's reinforcing layer may be a polyamide (PA), (e.g., Nylon (polyamide-6 (PA-6)) and thus may result in an epoxide/polyamide reaction. Generally, polyamides are high molecular weight condensation polymers which are chain terminated with both carboxylic acid and primary amine chemical functionality. These polymers are often end-capped with both a primary amine and carboxylic acid. The reaction of an epoxide group with a carboxylic acid on the end of a polyamide such as PA-6, proceeds in the same manner as shown above for the polyester. The reaction of an epoxide group with a primary amine of a polyamide (shown below as "PA") proceeds according to:



[0042] In both of the epoxide/polyester and epoxide/polyamide reactions shown above, a covalent bond is formed between the epoxy of the structural foam and the carboxylic acid, alcohol, or amine of the reinforcement layer. The resulting composite laminate exhibits the improved physical characteristics identified herein based upon the strength of the bond between the reinforcement layer and structural foam. The increased bond strength between the reinforcement layer and structural foam results in a number of improved physical characteristics of the composite laminate. Data depicting those improvements is shown below. Various examples of structural foams

have been utilized to obtain the data, those structural foams being identified as having the compositions shown at Table 1.

[0043] Table 1

Ingredient	Wt. %	A	B	C	D
Epoxy/Elastomer Adduct	15.70	15.58	15.58	14.71	
Epoxidized Ethylene Copolymer	1.95	1.93	1.93	1.74	
Ethylene Methacrylate	1.95	1.93	1.93	8.03	
Filler	43.1	46.56	43.09	50.93	
Epoxy Resins (solid-liquid mixture)	17.05	14.21	16.71	9.00	
Multifunctional Phenolic Novalac Epoxy Resin	2.93	2.94	2.94	3.59	
Curing Agent and/or Accelerator	2.20	2.06	2.27	3.23	
Impact Modifier	14.1	13.98	13.98	7.36	
Blowing Agent	0.88	0.65	1.53	1.21	
Pigment	0.15	0.15	0.025	0.2	

[0044] The improved bond between the reinforcement layer and structural foam results in improved characteristics that include an increased vertical rise during expansion of the structural foam. Vertical rise is defined as the thickness of the structural foam upon expansion as compared to the thickness of the structural foam prior to expansion. The reinforcement layer acts to restrict the lateral expansion of the structural foam which results in more controlled expansion direction and increased vertical rise. An increase in the vertical rise coupled with controlled expansion improves the reinforcing capability of the composite laminate by providing more precise contact of the structural foam with a cavity wall and increasing the density of the structural foam upon expansion. Fig. 2 includes a graphic representation of the vertical rise of structural foams A, B, C, and D shown both with and without a reinforcement layer.

[0045] The improved bond between the reinforcement layer and structural foam also results in improved lap shear strength when comparing structural foams without a reinforcement layer to those including a reinforcement layer. Increased lap shear strength results in improved reinforcing capabilities by increasing the overall strength of the composite laminate. Lap shear strength of structural foams is generally directly related to volume expansion, such that lower foam density (higher expansion) results in lower lap shear strength, and to bond-line, such that smaller bond lines lead to higher lap shear strengths. The bond-line can be defined as the bonding gap or the distance between two surfaces that an adhesive is bonding together. The

improvement in lap shear strength gained from the present invention over structural foams without a reinforcement layer can be attributed to an increase in foam density, but more significantly from the reinforcing layer effectively reducing the bond-line by half. Fig. 3 includes a graphic representation of the lap shear stress of structural foams A, B, C, and D shown with and without a reinforcement layer. Table 2 below includes numerical results for vertical rise and lap shear stress.

[0046] Table 2

Material	Vertical Rise		Lap Shear Stress			
	ctrl	w/ reinf.	ctrl		w/ reinf.	
	mm/mm	mm/mm	MPa	psi	MPa	psi
A	2.42	2.34	4.32	627	5.33	773
B	2.16	2.34	3.68	534	5.03	730
C	2.77	3.10	2.97	431	4.21	611
D	2.66	3.02	2.99	434	3.67	532

The improved bond between the reinforcement layer and structural foam also results in improved flexural strength and flexural modulus when comparing structural foams without a reinforcement layer to those including a reinforcement layer. Flexural strength and modulus was measured according to ASTM D790, using a 3-point bend testing mode. Figures 4 and 5 include graphic representations of the flexural strength and flexural modulus, respectively, of structural foams A, B, C, and D shown with and without a reinforcement layer.

[0047] The improved bond between the reinforcement layer and structural foam also results in improved energy absorption. Figures 6-9 include graphic representations of the flexural testing load displacement curves for structural foams A (figure 6), B (figure 7), C (figure 8) and D (figure 9), shown both with and without a reinforcement layer.

[0048] In Examples I, II and III below, the composite laminates are fabricated by locating a 0.18 mm thick polyethylene terephthalate film between two pieces of epoxy-based expandable structural foam. One example of this epoxy-based expandable structural foam is disclosed in US Patent No. 7,892,396. The resulting sandwich structure is compressed in a hot press at 180°F for 2 to 3 minutes such that the film forms a middle layer of the composite laminate and the final thickness of the total structure is about 3 mm.

[0049] Example I

[0050] Table 3 provides a comparison of two epoxy-based expandable structural foam properties in the neat state (e.g., with no reinforcement layer) and as a composite laminate, using polyester terephthalate film. All properties listed are for materials in the post-activation state.

[0051] Table 3 shows that the relative vertical rise of the composite laminate of this invention is higher than that of the neat material. The reinforcing layer constrains the lateral (horizontal or in-plane) movement of the activated material, resulting in the expansion to be directed perpendicular to the plane or axis of the reinforcing layer.

[0052] Lap shear strength is measured according to ASTM D1002, using a 3 mm bond line and an EG-60 metal substrate. Table 3 shows greater lap shear strength for the composite structures than the neat epoxy-resin adhesive. The reinforcing layer effectively reduces the apparent bond line, resulting in higher lap shear strengths.

[0053] Flexural testing is accomplished according to ASTM D790, using a 3-point bend testing mode. The test specimens were constructed using a sandwich configuration. The top and bottom substrates were 0.030" thick EG60 steel with dimensions of 1" x 6". Structural foam filled the middle, giving a total thickness (foam and steel) of 6 mm. Table 3 shows greater flexural strength and modulus for the composite laminate samples than the neat epoxy-resin adhesive.

[0054] Tensile testing was conducted in the spirit of ASTM D638, using a JISK 6301-1-MET dog bone configuration at 10 mm wide, 3 mm thick and tested at a speed of 5mm/min. The test specimens were constructed by expanding the foam between two release surfaces with 3 mm spacers and then die cutting the tensile bars while the samples were still warm. Samples containing the PET film have the film orientated in the plane of the sample so that under tension the film is being stretched along with the rest of the sample. Table 3 shows greater tensile strength and modulus for the composite laminate samples than the neat epoxy-resin adhesive.

[0055] TABLE 3

	Material B		Material C	
	no reinforcement	w/ reinforcement	no reinforcement	w/ reinforcement
Vertical Rise	2.16	2.34	2.77	3.10
Lap Shear (MPa)	3.68	5.03	2.97	4.21
Flex Strength (MPa)	122.5	143.3	94.4	120.4
Flex Modulus (GPa)	28.1	34.2	19.4	25.1
Tensile Stress (MPa)	5.5	16.2	4.8	10.3
Tensile Modulus (MPa)	685	1318	655	1065

[0056] Example II

[0057] In this example, composite structural laminates are fabricated by pressing a 0.18 mm thick polyethylene terephthalate film between two pieces of epoxy-based expandable structural foam. An example of this epoxy-based expandable structural foam is similar to the activatable material disclosed in US Patent No. 7,892,396, except for the absence of a core/shell polymer impact modifier. The sandwich structure is compressed in a hot press at 180°F for 2 to 3 minutes such that the film is essentially in the middle of the structure and the final thickness of the total structure is about 3 mm.

[0058] Table 4 provides a comparison of an epoxy-based expandable structural foam property in the neat state (with no reinforcement) and as a composite laminate, using polyester terephthalate film. All properties listed are for materials in the post-activation state.

[0059] TABLE 4

	Material D	
	no reinforcement	w/ reinforcement
Vertical Rise	2.66	3.02
Lap Shear (MPa)	2.99	3.67
Flex Strength (MPa)	111.9	156.2
Flex Modulus (GPa)	27.1	37.3
Tensile Stress (MPa)	5.6	10.0
Tensile Modulus (MPa)	998	1152

[0060] Test details are the same as those given in Example I. Table 4 shows all properties of the composite laminate are improved over those of the neat epoxy-resin adhesive.

[0061] **Example III**

[0062] Structural foam materials formed in accordance to the present invention have also exhibited desirable post activation compression properties. In particular, structural foam materials of the present invention were foamed to form samples that were then tested according to a method that is based upon ASTM C39. While the method is described herein, it should be understood that any unspecified parameters will be in accordance with ASTM C39.

[0063] Three distinct sample types were formed. The first sample was formed by foaming the neat (non-reinforced) epoxy based foam material in cylinders or cylinder cups followed by removing excess foam that extends out of the cylinders or cups (e.g., by cutting away foam that extends out of the cylinders or cups). The second sample was constructed by cutting discs from a flat composite laminate sample and stacking them in a cylinder or cylinder cup such that the plane of the PET reinforcing layers are perpendicular to the axis of the cylinder. This sample was then finished by foaming the layered composite laminate in the cylinders or cylinder cups followed by removing excess foam that extends out of the cylinders or cups (e.g., by cutting away foam that extends out of the cylinders or cups). The third sample was constructed by rolling a flat composite laminate sample and sliding them in a cylinder or cylinder cup such that the plane of the PET reinforcing layers are parallel to the axis of the cylinder. This sample was then finished by foaming the layered composite laminate in the cylinders or cylinder cups followed by removing excess foam that extends out of the cylinders or cups (e.g., by cutting away foam that extends out of the cylinders or cups).

[0064] The test samples are typically foamed to a volume that is less than 1000%, more typically less than 750% and even more typically less than 500% relative to the original volume of the structural foam material prior to foaming. This is done to form cylindrical samples that are 60 mm in height and 30 mm in diameter. The cylinder samples are then tested according to ASTM C39.

[0065] Table 5 provides a comparison of cylinder compression properties of an epoxy-based expandable structural foam in the neat state and composite structural laminates where the PET film resides in stacked layers perpendicular to the cylinder axis and parallel to the cylinder axis. All properties listed are for materials in the post-activation state.

[0066] TABLE 5

	Material C	
	Peak Compression Stress (MPa)	Compression Modulus (MPa)
Neat epoxy based structural foam	4.7	420
Film perpendicular to cylinder axis	7.0	433
Film parallel to cylinder axis	15.6	1035

[0067] Table 5 shows that the orientation of the film has a large effect on the compression properties of the sample, and in every instance compression of the composite laminate sample is greater than the neat sample.

[0068] It is contemplated that an activatable composite laminate according to the present invention may be employed as a structural adhesive material. In such an embodiment, the composite material is typically activated and cured (e.g., at temperatures common to e-coat or automotive painting operations) to adhere to a first member and a second member. Contact with attachment surface of the first member and the second member may occur prior to or during activation and curing of the material. Examples of structural adhesive applications are disclosed in US Patent Nos. 6,887,914 and 6,846,559; and US Patent Publication No. 2004/0204551, all of which are incorporated herein by reference for all purposes.

[0069] During use of the composite laminates, one or more fasteners or adhesives may be attached to the composite laminate for attachment to a cavity wall or other location within a cavity. The fasteners may be mechanical fasteners and may include but are not limited to push-pins, tree fasteners, hinges, screws, a mechanical interlock, integral locks, a male feature, a female feature or any combination thereof. The composite laminate may include one push pin on each opposing end of the composite laminate.

[0070] In addition to the improved physical characteristics of the composite laminate structures disclosed herein, the ease of manufacture associated with the composite laminates make them easily customized to any shape or size required for a given cavity. The composite laminates may be co-extruded and then easily modified (e.g., die-cut, sliced). They can be modified prior to distribution to a customer or on on-site during assembly of the composite laminate within a cavity.

[0071] Any numerical values recited herein include all values from the lower value to the upper value in increments of one unit provided that there is a separation of at least 2 units between any lower value and any higher value. As an example, if it is stated that the amount of a component or a value of a process variable such as, for example, temperature, pressure, time and the like is, for example, from 1 to 90, preferably from 20 to 80, more preferably from 30 to 70, it is intended that values such as 15 to 85, 22 to 68, 43 to 51, 30 to 32 etc. are expressly enumerated in this specification. For values which are less than one, one unit is considered to be 0.0001, 0.001, 0.01 or 0.1 as appropriate. These are only examples of what is specifically intended and all possible combinations of numerical values between the lowest value and the highest value enumerated are to be considered to be expressly stated in this application in a similar manner. As can be seen, the teaching of amounts expressed as "parts by weight" herein also contemplates the same ranges expressed in terms of percent by weight. Thus, an expression in the Detailed Description of the Invention of a range in terms of at "x" parts by weight of the resulting polymeric blend composition" also contemplates a teaching of ranges of same recited amount of "x" in percent by weight of the resulting polymeric blend composition."

[0072] Unless otherwise stated, all ranges include both endpoints and all numbers between the endpoints. The use of "about" or "approximately" in connection with a range applies to both ends of the range. Thus, "about 20 to 30" is intended to cover "about 20 to about 30", inclusive of at least the specified endpoints.

[0073] The disclosures of all articles and references, including patent applications and publications, are incorporated by reference for all purposes. The term "consisting essentially of" to describe a combination shall include the elements, ingredients, components or steps identified, and such other elements ingredients, components or steps that do not materially affect the basic and novel characteristics

of the combination. The use of the terms "comprising" or "including" to describe combinations of elements, ingredients, components or steps herein also contemplates embodiments that consist essentially of the elements, ingredients, components or steps. By use of the term "may" herein, it is intended that any described attributes that "may" be included are optional.

[0074] Plural elements, ingredients, components or steps can be provided by a single integrated element, ingredient, component or step. Alternatively, a single integrated element, ingredient, component or step might be divided into separate plural elements, ingredients, components or steps. The disclosure of "a" or "one" to describe an element, ingredient, component or step is not intended to foreclose additional elements, ingredients, components or steps. All references herein to elements or metals belonging to a certain Group refer to the Periodic Table of the Elements published and copyrighted by CRC Press, Inc., 1989. Any reference to the Group or Groups shall be to the Group or Groups as reflected in this Periodic Table of the Elements using the IUPAC system for numbering groups.

[0075] It will be appreciated that concentrates or dilutions of the amounts recited herein may be employed. In general, the relative proportions of the ingredients recited will remain the same. Thus, by way of example, if the teachings call for 30 parts by weight of a Component A, and 10 parts by weight of a Component B, the skilled artisan will recognize that such teachings also constitute a teaching of the use of Component A and Component B in a relative ratio of 3:1. Teachings of concentrations in the examples may be varied within about 25% (or higher) of the stated values and similar results are expected. Moreover, such compositions of the examples may be employed successfully in the present methods.

[0076] It will be appreciated that the above is by way of illustration only. Other ingredients may be employed in any of the compositions disclosed herein, as desired, to achieve the desired resulting characteristics. Examples of other ingredients that may be employed include antibiotics, anesthetics, antihistamines, preservatives, surfactants, antioxidants, unconjugated bile acids, mold inhibitors, nucleic acids, pH adjusters, osmolarity adjusters, or any combination thereof.

[0077] It is understood that the above description is intended to be illustrative and not restrictive. Many embodiments as well as many applications besides the examples provided will be apparent to those of skill in the art upon reading the above

description. The scope of the invention should, therefore, be determined not with reference to the above description, but should instead be determined with reference to the appended claims, along with the full scope of equivalents to which such claims are entitled. The disclosures of all articles and references, including patent applications and publications, are incorporated by reference for all purposes. The omission in the following claims of any aspect of subject matter that is disclosed herein is not a disclaimer of such subject matter, nor should it be regarded that the inventors did not consider such subject matter to be part of the disclosed inventive subject matter.

CLAIMS

1. A method of forming a composite laminate for providing sealing, baffling or reinforcement to a structure, the method comprising:

providing a reinforcement layer having a high surface tension of at least about 35 dynes/cm;

locating an epoxy-based expandable structural foam material onto the reinforcement layer to form the composite laminate wherein the surface tensions of the structural foam and reinforcement layer are within about 15 dynes/cm of one another;

wherein the high surface tensions of the reinforcement layer and structural foam provide sufficient wetting for load transfer from the structural foam to the reinforcement layer to:

- i. increase the tensile strength of the composite laminate; and
- ii. increase the lap shear strength of the composite laminate.

2. The method of claim 1, including a step of exposing the composite structure to a temperature greater than 150°C so that a covalent bond is formed between the reinforcement layer and structural foam.

3. The method of claim 1 or claim 2, wherein the reinforcement layer includes a carboxylic acid chemical functional group and the structural foam material includes a component that forms a covalent bond with the carboxylic acid of the reinforcement layer upon exposure to temperatures greater than 150°C.

4. The method of claim 1 or claim 2, wherein the reinforcement layer includes an amine chemical functional group and the structural foam material includes a component that forms a covalent bond with the amine of the reinforcement layer upon exposure to temperatures greater than 150°C.

5. The method of any of claims 1 through 4, wherein the reinforcement layer comprises a metal foil.

6. The method of any of claims 1 through 5, wherein the reinforcement layer comprises a polymeric film selected from the group consisting of: acetals, acrylics, polyamides, polycarbonates, polyetheramines, polyethylene terephthalate, polyimides, polysulfones, polyvinyl chlorides, phenolics, or any combination thereof.

7. The method of any of claims 1 through 6, wherein the surface of the reinforcement layer is treated to raise its surface tension to at least 35 dynes/cm.

8. The method of claim 7, wherein the reinforcement layer is treated by applying a liquid primer, corona discharge or flaming with petroleum based gas and air mixture so that its surface tension is raised to at least 35 dynes/cm.

9. The method of claim 3, wherein the structural foam comprises an epoxy resin that forms the covalent bond with the carboxylic acid of the reinforcement layer.

10. The method of claim 4, wherein the structural foam comprises an epoxy resin that forms the covalent bond with the amine of the reinforcement layer.

11. The method of any of claims 1 through 10, wherein the structural foam is located onto the reinforcement layer by a co-extrusion process.

12. The method of claim 11, wherein the covalent bond between the reinforcement layer and the structural foam is not formed during the co-extrusion process.

13. A composite laminate for providing sealing, baffling or reinforcement to a structure comprising:

 a reinforcement layer having a surface tension of at least about 35 dynes/cm;
 and

 an epoxy-based expandable structural foam material located onto the reinforcement layer to form the composite laminate wherein the surface tensions of the structural foam and reinforcement layer are within about 15 dynes/cm of one

another so that adhesion between the structural foam and reinforcement layer is improved.

14. The composite laminate of claim 13, wherein the reinforcement layer comprises a metal foil.

15. The composite laminate of claim 13 or claim 14, wherein the reinforcement layer comprises a polymeric film selected from the group consisting of: acetals, acrylics, polyamides, polycarbonates, polyetheramines, polyethylene terephthalate, polyimides, polysulfones, polyvinyl chlorides, phenolics, or any combination thereof.

16. The composite laminate of claim 13, wherein the surface of the reinforcement layer is treated to raise its surface tension to at least 35 dynes/cm.

17. The composite laminate of claim 16, wherein the reinforcement layer is treated by applying a liquid primer, corona discharge or flaming with petroleum based gas and air mixture so that its surface tension is raised to at least 35 dynes/cm.

18. The composite laminate of any of claims 13 through 17, wherein the structural foam comprises:

- i. an epoxy resin;
- ii. an epoxy/elastomer adduct, the adduct including about 1:3 to 3:1 parts of epoxy to elastomer; and
- iii. a core/shell polymer impact modifier.

19. The composite laminate of any of claims 13 through 18, wherein the reinforcement layer includes a carboxylic acid chemical functional group and the epoxy resin of the structural foam forms a covalent bond with the carboxylic acid of the reinforcement layer upon exposure to temperatures greater than 150°C.

20. The composite laminate of claims 13 though 18, wherein the reinforcement layer includes an amine chemical functional group and the epoxy resin of the

structural foam forms a covalent bond with the amine of the reinforcement layer upon exposure to temperatures greater than 150°C.

21. A method of forming a composite laminate for providing sealing, baffling or reinforcement to a structure, the method comprising:

providing a polymeric reinforcement layer having a surface tension of at least about 35 dynes/cm wherein the reinforcement layer includes a carboxylic acid or an amine chemical functional group;

locating an epoxy-based expandable structural foam material onto the reinforcement layer by a co-extrusion process to form the composite laminate wherein the structural foam material comprises:

- i. an epoxy resin;
- ii. an epoxy/elastomer adduct, the adduct including about 1:3 to 3:1 parts of epoxy to elastomer; and
- iii. a core/shell polymer impact modifier;

wherein the epoxy resin forms a covalent bond with the carboxylic acid or amine of the reinforcement layer upon exposure to temperatures greater than 150°C;

exposing the composite structure to a temperature greater than 150°C so that a covalent bond is formed between the reinforcement layer and structural foam;

wherein the covalent bond allows for load transfer from the structural foam to the reinforcement layer to increase the tensile strength of the composite laminate.

22. The method of claim 21, wherein upon exposure of the composite laminate to temperatures greater than 150°C, the covalent bond between the reinforcement layer and the structural foam substantially prevents lateral expansion of the foam so that expansion of the foam is substantially vertical.

1/5




Fig - 1




Fig - 2

2/5




Fig -3




Fig -4

3/5





Fig -5

3 Point Bend Test of Material A with and without Reinforcement Layer



Flexural Testing Load Displacement Curves for Material A

Fig -6

4/5




Fig - 7




Fig - 8

5/5




Fig -9

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2011/027166

A. CLASSIFICATION OF SUBJECT MATTER	INV. B32B5/18	B32B5/20	B32B27/38	C08J9/00	B62D29/00
ADD.					

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

B32B C08J B62D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2008/311405 A1 (WANG WEI [US] ET AL) 18 December 2008 (2008-12-18)	1,2,4,7, 8,13,16, 17,19,20
Y	paragraph [0005] - paragraph [0043]; examples paragraph [0045]	1-22
X	US 2004/204551 A1 (CZAPLICKI MICHAEL J [US] ET AL) 14 October 2004 (2004-10-14) paragraph [0005] - paragraph [0054] paragraph [0053]	1,13
X	US 2002/192387 A1 (AGARWAL RAJAT K [US] ET AL) 19 December 2002 (2002-12-19)	1,5,13, 14
Y	abstract paragraph [0009] - paragraph [0039]; examples	1-22
	----- ----- ----- -----	-/-

Further documents are listed in the continuation of Box C.

See patent family annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search	Date of mailing of the international search report
13 May 2011	24/05/2011
Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Fax: (+31-70) 340-3016	Authorized officer Hutton, David

INTERNATIONAL SEARCH REPORT

International application No PCT/US2011/027166

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category [*]	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2008/029200 A1 (SHEASLEY DAVID [US]) 7 February 2008 (2008-02-07) the whole document paragraphs [0072] - [0084] paragraphs [0008] - [0064] paragraph [0070] -----	1-22
A	US 2006/188726 A1 (MUENZ XAVER [DE] ET AL) 24 August 2006 (2006-08-24) the whole document paragraphs [0080] - [0083] -----	1-22
A	US 5 755 486 A (WYCECH JOSEPH S [US]) 26 May 1998 (1998-05-26) the whole document -----	1-22
A	US 2005/103422 A1 (KAWAGUCHI YASUHIKO [JP]) 19 May 2005 (2005-05-19) the whole document -----	1-22
A	US 2003/183317 A1 (CZAPLICKI MICHAEL J [US] ET AL) 2 October 2003 (2003-10-02) the whole document paragraphs [0016], [0017], [0036], [0037]; claims -----	1-22

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/US2011/027166

Patent document cited in search report		Publication date		Patent family member(s)		Publication date
US 2008311405	A1	18-12-2008	WO	2006076310 A2		20-07-2006
US 2004204551	A1	14-10-2004	CA	2517796 A1		16-09-2004
			EP	1599527 A2		30-11-2005
			JP	2006520848 T		14-09-2006
			US	2007088138 A1		19-04-2007
			WO	2004078853 A2		16-09-2004
US 2002192387	A1	19-12-2002	WO	02098650 A1		12-12-2002
US 2008029200	A1	07-02-2008	CA	2652744 A1		31-01-2008
			EP	2024195 A2		18-02-2009
			JP	2009540061 T		19-11-2009
			WO	2008014053 A2		31-01-2008
US 2006188726	A1	24-08-2006	AT	403701 T		15-08-2008
			DE	10302298 A1		05-08-2004
			EP	1590403 A1		02-11-2005
			WO	2004065485 A1		05-08-2004
			ES	2309489 T3		16-12-2008
US 5755486	A	26-05-1998	AT	230693 T		15-01-2003
			AU	711241 B2		07-10-1999
			AU	5750596 A		11-12-1996
			BR	9609162 A		09-05-2000
			CA	2221126 A1		28-11-1996
			CN	1187792 A		15-07-1998
			CZ	9703677 A3		13-05-1998
			DE	69625683 D1		13-02-2003
			DE	69625683 T2		23-10-2003
			EP	0827473 A1		11-03-1998
			ES	2188756 T3		01-07-2003
			HU	9900371 A2		28-05-1999
			JP	11505777 T		25-05-1999
			PL	324907 A1		22-06-1998
			PL	182181 B1		30-11-2001
			SI	9620084 A		30-06-1998
			SK	157397 A3		03-06-1998
			WO	9637400 A1		28-11-1996
US 2005103422	A1	19-05-2005	AT	341447 T		15-10-2006
			CN	1626578 A		15-06-2005
			DE	602004002652 T2		16-08-2007
			EP	1531040 A2		18-05-2005
			ES	2270256 T3		01-04-2007
			JP	3689418 B2		31-08-2005
US 2005103422	A1		JP	2005139218 A		02-06-2005
US 2003183317	A1	02-10-2003	US	2008061602 A1		13-03-2008