

608927

COMMONWEALTH OF AUSTRALIA

PATENTS ACT 1952 - 1960

CONVENTION APPLICATION FOR A PATENT

We, FORD MOTOR COMPANY OF CANADA, LIMITED, a company organized and existing under the laws of Canada and having its principal office at The Canadian Road, Oakville, Ontario, Canada, hereby apply for the grant of a Patent for an invention entitled:

STABILIZER SYSTEM FOR EXTRUDABLE POLYESTER BLENDS - II

which is described in the accompanying complete specification. This application is made under the provisions of part XVI of the Patents Act 1952 - 1960 and is based on the following application or applications for a patent or patents or similar protection made in the following country or countries on the following date or dates:

in the United States of America on December 28, 1987
under Serial Number 138,470

APPLICATION ACCEPTED AND AMENDMENTS
24.1.91
ALLOWED

Our address for service is Messrs. EDWARD WATERS & SONS, 50, Queen Street, Melbourne,
Street, Melbourne, Victoria, Australia who we hereby appoint to act for us.
Victoria, Australia

Dated this 6th day of September 1988 ~~XXXX~~

FORD MOTOR COMPANY OF CANADA, LIMITED

By R.W. Carter (C.S.)
R.W. Carter
Secretary

COMMONWEALTH OF AUSTRALIA

PATENTS ACT 1952 - 1960

DECLARATION IN SUPPORT OF A CONVENTION

APPLICATION FOR A PATENT

In support of the Convention Application made under the Patents Act 1952 - 1960 by FORD MOTOR COMPANY OF CANADA, LIMITED, a company organized and existing under the laws of Canada and having its principal office at The Canadian Road, Oakville, Ontario, Canada, for a patent for an invention entitled: STABILIZER SYSTEM FOR EXTRUDABLE POLYESTER BLENDS - II

I, R.W. Carter of 190 Tilford Road, Oakville, Ontario, Canada L6L 4Z3, Secretary

of the said FORD MOTOR COMPANY OF CANADA, LIMITED, do solemnly and sincerely declare as follows:

1. I am authorized by FORD MOTOR COMPANY OF CANADA, LIMITED, the applicant for the patent to make this declaration on its behalf.

2. The basic application(s) as defined by Section 141 of the Act was were made in the following country by the following applicant(s), namely:-

in the United States of America on December 28, 1987
under Serial Number 138,470 by Mo-Fung Cheung;
Amos Golovoy;
Henk van Oene

3. Mo-Fung Cheung of 28118 Gettysburg, Farmington Hills, Mich 48331;
Amos Golovoy of 7865 Royal Court N., Canton, Michigan 48187;
Henk van Oene of 25355 Shiawassee Circle #205, Southfield, Michigan 48034, respectively

~~/s/~~are the actual inventor(s) of the invention and the facts upon which the FORD MOTOR COMPANY OF CANADA, LIMITED is entitled to make the application are as follows:

The said FORD MOTOR COMPANY OF CANADA, LIMITED is the assignee of FORD MOTOR COMPANY, a company organized and existing by virtue of the laws of the State of Delaware, and having its principal place of business at The American Road, Dearborn, State of Michigan, United States of America who was the assignee of the said inventor(s).

4. The basic application referred to in paragraph 2 of this Declaration was the first application made in a Convention Country in respect of the invention, the subject of the applications.

DECLARED at Oakville, Ontario, Canada this 6th day of September 1988

R.W. Carter
R.W. Carter

To:
The Commissioner of Patents.

(12) PATENT ABRIDGMENT (11) Document No. AU-B-27502/88
(19) AUSTRALIAN PATENT OFFICE (10) Acceptance No. 608927

(54) Title
PHOSPHATE + IMIDE OR OXAZOLINE POLYMER

International Patent Classification(s)
(51)* C08L 025/06 C08K 005/52 C08L 067/02 C08L 075/00

(21) Application No. : 27502/88 (22) Application Date : 23.12.88

(30) Priority Data

(31) Number (32) Date (33) Country
138470 28.12.87 US UNITED STATES OF AMERICA

(43) Publication Date : 29.06.89

(44) Publication Date of Accepted Application : 18.04.91

(71) Applicant(s)
FORD MOTOR COMPANY OF CANADA, LIMITED

(72) Inventor(s)
MO-FUNG CHEUNG; AMOS GOLOVOY; HENK VAN OENE

(74) Attorney or Agent
WATERMARK PATENT & TRADEMARK ATTORNEYS, Locked Bag 5, HAWTHORN VIC
3122

(56) Prior Art Documents
AU 27501/88

(57) Claim

1. A stabilizer system useful to retard transesterification in moldable polymer blends comprising polyester, wherein the stabilizer system comprises:

(A) phosphate component selected from mono- and di-esters of orthophosphoric acid;

(B) reactive functionality component selected from compounds having (1) imide or (2) oxazoline functionality; and optionally,

(C) hindered phenol component,

wherein said phosphate component comprises at least about 51 weight percent of said stabilizer system.

5. A composition comprising:

I. polyester; and

(11) AU-B-27502/88
(10) 608927

-2-

II. a stabilizer system comprising:

- (A) phosphate component selected from mono- and di-esters of ortho-phosphoric acid;
- (B) reactive functionality component having one reactive functionality capable of reacting with a hydroxyl or carboxyl group; and, optionally,
- (C) hindered phenol component,

wherein said phosphate component comprises at least about 51 weight percent of said stabilizer system.

608927

Form 10

COMMONWEALTH OF AUSTRALIA

PATENTS ACT 1952-69

COMPLETE SPECIFICATION

(ORIGINAL)

Class

Int. Class

Application Number:
Lodged:

Complete Specification Lodged:
Accepted:
Published:

Priority:

Related Art:

Name of Applicant: FORD MOTOR COMPANY OF CANADA, LIMITED

Address of Applicant: The Canadian Road, Oakville, Ontario, Canada

Actual Inventor: MO-FUNG CHEUNG, AMOS GOLOVOY and HENK VAN OENE

Address for Service: EDWD. WATERS & SONS,
50 QUEEN STREET, MELBOURNE, AUSTRALIA, 3000.

Complete Specification for the invention entitled:

STABILIZER SYSTEM FOR EXTRUDABLE POLYESTER BLENDS

The following statement is a full description of this invention, including the best method of performing it known to: US

STABILIZER SYSTEM FOR EXTRUDABLE POLYESTER BLENDS - II

Technical Field

5

This invention is directed to a stabilizer system useful to retard transesterification in moldable polymer blends containing polyester(s) during processing of the blends at elevated temperatures, particularly at
10 temperatures above about 285°C.

Background of the Invention

Blending two or more plastic polymeric materials
15 to achieve certain specific properties has become an important technology. Such polymer blends can be thought of as macromolecular plastic alloys. The polymeric materials of the blend are chosen so as to optimize the properties of the blend. For example, a high glass
20 transition temperature (T_g) polymer characterized by exceptional toughness and poor solvent resistance might be blended with a polymer which has excellent solvent resistance but a lower T_g , where the latter polymer alone exhibits poor mechanical properties, e.g., tensile
25 and flexural modulus. The resulting blend would be expected to have properties intermediate those of the individual blend constituents, the particular properties dependent on the proportions of the constituents.

30 Polyesters having aromatic moieties, e.g., polyarylates, are often employed as at least one of the polymers in such blends. Polyarylates are high temperature, high performance polymers which have a good combination of thermal and mechanical properties.
35 Additionally, polyarylates have inherent combustion

resistance as well as good weatherability. They also have good melt stability at high temperatures and good color retention. Still further, they have good processability which allows them to be molded into a variety of articles. Polyarylates have been blended with a number of other polymers, such as ABS resins (U.S. Pat. No. 3,792,118), polycarbonate resins (U.S. Pat. No. 3,792,115), polyurethane resins, methacrylate resins, etc. When there is an extreme of viscosity difference between a high viscosity polyarylate and the other polymer, severe service irregularities (e.g., jetting) are observed when these blends are injection molded. This is observed especially when polyarylate is blended with, for example, ABS resins and poly(methyl methacrylate) resins. Additionally, the extremely high viscosity of polyarylates prevents a uniform of product from being obtained by conventional polymer techniques, i.e., extrusion or Banbury type melt mixing, when the polyarylate is blended with a resin having a lower viscosity. The non-uniform blend will not weather as well as the uniform blend of the resins nor will it have an acceptable balance of properties. Still further, the inclusion of lower molecular weight constituents (which generally have lower melt viscosities) in order to lower the melt viscosity of the blend and make the blend more processable is generally at the expense of physical properties of the blend such as toughness. Therefore, it is preferred that the blend comprise constituents having molecular weights and melt viscosities similar to the polyarylate, e.g., polycarbonate. However, the relatively high melt viscosities of such blends makes them difficult to process at normal processing temperatures, i.e., normally below about 285°C. It is well known that the processability of such blends can be improved if the blends are molded at higher

temperatures. However, at such higher temperatures, exchange reactions, such as alcoholysis, acidolysis, and transesterification, among the polyester(s) generally take place. Such reactions may take place when one or
5 two or more different polyesters are present in the blend. The extent of such reactions effects the ultimate properties of the blend. In transesterification, an exchange of the ester moiety between two similar or different polyester molecules takes place which generates
10 new molecular configurations, and hence a new composition. Transesterification during the melt-mixing of such blends results in poor mechanical properties and loss of crystallinity if the polyester is a semi-crystalline material. The product becomes
15 embrittled and loses impact strength as compared to a product made from the same polymer blend in which transesterification did not occur.

French patent 2,567,137 to Bonum and Logeat
20 discloses incorporating esterified orthophosphoric acids into compositions comprising thermoplastic polyester pairs with different chemical structures, such as ethyleneglycol terephthalate and butanediol polyterphthalate-1,4 to prevent transesterification
25 during molding thereof. It is also known that in blends containing polyesters, a residual catalyst generally remains from the polymerization which may accelerate, e.g., ester-carbonate, interchange reactions in the melt state. In Chemistry of Miscible Polycarbonate-
30 Copolyester Blends, Smith, Barlow and Paul, Journal of Applied Polymer Science, Vol. 26, 4233-4245 (1981), it is taught that interchange reactions are greatly suppressed by deactivating the residual titanium catalyst with arsenic oxide additive. Usually, however, rather than
35 adding compounds in an attempt to deactivate catalysts,

workers in the art add any of numerous compounds to such polymer blends to improve the physical properties thereof. For example, in U.S. Patent 4,066,611, it is taught that particular phosphorous compounds may be
5 incorporated into a bisphenol A polycarbonate/poly-(tetramethylene terephthalate) blend to enhance the mechanical properties of the blend. U.S. patent 4,066,611 discloses that cyclic diphosphite compounds can improve the thermal-oxidative stability and hydrolytic
10 stability of aromatic carbonate polymer compositions. However, attempts to prevent transesterification of polymer blends containing polyester during processing at elevated temperatures above about 280°C have been less than successful.

15

It is an object of the present invention to provide a stabilizer system capable of retarding transesterification of ester containing polymer blends during melt-mixing and molding, particularly at the
20 higher temperatures generally necessary to effectively process such blends. We have found an effective stabilizer system comprising a phosphate component selected from specifically defined mono- and diesters of orthophosphoric acid as the first component and an imide or oxazoline containing compound as the second component,
25 which system retards transesterification in polyesters and in polymer blends containing polyesters even at higher working temperatures (i.e., 285°C and above). Use of this stabilizer system in polyester containing polymer
30 blends allows them to be processed at higher temperatures without any deterioration in properties. The stabilizer system may further comprise a hindered phenol as a third component which provides thermal stability to the blend and is particularly useful at processing temperatures
35 above about 300°C.

Description of the Invention

A stabilizer system is disclosed which is useful
5 to retard transesterification in compositions comprising
polyester, particularly in moldable polymer blends
comprising polyester, wherein the stabilizer system
comprises:

- 10 (A) phosphate component selected from mono- and
di-esters of orthophosphoric acid;
- (B) reactive functionality component selected
from compounds having (1) imide or (2)
15 oxazoline functionality; and optionally,
- (C) hindered phenol component.

The phosphate component comprises at least about
20 51 weight percent of the stabilizer system. Preferably,
this component comprises between about 51 and about 75
weight percent of the stabilizer system. The reactive
functionality component is preferably selected from
carbodiimides and styrene polymers comprising oxazoline
25 functionality on their backbones.

According to another aspect of the invention,
the stabilizer system of this invention is useful to
retard transesterification of polyester containing
30 polymer blends during their processing at elevated
temperatures, particularly at temperatures above about
285°C. This invention is also directed to such
compositions comprising polyester, particularly polymer
blends comprising polyester, and the stabilizer system
35 described above. One embodiment of such compositions

comprises, in addition to the stabilizer system, a polymer blend of:

- 5 (I) aromatic component selected from the group consisting of: polysulfone, polyarylsulfone, polyether ketone, polyester ether ketone and polyarylate, wherein the polyarylate is the reaction product of at least one dihydric phenol and at least one aromatic dicarboxylic acid;
- 10
- (II) polyester being the reaction product of an aliphatic or cycloaliphatic diol, or mixtures thereof and at least one aromatic dicarboxylic acid; and
- 15
- (III) at least one thermoplastic polymer selected from the group consisting of an aromatic polycarbonate, a styrene resin, a vinyl chloride polymer, a
- 20 poly(arylether), a copolyetherester block copolymer, and a polyhydroxyether.

25 Preferably, at least (II) or (III) has the ability to crystallize upon cooling.

In addition to the stabilizer system in the composition comprising at least about 51 weight percent phosphate component, the above defined polymer blend

30 composition comprises at least about 0.1 weight percent phosphate component, at least about 0.01 weight percent reactive functionality component and, optionally, hindered phenol component. When a hindered phenol component is included as part of the stabilizer system in

35 the composition, the composition preferably comprises at

least about 0.01 weight percent hindered phenol component. The weight percent of each stabilizer system component is based on the weight of the polymer blend of the composition. Preferably the composition comprises a
5 blend of polyarylate, polyethylene terephthalate and polycarbonate.

Advantageously, the stabilizer system of this invention retards transesterification in polymer blends
10 comprising polyester which allows the blends to be desirably processed at temperatures above 285°C with substantially no change in physical properties. Since the polymer blend can be processed at higher temperatures, it may advantageously be composed of
15 polymers having higher molecular weights, which polymers generally also have more desirable physical properties, such as toughness and impact resistance. As pointed out above, such high molecular weight polymers have melt viscosities at normal processing temperatures which
20 preclude their use in most applications. While the phosphate component is somewhat useful by itself to retard transesterification of polyester blends at moderate temperatures up to about 280°C, the combination of the phosphate and the reactive functionality component
25 provides a stabilizer system which has unexpected stabilizing properties capable of preventing transesterification, even at temperatures higher than about 285°C, and even above about 300°C. At these higher temperatures, the phosphate stabilizer by itself is not
30 effective to prevent transesterification of polymer blends comprising polyester.

The stabilizer system of this invention retards transesterification of the polyester present in the
35 polymer blend during processing, i.e., melt-mixing and

molding, of the blend. Because transesterification is substantially prevented and the polyester present in the blend does not undergo any significant change in its structure during processing, it is now possible to

5 recycle in a second transformation, the polymer scrap produced by the first transformation. Moreover, the same mechanical and thermal properties can be obtained independent of the length of time the blend composition is maintained at the high temperature in the molding

10 apparatus, e.g., an extruder, which time can vary considerably depending on the type and size of the part being molded as well as the molding technique employed. Presently, in order to somewhat limit the deterioration of compositions comprising polyester, they are maintained

15 at elevated temperatures for relatively short periods of time. Incorporating the stabilizer system of this invention into polymer blends comprising polyester allows the composition to be processed at higher temperatures and for longer periods of time without any significant

20 change in the physical properties of the polymer blend, which has definite commercial advantages. For example, we have found that a polyarylate, polyethylene terephthalate, polycarbonate blend comprising an phosphate/carbodiimide/hindered phenol stabilizer system

25 has excellent thermal stability and can crystallize even after prolonged exposure to high temperatures, i.e., 30 minutes at 300°C. The same blend without the stabilizer system loses its individual glass transition temperature as well as crystallinity even after 10 minutes at 280°C.

30

Detailed Description of the Invention

The stabilizer system of this invention comprises at least two components: a phosphate component

35 and a reactive functionality component selected from

compounds having (1) imide or (2) oxazoline functionality. If the composition is to be molded at temperatures above about 300°C, it preferably also includes a hindered phenol component.

5

The phosphate component is selected from mono- and di-esters of orthophosphoric acids. As would be known to those skilled in the art, the mono- and di-ester have, respectively, two and one ionizable hydrogen atoms.

10 Particularly preferred of these mono- and di-esters are those which contain at least one phenyl group, since such compounds containing phenyl groups generally are relatively more stable at high temperatures. The phosphate component may be any such mono- or di-ester or
15 mixtures of any of them. Exemplary of such esters are diphenyl phosphate, dibenzyl phosphate, naphthol AS BI phosphate, with diphenyl phosphate being preferred for the polyarylate, polyethylene terephthalate, polycarbonate polymer blend described herein.

20

The second component of the stabilizer system of this invention comprises a compound having reactive functionality selected from imide and oxazoline. Such functionalities are capable of reacting with a hydroxyl
25 or carboxyl group. The second component comprises a compound (1) having one or more of such functionalities, (2) which is soluble in the polymer blend and (3) which has thermal stability at the processing temperatures of the blend. This compound may thus, for example, be
30 selected from carbodiimides such as benzene,2,4,-diisocyanate-1,3,5-tris(1-methyl-ethyl)-homopolymer, 2,2'-dimethyl-4,4'-dinitrodiphenyl-carbodiimide, 2,2',6,6'-tetrachloro-diphenylcarbodiimide, and 2,2'-dinitro-4,4'-dichloro-diphenylcarbodiimide. The
35 first named carbodiimide is preferred for use in the

preferred polymer blend comprising polyarylate, polyethylene terephthalate, and polycarbonate. Exemplary of compounds containing the oxazoline functionality are reactive polystyrene, i.e., polymeric styrene having
5 oxazoline functionality on its backbone, obtained from Dow Chemical Co., Midland, MI. The second component of the stabilizer system may also comprise mixtures of any of the various suitable compounds described above. Selection of still other materials useful as the second
10 component of this invention would be apparent to those skilled in the art in view of the present disclosure. Numerous such materials are known and many are commercially available.

15 The stabilizer system optionally comprises a hindered phenol. Numerous such materials are known and are commercially available, e.g., octadecyl-3,5-di-tert-butyl-4-hydroxy-hydrocinnamate, 1,3,5-tris(4-tert-butyl-3-hydroxy-2,6-dimethylbenzyl)-1,3,5-triazine-2,4,6-(1H,-
20 3H,5H)-trione, and 1,3,5-trimethyl-2,4,6-tris(3,5-di-tert-butyl-4-hydroxy-benzyl) benzene, the last one being preferred in the invention composition for use with the preferred polymer blend of polyarylate, polyethylene terephthalate and polycarbonate. The hindered phenol
25 component, when employed as a component in the stabilizer system, serves to improve the thermal stability of the polymer blend composition employing the stabilizer system. Incorporation of a hindered phenol component is particularly advantageous when the composition is to be
30 subjected to temperatures above about 300°C during processing, e.g., during the melt-mixing or molding of the blend.

The stabilizer system comprises a major weight
35 proportion, i.e., greater than about 51 weight percent,

of the phosphate component. Preferably, this component comprises between about 51 and about 75 weight percent of the stabilizer system.

5 This stabilizer system retards transesterification in extrudable compositions containing polyester during the processings of such compositions. In view of the present disclosure, it will be apparent to those skilled in the art that any composition containing
10 polyester could benefit from the incorporation of the stabilizer system of this invention therein, such compositions being numerous and varied. Exemplary of one embodiment of this type of composition, and one which particularly benefits from inclusion of the stabilizer
15 system since it is generally processed at the high temperatures which encourage transesterification, are those compositions comprising a polyester blend of:

20 (I) aromatic component selected from the group consisting of polysulfone, polyarylsulfone, polyether ketone, polyesterether ketone and polyarylate, wherein the polyarylate is the reaction product of at least one dihydric phenol and at least one aromatic dicarboxylic acid;

25 (II) polyester being the reaction product of an aliphatic or cycloaliphatic diol, or mixtures thereof, and at least one aromatic dicarboxylic acid; and
30

35 (III) at least one thermoplastic polymer selected from the group consisting of an aromatic polycarbonate, a styrene resin,

a vinyl chloride polymer, a poly(aryl ether), a copolyetherestic block copolymer, and a polyhexdroxy ether.

5 In such compositions, in addition to the phosphate component being in the major weight proportion as discussed above, the components of the stabilizer system are present in proportions so as to provide at least about 0.1 weight percent phosphate component, preferably
10 between about 0.1 and about 3 weight percent, more preferably between about 0.25 and about 0.75 weight percent of the phosphate component. Additionally, the stabilizer system comprises at least about 0.01 weight percent of the reactive functionality component,
15 preferably between about 0.01 and about 1 weight percent, more preferably between about 0.1 and about 0.5 weight percent of this second component. When a hindered phenol is employed in such compositions, the stabilizer system preferably comprises at least about 0.01 weight percent
20 of the hindered phenol component, preferably between about 0.1 and about 1 weight percent, more preferably between about 0.1 and about 0.5 weight percent of this optional component. The weight percent of each stabilizer system component is based on the weight of the
25 polymer blend of the composition.

The components of the stabilizer system may be combined to form the system in any suitable manner according to techniques known to those skilled in the
30 art. For example, the stabilizer system of this invention may be made by dry blending the stabilizer components into a powdered mixture which is then available to be dusted into the polymer blend prior to loading the composition into the melt-mixing apparatus.
35 The order of combination of the components of the

stabilizer system is not critical. Alternately, the stabilizer system components can be added individually into the composition blend or pre-compounded with one of the polymer blend components. The stabilizer can also be
5 metered into the polymer blend composition as it is being melt-mixed in the appropriate apparatus, e.g., into an extruder barrel downstream port.

Component I

10

Polysulfones that may be employed in the practice of the present invention are high molecular weight polymers containing sulfone groups. The polyarylsulfones additionally contain aromatic nuclei in
15 the main polymer chain. Polysulfones and polyarylsulfones are rigid, strong thermoplastic materials that can be molded, extruded, and thermoformed into a variety of shapes. They are highly resistant to chemicals, heat, oxidation and hydrolysis. Numerous such
20 materials are known to those skilled in the art and many are commercially available. For example, the Amoco Corporation manufactures and sells polysulfones under the trademark Udel. The polyarylsulfones which may be suitably employed in the practice of this invention are
25 commercially available from various sources, including Amoco which markets a product under the trademark UDEL polysulfone and from I.C.I. U.S. Inc. which markets such materials in various grades having different performance characteristics.

30

Polyether ketones and polyesterether ketones useful in the present invention as the aromatic component may be selected from any of numerous known materials of these types. Such materials are commercially available
35 from I. C. I. U.S. Inc. under the trademark Victrex.

The polyarylates suitable for use herein are derived from a dihydric phenol and an aromatic dicarboxylic acid. Exemplary of polyarylates are those made by reaction of bisphenol-A and aromatic dicarboxylic acids such as terephthalic acid, isophthalic acid, naphthalene dicarboxylic acid as well as mixtures thereof. The polyarylates of the present invention can be prepared by any of the well known prior art polyester forming reactions, such as the reaction of the acid chlorides of the aromatic dicarboxylic acid with the dihydric phenol, the reaction of the diaryl ester of the aromatic dicarboxylic acids with the dihydric phenols, and the reaction of the aromatic diacids with diester derivatives of the dihydric phenol. These processes are described, for example, in U.S. Pat. Nos. 3,317,464, 3,948,856, 3,780,148, 3,842,213.

Component II

The polyesters of the extrudable composition described herein are derived from an aliphatic or cycloaliphatic diol, or mixtures thereof, containing from 2 to about 10 carbon atoms and at least one aromatic dicarboxylic acid. The polyesters as described herein can be produced by methods well known in the art. Numerous such polyester are known to those skilled in the art and many are commercially available. The preferred dicarboxylic acid employed to make the polyester is terephthalic acid or mixtures of terephthalic and isophthalic acid. The preferred polyesters are poly(1,4-cyclohexanedimethanol tere/iso/-phthalate) and a copolyester of 1,4-cyclohexanedimethanol, ethylene glycol and terephthalic acid and poly(ethylene terephthalate). The polyester component may also comprise in minor

amounts, from about 0.5 to about 2 percent by weight, of the reaction product of aliphatic acids and/or aliphatic polyols, to form copolyesters. The aliphatic polyols include glycols such as poly(ethylene glycol).

- 5 Copolyesters are those derived from aliphatic dicarboxylic acids including cycloaliphatic straight and branched chain acids. In addition, there can be minor amounts of units derived from aliphatic glycols and polyols.

10

Component III

The thermoplastic polymers suitable for use in this invention are selected from the group consisting of
15 an aromatic polycarbonate, a styrene resin, an alkyl acrylate resin, a vinyl chloride polymer, a poly(aryl ether), a copolyetherester block polymer, a polyhydroxyether, or mixtures thereof.

20

Polycarbonate

- The thermoplastic aromatic polycarbonates that can be employed herein are homopolymers and copolymers and mixtures thereof which have an intrinsic viscosity of
25 0.40 to 1.0 dl./g. as measured in methylene chloride at 25°C that are prepared by reacting a dihydric phenol with a carbonate precursor. The polycarbonates can be prepared by methods well known to those skilled in the art. Typical of some of the dihydric phenols that may be
30 employed in the practice of this invention are bisphenol-A (2,2-bis(4-hydroxyphenyl) propane), bis(4-hydroxyphenyl) methane, 2,2-bis(4-dydroxy-3-methylphenyl) propane, 4,4-bis(4-hydroxyphenyl) heptane, 2,2-(3,5,3',5'-tetrachloro-4,4'-
35 dihydroxydiphenyl) propane, 2,2-(3,5,5',5'-tetrabromo-

4,4'-dihydroxydiphenyl)-propane, (3,3'-dichloro-4,4'-dihydroxydiphenyl) methane. It is of course, possible to employ two or more different dihydric phenols or a copolymer of a dihydric phenol with a glycol or with hydroxy or acid terminated polyester, or with a dibasic acid in the event a carbonate copolymer or inter-polymer rather than a homopolymer is desired for use in the preparation of the aromatic carbonate polymers of this invention.

10

The carbonate precursor may be either a carbonyl halide, a carbonate ester or a haloformate. Typical of the carbonate esters which may be employed herein are diphenyl carbonate, di-(halophenyl) carbonates, and di-(alkylphenyl) carbonates. The haloformates suitable for use herein include bis-haloformates of dihydric phenols or glycols. While other carbonate precursors will occur to those skilled in the art, carbonyl chloride, also known as phosgene, is preferred.

20

Styrene Resin

The styrene resins suitable for use herein are ABS type polymers, the molecules of which consist of two or more polymeric parts of different compositions that are bonded chemically. The polymer is preferably prepared by polymerizing a conjugated diene such as butadiene or a conjugated diene with a monomer copolymerizable therewith such as styrene to provide a polymeric backbone. After formation of the backbone, at least one grafting monomer and preferably two are polymerized in the presence of the prepolymerized backbone to obtain the graft polymer.

35

The backbone polymer, as mentioned, is preferably a conjugated diene polymer such as polybutadiene polyisoprene, or a copolymer such as butadiene styrene, butadiene-acrylonitrile, or the like.

5 Exemplary of the monomers generally utilized in preparing the backbone of the polymer are butadiene; isoprene; 1,3-heptadiene; methyl-1,3-pentadiene; 2,3-dimethyl-1,3-butadiene; 1,3-pentadiene; 2-methyl-3-ethyl-1,3-butadiene; 2-ethyl-1,3-pentadiene; 10 1,3- and 2,4-hexadienes, chloro and bromo substituted butadienes such as dichlorobutadiene, bromobutadiene, dibromobutadiene, mixtures thereof, and the like. The preferred conjugated diene utilized herein is butadiene.

15 One group of monomers that may be polymerized in the presence of the prepolymerized backbone are preferably monovinylaromatic hydrocarbons. Examples of the monovinylaromatic compounds and substituted monovinylaromatic compounds that may be used are styrene 20 and other vinyl substituted aromatic compounds including alkyl-, cycloalkyl-, aryl-, alkaryl-, aralkyl-, alkoxy-, aryloxy-, and other substituted vinylaromatic compounds. The preferred monovinylaromatic hydrocarbons used herein are styrene and/or *o*-methylstyrene.

25 A second group of monomers that may be polymerized in the presence of the prepolymerized backbone are acrylonitrile, substituted acrylonitrile and/or acrylic acid esters exemplified by acrylonitrile 30 and alkyl acrylates such as methyl methacrylate. The preferred acrylic monomer used herein is acrylonitrile and the preferred acrylic acid esters are ethyl acrylate and methyl methacrylate.

In the preparation of the graft polymer, the conjugated diolefin polymer or copolymer exemplified by 1,3-butadiene polymer or copolymer comprises from about 50% by weight to about 5% by weight of the total graft polymer composition and the monomers polymerized in the presence of the backbone exemplified by styrene and acrylonitrile comprise from about 40 to about 95% by weight of the total graft polymer composition.

The second group of grafting monomers, exemplified by acrylonitrile, ethyl acrylate or methyl methacrylate, of the graft polymer composition, preferably comprise from about 10% to about 40% by weight of the total graft copolymer composition and the monovinylaromatic hydrocarbon exemplified by styrene comprise from about 30 to about 70% by weight of the total graft polymer composition.

Optionally, the elastomeric backbone may be an acrylate rubber such as one based on n-butyl acrylate, ethylacrylate, 2-ethylhexylacrylate, and the like. Additionally, minor amounts of a diene may be copolymerized in the acrylate rubber backbone to yield improved grafting with the matrix polymer.

Alkyl Acrylate Resin

The alkyl acrylate resin useful in the present invention includes a homopolymer of methyl methacrylate (i.e., polymethyl methacrylate) or a copolymer of methyl methacrylate with a vinyl monomer (e.g., acrylonitrile, N-allylmaleimide, N-vinyl maleimide, or an alkyl acrylate or methacrylate in which the alkyl group contains from 1 to 8 carbon atoms such as methyl acrylate, ethyl acrylate, butyl acrylate, ethyl methacrylate and butyl

methacrylate). The amount of methyl methacrylate is not less than 70% by weight of this copolymer resin.

The alkyl acrylate resin may be grafted onto an unsaturated elastomeric backbone such as polybutadiene, polyisoprene, and/or butadiene or isoprene copolymers. In the case of the graft copolymer, the alkyl acrylate resin comprises greater than 50 weight percent of the graft copolymers.

Vinyl Chloride Polymers

Vinyl chloride polymers for the purpose of this invention are polyvinyl chloride and copolymers of vinyl chloride with olefinically unsaturated polymerisable compounds which contain at least 80 percent by weight of vinyl chloride incorporated therein. Olefinically unsaturated compounds which are suitable for copolymerization are, for example, vinylidene halides such as vinylidene chloride and vinylidene fluoride, vinyl esters such as vinyl acetate, vinyl propionate, vinyl butyrate, vinyl chloroacetate, vinyl benzoate, acrylic and α -alkyl-acrylic acids and their alkyl esters, amides and nitriles, methacrylic acid, methyl methacrylate, ethyl acrylate, 2-ethyl-hexylacrylate, butyl methacrylate, acrylamide, N-methyl acrylamide, acrylonitrile and methacrylonitrile, aromatic vinyl compounds such as styrene and vinyl naphthalene and olefinically unsaturated hydrocarbons such as ethylene, bicyclo-[2,2,1]-hepta-2-ene and bicyclo-[2,2,1]-hepta-2,5-dienes. These vinyl chloride polymers are known and can be prepared by the usual methods of emulsion, suspension, bulk or mass polymerisation. Vinyl chloride polymers which have molecular weights of 40,000 to 60,000 are preferred.


Poly(aryl ether)s

The poly(aryl ether) resin component of the
5 blend of this invention may be described as a linear,
thermoplastic polyarylene polyether polysulfone, wherein
the arylene units are interspersed with ether and sulfone
linkages. These resins may be obtained by reaction of an
alkali metal double salt of a dihydric phenol and a
10 dihalobenzenoid compound, either of both of which contain
a sulfone linkage $-SO_2-$ between arylene groupings to
provide sulfone units in the polymer chain in addition to
arylene units and ether units.


15 Typical examples are the reaction products
prepared from 2,2-bis-(4-hydroxyphenyl) propane with
4,4'-dichlorodiphenylsulfone and equivalent reaction
products such as those from 4,4'-dichlorodiphenylsulfone
with bisphenol of benzophenone (4,4'-dihydroxydiphenyl
20 ketone), or the bisphenol of acetophenone
[1,1-bis(4-hydroxyphenyl) ethane], or the bisphenol of
vinyl cyclohexane [1-ethyl-1-(hydroxyphenyl)-
3-(4-hydroxyphenyl)cyclohexane]], or
4,4'-dihydroxydiphenyl sulfone or alpha,
25 alpha'-bis(4-hydroxyphenyl)-p-diisopropylbenzene.

Copolyetherester Block Copolymer

The polyetheresters consist essentially of a
30 multiplicity of recurring intralinear long chain and
short chain ester units connected head-to-tail through
ester linkages, said long chain ester units being
represented by the following structure:



and said short chain ester units being represented by the
5 following structure



10 wherein: G is a divalent radical remaining after removal
of terminal hydroxy groups from a poly(alkylene oxide)
glycol having a molecular weight of about 400-3500: D is
a divalent radical remaining after removal of hydroxyl
groups from a low molecular weight diol having amolecular
15 weight less than about 250; and R₂ is a divalent
radical remaining after removal of carboxyl groups from a
dicarboxylic acid having a molecular weight less than
about 300; with the provisos that the short chain ester
units constitute about 25-65% by weight of the
20 copolyester, at least about 70% of the R₂ groups must
be 1,4-phenylene radicals, at least about 70% of the D
groups must be the 1,4-butylene radicals, and the sum of
the percentages of the R₂ groups which are not
1,4-phenylene radicals and of the D groups which are not
25 1,4-butylene radicals cannot exceed about 30%.

Included among the low molecular weight diols
(other than 1,4-butanediol) which react to form short
chain ester units are acyclic, alicyclic and aromatic
30 dihydroxy compounds.


Dicarboxylic acids (other than terephthalic
acid) which are reacted with the foregoing long chain
glycols or low molecular weight diols to produce the
35 copolyesters of this invention are aliphatic,

cycloaliphatic or aromatic dicarboxylic acids of a low molecular weight. The term "dicarboxylic acids" as used herein, includes acid equivalents of dicarboxylic acids having two functional carboxyl groups which perform
5 substantially like dicarboxylic acids in reaction with glycols and diols in forming copolyester polymers. These equivalents include esters and ester-forming derivatives, such as acid halides and anhydrides. The molecular weight requirement pertains to the acid and not to its
10 equivalent ester or ester-forming derivative. Aromatic dicarboxylic acids are a preferred class for preparing the copolyester polymers useful for compositions of this invention. Among the aromatic acids, those with 8-16 carbon atoms are preferred, particularly the phenylene
15 dicarboxylic acids, i.e., terephthalic and isophthalic acids.

The most preferred copolyesters of this invention are those prepared from dimethylterephthalate,
20 1,4-butanediol and poly(tetramethylene oxide) glycol having a molecular weight from about 600-1500.

Polyhydroxyether

25 The thermoplastic polyhydroxyethers in the present invention have the general formula



30 wherein D is the radical residuum of a dihydric phenol, E' is a radical residuum of an epoxide selected from mono- and diepoxides and contains from 1 to 2 hydroxyl groups and n is an integer which represents the degree of polymerization and is at least 30 and preferably is above
35 about 80.

In general, thermoplastic polyhydroxyethers are prepared by contacting under polymerization conditions a dihydric phenol and an epoxide containing from 1 to 2 epoxide groups in substantially equimolar amounts. These polyhydroxy ethers are prepared by methods well known in the art such as those detailed in, for example, U.S. Pat. Nos. 3,238,087; 3,305,528; 3,294,747, and 3,277,051.

U.S. patent 4,259,458 is hereby expressly incorporated herein by reference for its teachings relative the materials of Components I, II and III disclosed above.

In one embodiment of the extrudable composition blend employed with the stabilizer system of the present invention, the first component (I), which is preferably a polyarylate, is preferably used in amounts of from about 4 to about 80, more preferably from about 40 to about 60 weight percent. The second component (II), the polyester, is preferably used in amounts of from about 4 to about 60, more preferably from about 10 to about 45 weight percent. The thermoplastic polymer is preferably used in amounts of from about 10 to about 92, more preferably from about 10 to 60 weight percent.

The stabilizer system may be incorporated into the composition as described above, either before or during processing of the composition according to any of the known techniques. It should, of course, be apparent to those skilled in the art that other additives may be included in the present compositions. These additives include plasticizers; pigments; flame retardant additives; reinforcing agents, such as glass fibers; thermal stabilizers; ultraviolet light stabilizers

processing aids, impact modifiers and the like. Useful flame retardant materials include decabromodiphenyl ether and triarylphosphates, such as triphenylphosphate, and halogen monomer organic compounds such as

5 tetrafluoro-phthalic acid or tetrabromo-phthalic anhydride, bis-(di- or pentabromophenyl) oxide, these organic compounds eventually being associated with compounds with synergistic effect such as antimonium anhydride. Polymeric compounds especially, e.g., bromide

10 polystyrene and bromide polycarbonates are also suitable as flame retardants. The impact modifiers which can be used are described in U.S. Patent application Ser. No. 049,131 of L. M. Robeson, titled "Impact Modified Polyarylate Blends", filed June 18, 1979. These impact

15 modifiers are a graft copolymer of a vinyl aromatic, an acrylate, an unsaturated nitrile, or mixtures thereof, grafted onto an unsaturated elastomeric backbone and having a tensile modulus (as measured by ASTM D-638, except that the test piece is compression molded to a 20

20 mil thickness) of less than about 100,000 psi, and preferably from about 15,000 to less than about 100,000 psi.

The invention will be further understood by

25 referring to the following detailed examples. It should be understood that the specific examples are presented by way of illustration and not by way of limitation. Unless otherwise specified, "parts" is intended to mean "parts by weight".

30

The following tests are used to evaluate the blends made according to the examples herein.

Differential Scanning Calorimetry (DSC) is used to

35 evaluate the stability of the blends. The criteria for

stability are the retention of the crystalline heat of fusion and the melting point of the polyethylene terephthalate. The glass transition temperatures of polycarbonate and polyarylate may essentially be masked
5 by the cold crystallization exotherm of the polyethylene terephthalate. One evaluation scheme is designed as outlined in the following:

Isothermal Test

10

The sample is first rapidly scanned at a rate of 20°C/min. and then isothermally held at the maximum temperature for a specific period of time. The sample is then cooled to ambient
15 temperature and rescanned at a slower rate of 5°C/min. from 30°C to 280°C.

Example 1

20

The following ingredients are premixed and dried in a vacuum oven at 110°C:

	<u>Raw Materials</u>	<u>Parts by Weight</u>
25	Ardel ¹ (D-100)	50
	Calibre ² (300-15)	20
	Cleartuf ³ (1006B)	30

¹Trademark, Amoco Performance Products, Inc., Ridgefield, CT, polyarylate
30

²Trademark, Dow Chemical Co., Midland, MI, polycarbonate

³Trademark, Goodyear Tire and Rubber Co., Akron, OH, polyethylene terephthalate
35

The mixture is then charged into a Haake mini extruder and extruded to form a polyester blend. The maximum temperature setting for the extruder is 285°C. (The procedure of this example for making and extruding a polyester blend extrudate is also followed in the examples set forth below unless otherwise indicated therein.)

The heat of fusion (ΔH_f) of the extrudate is between 12-15 J/g and the melting point (T_m) is between 250°C and 255°C.

The result of a DSC isothermal test performed on samples of the extrudate after 10 min. at 300°C gives essentially no heat of fusion and reveals a glass transition temperature (T_g) at about 115-120°C which is a strong indication that an extensive ester exchange reaction takes place.

Example 2

The polyester blend comprising phosphate is prepared from the following:

	<u>Raw Materials</u>	<u>Parts by Weight</u>
	Ardol ¹ (D-100)	50
	Calibre ² (300-15)	20
	Cleartuf ³ (1006B)	30
	Diphenyl phosphate	0.5

¹Trademark, Amoco Performance Products,
Inc., Ridgefield, CT, polyarylate

²Trademark, Dow Chemical Co., Midland, MI,
polycarbonate

5 ³Trademark, Goodyear Tire and Rubber Co., Akron, OH,

³Trademark, Goodyear Chemicals, polyethylene
terephthalate

10 Samples of the polymer blend containing
phosphate (extruded at a maximum temperature of 290°C)
are subjected to DSC isothermal testing. The results are
listed below:

		<u>ΔH_f (J/g)</u>	<u>T_m (°C)</u>
15	Isothermal Test:		
	Original	11.2	251.7
	30 min./300°C	7.6	245.0

20 Example 3

A polyester blend containing carbodiimide is
prepared and extruded from the following ingredients:

25	<u>Raw Materials</u>	<u>Parts by Weight</u>
	Ardel (D-100) ¹	50.0
	Calibre (300-15) ²	20.0
	Cleartuf (1006B) ³	23.3
30	KE7646 ⁴	6.7

¹Trademark, Amoco Performance Products,
Inc., polyarylate

²Trademark, Dow Chemical Co., polycarbonate

³Trademark, Goodyear Chemicals, polyethylene
terephthalate

⁴KE7646 is a concentrate of polyethylene
terephthalate with 15% of Aromatic
polycarbodiimide (P-100) from
Mobay Chemical Co., Rhein-Chemie Div., Mogadove,
OH.

The maximum temperature setting for the extruder
is 280°C. The results of DSC isothermal tests performed
on samples of the extrudate of this example are shown in
the following:

<u>ΔH_f (J/g) Tm (°C)</u>			
Isothermal Test:	Original	12.3	247
	30 min./300°C	1.4	245

The substantial change of the heat of fusion
indicates that ester exchange reactions are taking place
in the extrudate. Thus, carbodiimide by itself is not
sufficient to inhibit such reactions in the polyester.

Example 4

A polyester blend containing a hindered phenol
is made and extruded from the following ingredients:

	<u>Raw Materials</u>	<u>Parts by Weight</u>
	Ardel (D-100) ¹	50
	Calibre (300-15) ²	20
5	Cleartuf-2% Ethanox 330 ³	30

¹Trademark, Amoco Performance Products,
Inc., polyarylate

²Trademark, Dow Chemical Co., polycarbonate

10 ³Manufactured by Goodyear Chemical Co.,
Ethanox 330 (trademark, Ethyl Corp., Baton Rouge,
LA.), antioxidant

15 The sample after being isothermally held at
280°C for 10 minutes gives no heat of fusion nor melting
point (i.e., no melting endotherm). This shows that a
hindered phenol by itself is not sufficient to suppress
ester exchange reactions.

20 Example 5

A polyester blend containing phosphate and
carbodiimide is extruded from the following ingredients:

	<u>Raw Materials</u>	<u>Parts by weight</u>
	Ardel (D-100) ¹	50.0
	Calibre (300-15) ²	20.0
	Cleartuf (1006B) ³	28.3
30	KE7646 ⁴	1.7
	Diphenyl phosphate	0.5

¹Trademark, Amoco Performance Products,
Inc., polyarylate

²Trademark, Dow Chemical Co., polycarbonate

³Trademark, Goodyear Chemicals,
polyethylene terephthalate

⁴KE7646 is a concentrate of polyethylene
terephthalate with 15% of Aromatic
polycarbodiimide (P-100) from
Mobay Chemical Co., Rhein-Chemie Div.,
Mogadove, OH

The maximum temperature setting of the extrudes
is 290°C. Samples of the extrudate are subjected to
isothermal testing and give the following result:

	<u>ΔH_f (J/g)</u>	<u>T_m (°C)</u>
15		
Isothermal Test:		
Original	16.0	256.2
30 min./300°C	14.0	249.0

20 From the above examples, it can be seen that the
incorporation of phosphate with carbodiimide at elevated
processing temperatures, i.e., above about 285 °C,
prevents transesterification and maintains the properties
of the blend.

25 In view of the disclosure, many modifications of
this invention will be apparent to those skilled in the
art. It is intended that all such modifications which
fall within the true scope of this invention be included
30 within the terms of the appended claims.

~~We claim~~

THE CLAIMS DEFINING THE INVENTION ARE AS FOLLOWS:

1. A stabilizer system useful to retard transesterification in moldable polymer blends comprising polyester, wherein the stabilizer system comprises:

- 5 (A) phosphate component selected from mono- and di-esters of orthophosphoric acid;
- (B) reactive functionality component selected from compounds having (1) imide or
- 10 (2) oxazoline functionality; and optionally,
- (C) hindered phenol component,

wherein said phosphate component comprises at

15 least about 51 weight percent of said stabilizer system.

2. The stabilizer system according to claim 1, wherein said phosphate component comprises between about 51 and about 75 weight percent of said stabilizer system.

3. The stabilizer system according to claim 1, wherein said phosphate component is selected from said mono- and di- esters containing at least one phenyl group per molecule.

4. The stabilizer system according to claim 1, wherein said reactive functionality component is selected from carbodiimides and polymeric styrene having oxazoline functionality on its backbone.

5. A composition comprising:

I. polyester; and

II. a stabilizer system comprising:

(A) phosphate component selected from mono- and di-esters of ortho-phosphoric acid;

(B) reactive functionality component having one reactive functionality capable of reacting with a hydroxyl or carboxyl group; and, optionally,

(C) hindered phenol component,

wherein said phosphate component comprises at least about 51 weight percent of said stabilizer system.

6. A moldable composition comprising a polymer blend comprising polyester and a stabilizer system useful to retard transesterification thereof:

the polymer blend comprising:

(I) aromatic component selected from the group consisting of: polysulfone, polyarylsulfone, polyether ketone, polyester ether ketone and polyarylate, wherein the polyarylate is the reaction product of at least one dihydric phenol and at least one aromatic dicarboxylic acid;

- 15 (XI) polyester being the reaction product of
 an aliphatic or cycloaliphatic diol, or
 mixtures thereof and at least one
 aromatic dicarboxylic acid; and
- 20 (III) at least one thermoplastic polymer
 selected from the group consisting of an
 aromatic polycarbonate, a styrene resin,
 a vinyl chloride polymer, a
25 poly(arylether), a copolyethester block
 copolymer, and a polyhydroxyether; and

the stabilizer system comprising:

- 30 (A) phosphate component selected from mono-
 and di-esters of orthophosphoric acid;
- (B) reactive functionality component having
 one reactive functionality capable of
 reacting with a hydroxyl or carboxyl
35 group; and, optionally,
- (C) hindered phenol component,

40 wherein said phosphate component comprises at least about
 51 weight percent of said stabilizer system and said (A)
 and (B) are present in said composition in amounts so as
 to provide at least about 0.1 weight percent phosphate
 component and at least about 0.01 weight percent reactive
45 functionality component, the weights percent of each
 stabilizer system component being based on the total
 weight of said polymer blend.

7. The composition according to claim 6, wherein said hindered phenol component is present in said composition in an amount of at least about 0.01 weight percent hindered phenol component.

8. The composition according to claim 6, wherein said composition comprises between about 0.1 and about 3 weight percent phosphate component, between about about 0.01 and about 1 weight percent reactive
5 functionality component and between about 0.01 and about 1 weight percent hindered phenol component, the weight percent of each stabilizer system component being based on the total weight of said polymer blend.

9. The composition according to claim 6, wherein said aromatic component (I) is present in amount between about 4 and 80 weight percent, said polyester component (II) is present in an amount between about 4
5 and about 60 weight percent and said thermoplastic component (III) is present in an amount between about 10 and 92 weight percent, the weight percent of each of said components (I), (II), and (III) being based on the total weight thereof.

10. The composition according to claim 6, wherein said aromatic component (I) is polyarylate, said polyester component (II) is polyethylene terephthalate, and said thermoplastic component (III) is polycarbonate.

11. The composition according to claim 10, wherein said stabilizer system comprises diphenyl phosphate, benzene, 2,4-diisocyanate-1,3,5-
5 tris(1-methylethyl)-homopolymer, and 1,3,5-trimethyl-2,4,6-di-tert-butyl-4-hydroxy benzyl) benzene.

12. The composition according to claim 6,
wherein at least said component (II) or (III) has the
ability to crystallize upon cooling.

DATED this 22nd day of December 1988.

FORD MOTOR COMPANY OF CANADA, LIMITED

EDWD. WATERS & SONS
PATENT ATTORNEYS
50 QUEEN STREET
MELBOURNE. VIC. 3000.