

(19)



(11)

EP 1 999 217 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention of the grant of the patent:
02.09.2009 Bulletin 2009/36

(51) Int Cl.:
C09D 7/00 (2006.01)

(21) Application number: **07727295.3**

(86) International application number:
PCT/EP2007/052821

(22) Date of filing: **23.03.2007**

(87) International publication number:
WO 2007/113145 (11.10.2007 Gazette 2007/41)

(54) **COATING COMPOSITION COMPRISING A REACTIVE DILUENT OF MALONATE**
 BESCHICHTUNGSZUSAMMENSETZUNG MIT REAKTIVVERDÜNNER AUS MALONAT
 COMPOSITION DE REVÊTEMENT COMPRENANT UN DILUANT RÉACTIF DE MALONATE

(84) Designated Contracting States:
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IS IT LI LT LU LV MC MT NL PL PT RO SE SI SK TR

- **LANSBERGEN, Adrianus, Jozefus, Hendricus NL-6862 WV Oosterbeek (NL)**
- **SPIERENBURG, Martin, Leonhard NL-2182 WJ Hilegom (NL)**
- **KLAASEN, Robert, Paul 1060 PW Amsterdam (NL)**

(30) Priority: **30.03.2006 EP 06111959**

(43) Date of publication of application:
10.12.2008 Bulletin 2008/50

(74) Representative: **Schalkwijk, Pieter Cornelis Akzo Nobel N.V. Intellectual Property Department P.O. Box 9300 6800 SB Arnhem (NL)**

(73) Proprietor: **Akzo Nobel Coatings International BV 6824 BM Arnhem (NL)**

- (72) Inventors:
- **MEIJER, Michel, Daniel NL-2321 JB Leiden (NL)**
 - **MES, Gijsbert, Pieter NL-6721 SP Bennekom (NL)**
 - **KELDERS, Hendrik, Philip NL-2465 BP Rijnsaterwoude (NL)**

(56) References cited:
EP-A- 0 653 468 US-A- 5 064 892

Remarks:

The file contains technical information submitted after the application was filed and not included in this specification

EP 1 999 217 B1

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

[0001] The present invention relates to a coating composition comprising a reactive diluent and an oxidatively crosslinkable binder system, such as an alkyd binder.

[0002] The present invention is defined by claims 1 to 10.

[0003] Oxidatively crosslinkable binders are binders which crosslink on exposure to oxygen. Examples of such binders are polymers which contain residues of aliphatic compounds, e.g., unsaturated fatty acid residues. The unsaturation in polymers from such fatty acid groups imparts latent crosslinkability, so that when a coating composition based on such a binder is exposed to air, the binder undergoes crosslinking, thereby improving the coating's properties such as hardness, durability, and chemical resistance. A particular advantage of coatings based on binders with unsaturated fatty acid residues is an improved glossy appearance.

[0004] Oxidatively crosslinkable binders can be polymers of any type, such as polyurethanes or acrylates, comprising unsaturated fatty acid groups. Typical examples of commonly used oxidatively crosslinkable binders are alkyds.

Alkyds are well-known binders of decorative paints curable under the influence of oxygen and can be prepared by esterification from polybasic acids or anhydrides, polyols, and fatty acids. Alkyd resins are generally used in coating compositions which ordinarily contain large amounts of solvents. Since solvents evaporate after application of the paint, they form an environmental and health problem.

[0005] To reduce the volatile content in solvent borne paints, it has been proposed to use reactive diluents. A feature of reactive diluents is that such diluents can copolymerize with the used binder system. This way reactive diluents can be used to replace part or all of the traditional solvents normally used in such formulations, thereby reducing emission of solvents on drying of the coating.

[0006] Reactive diluents usually are compounds or mixtures of compounds of relatively low viscosity and a relatively high boiling point which act as solvents during the formulation and processing of the coating. Reactive diluents for paint systems have been disclosed in, e.g., EP-A-0 357 128. The drawback of these reactive diluents is that they generate acrolein, a toxic volatile, as a side reaction of oxidative drying.

[0007] In WO 97/02230, WO 97/02226, and WO 98/00387 reactive diluents based on esters and ethers of 2,7-octadienol have been proposed. It was found that these induce severe yellowing and embrittlement upon aging of the paint film.

[0008] EP 0653468-A2 discloses coatings with a high acid-rain-resistance, containing one or more hydroxyfunctional (meth)acryl copolymers. US-5,064,892 discloses a resin composition based on a polymer and an ester of an unsaturated fatty acid and an alcohol containing a terminal unsaturation.

[0009] In non pre-published European patent application 07 727 296 (WO 2007/113146) a coating composition is described comprising an oxidatively drying binder and a reactive diluent which is at least partly an ester of a polyunsaturated alcohol and a compound comprising at least one carboxylic acid group, the ester being without chain-end double bonds.

[0010] The object of the invention is to find reactive diluents particularly useful for paints which do not form toxic volatiles with oxidative drying, result in good viscosity reduction, and do not affect properties like drying behaviour, hardness, yellowing, and durability.

[0011] The object of the invention is achieved by a reactive diluent which is at least partly an ester of malonic acid and an alcohol. The alcohol can for example be an unsaturated mono-alcohol, e.g., a polyunsaturated mono-alcohol. Preferably, these olefinic unsaturations are not present in the chain ends. Suitable mono-alcohols are geraniol, farnesol, citronellol, and nerol.

[0012] The reactive diluent may comprise a building block derived from an aldehyde coupled to the malonate backbone by a Knoevenagel reaction. A Knoevenagel reaction is a nucleophilic addition of an active hydrogen compound to a carbonyl group followed by a dehydration reaction in which a molecule of water is eliminated. In this reaction the carbonyl group is an aldehyde or a ketone. Usually a weakly basic amine is used as a catalyst. The aldehyde derived building block can, e.g., be selected from the group comprising citronellal, furfural, isobutyraldehyde, benzylaldehyde and cinnamaldehyde.

[0013] The reactive diluent may optionally be a polyester, e.g. a polymalonate, by using one or more polyol building blocks, such as diols or triols. Examples of suitable divalent polyols are ethylene glycol, 1,3-propane diol, 1,6-hexane diol, 1,12-dodecane diol, 3-methyl-1,5-pentane diol, 2,2,4-trimethyl-1,6-hexane diol, 2,2-dimethyl-1,3-propane diol, 2-ethyl-2-butyl-1,3-propane diol, cyclohexane-1,4-dimethanol, benzene-1,4-dimethanol, and hydrogenated bisphenol-A. Examples of suitable triols are glycerol, trimethylol ethane, and trimethylol propane. Linear diols will yield low-viscosity diluents, cyclic diols and triols will yield higher-viscosity diluents with higher hardness or better drying properties.

[0014] Typical oxidatively drying binders are alkyd resins. At least a part of the alkyd resin is oxidatively drying as a result of the incorporation of a large number of unsaturated, aliphatic compounds, at least a portion of which is polyunsaturated. The unsaturated aliphatic compounds preferably are unsaturated fatty acids, more particularly polyunsaturated fatty acids. Examples of fatty acids comprising one equivalent of unsaturated CC bonds are myristoleic acid, palmitoleic acid, oleic acid, gadoleic acid, erucic acid, and ricinoleic acid, and mixtures thereof. Examples of fatty acids comprising

two or more equivalents of unsaturated CC bonds include linoleic fatty acid, linolenic fatty acid, elaeostearic fatty acid, licanic fatty acid, arachidonic fatty acid, clupanodonic fatty acid, nisinic fatty acid, and mixtures thereof. Fatty acids containing conjugated double bonds, such as dehydrated castor oil fatty acid, wood oil fatty acid and/or calendula oil fatty acid, can be used as well. Fatty acids derived from soya oil are especially suitable.

[0015] Examples of suitable divalent polyol compounds are ethylene glycol, 1,3-propane diol, 1,6-hexane diol, 1,12-dodecane diol, 3-methyl-1,5-pentane diol, 2,2,4-trimethyl-1,6-hexane diol, 2,2-dimethyl-1,3-propane diol, and 2-methyl-2-cyclohexyl-1,3-propane diol. Examples of suitable triols are glycerol, trimethylol ethane, and trimethylol propane. Suitable polyols having more than 3 hydroxyl groups are pentaerythritol, sorbitol, and etherification products of the compounds in question, such as ditrimethylol propane and di-, tri-, and tetrapentaerythritol. Preferably, use is made of compounds having 3-12 carbon atoms, e.g., glycerol, pentaerythritol and/or dipentaerythritol.

[0016] Alternatively or additionally, polycarboxylic acids can be used as building blocks for the oxidatively drying polyunsaturated condensation products. Examples of suitable polycarboxylic acids include phthalic acid, citric acid, fumaric acid, mesaconic acid, maleic acid, citraconic acid, isophthalic acid, terephthalic acid, 5-tert. butyl isophthalic acid, trimellitic acid, pyromellitic acid, succinic acid, adipic acid, 2,2,4-trimethyl adipic acid, azelaic acid, sebacic acid, dimerized fatty acids, cyclopentane-1,2-dicarboxylic acid, cyclohexane-1,2-dicarboxylic acid, 4-methylcyclohexane-1,2-dicarboxylic acid, tetrahydrophthalic acid, endomethylene-cyclohexane-1,2-dicarboxylic acid, butane-1,2,3,4-tetracarboxylic acid, endoisopropylidene-cyclohexane-1,2-dicarboxylic acid, cyclohexane-1,2,4,5-tetracarboxylic acid, and butane-1,2,3,4-tetracarboxylic acid. If so desired, the carboxylic acids in question maybe used as anhydrides or in the form of an ester, e.g., an ester of an alcohol having 1-4 carbon atoms.

[0017] Optionally, the oxidatively drying polyunsaturated condensation product may comprise other building blocks, which can for example be derived from monocarboxylic acids such as pivalic acid, 2-ethylhexanoic acid, lauric acid, palmitic acid, stearic acid, 4-tert. butyl-benzoic acid, cyclopentane carboxylic acid, naphthenic acid, cyclohexane carboxylic acid, 2,4-dimethyl benzoic acid, 2-methyl benzoic acid, benzoic acid, 2,2-dimethylol propionic acid, tetrahydrobenzoic acid, and hydrogenated or non-hydrogenated abietic acid or its isomer. If so desired, the monocarboxylic acids in question may be used wholly or in part as triglyceride, e.g., as vegetable oil, in the preparation of the alkyd resin. If so desired, mixtures of two or more of such monocarboxylic acids or triglycerides may be employed.

[0018] Optionally, isocyanates may also be used as building blocks for the oxidatively drying polyunsaturated condensation product. Suitable isocyanates are for example diisocyanates, such as 1,6-hexane diisocyanate, isophorone diisocyanate, toluene diisocyanate, diphenyl diisocyanate, and dicyclohexylmethane diisocyanate. Triisocyanates can also be used.

[0019] The unsaturated groups in the oxidatively drying polyunsaturated condensation product are preferably introduced by the fatty acids, but may, alternatively or additionally, be introduced by one or more of the polyols, carboxylic acids or anhydrides or other building blocks used, such as fatty mono-alcohols.

[0020] The oxidatively drying polyunsaturated condensation product has pendant groups in an amount of more than 20%, preferably more than 50%, by weight of the condensation product. An amount of more than 65% is even more preferred.

[0021] A specific example of a suitable alkyd is the condensation product of soya oil, phthalic anhydride, and pentaerythritol.

[0022] The alkyd resins can be obtained by direct esterification of the constituent components, with the option of a portion of these components having been converted already into ester diols or polyester diols. Alternatively, the unsaturated fatty acids can be added in the form of a drying oil, such as sunflower oil, linseed oil, tuna fish oil, dehydrated castor oil, coconut oil, and dehydrated coconut oil. Transesterification with the polyols and, optionally, other building blocks will then give the final alkyd resin. This transesterification generally takes place at a temperature in the range of 115 to 250°C, optionally with solvents such as toluene and/or xylene also present. The reaction generally is carried out in the presence of a catalytic amount of a transesterification catalyst. Examples of transesterification catalysts suitable for use include acids such as p-toluene sulphonic acid, a basic compound such as an amine, or compounds such as calcium oxide, zinc oxide, tetraisopropyl orthotitanate, dibutyl tin oxide, and triphenyl benzyl phosphonium chloride.

[0023] Optionally, the oxidatively drying binder may be used in combination with other resins, for example acrylic resins or polyurethanes. Preferably, the coating composition comprises at least 20 wt.% of oxidatively drying binder, more preferably more than 60 wt.% of total binder.

[0024] The number average molecular weight Mw of the binder will generally be above 150. Preferably, it will be higher than 1,000, e.g. higher than 5,000. For reasons of viscosity, the number average molecular weight will generally be below 120,000, preferably below 80,000.

[0025] Alkyds are often characterized by their oil length. Oil length is defined as the weight percentage of fatty acid building blocks (calculated as their triglycerides) in the alkyd resin. Long oil lengths (55% or higher) result in improved oxidative drying, good substrate adhesion, excellent flow properties, good solubility in aliphatic solvents, and low viscosity, even with low solvent content. However, these alkyds show strong yellowing. Medium oil length alkyds (40 - 55%) also have good solubility but show a higher viscosity. Paint films made of medium oil length alkyds have better mechanical

properties such as hardness and durability. Short oil length alkyds (less than 40%) require additional measures, such as the use of additional siccatives or amino resins, to obtain acceptable drying times. The reactive diluents according to the present invention can be used with alkyds of any oil length.

[0026] To support the oxidatively drying mechanism, siccatives or driers can be used. Examples of suitable siccatives are metal salts of aliphatic acids, including cycloaliphatic acids, or aromatic acids, such as ethylhexanoic acid, octanoic acid, and naphthenic acid, where the metal is, for example, cobalt, manganese, lead, vanadium, iron, zirconium, calcium, copper, potassium, lithium, zinc, aluminium, magnesium, bismuth, or a rare earth metal. Alternatively, the siccative may be selected from metal oxide acetylacetonates, metal acetylacetonates, metal chlorides, metal sulphates, and metal alcoholates, where the metal is, for example, selected from the above-mentioned metals. Mixtures of siccatives can also be used. The siccatives (calculated as metal) are usually applied in an amount of 0.001 to 3 wt.%, calculated on the total binder solids content.

[0027] Besides these siccatives, the coating composition may optionally comprise drying-accelerating complexing agents, for example, 2,2'-bipyridyl and 1,10-phenantroline. The complexing agents can be added in an amount of 0 - 3 wt.%, e.g., 0.1 - 1.5 wt.%, based on the weight of the total binder.

[0028] The composition is particularly suitable for formulation as a solvent borne coating composition. The reactive diluents of the present invention can be used to reduce the volatile organic content (VOC) below 300 g/l, a so-called high solids composition (solids content more than about 60%). However, it is also suitable for conventional coating compositions with a higher solvent content. In this context, VOC is determined in accordance with US standard ASTM D 2369 (one hour at 110°C). Suitable solvents are for instance aromatic solvents such as toluene or xylene, as well as aliphatic solvents such as ethyl diglycol, ethyl glycol acetate, butyl glycol, butyl glycol acetate, butyl diglycol, butyl diglycol acetate, and methoxypropylene glycol acetate. Commercially available solvents are for instance Shellsol® D40, an aliphatic hydrocarbon solvent available from Shell, Dowanol® PMA from Dow, and Solvesso®-150, available from ExxonMobil.

[0029] Alternatively, the reactive diluents according to the invention can be formulated into air-drying water borne compositions by combining them with alkyd emulsions, optionally comprising co-solvents or humectants, such as glycols. Particularly useful for water borne compositions are reactive diluents with ionic and/or nonionic stabilizing groups built into their structure, e.g. by using diols containing carboxyl, sulfosuccinate or polyethylene glycol side groups.

[0030] The composition according to the invention can be used as a clear varnish or may contain pigments. Pigments can ordinarily include opacifying pigments, such as titanium dioxide, zinc oxide, leaded zinc oxide, titanium calcium, or tinting pigments, such as carbon black, yellow oxides, brown oxides, tan oxides, raw and burnt sienna or umber, chromium oxide green, phthalocyanine green, phthalonitrile blue, ultramarine blue, cadmium pigments or chromium pigments. Fillers can also be added, such as clay, silica, talc, and mica.

[0031] The coating composition can furthermore contain one or more additives such as UV stabilizers, cosolvents, dispersants, surfactants, inhibitors, fillers, antistatic agents, flame-retardant agents, lubricants, anti-foaming agents, extenders, plasticizers, anti-freezing agents, waxes, thickeners, thixotropic agents, etc. Furthermore, the coating composition according to the invention may optionally comprise various anti-oxidants and anti-skinning agents.

[0032] The invention is further illustrated by the following examples. In the examples, the following commercially obtained compounds are used:

Dowanol® PM	methoxypropanol, available from Dow;
Exkin® 2	anti-skinning agent (MEKoxim), available from Elementis
Kronos® 2310	titanium dioxide, a white pigment available from Kronos;
Nuodex® Combi APB	a siccative composition comprising metal driers (cobalt, zirconium and calcium), commercially available from Elementis
Shellsol® D40	an aliphatic hydrocarbon solvent supplied by Shell.

[0033] The following measuring methods were used:

- VOC (volatile organic content) was determined according to ASTM D2369 (1 hour at 110°C);
- Viscosity was determined on a Brookfield® CAP2000 cone and plate viscometer at 23°C;
- Nuclear Magnetic Resonance measurements were performed with a Bruker AC300 Nuclear Magnetic Resonance meter;
- Yellowing was determined as follows. A 30-micrometer dry film was applied on a glass plate. After 1 week's drying of the paint the L, a, b values of the paint (according to CIE lab, ASTM-E313) were determined with a MacbethColorEye® 7000A. Subsequently, these panels were placed in a dark 50°C oven for 175 hours and the L, a, b values were measured again. The difference in b-value, Δb , is denoted as the yellowing;
- The drying time was measured as follows. The coating composition was applied on a glass plate with a draw bar in a dry layer thickness of 30 μm . Curing took place at 10°C and 80% humidity in a climatized room under TL-055

EP 1 999 217 B1

light. Drying was tested by means of a BK drying recorder. The end of BK phase 3, which is reached when the coating is not damaged down to the substrate anymore, was recorded as the drying time;

- The nail hardness of the coating was tested by strongly scraping through the film using a pair of tweezers. The results were rated 0 (not acceptable) to 5 (excellent).

5

Example 1-11:

[0034] Reactive diluents were prepared by the following procedure:

10 Dimethylester of the alkylidenemalonate mentioned in table 1, unsaturated alcohol as mentioned in table 1, if applicable diol mentioned in table 1, and dibutyltin oxide (1500 ppm) were transferred into a flask fitted with stirrer, thermometer, nitrogen inlet and condenser. The mixture was put under nitrogen atmosphere and heated until 150°C. At 130°C the transesterification starts, so methanol is formed and distills off. The mixture is heated at 150°C during 20-24 hours. To remove the remaining free mono-alcohol, the flask is put under 20-40 mbar vacuum for an hour. 15 A small stream of nitrogen is passed through the flask. The conversion is determined by ¹H-NMR.

[0035] Dimethyl alkylidenemalonates were prepared according to the following procedure for Knoevenagel modification:

20 Dimethyl malonate (5 moles), aldehyde (5 moles), 530 g toluene, 2.8 g piperidine and 2.93 g propionic acid were mixed together in a flask fitted with stirrer, thermometer, nitrogen inlet and condenser, and heated until reflux. Via a Dean stark trap water was separated. Every 2 hours half of the starting amount of piperidine and propionic acid were added to the flask. After 20 hours 130 g toluene and 2 mole aldehyde were extra added. The reaction is finished when the theoretical amount of water is collected or when ¹H-NMR shows no remaining free methylene group of 25 the malonate. When the reaction is complete, part of the toluene is evaporated under vacuum. After cooling to room temperature, 300 g diethyl ether is added to the residue and the product is washed with water, once with 0.05 N HCl to remove piperidine, again with water, then with 4% Na₂CO₃ to remove propionic acid, next twice with water to neutralize. The organic phase is dried on MgSO₄ and the solvent is evaporated.

30

Table 1:

Example	Alcohol	Diol	Alkylidene
1	2,7-Octadienol 154 g	None	dimethylmalonate 80 g
2	2,7-Octadienol 108 g	None	Isobutylidene dimethylmalonate 83.7 g
3	2,7-Octadienol 62.4 g	None	Furylidene dimethylmalonate 52.9 g
4	2,7-Octadienol 126 g	None	Benzylidene dimethylmalonate 95 g
5	2,7-Octadienol 126 g	None	Cinnamylidene dimethylmalonate 120 g
6	2-Methoxy-3-butenol 108 g	None	Isobutylidene dimethylmalonate 82.6 g
7	Nerol 132 g	None	Isobutylidene dimethylmalonate 80 g
8	2-Hexenol 140.8 g	None	Isobutylidene dimethylmalonate 130.2 g
9	2,7-Octadienol 237.8 g	1,6-Hexanediol 167 g	dimethylmalonate 311 g
10	2,7-Octadienol 401.6 g	1,6-Hexanediol 80.3 g	dimethylmalonate 300 g
11	Nerol 256 g	1,6-Hexanediol 80.8 g	dimethylmalonate 200 g

Example 12:

[0036] A reactive diluent was obtained by Knoevenagel modification of malonate groups of resin obtained from example 9 according to the above procedure using isobutyraldehyde.

55

Example 13:

[0037] A reactive diluent was obtained by Knoevenagel modification of malonate groups of resin obtained from example 10 according to the above procedure using isobutyraldehyde.

Examples 14 and 15:

[0038] Reactive diluents were obtained by Knoevenagel modification of malonate groups of resin obtained from example 11 according to the above procedure using isobutyraldehyde (example 14) or anisaldehyde (example 15).

Paint compositions

[0039] The above mentioned reactive diluents were used in a paint composition comprising 422 wt parts solid binder (containing 70% alkyd A and 30% reactive diluent, or 100% Alkyd A for comparative example 1), 333 wt parts Kronos® 2310 (Titanium dioxide), 9.4 wt parts pigment dispersing agent, 31.5 wt parts Nuodex® Combi APB drier and 2.2 wt parts Exkin® 2 (MEKoxim). The paint was diluted with Shellsol® D40 to an application viscosity of 0.5 Pa.s. The paint properties of the first series of paints are shown in Table 2.

Comparative example 1:

[0040] A high solids alkyd paint was formulated without a reactive diluent. Alkyd A was a high solids alkyd consisting of partly conjugated linoleic, oleic and stearic fatty acids, with an oil content of 74% and a solids content of 89% in Shellsol D40, with a viscosity of 10 Pa.s at 23°C.

Comparative example 2:

[0041] A reactive diluent was made according to Example S1 of patent WO 97/02230. The reactive diluent was an ether-ester prepared of dimethyl maleate, 2,7-octadienol and zinc acetate catalyst. The resulting reactive diluent was added to a sample of the same paint composition as the reactive diluents of Examples 1 -13, as described above.

Table 2

	VOC (g/l)	Drying (hrs) BK phase 1-3	Yellowing Δb -value	Nail hardness (rating)	Durability Half-life (hrs)
Comp. Example 1	286	5.2	3.4	1.0	800
Comp. Example 2	163	6.6	5.9	2.0	500
Example 1	140	5.7	6.0	2.5	350
Example 2	150	5.9	5.3	2.5	510
Example 5	187	7.1	4.5	2	530
Example 6	165	5.8	3.3	2.5	760
Example 7	152	6.9	3.1	1.5	760
Example 8	149	6.5	2.8	2.0	470

[0042] A second series was tested. For a better comparison with the first series, Comparative Example 1 was tested again in this second series. The paint properties of a second series of paints are shown in Table 3.

Table 3

	VOC (g/l)	Drying (hrs) BK phase 1-3	Nail hardness (rating)	Durability Half-life (hrs)
Comp. Example 1	279	5.9	1.0	590
Example 10	156	7.0	2.5	290
Example 11	174	6.7	2.0	240
Example 12	190	5.1	2.0	310
Example 13	158	5.8	2.0	310
Example 14	174	5.5	1.5	185

Example 16:

[0043] A reactive diluent was produced by the procedure mentioned under example 1-11 using 155.3 g dimethyl isobutylidenemalonate, 52.3 g 1,3-propanediol and 35.2 g nerol. This material was modified by addition of sodium bisulfite onto the Knoevenagel double bonds as follows: Resin and 65.4 g sodium bisulfite were reacted at 95°C in a solvent mixture of 130 g water and 130 g methoxypropanol (Dowanol® PM). When all Knoevenagel double bonds had disappeared according to ¹H-NMR, solvents were removed by evaporation. This yielded a low viscosity diluent that dissolved completely in water at a solids content of 75%.

Claims

1. Coating composition comprising an oxidatively drying binder and a reactive diluent, **characterized in that** at least a part of the diluent is an ester of malonic acid and an alcohol.
2. Coating composition according to claim 1, **characterized in that** the diluent is an ester of malonic acid and an unsaturated mono-alcohol.
3. Coating composition according to claim 2, **characterized in that** the chain end of the mono-alcohol is free of unsaturated double bonds.
4. Coating composition according to claim 3, **characterized in that** the alcohol is selected from the group comprising geraniol, farnesol, citronellol and nerol.
5. Coating composition according to any one of the preceding claims, **characterized in that** the ester comprises more than one ester group and comprises diol building blocks.
6. Coating composition according to any one of the preceding claims, **characterized in that** it comprises a building block derived from an aldehyde coupled to the malonate backbone by a Knoevenagel reaction.
7. Coating composition according to claim 6, **characterized in that** the aldehyde-derived building block is selected from the group comprising citronellal, furfural, isobutyraldehyde, benzylaldehyde and cinnamaldehyde.
8. Coating composition according to any one of the preceding claims, **characterized in that** the binder is an alkyd.
9. Coating composition according to any one of the preceding claims, **characterized in that** the composition comprises one or more solvents.
10. Coating composition according to any one of the preceding claims, **characterized in that** the composition is a water borne composition.

Patentansprüche

1. Beschichtungszusammensetzung, die ein oxidativ trocknendes Bindemittel und ein reaktives Verdünnungsmittel umfasst, **dadurch gekennzeichnet, dass** wenigstens ein Teil des Verdünnungsmittels ein Ester von Malonsäure und einem Alkohol ist.
2. Beschichtungszusammensetzung gemäß Anspruch 1, **dadurch gekennzeichnet, dass** das Verdünnungsmittel ein Ester von Malonsäure und einem ungesättigten Monoalkohol ist.
3. Beschichtungszusammensetzung gemäß Anspruch 2, **dadurch gekennzeichnet, dass** das Kettenende des Monoalkohols frei von ungesättigten Doppelbindungen ist.
4. Beschichtungszusammensetzung gemäß Anspruch 3, **dadurch gekennzeichnet, dass** der Alkohol aus der Gruppe ausgewählt ist, die Geraniol, Farnesol, Citronellol und Nerol umfasst.
5. Beschichtungszusammensetzung gemäß einem der vorstehenden Ansprüche, **dadurch gekennzeichnet, dass**

EP 1 999 217 B1

der Ester mehr als eine Estergruppe umfasst und Diolbausteine umfasst.

- 5
6. Beschichtungszusammensetzung gemäß einem der vorstehenden Ansprüche, **dadurch gekennzeichnet, dass** sie einen von einem Aldehyd abgeleiteten Baustein umfasst, der durch eine Knoevenagel-Reaktion an das Malonatgerüst gekoppelt ist.
- 10
7. Beschichtungszusammensetzung gemäß Anspruch 6, **dadurch gekennzeichnet, dass** der von einem Aldehyd abgeleitete Baustein aus der Gruppe ausgewählt ist, die Citronellal, Furfural, Isobutyraldehyd, Benzaldehyd und Zimtaldehyd umfasst.
- 15
8. Beschichtungszusammensetzung gemäß einem der vorstehenden Ansprüche, **dadurch gekennzeichnet, dass** das Bindemittel ein Alkyd ist.
- 20
9. Beschichtungszusammensetzung gemäß einem der vorstehenden Ansprüche, **dadurch gekennzeichnet, dass** die Zusammensetzung ein oder mehrere Lösungsmittel umfasst.
10. Beschichtungszusammensetzung gemäß einem der vorstehenden Ansprüche, **dadurch gekennzeichnet, dass** die Zusammensetzung eine Zusammensetzung auf Wasserbasis ist.

Revendications

- 25
1. Composition de revêtement comprenant un liant de séchage par oxydation et un diluant réactif, **caractérisée en ce qu'**au moins une partie du diluant est un ester d'acide malonique et un alcool.
- 30
2. Composition de revêtement selon la revendication 1, **caractérisée en ce que** le diluant est un ester d'acide malonique et un mono-alcool insaturé.
- 35
3. Composition de revêtement selon la revendication 2, **caractérisé en ce que** l'extrémité de la chaîne du mono-alcool est dénuée de doubles liaisons insaturées.
- 40
4. Composition de revêtement selon la revendication 3, **caractérisée en ce que** l'alcool est choisi dans le groupe comprenant le géraniol, le farnésol, le citronellol et le nérol.
- 45
5. Composition de revêtement selon l'une quelconque des revendications précédentes, **caractérisée en ce que** l'ester comprend plusieurs groupes esters et comprend des blocs de construction diol.
- 50
6. Composition de revêtement selon l'une quelconque des revendications précédentes, **caractérisée en ce qu'**elle comprend un bloc de construction dérivé d'un aldéhyde raccordé à l'ossature de malonate par une réaction de Knoevenagel.
- 55
7. Composition de revêtement selon la revendication 6, **caractérisée en ce que** le bloc de construction dérivé d'un aldéhyde est choisi dans le groupe comprenant le citronellal, le furfural, l'isobutyraldéhyde, le benzylaldéhyde, et le cinnamaldéhyde.
8. Composition de revêtement selon l'une quelconque des revendications précédentes, **caractérisée en ce que** le liant est un alkyde.
9. Composition de revêtement selon l'une quelconque des revendications précédentes, **caractérisée en ce que** la composition comprend un ou plusieurs solvants.
10. Composition de revêtement selon l'une quelconque des revendications précédentes, **caractérisée en ce que** la composition est une composition en suspension dans l'eau.

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- EP 0357128 A [0006]
- WO 9702230 A [0007] [0041]
- WO 9702226 A [0007]
- WO 9800387 A [0007]
- EP 0653468 A2 [0008]
- US 5064892 A [0008]
- EP 07727296 A [0009]
- WO 2007113146 A [0009]