



US009293543B2

(12) **United States Patent**
Azumo et al.

(10) **Patent No.:** **US 9,293,543 B2**
(45) **Date of Patent:** **Mar. 22, 2016**

(54) **FILM FORMING METHOD AND FILM FORMING APPARATUS**

(71) Applicants: **TOKYO ELECTRON LIMITED**,
Tokyo (JP); **OSAKA UNIVERSITY**,
Osaka (JP)

(72) Inventors: **Shuji Azumo**, Ibaraki (JP); **Yusaku Kashiwagi**, Ibaraki (JP); **Yuichiro Morozumi**, Tokyo (JP); **Yu Wamura**, Iwate (JP); **Katsushige Harada**, Yamanashi (JP); **Kosuke Takahashi**, Iwate (JP); **Heiji Watanabe**, Osaka (JP); **Takayoshi Shimura**, Osaka (JP); **Takuji Hosoi**, Osaka (JP)

(73) Assignees: **TOKYO ELECTRON LIMITED**,
Tokyo (JP); **OSAKA UNIVERSITY**,
Osaka (JP)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 227 days.

(21) Appl. No.: **14/044,119**

(22) Filed: **Oct. 2, 2013**

(65) **Prior Publication Data**

US 2014/0094027 A1 Apr. 3, 2014

(30) **Foreign Application Priority Data**

Oct. 3, 2012 (JP) 2012-221662

(51) **Int. Cl.**
H01L 21/283 (2006.01)
H01L 21/441 (2006.01)

(Continued)

(52) **U.S. Cl.**
CPC **H01L 29/401** (2013.01); **C23C 16/303** (2013.01); **C23C 16/308** (2013.01); **H01L 21/022** (2013.01); **H01L 21/0228** (2013.01); **H01L 21/02178** (2013.01); **H01L 21/02252**

(2013.01); **H01L 21/02271** (2013.01); **H01L 21/02326** (2013.01); **H01L 21/02332** (2013.01); **H01L 21/044** (2013.01); **H01L 21/049** (2013.01); **H01L 21/28264** (2013.01); **H01L 29/513** (2013.01); **H01L 29/517** (2013.01); **H01L 29/518** (2013.01); **H01L 29/66045** (2013.01); **H01L 29/66068** (2013.01); **H01L 29/66712** (2013.01); **H01L 29/66734** (2013.01);

(Continued)

(58) **Field of Classification Search**
None
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

7,304,331 B2 * 12/2007 Saito H01L 29/1066
257/187
2002/0090773 A1 * 7/2002 Bojarczuk, Jr. ... H01L 21/28202
438/197
2006/0011915 A1 * 1/2006 Saito H01L 29/1066
257/65

OTHER PUBLICATIONS

Fujitsu Laboratories Ltd., "Development of Defect Control Technology of High Dielectric Constant Gate that Realizes High-Speed Transistor," press release 2002-0164, Jul. 1, 2002 (8 pages).

(Continued)

Primary Examiner — Zandra Smith


Assistant Examiner — Molly Reida

(74) *Attorney, Agent, or Firm* — Rothwell, Figg, Ernst & Manbeck, P.C.

(57) **ABSTRACT**

Provided is a method of forming a gate insulating film for use in a MOSFET for a power device. An AlN film is formed on a SiC substrate of a wafer W and then the formation of an AlO film and the formation of an AlN film on the formed AlO film are repeated, thereby forming an AlON film having a laminated structure in which AlO films and AlN films are alternately laminated. A heat treatment is performed on the AlON film having the laminated structure.

19 Claims, 10 Drawing Sheets



- (51) **Int. Cl.**
H01L 29/51 (2006.01)
H01L 29/40 (2006.01)
H01L 21/04 (2006.01)
H01L 21/28 (2006.01)
H01L 21/02 (2006.01)
C23C 16/30 (2006.01)
H01L 29/66 (2006.01)
H01L 29/78 (2006.01)
H01L 29/16 (2006.01)
H01L 29/20 (2006.01)

- (52) **U.S. Cl.**
CPC *H01L 29/7802* (2013.01); *H01L 29/7813*
(2013.01); *H01L 29/1602* (2013.01); *H01L*
29/1608 (2013.01); *H01L 29/2003* (2013.01)

(56) **References Cited**

OTHER PUBLICATIONS
K. Manabe, et al., "Suppression of Charges in Al₂O₃ Gate Dielectric and Improvement of MOSFET Performance by Plasma Nitridation," IEICE Trans. Electron., vol. E87-C, No. 1, Jan. 2004, pp. 30-36 (7 pages).

* cited by examiner

FIG. 1




FIG. 2




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8A




FIG. 8B




FIG. 8C



FIG. 8D




FIG. 8E




FIG. 8F




FIG. 9A



FIG. 9B




FIG. 9C



FIG. 9D




FIG. 9E




FIG. 9F




FIG. 10




FIG. 11





FIG. 12



FILM FORMING METHOD AND FILM FORMING APPARATUS

CROSS-REFERENCE TO RELATED APPLICATIONS

This application is based on and claims priority from Japanese Patent Application No. 2012-221662, filed on Oct. 3, 2012, with the Japan Patent Office, the disclosure of which is incorporated herein in its entirety by reference.

TECHNICAL FIELD

The present disclosure relates to a film forming method and a film forming apparatus that form an aluminum oxynitride (AION) film for use in a MOSFET (Metal Oxide Semiconductor Field Effect Transistor) as a gate insulating film.

BACKGROUND

A substrate formed of, for example, silicon carbide (SiC), gallium nitride (GaN) and diamond has recently been considered to be used in a power MOSFET device because this type of substrate is advantageous over silicon (Si) in terms of thermal conductivity, dielectric breakdown electric field strength, and electron saturation rate, enabling a high temperature operation of an element. As for a method of forming a gate insulating film of the power MOSFET device, it has been proposed to deposit a material capable of forming an insulating film on a substrate using a deposition method. As for the material to be deposited, a high-dielectric material is considered to be desirable and in particular, alumina (Al_2O_3) is attracting attention considering the physical property value such as, for example, a band gap.

Since Al_2O_3 has a plurality of electron traps, however, when the gate insulating film is formed of Al_2O_3 alone, a flat band voltage is shifted, thereby making a threshold voltage unstable. Thus, it has been proposed to eliminate the electron traps by adding nitrogen having valence electrons of which the number is intermediate between the number of valence electrons of the oxygen in the insulating film and the number of valence electrons of the silicon in the substrate. See, e.g., "Development of Defect Control Technology of High Dielectric Constant Gate That Realizes High-speed Transistor" released to the press by Fujitsu Laboratories (searched on Jul. 2, 2012) through online [Internet (URL:<http://pr.fujitsu.com/jp/news/2002/07/1.html>)]. In addition, when adding nitrogen by several at % to Al_2O_3 that forms a gate insulating film, a method of producing an AION film by nitriding Al_2O_3 by plasma is used. See, e.g., "K. Manabe, *IEICE TRANS. ELECTRON*, Vol. E87-C, No. 1, page 30, 2004".

SUMMARY

A film forming method according to the present disclosure is a method of forming a gate insulating film for use in a MOSFET for a power device. The film forming method includes forming an AlN film, forming an AIO film, and alternately and repeatedly performing the formation of the AlN film and the formation of the AIO film, thereby forming an AION film having a laminated structure in which AIO films and AlN films are alternately laminated.

The foregoing summary is illustrative only and is not intended to be in any way limiting. In addition to the illustrative aspects, embodiments, and features described above, fur-

ther aspects, embodiments, and features will become apparent by reference to the drawings and the following detailed description.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a cross-sectional view schematically illustrating a configuration of a film forming apparatus that performs a film forming method according to a first exemplary embodiment of the present disclosure.

FIG. 2 is a cross-sectional view schematically illustrating a configuration of a MOSFET which has a planar structure and uses an AION film formed by the first exemplary embodiment as a gate insulating film.

FIGS. 3A to 3F are process charts illustrating the film forming method according to the first exemplary embodiment.

FIG. 4 is a horizontal cross-sectional view schematically illustrating a configuration of a semi-batch type film forming apparatus that performs the film forming method according to the first exemplary embodiment.

FIG. 5 is a cross-sectional view schematically illustrating a configuration of a batch type film forming apparatus that performs the film forming method according to the first exemplary embodiment.

FIG. 6 is a cross-sectional view schematically illustrating a configuration of a MOSFET having a trench gate structure in which an AION film formed according to the film forming method according to the first exemplary embodiment is used as a gate insulating film.

FIG. 7 is an enlarged cross-sectional view illustrating a configuration of an AION film when respective AlN films are formed to have uneven thicknesses.

FIGS. 8A to 8F are process charts illustrating a film forming method according to a second exemplary embodiment of the present disclosure.

FIGS. 9A to 9F are process charts illustrating a film forming method according to a third exemplary embodiment of the present disclosure.

FIG. 10 is a horizontal cross-sectional view schematically illustrating a configuration of a modified example of the semi-batch type film forming apparatus of FIG. 4.

FIG. 11 is a graph illustrating flat band shifts of an Al_2O_3 film and AION film as gate insulating films.

FIG. 12 is a cross-sectional view illustrating a coating property over steps of an AION film in a trench structure.

DETAILED DESCRIPTION

In the following detailed description, reference is made to the accompanying drawing, which form a part hereof. The illustrative embodiments described in the detailed description, drawing, and claims are not meant to be limiting. Other embodiments may be utilized, and other changes may be made without departing from the spirit or scope of the subject matter presented here.

The thickness of a gate insulating film in a conventional MOSFET using a silicon substrate is several nm. Therefore, when an Al_2O_3 film which is a gate insulating film is nitrided by plasma, nitrogen may be sufficiently doped in the film thickness direction of the Al_2O_3 film so that an AION film in which nitrogen is uniformly diffused may be produced.

Since a gate insulating film in a power MOSFET has a thickness of at least 50 nm, preferably 100 nm in consideration of pressure-resistance, however, nitrogen is not sufficiently doped in the film thickness direction of the Al_2O_3 film which is the gate insulating film when nitridation is attempted

by plasma. As a result, an AION film in which nitrogen is uniformly diffused in the thickness direction may not be produced. When the AION film in which nitrogen is not uniformly diffused is also used as the gate insulating film, a desired flat band voltage or a threshold voltage may not be achieved.

The present disclosure is to provide a film forming method and a film forming apparatus capable of obtaining an AION film as an insulating film which has a suitably controlled nitrogen density and is pressure-resistant.

A method of forming a gate insulating film for use in a MOSFET for a power device according to an aspect of the present disclosure includes: forming an AlN film; forming an AIO film; and repeating the formation of the AlN film and the formation of the AIO film, thereby forming an AION film having a laminated structure in which AIO films and AlN films are alternately laminated.

In the film forming method, the film thickness of the AION film is 50 nm or more, and the AION film is formed on a substrate which includes any one of silicon carbonate, gallium nitride, and diamond.

In the film forming method, a heat treatment is performed on the AION film having the laminated structure. In addition, the AlN film formed at the very first among the AlN films is formed before the AIO film formed at the very first among the AIO films. Further, the formation of AlN film and/or the formation of AIO film are performed by ALD, CVD or PVD.

A method of forming a gate insulating film for use in a MOSFET for a power device according to another aspect of the present disclosure includes: forming an AlN film; oxidizing the AlN film after the AlN film is formed; and repeating the formation of the AlN film and the oxidation of the AlN film alternately, thereby forming an AION film having a laminated structure in which oxidized AlN films are laminated.

In the film forming method, the film thickness of the AION film is 50 nm or more, and the AION film is formed on a substrate which includes any one of silicon carbonate, gallium nitride, and diamond.

In the film forming method, a heat treatment is performed on the AION film having the laminated structure. In addition, the formation of AlN film is performed by ALD, CVD or PVD.

A film forming method of forming a gate insulating film for use in a MOSFET for a power device according to another aspect of the present invention includes: forming an AIO film; nitriding the AIO film after the AIO film is formed; and repeating the formation of the AIO film and the nitridation of the AIO film alternately, thereby forming an AION film having a laminated structure in which nitrided AIO films are laminated.

In the film forming method, the film thickness of the AION film is 50 nm or more, and the AION film is formed on a substrate which includes any one of silicon carbonate, gallium nitride, and diamond.

In the film forming method, a heat treatment is performed on the AION film having the laminated structure. In addition, the formation of AION film is performed by ALD, CVD or PVD.

A film forming apparatus according to still another aspect disclosure includes: a film forming unit configured to form an AlN film and an AIO film. The film forming unit repeats the formation of AlN film and the formation of AIO film, thereby forming an AION film having a laminated structure in which AIO films and AlN films are alternately laminated.

A film forming apparatus according to still another aspect of the present disclosure includes: a film forming unit configured to form an AlN film; and an oxidation unit configured

to oxidize the AlN film after the AlN film is formed. The film forming unit and the oxidation unit repeat the formation of the AlN film and the oxidation of the AlN film alternately, thereby forming an AION film having a laminated structure in which oxidized AlN films are laminated.

A film forming apparatus according to yet another aspect of the present disclosure includes: a film forming unit configured to form an AIO film; and a nitridation unit configured to nitride the AIO film after the AIO film is formed. The film forming unit and the nitridation unit repeat the formation of AIO film and the nitridation of the AIO film, thereby forming an AION film having a laminated structure in which nitrided AIO films are laminated.

According to the present disclosure, an AION film as an insulating film which has a suitably controlled nitrogen density and is pressure-resistant may be obtained.

Hereinafter, exemplary embodiments of the present disclosure will be described with reference to accompanying drawings.

First, the film forming method according to the first exemplary embodiment of the present disclosure will be described.

FIG. 1 is a cross-sectional view schematically illustrating a configuration of a film forming apparatus that performs the film forming method according to the first exemplary embodiment of the present disclosure. The film forming apparatus forms an AION film as a gate insulating film on a semiconductor wafer ("wafer") as a substrate.

Referring to FIG. 1, the film forming apparatus 10 includes a chamber 11 having, for example, a cylindrical shape, a placing table 12 disposed on the bottom portion within the chamber 11, a gas introduction section 13 configured to introduce a processing gas into the chamber 11, an exhausting section 14 configured to exhaust the inside of the chamber 11, and a gate (not illustrated) configured to allow the inside and outside of the chamber 11 to communicate with each other.

The inside of the chamber 11 is isolated from the external atmosphere when a film forming process using ALD (Atomic Layer Deposition) is performed for wafers W in a semi-batch method within the chamber 11. The ALD will be described later. The placing table 12 has a heater 15 incorporated therein and a plurality of wafers W are placed on the placing table 12. The plurality of wafers W placed on the placing table 12 are heated simultaneously. In addition, the placing table 12 may be equipped with a chiller to cool the plurality of wafers W placed thereon and the plurality of wafers W may be placed in a single wafer processing type.

The gas introduction section 13 is configured by three gas introduction tubes 13a, 13b, 13c in which the gas introduction tube 13a introduces an aluminum source such as, for example, TMA (trimethylaluminum), the gas introduction tube 13b introduces an oxygen source such as, for example, ozone (O₃), and the gas introduction tube 13c introduces a nitrogen source such as, for example, ammonia (NH₃). The operation of each of the constituent elements of the film forming apparatus 10 is controlled by a controller 10a.

The film forming apparatus 10 forms an AIO film (e.g., Al₂O₃ film) or an AlN film on a wafer W by ALD. For example, when forming an Al₂O₃ film, TMA is introduced from the gas introduction tube 13a first so as to cause respective TMA molecules to be physically adsorbed to the film formed on a surface of the wafer W or the wafer W, and excess TMA molecules (the TMA molecules which are not adsorbed to, for example, the wafer W) are discharged to the outside of the chamber 11 by the exhausting section 14, thereby forming a TMA molecule layer in which a plurality of molecules do not overlap in the thickness direction (i.e., a single layer). Then, O₃ is introduced from the gas introduction tube 13b and

the wafer W is heated by the heater 15 so as to cause O₃ to chemically react with the TMA molecule layer, thereby producing an Al₂O₃ film while discharging the excess O₃ or a by-product to the outside of the chamber 11. In addition, for example, when forming an AlN film, TMA is introduced from the gas introduction tube 13a first so as to cause respective TMA molecules to be physically adsorbed and the excess TMA molecules are discharged to the outside of the chamber 11 by the exhausting section 14, thereby forming one TMA molecule layer. Then, NH₃ is introduced from the gas introduction tube 13c and furthermore, the wafer W is heated so as to cause NH₃ to chemically react with the TMA molecule layer, thereby producing an AlN film while discharging the excess NH₃ or a by-product to the outside of the chamber 11. That is, the film forming apparatus 10 may form an Al₂O₃ film or an AlN film. Meanwhile, the discharge of excess gas (e.g., O₃ or NH₃) or the by-product may also be performed by purging an inert gas such as, for example, N₂ into the chamber 11.

In addition, in order to obtain a film of a high quality by suppressing crystal defects, it is required to manage a dew point of TMA and, for example, the gas introduction tube 13a is provided with a purifier 13g configured to remove moisture. Further, in order to quickly switch processing gasses as being introduced for the purpose of enhancing throughput, the gas introduction tubes 13a, 13b, 13c are provided with valves 13d, 13e, 13f, respectively, which are disposed adjacent to the chamber 11. Thus, the volume from the inside of the chamber 11 to each of the valves 13d, 13e, 13f is reduced as much as possible so that, for example, when the processing gases are switched from TMA to O₃, the amount of TMA remaining between the inside of the chamber 11 and the valve 13d may be reduced as much as possible. Consequently, the switching of processing gases may be quickly performed.

FIG. 2 is a cross-sectional view schematically illustrating a configuration of a MOSFET having a planar structure in which an AlON film formed by the film forming method according to the present exemplary embodiment.

Referring to FIG. 2, the MOSFET 16 includes: an n-type SiC portion 18 formed at a lower portion on a SiC substrate 17 that configures a wafer W and partially exposed on a surface of the SiC substrate 17; a second n-type SiC portion 19 formed at an upper portion and exposed on the surface of the SiC substrate 17, in which the second n-type SiC portion 19 is not entangled with the first n-type SiC portion 18; a p-type SiC portion 20 interposed between the first n-type SiC portion 18 and the second SiC portion 19 and partially exposed on the surface of the SiC substrate 17; and a gate insulating film 21 formed on the surface of the SiC substrate 17. Since the gate insulating film 21 is formed in a flat plate shape to cover the entire exposed portion of the first n-type SiC portion 18, the entire exposed portion of the p-type SiC portion 20, and a portion of the exposed portion of the second n-type SiC portion 19 on the surface of the SiC substrate 17, the gate insulating film 21 may be easily formed by laminating a plurality of films as in the film forming method according to the present exemplary embodiment as described below.

Meanwhile, there is no need for forming the SiC substrate 17 only by pure SiC and the SiC substrate 17 may be doped with impurities. In addition, the substrate that configures the wafer W is not limited to the SiC substrate 17 and may be, for example, a substrate made of gallium nitride (GaN) or diamond.

FIGS. 3A to 3E are process charts illustrating the film forming method according to the present exemplary embodiment.

In the film forming apparatus 10 or any other heat treatment apparatus, for example, a heat treatment furnace provided with a lamp heater (FIG. 3A), a thin silicon oxide (SiO₂) film 22 is formed on a surface of an SiC substrate 17, then one TMA molecule layer is formed on the surface of the SiC substrate 17 by the introduction of TMA from the gas introduction tube 13a and the subsequent exhaust of the inside of the chamber 11 and then, an AlN film 23 is formed by the introduction of NH₃ from the gas introduction tube 13c and the heating of the surface of the SiC substrate 17 (FIG. 3B) (first film forming step). In the film forming method according to the present exemplary embodiment, the formation of the AlN film 23 and the formation of the AlO film 24 are repeated as described below. The formation of the AlN film 23 which does not use an oxygen source such as, for example, O₃ is performed first. Thus, the oxidation of the surface of the SiC substrate 17 by oxygen atoms which pass through the thin SiO₂ film 22 may be suppressed. In addition, the thin SiO₂ film 22 is not essential, and when the thin SiO₂ film 22 is not formed, the thermal oxidation in the heat treatment furnace is not performed as well. Accordingly, the oxidation of the surface of the SiC substrate 17 may be suppressed more securely.

Subsequently, one TMA molecule layer is formed by the introduction of TMA from the gas introduction tube 13a and the subsequent exhaust of the inside of the chamber 11, then, an AlO film 24 is formed by the introduction of O₃ from the gas introduction tube 13b and the heating of the SiC substrate 17, and another AlN film 23 is formed on the formed AlO film 24 in the same manner as FIG. 3B (FIG. 3C) (second film forming step).

Subsequently, the formation of the AlO film 24 and the formation of the AlN film 23 are repeated, thereby forming an AlON film 25 having a laminated structure in which AlO films 24 and AlN films 23 are alternately laminated. The AlON film 25 has a film thickness of 30 nm to 150 nm, preferably not less than 50 nm (FIG. 3D).

Meanwhile, the formation of the AlN film 23 and the formation of the AlO film 24 do not necessarily have to be performed alternately. A laminated structure having a predetermined film thickness may be formed by repeating the formation of the AlN film 23 by a predetermined number of times first, and then, repeating the formation of AlO film 24 by a predetermined number of times. The film thickness of the AlO film 24 or the AlN film 23 formed at a time is 0.1 nm to 20 nm, preferably 1 nm to 5 nm in light of realizing a uniform film thickness. Further, the AlO film 24 or the AlN film 23 may be formed not only by ALD but also by CVD (Chemical Vapor Deposition). Especially, when the film thickness is large, they may be suitably formed by CVD.

For example, as an example, the formation of the AlN film 23 and the formation of the AlO film 24 may be alternately repeated by 24 times by setting the film thickness of the AlO film 24 formed at a time to 0.36 nm and the film thickness of the AlN film 23 formed at a time to 3 nm. As such, an AlON film 25 having a thickness of about 80 nm and containing nitrogen of about 20 at % may be formed.

Subsequently, a heat treatment (annealing processing) is performed on the AlON film 25 by heating the SiC substrate 17 formed with the AlON film 25 to a temperature in the range of, for example, 600° C. to 1100° C., in the film forming apparatus 10 or any other heat treatment apparatus (FIG. 3E). In addition, a conventional photo process is performed on the SiC substrate 17, then the SiC substrate 17 is carried-in into a plasma etching apparatus, and an unnecessary portion of the AlON film 25 is removed by, for example, a dry etching, thereby obtaining a gate insulating film 21 (FIG. 3F). Thereafter, the present process is finished. The interfaces of the AlO

films **24** and the AlN films **23** collapse by, for example, diffusion action of respective molecules in the annealing processing so that AIO molecules and AlN molecules are mixed up in the gate insulating film **21**.

The film forming method according to the exemplary embodiment as described above may be performed not only by the film forming apparatus **10** but also by a film forming apparatus having any other configuration.

FIG. **4** is a horizontal cross-sectional view schematically illustrating a configuration of a semi-batch type film forming apparatus that performs the film forming method according to the exemplary embodiment.

Referring to FIG. **4**, the film forming apparatus **26** includes: a chamber **27** having a cylindrical shape, a susceptor **28** having a disc shape and disposed within the chamber **27** to be rotated horizontally about the central axis of the chamber **27**, a gate **29** configured to cause the chamber **27** to communicate with the outside, a gas introduction tube **30a** configured to introduce TMA, a gas introduction tube **30b** configured to introduce O₃ and NH₃ into the chamber **27** in a switching manner, and two gas introduction tubes **30c** disposed between the gas introduction tubes **30a** and **30b** in the circumferential direction of the chamber **27**, respectively, and configured to introduce N₂ into the chamber **27**. The gas introduction tube **30a** is provided with a purifier **30e** in order to remove moisture.

The chamber **11** accommodates a plurality of, e.g. six flat boats **26a** which are arranged at an equal interval in the circumferential direction in the susceptor **28**. A plurality of wafers **W** are placed on each boat **26a** and each boat **26a** horizontally rotates about the central axis thereof. That is, each boat **26a** revolves around the central axis of the chamber **27** while rotating on its central axis, and the wafers **W** placed on each boat **26a** turns around the central axis of the chamber **27**. Each boat **26a** is carried-in/-out into/from the chamber **27** through the gate **29** by the arm **26c** disposed outside of the chamber **27**.

The susceptor **28** incorporates a heater (not illustrated) and heats each wafer **W** through each boat **26a**. Meanwhile, the susceptor **28** may also incorporate a chiller (not illustrated) so as to cool each wafer **W** through each boat **26a**.

In the film forming apparatus **26**, when an AlN film **23** is formed by ALD, TMA is introduced into the chamber **27** from the gas introduction tube **30a**, NH₃ is introduced into the chamber **27** through the gas introduction tube **30b**, and N₂ is introduced into the chamber **27** from each of the gas introduction tubes **30c**. The gas introduction tubes **30c** introduce N₂ between the gas introduction tubes **30a** and **30b**, respectively, so that the inside of the chamber **27** is divided into a TMA adsorption region P₁ in which respective TMA molecules are chemically adsorbed to, for example, a surface of each wafer **W** so as to form a TMA molecule layer and a film forming region P₂ in which NH₃ is chemically reacted with the TMA molecule layer so as to form an AlN film **23**. Since each wafer **W** sequentially passes through the TMA adsorption region P₁ and the film forming region P₂ while it turns around the central axis of the chamber **27**, an AlN film **23** is formed at each turn of the wafer **W**.

When forming an AIO film **24** by ALD, TMA is introduced into the chamber **27** from the gas introduction tube **30a**, O₃ is introduced into the chamber **27** from the gas introduction tube **30b**, and N₂ is introduced into the chamber **27** from each of the gas introduction tubes **30c**, thereby forming a TMA molecule layer in the TMA adsorption region P₁ and O₃ is chemically reacted with the TMA molecule layer, thereby forming an AIO film **24** in the film forming region P₂. Also in this case, since each wafer **W** sequentially passes through the TMA

adsorption region P₁ and the film forming region P₂ while the wafer turns around the central axis of the chamber **27**, an AIO film **24** is formed at each turn of the wafer. That is, in the film forming apparatus **26**, when O₃ and NH₃ introduced from the gas introduction tubes **30b** are switched, AIO films **24** and AlN films **23** may be alternately formed.

In addition, when a plurality of wafers **W** are placed on the boats **26a**, respectively, and each of the boats **26a** is revolved around the central axis of the chamber **27**, an AlN film **23** or an AIO film **24** may be formed on the plurality of wafers substantially simultaneously. Meanwhile, each of the constituent elements of the film forming apparatus **26** is controlled by the controller **26b**.

Also in the film forming apparatus **26**, the gas introduction tubes **30b** are placed adjacent to the film forming apparatus **26** so as to quickly switch the processing gases.

When the film forming method according to the present exemplary embodiment is performed using the film forming apparatus **26**, a thin SiO₂ film **22** is formed on a surface of a SiC substrate **17** in the film forming apparatus **26** or any other heat treatment apparatus (FIG. **3A**). Meanwhile, the SiO₂ film **22** is not essential and, when the SiO₂ film **22** is not formed, the oxidation of the surface of the SiC **17** may be suppressed.

Subsequently, in the film forming apparatus **26**, one TMA molecule layer is formed on the surface of the SiC substrate **17** by the introduction of TMA from the gas introduction tube **30a** and then, an AlN film **23** is formed by the introduction of NH₃ from the gas introduction tube **30c** and the heating of the SiC substrate **17** (FIG. **3B**) (first film forming step). Since the AlN film **23** is formed at first and thus, the thin SiO₂ film **22** is not exposed to an oxygen source, oxygen atoms may be suppressed from oxidizing the surface of the SiC substrate **17** by passing through the thin SiO₂ film **22**.

Subsequently, one TMA molecule layer is formed by the introduction of TMA from the gas introduction tube **30a** and then, an AIO film **24** is formed by the introduction of O₃ from the gas introduction tube **30b** and the heating of the SiC substrate **17**. Then, another AlN film **23** is formed on the formed AIO film **24** in the same manner as described above (FIG. **3C**) (second film forming step).

Subsequently, the formation of the AIO film **24** and the formation of the AlN film **23** are repeated, thereby forming an AION film **25** having a laminated structure in which AIO films **24** and AlN films **23** are alternately laminated (FIG. **3D**), and a heat treatment (annealing processing) is performed on the AION film **25** formed on the SiC substrate in the film forming apparatus **26** or any other heat treatment apparatus (FIG. **3E**). In addition, a photo process is conducted by a conventional method and then, an unnecessary portion of the AION film **25** is removed by, for example, a dry etching, thereby obtaining a gate insulating film **21** (FIG. **3F**). Also in this case, the interfaces of the AIO films **24** and the AlN films **23** collapse by, for example, the diffusion action of respective molecules in the annealing processing so that AIO molecules and AlN molecules are mixed up in the gate insulating film **21**.

In the film forming apparatus **26** of FIG. **4** as described above, any one of the AlN film **23** and the AIO film **24** is formed on each wafer at each turn of the wafer **W**. However, the film forming apparatus may be configured such that both the AlN film **23** and the AIO film are formed on each wafer **W** at each turn of the wafer **W** makes one turn. For example, as illustrated in FIG. **10**, in a film forming apparatus **40** having a configuration similar to that of the film forming apparatus **26**, a gas introduction tube **41a** configured to introduce N₂ into the chamber **27**, a gas introduction tube **41b** configured to introduce TMA into the chamber **27**, a gas introduction tube **41c** configured N₂ into the chamber **27**, a gas introduction

tube **41d** configured to introduce NH_3 into the chamber **27**, a gas introduction tube **41e** configured to introduce N_2 into the chamber **27**, a gas introduction tube **41f** configured to introduce TMA into the chamber **27**, a gas introduction tube **41g** configured to introduce N_2 into the chamber **27**, and a gas introduction tube **41h** configured to introduce O_3 into the chamber **27** may be arranged clockwise in the circumferential direction of the chamber **27**, thereby dividing the inside of the chamber **27** into a TMA adsorption region P_3 in which respective TMA molecules are chemically adsorbed to, for example, a surface of each wafer **W**, an AlN film forming region P_4 in which NH_3 is chemically reacted with the TMA molecule layer to form an AlN film **23**, a TMA adsorption region P_5 in which respective TMA molecules are chemically adsorbed to, for example, the surface of the wafer **W**, and an AlO film forming region P_6 in which O_3 is chemically reacted with the TMA molecule layer to form an AlO film **24**.

In the film forming apparatus **40**, whenever each wafer **W** makes a turn, the wafer **W** sequentially passes through the TMA adsorption region P_3 , the AlN film forming region P_4 , the TMA adsorption region P_5 , and the AlO film forming region P_6 . As a result, both the AlN film **23** and the AlO film **24** are formed on the wafer **W** whenever the wafer **W** makes a turn.

Also in the film forming apparatus **40**, the gas introduction tubes **41b**, **41f** configured to introduce TMA are provided with purifiers **41i**, **41j**, respectively.

In the film forming apparatus **26**, it is not required to form the AlN films **23** and the AlO films **24** alternately. While each wafer **W** is turned by a predetermined number of times, NH_3 may only be introduced from the gas introduction tube **30b** in several turns from the beginning, and then O_3 may only be introduced from the gas introduction tube **30b** in the subsequent several turns. Thus, in the several turns from the beginning, a laminated structure of a plurality of AlN films **23** is formed on each wafer **W** and in the subsequent several turns, a laminated structure of AlO films **24** is formed on each wafer **W**.

FIG. **5** is a cross-sectional view schematically illustrating a batch-type film forming apparatus according to the present exemplary embodiment.

In FIG. **5**, the film forming apparatus **31** includes a chamber **32** having a dual piping structure, a cover member **33** configured to close the lower end of the chamber **32**, a wafer board **34** configured to dispose a plurality of wafers **W** in multiple tiers, a rotation shaft **35** configured to support the lower end of the wafer board **34**, a gas introduction section **36** configured to introduce a processing gas into the chamber **32**, an exhausting section **37** configured to exhaust the inside of the chamber **32**, and a heater (not illustrated) configured to heat each of the wafers **W** disposed on the wafer board **34**.

The inside of the chamber **32** is isolated from the external atmosphere when the film forming processing is performed on each of the wafers in the inside thereof using ALD. The gas introduction section **36** is made up of three gas introduction tubes **36a**, **36b**, **36c** in which the gas introduction tube **36a** introduces TMA, the gas introduction tube **36b** introduces O_3 , and the gas introduction tube **36c** introduces NH_3 . The wafer board **34** is configured to be separable from the chamber **32** together with the rotation shaft **35** or the cover member **33**, and retreated downwardly from or introduced upwardly into the chamber **32**. The operation of each constituent element of the film forming apparatus **31** is controlled by the controller **31a**. Meanwhile, the gas introduction tube **36a** configured to introduce TMA is provided with a purifier **36g** so as to remove moisture.

In the film forming apparatus **31**, when forming an AlO film **24**, TMA is introduced from the gas introduction tube **36a** so that respective TMA molecules are physically adsorbed to, for example, a surface of each wafer **W**, excess TMA molecules are discharged to the outside of the chamber **32** by the exhausting section **37**, thereby forming one TMA molecule layer on the surface of each wafer **W** and then O_3 is introduced from gas introduction tube **36b** and the wafer **W** is heated by the heater so as to cause O_3 to chemically react with the TMA molecule layer, thereby producing Al_2O_3 while discharging excess O_3 or a by-product to the outside of the chamber **32**. When forming an AlN film **23**, TMA is introduced from the gas introduction tube **36a** so that respective TMA molecules are physically adsorbed to, for example, a surface of each wafer **W** and excess TMA molecules are discharged to the outside of the chamber **32** by the exhausting section **37**, thereby forming one TMA molecule layer on the surface of each wafer **W**. Then, NH_3 is introduced from the gas introduction tube **36c** and the wafers **W** are heated so as to cause NH_3 to chemically react with the TMA molecule layer, thereby producing an AlN film while discharging excess O_3 or a by-product to the outside of the chamber **32**. That is, the film forming apparatus **31** may simultaneously produce an Al_2O_3 film and an AlN film having a thickness of several nanometers on a plurality of wafers **W**.

Also in the film forming apparatus **31**, the gas introduction tubes **36a**, **36b**, **36c** are provided with valves **36d**, **36e**, **36f**, respectively. The valves **36d**, **36e**, **36f** are disposed adjacent to the chamber **32** so as to ensure quick switching of processing gases. Since the sequence of performing the film forming method according to the present exemplary embodiment using the film forming apparatus **31** is substantially same as the sequence of performing the film forming method using the film forming apparatus **10**, the descriptions thereof will be omitted.

With the film forming method according to the present exemplary embodiment, a foil led AlON film **25** has a laminated structure in which AlO films **24** and AlN films **23** are alternately layered. Thus, the AlN films **23** are substantially equally disposed in the thickness direction of the AlON film **25**. In addition, since a heat treatment is performed on the AlON film **25** having the laminated structure, the laminated structure is eliminated by being annealed so that nitrogen contained in each of the AlN films **23** is diffused within the AlON film **25**. As a result, even if the film thickness of the AlON film **25** is thick, nitrogen may be substantially uniformly diffused in the thickness direction. That is, an AlON film **25** which has a suitably controlled nitrogen density and is pressure-resistant may be obtained.

In the film forming methods according to the present exemplary embodiment described above, the content of nitrogen of the AlON film **25** be controlled within a range of about 1% to about 40% by adjusting the pressure of the chamber **11**(**27**, **32**) and/or the temperature of wafers **W** and furthermore, by adjusting the length of time for exposing the SiC wafers **17** to NH_3 and/or O_3 .

In addition, in the film forming method according to the present exemplary described above, the thin SiO_2 film **22** is formed on a surface of a SiC substrate **17** prior to forming the AlON film **25**. However, the AlN film **23** may be formed directly on the surface of the SiC substrate **17** without forming the SiO_2 film **22**.

In the film forming method according to the present exemplary embodiment as described above, a SiC substrate **17** is heated so as to cause TMA to chemically react with NH_3 or O_3 . However, plasma may be produced from NH_3 or O_3 within the chamber **11**(**27**, **32**) or plasma of NH_3 or O_3 may be

11

introduced into the chamber **11(27, 32)** so as to cause the plasma to chemically react with TMA.

Meanwhile, in the film forming method according to the present exemplary embodiment as described above, TMA is used as an aluminum source. However, other aluminum sources such as, for example, triethylaluminum, may be used. In addition, although O₃ is used as an oxygen source in the present exemplary embodiment, other oxygen sources such as, for example, oxygen, water, nitrous oxide, nitrogen oxide, carbon monoxide or carbon dioxide, may be used. Furthermore, NH₃ is used as a nitrogen source in the present exemplary embodiment, other nitrogen sources such as, for example, nitrogen, nitrous oxide or nitrogen oxide, may be used.

In the film forming method as described above, the thicknesses of respective AIO films **24** or the thicknesses of respective AlN films **23** may not equal to each other. For example, in the AION film **25**, when the concentration of nitrogen is increased only in an area adjacent to a surface of a SiC substrate **17**, as illustrated in FIG. 7, the AlN film **23** formed in the vicinity of the surface of the SiC substrate **17** has a thick film thickness and the film thicknesses of the AlN films **23** are reduced as the distance from the surface of the SiC substrate **17** increases.

Further, even if the AION film **25** as a gate insulating film **21** is formed in a trench **39** in a MOSFET **38** having a trench gate structure as illustrated in FIG. 6 using the film forming method as illustrated in FIGS. 3A to 3F, an AlN film **23** or an AIO film **24** may be formed in a substantially uniform film thickness along the inner surfaces of the trench **39** since ALD is excellent in coating property over steps. As a result, a homogeneous gate insulating film **21** may be produced. Since CVD is also relatively excellent in coating property over steps as compared with other film forming methods, the AlN film **23** or the AIO film **24** may also be formed in a substantially uniform film thickness along the inner surfaces of the trench **39** by CVD.

Although the film forming apparatuses **10, 26, 31** are used for forming an AlN film **23** or an AIO film **24** by ALD in the present exemplary embodiment as described above, the method of forming the AlN film **23** or the AIO film **24** is not limited to ALD and, for example, CVD or PVD (Physical Vapor Deposition) may also be used.

For example, when forming an AlN film **23** or an AIO film **24** by CVD in any of the film forming apparatuses **10(26, 31)** as described above, TMA is introduced into the chamber **11(27, 32)** in which a wafer **W** formed with a thin SiO₂ film **22** (SiC substrate **17**) is accommodated, NH₃ is introduced into the chamber **11(27, 32)** without exhausting the inside of the chamber **11(27, 32)**, and the SiC substrate **17** is heated to cause TMA and NH₃ to chemically react with each other on the SiC substrate **17**, thereby forming an AlN film **23**.

Subsequently, an AIO film **24** is formed through a chemical reaction by introducing TMA, introducing O₃ and heating the SiC substrate **17** and an AlN film **23** is also formed through a chemical reaction in the same method as the above-described method. When the AIO film **24** or the AlN film **23** is formed by CVD, another AIO film **24** or another AlN film **23** which is relatively thick (e.g., about 20 nm) may be formed.

Subsequently, the formation of the AIO film **24** and the formation of the AlN film **23** by CVD are repeated, thereby an AION film **25** having a laminated structure in which AIO films **24** and AlN films **23** are alternately laminated and a heat treatment (annealing processing) is performed on the AION film **25**. In addition, a conventional photo process is performed on the SiC substrate **17** and then, an unnecessary

12

portion of the AION film **25** is removed by, for example, a dry etching, thereby obtaining a gate insulating film **21**.

In ALD as described above, after introducing TMA into the chamber **11(27, 32)**, all the excess TMA molecules are discharged to the outside of the chamber **11(27, 32)** so as to form one TMA molecule layer. However, O₃ or NH₃ may be introduced before all the TMA molecules are discharged. In such a case, an AIO film **24** or an AlN film **23** having a thickness which is slightly thicker than the one TMA molecular layer is formed.

Specifically, TMA is introduced into the chamber **11(27, 32)** in which a wafer **W** formed with a thin SiO₂ film **22** (SiC substrate **17**) is accommodated, NH₃ is introduced into the chamber **11(27, 32)** while exhausting the inside of the chamber **11(27, 32)** but before all the excess TMA molecules are discharged, and the SiC substrate **17** is heated to cause TMA and NH₃ to chemically react with each other on the SiC substrate **17**, thereby forming an AlN film **23**.

Subsequently, an AIO film **24** is formed through a chemical reaction by the introduction of TMA, the introduction of O₃ prior to discharging all the excess TMA molecules O₃, and the heating of the SiC substrate **17**. In addition, in the same method as the above-described method, an AlN film **23** is formed through a chemical reaction. In the present method, since all the excess TMA molecules are not discharged when forming the AIO film **24** or when forming the AlN film **23**, a slightly thick AIO film **24** or AlN film **23** is formed.

Subsequently, the formation of the AIO film **24** and the formation of the AlN film **23** as described above are repeated, thereby forming an AION film **25** having a laminated structure in which the AIO films **24** and the AlN films **23** are alternately laminated and a heat treatment (annealing processing) is performed on the AION film **25**. In addition, a conventional photo process is performed on the SiC substrate **17** and then, an unnecessary portion of the AION film **25** is removed by, for example, a dry etching, thereby obtaining a gate insulating film **21**.

Subsequently, a film forming method according to a second exemplary embodiment of the present disclosure will be described.

The film forming method according to the present exemplary embodiment is different from the first exemplary embodiment in that AlN films **23** are only formed without forming an AIO film **24** and the oxidation of the formed AlN films **23** is performed. The film forming method according to the present exemplary embodiment may also be performed using not only the film forming apparatus **10** but also the film forming apparatuses **26, 31**. Hereinafter, a case in which the film forming method is performed using the film forming apparatus **10** will be described as a representative example.

FIGS. **8A** to **8F** are process charts illustrating the film forming method according to the present exemplary embodiment.

In the film forming apparatus **10** or any other heat treatment apparatus, a thin silicon oxide (SiO₂) film **22** is formed on a surface of a SiC substrate **17** (FIG. **8A**). Meanwhile, the thin SiO₂ film **22** is not essential and, when the thin SiO₂ film **22** is not formed, the oxidation of the surface of the SiC substrate **17** may be suppressed.

Subsequently, in the film forming apparatus **10**, one TMA molecule layer is formed by introducing TMA from the gas introduction tube **13a** and subsequently exhausting the inside of the chamber **11**, and then, an AlN film **23** is formed by introducing NH₃ from the gas introduction tube **13c** and heating the SiC substrate **17** (FIG. **8B**) (film forming step).

Subsequently, the AlN film **23** is oxidized by introducing O₃ from the gas introduction tube **13b** and heating the SiC substrate **17**, thereby producing an oxidized AlN film **23a** (FIG. **8C**) (oxidation step).

Subsequently, the formation of the AlN film **23** and the oxidation of the AlN film **23** are repeated, thereby forming an AION film **25** having a laminated structure of oxidized AlN films **23a**. The film thickness of the AION film is in the range of 30 nm to 150 nm, preferably not less than 50 nm (FIG. **8D**). For example, the film thickness of the AlN film **23** formed at a time is in the range of 0.1 nm to 20 nm and an oxidation time of the AlN film **23** is in the range of 0.1 sec to 120 sec. Meanwhile, the AlN film **23** may be formed not only by ALD but also by CVD. Specially, when the film thickness is thick, the AlN film **23** may be suitably formed by CVD.

For example, the film thickness of the AlN film **23** formed at a time is set to 2 nm, the concentration of O₃ within the chamber **11** when oxidizing the AlN film **23** is set to 100 g/cm³ to 400 g/cm³, the pressure within the chamber **11** is set to 1 Torr, and then oxidation is performed for 10 seconds. Under these conditions, the formation of the AlN film **23** and the oxidation of the AlN film **23** are alternately repeated by 40 times. As such, an AION film **25** having a thickness of about 80 nm and containing nitrogen of about 10 at % may be formed.

Subsequently, a heat treatment (annealing processing) is performed on the AION film by heating the SiC substrate **17** formed with the AION film **25** to a temperature in the range of, for example, 600° C. to 1100° C., in the film forming apparatus **10** or any other heat treatment apparatus (FIG. **8E**). In addition, a conventional photo process is performed on the SiC substrate **17** and then, the SiC substrate **17** is carried-in into a plasma etching apparatus and an unnecessary portion of the AION film **25** is removed by, for example, a dry etching, thereby obtaining a gate insulating film **21** (FIG. **8F**). Then, the present process is finished. The respective interfaces of in the AION film **25** collapse by, for example, the diffusion action of respective molecules in the annealing processing so that AlO molecules and AlN molecules are mixed up in the gate insulating film **21**.

With the film forming method according to the present exemplary embodiment, since the formation of the AlN film **23** and the oxidation of the AlN film **23** are repeated alternately, AlN films **23** is oxidized whenever they are formed. Thus, the film thickness of the AlN film **23** formed at a time may be set to be small so that the AlN film **23** may be uniformly oxidized. In addition, the uniformly oxidized AlN films **23a** are laminated to form an AION film **25**. As a result, even if the film thickness of the AION film **25** is large, the AION film **25** may be homogenized in the film thickness direction. Further, since a heat treatment is performed on the AION film **25** having the laminated structure, the laminated structure is eliminated by being annealed so that nitrogen contained in each of the oxidized AlN films **23a** is diffused in the AION film **25**. As a result, even if the film thickness of the AION film **25** is large, nitrogen may be substantially uniformly diffused in the thickness direction. That is, an AION film **25** which has a suitably controlled nitrogen density and is pressure-resistant may be obtained.

Meanwhile, the formation of the AlN film **23** and the oxidation of the AlN film **23** do not necessarily have to be performed alternately. A laminated structure having a predetermined film thickness may be formed by repeating the formation of the AlN film **23** by a predetermined number of times first and then repeating the oxidation of the AlN film **23** by the predetermined number of times.

In addition, in the film forming method according to the present exemplary embodiment, AlN films **23** may also be formed by CVD or PVD rather than by ALD.

For example, when forming an AlN film **23** by CVD in any of the film forming apparatuses **10(26,31)** as described above, TMA is introduced into the chamber **11(27, 32)** in which a wafer **W** formed with a thin SiO₂ film **22** (SiC substrate **17**) is accommodated, NH₃ is introduced into the chamber **11(27, 32)**, and the SiC substrate **17** is heated to cause TMA and NH₃ to chemically react with each other on the SiC substrate **17**, thereby forming an AlN film **23**. When the AlN film **23** is formed by CVD, excess TMA molecules are not discharged to the outside of the chamber **11(27, 32)** unlike ALD. Thus, a relatively thick (e.g., about 20 nm) AlN film **23** is formed.

Subsequently, an oxidized AlN film **23a** is produced by introducing O₃ and heating the SiC substrate **17**. Further, the formation of the AlN film **23** by CVD and the oxidation of the AlN film **23**, thereby forming an AION film **25** having a laminated structure of oxidized AlN films **23a** and a heat treatment (annealing processing) is performed on the AION film **25**. In addition, a conventional photo process is performed on the SiC substrate **17** and then, an unnecessary portion of the AION film **25** is removed by, for example, a dry etching, thereby obtaining a gate insulating film **21**.

In ALD as described above, after introducing TMA into the chamber **11(27, 32)**, all the excess TMA molecules are discharged to the outside of the chamber **11(27, 32)** so as to form one TMA molecule layer. However, NH₃ may be introduced before all the TMA molecules are discharged. In such a case, an AlN film **23** having a thickness which is slightly thicker than the TMA molecular layer is formed.

Specifically, TMA is introduced into the chamber **11(27, 32)** in which a wafer **W** formed with a thin SiO₂ film **22** (SiC substrate **17**) is accommodated, NH₃ is introduced into the chamber **11(27, 32)** while exhausting the inside of the chamber **11(27, 32)** but before all the excess TMA molecules are discharged, and the SiC substrate **17** is heated to cause TMA and NH₃ to chemically react with each other on the SiC substrate **17**, thereby forming an AlN film **23**.

Subsequently, an oxidized AlN film **23a** is produced by introducing O₃ and heating the SiC substrate **17**, and the formation of the AlN film **23** by CVD and the oxidation of the AlN film **23** are repeated, thereby forming an AION film **25** having a laminated structure of oxidized AlN films **23a**. In addition, a heat treatment (annealing processing) is performed on the AION film **25**, a conventional photo process is performed on the SiC substrate **17**, and then, an unnecessary portion of the AION film **25** is removed by, for example, a dry etching, thereby obtaining a gate insulating film **21**.

In addition, the oxidation of the AlN films **23** may be performed by plasma generated from O₃ within the chamber **11** or plasma of O₂ introduced from the gas introduction tube **13b** rather than by the heating of the SiC substrate **17**.

In the film forming method according to the present exemplary embodiment as described above, the oxidation degrees of respective formed AlN films **23** may not be equal to each other. For example, when increasing the concentration of nitrogen only in the portion adjacent to the surface of the SiC in the AION film **25**, an oxidation time of the AlN film **23** formed in the vicinity of the surface of the SiC substrate **17** may be shortened. Therefore, an unnecessary oxidation time may be reduced, thereby improving throughput.

Subsequently, a film forming method according to a third exemplary embodiment of the present disclosure will be described.

The film forming method according to the present exemplary embodiment is different from the first exemplary

embodiment in that AIO films **24** are only formed without forming an AlN film **23** and nitridation is performed on the formed AIO films **24**. The film forming method according to the present exemplary embodiment may also be performed using not only the film forming apparatus **10** but also the film forming apparatuses **26**, **31**. Hereinafter, a case in which the film forming method is performed using the film forming apparatus **10** will be described as a representative example.

FIGS. **9A** to **9F** are process charts illustrating the film forming method according to the present exemplary embodiment.

In the film forming apparatus **10** or any other heat treatment apparatus, a thin silicon oxide (SiO₂) film **22** is formed on a surface of a SiC substrate **17** (FIG. **9A**). Meanwhile, the thin SiO₂ film **22** is not essential and, when the thin SiO₂ film **22** is not formed, the oxidation of the surface of the SiC substrate **17** may be suppressed.

Subsequently, in the film forming apparatus **10**, one TMA molecule layer is formed by introducing TMA from the gas introduction tube **13a** and subsequently exhausting the inside of the chamber **11**, and then, an AIO film **24** is formed by introducing O₃ from the gas introduction tube **13b** and heating the SiC substrate **17** (FIG. **9B**) (film forming step).

Subsequently, the AIO film **24** is nitrided by plasma which is formed within the chamber **11** by introducing NH₃ or N₂ as a nitrogen source from the gas introduction tube **13c**, thereby forming a nitrided AIO film **24a** (FIG. **9C**) (nitridation step).

Subsequently, the formation of the AIO film **24** and the nitridation of the AIO film **24** are repeated, thereby forming an AION film **25** having a laminated structure of nitrided AIO films **24a**. The film thickness of the AION film **25** is 30 nm to 150 nm, preferably not less than 50 nm (FIG. **9D**). For example, the film thickness of an AIO film **24** formed at a time is in the range of 0.1 nm to 20 nm and a nitridation time of the AIO film **24** by plasma is in the range of 1 sec to 600 sec. Meanwhile, AIO films **24** may be formed not only by ALD but also by CVD. Specially, when the film thickness is large, the AIO films **24** may be suitably formed by CVD.

Subsequently, the SiC substrate **17** formed with the AION film **25** is heated to a temperature in the range of, for example, 600° C. to 1100° C., in the film forming apparatus **10** or any other heat treatment apparatus so as to perform a heat treatment (annealing processing) on the AION film (FIG. **9E**) and further a conventional photo process is performed on the SiC substrate **17**. Then, the SiC substrate **17** is carried-in into a plasma etching apparatus so as to remove an unnecessary portion of the AION film **25** by, for example, a dry etching, thereby obtaining a gate insulating film **21** (FIG. **9F**). Then, the present process is finished. The respective interfaces of in the AION film **25** collapse by, for example, diffusion action of respective molecules in the annealing processing so that AIO molecules and AlN molecules are mixed up in the gate insulating film **21**.

With the film forming method according to the present exemplary embodiment, since the formation of the AIO film **24** and the nitridation of the AIO film **24** are repeated alternately, the AIO films **24** are nitrided whenever they are formed. Thus, the film thickness of the AIO film **24** formed at a time may be set to be small so that the AIO film **24** may be uniformly nitrided. In addition, uniformly nitrided AIO films **24a** are laminated to form an AION film **25**. As a result, even if the film thickness of the AION film **25** is large, the AION film **25** may be homogenized in the film thickness direction. Further, since a heat treatment is performed on the AION film **25** having the laminated structure, the laminated structure is eliminated by being annealed so that nitrogen contained in each of the nitrided AIO films **24a** is diffused in the AION film

25. As a result, even if the film thickness of the AION film **25** is large, nitrogen may be substantially uniformly diffused in the thickness direction. That is, an AION film **25** which has a suitably controlled nitrogen density and is pressure-resistant may be obtained.

Meanwhile, the formation of the AIO film **24** and the nitridation of the AIO film **24** do not necessarily have to be performed alternately. The laminated structure having a predetermined film thickness may be formed by repeating the formation of AIO film **24** by a predetermined number of times first and then repeating the nitridation of the AIO film **24** by the predetermined number of times.

In addition, in the film forming method according to the present exemplary embodiment, AIO films **24** may also be formed by CVD or PVD rather than by ALD.

For example, when AIO films **24** are formed by CVD in any of the film forming apparatuses **10**(**26**, **31**) as described above, TMA is introduced into the chamber **11**(**27**, **32**) in which a wafer **W** formed with a thin SiO₂ film **22** (SiC substrate **17**) is accommodated, O₃ is introduced into the chamber **11**(**27**, **32**), and the SiC substrate **17** is heated to cause TMA and O₃ to chemically react with each other on the SiC substrate **17**, thereby forming an AIO film **24**. When an AIO film **24** is formed by CVD, a relatively thick (e.g., about 20 nm) AIO film **24** is formed since excess TMA molecules are not discharged to the outside of the chamber **11**(**27**, **32**) unlike ALD.

Subsequently, a nitrided AIO film **24a** is produced by nitridation by plasma of NH₃ or N₂ within the chamber **11**(**27**, **32**). Further, the formation of the AIO film **24** by CVD and the nitridation of the AIO film **24** are repeated, thereby forming an AION film **25** having a laminated structure of nitrided AIO films **24a** and a heat treatment (annealing processing) is performed on the AION film **25**. In addition, a conventional photo process is performed on the SiC substrate **17** and then, an unnecessary portion of the AION film **25** is removed by, for example, a dry etching, thereby obtaining a gate insulating film **21**.

In ALD as described above, after introducing TMA into the chamber **11**(**27**, **32**), all the excess TMA molecules are discharged to the outside of the chamber **11**(**27**, **32**) so as to form one TMA molecule layer. However, O₃ may be introduced before all the TMA molecules are discharged. In such a case, an AIO film **24** having a thickness which is slightly thicker than the one TMA molecular layer is formed.

Specifically, TMA is introduced into the chamber **11**(**27**, **32**) in which a wafer **W** formed with a thin SiO₂ film **22** (SiC substrate **17**) is accommodated, O₃ is introduced into the chamber **11**(**27**, **32**) while exhausting the inside of the chamber **11**(**27**, **32**) but before all the excess TMA molecules are discharged, and the SiC substrate **17** is heated to cause TMA and O₃ to chemically react with each other on the SiC substrate **17**, thereby forming an AIO film **24**.

Subsequently, a nitrided AIO film **24a** is produced by nitridation by plasma of NH₃ or N₂ generated in the chamber **11**(**27**, **32**), the formation of the AIO film **24** by CVD and the nitridation of the AIO film **24** are repeated, thereby forming an AION film **25** having a laminated structure of nitrided AIO films **24a**, and a heat treatment (annealing processing) is performed on the AION film **25**. In addition, a conventional photo process is performed on the SiC substrate **17**, and then, an unnecessary portion of the AION film **25** is removed by, for example, a dry etching, thereby obtaining a gate insulating film **21**.

The nitridation of the AIO films **24** may be performed by heating the SiC substrate **17** rather than by plasma.

In the film forming method according to the present exemplary embodiment as described above, the nitridation degrees of respective formed AIO films **24** may not be equal to each other. For example, when increasing the concentration of nitrogen only in the portion adjacent to the surface of the SiC in the AION film **25**, a nitridation time of the AIO film **24** formed in the vicinity of the surface of the SiC substrate **17** may be increased. Therefore, an unnecessary nitridation time may be reduced, thereby improving throughput.

Meanwhile, when forming an AlN film **23** or an AIO film **24** by ALD or CVD, the temperature within the chamber **11** during film-forming may be in the range of 100° C. to 750° C. This temperature range is desirable due to the following reasons. When the film forming temperature is 700° C. or higher, the AlN film may be crystallized as the AlN film is heated. In such a case, since crystal grain boundaries may be generated in the AlN film **23** and the crystal grain boundaries may form a leak path, an amorphous AION film **25** which is excellent as an insulating film may not be obtained. When the film forming temperature is about 700° C., an effect of omitting an annealing processing in the subsequent process may be expected. That is, in consideration of suppressing the generation of crystal grain boundaries and the simplification of processing, it is desirable that the film forming temperature is not higher than 750° C.

In addition, when the AlN film **23** or the AIO film **24** is formed at a high temperature, diffusion may occur between the AlN film **23** or AIO film **24** and a thin SiO₂ film **22** as an underlayer, thereby causing deterioration in film quality or electric characteristic. Accordingly, it is more desirable that the temperature within the chamber **11** during film-forming is in the range of 250° C. to 400° C. Specially, when the temperature is 400° C. or less, the crystallization of AlN or the deterioration of SiO₂ film **22** may be suppressed and thus, an amorphous AION film **25** may be obtained. In consideration of facilitation of chemical reaction during film-forming, it is more desirable that the temperature within the chamber **11** during film-forming is in the range of 300° C. to 400° C.

In each of the film forming methods of the exemplary embodiments as described above, the AlN film **23** or the AIO film **24** is formed by ALD or CVD. However, the method of forming the AlN film **23** or the AIO film **24** is not limited thereto. For example, the AlN film **23** or the AIO film **24** may also be obtained by forming an Al film by ALD, CVD or PVD and performing a nitridation processing or an oxidation processing on the Al film.

Although the present disclosure has been described above using exemplary embodiments, the present disclosure is not limited to the exemplary embodiments.

Further, the object of the present disclosure may also be achieved when a storage medium in which software program codes that implement functions of each of the exemplary embodiments as described above are stored is provided to a computer (e.g., the controller of the film forming apparatus **10**(**26**, **31**)) and the program codes stored in the storage medium are read and executed by the CPU of the computer.

In such a case, since the program codes read from the storage medium implement the functions of each of the exemplary embodiments as described above, the program codes and the storage medium that stores the program codes will configure the present disclosure.

As for the storage medium for supplying the program codes, for example, a RAM, a NV-RAM, a floppy (registered trademark) disc, a hard disc, a magneto-optical disc, an optical disc such as a CD-ROM, CD-R, CD-RW or DVD (DVD-ROM, DVD-RAM, DVD-RW, DVD+RW), a magnetic tape, a non-volatile memory card or any other ROM which may store

the program codes may be used. Alternatively, the program codes may be supplied to the computer by downloading the program codes from, for example, any other computer or database that is connected to the Internet, a commercially available network, or a local area network.

In addition to the case in which the functions of each of the exemplary embodiments are implemented by executing the program codes read by the computer, a case in which, based on the program codes, and for example, an OS (operating system) operated on a CPU performs some or the entirety of actual processings so that the functions of each of the exemplary embodiments as described above are implemented by the processings is also included in the present disclosure.

Further, a case in which program codes read from the storage medium is stored in a function extension board inserted into the computer or a function extension unit connected to the computer, and then, for example, a CPU provided in the function extension board or the function extension unit performs some or the entirety of actual processings based on the commands of the program codes so that the functions of each of the exemplary embodiments as described above are implemented is also included in the present disclosure.

The program codes may be configured in the forms of, for example, object codes, program codes executed by an interpreter, or script data supplied to an OS.

EXAMPLE

Next, an Example of the present disclosure will be described.

When forming gate insulating films of MOSFETs, AION films **25** were formed by setting the pressure within the chamber **11** to 0.35 Torr, setting the temperature within the chamber **11** to 350° C., and then repeating the formation of the AlN film **23** by ALD and the oxidation of the AlN film **23** was repeated (Example). Meanwhile, the thickness of each of the AION films **23** was 3 nm. Since the AION films **25** were formed as samples for test, the thickness thereof was set to 30 nm.

Meanwhile, when forming the gate insulating films of MOSFETs, Al₂O₃ films were formed by a deposition method (Comparative Example).

Thereafter, for the MOSFETs of Example and Comparative Example, flat band voltages were measured. As illustrated in FIG. **11**, in the comparative example, a large flat band shift has been confirmed. However, in the Example of the present disclosure, such a large flat band shift has not been confirmed. As a result, it has been found out that in the AION films **25** of the Example, electron traps have been eliminated by adding nitrogen.

In addition, in order to confirm a coating property over steps of the AION film **25** when AlN films **23** were formed by CVD, an AION film **25** having a thickness of about 60 nm was formed by setting the pressure within the chamber **11** to 0.30 Torr, setting the temperature within the chamber **11** to 380° C., and then repeating the formation of the AlN film **23** by CVD and the oxidation of the AlN film **23** and a trench structure on a wafer W was coated with the AION film **25**.

Thereafter, it has been confirmed from the cross-sectional structure of the trench that the inner surfaces of the trench were covered by the AION film **25** in a substantially uniform film thickness as illustrated in FIG. **12**. That is, it has been found out that when a gate insulating film is formed by an AION film **25** in a MOSFET having a trench structure having an aspect ratio of about **4**, the AlN film **23** may be formed by CVD.

19

From the foregoing, it will be appreciated that various embodiments of the present disclosure have been described herein for purposes of illustration, and that various modifications may be made without departing from the scope and spirit of the present disclosure. Accordingly, the various embodiments disclosed herein are not intended to be limiting, with the true scope and spirit being indicated by the following claims.

What is claimed is:

1. A method of forming a gate insulating film for use in a MOSFET for a power device, the method comprising:
 - forming an AlN film;
 - forming an AIO film; and
 - repeating the forming the AlN film and the forming the AIO film, thereby forming an AION film having a laminated structure in which AIO films and AlN films are alternately laminated.
2. The method of claim 1, wherein the film thickness of the AION film is 50 nm or more.
3. The method of claim 1, wherein the AION film is formed on a substrate and the substrate includes any one of silicon carbonate, gallium nitride and diamond.
4. The method of claim 1, wherein a heat treatment is performed on the AION film having the laminated structure.
5. The method of claim 1, wherein the AlN film formed at the very first among the AlN films is formed before the AIO film formed at the very first among the AIO films.
6. The method of claim 1, wherein the formation of the AlN film and/or the formation of the AIO film are performed by ALD, CVD or PVD.
7. A method of forming a gate insulating film for use in a MOSFET for a power device, the method comprising:
 - forming an AlN film;
 - oxidizing the AlN film after the AlN film is formed; and
 - repeating the forming the AlN film and the oxidizing the AlN film alternately, thereby forming an AION film having a laminated structure in which oxidized AlN films are laminated.
8. The method of claim 7, wherein the film thickness of the AION film is 50 nm or more.
9. The method of claim 7, wherein the AION film is formed on a substrate and the substrate includes any one of silicon carbonate, gallium nitride and diamond.
10. The method of claim 7, wherein a heat treatment is performed on the AION film having the laminated structure.

20

11. The method of claim 7, wherein the formation of the AlN film is performed by ALD, CVD or PVD.

12. The method of forming a gate insulating film for use in a MOSFET for a power device, the method comprising:

- forming an AIO film;
- nitriding the AIO film after the AIO film is formed; and
- repeating the forming the AIO film and the nitriding the AIO film alternately, thereby forming an AION film having a laminated structure in which nitrided AIO films are laminated.

13. The method of claim 12, the film thickness of the AION film is 50 nm or more.

14. The method of claim 12, wherein the AION film is formed on a substrate and the substrate includes any of silicon carbonate, gallium nitride and diamond.

15. The method of claim 12, wherein a heat treatment is performed on the AION film having the laminated structure.

16. The method of claim 12, wherein the formation of the AIO film is performed by ALD, CVD or PVD.

17. A film forming apparatus comprising:

- a film forming unit configured to form an AlN film and an AIO film,

 wherein the film forming unit repeats a formation of the AlN film and a formation of the AIO film, thereby forming an AION film having a laminated structure in which AIO films and AlN films are alternately laminated.

18. A film forming apparatus comprising:

- a film forming unit configured to form an AlN film; and
- an oxidation unit configured to oxidize the AlN film after the AlN film is formed,

 wherein the film forming unit and the oxidation unit repeat the formation of the AlN film and the oxidation of the AlN film alternately, thereby forming an AION film having a laminated structure in which oxidized AlN films are laminated.

19. A film forming apparatus comprising:

- a film forming unit configured to form an AIO film; and
- a nitridation unit configured to nitride the AIO film after the AIO film is formed,

 wherein the film forming unit and the nitridation unit repeat the formation of the AIO film and the nitridation of the AIO film, thereby forming an AION film having a laminated structure in which nitrided AIO films are laminated.

* * * * *