



- (51) **International Patent Classification:**
F27D 1/00 (2006.01) *C04B 35/52* (2006.01)
C21B 7/06 (2006.01) *C04B 35/532* (2006.01)
- (21) **International Application Number:** PCT/EP2012/057338
- (22) **International Filing Date:** 23 April 2012 (23.04.2012)
- (25) **Filing Language:** English
- (26) **Publication Language:** English
- (30) **Priority Data:**
11167940.3 27 May 2011 (27.05.2011) EP
- (71) **Applicant (for all designated States except US):** SGL
CARBON SE [DE/DE]; Söhnleinstr. 8, 65201 Wiesbaden
(DE).
- (72) **Inventors; and**
- (75) **Inventors/Applicants (for US only):** TOMALA, Janusz
[PL/PL]; Szczecinska 30, 47-400 Racibórz (PL).
WIEBEL, Christian [DE/DE]; Werner-von-Siemens-Str.
18, 86405 Meitingen (DE). HILTMANN, Frank
[DE/DE]; Werner-von-Siemens-Str. 18, 86405 Meitingen
(DE).
- (81) **Designated States (unless otherwise indicated, for every
kind of national protection available):** AE, AG, AL, AM,

AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ,
CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO,
DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN,
HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR,
KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME,
MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ,
OM, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SC, SD,
SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR,
TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

- (84) **Designated States (unless otherwise indicated, for every
kind of regional protection available):** ARIPO (BW, GH,
GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ,
UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU,
TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE,
DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU,
LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK,
SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,
GW, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

- *as to applicant's entitlement to apply for and be granted a
patent (Rule 4.17(ii))*

Published:

- *with international search report (Art. 21(3))*



(54) **Title:** REFRACTORY FOR AN INNER LINING OF A BLAST FURNACE, OBTAINED BY SEMI-GRAPHITIZATION OF A MIXTURE COMPRISING C AND SI

(57) **Abstract:** A refractory, which is particularly suitable for use in an inner lining of a blast furnace, is obtainable by a process including the following steps: a) providing a mixture containing - coke, - silicon and - binder, b) forming a green block from the mixture provided in step a), c) baking the green block of step b) and d) semi-graphitizing the baked block of step c) at a temperature between 1600 and 2000°C.

REFRACTORY FOR AN INNER LINING OF A BLAST FURNACE, OBTAINED BY SEMI-GRAPHITIZATION OF A MIXTURE COMPRISING C AND SI

5 The present invention relates to a refractory for an inner lining of a blast furnace, to a blast furnace comprising an inner lining including such a refractory and to the use of such a refractory in an inner lining of a blast furnace.

10 Refractories are characterized in that they retain a high strength at high temperatures, such as at temperatures above 1000 °C. Due to this, refractories are used in a plurality of applications, in which high thermal resistances are required, for example in linings of furnaces, kilns, incinerators and reactors, as a material for crucibles for melts or the like.

15

Refractories used in an inner lining of a blast furnace have, in particular, to meet a plurality of demands, such as a high refractoriness, an adequate thermal conductivity with regard to the blast furnace design, a high mechanical strength including a high compressive strength at temperatures
20 of up to 2000 °C, a good resistance to temperature changes, an excellent corrosion resistance and a high oxidation resistance. In particular, a high resistance to dissolution in the liquid hot metal and slag is desirable for a refractory of an inner lining of a blast furnace.

25 Modern refractories for an inner lining of a blast furnace are based on carbon and graphite materials, because of the high refractoriness, the good resistance to temperature changes and the satisfactory compressive strength of carbon and graphite at temperatures of up to 2000 °C. These

refractories are typically produced by forming a green block from a raw material mixture including carbonaceous material and baking the green block at a temperature between 1100 and 1300 °C. However, standard carbon materials have the disadvantage of providing only a low resistance to alkalis, a low resistance to oxidation, an insufficient resistance to dissolution of carbon material in the liquid hot metal and slag, which are not saturated with carbon, and a relatively high penetrability of liquid hot metal into their pores. In order to at least partially compensate or improve the aforementioned disadvantageous properties of carbon and graphite, specific additives are usually added to the carbon and graphite materials. For example, fine-powdered silicon is often added to such materials, because it causes a reduction of the pore diameter in the refractory – with the conversion to silicon carbide during thermal treatment – to such small values that the penetration of liquid hot metal into the refractory is reduced or even completely avoided. On the other hand, the addition of aluminum oxide increases the resistance of the material to dissolution of carbon in the liquid hot metal and slag.

DE 601 20 675 T2 discloses a method for producing a refractory, which is intended to be particularly suitable for use in a lining of a blast furnace, wherein the method comprises the steps of i) providing a mixture including 50 to 80 % by weight of a carbonaceous material, such as calcined coke or graphite, 5 to 15 % by weight of aluminum oxide powder, 5 to 15 % by weight of silicon powder and 5 to 20 % by weight of one or more materials selected from the group consisting of metallic titanium, titanium carbide, titanium nitride and titanium carbonitride, ii) adding a binder to this mixture, iii) forming a green block from the mixture of step ii) and baking the green block at a temperature of 1250 °C. The addition of 5 to 20 % by weight of the at least one material selected from the group consisting of metallic titanium, titanium carbide, titanium nitride and tita-

nium carbonitride is intended to improve the resistance of the refractory to molten iron, whereas the addition of silicon is intended to cause a comparatively small pore diameter in the refractory. Even if the material is in principle suitable for the use in an inner lining of a blast furnace, the thermal conductivity and the mechanical strength of this material are in need of improvement. The same applies for the other known refractories mentioned above.

Accordingly, the object underlying the present invention is to provide a refractory, which has in particular an excellent thermal conductivity and a high mechanical strength and which also provides a good resistance against dissolution in the molten hot metal and slag, a good corrosion resistance as well as a small penetrability of liquid hot metal and reactive gases, such as carbon monoxide and carbon dioxide, into its pores, so that it is perfectly well suitable for use in an inner lining and in particular in the inner lining of a blast furnace. Moreover, the refractory shall be stable even if shaped to a block having comparatively large dimensions.

According to the present invention, this object is satisfied by a refractory particularly for the use in an inner lining of a blast furnace, which is obtainable by a process including the following steps:

- a) providing a mixture containing
 - coke,
 - silicon and
 - binder,
- b) forming a green block from the mixture provided in step a),
- c) baking the green block of step b) and
- d) semi-graphitizing the baked block of step c) at a temperature between 1600 and 2000 °C.

This solution is based on the surprising finding that a refractory, which is obtainable by semi-graphitizing a baked block made of a mixture containing coke, silicon and binder at a temperature between 1600 and 2000 °C, has a good resistance to dissolution of carbon material in the molten hot metal and slag. It also has a good corrosion resistance, a small penetrability of liquid hot metal and reactive gases into its pores (due to the fact that its pores have a comparatively small diameter), a good resistance to temperature changes as well as a high refractoriness. Moreover, it also has an improved thermal conductivity and an improved mechanical strength, such as an improved compressive strength at temperatures of up to 2000 °C. An excellent thermal conductivity of the refractory is advantageous for two reasons, namely firstly because it reduces possible damage to or destruction of the refractory and secondly because it leads to a high heat flux leading to a lower surface temperature of hot parts of the refractory which are in contact with the hot metal and the slag. This in turn allows the formation of a protective layer of highly viscous iron adhering to the refractory, which again increases the erosion and corrosion resistance of the refractory. It also supports the application of thinner hearth walls to increase the working volume of the blast furnace.

In particular, the thermal conductivity and the mechanical strength of a refractory are, above all, improved - in comparison to a material containing highly conductive synthetic graphite, e.g. graphite as used in connecting pins for graphite electrodes used in electric arc furnaces, as main raw material, which is only baked at a temperature of about 1100 to 1300°C -, if the baked block is subjected to a semi-graphitization at a temperature between 1600 and 2000 °C. Without being wished to be bound to a theory, the inventors of the present patent application believe that the improvement of the thermal conductivity and also the improvement of the me-

chanical strength are particularly due to the fact that during the heat treatment at 1600 and 2000 °C amorphous carbon included in the green block is at least partially converted into graphite or into a graphite-like structure. Additionally, the semi-graphitization of the baked block at a temperature between 1600 and 2000 °C leads to a homogenization of the composition and of the microstructure of the refractory. Moreover, the silicon included in the green block contributes to these effects, because a part of this silicon reacts during the baking and during the semi-graphitization with carbon to produce silicon carbide in the form of needle-like crystals, which further improve the mechanical strength of the refractory. However, because the final semi-graphitization is not performed at a temperature above 2000 °C, as would be used during a conventional graphitization, a decomposition of the silicon carbide crystals formed during the baking, which would occur in a conventional graphitization step, is reliably avoided. Consequently, the addition of silicon to the mixture for forming the green block and the subsequent semi-graphitization of the baked block at a temperature between 1600 and 2000 °C cooperate synergistically and synergistically increase the mechanical strength of the refractory. All in all, the semi-graphitization of the baked block at a temperature between 1600 and 2000 °C advantageously influences three properties of the refractory:

- firstly it significantly increases the thermal conductivity of the refractory,
- secondly it significantly increases the mechanical strength of the refractory and
- thirdly it improves the erosion and corrosion resistance of the refractory.

On account of its excellent mechanical strength and its excellent thermal conductivity, the refractory according to the present invention further has the advantage that it is stable, even if it is shaped to a block having comparatively large dimensions, such as a W x H x L of at least 700 x 700 x

2500 mm. This is particularly advantageous, because if large blocks are used for a lining the number of block joints in a lining of a given size can be reduced and the stability of the lining can thus be increased, because the block joints are the weak point of the lining.

5

Apart from that, the silicon further leads to the formation of a microporous structure, which means that the cumulated porosity from pores with a diameter above 1 μm does not exceed 4% of the sample volume, which is usually measured by mercury porosimetry. Due to this microporous structure, the refractory according to the present invention has a small penetrability for liquid hot metal and reactive gases.

10

Due to all the aforementioned advantageous properties, the refractory according to the present invention is perfectly suited for use in an inner lining and in particular in the inner lining of a blast furnace.

15

As set out above, semi-graphitization denotes in the sense of the present patent application a heat treatment performed at a temperature between 1600 and 2000 °C. Thus, the term semi-graphitization is only used in the present patent application to make clear that it is believed that during this step amorphous carbon is at least partially converted into graphite or into a graphite-like structure.

20

In principal, the present invention is not limited concerning the type of coke used in step a) for the preparation of the mixture. Thus, in principal all types of coke can be used, such as petroleum coke, anthracite, coal-tar pitch coke, acetylene coke, metallurgical coke or the like.

25

However, according to a first particularly preferred embodiment of the present invention in step a) coke is used, with at least a part of the coke

30

being isotropic coke. Isotropic cokes are characterized by a high coefficient of thermal expansion without preferred orientation. Surprisingly, the use of isotropic coke leads to a refractory with a particularly high mechanical strength. This is presumably due to the fact that the isotropic coke
5 shrinks during the semi-graphitization step more homogeneously than anisotropic coke and thus leads to a refractory with a more homogeneous microstructure. Moreover, the use of isotropic coke contributes to an isotropic thermal conductivity of the refractory. Particular good results are obtained, if at least 50 % by weight of the coke used in step a) consists of
10 isotropic coke. Even better results are obtained, if the coke applied in step a) consists of at least 80 % by weight, preferably of at least 90 % by weight, more preferably of at least 95 % by weight, even more preferably of at least 99 % by weight and most preferably solely of isotropic coke.

15 According to a second particularly preferred embodiment of the present invention in step a) coke is used with a comparatively low iron content. This embodiment is based on the finding that the use of coke with a comparatively low iron content improves the corrosion resistance and particularly the carbon monoxide resistance, the carbon dioxide resistance and
20 the oxidation resistance of the refractory. Moreover, as a secondary effect, the use of coke with a comparatively low iron content improves the hot metal resistance. Accordingly, it is preferred that the coke used in step a) has an iron content of at most 0.1 % by weight, more preferably of at most 0.05 % by weight, even more preferably of at most 0.01 % by weight, especially preferably of at most 0.005 % by weight and most preferably of at
25 most 0.001 % by weight.

Apart from the silicon and the coke, the mixture provided in step a) advantageously further comprises graphite. The addition of a certain amount

of graphite facilitates the baking process and increases the thermal conductivity of the finished product.

All kinds of natural and synthetic graphites can be used and particular
5 good results are obtained with synthetic graphite.

Likewise, the present invention is not particularly limited with regard to the amount of coke and graphite added in step a). However, good results are notably obtained, if the mixture provided in step a) comprises 60 to
10 85 % by weight and preferably 65 to 75 % by weight of a mixture of coke and of graphite based on the dry aggregate of the refractory. With dry aggregate of the refractory according to the present invention the sum of all ingredients of the refractory except the binder is meant.

15 As set out above, the silicon effects the formation of a microporous structure in the refractory, which leads to a small penetration tendency of liquid hot metal and reactive gases of the refractory. Moreover, the silicon contributes, in synergistic cooperation with the semi-graphitization to a high mechanical strength of the refractory according to the present inven-
20 tion, because a part of this silicon reacts during the baking and during the semi-graphitization with carbon to produce silicon carbide in the form of needle-like crystals. In order to achieve both effects to a sufficient degree, it is preferable that the mixture provided in step a) comprises 5 to 15 % by weight and more preferably 8 to 12 % by weight of silicon based on the dry
25 aggregate of the refractory.

According to a further particularly preferred embodiment of the present invention the mixture provided in step a) further comprises titanium dioxide. The addition of titanium dioxide increases the viscosity of liquid hot
30 metal at the interface with the refractory and improves on account of this

reason the erosion and corrosion resistance of the refractory. In order to obtain a high degree of this advantageous effect, it is preferred that the mixture provided in step a) comprises 6 to 14 % by weight and more preferably 8 to 12 % by weight of titanium dioxide based on the dry aggregate
5 of the refractory.

According to a still further particularly preferred embodiment of the present invention, the mixture provided in step a) further comprises a silicon carbide-carbon powder mix (SiC-C powder), which contains at least 50 %
10 by weight of silicon carbide. The addition of SiC-C powder improves the oxidation resistance as well as the mechanical resistance of the refractory. Good results in this regard are particularly achieved, if the mixture provided in step a) includes 4 to 15 % by weight and preferably 8 to 12 % by weight of SiC-C powder based on the dry aggregate of the refractory.

15

Last but not least, the mixture provided in step a) comprises at least one binder. The binder may be any binder known in this field, such as one selected from the group consisting of coal-tar pitch, petroleum pitch, phenolic resin, furfurylic resin, coal tar, petroleum tar and any mixture of two
20 or more of the aforementioned compounds. The amount of the binder is preferably selected in such an amount that a workable paste is obtained, which means that a suitable viscosity of the paste for the forming process is obtained.

25 All in all, the refractory according to the present invention is obtainable from a mixture, which has to contain coke, silicon, binder and optionally graphite and/or titanium dioxide and/or SiC-C powder. It is preferred that the mixture provided in step a) includes coke, silicon, binder and at least one compound selected from the group consisting of graphite, titanium
30 dioxide and SiC-C powder. It is more preferred that the mixture provided

in step a) includes coke, silicon, binder, graphite and titanium dioxide and optionally also SiC-C powder.

According to a further particular preferred embodiment of the present invention, the mixture provided in step a) includes i) coke, preferably isotropic coke having an iron content of at most 0.1 % by weight, ii) silicon, iii) graphite, preferably synthetic graphite, iv) titanium dioxide, v) SiC-C powder and iv) at least one binder, wherein the single components are preferably contained in the mixture in the aforementioned amounts.

10

Merely by way of example, the mixture provided in step a) may comprise:

i) a mixture of:

- 60 to 80 % by weight of a mixture of coke, preferably coke having an iron content of at most 0.1 % by weight, and of graphite,
- 7 to 12 % by weight of silicon,
- 8 to 13 % by weight of titanium dioxide and
- 6 to 13 % by weight of silicon carbide-carbon powder, wherein the sum of the aforementioned ingredients is 100 % by weight,

15

and

ii) at least one binder.

20

According to an even more preferred embodiment of the present invention, the mixture provided in step a) comprises:

i) a mixture of:

- 65 to 75 % by weight of a mixture of coke, preferably coke having an iron content of at most 0.1 % by weight, and of graphite,
- 9 to 11 % by weight of silicon,
- 9 to 11 % by weight of titanium dioxide and
- 8 to 11 % by weight of silicon carbide-carbon powder, wherein the sum of the aforementioned ingredients is 100 % by weight,

25

30

and

ii) at least one binder.

The forming of the green block in step b) can be performed by any method
5 known to a person skilled in the art, such as by block-pressing, extrusion,
hot-pressing or vibro-molding.

Concerning the baking temperature, the present invention is not particu-
larly limited. Good results are obtained in this regard, if in step c) the
10 green block is baked at a temperature between 700 and 1200 °C, prefera-
bly between 800 and 1100 °C and more preferably between 800 and
900 °C.

As set out above, it is one of the most important features of the present
15 invention that the baked block is semi-graphitized in step d) at a tempera-
ture between 1600 and 2000 °C. The thermal conductivity of the refractory
tends to be higher, as the semi-graphitization temperature becomes high-
er. Due to this, it is preferred that in step d) the baked block is semi-
graphitized at a temperature between 1700 and 2000 °C, more preferably
20 between 1800 and 2000 °C and most preferably between 1900 and
2000 °C.

According to another preferred embodiment of the present invention, the
heat treated block, i.e. the baked and/or semi-graphitized block, may be
25 impregnated before and/or after the semi-graphitization according to step
d) with an impregnation agent, such as e.g. with coal tar, petroleum tar,
coal-tar pitch, petroleum pitch, resin or the like, to fill the pores in order
to increase the apparent density, the mechanical strength and the thermal
conductivity of the final product. After the impregnation, the blocks are
30 rebaked preferably at a temperature between 700 and 1200 °C, more pref-

erably at a temperature between 800 and 1100 °C and even more preferably at a temperature between 800 and 900 °C, in order to carbonize the impregnation agent. The impregnation and rebaking may be repeated several times. Preferably, the rebaking after the final impregnation step and
5 the semi-graphitization are performed concurrently, i.e. in one step, which is particularly preferred, if the semi-graphitization is the final heat treatment step.

According to a further particular preferred embodiment of the present
10 invention, the steps c) and d) are performed concurrently, i.e. in one step, particularly if the block is not impregnated and rebaked before the semi-graphitization.

Due to the high mechanical stability of the refractory, the refractory according to the present invention is even stable in the long term when it
15 has comparatively large dimensions. Because the block joints arranged between the single blocks of a lining are the weak point of the lining and because the number of block joints in a lining of a given size can be reduced if large blocks are used for a lining, it is preferable for the refractory
20 according to the present invention to be formed into an article with comparatively large dimensions, such as to a block having comparatively large dimensions, such as a W x H x L of at least 700 x 700 x 2500 mm.

Moreover, the present invention relates to a blast furnace comprising an
25 inner lining, wherein the inner lining comprises at least one above described refractories.

A further subject matter of the present invention is the use of the aforementioned refractory in an inner lining of a blast furnace.

In the following the present invention will be described in more detail by way of a non-limiting example.

5

Example 1

A refractory was prepared by first preparing a mixture comprising:

- 10
- 74 parts by weight of a mixture of isotropic coke, such as coal-tar pitch coke, or petroleum coke having an iron content of 0.01 % by weight and of synthetic graphite,
 - 9 parts by weight of metallic silicon powder having a maximum grain size of 63 μm ,

15

 - 9 parts by weight of titanium dioxide (rutilite) having a maximum grain size of 45 μm and
 - 8 parts by weight of SiC-C powder having a maximum grain size of 63 μm .
 - To this mixture coal-tar pitch was added as a binder in such an amount that a workable paste, i.e. a paste having a suitable viscosity for the forming process, was obtained.

20

For the mixing step for example a sigma-blade mixer may be used.

- 25
- Then, the mixture was formed by vibro-molding into green blocks having each a dimension of (W x H x L) 630 x 630 x 2500 mm, before the blocks were baked in a coke breeze packing at a maximum temperature of 850 to 1000 °C.

Afterwards, the baked blocks were semi-graphitized in an Acheson furnace at a final temperature of 2000 °C.

The blocks obtained with this method had the following properties:

5

- apparent density: 1.72 g/cm³,
- cold crushing strength: 42 MPa,
- thermal conductivity: 45 W/m·K and
- pore size distribution: sum of open porosity from pores with a diameter of larger than 1 μm equaled 2.7 % of the sample volume.

10

Comparative Example 1

15 A refractory was prepared as described in example 1, except that - instead of the semi-graphitization at a final temperature of 2000 °C - the baked bodies were submitted to a graphitization treatment at 2500°C in an Acheson furnace.

20 The blocks obtained with this method had the following properties:

- apparent density: 1.71 g/cm³,
- cold crushing strength: 27 MPa,
- thermal conductivity: 85 W/m·K and
- pore size distribution: sum of open porosity from pores with a diameter of larger than 1 μm equaled 7.0 % of sample volume.

25

Claims

- 5 1. A refractory particularly for the use in an inner lining of a blast furnace, which is obtainable by a process including the following steps:
- 10 a) providing a mixture containing
- coke,
 - silicon and
 - binder,
- b) forming a green block from the mixture provided in step a),
- c) baking the green block of step b) and
- d) semi-graphitizing the baked block of step c) at a temperature between 1600 and 2000 °C.
- 15
2. A refractory according to claim 1, wherein the coke provided in step a) consists of at least 50 % by weight, preferably of at least 80 % by weight, more preferably of at least 90 % by weight, even more preferably of at least 95 % by weight, particularly preferably of at least 99 % by weight and most preferably solely of isotropic coke.
- 20
3. A refractory according to claim 1 or 2, wherein the coke provided in step a) has an iron content of at most 0.1 % by weight, preferably of at most 0.05 % by weight, more preferably of at most 0.01 % by weight, even more preferably of at most 0.005 % by weight and most preferably of at most 0.001 % by weight.
- 25

4. A refractory according to any one of the preceding claims, wherein the mixture provided in step a) further comprises graphite.
5. A refractory according to claim 4, wherein the graphite is synthetic graphite.
6. A refractory according to claim 4 or 5, wherein the mixture provided in step a) comprises 60 to 85 % by weight and preferably 65 to 75 % by weight of a mixture of coke and of graphite based on the dry aggregate of the refractory.
7. A refractory according to any one of the preceding claims, wherein the mixture provided in step a) comprises 5 to 15 % by weight and preferably 8 to 12 % by weight of silicon based on the dry aggregate of the refractory.
8. A refractory according to any one of the preceding claims, wherein the mixture provided in step a) further comprises 6 to 14 % by weight and preferably 8 to 12 % by weight of titanium dioxide based on the dry aggregate of the refractory.
9. A refractory according to any one of the preceding claims, wherein the mixture provided in step a) further comprises 4 to 15 % by weight and preferably 8 to 12 % by weight of a silicon carbide-carbon powder mix based on the dry aggregate of the refractory, which contains at least 50 % by weight of silicon carbide.
10. A refractory according to any of the preceding claims, wherein the at least one binder is selected from the group consisting of coal-tar pitch, petroleum pitch, phenolic resin, furfurylic resin, coal tar, pe-

troleum tar and any mixture of two or more of the aforementioned compounds.

11. A refractory according to any of the preceding claims, wherein the mixture provided in step a) comprises:
- 5
- a mixture of:
 - 60 to 80 % by weight and preferably 65 to 75 % by weight of a mixture of coke having an iron content of at most 0.1 % by weight and of graphite,
 - 10 - 7 to 12 % by weight and preferably 9 to 11 % by weight of silicon,
 - 8 to 13 % by weight and preferably 9 to 11 % by weight of titanium dioxide and
 - 6 to 13 % by weight and preferably 8 to 11 % by weight of silicon carbide-carbon powder, wherein the sum of the
 - 15 - aforementioned ingredients is 100 % by weight,
- and
- at least one binder.
12. A refractory according to any one of the preceding claims, wherein the forming in step b) is performed by block pressing, extrusion, hot pressing or vibro-molding.
13. A refractory according to any one of the preceding claims, wherein in step c) the green block is baked at a temperature between 700 and 1200 °C, preferably between 800 and 1100 °C and more preferably between 800 and 900 °C.
14. A refractory according to any one of the preceding claims, wherein in step d) the baked block is semi-graphitized at a temperature be-
- 20
- 25
- 30

tween 1700 and 2000 °C, preferably between 1800 and 2000 °C and more preferably between 1900 and 2000 °C.

- 5 15. A refractory according to any one of the preceding claims, wherein the heat treated block is impregnated before and/or after the semi-graphitization according to step d) with an impregnation agent, which is preferably selected from the group consisting of coal tar, petroleum tar, coal-tar pitch, petroleum pitch, resin and mixtures of two or more of the aforementioned compounds, and wherein the im-
- 10 10 impregnated green block is rebaked preferably at a temperature between 700 and 1200 °C, more preferably at a temperature between 800 and 1100 °C and even more preferably at a temperature between 800 and 900 °C.
- 15 16. A refractory according to any one of the preceding claims, wherein steps c) and d) are performed in one step.
- 20 17. A blast furnace comprising an inner lining, wherein the inner lining comprises at least one refractory according to any one of the preceding claims.
18. Use of a refractory according to any one of claims 1 to 16 in an inner lining of a blast furnace.

INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2012/057338

A. CLASSIFICATION OF SUBJECT MATTER
 INV. F27D1/00 C21B7/06 C04B35/52 C04B35/532
 ADD.
 According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED
 Minimum documentation searched (classification system followed by classification symbols)
 F27D C21B C04B C01B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)
 EPO-Internal, COMPENDEX, INSPEC, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 1 538 223 A2 (SGL CARBON AG [DE]) 8 June 2005 (2005-06-08)	1-7,9, 10, 12-14, 16-18
Y	claims 1,4,6,8,10 paragraphs [0025] - [0026]; examples 1-2 paragraphs [0010], [0018] ----- -/--	15

Further documents are listed in the continuation of Box C.

See patent family annex.

* Special categories of cited documents :

<p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier application or patent but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p>	<p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art</p> <p>"&" document member of the same patent family</p>
---	---

Date of the actual completion of the international search 21 June 2012	Date of mailing of the international search report 28/06/2012
---	--

Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Fax: (+31-70) 340-3016	Authorized officer Buffet, Noemie
--	--

INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2012/057338

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 703 198 A2 (NIPPON STEEL CORP [JP]; NIPPON ELECTRODE COMPANY LTD [JP]) 27 March 1996 (1996-03-27)	1-7,10, 12-14, 16-18
Y	page 4, line 18 claims 1-2 page 4, lines 31-48; example 1 page 7, line 18 - page 8, line 1; examples 3, 4 tables 3, 4 page 2, lines 23-28 page 3, lines 37-39	8
Y	----- DATABASE WPI Week 197716 Thomson Scientific, London, GB; AN 1977-28213Y XP002662274, -& JP 52 032006 A (NIPPON ELECTRODE KK) 10 March 1977 (1977-03-10) abstract table 2	8,11
X	----- JP 6 101975 A (AKECHI CERAMICS KK) 12 April 1994 (1994-04-12)	1-7,9, 10, 12-14, 16-18
Y	An automated translation was consulted (http://www.ipdl.inpit.go.jp/homepg_e.ipdl) abstract claim 1 paragraphs [0005], [0021] examples 1-4; table 1	8,11
X	----- US 3 083 111 A (NICKERSON JOHN D) 26 March 1963 (1963-03-26) claim 1 column 1, lines 8-9, 50-55 column 2, lines 18-20, 26-30	1-6,10, 12-14, 16-18
Y	----- EP 1 671 928 A1 (SGL CARBON AG [DE]) 21 June 2006 (2006-06-21)	15
A	paragraphs [0003], [0007] page 2, lines 5-8, 54-55, paragraph 2 ----- -/--	3

INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2012/057338

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	ASBRAND M ET AL: "Development of a supermicroporous, low thermal conductive carbon grade as blast furnace lining", INTERNATIONAL COLLOQUIUM ON REFRACTORIES IN AACHEN,, vol. 45, 1 January 2002 (2002-01-01), pages 48-51, XP008124362, page 48, column 2, paragraph "Iron content" page 49, column 2, lines 23-24 page 50, column 2, lines 1-6 -----	1,3,4
X	"Prodn. of carbon refractories for blast furnace", WPI WORLD PATENT INFORMATION DERWENT, vol. 4, no. 85, 1985, XP002009200, abstract & JP 59 217672 A (NIPPON STEEL CORP; NIHON DENKIYOKU KK) 7 December 1984 (1984-12-07) -----	1-5,10, 12-14, 16-18
X	EP 1 275 626 A1 (NIPPON STEEL CORP [JP]; NIPPON ELECTRODE COMPANY LTD [JP]) 15 January 2003 (2003-01-15) cited in the application claims 1-2 paragraphs [0001], [0021], [0038] tables 1-3 -----	1-8, 10-14, 16-18

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No PCT/EP2012/057338

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 1538223	A2	08-06-2005	CN 1624155 A 08-06-2005
			DE 10356376 B3 09-06-2005
			EP 1538223 A2 08-06-2005
			JP 4787490 B2 05-10-2011
			JP 2005162607 A 23-06-2005
EP 0703198	A2	27-03-1996	DE 69516963 D1 21-06-2000
			DE 69516963 T2 26-04-2001
			EP 0703198 A2 27-03-1996
			JP 2911371 B2 23-06-1999
			JP 8081706 A 26-03-1996
			PL 310428 A1 18-03-1996
			US 5576254 A 19-11-1996
JP 52032006	A	10-03-1977	JP 1078403 C 25-12-1981
			JP 52032006 A 10-03-1977
			JP 56018559 B 30-04-1981
JP 6101975	A	12-04-1994	NONE
US 3083111	A	26-03-1963	NONE
EP 1671928	A1	21-06-2006	AT 380159 T 15-12-2007
			CN 1847145 A 18-10-2006
			DE 602004010538 T2 13-11-2008
			EP 1671928 A1 21-06-2006
			ES 2297331 T3 01-05-2008
			JP 4856422 B2 18-01-2012
			JP 2006169103 A 29-06-2006
EP 1275626	A1	15-01-2003	AT 329889 T 15-07-2006
			CN 1366515 A 28-08-2002
			DE 60120675 T2 14-06-2007
			EP 1275626 A1 15-01-2003
			JP 3593101 B2 24-11-2004
			PL 351820 A1 16-06-2003
			US 2002183189 A1 05-12-2002
			WO 0174738 A1 11-10-2001