



US006941625B2

(12) **United States Patent**
Namerikawa et al.

(10) **Patent No.:** US 6,941,625 B2
(45) **Date of Patent:** Sep. 13, 2005

(54) **METHOD OF PRODUCING A
PIEZOELECTRIC/ELECTROSTRICTIVE
DEVICE**

4,814,659 A 3/1989 Sawada
4,889,760 A * 12/1989 Kippenberg et al. 428/192
4,906,512 A * 3/1990 Roess 428/192
5,043,621 A 8/1991 Culp

(75) Inventors: **Masahiko Namerikawa, Seto (JP);
Kazuyoshi Shibata, Mizunami (JP);
Masaki Iwamoto, Kasugai (JP)**

(Continued)

(73) Assignee: **NGK Insulators, Ltd., Nagoya (JP)**

FOREIGN PATENT DOCUMENTS

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

DE	197 32 571	7/1998
EP	1 091 424	4/2001
JP	61-182284	8/1986
JP	63-295269	12/1988
JP	4-309274	10/1992

(21) Appl. No.: **10/950,617**

OTHER PUBLICATIONS

(22) Filed: **Sep. 27, 2004**

U.S. Appl. No. 09/672,069, filed Sep. 28, 2000, Takeuchi et al.
Smith N.C., "Tapered Piezoelectric Actuator", IBM Technical Disclosure Bulletin, vol. 27, No. 6, Nov. 1, 1984, pp. 3568.

(65) **Prior Publication Data**

US 2005/0035690 A1 Feb. 17, 2005

Related U.S. Application Data

Primary Examiner—A. Dexter Tugbang
Assistant Examiner—Tai Nguyen
(74) *Attorney, Agent, or Firm*—Burr & Brown

(62) Division of application No. 10/631,293, filed on Jul. 31, 2003, now Pat. No. 6,813,815, which is a continuation of application No. 09/918,274, filed on Jul. 30, 2001, now abandoned.

(57) **ABSTRACT**

(51) **Int. Cl.**⁷ **H04R 17/00**; H01L 41/04; H01L 41/08; H01L 41/18

A method of producing a piezoelectric/electrostrictive device in which a piezoelectric/electrostrictive element including a substantially trapezoidal laminate having narrower and wider surfaces lying substantially in parallel to each other and first and second surfaces opposed to each other between the narrower and wider surfaces. The first and second surfaces are inclined at given angles to one of the narrower and wider surfaces. The laminate includes piezoelectric/electrostrictive layers and interposed internal electrodes, the internal electrodes being broken up into a first and a second group, each of the first group internal electrodes lying over one of the second group internal electrodes through one of the piezoelectric/electrostrictive layers. A first external electrode is formed on the first surface of the laminate and is coupled to the first group internal electrodes. A second external electrode is formed on the second surface of the laminate and is coupled to the second group internal electrodes.

(52) **U.S. Cl.** **29/25.35**; 29/830; 29/831; 29/426.1; 29/426.2; 29/762; 29/851; 310/367


(58) **Field of Search** 29/25.35, 830, 29/831, 426.1, 426.2, 762, 851; 310/326, 322, 367, 324, 334; 156/89.11, 89.2-6, 101; 427/58, 79; 428/292; 264/618

(56) **References Cited**

U.S. PATENT DOCUMENTS

3,474,268 A	10/1969	Rudnick	
3,679,950 A *	7/1972	Rutt	361/321.4
3,879,643 A	4/1975	Hubbard	
4,353,957 A *	10/1982	Rutt et al.	428/110
4,523,121 A	6/1985	Takahashi et al.	
4,632,856 A	12/1986	Marcus et al.	

3 Claims, 26 Drawing Sheets



U.S. PATENT DOCUMENTS

			5,939,816 A	8/1999	Culp	
			6,274,966 B1	8/2001	Kohno et al.	
			6,414,418 B1	7/2002	Heinz et al.	
			2002/0194717 A1	12/2002	Takeuchi et al.	
5,153,477 A	10/1992	Jomura et al.				
5,182,484 A	1/1993	Culp				
5,237,239 A	8/1993	Inoue et al.				
5,281,899 A	1/1994	Culp				
5,601,673 A	* 2/1997	Alexander 156/89.12				* cited by examiner

FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG.5




FIG.6




FIG. 7




FIG. 8




FIG. 9




FIG. 10




FIG.12




FIG.13




FIG. 14




FIG. 15




FIG. 16




FIG. 17




FIG. 18




FIG.19




FIG.20




FIG.21




FIG.22




FIG.23




FIG.24




FIG.25




FIG.26




FIG. 27




FIG. 28




FIG. 29




FIG.30




FIG.31




FIG.32




FIG.33




FIG.34




FIG.35




FIG.36




FIG.37




FIG.38





FIG. 39



METHOD OF PRODUCING A PIEZOELECTRIC/ELECTROSTRICTIVE DEVICE

CROSS REFERENCE TO RELATED APPLICATIONS

This application is a division of U.S. application Ser. No. 10/631,293, filed Jul. 31, 2003, now U.S. Pat. No. 6,813,815 allowed, which is a continuation of U.S. application Ser. No. 09/918,274, filed Jul. 30, 2001, now abandoned, the entireties of which are incorporated herein by reference.

FIELD OF THE INVENTION

The present invention relates generally to a piezoelectric/electrostrictive element, a piezoelectric/electrostrictive device and a production method thereof, and more particularly to a laminated piezoelectric/electrostrictive element and a laminated piezoelectric/electrostrictive device made up of piezoelectric/electrostrictive layers and internal electrode layers laminated alternately, and a production method thereof.

BACKGROUND OF THE INVENTION

In recent years, a variety of fields such as optics, magnetic recording, precision machining, and printing demand a displacement element for controlling, for example, the length or position of an optical path in the order of a submicron or vibrations precisely. As such a displacement element meeting the above demand, there is one employing displacement provided by a reverse piezoelectric effect or an electrostrictive effect taken place when the voltage is applied to a piezoelectric/electrostrictive material made of, for example, a ferroelectric substance.

Conventionally, as such a displacement element, a laminated piezoelectric element **100**, as shown in FIG. **34**, which is disclosed in Japanese Patent First Publication No. 4-309274 is known. The piezoelectric/electrostrictive element **100** includes, as shown in FIG. **34**, a lamination **104** formed by laminating a plurality of piezoelectric ceramic layers **101** and electrode layers **102** alternately and a pair of electrically insulated external electrodes **104** and **105** which connect the electrode layers **102** alternately on opposed side surfaces of the laminate **103** and are so formed as to extend to upper and lower surfaces of the laminate **103**. In the laminated piezoelectric element **100**, ridges defined by the side surfaces and the upper and lower surfaces of the laminate **103** are rounded to an extent where the radius of curvature of the ridges exceeds half the thickness of the piezoelectric ceramic layers **101**.

The production of the laminated piezoelectric element **100** shown in FIG. **34** is accomplished by first weighing and grinding raw material, mixing it with binder, and defoaming the mixture, after which the mixture is shaped into a sheet from which rectangular green sheets **101A** are punched (which will be the piezoelectric ceramic layers **101** by baking). A conductive paste is printed over a given area of one surface of the green sheet **101A** to form the electrode layer **102**. Next, the green sheets **101A** on which the electrode layers **102** are printed properly are, as shown in FIG. **35**, laminated and bonded by pressure and cut as needed after which it is baked to produce the laminate **103** as shown in FIG. **36**. As a result, the green sheets **101A** are, as mentioned above, baked to produce the piezoelectric ceramic layers **101**. In the laminate **103**, arrangement positions of the electrode layers **102** are predetermined on a pair

of opposed side surfaces thereof so that the electrode layers **102** may be exposed alternately. Afterwards, on given areas of upper and lower surfaces of the thus produced laminate **103**, an external upper surface electrode **104A**, and an external lower surface electrode **105A** are formed. Next, on a pair of opposed side surfaces **106** and **107** to which the electrode layers **102** of the laminate **103** are exposed alternately, external side surface electrodes (thick film electrodes) **104B** and **105B** are formed to make the laminated piezoelectric element **100** shown in FIG. **34**. The external side surface electrode **104B** is so formed as to connect with the external upper surface electrode **104A**, while the external side surface electrode **105B** is so formed as to connect with the external lower surface electrode **105A**. As a method of forming the above-mentioned external electrodes **104** and **105**, there is a dipping method or an evaporation method.

FIG. **37** shows an actuator **200** utilizing the thus constructed laminated piezoelectric element **100**. The actuator **200** has the laminated piezoelectric element **100** secured on a movable plate (diaphragm) **110** by an adhesive **111**.

As another displacement element, a piezoelectric displacement element, as disclosed in Japanese Patent First Publication No. 63-295269, is known which is equipped with a plurality of opposed inner electrode layers in a ceramic thin plate exhibiting the piezoelectric effect. Corners that are boundaries of side surfaces and upper and lower surfaces of the ceramic thin plate are chamfered mechanically. On front and reverse surfaces and the opposed side surfaces of the ceramic thin plate, a pair of opposed surface electrodes connecting with internal electrode layers is so formed that the electrodes are electrically insulated from each other. The opposed surface electrodes are formed on the surfaces of the ceramic thin plate by a physical vapor deposition method such as a sputtering method or a vapor deposition method or a film forming method such as plating.

SUMMARY OF THE INVENTION

The laminated piezoelectric element **100**, as shown in FIG. **34**, has problems in that the possibility that edges of the green sheets **101A** (shown in FIG. **35**) are deformed, damaged, or broken by handling is high. Particularly, a thin piezoelectric element in which a total film thickness (thickness) of the laminate **103** is 100 μm or less has a high possibility that the green sheets **101A** are broken by handling. The conventional laminated piezoelectric element **100**, thus, has a problem that the fabrication yield is low.

The piezoelectric displacement element, as disclosed in Japanese Patent First Publication No. 63-295269 is chamfered by mechanically cutting end portions of the ceramic thin film diagonally, which results in an increase in production processes. The mechanical cutting may also cause damage to the ceramic thin film.

The invention was made in order to solve the above problems. It is, thus, an object of the invention to provide a piezoelectric/electrostrictive element and a piezoelectric/electrostrictive device which are excellent in strength, shock resistance, handling, dimensional accuracy, positional accuracy, stability of element characteristics, and fabrication yield, and to provide a production method thereof.

In order to solve the above problems, the first feature of the invention lies in a piezoelectric/electrostrictive element including a substantially trapezoidal laminate having narrower and wider surfaces lying substantially in parallel to each other and first and second surfaces opposed to each other between the narrower and wider surfaces. The first and

second surfaces are inclined at given angles with respect to one of the narrower and wider surfaces. The trapezoidal laminate is made up of a plurality of piezoelectric/electrostrictive layers and a plurality of internal electrodes, each of which is disposed between an adjacent two of the piezoelectric/electrostrictive layers. The internal electrodes are divided into a first and a second group, each of the first group internal electrodes lying over one of the second group internal electrodes through one of the piezoelectric/electrostrictive layers. A first external electrode is formed on the first surface of the laminate, and is coupled to the first group internal electrodes; and a second external electrode formed on the second surface of said laminate, said second external electrodes being coupled to the second group internal electrodes.

The thus constructed piezoelectric/electrostrictive element is of a substantially trapezoidal shape which decreases in width from one of the bottom surfaces to the other bottom surface, so that the angle which the slant surfaces of both sides make with the other bottom surface is obtuse, thus resulting in an increase in strength of a ridge portion (a corner) defined by the other bottom surface and the slant surfaces. Therefore, for example, when the other (narrower) bottom surface is secured on a movable plate (diaphragm), the breakage or damage of the ridge portion caused by an external force or vibrations of the piezoelectric/electrostrictive element itself is avoided. When the other bottom surface of the piezoelectric/electrostrictive element is secured on the movable plate (diaphragm) by adhesive, a recess-shaped (V-groove shaped) gap defined by the movable plate and the slant surfaces of both the sides of the piezoelectric/electrostrictive element can be filled with the adhesive, thereby resulting in a further increase in force (bonding strength) which secures the piezoelectric/electrostrictive element to the movable plate. The existence of the adhesive in the recess-shaped gap offers the effect of avoiding removal of the piezoelectric/electrostrictive element from the movable plate even if the stress arising from a difference in thermal expansion between the piezoelectric/electrostrictive element and the movable plate is produced.

The piezoelectric/electrostrictive layers are decreased in width gradually in one of the directions of lamination. Thus, for example, when the external electrode layers, the piezoelectric/electrostrictive layers, and the internal electrode layers are laminated in a given order, it is possible to pile up the piezoelectric/electrostrictive layers on a backing layer stably. Therefore, when the external electrode layers, the piezoelectric/electrostrictive layers, and the internal electrode layers are laminated by printing using, for example, a screen printing method, the printing is achieved easily since a lower one of the piezoelectric/electrostrictive layers has an area greater than that of an upper one of the piezoelectric/electrostrictive layers. The screen printing method makes it possible to apply, for example, via a conductive paste, the external electrode layers to the slant surface (a side surface portion) of the laminate.

Both the external electrode layers formed on the side surface portions extend along the wider surface of said laminate, thereby ensuring a joint area (a pad portion) which establishes a joint of wires for applying a drive voltage to the external electrode layers or wires for detecting a produced voltage, which facilitates connection of the wires. Particularly, as described above, when the narrower bottom surface of the laminate is secured on the movable plate, it is possible to bond the wires on a sufficient area of the wider bottom surface. The width of one of the external electrode layers extending on the wider bottom surface of the laminate

is greater, thereby allowing the one of the external electrode layers to be used as a voltage applying electrode or a voltage detecting electrode.

Additionally, one of the surfaces of the piezoelectric/electrostrictive element may be formed by a piezoelectric/electrostrictive layer to increase a bonding strength using adhesive has the affinity to the piezoelectric/electrostrictive layers, for example, when the side of the piezoelectric/electrostrictive layer is bonded to the movable plate.

The second feature of the invention lies in a piezoelectric/electrostrictive device in which a piezoelectric/electrostrictive element includes a substantially trapezoidal laminate having narrower and wider surfaces lying substantially in parallel to each other and first and second surfaces opposed to each other between the narrower and wider surfaces. The first and second surfaces are inclined at given angles with respect to one of the narrower and wider surfaces. The trapezoidal laminate is made up of a plurality of piezoelectric/electrostrictive layers and a plurality of internal electrodes, each of which is disposed between an adjacent two of the piezoelectric/electrostrictive layers. The internal electrodes are divided into a first and a second group, each of the first group internal electrodes lying over one of the second group internal electrodes through one of the piezoelectric/electrostrictive layers. A first external electrode is formed on the first surface of the laminate, and is coupled to the first group internal electrodes. A second external electrode is formed on the second surface of said laminate, and is coupled to the second group internal electrodes. The piezoelectric/electrostrictive element is bonded to a surface of a movable plate on a side of the narrower surface of the laminate.

In the piezoelectric/electrostrictive device, the narrower bottom surface of the laminate is bonded to the surface of the movable plate, so that a corner portion having an obtuse angle defined by the narrower bottom surface and both side surface portions engages the movable plate. The corner having the obtuse angle will have strength greater than a corner having an acute angle or a right angle and offers the effect of increasing the durability such as the strength or shock resistance of the piezoelectric/electrostrictive device.

A gap (recess) formed by both the side surface portions of the piezoelectric/electrostrictive device and the movable plate defines a liquid sump of adhesive having flowability prior to solidification and works to absorb an excess or a lack of the adhesive caused by a variation in quantity of the applied adhesive or undulations of the movable plate and the piezoelectric/electrostrictive element. The application of a proper quantity of the adhesive to a suitable area of the movable plate will enable automatic alignment of the piezoelectric/electrostrictive element with a proper position with aid of an effect such as surface tension of the adhesive within the gap.

Additionally, filling the gap with the adhesive enables firm installation of the piezoelectric/electrostrictive element on the movable plate. If the adhesive with which the gap is filled keeps the elasticity after being solidified, it alleviates the stress arising from a difference in thermal expansion between the movable plate and the piezoelectric/electrostrictive element, thereby avoiding removal of the piezoelectric/electrostrictive element from the movable plate. Specifically, the filling of the gap defined by the side portions of the piezoelectric/electrostrictive element and the movable plate with the adhesive will restrict a reduction in strength to fix the piezoelectric/electrostrictive element even if the piezoelectric/electrostrictive element is decreased in size.

5

Further, the external electrode layers formed on both the side surface portions of the piezoelectric/electrostrictive element extend on the wider bottom surface of the laminate, thus providing a joint area sufficient for establishing connection of external wires to the external electrode layers.

The movable plate is made of a conductive material. One of the external electrode layers of the piezoelectric/electrostrictive element is connected to the movable plate, thereby increasing a wiring space of the other external electrode layer and facilitating ease of a connecting operation.

The third feature of the invention lies in a method of producing a piezoelectric/electrostrictive element including the following steps:

a first step of preparing a ceramic substrate having a given width;

a second step of forming a laminate on the ceramic substrate, the laminate being made up of first and second portions laid to overlap one another;

a third step of baking the ceramic substrate and the laminate at a given temperature; and

a fourth step of removing the laminate from the ceramic substrate;

the first portion of the laminate is formed using the following steps:

printing a first electrode layer and a second electrode layer on the ceramic substrate which are disposed at a given interval away from one another;

forming a piezoelectric/electrostrictive layer using a piezoelectric/electrostrictive paste on the first and second electrode layers so as to cover portions of the first and second electrode layers other than edge portions thereof lying outward in a widthwise direction of the ceramic substrate; and

forming a first electrode layer on an upper surface and a side surface of the piezoelectric/electrostrictive layer so as to establish an electric connection only with the first electrode layer lying immediately beneath the first electrode layer formed in this step.

The second portion of the laminate is formed by performing the following set of steps a given number of times which include:

forming a piezoelectric/electrostrictive layer using a piezoelectric/electrostrictive paste on an uppermost one of the first electrode layers, the piezoelectric/electrostrictive layer formed in this step having a width smaller than that of the piezoelectric/electrostrictive layer lying immediately beneath the piezoelectric/electrostrictive layer formed in this step;

forming a second electrode layer on an upper surface and a side surface of an uppermost one of the piezoelectric/electrostrictive layers so as to establish an electric connection only with the second electrode layer lying immediately beneath the second electrode layer formed in this step;

forming a piezoelectric/electrostrictive layer using a piezoelectric/electrostrictive paste on an uppermost one of the second electrode layers, the piezoelectric/electrostrictive layer formed in this step having a width smaller than that of the piezoelectric/electrostrictive layer lying immediately beneath the piezoelectric/electrostrictive layer formed in this step; and

forming a first electrode layer on an upper surface and a side surface of an uppermost one of the piezoelectric/electrostrictive layers so as to establish an electric

6

connection only with the first electrode layer lying immediately beneath the first electrode layer formed in this step.

In the method of producing the thus constructed piezoelectric/electrostrictive element according to the third feature, it is possible to pile up the piezoelectric/electrostrictive layers by printing so that areas thereof decrease gradually, thus resulting in ease of manufacture. The piezoelectric/electrostrictive layers, the first electrode material layer, and the second electrode material layer may be formed using a printing method, thus allowing a piezoelectric/electrostrictive element to be produced which is higher in dimensional accuracy, positional accuracy, less susceptible to adverse effects, such shifting during transportation, and deformation caused by the transportation, and eliminating the need for process of transporting and piling up the piezoelectric/electrostrictive layers, which avoids breakage or damage of the piezoelectric/electrostrictive layers caused by handling thereof.

The formation of portions which become continuous external side surface electrodes on both sides of the laminate is achieved in sequence by repeating printing of the first and second electrode material layers, thus eliminating the need for a process of forming additional external side surface electrodes.

Further, a film which disappears upon baking of the laminate is preformed on a ceramic substrate used in producing the piezoelectric/electrostrictive element, thereby resulting in easy removal of the piezoelectric/electrostrictive element from the ceramic substrate when baked.

In this invention, the external side surface electrode which defines an outermost contour of the piezoelectric/electrostrictive element as viewed in a plane may be formed by printing with high positional accuracy. For example, when the piezoelectric/electrostrictive element is positioned by positioning pins to mount the piezoelectric/electrostrictive element on a movable plate, it is possible to arrange the piezoelectric/electrostrictive element with high positional accuracy.

The fourth feature of the invention lies in a method of producing a piezoelectric/electrostrictive device in which a piezoelectric/electrostrictive element includes a substantially trapezoidal laminate having narrower and wider surfaces lying substantially in parallel to one another and first and second surfaces opposed to one another between the narrower and wider surfaces. The first and second surfaces are inclined at given angles with respect to one of the narrower and wider surfaces. The trapezoidal laminate is made up of a plurality of piezoelectric/electrostrictive layers and a plurality of internal electrodes, each of which is disposed between an adjacent two of the piezoelectric/electrostrictive layers. The internal electrodes are broken up into a first and a second group, each of the first group internal electrodes lying over one of the second group internal electrodes through one of the piezoelectric/electrostrictive layers. A first external electrode is formed on the first surface of the laminate and is coupled to the first group internal electrodes. A second external electrode is formed on the second surface of the laminate and is coupled to the second group internal electrodes. The piezoelectric/electrostrictive element is bonded to a surface of a movable plate by an adhesive.

In the method of producing the thus constructed piezoelectric/electrostrictive device, the narrower bottom surface side of the laminate is bonded to the movable plate through the adhesive, thus facilitating ease of filling a gap

(recess) defined by slants of both side surfaces of the piezoelectric/electrostrictive element and the movable plate with the adhesive. This allows the gap to be filled with the adhesive in quantity suitable for the size of the gap, thus ensuring the bonding strength. When piezoelectric/electrostrictive elements are joined to each other, gaps (recesses) are also formed by side surface portions of the piezoelectric/electrostrictive elements, thus offering a similar effect of increasing the bonding strength.

The narrower bottom surface of the piezoelectric/electrostrictive element is bonded to the movable plate, so that angles which the side surface portions of the piezoelectric/electrostrictive element make with the movable plate will be obtuse, thus providing the effect of avoiding local breakage or damage of the piezoelectric/electrostrictive element. The same is true for a case where piezoelectric/electrostrictive elements are bonded at narrower bottom surfaces to one another.

Automatic positioning of the piezoelectric/electrostrictive element is achieved by setting a coefficient of viscosity of the adhesive applied on the surface of the movable plate to a given value to enable the filling with adhesive of the gaps (recesses) defined by the slants of the side surfaces of the piezoelectric/electrostrictive element and the movable plate.

BRIEF DESCRIPTION OF THE DRAWINGS

For a fully understanding of the nature and objects of the invention, reference should be made to the following detailed description of a preferred mode of practicing the invention, read in connection with the accompanying drawings in which:

FIG. 1 is a perspective view which shows a piezoelectric/electrostrictive element according to the first embodiment of the invention;

FIG. 2 is a plan view of a piezoelectric/electrostrictive element according to the first embodiment of the invention;

FIG. 3 is a bottom view of a piezoelectric/electrostrictive element according to the first embodiment of the invention;

FIG. 4 is a cross-sectional elevation on section line A—A of FIG. 2;

FIG. 5 is a side view of a piezoelectric/electrostrictive device according to the first embodiment of the invention;

FIG. 6 is a plan view of a piezoelectric/electrostrictive device according to the first embodiment of the invention;

FIG. 7 is an explanatory side view which represents usage of a piezoelectric/electrostrictive device according to the first embodiment of the invention;

FIG. 8 is an explanatory side view which shows a modified embodiment 1 of a piezoelectric/electrostrictive device according to the first embodiment of the invention;

FIG. 9 is an explanatory side view which shows a modified embodiment 2 of a piezoelectric/electrostrictive device according to the first embodiment of the invention;

FIG. 10 is an explanatory side view which shows a modified embodiment 3 of a piezoelectric/electrostrictive device according to the first embodiment of the invention;

FIG. 11 is an explanatory side view which shows a modified embodiment 4 of a piezoelectric/electrostrictive device according to the first embodiment of the invention;

FIG. 12 is a plan view which illustrates a production method of a piezoelectric/electrostrictive element according to the first embodiment of the invention;

FIG. 13 is a side view which illustrates a production method of a piezoelectric/electrostrictive element according to the first embodiment of the invention;

FIG. 14 is a plan view which illustrates a production method of a piezoelectric/electrostrictive element according to the first embodiment of the invention;

FIG. 15 is a process sectional view which shows a production method of a piezoelectric/electrostrictive element according to the first embodiment of the invention;

FIG. 16 is a process sectional view which shows a production method of a piezoelectric/electrostrictive element according to the first embodiment of the invention;

FIG. 17 is a process sectional view which shows a production method of a piezoelectric/electrostrictive element according to the first embodiment of the invention;

FIG. 18 is a process sectional view which shows a production method of a piezoelectric/electrostrictive element according to the first embodiment of the invention;

FIG. 19 is a process sectional view which shows a production method of a piezoelectric/electrostrictive element according to the first embodiment of the invention;

FIG. 20 is a process sectional view which shows a production method of a piezoelectric/electrostrictive element according to the first embodiment of the invention;

FIG. 21 is a process sectional view which shows a production method of a piezoelectric/electrostrictive element according to the first embodiment of the invention;

FIG. 22 is a process sectional view which shows a production method of a piezoelectric/electrostrictive element according to the first embodiment of the invention;

FIG. 23 is a process sectional view which shows a production method of a piezoelectric/electrostrictive element according to the first embodiment of the invention;

FIG. 24 is a process sectional view which shows a production method of a piezoelectric/electrostrictive element according to the first embodiment of the invention;

FIG. 25 is a side view of a piezoelectric/electrostrictive element according to the second embodiment of the invention;

FIG. 26 is a plan view of a piezoelectric/electrostrictive element according to the second embodiment of the invention;

FIG. 27 is a side view of a piezoelectric/electrostrictive device according to the second embodiment of the invention;

FIG. 28 is a plan view which represents a production method of a piezoelectric/electrostrictive device according to the second embodiment of the invention;

FIG. 29 is a plan view which represents a production method of a piezoelectric/electrostrictive device according to the second embodiment of the invention;

FIG. 30 is a plan view which illustrates a movable plate positioning jig used in a production method of a piezoelectric/electrostrictive device according to the second embodiment of the invention;

FIG. 31 is a side view which illustrates a movable plate positioning jig used in a production method of a piezoelectric/electrostrictive device according to the second embodiment of the invention;

FIG. 32 is a plan view which illustrates an element positioning jig use in a production method of a piezoelectric/electrostrictive device according to the second embodiment of the invention;

FIG. 33 is a side view which shows a combination of a movable plate positioning jig and an element positioning jig used in a production method of a piezoelectric/electrostrictive device according to the second embodiment of the invention;

FIG. 34 is a perspective view which shows a conventional piezoelectric/electrostrictive element;

FIG. 35 is a perspective view which shows a production process of a conventional piezoelectric/electrostrictive element;

FIG. 36 is a perspective view which shows a laminate of a conventional piezoelectric/electrostrictive element;

FIG. 37 is a side view which shows a conventional piezoelectric/electrostrictive device;

FIG. 38 is an explanatory plan view which shows positioning of a conventional piezoelectric/electrostrictive element; and

FIG. 39 is an enlarged partial side view of a conventional piezoelectric/electrostrictive element.

DETAILED DESCRIPTION OF THE INVENTION

A piezoelectric/electrostrictive element, a piezoelectric/electrostrictive device, and a production method thereof will be explained in detail with reference to embodiments as illustrated in the drawings. The attention should be paid to the fact that the drawings are schematic, and the thickness and a film thickness ratio of material layers are different from those in actual use. Practical thickness or dimensions should be decided with reference to the following explanation. Of course, parts whose dimensional relation and ratio are different from one another are included in the several drawings.

The piezoelectric/electrostrictive element and the piezoelectric/electrostrictive device according to the invention includes an element which converts electric energy into mechanical energy, or vice versa by the reverse piezoelectric effect or the electrostrictive effect, or the piezoelectric effect and a device equipped with the same. The piezoelectric/electrostrictive device of the present invention may be employed as passive elements such as acceleration sensors or impact sensors utilizing the piezoelectric effect, as well as active elements such as a variety of actuators or transducers, especially displacement elements using displacement by the reverse piezoelectric effect or the electrostrictive effect.

FIRST EMBODIMENT OF THE INVENTION Piezoelectric/Electrostrictive Element

First, an outline of a structure of a piezoelectric/electrostrictive element of this embodiment will be described using FIGS. 1 to 4. The piezoelectric/electrostrictive element 10 of this embodiment, as shown in FIG. 1, includes, for example, four piezoelectric/electrostrictive layers 11A, 11B, 11C, and 11D, for example, three internal electrode layers 12A, 12B, and 12C interposed between an adjacent two of the piezoelectric/electrostrictive layers 11A, 11B, 11C, and 11D. A pair of external electrode layers 14 and 15 connect the internal electrode layers 12A, 12B, and 12C in an alternate manner alternately. The piezoelectric/electrostrictive element 10 has a substantially trapezoidal laminated structure in which upper and lower opposed bottom surfaces are both rectangular.

As shown in FIG. 1, an area of one of the bottom surfaces (upper surface) f1 of the piezoelectric/electrostrictive element 10 is wider than that of the other bottom surface (lower surface) f2. As shown in FIG. 1, the width of the wider bottom surface f1 (i.e., the length in an arrow direction as expressed by x in the drawing) is W1, and the length thereof (i.e., the length in an arrow direction as expressed by y in the drawing) is L1. FIG. 2 is a plan view which shows the wider bottom surface f1. FIG. 3 is a bottom illustration of the

piezoelectric/electrostrictive element 10 as viewed from the narrower bottom surface f2. As shown in FIG. 3, the width of the bottom surface f2 is W2, which is smaller than the width W1 of the bottom surface f1. The length of the bottom surface f2 is equal to the length L1 of the bottom surface f1.

As can be seen from the bottom illustration of the piezoelectric/electrostrictive element in FIG. 3, both side edges of the bottom surface f2 are located inward from both side edges of the bottom surface f1 by the same distance W3 and overlap with the bottom surface f1 in a lengthwise direction. The piezoelectric/electrostrictive element 10, thus, has slant surfaces f3 and f4, as shown in FIGS. 1 and 3, formed on the sides thereof in the direction x. The pair of slant surfaces f3 and f4 are inclined in a direction in which they approach each other from the wider bottom surface f1 to the narrower bottom surface f2.

The external structure of the piezoelectric/electrostrictive element 10 has been explained above. Next, the structure and positional relation of parts making up the piezoelectric/electrostrictive element 10 will be explained in detail using FIGS. 1 to 4. FIG. 4 is a cross-sectional view taken along section line A—A shown in FIG. 2.

In the piezoelectric/electrostrictive element 10 according to this embodiment, the piezoelectric/electrostrictive layers 11A, 11B, 11C, and 11D are made of, for example, lead zirconium titanate (PZT). When formed by PZT, the strength of the piezoelectric/electrostrictive layers 11A, 11B, 11C, and 11D is on the order of 70 MPa. The internal electrode layers 12A, 12B, and 12C and the external electrode layers 14 and 15 are made of, for example, platinum (Pt).

In the piezoelectric/electrostrictive element 10, the piezoelectric/electrostrictive layers 11A, 11B, 11C, and 11D which are laminated from the bottom surface f1 to the bottom surface f2 decrease in width gradually, so that the whole of the piezoelectric/electrostrictive element 10 has, as mentioned above, the slant surfaces f3 and f4 formed on the side portions.

Between the piezoelectric/electrostrictive layers 11A and 11B, the internal electrode layer 12A is disposed which extends from the slant surface f3 toward the slant surface f4. The internal electrode 12A does not contact the slant surface f4. Between the piezoelectric/electrostrictive layers 11B and 11C, the internal electrode layer 12B is disposed which extends from the slant surface f4 toward the slant surface f3. The internal electrode 12B does not contact the slant surface f3. Between the piezoelectric/electrostrictive layers 11C and 11D, the internal electrode layer 12C is disposed which extends, like the above described internal electrode layer 12A, from the slant surface f3 toward the slant surface f4, and does not contact the slant surface f4. It is advisable that the end edges of the above described internal electrodes 12A and 12C on the side of the slant surface f3 lie at the same location as viewed on a plane and overlap vertically, however, the internal electrode layer 12C may be shorter in the x direction extending from the slant surface f3.

Further, slant portions 14A and 15A of the external electrode layers 14 and 15 are formed on the slant surfaces f3 and f4. In this embodiment, the width of the slant portion 14A (i.e., the length in a direction of slant surface inclination) is greater than that of the slant portion 15A. The slant portion 14A is, as shown in FIG. 4, so formed as to cover the whole of the slant surface f4, thereby establishing connection of the slant portion 14A of the external electrode layer 14 to the internal electrode layer 12B. The slant surface portion 15A is formed to establish a connection of the slant portion 15A of the external electrode layer 15 to the internal electrode layers 12A and 12C. Specifically, the external

11

electrode layers **15** and **14** are so constructed as to connect with the internal electrode layers **12A**, **12B**, and **12C** alternately.

On an upper surface (i.e., an outer surface) of the widest piezoelectric/electrostrictive layer **11A**, upper surface portions **14B** and **15B** of the external electrode layers **14** and **15** are, as shown in FIGS. **1** and **4**, formed which extend from x-direction side edges of the outer surface of the piezoelectric/electrostrictive layer **11A** so as to approach one another. The upper surface portions **14B** and **15B** of the external electrode layers **14** and **15** are separate from one another on the side of one of the edge portions of the piezoelectric/electrostrictive element **10**. Specifically, in this embodiment, the width (i.e., the length in the x direction) of the upper surface portion **14B** of the external electrode layer **14** is greater than the width of the external electrode layer **15**. The edge of the upper surface portion **14B** of the external electrode layer **14** on the side of the slant surface **f3** lies at the same location as that of the edge of the above described internal electrode layer **12B** as viewed on a plane, but however, it is not limited to this location.

On a lower surface (i.e., an outer surface) of the narrowest piezoelectric/electrostrictive layer **11D**, the lower surface portion **14C** of the external electrode layer **14** is formed. The lower surface portion **14C** extends from a lower edge of the slant surface **14A** toward the slant surface **f3**. An edge of the lower surface portion **14C** on the side of the slant surface **f3** is set to lie at the same location as that of an edge of the internal electrode layer **12B** as viewed on a plane, however, it is not limited to this location.

In this embodiment, the piezoelectric/electrostrictive layers **11A**, **11B**, **11C**, and **11D** are four layers. The internal electrode layers **12A**, **12B**, and **12C** are three layers. The upper surface portion **14B** and the lower surface portion **14C** of the external electrode layer **14** are so arranged on the upper and lower surfaces of the piezoelectric/electrostrictive element **10** as to function as opposed electrodes, however, the number of the layers and the number of the internal electrode layers connecting with the external electrode layers **14** and **15**, respectively, may be equal to or unequal number with respect to one another. The number of the electrode layers are determined in terms of relations to a drive voltage and the degree of displacement of a movable plate, as will be described later. An increase in total number of the piezoelectric/electrostrictive layers will cause a driving force driving the movable plate on which the piezoelectric/electrostrictive element **10** is installed to be increased, thus enabling a greater displacement and result in an increase in rigidity of the piezoelectric/electrostrictive element **10**, thereby increasing the resonance frequency, which allows the speed of a displacement operation to be increased easily.

As a practical material of the piezoelectric/electrostrictive layers **11A**, **11B**, **11C**, and **11D** in this embodiment, ceramic may be used which contains one or a mixture of lead zirconate, lead titanate, lead magnesium-niobate, lead nickel niobate, lead zinc niobate, lead manganese niobate, lead antimony stannate, lead manganese tungstate, lead cobalt niobate, barium titanate, sodium bismuth titanate, potassium sodium niobate, and strontium bismuth tantalate in addition to the above described lead zirconium titanate (PZT).

Particularly, material whose main components are lead zirconate, lead titanate, and lead magnesium niobate or material whose main component is sodium bismuth titanate have high electromechanical coupling factor and piezoelectric constant, are low in reactivity to a firing setter (in this case, ceramic oxide such as zirconia, alumina, or magnesia),

12

and provide stable compositions when the piezoelectric/electrostrictive layers **11A**, **11B**, **11C**, and **11D**).

Further, one or some of oxides such as lanthanum (La), calcium (Ca), strontium (Sr), molybdenum (Mo), tungsten (W), barium (Ba), niobium (Nb), zinc (Zn), nickel (Ni), manganese (Mn), cerium (Ce), cadmium (Cd), chromium (Cr), cobalt (Co), antimony (Sb), iron (Fe), yttrium (Y), tantalum (Ta), lithium (Li), bismuth (Bi), and tin (Sn) may be mixed with the above described ceramic material.

Additionally, for example, lanthanum (La) and strontium (Sr) may be added to main components of lead zirconate, lead titanate, and lead magnesium niobate for providing the advantage that it is possible to adjust the coercive electric field and piezoelectric characteristics.

The addition of an easy-to-vitrify material such as silica is preferably avoided. The reason for this is that material such as silica reacts easily with a piezoelectric/electrostrictive material during heat treatment (i.e., firing) of the piezoelectric/electrostrictive layers **11A**, **11B**, **11C**, and **11D** and change components thereof, thus resulting in the deterioration of piezoelectric characteristics.

As the piezoelectric/electrostrictive layers **11A**, **11B**, **11C**, and **11D**, the above described variety of piezoelectric ceramics are preferably used, but electrostrictive ceramics, ferroelectric ceramics or antiferroelectric ceramics may be employed. However, in a case where the piezoelectric/electrostrictive element **10** is used to position a magnetic head of a hard disc drive, the linearity to the amount of displacement of moving parts, a drive voltage, or an output voltage is important. The use of material that is smaller in electric-field strain hysteresis is, thus, preferable. Specifically, material having a coercive electric field of 10 kV/mm or less is preferably used.

The external electrode layers **14** and **15** are preferably made of metal which is solid at room temperature and excellent in conductivity. As such a metal, in addition to the above described platinum (Pt), one of aluminum (Al), titanium (Ti), chromium (Cr), iron (Fe), cobalt (Co), nickel (Ni), copper (Cu), zinc (Zn), niobium (Nb), molybdenum (Mo), ruthenium (Ru), palladium (Pd), rhodium (Rh), silver (Ag), tin (Sn), tantalum (Ta), tungsten (W), iridium (Ir), gold (Au), and lead (Pb) or an alloy thereof may be used. A cermet material in which the same material as that of the piezoelectric/electrostrictive layers **11A**, **11B**, **11C**, and **11D** is dispersed in the above materials may be used.

The selection of materials of the external electrode layers **14** and **15** and the internal electrode layers **12A**, **12B**, and **12C** of the piezoelectric/electrostrictive element **10** is determined depending upon a method of forming the piezoelectric/electrostrictive layers **11A**, **11B**, **11C**, and **11D**. The method of forming the piezoelectric/electrostrictive layers will be described later.

In the thus constructed piezoelectric/electrostrictive element **10**, corners (ridge portions) **16** and **17** of both width-wise sides of the lower surface **f2**, as shown in FIG. **4**, have obtuse angles. Specifically, the angles which the lower surface **f2** makes with the slant surfaces **f3** and **f4** are obtuse, so that the corners **16** and **17** have a greater strength as compared with corners having right angles or acute angles. The increase in strength of the corners **16** and **17** serves to avoid the damage or breakage of the corners **16** and **17** caused by an external force or vibrations of the piezoelectric/electrostrictive element **10** when the lower surface **f2** of the piezoelectric/electrostrictive element **10** is installed on a movable plate (i.e., a diaphragm).

The upper surface portions **14B** and **15B** of the external electrode layers **14** and **15** are both disposed on the side of

the wider bottom surface f1, thus allowing the upper surface portions 14B and 15B to be used as connection areas (i.e., pad portions), which facilitates connection of wires.

Piezoelectric/Electrostrictive Device

Next, an embodiment of a piezoelectric/electrostrictive device 20 employing the piezoelectric/electrostrictive element 10 according to the first embodiment will be described using FIGS. 5 to 7. FIG. 5 is a side view of the piezoelectric/electrostrictive device 20. FIG. 6 is a plan view of the piezoelectric/electrostrictive device 20.

The piezoelectric/electrostrictive device 20 is constructed to be of a unimorph type wherein the narrower lower surface f2 of the above described piezoelectric/electrostrictive element 10 is joined to a movable plate (diaphragm) 21 using adhesive 22. In the piezoelectric/electrostrictive device 20 according to this embodiment, the piezoelectric/electrostrictive element 10 is substantially identical in width (i.e., the length in y direction, as expressed by an arrow in FIG. 6) with the movable plate 21. The length (i.e., the length in an x direction, as expressed by an arrow in FIG. 6) of the movable plate 21 is set longer than that of the piezoelectric/electrostrictive element 10. The movable plate 21 may have flexibility and mechanical strength which withstands breakage caused by bending. Material may be selected in terms of the response and operationability.

In the piezoelectric/electrostrictive device 20, the adhesive 22 is interposed between an upper surface of the movable plate 21 and a bottom surface (lower surface) and the slant surfaces f3 and f4 of the piezoelectric/electrostrictive element 10 to bond the piezoelectric/electrostrictive element 10 on the upper surface of the movable plate 21. Particularly, V groove-shaped gaps defined between the slant surfaces f3 and f4 of the piezoelectric/electrostrictive element 10 and the upper surface of the movable plate 21 are filled with the adhesive 22. As a result, the shape defined by the piezoelectric/electrostrictive element 10 and the adhesive 22 will be substantially trapezoidal or rectangular.

The movable plate 21 is a portion which operates based on driving of the piezoelectric/electrostrictive element 10 and has a variety of parts installed thereon according to the purpose of use of the piezoelectric/electrostrictive device 20. For instance, in a case where the piezoelectric/electrostrictive device 20 is used as a displacement element, a shielding plate of an optical shutter etc. is installed. In a case where the piezoelectric/electrostrictive device 20 is employed to position a magnetic head of a hard disc drive or in a ringing inhibiting mechanism, parts such as a magnetic head, a slider with the magnetic head, or a suspension with a slider which are required to be positioned are installed.

As material of the movable plate 21, ceramic including zirconia is preferable. Particularly, material containing a main component of stabilized zirconia or partially stabilized zirconia is desirable as the material of the movable plate 21 because it exhibits a greater mechanical strength and toughness if shaped to have a thin wall.

When the movable plate 21 is made of a metallic material, it is preferably flexible or bendable. For example, as ferrous materials, a variety of stainless steels or a variety of spring steels are desirable. As non-ferrous materials, beryllium copper, phosphor bronze, nickel, or nickel-iron alloy is desirable.

In the thus constructed piezoelectric/electrostrictive device 20, the V groove-shaped gaps defined by the slant surfaces f3 and f4 and the upper surface of the movable plate 21 are formed on both sides of the piezoelectric/electrostrictive element 10 and work as a liquid sumps for

the adhesive 22 that is liquid or pastelike. The adhesive 22 held in the gaps is solidified while being kept lump by the surface tension, thereby preventing the adhesive 22 from overflowing to or around the upper side of the piezoelectric/electrostrictive element 10 or the lower side of the movable plate 21. The V groove-shaped gaps defined by the slant surfaces f3 and f4 of the piezoelectric/electrostrictive element 10 and the upper surface of the movable plate 21 may be filled with the adhesive 22 in proper quantities by determining the quantity of the adhesive 22 to be applied to the movable plate 21 to a predetermined value.

The side corners of the lower surface f2 of the piezoelectric/electrostrictive element 10 both have, as described above, obtuse angles, and thus have a greater strength as compared with when they have right angles or acute angles. The increase in strength of the corners 16 and 17 serves to avoid the damage or breakage of the corners 16 and 17 caused by vibrations of the piezoelectric/electrostrictive element 10 or external forces.

Further, the stress arising from a thermal expansion difference between the piezoelectric/electrostrictive element 10 and the movable plate 21 is maximized near the ends of the piezoelectric/electrostrictive element 10, but the adhesive 22 in the V groove-shaped gaps works to hold the adhesive strength and reduce the stress because of a low elasticity of the adhesive, thereby avoiding breakage and removal of the piezoelectric element 10 from the movable plate 21.

The upper surface portions 14B and 15B of the external electrode layers 14 and 15 are arranged on the side of the wider bottom surface f1 (i.e., on the same plane), thereby facilitating connection of wire to the upper surface portions 14B and 15B.

In a case where the thus constructed piezoelectric/electrostrictive device 20 is used as an active device, wires 23 and 24 may be connected to the upper surface portion 14B of the external electrode layer 14 and the upper surface portion 15B of the external electrode layer 15 formed on the bottom surface f1, respectively, and to a voltage applying circuit 25. Such an active device may be employed as transducers, actuators, frequency domain functional parts (filters), transformers, vibrators or resonators for communications or power sources, oscillators, or discriminators. The wires 23 and 24 are provided preferably by a flexible printed circuit (FPC), flexible flat cables (FFC), or bonding wires.

In a case where the piezoelectric/electrostrictive device 20 is used as a passive device, the wires 23 and 24 may be connected to a voltage detecting circuit 26 instead of the voltage applying circuit 25. In the case where the wires 23 and 24 are joined to the upper surface portions 14B and 15B of the external electrode layers 14 and 15 of the piezoelectric/electrostrictive element 10, it is advisable that the adhesive 22 have electric insulation ability. Such a passive device may be employed as ultrasonic sensors, acceleration sensors, angular rate sensors, shock sensors, or mass sensors.

Modified Embodiment 1 of Piezoelectric/Electrostrictive Device

FIG. 8 is an explanatory side view which illustrates the modified embodiment 1 of the piezoelectric/electrostrictive device using the piezoelectric/electrostrictive element 10 according to the first embodiment. The structure of the modified embodiment 1 will be explained with the same reference numbers assigned to the same parts of the modified embodiment 1 as those of the above-described piezoelectric/electrostrictive device 20 and similar reference numbers assigned to similar parts thereof.

15

The piezoelectric/electrostrictive device **20A** according to the modified embodiment 1 has the narrower bottom surface **f2** of the above described piezoelectric/electrostrictive element **10** bonded and secured to the upper surface of the movable plate **21** having the conductivity using the adhesive **22** having the conductivity.

In the modified embodiment 1, the lower surface portion **14C** and a lower portion of the slant surface **14A** of the external electrode layer **14** formed on the bottom surface **f2** of the piezoelectric/electrostrictive element **10** are joined to and secured on the movable plate **21** through the adhesive **22A**. The adhesive **22A** is set so as not to extend over the slant surface **15A** of the external electrode layer **15**. This is achieved by determining the quantity of the adhesive **22A** to be applied to the movable plate **21** properly.

In the thus constructed piezoelectric/electrostrictive device **20A**, the wire **23** is joined to the movable plate **21**, and the wire **24** is coupled to the upper surface portion **15B** of the external electrode layer **15**. The use of the piezoelectric/electrostrictive device **20A** as an active device may be achieved by connecting the wires **23** and **24**, as shown in FIG. 8, to the voltage applying circuit **25**. The use of the piezoelectric/electrostrictive device **20A** as a passive device may be achieved by connecting the wires **23** and **24**, as shown in FIG. 8, to the voltage detecting circuit **26**.

As the adhesive **22** having the conductivity, a variety of conductive bonds including metallic fillers or anisotropic conductive bonds used in the field of semiconductor packaging may be selected properly.

The movable plate **21** having the conductivity may be made of a metallic material that is flexible or bendable. For example, as ferrous materials, a variety of stainless steels or a variety of spring steels are desirable. As non-ferrous materials, beryllium copper, phosphor bronze, nickel, or nickel-iron alloy is desirable.

Modified Embodiment 2 of Piezoelectric/Electrostrictive Device

FIG. 9 is a side view which illustrates the modified embodiment 2 of the piezoelectric/electrostrictive device using the piezoelectric/electrostrictive elements **10** according to the first embodiment. The structure of the modified embodiment 2 will be explained with the same reference numbers assigned to the same parts of the modified embodiment 2 as those of the above described piezoelectric/electrostrictive device **20** and similar reference numbers assigned to similar parts thereof.

The piezoelectric/electrostrictive device **20B** according to the modified embodiment 2 has a bimorph type structure in which the above constructed piezoelectric/electrostrictive element **10** is secured on each surface of the single movable plate **21** by the adhesive **22**. The narrower bottom surfaces **f2** of the piezoelectric/electrostrictive elements **10** are placed in contact with the respective surfaces of the movable plate **21** and bonded so that the movable plate **21** is sandwiched therebetween.

In the piezoelectric/electrostrictive device **20B** according to the modified embodiment 2, wires may be connected to the upper surface portions **14B** and **15B** of the external electrode layers **14** and **15** of each of the piezoelectric/electrostrictive elements **10**. Alternatively, the movable plate **21** may be used as a common electrode of the piezoelectric/electrostrictive elements **10**, and a wire may be connected only to the upper surface portion **15B** of each of the piezoelectric/electrostrictive element **10**.

The assembly of the piezoelectric/electrostrictive elements **10** may be of a symmetrical type (a series type) in which the directions of polarization are symmetrical with

16

respect to the movable plate **21** or an asymmetrical type (a parallel type) in which the directions of polarization of the piezoelectric/electrostrictive elements **10** are the same.

Modified Embodiment 3 of Piezoelectric/Electrostrictive Device

FIG. 10 is a side view which illustrates the modified embodiment 3 of the piezoelectric/electrostrictive device using the piezoelectric/electrostrictive elements **10** according to the first embodiment. The structure of the modified embodiment 2 will be explained using the same reference numbers assigned to the same parts as those of the above described piezoelectric/electrostrictive device **20** and similar reference numbers assigned to similar parts.

In the piezoelectric/electrostrictive device **20C** according to the modified embodiment 3, a pair of piezoelectric/electrostrictive elements **10** are so arranged that the narrower bottom surfaces **f2** thereof are opposed to each other and bonded to each other through the adhesive **22**. The piezoelectric/electrostrictive device **20C** has a bimorph type structure which is not equipped with a movable plate.

In the modified embodiment 3, the assembly of the piezoelectric/electrostrictive elements **10**, like the above described modified embodiment 2, may be of the symmetrical type (the series type) or the asymmetrical type (the parallel type).

Modified Embodiment 4 of Piezoelectric/Electrostrictive Device

FIG. 11 is a side view which illustrates the modified embodiment 4 of the piezoelectric/electrostrictive device using the piezoelectric/electrostrictive elements **10** according to the first embodiment.

The piezoelectric/electrostrictive device **20D** according to the modified embodiment 4, as shown in FIG. 11, includes a base body **30** which has movable plate portions **31** and a fixing portion **32** formed integrally. The movable plate portions **31** are opposed to each with through a given gap. The fixing portion **32** is interposed between the movable plate portions **31** on the same side of ends of the movable plate portions **31**. The piezoelectric/electrostrictive device **20D** has the piezoelectric/electrostrictive elements **10** bonded and secured to opposed outside surfaces on the same side of end portions of the pair of movable plate portions **31**.

The piezoelectric/electrostrictive device **20D** has the structure in which the movable plate portions **31** are displaced by driving the piezoelectric/electrostrictive elements **10**, or the displacement of the movable plate portions **31** is detected by the piezoelectric/electrostrictive elements **10**. For instance, in the piezoelectric/electrostrictive device **20D** shown in FIG. 11, the movable plate portions **31** and the piezoelectric/electrostrictive elements **10** constitute actuator portions **33**. On the other ends of the movable plate portions **31**, movable portions **34** are formed which are so formed as to have thick walls projecting inwardly. The movable portions **34** are displaced following displacing operations of the movable plate portions **31**.

The base body **30** may be made of metal or ceramic as a whole or have a hybrid structure made of a combination of metal and ceramic. The base body **30** may also have a structure in which respective parts are bonded by adhesive such as organic resin or glass, a ceramic one-piece structure made of a fired ceramic green laminate, or a metallic one-piece structure formed integrally by brazing, soldering, eutectic bonding, or welding. It is advisable that the base body **30** be made of a ceramic laminate formed integrally by firing a ceramic green laminate. Such ceramic one-piece members are of a structure which has high reliability of joints and is excellent in ensuring the rigidity and easy to manufacture.

The piezoelectric/electrostrictive elements **10** are bonded and secured to outside surfaces on the same side of the end portions of the base body **30** through the adhesive **22**. The adhesive **22** may be an organic adhesive or inorganic adhesive. The piezoelectric/electrostrictive elements **10** are bonded at the narrower bottom surfaces **f2** to the base body **30**. The V groove-shaped gaps defined by the slant surfaces **f3** and **f4** of the piezoelectric/electrostrictive elements **10** and the external surfaces of the base body **30** are filled with the adhesive **22**. As a result, the shape defined by the piezoelectric/electrostrictive elements **10** and the adhesive **22** will be substantially trapezoidal or rectangular parallel-pipedic.

On the wider bottom surfaces **f1** of the piezoelectric/electrostrictive elements **10**, the upper surface portions **14B** of the external electrode layers **14** and the upper surface portions **15B** of the external electrode layers **15** are disposed away from each other while keeping electric insulation. A wire is, thus, bonded to the upper surface portions **14B** and **15B** which is to be joined to a voltage applying circuit or a voltage detecting circuit which is not shown.

A gap (air), as shown in FIG. **11**, may be defined between the opposed end surfaces **34A** of the pair of movable portions **34**. Alternatively, a plurality of members made of material identical with or different from that of the movable portions **34** may be disposed between the opposed end surfaces **34A**.

In the thus constructed piezoelectric/electrostrictive device **20D**, the movable portions **34**, the movable plate portions **31**, and the fixing portion **32** that define the basic structure are formed integrally by a tough material. The piezoelectric/electrostrictive device **20D**, therefore, has the advantages that it is higher in mechanical strength, excellent in handling, impact resistance, and moisture resistance, and less susceptible to harmful vibrations (e.g., residual vibrations or noise during high-speed operation) as compared with a piezoelectric/electrostrictive device in which all parts are made of a piezoelectric/electrostrictive material that is fragile and relatively heavy.

The formation of the gap between the opposed end surfaces **34A** of the movable portions **34** of the piezoelectric/electrostrictive device **20D** provides the flexibility of the movable portion **34** including one of the end surfaces **34A** and the movable portion **34** including the other end surface **34A**, so that a deformation limit to which the piezoelectric/electrostrictive device is not broken will be high. The piezoelectric/electrostrictive device **20D**, therefore, has the advantage that it is excellent in handling.

In the piezoelectric/electrostrictive device **20D**, the movable portions **34** are portions which operate, as described above, based on the amount of displacement of the movable plate portions **31** and have a variety of parts installed thereon according to the purpose of use of the piezoelectric/electrostrictive device **20D**. For instance, in a case where the piezoelectric/electrostrictive device **20D** is used as a displacement element, for example, a shielding plate of an optical shutter is installed. In a case where the piezoelectric/electrostrictive device **20D** is employed to position a magnetic head of a hard disc drive or in a ringing inhibiting mechanism, parts requiring positioning of the magnetic head, a slider with the magnetic head, or a suspension with a slider are installed.

The fixing portion **32** is, as described above, a portion supporting the movable plate portions **31** and the movable portions **34**. For instance, in a case of use in positioning a magnetic head of a hard disc drive, the fixing portion **32** may be installed on a carriage arm mounted on a voice coil motor

(VCM), a mount plate attached to the carriage arm, or a suspension to fix the whole of the piezoelectric/electrostrictive device **20D**.

Further, in this modified embodiment, the movable plate portions **31** are portions driven by the displacement of the piezoelectric/electrostrictive elements **10** and thus are thin plate like members having the flexibility and work to perform a function of amplifying as a bending displacement an expansion/contraction displacement of the piezoelectric/electrostrictive elements **10** disposed on the surface thereof to transfer it to the movable portions **34**. Therefore, the shape and material of the movable plate portions **31** which only exhibit the flexibility and mechanical strength less susceptible to breakage caused by the bending displacement may be selected properly in terms of response and operability of the movable portions **34**.

The movable plates **31** are preferably made of ceramics including zirconia. Of the ceramics, material containing a main component of stabilized zirconia and material containing a main component of partially stabilized zirconia are desirable in terms of a greater mechanical strength and a higher toughness even though a wall thickness is small.

If the movable plate **31** is made of a metallic material, it is preferably flexible or bendable. For example, as ferrous materials, a variety of stainless steels or a variety of spring steels are desirable. As non-ferrous materials, beryllium copper, phosphor bronze, nickel, or nickel-iron alloy is desirable.

As the above described stabilized and partially stabilized zirconia, the following stabilized or partially stabilized ones are preferable. Specifically, as compounds stabilizing or partially stabilizing zirconia, there are yttrium oxide, ytterbium oxide, cerium oxide, calcium oxide, and magnesium oxide. The desired stabilization of zirconia may be achieved by adding at least one of the above compounds or a mixture thereof to the zirconia.

Added amounts of yttrium oxide and ytterbium oxide are 1 to 30 mol %, preferably 1.5 to 10 mol %. An added amount of cerium oxide is 6 to 50 mol %, preferably 8 to 20 mol %. Added amounts of calcium oxide and magnesium oxide is 5 to 40 mol %, preferably 5 to 20 mol %. Of these, yttrium oxide is preferably used as a stabilizer. In the case where yttrium oxide is used as a stabilizer, the amount thereof is preferably 1.5 to 10 mol % and more preferably 2 to 4 mol %.

In order to obtain the mechanical strength and stabilized crystal phase, the mean crystal grain size is 0.05 to 3 μm , preferably 1 μm or less. As described above, the movable plate portion **31**, like the movable portion **34** and the fixing portion **32**, may be made of ceramic. The use of substantially the same material is advantageous to improve the reliability of joints and the strength of the piezoelectric/electrostrictive device **20D** and alleviate the complexity of manufacture. Production Method of Piezoelectric/Electrostrictive Element of the First Embodiment

Next, a production method of the piezoelectric/electrostrictive element **10** according to the first embodiment will be described below using FIGS. **12** to **24**. The production method will be discussed while comparing and associating new reference numbers of respective material layers with reference numbers of the piezoelectric/electrostrictive element **10** that is a finished product as shown in FIGS. **1** to **4**. The method includes the following steps **1**–**12**.

(1) First, a ceramic substrate **41**, as shown in FIG. **12**, is prepared which has a give size and is made of oxide such as zirconia, alumina, or magnesia. The ceramic substrate **41** functions as a table for screen printing and a firing substrate.

Incidentally, the ceramic substrate **41** measures approximately 40 mm×50 mm×0.3 mm.

(2) Carbon powder or a theobromine powder-dispersed paste is printed using a 360 mesh metal screen having an emulsion film thickness of 10 μm on a row of areas on the ceramic substrate **41** which have a width greater than that of the piezoelectric/electrostrictive element **10** and then dried to form, as shown in FIG. **12**, a row of disappearing films **42**. Each of the disappearing films **42** contains a plurality of element-forming areas in an x direction. FIG. **13** is a cross section on section line B—B of FIG. **12**. The disappearing films **42** will disappear by firing in a subsequent process to perform the function of facilitating removal of the piezoelectric/electrostrictive elements **10** from the ceramic substrate **41**. A printing direction of the disappearing films **42** is a direction as illustrated by an arrow x in FIG. **12**.

(3) Next, a platinum (Pt) paste is printed in a direction, as indicated by arrow y in FIG. **14**, using screens (printing plates) **43A**, as illustrated by hatching, and dried. The screens **43A** is set to 360 in mesh and 5 μm in emulsion film thickness. In this process, portions corresponding to the upper surface portions **14B** and **15B** of the external electrode layers **14** and **15** of the piezoelectric/electrostrictive element **10** of the first embodiment are printed. The use of the screen **43A**, as illustrated by hatching in FIG. **14**, enables simultaneous printing over the plurality of element-forming areas along the x direction. FIG. **15** shows Pt paste films **44** and **45** printed at an interval array from each other using the screen **43A** within one of the element-forming areas on the disappearing film **42**. An area including the Pt paste films **44** and **45** and an intervening area is set to equal to that of a wider one of bottom surfaces an unbaked preform of the piezoelectric/electrostrictive element **10**. The screen **43A**, as shown in FIG. **15**, works to stick an emulsion film **47** to the metal screen **46** in a given pattern and transfer platinum pastes to the disappearing films **42** by pattern portions on which the emulsion layer **47** does not exist.

(4) Next, a piezoelectric paste is, as shown in FIG. **16**, printed using a screen **43B** and dried to form an unbaked preform of a first one of the piezoelectric/electrostrictive layers **11A**. The screen **43B** is provided by forming the emulsion layer **47** having a thickness of 25 μm in a given pattern on the 360 mesh metal screen **46**. A pattern of an opening of the emulsion layer **47** is determined to be slightly smaller than the above described area including the Pt paste films **44** and **45** and the intervening area therebetween. For details, the unbaked preform of the piezoelectric/electrostrictive layer **11A** printed by the screen **43B** are located at both x-direction edges inside x-direction outside edges of the Pt paste films **44** and **45** by a distance x1. Both y-direction side edges of the unbaked preform of the piezoelectric/electrostrictive layer **11A** overlap both y-direction side edges of each of the Pt paste films **44** and **45**.

(5) Next, a Pt paste film **48** is, as shown in FIG. **17**, printed using a screen **43C** which will be a Pt film serving as the internal electrode layer **12A** and the slant surface portion **15A** of the external electrode layer **15** after firing and then dried. The Pt paste film **48** is laid to overlap a given length L of the Pt paste film **44** in the x direction that is formed in the above process through the unbaked preform of the piezoelectric/electrostrictive layer **11A**. Overlapped portions of the Pt paste films **44** and **48** function as voltage-applying electrodes effectively.

(6) Afterwards, a piezoelectric paste is, as shown in FIG. **18**, printed using a screen **43D** and dried to form an unbaked preform of the piezoelectric/electrostrictive layer **11B**. One of x-direction edges of the unbaked preform of the

piezoelectric/electrostrictive layer **11B** is located on an extension of a slant surface portion of the Pt paste film **48** connecting with the Pt paste film **45**. The other edge of the preform of the piezoelectric/electrostrictive layer **11B** is located slightly inside an edge of the unbaked preform of the piezoelectric/electrostrictive layer **11A** and on an extension of a slant surface portion of the unbaked preform of the piezoelectric/electrostrictive layer **11A**.

(7) Next, a Pt paste film **49** is, as shown in FIG. **19**, printed using a screen **43E** which will be a Pt paste film **49** serving as the internal electrode layer **12B** and the slant surface portion **14A** of the external electrode layer **14** after firing and then dried. The Pt paste film **49** is opposed to the Pt paste film **48** through the unbaked preform of the piezoelectric/electrostrictive layer **11B**. The Pt paste films **48** and **49** overlap each other by the distance L in the x direction.

(8) Further, a piezoelectric paste is, as shown in FIG. **20**, printed using a screen **43F** which is smaller in width (length in the x direction) than the unbaked preform of the piezoelectric/electrostrictive layer **11B** serving as ground coat and then dried to form an unbaked preform of the piezoelectric/electrostrictive layer **11C**. The unbaked preform of the piezoelectric/electrostrictive layer **11C** is slightly inside an edge of the unbaked preform of the piezoelectric/electrostrictive layer **11B** exposed at one side from the Pt paste film **49** and the slant surface portion of the Pt paste film **49**.

(9) Afterwards, a Pt paste film **50** is, as shown in FIG. **21**, printed using a screen **43G** which serves as the internal electrode layer **12C** and the slant surface portion **15A** of the external electrode layer **15** after firing and then dried.

(10) Next, a Pt paste is, as shown in FIG. **22**, printed using a screen **43H** and then dried to form an unbaked preform of the piezoelectric/electrostrictive layer **11D**. The preform of the piezoelectric/electrostrictive layer **11D** is set smaller in width than the unbaked preform of the piezoelectric/electrostrictive layer **11C** serving as ground coat.

(11) Afterwards, a Pt paste film **51** is, as shown in FIG. **23**, printed using a screen **43I** which serves as the lower surface portion **14C** and the slant surface portion **14A** of the external electrode layer **14** after firing and then dried. The screen **43I** as used in this process is provided by forming the emulsion layer **47** having a thickness of 5 μm in a given pattern on the 360 mesh metal screen **46**.

(12) Finally, the temperature is increased at a rate which does not leave organic components of each material layer and the disappearing films **42** to perform the firing at a maximum temperature of 1100 to 1300° C., thereby causing the disappearing films **42** to disappear, as shown in FIG. **24**, to allow the piezoelectric/electrostrictive elements **10** to be removed easily from the ceramic substrate **41**.

It is possible for the production method of the piezoelectric/electrostrictive elements **10** to stack the piezoelectric/electrostrictive layers **11A**, **11B**, **11C**, and **11D** in the printing method so as to decrease in area gradually, thus resulting in ease of manufacture of the piezoelectric/electrostrictive elements **10**. It is also possible to form the piezoelectric/electrostrictive layers **11A**, **11B**, **11C**, and **11D** and each electrode layer (i.e., the Pt film in this embodiment) in the printing method, thus eliminating the need for handling and transportation. This enables the manufacture of the piezoelectric/electrostrictive elements **10** that are higher in dimensional and positional accuracy without adverse effects such as deformation caused by handling or transportation.

The formation of the side portions of the laminate (i.e., both sides in the x direction) which become the continuous external electrodes is achieved by forming the piezoelectric/

electrostrictive layer and the electrode layer repeatedly, thereby eliminating the need for an additional process of forming external electrode layers, resulting in a decrease in process.

Further, easy removal of the piezoelectric/electrostrictive elements 10 after firing is achieved by forming the disappearing films 42 on the ceramic substrate 41 which will disappear by the firing process prior to producing the piezoelectric/electrostrictive elements 10. The disappearing films 42 disappear in the firing process by sublimation and burning, thereby preventing particles from sticking to the piezoelectric/electrostrictive elements 10.

In the production method of the piezoelectric/electrostrictive elements, a variety of piezoelectric materials and conductive pastes that are screen printable may be selected.

The production method of the piezoelectric/electrostrictive elements enables the formation of the external electrode layers in the printing method with a higher positioning accuracy, which achieves accurate positioning of the piezoelectric/electrostrictive elements when disposed and secured on, for example, a movable plate.

Second Embodiment

Piezoelectric/Electrostrictive Element

FIGS. 25 and 26 show a piezoelectric/electrostrictive element according to the second embodiment of the invention. FIG. 25 is a side view of the piezoelectric/electrostrictive element 60. FIG. 26 is a plan view of the piezoelectric/electrostrictive element 60. The piezoelectric/electrostrictive element 60, as shown in the drawings, consists of four piezoelectric/electrostrictive layers 61, 62, 63, and 64, upper surface electrode layers 65 and 66 formed at an interval away from each other on an outside surface of the piezoelectric/electrostrictive layer 61, internal electrode layers 67, 68, 69, and 70 formed on lower surfaces of the piezoelectric/electrostrictive layers 61, 62, 63, and 64, a slant surface portion 71 leading to an upper surface electrode 65 in connection with the internal electrode layers 68 and 70, a slant surface portion 72 leading to an upper surface electrode 66 in connection with the internal electrode layers 67 and 69, and an insulating layer 73 covering the slant surface portions 71 and 72 and the internal electrode layer 70.

The piezoelectric/electrostrictive element 60 has a substantially trapezoidal laminated structure having a pair of opposed upper and lower bottom surfaces of rectangular shape. The insulating layers 73 is made of material which may be the same material as that of the piezoelectric/electrostrictive layer 61 or different therefrom.

Both side edges of the bottom surface f2 are, as shown in FIG. 25, located inside side edges of the bottom surface f1 by equal distances, thereby forming slant surfaces f3 and f4 on both sides of the piezoelectric/electrostrictive element 60 in the x direction. The slant surfaces f3 and f4 are inclined in a direction in which they approach each other from the wider bottom surface f1 to the narrower bottom surface f2.

The upper surface electrode layer 65 is wider than the upper surface electrode layer 66. The upper surface electrode layer 65 and the internal electrode layers 68 and 70 are so formed as to extend from the slant surface portion 71 to the slant surface f4. The internal electrode layers 67 and 69 are so formed as to extend from the slant surface portion 72 leading to the upper surface electrode layer 66 to the side of the slant surface f3.

In the piezoelectric/electrostrictive element 60, areas of the upper surface electrode layer 65 and the internal electrode layers 67, 68, 69, and 70 which overlap each other

through the piezoelectric/electrostrictive layers practically define voltage-applied areas or voltage-detecting areas.

In the piezoelectric/electrostrictive element 60 of the second embodiment, the bottom surface f2 and the slant surfaces f3 and f4 are covered with the insulating layer 73. Wires leading to a voltage applying circuit or a voltage detecting circuit are, thus, to be connected to the upper surface electrode layers 65 and 66 of the bottom surface f1.

In the piezoelectric/electrostrictive element 60 of the second embodiment, the piezoelectric/electrostrictive layers 61, 62, 63, and 64 are made of, for example, zirconium lead titanate (PZT). The internal electrode layers 67, 68, 69, and 70, the upper surface electrode layers 65 and 66, and the slant surface portions 71 and 72 are made of, for example, platinum (Pt).

In the piezoelectric/electrostrictive element 60, the piezoelectric/electrostrictive layers 61, 62, 63, and 64 laminated from the bottom surface f1 to the bottom surface f2 are decreased in width (length in the x direction) gradually. As a result, in the whole of the piezoelectric/electrostrictive element 60, the slant surfaces f3 and f4 are, as describe above, formed on the side portions.

In this embodiment, the piezoelectric/electrostrictive layers 61, 62, 63, and 64 are four layers. The electrode layers holding the piezoelectric/electrostrictive layers therebetween are five layers, however, the number of the layers and the number of the internal electrode layers connecting with the slant surface portions 71 and 72 may be equal to each other or not. The number of the electrode layers are determined in terms of relations to a drive voltage and the degree of displacement. An increase in total number of the piezoelectric/electrostrictive layers will cause a driving force driving the movable plate on which the piezoelectric/electrostrictive element 60 is installed to be increased, thus enabling a greater displacement and result in an increase in rigidity of the piezoelectric/electrostrictive element 60, thereby increasing the resonance frequency, which allows the speed of a displacement operation to be increased easily. Piezoelectric/Electrostrictive Device

FIG. 27 is a side view of a piezoelectric/electrostrictive device 70 according to the second embodiment. The piezoelectric/electrostrictive device 70 is constructed to be of a unimorph type wherein the narrower bottom surface f2 of the above described piezoelectric/electrostrictive element 60 is joined to a movable plate (diaphragm) 71 using adhesive 72. In the piezoelectric/electrostrictive device 70 of the second embodiment, the movable plate 71 is identical in width. The length of the movable plate 71 is greater than that of the piezoelectric/electrostrictive element 60. The movable plate 71 may have flexibility and mechanical strength which withstands breakage caused by bending. Material may be selected in terms of the response and operationability.

In the piezoelectric/electrostrictive device 70, the adhesive 72 is interposed between an upper surface of the movable plate 71 and a bottom surface (lower surface f2 and the slant surfaces f3 and f4 of the piezoelectric/electrostrictive element 60 to bond the piezoelectric/electrostrictive element 60 on the upper surface of the movable plate 71. Particularly, V groove-shaped gaps defined between the slant surfaces f3 and f4 of the piezoelectric/electrostrictive element 60 and the upper surface of the movable plate 71 are filled with the adhesive 72. As a result, the shape defined by the piezoelectric/electrostrictive element 60 and the adhesive 72 will be substantially trapezoidal or rectangular.

The movable plate 71 is a portion which operates based on driving of the piezoelectric/electrostrictive element 70 and

has a variety of parts installed thereon according to the purpose of use of the piezoelectric/electrostrictive device **70**. For instance, in a case where the piezoelectric/electrostrictive device **70** is used as a displacement element, a shielding plate of an optical shutter etc. is installed. In a case where the piezoelectric/electrostrictive device **70** is employed to position a magnetic head of a hard disc drive or in a ringing inhibiting mechanism, parts such as a magnetic head, a slider with the magnetic head, or a suspension with a slider which are required to be positioned are installed.

The movable plate **71** is a portion driven by the displacement of the piezoelectric/electrostrictive elements **60**. The movable plate **71** is a flexible member and performs a function of amplifying as a bending displacement an expansion/contraction displacement of the piezoelectric/electrostrictive elements **60** that is disposed on the surface of the movable plate portions **71**. The material of the movable plate **71** which exhibits the flexibility and mechanical strength less susceptible to breakage caused by the bending displacement may be selected.

As material of the movable plate **71**, ceramic including zirconia is desirable. Particularly, material containing a main component of stabilized zirconia or partially stabilized zirconia is desirable as the material of the movable plate **71** because it exhibits a greater mechanical strength, a high toughness, and a small reactivity to the piezoelectric/electrostrictive layers and an electrode material if shaped to have a thin wall.

If the movable plate **71** is made of a metallic material, it is preferably flexible or bendable. For example, as ferrous materials, a variety of stainless steels or a variety of spring steels are desirable. As non-ferrous materials, beryllium copper, phosphor bronze, nickel, or nickel-iron alloy is desirable.

In the thus constructed piezoelectric/electrostrictive device **70**, the V groove-shaped gaps defined by the slant surfaces **f3** and **f4** and the upper surface of the movable plate **71** are formed on both sides of the piezoelectric/electrostrictive element **70** and work as a liquid sumps for the adhesive **72** that is liquid or pastelike. The adhesive **72** held in the gaps is solidified while being kept lump by the surface tension, thereby preventing the adhesive **72** from overflowing to or around the upper side of the piezoelectric/electrostrictive element **60** or the lower side of the movable plate **71**. The V groove-shaped gaps defined by the slant surfaces **f3** and **f4** of the piezoelectric/electrostrictive element **60** and the upper surface of the movable plate **71** may be filled with the adhesive **72** in proper quantities by determining the quantity of the adhesive **72** to be applied to the movable plate **71** to a predetermined value.

The side corners of the lower surface **f2** of the piezoelectric/electrostrictive element **60** both have, as described above, obtuse angles, and thus have a greater strength as compared with when they have right angles or acute angles. The increase in strength of the corners serves to avoid the damage or breakage of the corners caused by vibrations of the piezoelectric/electrostrictive element **60** or external forces when the bottom surface (lower surface) **f2** of the piezoelectric/electrostrictive element **60** is secured on the movable plate **71**.

Further, the stress arising from a thermal expansion difference between the piezoelectric/electrostrictive element **60** and the movable plate **71** is maximized near the ends of the piezoelectric/electrostrictive element **60**, but the adhesive **72** in the V groove-shaped gaps works to hold the adhesive strength and reduce the stress because of a low elasticity of the adhesive, thereby avoiding breakage and removal of the piezoelectric element **60** from the movable plate **71**.

The upper surface electrode layers **65** and **66** are arranged on the side of the wider bottom surface **f1** (i.e., on the same plane), thereby facilitating connection of wire to the upper surface electrode layers **65** and **66**.

When used as an active device, the thus constructed piezoelectric/electrostrictive device **70** may be designed as a transducer, an actuator, a frequency domain functional part (a filter), a transformer, a vibrator or a resonator for communications or a power source, an oscillator, or a discriminator. Wires may be provided preferably by a flexible printed circuit (FPC), flexible flat cables (FFC), or bonding wires.

When used as a passive device, the piezoelectric/electrostrictive device **70** may be designed as an ultrasonic sensor, an acceleration sensor, an angular rate sensor, a shock sensor, or a mass sensor.

In the piezoelectric/electrostrictive device **70** of the second embodiment, the adhesive **72** sticks directly to the insulating layer **73** whose surface roughness is great and which covers the bottom surface **f2** and the slant surfaces **f3** and **f4** of the piezoelectric/electrostrictive element **60**, thus resulting in an increase in bonding strength as compared with when the adhesive **72** sticks to a metallic electrode.

In the piezoelectric/electrostrictive device **70**, by forming the upper surface electrode layers **65** and **66** of the piezoelectric/electrostrictive element **60** in the printing method, the contour of the widest bottom surface **f1**, patterns of the upper surface electrode layers **65** and **66** are formed precisely, thus enabling the positioning based on the upper surface electrode layers **65** and **66**. This allows the piezoelectric/electrostrictive element **60** to be positioned accurately on the movable plate **71**.

The piezoelectric/electrostrictive device **70** of the second embodiment is, as described above, of the unimorph type, but may be of a bimorph type.

35 Production Method of Piezoelectric/Electrostrictive Device

A production method of a piezoelectric/electrostrictive device which may be employed with the first and second embodiments will be described below using FIGS. **28** to **33**. The method includes the following steps A-E.

(A) First, a movable plate **80**, as shown in FIG. **28**, is prepared. An adhesive **81** is, as shown in FIG. **29**, applied to a given position of the movable plate **80** using the screen printing method.

(B) Next, the movable plate **80** is, as shown in FIGS. **30** and **31**, put on a movable plate positioning jig **82**. The movable plate positioning jig **82** has a pair of guide pins **84** installed on side portions of a movable plate positioning substrate **83**. Three vertically extending positioning pins **35** are installed on a central portion of the movable plate positioning substrate **83** in engagement with two sides of the movable plate **80**.

(C) The piezoelectric/electrostrictive element **10** is set on an element positioning plate **86**. The element positioning plate **86** has formed therein a plurality of vacuum openings **87** for fixing in place the piezoelectric/electrostrictive element **10** by use of suction. The piezoelectric/electrostrictive element **10** is set so that the wider bottom surface **f1** may be fixed in place by the suction of vacuum openings **87**. The element positioning plate **86** has formed therein guide holes **88** in which guide pins **84** are fitted when combined with the movable plate positioning jig **82**. The element positioning plate **86** has also formed therein openings **89** for reception of the positioning pins **35** installed on the movable plate positioning jig **82**.

(D) The guide pins **84** of the movable plate positioning jig **82** are, as shown in FIG. **33**, inserted into the guide holes **88** of the element positioning plate **86**. The element positioning

plate **86** is brought close to the movable plate positioning jig **82** to bring the piezoelectric/electrostrictive element **10** into contact with the movable plate **80** disposed on the movable plate positioning jig **82**, thereby causing the piezoelectric/electrostrictive element **10** to be bonded and secured by the adhesive **81** applied to the movable plate **80**.

(E) Afterwards, the suction by the vacuum openings **87** of the element positioning plate **86** is stopped. The element positioning plate **86** is then lifted upward to terminate the positioning of the piezoelectric/electrostrictive element **10**.

Afterwards, a weight is put on the piezoelectric/electrostrictive element **10** to hold it from moving during solidification of the adhesive. For example, in a case of a thermosetting one-component epoxy resin adhesive, it is put in an oven heated up to a solidifying temperature. In a case of a UV cured adhesive, an ultraviolet ray is radiated to solidify the bond.

In the above described piezoelectric/electrostrictive device production method, the piezoelectric/electrostrictive element **10** is bonded to one of the surfaces of the movable plate **80**. In a case where the piezoelectric/electrostrictive elements **10** are bonded to the surfaces of the movable plate **80**, the piezoelectric/electrostrictive element **10** is adhered to one of the surfaces of the movable plate **80** in the above manner, after which another movable plate positioning jig is prepared which is designed to be disposed on the movable plate **80** that is turned over to bond the piezoelectric/electrostrictive element **10** to the reverse surface.

In the above piezoelectric/electrostrictive device production method, proper bonding may be carried out in a proper quantity of the adhesive **81**, as shown in FIG. **5**, by determining the quantity and thickness of the adhesive **81** to be applied to the movable plate **80** to predetermined values. It is possible to control an applied position and an applied quantity of adhesive accurately, depending upon physical properties (the coefficient of viscosity or thixotropy). Thus, as an application method of the adhesive, the screen printing method is preferably used.

Other Embodiments

It should be noted that the discussion and the drawings that are parts of the disclosure of the above described first and second embodiments of the invention do not limit the invention. From this disclosure, one skilled in the art will know alternative various forms of embodiments, and working techniques.

For instance, the first and second embodiments refer to the cases where the number of the inner electrode layers are three and four, but may be one, two or more, or five or more.

When produced by the printing method, the piezoelectric/electrostrictive elements **10** and **60** have advantages of production, dimensional accuracy, and positional accuracy, but even if the piezoelectric/electrostrictive elements **10** and **60** are not produced by the printing method, they may have the advantage of strength as long as at least the corners of the side portions of the bottom surface have obtuse angles.

In the above described first and second embodiments, the adhesive is put in the V groove-shaped gaps defined by the

piezoelectric/electrostrictive element and the movable plate. The invention may also be used in the case where only the narrower bottom surface is bonded by adhesive.

What is claimed:

1. A method of producing a piezoelectric/electrostrictive device in which a piezoelectric/electrostrictive element includes a substantially trapezoidal laminate having narrower and wider surfaces lying substantially in parallel to each other and first and second surfaces opposed to each other between the narrower and wider surfaces, the first and second surfaces being inclined at given angles to one of the narrower and wider surfaces, said laminate being made up of a plurality of piezoelectric/electrostrictive layers and a plurality of internal electrodes each of which is disposed between adjacent two of the piezoelectric/electrostrictive layers, the internal electrodes being broken up into a first and a second group, each of the first group internal electrodes lying over one of the second group internal electrodes through one of the piezoelectric/electrostrictive layers; a first external electrode formed on the first surface of said laminate, said first external electrodes being coupled to the first group internal electrodes; and a second external electrode formed on the second surface of said laminate, said second external electrodes being coupled to the second group internal electrodes, and the piezoelectric/electrostrictive element is bonded to a surface of a movable plate by adhesive.

2. A method of producing a piezoelectric/electrostrictive device as set forth in claim **1**, wherein said piezoelectric/electrostrictive elements are bonded to surfaces of said movable plate through adhesive.

3. A method of producing a piezoelectric/electrostrictive device in which a pair of piezoelectric/electrostrictive elements each include a substantially trapezoidal laminate having narrower and wider surfaces lying substantially in parallel to each other and first and second surfaces opposed to each other between the narrower and wider surfaces, the first and second surfaces being inclined at given angles to one of the narrower and wider surfaces, said laminate being made up of a plurality of piezoelectric/electrostrictive layers and a plurality of internal electrodes each of which is disposed between adjacent two of the piezoelectric/electrostrictive layers, the internal electrodes being broken up into a first and a second group, each of the first group internal electrodes lying over one of the second group internal electrodes through one of the piezoelectric/electrostrictive layers; a first external electrode formed on the first surface of said laminate, said first external electrodes being coupled to the first group internal electrodes; and a second external electrode formed on the second surface of said laminate, said second external electrodes being coupled to the second group internal electrodes, and the piezoelectric/electrostrictive elements are bonded to each other on sides of the respective narrower surfaces of said laminates through adhesive.