

**(12) PATENT**  
**(19) AUSTRALIAN PATENT OFFICE**

**(11) Application No. AU 199746162 B2**  
**(10) Patent No. 729075**

(54) Title  
**A paste**

(51)<sup>7</sup> International Patent Classification(s)  
**A61L 025/00 C09J 153/00**  
**A61F 005/443**

(21) Application No: **199746162** (22) Application Date: **1997.10.22**

(87) WIPO No: **WO98/17329**

(30) Priority Data

(31) Number <b>1167/96</b>	(32) Date <b>1996.10.22</b>	(33) Country <b>DK</b>
<b>0488/97</b>	<b>1997.04.30</b>	<b>DK</b>

(43) Publication Date : **1998.05.15**

(43) Publication Journal Date : **1998.07.09**

(44) Accepted Journal Date : **2001.01.25**

(71) Applicant(s)  
**Coloplast A/S**

(72) Inventor(s)  
**Laila Busk Gothjaelsen; Danuta Ciok**

(74) Agent/Attorney  
**F B RICE and CO,605 Darling Street,BALMAIN NSW 2041**

(56) Related Art  
**US 5492943**



INT

<b>(51) International Patent Classification<sup>6</sup> :</b> <b>A61L 25/00, A61F 5/443, C09J 153/00</b>		<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 98/17329</b> <b>(43) International Publication Date:</b> 30 April 1998 (30.04.98)
<b>(21) International Application Number:</b> PCT/DK97/00463 <b>(22) International Filing Date:</b> 22 October 1997 (22.10.97)		<b>(81) Designated States:</b> AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).	
<b>(30) Priority Data:</b> 1167/96 22 October 1996 (22.10.96) DK 0488/97 30 April 1997 (30.04.97) DK		<b>Published</b> With international search report.	
<b>(71) Applicant (for all designated States except US):</b> COLOPLAST A/S [DK/DK]; Holtedam 1, DK-3050 Humlebaek (DK).			
<b>(72) Inventors; and</b> <b>(75) Inventors/Applicants (for US only):</b> GOTHJAEELPSEN, Laila, Busk [DK/DK]; Engkjaer 13, DK-2650 Hvidovre (DK). CIOK, Danuta [PL/DK]; Violens Kvarter 8, DK-2990 Nivaa (DK).			
<b>(74) Common Representative:</b> COLOPLAST A/S; Patent Dept., Att.: Kim Nilausen, Holtedam 1, DK-3050 Humlebaek (DK).			

**(54) Title:** A PASTE

**(57) Abstract**

A mouldable mass of a hypoallergenic, substantially non-memory putty-like adhesive for use in connection with an ostomy appliance, said mass comprising: a) 1 to 20 % by weight of a blockcopolymer having a major content of di-block copolymer, b) 5 to 60 % by weight of a tackifying liquid constituent, and c) 1 to 10 % by weight of a waxy constituent has superior quality with respect to cohesion, gives the mass resistance against erosion and at the same time enables the removal of the mass as an integrated unit without leaving residues at the skin.

**TITLE**

A MOULDABLE MASS FOR USE IN CONNECTION WITH AN OSTOMY APPLIANCE

**FIELD OF THE INVENTION**

The present invention relates to a mouldable mass for use in connection with an ostomy appliance or fistulas, to a method for preparing such a mouldable mass and to the use of a mouldable mass to provide a smooth surface on which an ostomy appliance is to be applied or for use in connection with fistulas.

**BACKGROUND OF THE INVENTION**

In connection with surgery for a number of diseases in the gastro-intestinal tract a consequence is, in many cases, that the colon, the ileum or the urethra has been exposed surgically and the patient is left with an abdominal stoma and the effluents or waste products of the body, which are conveyed through these organs, are discharged through the artificial orifice or opening and are collected in a collection bag, which is usually adhered to the skin by means of an adhesive wafer or plate having an inlet opening for accommodating the stoma. Also in connection with a fistula, the patient will have to rely on an appliance to collect the bodily material emerging from such opening.

Often, a paste is used for filling the area between the stoma or fistula and a mounting gasket, ostomy washer and/or skin barrier or to build up an area on the abdomen around the stoma so as to provide a relatively flat and smooth surface onto which an appliance or skin barrier can be securely attached.

Such paste should have a composition which is sufficiently tacky to secure the appliance or skin barrier to the abdomen, a cohesion ensuring safe removal thereof without leaving residues on the skin. On the other hand, the paste must not be so sticky that it cannot be easily shaped by the finger or hand without sticking to the finger or hand.

Furthermore, the paste must show a sufficient elasticity in order to be able to follow the movements of the patient without slipping the skin and should also show a great



resistance to erosion caused by aggressive exudates from an ostomy in order to minimize the risk of leakage.

Pastes for use for protecting the area of skin between the stoma and an attached appliance, face plate or skin barrier and for providing a smooth abdominal surface around 5 the stoma for attachment of a skin barrier or appliance are known from EP patent No. EP 0 048 556 B1 and US patent No. 4,204,540

Thus, European Patent Specification No. EP 0 048 556 B1 discloses a composition of paste-like consistency useful for protecting and treating the skin contiguous to a stoma in the form of an alcohol based composition including as a film former the partial ester 10 of the polycarboxylic resin formed from vinyl methyl ether and maleic anhydride, one or more hydrocolloid gums, one or more gelling and thickening agents, a plasticizer, and other optional ingredients.

The composition disclosed in EP 0 048 556 B1 suffers from the drawback that it comprises a considerable amount (25% to 45% by weight) of alcohol, ethanol and isopropanol being preferred. When using such a paste, there is only a limited time for forming 15 the paste after the application as the paste cures when exposed to air. Furthermore, the paste shows less attractive physical properties as a considerable amount of alcohol may be trapped in the paste and have an adverse effect on the properties of the adhesive of an ostomy appliance which is placed upon the paste. Still further, the considerable amount of alcohol may irritate the skin and cannot be used on skin which has been 20 sensibilised.

The method of protecting the area of skin between the stoma and an attached appliance, face plate or skin barrier and for providing a smooth abdominal surface around the stoma for attachment of a skin barrier or appliance disclosed in US patent No. 4,204,540 comprises shaping and placing around the stoma the shaped mass. The 25 mass comprises a homogeneous mixture of mineral oil, a premix comprising (A) a pressure sensitive adhesive and an optional elastomer wherein the pressure sensitive adhesive is a low molecular weight polyisobutylene and the optional elastomer is a

medium molecular weight polyisobutylene or butyl rubber, and (B) a second component which is a mixture of one or more hydrocolloid gums, a cohesive strengthening agent or a mixture of hydrocolloid gums and cohesive strengthening agent wherein the hydrocolloids are up to 40% guar gum, locust bean gum or mixtures thereof and from 0 5 to 25% pectin, gum karaya or mixtures thereof, and wherein the cohesive strengthening agent is finely divided cellulose, finely divided substantially water insoluble sodium carboxymethylcellulose or finely divided water insoluble starch-acrylonitrile graft copolymer. It is stated that by controlling the amount of mineral oil the resulting composition can easily be shaped according to the particular need. The pressure sensitive adhesive 10 is based on natural or synthetic viscous substances either possessing dry tack by themselves or developing such tack upon the addition of a plasticizer.

The pastes disclosed in US patent No. 4,204,540 suffers from the drawback that the shapeability is very dependant of the content of mineral oil. If an insufficient amount of mineral oil is added the composition will be too tough to shape and if too much mineral 15 oil is added the composition becomes sticky and difficult to handle. Generally, pastes consisting of polyisobutylene, butyl rubber and mineral oil will be very hard, if the content of butyl rubber is high and hence, the paste will be difficult to shape, or it will be very soft and liquid if the content of butyl rubber is low and the content of mineral oil is high.

20 US patent No. 5,492,943 discloses a pressure sensitive adhesive composition including a blend of two viscoelastic adhesive elastomers, specifically, high molecular weight polyisobutylene and a styrene block copolymer, which along with a plasticizer (preferably petrolatum) and a suitable tackifier and antioxidant, form a continuous phase in which hydrocolloids such as sodium carboxymethylcellulose and pectin are dispersed. The adhesive compositions disclosed in US patent No. 5,492,943 are stated to be used 25 for wafers for adhering ostomy appliances to the skin and differ from known compositions by completely avoiding the use of low molecular weight polyisobutylene and furthermore by preferably not including gelatin.

## BRIEF DESCRIPTION OF THE INVENTION

It has surprisingly been found that the above-mentioned draw-backs related to known masses are overcome with the mouldable mass of hypoallergenic, substantially non-memory putty-like adhesive of the invention.

In a first aspect, the present invention provides a mouldable mass of a hypoallergenic, substantially non-memory putty-like adhesive when used in connection with an ostomy appliance comprising a styrene block copolymer and a tackifying constituent, characterised in that the mass comprises:

- 10 a) 1 to 20% by weight of a styrene block copolymer having a molecular weight of from 20,000 to 150,000 and wherein the contents of di-block copolymer is above 25%;
- b) 5 to 60% by weight of a tackifying liquid constituent in the form of a viscous polymeric material being compatible with the block copolymer;
- 15 c) 1 to 10% by weight of a waxy constituent; and
- d) a hydrocolloid.

In a second aspect, the present invention provides a method for preparing a mouldable mass of a hypoallergenic, substantially non-memory putty-like adhesive when used in connection with an ostomy appliance comprising a styrene block copolymer and a tackifying constituent wherein the mass comprises:

- 20 a) 1 to 20% by weight of a block copolymer having a molecular weight of from 20,000 to 150,000 wherein the contents of di-block copolymer is above 25%;
- b) 5 to 60% by weight of a tackifying liquid constituent in the form of a viscous polymeric material being compatible with the block copolymer;
- c) 1 to 10% by weight of a waxy constituent; and
- d) a hydrocolloid

which method comprises mixing the block copolymer having a molecular weight of from 20,000 to 150,000 wherein the contents of di-block copolymer is above 10% and a part of the tackifying liquid constituent in the form of a viscous polymeric material being compatible with the block copolymer during heating at a temperature from 50 to 200° C, and admixing the remaining part of the tackifying liquid constituent and the waxy constituent, whereafter the hydrocolloid is admixed after reducing the temperature to a level below 100° C.



In a third aspect, the present invention provides a mouldable mass of a hypoallergenic, substantially non-memory putty-like adhesive when used in connection with an ostomy appliance comprising a styrene block copolymer and a tackifying constituent wherein the mass comprises:

- 5      a) 1 to 20% by weight of a block copolymer having a molecular weight of from 20,000 to 150,000 wherein the contents of di-block copolymer is above 25%;
- b) 5 to 60% by weight of a tackifying liquid constituent in the form of a viscous polymeric material being compatible with the block copolymer;
- 10     c) 1 to 10% by weight of a waxy constituent; and
- d) a hydrocolloid

as a paste for preparing the skin around a stoma to provide a plane surface for placing an ostomy appliance.

In one embodiment, the present invention provides a mouldable mass of a hypoallergenic, substantially non-memory putty-like adhesive for use in connection with fistulas or an ostomy appliance, preferably as a paste for smoothing out a surface on which an ostomy appliance is to be applied.

Furthermore, the invention relates to a method for preparing a mouldable mass of a hypoallergenic, substantially non-memory putty-like adhesive.

Still further, the invention relates to the use of a mouldable mass of a hypoallergenic, substantially non-memory putty-like adhesive for smoothing out a surface on which an ostomy appliance is to be applied.

25     Detailed Description of the Invention

The invention relates to a mouldable mass of a hypoallergenic, substantially non-memory putty-like adhesive for use in connection with an ostomy appliance, said mass comprising:

- 30     a) 1 to 20% by weight of a block copolymer having a major content of di-block copolymer;
- b) 5 to 60% by weight of a tackifying liquid constituent; and
- c) 1 to 10% by weight of a waxy constituent.



In a mass according to the invention, the combination of a block copolymer having a major content of di-block copolymer with a tackifying liquid constituent, and a waxy constituent has shown superior quality with respect to cohesion, giving the mass resistance against erosion and at the same time enabling the removal of the mass as an integrated unit without leaving residues at the skin. This will improve the performance of the mass and decrease the nuisance and skin problems experienced by the user if he



has to use aggressive agents to remove residues at the skin before applying a substitute ostomy appliance.

The mouldable mass further comprises one or more optional constituents such as petroleum jelly in an amount of up to 20% by weight, polybutylene oil in an amount of up to 30% by weight and/or liquid paraffin in an amount of up to 30% by weight.

The mouldable mass of the invention differs from the masses/pastes disclosed in EP patent No. EP 0 048 556 B1 and US patents Nos. 4,204,540 and 5,492,943 in that a quite different polymeric material and a waxy constituent are used. This enables the avoidance of the need of use of solvents in the mouldable mass according to the invention. Furthermore, the amount of mineral oil needed for plasticizing the blockcopolymer having a major content of di-block copolymer and the polyisobutylene and/or polybutylene used in the mouldable mass of the invention instead of butyl rubber is considerably lower than the amounts needed in the compositions disclosed in US patent No. 4,204,540 and, at the same time, the criticality of the content of mineral oil is avoided. US patent No. 5,492,943 discloses a pressure sensitive adhesive composition to be used for wafers for adhering ostomy appliances to the skin. The patent only discloses the suitability of the compositions for use for preparation of wafers for adhering ostomy appliances to the skin and is silent with respect to the use of the adhesive composition as a paste. The adhesive compositions of the present invention differ from the adhesives known from US patent No. 5,492,943 comprising an elastomer blend composed substantially entirely of one or more high molecular weight polyisobutylenes having a molecular weight of about 750,000 to 2,350,000 and one or more styrene block copolymers compositions by including low molecular weight polyisobutylenes or polybutenes and furthermore by including gelatine.

Thus, the compositions of the present invention and the properties rendering the same suitable for use as an ostomy paste are neither taught nor indicated in the above known references.

The block copolymer preferably has a low molecular weight and a high content of diblock component. The molecular weight of the block copolymer is from 20,000 to 150,000, preferably from 30,000 to 100,000. The content of diblock copolymer in the blockcopolymer is preferably above 10%, more preferred above 25% and more preferred above 30%. The content of diblock copolymer imparts cohesion to the mass and renders the mouldable mass less elastic than a corresponding mass comprising a threeblock copolymer due to a minor degree of physical cross-linking and imparts to the plasticity or substantially non-memory putty-like characteristics of the mass.

The mouldable masses of the invention comprise a tackifying viscous liquid constituent. 10 The action of the tackifying liquid constituent is to plasticize and tackify the copolymer. Such a plasticizer should be compatible with the copolymer as compatibility with the copolymer ensures that the adhesive may be removed as an integrated unit.

Furthermore, the mouldable masses of the invention comprise a waxy constituent. The role of the waxy constituent is to render the mass plastic and mouldable and impart 15 non-memory characteristics to the mass.

The blockcopolymer may be a copolymer comprising a block of a relatively hard polymer which may form physical cross-linking and a block of a softer polymer. The constituents of the blockcopolymer may be the same as are conventionally used for blockcopolymers such as SBS, SIS or SEBS copolymers, e.g. styrene and butadiene, 20 isoprene or ethylenebutylene copolymers. The preferred copolymer is a SEBS (styrene-ethylenebutylene-styrene copolymer) having a content of diblock component above 30%.

The tackifying viscous liquid constituent is preferably a viscous polymeric material being compatible with the blockcopolymer. The tackifying liquid may be a polybutylene or 25 polyisobutylene and is preferably a saturated component which cannot give rise to chemical cross-linking deteriorating the non-memory putty-like characteristics of the mass. The tackifying liquid component is more preferred a polybutylene and more

preferably polyisobutylene. The molecular weight of a tackifying viscous polymeric component is preferably from 10,000 to 120,000 when determined by GPC.

The mouldable mass of the invention may, if required, comprise a further oily plasticiser for plasticizing SEBS and polyisobutylene/polybutylene in order to reduce the elasticity.

5 Such oily plasticizer is suitably a viscous polymeric material having molecular weight from 300 to 10,000 when determined by GPC.

The mouldable mass of the invention may comprise a tackifier increasing the adhesive properties of the composition in order to ensure a good contact between the appliance and the skin. Such a tackifier is preferably a hydrocarbon tackifier homogeneously distributed in the mass. The tackifier is preferably a terpene tackifier resin or a dicyclopentadiene tackifier resin. Especially preferred according to the invention as hydrocarbon tackifier resin are polymers and copolymers of dicyclopentadiene, alpha-pinene and/or beta-pinene.

10 The waxy component may e.g. be a mineral wax or petroleum jelly and is most preferred microcrystalline wax being compatible with the preferred blockcopolymer SEBS.

In accordance with a preferred embodiment of the invention the mass comprises a hydrocolloid which are able to absorb moisture or liquids from the body and thus to increase the wearing-time of the adhesive and thus of the ostomy appliance. A hydrocolloid component may e.g. be a water absorbing and water swellable component 20 being mixable with the main components of the mass. Any hydrocolloid known per se for ostomy or wound care purposes may be used. The hydrocolloid may e.g. be sodium carboxymethylcellulose (CMC), hydroxyethylcellulose, pectin, gelatine, guar gum, karaya, locust bean gum, carrageenan, xanthan, or sodium or calcium alginate. A hydrocolloid will typically be present in an amount of from 20 to 70% by weight of the total 25 composition in order to have a sufficient absorbent capacity and still retain the characteristics of the mouldable mass. More preferred, the total amount of hydrocolloids is from 30 to 60%, and preferably the total amount of hydrocolloids is from 45 to 60% by weight.

For some purposes it is suitable also to include smaller amounts of a filler in the mass of the invention which may add to the cohesion and also contribute to the plasticity. Such filler may e.g. be any filler known per se for ostomy or wound care purposes such as talc, calcium carbonate, china clay, zinc oxide or the like. Such filler may constitute 5 up to 3 - 20% by weight of the composition.

Still further, the masses according to the invention may optionally comprise further constituents such as emollients, disinfecting agents and/or bactericidal agents known per se for use for ostomy or wound care purposes.

An especially preferred embodiment of the invention is constituted by a mouldable 10 mass comprising SEBS, polybutene, polybutene oil, a tackifier resin, microcrystalline wax, CMC, pectin, gelatine and zinc white.

The mass may preferably be packed in metered amounts, e.g. in a blister pack or as a rod. A rod may be flat or rolled and have a release liner on one or both sides. The product is preferably produced and packed in a bag under aseptic conditions. The embodiment of a mass in the form of a relatively flat rod which is optionally rolled and which is 15 optionally covered with a release liner known per se on one or both sides is considered a further aspect of the invention. A rod may e.g. comprise an amount of the mass of the invention suitable for one or more applications,

The invention also relates to a method for preparing a mouldable mass of a hypoallergenic, substantially non-memory putty-like adhesive for use in connection with an ostomy appliance comprising

- a) a blockcopolymer having a major content of di-block copolymer,
- b) a tackifying liquid constituent, and
- c) a waxy constituent

25 which method comprises mixing the blockcopolymer having a major content of di-block copolymer and a part of the tackifying liquid constituent during heating at a temperature from 50 to 200 °C, and admixing the remaining part of the tackifying liquid constituent and the waxy constituent .

The mixing is preferably carried out in a Z-mixer which is preferably preheated to a temperature of 160°C. Firstly equal parts of copolymer and tackifying liquid constituent are mixed at 160°C for 20 minutes in vacuum.

5 Then, the remains of the tackifying liquid constituent is admixed together with the waxy constituent at the same temperature, and a mixing of 10 minutes is carried out for each addition.

If hydrocolloids are to be added, the temperature is lowered to below 100°C, preferable at the most 90°C, before addition, and a vacuum is applied

10 during addition and the further mixing for about 15 minutes.

In a further aspect, the invention relates to the use of a mouldable mass of a hypoallergenic, substantially non-memory putty-like adhesive for use in connection with an ostomy appliance comprising:

15 a) a block copolymer having a major content of di-block copolymer;

b) a tackifying liquid constituent; and

c) a waxy constituent

as a paste for smoothing out a surface on which an ostomy appliance is to be applied.

The invention is explained more in detail with reference to the below

20 working examples illustrating embodiments of the invention. The examples are not to be considered as limiting of the scope of protection being defined in the appended claims.

Throughout this specification, unless the context requires otherwise, the word "comprise", or variations such as "comprises" or "comprising", will

25 be understood to imply the inclusion of a stated element, integer or step, or group of elements, integers or steps, but not the exclusion of any other element, integer or step, or group of elements, integers or steps.

#### Materials and Methods

30 Kraton®G1726 from Shell: Styrene-ethylenebutylene-styrene copolymer (SEBS) having a molecular weight of 45,000 as determined by GPC and a content of di-block co-polymer of 70%.



Kraton®D1118 from Shell: Styrene-butadiene-styrene copolymer (SBS) having a molecular weight of 103,000 (GPC) and a content of di-block copolymer of 80%.

5 Vector®4114 from Exxon: Styrene-isoprene-styrene copolymer (SIS) having a molecular weight of 133,000 and a content of di-block copolymer of 40%.



Vistanex® LM-MH from Exxon: polyisobutylene (PIB) having a molecular weight of 90,000 (GPC).

Wax Total 40/60 from TOTAL.

Petroleum jelly: Vaselineum Album from Witco

5 Polybutene oil: Hyvis® 10 from BP having a molecular weight of 1,500, Hyvis® 30 from BP having a molecular weight of 3,000.

Polybutene: Hyvis® 2000 from BP having a molecular weight  $M_w$  of 30,000

Mineral Oil: PL 500 from Parafluid Mineral Oel

Tackifier resin: Regalite® R91 resin from Hercules or Arkon® P-90 resin from Arakawa

10 Sodium carboxymethylcellulose: Akucell® AF2881 from Akzo or  
Blanose® 9H4XF from Hercules Corp.

Guar gum: Guar Gum FG 200 from Nordisk Gelatine

Pectin: Pektin LM 12CG Z from Copenhagen Pectin or  
Pektin USP/100 from Copenhagen Pectin

15 Gelatin: Gelatine P.S.98.240.233 from ED. Geistlich Sohne AG

Zinc Oxide: Zinkoxid Pharma from Hoechst AG

A Z mixer Type LKB 025 from Herman-Linden was used.

## EXPERIMENTAL PART

### EXAMPLE 1.

Preparation of a mouldable mass according to the invention.

100 grams of Kraton® G1726 was used and the amounts of other ingredients used correspond to the composition stated in Table 1.

Equal amounts of Kraton® G1726 (SEBS) and of Vistanex® LM-MH were mixed in a Z Mixer for 20 minutes at 160 °C under a vacuum of 100 mbar. Then, the vacuum was released, the mixing was continued at 160 °C for 10 minutes and the remains of Vistanex® LM-MH, the wax, and petroleum jelly were admixed and mixed for 10 minutes 10 each. Then, the heating was turned off, and guar gum was added at maximum 90 °C under a vacuum of 100 mbar and mixed for 10 minutes. Finally, pectin, gelatine and zinc oxide were admixed at a temperature of 90 °C and mixed for 10 minutes.

The paste is then ready to use and may preferably be packed in metered amounts, e.g. in a blister pack or rod. A rod may be rolled and have a release liner on one or both 15 sides. The product is preferably produced and packed under aseptic conditions.

### EXAMPLE 2.

Preparation of a mouldable mass according to the invention.

100 grams of Kraton® G1726 was used and the amounts of other ingredients used correspond to the composition stated in Table 1.

20 Equal amounts of Kraton® G1726 (SEBS) and Vistanex® LM-MH were mixed in a Z Mixer for 20 minutes at 160 °C under a vacuum of 100 mbar. Then, the vacuum was released, the mixing was continued at 160 °C for 10 minutes and the remains of Vistanex® LM-MH, the wax, and Hyvis® 10 or PL 500 were admixed and mixed for 10 minutes each. Then, the heating was turned off, and guar gum was added at maximum

90 °C under a vacuum of 100 mbar and mixed for 10 minutes. Finally, pectin, gelatine and zinc oxide were admixed at a temperature of 90 °C and mixed for 10 minutes.

The paste is then ready to use and may preferably be packed in metered amounts, e.g. in a blister pack or rod. A rod may be rolled and have a release liner on one or both 5 sides. The product is preferably produced and packed under aseptic conditions.

### EXAMPLES 3 - 5

Preparation of mouldable masses according to the invention.

In the same manner as described in Example 2 above, mouldable masses according to the invention were produced having the compositions stated in the below Table 1:

10 **Table 1**

Composition of mouldable masses of the invention of Examples 1 - 5 stated in % by weight

Component	Example 1	Example 2	Example 3	Example 4	Example 5
SEBS	5	5	5	10	8
PIB	30	15	15	10	18
Microcrystalline wax	5	5	5	5	5
Petroleum jelly	10				
Polybutene oil, Hyvis® 10		25			
Liquid paraffin			25	25	20
CMC			12	20	15
Guar Gum	15	20			
Pectin	15	10	10	10	8
Gelatine	18	17.5	27	20	23
Zinc white	2	2.5	1		3

**EXAMPLE 6.**

Preparation of a mouldable mass according to the invention.

Equal amounts of Kraton® G1726 (SEBS) and Hyvis® 2000 were mixed in a Z Mixer for 30 minutes at 160 °C under a vacuum of 100 mbar and the Hyvis® 2000 was added 5 in four parts to ensure homogeneity during the admixing over a period of 20 minutes.

Then, the remains of Hyvis® 2000 was added in four parts at 160 °C over 30 minutes and the vacuum was released. The Hyvis® 10 was added in four parts and mixed for 15 minutes. Wax was added and mixed for 10 minutes. Then, the heating was turned off, and guar gum and CMC were added at maximum 90 °C under a vacuum of 100 10 mbar and mixed for 10 minutes. Finally, pectin, gelatine and zinc oxide were admixed at a temperature of 90 °C and mixed for 10 minutes.

The paste was ready to use and may preferably be packed in metered amounts, e.g. in a blister pack or rod. A rod may be rolled and have a release liner on one or both sides. The product is preferably produced and packed under aseptic conditions.

**15 EXAMPLES 7 - 8**

Preparation of mouldable masses according to the invention.

In the same manner as described in the Example 2 above, mouldable masses according to the invention were produced having the compositions stated in the below Table 2:

**Table 2**

Composition of mouldable masses of the invention of Examples 6 - 8 stated in % by weight

Component	Example 6	Example 7	Example 8
SEBS (Diblock content about 70%)	5		
SIS (Diblock content about 40%)		5	
SB (Diblock content about 80%)			5
PIB		15	15
Polybutene ( $M_w$ 30.000)	15		
Polybutene oil, Hyvis® 10	25	25	25
Microcrystalline wax	5	5	5
CMC	10	13	25
Guar Gum	15		
Pectin	5	10	8
Gelatine	18	22	15
Zinc white	2	5	2

### EXAMPLES 9 - 10

#### 5 Preparation of mouldable masses according to the invention.

Equal amounts of Kraton® G1726 (SEBS) and Hyvis® 2000 were mixed in a Z Mixer for 30 minutes at 160 °C under a vacuum of 100 mbar and the Hyvis® 2000 was added in four parts to ensure homogeneity during the admixing over a period of 20 minutes.

Then, the remains of Hyvis® 2000 was added in four parts at 160 °C over 30 minutes and the vacuum was released. The Hyvis® 10 was added in four parts and mixed for 15 minutes. Resin and wax was added and mixed for 10 minutes each. Then, the heating was turned off, and CMC were added at maximum 90 °C under a vacuum of 100 mbar and mixed for 10 minutes. Finally, pectin, gelatine and zinc oxide were admixed at a temperature of 90 °C and mixed for 10 minutes.

The paste was ready to use and may preferably be packed in metered amounts, e.g. in a blister pack or rod. A rod may be rolled and have a release liner on one or both sides. The product is preferably produced and packed under aseptic conditions.

**Table 3**

5 Composition of mouldable masses of the invention of Examples 9 - 10 stated in % by weight:

Component	Example 9	Example 10
SEBS (Diblock content about 70%)	5	5
Polybutene ( $M_w$ 30.000)	10	5
Polybutene oil, Hyvis® 10	25	25
Resin	5	10
Microcrystalline wax	5	5
CMC	15	15
Pectin	10	10
Gelatine	24	24
Zinc white	1	1

### EXAMPLES 11 - 12

Preparation of mouldable masses according to the invention.

In the same manner as described in the Example 6 above, mouldable masses according to the invention were produced having the compositions stated in the below Table 4.

**Table 4**

Composition of mouldable masses of the invention of Examples 11 - 13 stated in % by weight:

Component	Example 11	Example 12	Example 13
SEBS (Diblock content about 70%)	5	5	5
Polybutene ( $M_w$ 30.000)	15	15	20
Polybutene oil, Hyvis® 10 or 30*	25	25	20
Amorphous polyolefin wax	2.5	5	2.5
Microcrystalline wax	2.5		2.5
CMC	20	20	20
Pectin	10	12	10.5
Gelatine	19	17.5	19
Zinc white	1	0.5	0.5

In Examples 11-12, Hyvis® 10 was used and in Example 13, Hyvis® 30 was used.

## 5 EXAMPLE 13

Preparation of a mouldable mass according to the invention.

100 grams of Kraton® G1726 was used and the amounts of other ingredients used correspond to the composition stated in Table 4.

Equal amounts of Kraton® G1726 (SEBS) and Hyvis® 2000 were mixed in a Z Mixer 10 for 1½ hours at 160 °C under a vacuum of 100 mbar and the Hyvis® 2000 was added in four parts to ensure homogeneity during the admixing over a period of 20 minutes. Then, the remains of Hyvis® 2000 was added in four parts and wax was at 160 °C over 3 hours and the vacuum was released. Then, the heating was turned off, and Hyvis® 30 and CMC were added over 15 minutes at maximum 60 °C under a vacuum of 15 100 mbar and mixed for 1 hour. Finally, pectin, gelatine and zinc oxide were admixed at a temperature of 60 °C and mixed for 10 minutes.

The paste was ready to use and may preferably be packed in metered amounts. The product is preferably produced and packed under aseptic conditions.

## THE CLAIMS DEFINING THE INVENTION ARE AS FOLLOWS:-

1. A mouldable mass of a hypoallergenic, substantially non-memory putty-like adhesive for use in connection with an ostomy appliance comprising a styrene block copolymer and a tackifying constituent, characterised in that the mass comprises:
  - a) 1 to 20% by weight of a styrene block copolymer having a molecular weight of from 20,000 to 150,000 and wherein the contents of di-block copolymer is above 25%;
  - b) 5 to 60% by weight of a tackifying liquid constituent in the form of a viscous polymeric material being compatible with the block copolymer;
  - c) 1 to 10% by weight of a waxy constituent; and
  - d) a hydrocolloid.
2. A mouldable mass of a hypoallergenic, substantially non-memory putty-like adhesive when used in connection with an ostomy appliance comprising a styrene block copolymer and a tackifying constituent, characterised in that the mass comprises:
  - a) 1 to 20% by weight of a styrene block copolymer having a molecular weight of from 20,000 to 150,000 and wherein the contents of di-block copolymer is above 25%.
  - b) 5 to 60% by weight of a tackifying liquid constituent in the form of a viscous polymeric material being compatible with the block copolymer,
  - c) 1 to 10% by weight of a waxy constituent and
  - d) a hydrocolloid.
3. A mass as claimed in claim 1 or claim 2, characterised in that it comprises an oily plasticiser.
4. A mass as claimed in any one of claims 1 to 3, characterised in that it comprises one or more tackifiers.
5. A mass as claimed in any one of claims 1 to 4, characterised in that it comprises a filler.
- 30 6. A mass as claimed in any one of claims 1 to 5, characterised in that it comprises an active ingredient such as a bactericidal and/or disinfecting agent.



7. A method for preparing a mouldable mass of a hypoallergenic, substantially non-memory putty-like adhesive for use in connection with an ostomy appliance comprising a styrene block copolymer and a tackifying constituent wherein the mass comprises:

5        a) 1 to 20% by weight of a block copolymer having a molecular weight of from 20,000 to 150,000 wherein the contents of di-block copolymer is above 25%;

10      b) 5 to 60% by weight of a tackifying liquid constituent in the form of a viscous polymeric material being compatible with the block copolymer;

15      c) 1 to 10% by weight of a waxy constituent; and

20      d) a hydrocolloid,

which method comprises mixing the block copolymer having a molecular weight of from 20,000 to 150,000 wherein the contents of di-block copolymer is above 10% and a part of the tackifying liquid constituent in the form of a viscous polymeric material being compatible with the block copolymer during heating at a temperature from 50 to 200° C, and admixing the remaining part of the tackifying liquid constituent and the waxy constituent, whereafter the hydrocolloid is admixed after reducing the temperature to a level below 100° C.

25      8. A method for preparing a mouldable mass of a hypoallergenic, substantially non-memory putty-like adhesive when used in connection with an ostomy appliance comprising a styrene block copolymer and a tackifying constituent wherein the mass comprises:

20      a) 1 to 20% by weight of a block copolymer having a molecular weight of from 20,000 to 150,000 wherein the contents of di-block copolymer is above 25%;

25      b) 5 to 60% by weight of a tackifying liquid constituent in the form of a viscous polymeric material being compatible with the block copolymer;

30      c) 1 to 10% by weight of a waxy constituent; and

35      d) a hydrocolloid.



which method comprises mixing the block copolymer having a molecular weight of from 20,000 to 150,000 wherein the contents of di-block copolymer is above 10% and a part of the tackifying liquid constituent in the form of a viscous polymeric material being compatible with the block copolymer  
5 during heating at a temperature from 50 to 200° C, and admixing the remaining part of the tackifying liquid constituent and the waxy constituent, whereafter the hydrocolloid is admixed after reducing the temperature to a level below 100° C.

9. Use of a mouldable mass of a hypoallergenic, substantially non-  
10 memory putty-like adhesive for use in connection with an ostomy appliance comprising a styrene block copolymer and a tackifying constituent wherein the mass comprises:

15 a) 1 to 20% by weight of a block copolymer having a molecular weight of from 20,000 to 150,000 wherein the contents of di-block copolymer is above 25%;

b) 5 to 60% by weight of a tackifying liquid constituent in the form of a viscous polymeric material being compatible with the block copolymer;

c) 1 to 10% by weight of a waxy constituent; and

d) a hydrocolloid

20 as a paste for preparing the skin around a stoma to provide a plane surface for placing an ostomy appliance.

10. A mouldable mass of a hypoallergenic, substantially non-memory putty-like adhesive when used in connection with an ostomy appliance comprising a styrene block copolymer and a tackifying constituent wherein the mass comprises:

a) 1 to 20% by weight of a block copolymer having a molecular weight of from 20,000 to 150,000 wherein the contents of di-block copolymer is above 25%;

b) 5 to 60% by weight of a tackifying liquid constituent in the form of a viscous polymeric material being compatible with the block copolymer;

c) 1 to 10% by weight of a waxy constituent; and

d) a hydrocolloid.

30 as a paste for preparing the skin around a stoma to provide a plane surface for placing an ostomy appliance.



11. A mouldable mass of a hypoallergenic, substantially non-memory putty-like adhesive substantially as hereinbefore described and with reference to the accompanying examples excluding any comparative examples.

Dated this fourteenth day of May 1999

COLOPLAST A/S  
Patent Attorneys for the Applicant:

F B RICE & CO

