

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
28 December 2006 (28.12.2006)

PCT

(10) International Publication Number
WO 2006/138017 A1

(51) International Patent Classification:
C04B 24/16 (2006.01) **C04B 28/14** (2006.01)

(21) International Application Number:
PCT/US2006/019517

(22) International Filing Date: 19 May 2006 (19.05.2006)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
11/153,966 16 June 2005 (16.06.2005) US

(71) Applicant: **LYONDELL CHEMICAL TECHNOLOGY, L.P.** [US/US]; Two Greenville Crossing, 4001 Kennett Pike, Suite 238, Greenville, Delaware 19807 (US).

(72) Inventors: **SCHWARTZ, Steven, A.**; 102 Brierley Court, Downingtown, Pennsylvania 19335 (US). **LI-OTTA, Frank, J.**; 59 Tarrytown Lane, Downingtown, Pennsylvania 19335 (US). **BARSA, Edward, A.**; 9 Alexandra Court, Glen Mills, Pennsylvania 19342 (US).

(74) Agents: **GUO, Shao-Hua** et al.; Lyondell Chemical Company, 3801 West Chester Pike, Newtown Square, Pennsylvania 19073 (US).

(81) Designated States (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, LY, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: PREPARATION OF GYPSUM COMPOSITIONS

(57) Abstract: A gypsum composition containing a sulfonate-containing comb-branched copolymer is disclosed. The sulfonate-containing comb-branched copolymer comprises recurring units of a polyether macromonomer, an acrylic monomer, and a sulfonate monomer. The sulfonate-containing comb-branched copolymer not only increases the fluidity of gypsum slurry but also has reduced retardation on the gypsum setting.



WO 2006/138017 A1

PREPARATION OF GYPSUM COMPOSITIONS

FIELD OF THE INVENTION

The invention relates to gypsum compositions. The gypsum composition
5 comprises a sulfonate-containing comb-branched copolymer. The comb-branched copolymer improves the fluidity of the gypsum composition.

BACKGROUND OF THE INVENTION

Gypsum is commonly manufactured by drying, grinding, and calcining
10 natural gypsum rock. The drying step involves passing crude gypsum rock through a rotary kiln to remove free moisture. The dried rock is then ground. The calcination is to dehydrate the ground gypsum rock to hemihydrate:



15

Gypsum reacts with water and sets rather quickly. The setting is a reversal of the calcination. The hemihydrate gypsum dissolves in water until it is saturated. The soluble hemihydrate forms dihydrate which is less soluble than hemihydrate. As dihydrate crystals precipitate, the hemihydrate solution is no
20 longer saturated, and the process continues to consume the hemihydrate gypsum. The reaction can be followed by measuring the heat evolved. Initially there is very little reaction and no rise in temperature. This time is referred to as the induction period. As the amount of dihydrate increases, the mass thickness increases, and the gypsum sets.

25 A large amount of excess water is generally required to provide the gypsum slurry with sufficient fluidity during the process. It is desirable to reduce the amount of excess water to save energy and production cost associated with water removing.

Water reducing agents are known. For example, naphthalene sulfonate
30 has been used as a water reducing agent. One drawback of naphthalene

sulfonate is that it requires a high dosage. Further, gypsum compositions containing naphthalene sulfonate tend to set too fast. To slow down the setting, a setting retardant is often added.

5 Recently, acrylic-polyether comb-branched copolymers are used as water reducing agents in gypsum compositions. See U.S. Pat. No. 6,527,850. The comb-branched copolymers can be used in much lower dosages than naphthalene sulfonate. However, the comb-branched copolymers tend to retard the setting.

10 In sum, new water reducing agents are needed. Ideally, the water reducing agents would not only improve the fluidity but also have no or reduced retardation on gypsum setting.

SUMMARY OF THE INVENTION

15 The invention is a gypsum composition. The gypsum composition comprises a sulfonate-containing comb-branched copolymer. The comb-branched copolymer comprises recurring units of a polyether macromonomer, an acrylic monomer, and a sulfonate monomer. We surprisingly found that the sulfonate-containing comb-branched copolymer not only improves the fluidity but also has reduced retardation on the gypsum setting.

20

DETAILED DESCRIPTION OF THE INVENTION

The gypsum composition of the invention comprises water, gypsum, and a sulfonate-containing comb-branched copolymer. The comb-branched copolymer comprises recurring units of a polyether macromonomer, an acrylic monomer, and a sulfonate monomer.

25

Suitable polyether macromonomers have a polyether chain and a C=C double bond, which can be located either at the end of or inside the polyether chain. Examples include polyether monoacrylates, polyether monomethacrylates, polyether monoallyl ethers, polyether monomaleates, and polyether monofumarates. The polyether of the macromonomer is an alkylene oxide

30

polymer having a number average molecular weight preferably within the range of about 500 to about 10,000, more preferably within the range of about 1,000 to about 5,000, and most preferably within the range of about 1,000 to about 3,000. Suitable alkylene oxides include ethylene oxide, propylene oxide, butylene oxide, and the like, and mixtures thereof. The polyether
5 macromonomers preferably have hydroxyl functionality from 0 to 5. They can be either linear or branched polymers, homopolymers or copolymers, random or block copolymers, diblock or multiple-block copolymers.

Examples of polyether macromonomers are poly(propylene glycol) acrylates or methacrylates, poly(ethylene glycol) acrylates or methacrylates,
10 poly(ethylene glycol) methyl ether acrylates or methacrylates, acrylates or methacrylates of an oxyethylene and oxypropylene block or random copolymer, poly(propylene glycol) allyl ether, poly(ethylene glycol) allyl ether, poly(propylene glycol) mono-maleate, and the like, and mixtures thereof. Preferred polyether
15 macromonomer is selected from the group consisting of poly(propylene glycol) acrylates and methacrylates, poly(ethylene glycol) acrylates and methacrylates, acrylates and methacrylates of oxyethylene and oxypropylene block and random copolymers, and mixtures thereof.

Suitable acrylic monomers derive from acrylic acid and methacrylic acid. Preferred acrylic monomers include acrylic acid, methacrylic acid, their
20 ammonium and alkali metal salts, their C₁ to C₁₀ alkyl and C₆ to C₁₂ aryl esters, and their amides. Acrylic acid, methacrylic acid, ammonium acrylate, ammonium methacrylate, sodium acrylate, sodium methacrylate, potassium acrylate, and potassium methacrylate are preferred. Most preferred are acrylic
25 acid and methacrylic acid. Particularly preferred acrylic monomer is methacrylic acid.

Suitable sulfonate monomers include those which have a sulfonate group and a polymerizable C=C double bond. Preferably the sulfonate monomer is selected from the group consisting of 2-acrylamido-2-methylpropanesulfonic
30 acid, vinyl sulfonic acid, allyl ether sulfonic acid, 2-sulfoethyl methacrylate, styrene sulfonic acid, methallyl sulfonic acid, their sodium, potassium,

ammonium salts, and mixtures thereof. More preferably the sulfonate monomer is selected from the group consisting of 2-acrylamido-2-methylpropanesulfonic acid, styrene sulfonic acid, their sodium, potassium, and ammonium salts, and mixtures thereof.

5 The relative amounts of polyether macromonomer, acrylic monomer, and sulfonate monomer are determined by many factors within the skilled person's discretion, including the required physical properties of the comb-branched copolymer, the selection of the acrylic and sulfonate monomers, and the properties of the polyether macromonomer. Preferably, the molar ratio of
10 polyether macromonomer to the sum of acrylic and sulfonate monomers is 1/10 or greater. More preferably, the molar ratio of polyether macromonomer to the sum of acrylic and sulfonate monomers is 1/5 or greater. Preferably, the molar ratio of acrylic monomer to sulfonate monomer is within the range of 1/10 to 10. More preferably, the molar ratio of acrylic monomer to sulfonate monomer is
15 within the range of 1/2 to 1.

Optionally, other monomers may be incorporated into the comb-branched copolymer. Examples of other monomers include vinyl aromatics, vinyl halides, vinyl ethers, vinyl esters, vinyl pyrrolidinones, conjugated dienes, unsaturated phosphonic acids, and the like, and mixtures thereof. The amount of other
20 monomers used depends on the required physical properties of the comb-branched copolymer product but is preferably less than 50% by weight of the comb-branched copolymer.

The comb-branched copolymer can be made by batch, semi-batch and continuous polymerization process. It is preferably made by a continuous
25 process. In one process, a monomer stream, an initiator stream, and an optional chain transfer agent stream are formed. The polymerization is carried out by continuously feeding a reactor the three streams.

Alternatively, the polymerization can be performed by a multiple-zone process. The multiple-zone process comprises forming a monomer stream, an
30 initiator stream, and an optional chain transfer agent stream, polymerizing the streams in a first reactor, and transferring a first polymer stream from the first

reactor to a second reactor wherein the polymerization continues. The multiple-zone process enhances monomer conversion and process efficiency.

The monomer stream contains the polyether macromonomer, the acrylic monomer, and sulfonate monomer. Optionally, the monomer stream also
5 includes a solvent. The solvent is used to dissolve the monomer, to assist heat transfer of the polymerization, or to reduce the viscosity of the final product. The solvent is preferably selected from water, alcohols, ethers, esters, ketones, aliphatic hydrocarbons, aromatic hydrocarbons, halides, and the like, and mixtures thereof. Selections of solvent type and amount are determined by the
10 polymerization conditions including reaction temperature. Water and alcohols, such as methanol, ethanol, and isopropanol, are preferred.

The initiator stream contains a free radical initiator. The initiator is preferably selected from the group consisting of persulfates, hydrogen peroxide, organic peroxides and hydroperoxides, azo compounds, and redox initiators
15 such as hydrogen peroxide plus ferrous ion. Persulfates, such as ammonium and potassium persulfate, are preferred.

Optionally, the initiator stream contains a solvent. The solvent is used to dissolve or dilute the initiator, to control the polymerization rate, or to aid heat or mass transfer of the polymerization. Suitable solvents are described above.
20 Selections of solvent type and amount are determined by the nature of the initiator and the polymerization conditions. Water and alcohols such as methanol, ethanol, and isopropanol are preferred when persulfate is used as initiator.

The monomer and initiator streams optionally include a chain transfer
25 agent. Suitable chain transfer agent includes alkyl amines, alkyl sulfides, alkyl disulfides, carbon tetrahalides, allyl ethers, and mercaptans. Mercaptans, such as butyl mercaptan, mercaptoacetic and mercaptopropionic acids, are preferred.

Under some conditions, it is preferred to add the chain transfer agent in a separate stream. This is particularly desirable when the chain transfer agent causes decomposition of the initiator or polymerization of the monomer once it is mixed with those components. This is particularly important in a large,
5 commercial scale because these reactions can cause safety problems.

Optionally, the chain transfer agent stream contains a solvent that is used to dissolve or dilute the chain transfer agent. Suitable solvents include water, alcohols, ethers, esters, ketones, aliphatic and aromatic hydrocarbons, halides, and the like, and mixtures thereof. Selections of solvent type and amount are
10 determined by the nature of the chain transfer agent and the polymerization conditions. Water and alcohols, such as methanol, ethanol, and isopropanol, are preferred.

The comb-branched copolymer has a weight average molecular weight preferably within the range of 10,000 to 150,000, more preferably within the
15 range of 50,000 to 150,000, most preferably within the range of 50,000 to 100,000. It preferably has a molecular weight distribution M_w/M_n less than 3. More preferably, it has M_w/M_n less than 2. The comb-branched copolymer not only reduces the consistency but also leads to a quick setting of the gypsum composition.

20 The comb-branched copolymer is preferably fully or partially neutralized if the acrylic or sulfonate monomers are acids. Suitable neutralizing agents include alkali metal oxides and hydroxides, alkaline earth metal oxides and hydroxides, ammonium and amines. Examples are sodium hydroxide, potassium hydroxide, calcium hydroxide, ammonium, triethanolamine,
25 diethanolamine, triisopropanolamine, the like, and mixtures thereof.

The amount of the comb-branched copolymer present in the gypsum composition is preferably within the range of 0.001 to 5 wt%, more preferably within the range of 0.05 to 1 wt%, and most preferably within the range of 0.025 to 0.5 wt%.

The gypsum is preferably present in an amount greater than 40 wt% of the gypsum composition. More preferably, it is present in an amount greater than 45 wt% of the gypsum composition. Most preferably, it is present in an amount greater than 50 wt% of the gypsum composition.

5 Water is used to disperse and set the gypsum. An excess amount of water is needed in processing the gypsum composition. When the gypsum products such as gypsum wallboards are made, the excess water is removed by heating. One advantage of the invention is that a reduced amount of water is used in the gypsum composition so that less time and energy are needed to
10 remove the excess water. The amount of water required in the gypsum composition can be defined as consistency, i.e., the volume of water (ml) required to produce 100 g of gypsum.

Optionally, the gypsum composition comprises a setting accelerator which reduces the initial setting time of the gypsum composition. Examples of
15 suitable setting accelerators include metal sulfates, oxides and hydroxides such as sodium sulfate, calcium sulfate, and calcium hydroxide. Suitable accelerators include those treated with sugar, starch and boric acids as taught by U.S. Pat. No. 6,409,823.

The invention includes articles made from the gypsum composition such
20 as wallboards. Methods for making gypsum wallboards are known. See, for instance, U.S. Pat. No. 6,527,850.

The following examples merely illustrate the invention. Those skilled in the art will recognize many variations that are within the spirit of the invention and scope of the claims.

25

EXAMPLE 1

PREPARATION OF COMB-BRANCHED COPOLYMERS

Preparation of Polymer A

Step 1: forming the following streams:

Monomer stream: 2-acrylamido-2-methyl-1-propanesulfonic acid (62 parts by weight), methacrylic acid (39 parts by weight) and distilled water (545 parts by weight) are mixed. Sodium hydroxide (24 parts by weight, 50% aqueous solution) is added to the mixture to neutralize the acids. An acrylate of oxyethylene/oxypropylene random copolymer having oxyethylene/ oxypropylene ratio 70/30 by weight and number average molecular weight Mn of 3,000 (449 parts by weight) is added to the mixture.

Chain transfer stream: 0.9 wt% 3-mercaptopropionic acid aqueous solution.

Initiator stream: 1.8 wt% ammonium persulfate aqueous solution.

Step 2: continuously feeding the three streams to a reactor in the rates: monomer stream: 2.75 ml/min; chain transfer stream: 0.76 ml/min; and initiator stream: 0.217 ml/min. The polymerization is performed at a temperature of about 66°C. A polymer stream is continuously withdrawn from the reactor with a residence time of about 100 min.

The copolymer has a weight average molecular weight of 67,000 and molecular weight distribution (Mw/Mn) of 1.40 by GPC. The GPC analysis is performed on HP 1100 Series; Tosohaas (TSKgel) G4000PW GPC Column 300 mm x 7.5 mm ID, particle size 17 (μm) (Aldrich); mobile phase: 1% KNO₃ aqueous solution.

Preparation of Polymers B and C

Polymers B and C are prepared according to the above procedure by varying the amounts and types of monomers. In Polymer B, sodium styrene sulfonate is used. In Polymer C, no sulfonate monomer is used. The compositions, molecular weights, and molecular weight distributions are listed in Table I.

EXAMPLES 2-3 AND
COMPARATIVE EXAMPLES C4-C5

PREPARATION OF GYPSUM COMPOSITION SLURRY

A slurry is prepared by swiftly adding calcined stucco (100 g, CaSO_4
5 $\frac{1}{2}\text{H}_2\text{O}$, product of Samuel French and Company, Philadelphia, PA) and a set
accelerator (calcium sulfate dihydrate coated with sugar, 0.1 wt. % of the stucco,
product of United States Gypsum Corporation, Libertyville, IL) to aqueous
solutions (75 ml) containing Polymers A and B, respectively, in Examples 2 and
3. The polymer is used in 0.5 wt% of the stucco.

10 In Comparative Example C4, no polymer is used.

In Comparative Example C5, a non-sulfonate containing polymer is used.

The slurry is gently hand-agitated for 60 seconds using a $\frac{3}{4}$ " metal
spatula in order to provide uniform wetting of the gypsum. This is immediately
followed by more vigorous mixing for 30 seconds at a rate of about 160
15 strokes/min. The slurry is immediately poured into a funnel ($\frac{1}{2}$ " outlet diameter)
that is positioned 90 mm above a clean, glass plate. The slurry flows through
the funnel to produce a circular gypsum patty. Fluidity is determined by the
diameter of the resulting circular patty. Set times are determined by a "knife-set"
test and a $\frac{1}{4}$ pound and 1 pound Gillmore Needle Tests (ASTM C266). The
20 knife-set time is the period over which a knife cut made into the surface of a
poured gypsum patty ceases to heal. The Gillmore set time occurs when a
weighted needle rests on the surface of the gypsum patty without making a
detectable impression. Table II lists the test results which indicate that while all
copolymers increase the fluidity of the gypsum slurry, the sulfonate-containing
25 copolymers have significantly reduced retardation on the setting.

TABLE I
COMB-BRANCHED COPOLYMERS

Polymer	MA mole %	Polyether Macromonomer Mole %	Sulfonate Monomer		Mw	Mw/Mn
			Type	Mole %		
A	33	17	AMPS	50	67,000	1.4
B	50	17	SS	33	53,000	1.4
C	83	17	-	0	-	-

MA: methacrylic acid

AMPS: 2-acrylamido methylpropanesulfonic acid

SS: styrene sulfonic acid

TABLE II
PERFORMS OF COMB-BRANCHED COPOLYMERS IN GYPSUM COMPOSITIONS

Example	Polymer	Average Patty Diameter (mm)	Average Knife Set (s)	Average ¼ lb Gillmore (s)	Average 1 lb Gillmore (s)
2	A	143	205	483	767
3	B	143	211	491	791
C4	-	128	189	446	738
C5	C	148	248	568	890

We claim:

1. A gypsum composition comprising water, a gypsum, and a sulfonate-containing comb-branched copolymer that comprises recurring units of a polyether macromonomer, an acrylic monomer, and a sulfonate monomer.
- 5 2. The composition of claim 1 wherein the gypsum is derived from calcium sulfate hemihydrate.
3. The composition of claim 1 wherein the polyether macromonomer is selected from the group consisting of poly(propylene glycol) acrylates and methacrylates, poly(ethylene glycol) acrylates and methacrylates, acrylates
10 and methacrylates of oxyethylene and oxypropylene block and random copolymers, and mixtures thereof.
4. The composition of claim 1 wherein the polyether macromonomer is an acrylate or methacrylate of an oxyethylene and oxypropylene copolymer.
5. The composition of claim 1 wherein the polyether macromonomer has
15 a number average molecular weight within the range of 500 to 10,000.
6. The composition of claim 1 wherein the polyether macromonomer has a number average molecular weight within the range of 1000 to 5000.
7. The composition of claim 1 wherein the macromonomer has a molecular weight distribution less than 2.
- 20 8. The composition of claim 1 wherein the acrylic monomer is selected from the group consisting of methacrylic acid and its sodium, potassium, and ammonium salts.
9. The composition of claim 1 wherein the sulfonate monomer is selected from the group consisting of 2-acrylamido-2-methylpropanesulfonic acid, styrene sulfonic acid, their sodium, potassium, and ammonium salts, and
25 mixtures thereof.

10. The composition of claim 1 wherein the sulfonate-containing comb-
branched copolymer is a copolymer of an acrylate or methacrylate of an
oxyethylene and oxypropylene copolymer, methacrylic acid, and 2-
acrylamido-2-methylpropanesulfonic acid.
- 5 11. The composition of claim 10 wherein the sulfonate-containing comb-
branched copolymer is neutralized with a neutralizing agent selected from the
group consisting of sodium hydroxide, ammonium, and calcium hydroxide.
12. The composition of claim 1 wherein the sulfonate-containing comb-
branched copolymer is a copolymer of an acrylate or methacrylate of an
10 oxyethylene and oxypropylene copolymer, methacrylic acid, and styrene
sulfonic acid.
13. The composition of claim 12 wherein the sulfonate-containing comb-
branched copolymer is neutralized with a neutralizing agent selected from the
group consisting of sodium hydroxide, ammonium, and calcium hydroxide.
- 15 14. A method for making the gypsum composition of claim 1, said method
comprising mixing water, a gypsum, and a sulfonate-containing comb-
branched copolymer that comprises recurring units of a polyether
macromonomer, an acrylic monomer, and a sulfonate monomer.
15. A gypsum wallboard made from the composition of claim 1.

INTERNATIONAL SEARCH REPORT

International application No

PCT/US2006/019517

A. CLASSIFICATION OF SUBJECT MATTER

INV. C04B24/16 C04B28/14

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

C04B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 6 264 739 B1 (YAMATO FUJIO ET AL) 24 July 2001 (2001-07-24) abstract column 8, lines 6-34 -----	1-15



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

29 August 2006

Date of mailing of the international search report

06/09/2006

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Pollio, M

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/US2006/019517

Patent document cited in search report	Publication date	Patent family member(s)	Publication date	
US 6264739	B1	24-07-2001	JP 3184728 B2	09-07-2001
			JP 8217505 A	27-08-1996