




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 5 : A61F 2/24	A1	(11) International Publication Number: WO 90/09153 (43) International Publication Date: 23 August 1990 (23.08.90)
(21) International Application Number: PCT/US90/00641 (22) International Filing Date: 1 February 1990 (01.02.90) (30) Priority data: 310,424 13 February 1989 (13.02.89) US (71) Applicant: BAXTER INTERNATIONAL INC. [US/US]; One Baxter Parkway, Deerfield, IL 60015 (US). (72) Inventors: LAM, Hung, L. ; 4208 California Avenue, Norco, CA 91760 (US). NGUYEN, Than ; 8312 Magic Circle, Huntington Beach, CA 92646 (US). CARPENTIER, Alain ; 96, rue Didot, F-75014 Paris (FR). (74) Agent: SCHIFFER, Michael, C.; One Baxter Parkway, Deerfield, IL 60015 (US).		(81) Designated States: AT (European patent), BE (European patent), CA, CH (European patent), DE (European patent), DK (European patent), ES (European patent), FR (European patent), GB (European patent), IT (European patent), JP, LU (European patent), NL (European patent), SE (European patent). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>

(54) Title: SELECTIVELY FLEXIBLE ANNULOPLASTY RING**(57) Abstract**

An annuloplasty ring prosthesis (10) which is formed from a selectively flexible body element (14) having at least one defined length (16) about its circumference which is substantially rigid. The remainder of the body element gradually increases in flexibility. The body element (14) is a substantially annular shaped body element which is designed to be sutured to the annulus of a heart valve. The body element (14) is formed from a non-corrosive, anti-magnetic material, and is wrapped in a material (20) through which sutures can be drawn to suture the prosthesis to the heart valve annulus.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	ES	Spain	MG	Madagascar
AU	Australia	FI	Finland	ML	Mali
BB	Barbados	FR	France	MR	Mauritania
BE	Belgium	GA	Gabon	MW	Malawi
BF	Burkina Fasso	GB	United Kingdom	NL	Netherlands
BG	Bulgaria	HU	Hungary	NO	Norway
BJ	Benin	IT	Italy	RO	Romania
BR	Brazil	JP	Japan	SD	Sudan
CA	Canada	KP	Democratic People's Republic of Korea	SE	Sweden
CF	Central African Republic	KR	Republic of Korea	SN	Senegal
CG	Congo	LI	Liechtenstein	SU	Soviet Union
CH	Switzerland	LK	Sri Lanka	TD	Chad
CM	Cameroon	LJ	Luxembourg	TG	Togo
DE	Germany, Federal Republic of	MC	Monaco	US	United States of America
DK	Denmark				

- 1 -

SELECTIVELY FLEXIBLE ANNULOPLASTY RING

BACKGROUND OF THE INVENTION

5 The present invention relates to a support for a natural human heart which may be used for the surgical correction of a deformed heart valve, specifically a heart valve which has become dilated. In particular, the present invention relates to an annuloplasty ring prosthesis for implantation about heart valves.

10 The human heart generally includes four valves. Of these valves the more critical ones are known as the mitral valve, which is located in the left atrioventricular opening, and the tricuspid valve, which is located in the right atrioventricular opening. Both of these valves are intended to prevent regurgitation of blood from the ventricle into the atrium when the ventricle contracts. In preventing blood regurgitation both valves must be able to withstand considerable back pressure as the ventricle contracts. The valve cusps are anchored to the muscular wall of the heart by delicate but strong fibrous cords in order to support the cusps during ventricular contraction. Furthermore, the geometry of the heart valves ensure that the cusps over lay each other to assist in controlling the regurgitation of the blood during ventricular contraction.

25 Diseases and certain natural defects to heart valves can impair the functioning of the cusps in preventing regurgitation. For example, certain diseases cause the dilation of the heart valve annulus. Dilation may also cause deformation of the valve geometry or shape displacing one or more of the valve cusps from the center of the valve. Other

30

- 2 -

5 diseases or natural heart valve defects result in deformation of the valve annulus with little or no dilation. Dilation and/or deformation result in the displacement of the cusps away from the center of the valve. This results in an ineffective closure of the valve during ventricular contraction, which results in the regurgitation or leakage of blood during ventricle contraction. For example, diseases such as rheumatic fever or bacterial inflammations of the heart tissue can cause distortion or dilation of the valvular annulus. Other diseases or malformations result in the distortion of the cusps, which will also lead to ineffective closure of the valve.

10 One method of repairing an impaired valve is to completely replace the valve. This method is particularly suitable for replacing a heart valve when one of the cusps has been severely damaged or deformed. However, presently available artificial heart valves are not as durable as natural heart valves, and it is usually more preferable if the patient's heart valve can be left intact.

20 While it is difficult to retain a heart having diseased or deformed cusps, the ability to surgically correct the deformation of the valve annulus at least provides the possibility of retaining the patient's valve intact. That is, while the replacement of the entire valve eliminates the immediate problem associated with a dilated valve annulus, presently available heart valves do not possess the same durability as natural heart valves. It is thus desirable to save the valve instead of performing a complete replacement.

25 Techniques have been developed to repair the shape of the dilated or elongated valve. These techniques, known as annuloplasty, is a surgical procedure of restricting the dilation of the valve annulus. Typically, a prosthesis is sutured about the base of the valve leaflets to restrict the dilation of the valve annulus.

- 3 -

5 The prosthesis restricts the movement of the valve annulus during the opening and closing of the valve. The general desire in designing a prosthesis is to provide sufficient rigidity to ensure an adequate support of the valve annulus to allow for the possible healing of the valve annulus, while allowing for as close as possible the natural movement of the valve annulus during the opening and closing of the valve. This is particularly important since such prostheses are not normally removed from the heart valve, even if the valve annulus heals to a normal geometry.

10 Over the years different types of prostheses have been developed for use in annuloplasty surgery. In general prostheses are annular or partially annular shaped members which fit about the base of the valve annulus against the leaflets. Initially the prostheses were designed as rigid frame members, to correct the dilation and reshape the valve annulus to the natural state. These annular prostheses were formed from a metallic or other rigid material, which flexes little, if at all, during the normal opening and closing of the valve. Examples of rigid annuloplasty ring prostheses are disclosed in U.S. Patent Numbers 3,656,185, issued to Carpentier on April 18, 1972; and 4,164,046, issued to Cooley on August 14, 1979. Certain artificial heart valves have also been developed with rigid frame members similar to the rigidity of the described valve prosthesis. An example of this type of heart valve are disclosed in U.S. Patent Numbers 4,204,283, issued to Bellhouse et al on May 27, 1980; and 4,306,319, issued to Kaster on December 22, 1981.

25 As stated, rigid annuloplasty ring prostheses adequately promote the healing of the valve annulus by restricting valve dilation and reshaping the valve annulus. However, this rigidity prevents the normal flexibility of the valve annulus. That is, a normal heart valve annulus continuously flexes during the cardiac cycle, and a rigid ring prosthesis

30

- 4 -

interferes with this movement. Since it is standard to retain the prosthesis, even after the valve annulus has healed, the rigidity of the prosthesis will permanently impair the functioning of the valve and the associated ventricle. Another disadvantage with a rigid ring prosthesis is the tendency for the sutures to become torn loose during the normal movement of the valve annulus.

Other workers have suggested the use of completely flexible annuloplasty ring prostheses, in order to overcome the disadvantages of rigid ring prostheses. This type of prosthesis is formed with a cloth or other very flexible material frame member. The resulting prosthesis provides little, if any resistance to the dilation of the annulus during the opening and closing of the valve. Furthermore, while these types of annuloplasty ring prosthesis offer increased flexibility, such prosthesis fail to correct that valve disfunction due to the deformation of the valve annulus.

A further disadvantage with completely flexible ring prostheses is that the circumference of the ring is not fixed. That is, as the prosthesis is being sutured to the annulus using, what are known as mattress sutures, the body of the prosthesis may become bunched at localized areas. This bunching of the prosthesis is generally referred to as multiple plications of the ring prosthesis. The resulting sutured prosthesis will not provide the desired reshaping of the valve annulus.

Examples of completely flexible ring prostheses are disclosed in U.S. Patent Number 4,290,151, issued to Massana on September 22, 1981, and are discussed in the articles of Carlos D. Duran and Jose Luis M. Ubago, "Clinical and Hemodynamic Performance of a Totally Flexible Prosthetic Ring for Atrioventricular Valve Reconstruction", 5 Annals of Thoracic Surgery, (No. 5), 458-463, (November 1976) and M. Puig Massana

- 5 -

et al, "Conservative Surgery of the Mitral Valve Annuloplasty on a New Adjustable Ring", Cardiovascular Surgery 1980, 30-37, (1981).

5 Still further types of annuloplasty ring prostheses are designed to allow for adjustment of the ring circumference, either during the surgical implantation, or as the ring prosthesis during the opening and closing of the valve. This type of adjustable prosthesis is typically designed in combination with a rigid, or at least partially rigid frame member. For example, the ring prosthesis taught in U.S. Patent Number 4,489,446, issued to Reed on December 25, 1984, allows for self adjustment of the prosthesis annulus by constructing the valve frame member in two reciprocating pieces. However, while the resulting prosthesis is adjustable in at least one direction, the individual frame members are formed from a rigid material and thus the prosthesis suffers the same disadvantages with the rigid ring prosthesis discussed above.

10 Other examples of adjustable ring prostheses are taught in U.S. Patent Numbers 4,602,911, issued to Ahmadi et al and 4,042,979, issued to Angell on August 23, 1977, provide for mechanism of adjusting the ring circumference. In Ahmadi et al the ring prosthesis frame is a coiled spring ribbon which is adjusted by a mechanical screw assembly. In Angell, a drawstring is used to adjust the circumference of a rigid frame member. Again, these ring prostheses suffer from the disadvantages of the rigid ring prosthesis discussed above. The Angell prosthesis could also possess a substantially flexible portion after suturing which could include multiple plications for the reasons discussed above for the completely flexible prosthesis.

25 30 A further disadvantage with the Angell prosthesis relates to the design of the adjusting mechanism. The Angell prosthesis includes a rigid partial annular member. The open end of this

- 6 -

5 member forms a gap which can be narrowed by tightening the drawstring. The tighter the drawstring is pulled the narrower the gap. The stress applied to the ring prosthesis during the opening and closing of the valve is primarily directed to the drawstring. Thus failure of the drawstring allows the prosthesis annulus to expand, allowing the valve to dilate.

10 It would thus be advantageous to design an annuloplasty ring prosthesis having selective flexibility more closely resembling the naturally flexibility of the valve annulus to allow for a more natural movement of the valve during the cardiac cycle, while possessing selected areas of rigidity to allow for the reshaping of the valve. This annuloplasty ring prosthesis should also be formed from a substantially stiff body element to minimize the potential of forming multiple plications about the circumference of the prosthesis during the suturing
15 procedure.

20 An annuloplasty ring prosthesis which partially achieved these results was taught in U.S. Patent Number 4,055,861, issued to Carpentier on November 1, 1977. The support taught and disclosed is described as being deformable, to an equal degree and simultaneously in all directions within and outside its resting plane, so as to form a skew curve. The preferred support is described as having the elasticity of an annular bundle of 2 to 8 turns of a cylindrical bristle of poly(ethylene terephthalate). In describing the support the
25 individual bristles may either be interwoven, or merely arranged in a side by side relationship.

30 The extremities of the individual bristles are joined together to prevent the ends from sticking out through the outer cloth sheath by welding, gluing or ligature. It is thus apparent that the overall ring prosthesis will have a single flexibility. This flexibility will be dependent upon the flexibility of the individual bristles, and/or the number of these individual bristles used to construct the support.

- 7 -

5 While the device taught and disclosed in Carpentier '861 attempts to achieve flexibility in all planes, the resulting device may have a frame member either rigid or equivalent to the discussed completely flexible ring prosthesis, in either case such a ring prosthesis would have the disadvantages associated with such types of ring prostheses.

10 Furthermore, a ring prosthesis designed in accordance with Carpentier would suffer disadvantages from the excessive wear of the bristles rubbing against each other. This wear would cause flexural fatigue of the structure during normal activity of the valve. The ring prosthesis could also suffer from fatigue due to the differential application of the stress forces applied to the separate bristles or bristle windings. That is, during the natural movement of the valve the normal stress applied to the ring prosthesis would not be equally
15 applied to each of the bristle strands or windings. This could result in fatigue of some of the bristle strands or windings severely affecting the functioning of the ring prosthesis.

20 It would thus be desirable to provide a ring prosthesis which provides for a more natural flexibility of the valve annulus without suffering the above discussed disadvantages.

DESCRIPTION OF THE DRAWINGS

25 The present invention may be better understood and the advantages will become apparent to those skilled in the art by reference to the accompanying drawings, wherein like reference numerals refer to like elements in the several figures, and wherein:

30 Figure 1 is a top view of a partially cut-away annuloplasty ring prosthesis in accordance with an embodiment of the invention;

Figure 2 is a partially cut-away side view of the ring prosthesis of Figure 1;

- 8 -

Figure 3 is a end view of the prosthesis of Figure 1;

Figure 4 is a partially cut-away top view of a annuloplasty ring prosthesis in accordance with another embodiment of the invention;

5 Figure 5 is a partially section side view of the ring prosthesis of Figure 4;

Figure 6 is a sectional view of the ring prosthesis of Figure 4 taken along line 6-6;

10 Figure 7 is a sectional view of the ring prosthesis of Figure 4 taken along line 7-7;

Figure 8 is a top view of a partially cut-away annuloplasty ring prosthesis in accordance with a still further embodiment of the invention;

15 Figure 9 is a partially sectioned side view of the ring prosthesis of Figure 8;

Figure 10 is a cross-sectional view of the prosthesis of Figure 8 along lines 10-10; and

Figure 11 is a cross-sectional view of the prosthesis of Figure 8 along lines 11-11.

20 SUMMARY OF THE INVENTION

25 The present invention overcomes the above discussed disadvantages by providing an annuloplasty ring prosthesis which includes a substantially annular shaped body element with at least a first defined length about its circumference which is substantially more rigid than the remainder of the elements circumference, with the remainder of the body element gradually increasing in flexibility in a direction away from this rigid length. This body element is formed from a
30 non-corrosive, anti-magnetic material, and is wrapped in a material through which sutures can be drawn to suture the prosthesis to the heart valve annulus.

- 9 -

5 Preferably the annuloplasty ring prosthesis of the invention is dimensioned to be longer in a longitudinal direction than in a lateral direction, with the overall flexibility of the ring being greater in the lateral direction. In another preferred embodiment, the annuloplasty ring prosthesis is formed in the horizontal orientation, with a substantially straight length along one of the longitudinal oriented sides. The substantially more rigid length lies along this straight portion of the ring prosthesis.

10 In a still further preferred embodiment, the selective flexibility of the ring prosthesis is orientated to provide that a ratio of the stiffness of the ring in the longitudinal direction over the stiffness in the lateral direction is from about 1.15 to about 2.77. The stiffness is calculated by
15 measuring the spring rates of the ring in both directions.

The body element of the ring prosthesis may be formed from individual wire strands bundled together. The discrete rigid portion may be formed by crimping together a length of the wire bundle. In one preferred embodiment the body element is formed from a multi-lumen tubular enclosure and individual
20 non-corrosive, anti-magnetic wire strands positioned individually in each of said tubular enclosure lumens.

In a still further embodiment the body element is formed as a multi-layered structure of one or more individual
25 substantially flat bands of a non-corrosive, anti-magnetic material. The discrete rigid portion of this embodiment can be formed by crimping or spot welding a length of the layers together. This embodiment may be further modified by positioning plastic or other type of elastomer material between
30 the bands, to prevent wear.

The ring prosthesis of the invention is thus formed with a selective flexibility about its circumference while providing a defined structure. That is, the circumference of the

- 10 -

5 prosthesis is defined by the selectively flexible body element which gradually increases in flexibility away from at least one length which is substantially more rigid than the remainder of the body element. The body element allows the surgeon to correct the dilation and reshape the valve, without sacrificing the desired flexibility needed to allow the valve to more naturally open and close. The selectively flexible body element also ensures that the prosthesis will retain its shape as it is being sutured to the valve annulus to reduce the potential of forming multiple plications.

10

DESCRIPTION OF THE PREFERRED EMBODIMENTS

The present invention is directed to annuloplasty ring prostheses which are sutured to the annulus of a dilated and/or deformed heart valve. The dilation and/or deformation of heart valves may be the result of a disease, natural defect or physical damage to the valve annulus. This dilated and/or deformed heart valve will not completely close, allowing for regurgitation of blood with a closed valve.

15

20 The annuloplasty ring prosthesis of the invention is surgically sutured to the valve annulus. This prosthesis restricts the circumference of the dilated valve to a more natural dimension, and also provides sufficient rigidity to reshape the valve. The prosthesis of the invention thus restrains dilation of the valve and allows the surgeon to reshape the valve. The prosthesis of the invention accomplishes these tasks by being designed with selective flexibility about its circumference. The body element is formed about its circumference with at least one defined length which is rigid, with the body element gradually increasing in flexibility in a direction away from this rigid length. By properly suturing the rigid and flexible portions of the prosthesis about the valve annulus, the valve functions in a more normal manner than possible with presently available annuloplasty ring prosthesis.

25

30

- 11 -

Referring now to Figures 1 and 2, a annuloplasty ring prosthesis in accordance with an embodiment of the invention is seen generally at 10. Ring prosthesis 10 is formed from a selectively flexible body element, which will be described in greater detail below as being formed from a plurality of individual wire strands 14. This body element has a generally oblong or oval shape. The precise dimensions of ring prosthesis 10, as defined by the body element, is dependent upon whether the ring prosthesis is to implanted about a tricuspid or mitral valve. In any event, the dimensions of ring prosthesis 10 may be designed for any type of valve annulus. Normally, various sized and dimensioned ring prosthesis will be available.

As stated, ring prosthesis 10 is constructed from a plurality of individual wire strands, one of which is seen generally at 14. These strands 14 are manipulated to provide the prosthesis with any desired shape. The respective ends, not shown, of each of the wire strands 14 are placed in a generally abutting relationship. The wire ends are then held in position by any suitable manner, e.g. crimping.

The illustrated ring prosthesis 10 is designed for suturing about a mitral heart valve. Prosthesis 10 has the shape generally resembling the letter "D". That is, the illustrated ring prosthesis 10 is designed with a generally oblong shape, with one of the longitudinally oriented sides, seen as side 12, being substantially straight. For the purpose of this discussion the description of the substantially straight side 12 shall mean being substantially straight as seen in a direction illustrated in Figure 1. Generally, this substantially straight side 12 comprises from about 1/5 to about 1/3 of the total circumference of the ring prosthesis 10.

In accordance with the invention, selectively flexible body element of the ring prosthesis 10 is designed with at least one

- 12 -

5 defined length or portion about its circumference which is substantially more rigid or stiff than the remainder of the ring prosthesis, this rigid length is generally indicated at 16. The flexibility of the ring gradually increases in a direction away from this rigid length 16 to provide the overall prosthesis with a selective flexibility. Generally the rigid length comprises from about 1/8 to 1/2 of the ring prosthesis circumference. When suturing the ring prosthesis to the valve annulus, this rigid length is positioned adjacent to the anterior cusp of the mitral valve, or the median cusp of the tricuspid valve.

10 Preferably, the rigid length 16 is defined along the substantially straight side 12. Generally, the rigid length 16 comprises from about 5/8 to about 3/2 of the straight side 12. Thus this straight side 12 will be sutured adjacent to the anterior cusp of a mitral heart valve, or the median cusp of the tricuspid heart valve.

15 As seen, a malleable tube 18 is fixed about the bundle of wire strands 14 at a location around these abutting ends. This malleable tube 18 is pinched or crimped down upon the bundle of wire strands 14. The malleable tube 18 functions not only to hold the ends of the wire strands 14 in place, but in this embodiment also defines the rigid length 16 of the ring prosthesis 10. The rigid length 16 may comprise less or more than the entire length of the malleable tube 18. If the rigid length 16 comprises more than the length of the tube 18, then the wire strands 14 are pinched, crimped or welded together for this greater length.

25 It should be noted that the use of the malleable tube 18 simplifies the forming of the rigid length 16. The abutting ends of the wire strands 14 may be fixed together by an adhesive or by welding, with the rigid length 16 formed by selectively welding or in some other manner fixing the individual wire strands 14 together.

- 13 -

Both the wire strands 14, and the malleable tube 18 are formed from a biocompatible material. This material should also be anti-magnetic. One particular suitable material is a cobalt-nickel alloy manufactured under the trademark ELGILOY by the Elgiloy Company, a division of American Gage & Machine Company, 1565 Fleetwood, Elgin, Illinois. This material is also described in U.S. Patent Number 2,524,661.

Generally, ring prosthesis 10 will vary in size from 24 millimeters (mm) to 38 mm. The number of wire strands 14 used to construct the ring prosthesis 10 is dependent upon the desired flexibility, which is dependent upon the diameter of the wire strands 14, and the material from which the strands 14 are made. Generally, the individual wire strands 14 will have an outer diameter of from about 0.008 inch to about 0.022 inch. The number of wire strands 14 used to construct the ring prosthesis 10 will vary from about one to about twelve.

As stated the ring prosthesis of the invention possesses a selective flexibility about its circumference. This selective flexibility is dependent upon many variables, e.g. the composition, outer diameter and size of the individual wire strands 14, and the size of the rigid length 16. Generally, by altering these variables the flexibility of the ring prosthesis is selected to position rigid lengths at locations which provide the needed support to the valve annulus and allow the surgeon to reshape a deformed valve.

In accordance with a preferred embodiment of the invention these variable are manipulated to provide that the ring prosthesis will be stiffer in the longitudinal direction. The longitudinal direction for the ring prosthesis is the longest length, seen generally along line A-A, in Figure 1. The prosthesis 10 also includes a lateral direction, which is generally the width of the ring prosthesis 10 seen along line B-B. In a further preferred embodiment, the ring prosthesis 10

- 14 -

is designed to provide a ratio of the stiffness of the prosthesis 10 in the longitudinal direction over the stiffness in the lateral direction from about 1.15 to about 2.77.

5 For the purpose of describing the invention, the stiffness of the ring prosthesis 10 in the longitudinal and lateral directions is calculated by determining the spring rate of the ring prosthesis 10 for these directions. The spring rate may be calculated by the concept known as Finite Element Analysis. The Finite Element Analysis allows for calculating the spring rate in the longitudinal and lateral directions using the diameter and length of the individual and bundle of wire strands 14, and the rigid length 16. The type of material from which the wire strands 14 and the malleable tube 18 are made is also used in this calculation. For a more detailed discussion of this concept see, "Concept and Applications of Finite Element Analysis", Second Edition, Robert D. Cook, Department of Engineering Mechanics, University of Wisconsin-Madison, John Wiley & Sons, 1981. The shorter the length of the wire strands 14, and thus the smaller the circumference of the prosthesis, the greater the stiffness. For example, a ring prosthesis of 26 millimeters would have a ring spring rate of 160 grams per millimeter, while a ring prosthesis of 38 millimeters would have a ring spring rate of 240 grams per millimeter.

25 The ring prosthesis 10 further includes an outer sheath 20. This outer sheath 20 fits snugly wrapped about the wire strands 14. This sheath 20 may be any suitable type of biocompatible material, for example a knit fabric such as Dacron polymer (polyethylene terephthalate) fabric.

30 Preferably, the wire strands are embedded in an elastomeric material, or coated with an elastomeric material or polytetrafluoroethylene to reduce friction between the individual wire strands 14, and thus minimize wear.

In a preferred embodiment, the substantially straight side

- 15 -

12 of the ring prosthesis bows outward from a plane in which lies the remainder of the ring prosthesis 10. This preferred embodiment is seen better in Figure 3. Generally, the outward curvature of the straight side 12 provides an angle between a line drawn along the side 12, seen generally at 13, and that plane in which lies the remainder of the ring prosthesis 10, seen at 15, of from about 0° to about 15°. This curvature is preferably designed to conform to the geometry of that portion of the mitral valve annulus adjacent to the aortic valve root, and provides for a more compatible fit of the annuloplasty ring prosthesis 10 about the mitral valve.

In another still further embodiment of the invention the side 12 is not substantially straight, but is formed with a slight outward curvature as seen in phantom at side 12'.

While the ring prosthesis described and illustrated in Figure 1 through 3 provides an improvement over presently available ring prosthesis, other more preferable embodiments will now be described. These embodiments provide for a greater degree of control in the flexing of the prosthesis during the normal opening and closing of the associated heart valve, also ensure that the load applied to the prosthesis is evenly applied to the prosthesis structure. The individual wire strands 14 of the previously described embodiment, as illustrated in Figure 1-3, are free to move with respect to each other. This movement allows the wire strands 14 to rub against each other which causes unwanted wear. Also, the load applied to the ring prosthesis 10, as the valve opens and closes, unevenly varies between the individual strands 14. This may result in the concentration of the applied load onto one or more of the wire strands 14, which may also result in stress fatigue of those strands 14.

One preferred prosthesis is illustrated in Figures 3 through 5 at 22. In this embodiment the selectively flexible body

- 16 -

5 element comprises a multi-lumen elastomeric tube 28, with individual wire strands 24 fitted in respective ones of the individual lumens 26. The positioning of the wire strands 24 in the associated lumens 26 restricts the movement of the strands 24 with respect to each other. This ensures that the load will be borne evenly by the individual strands 24. Furthermore, the individual wire strands 24 can not rub against each other. This reduces the wearing of the strands 24.

10 The number of individual wire strands 24 used to construct this embodiment is dependent upon flexibility desired for the prosthesis 22. Generally, from about 2 to about 9 individual strands 24 are used to construct the prosthesis 22, with the individual strands 24 having similar dimensions and prepared from a similar material to that used for the wire strands 14 of the previously described embodiment.

15 The prosthesis 22 is also designed to have selective flexibility. This selective flexibility is provided by forming about the circumference of the prosthesis 22 one or more defined lengths, one or which is seen generally at 30, which are substantially more rigid than the remainder of the prosthesis 22 circumference. The prosthesis 22 is designed so that the flexibility of the prosthesis increases in a direction away from these lengths 30. The rigid lengths 30 of the prosthesis 22 may be formed by any suitable method, such as those methods described above for the rigid length 16 of the previous embodiment.

20 In the illustrated embodiment, the multi-lumen elastomeric tubing 28, as seen in Figure 4, does not run the entire circumference of the ring prosthesis 22. A portion of this elastomeric tubing 28 is removed, or the length of such tubing 28 is provided to expose a portion of the wire strands 24, preferably at a location adjacent to the position at which the wire strands 24 abut. The abutting ends of the wire strands 24

25

30

- 17 -

are held together by any suitable manner. A malleable tube 32 is secured about the wire strands 24 at this exposed location in a manner as described above. The crimping, pinching or welding of the tube 32 defines the rigid length 30. As with the previous embodiment, the size of this rigid length 30 is determined by the extent to which the tube 32, and adjacent portions of the wire strands 24 are crimped, pinched or welded. The arrangement of the individual wire strands 24 in the associated lumens 26 is seen better in Figure 6, while the placement of the wire strands 24 in the malleable tube 32 is best seen in Figure 7.

A preferred embodiment, as illustrated, provides that the ring prosthesis 22 is also designed with a substantially straight side, seen generally at 34. This straight side 34 is similar to the straight side 16 as described above for the previous embodiment, and will not be described in any greater detail herein. Furthermore, this straight side 34 may be curved outward in a manner similar to side 16 or the previously described embodiment, with this side 34 also preferably being formed outwardly curving as seen at 34'.

Referring now to Figures 8 through 11 a more preferred ring prosthesis of the invention, seen generally at 36, will be described. In this embodiment the selectively flexible body element of the annuloplasty ring prosthesis 36 is defined by a spiral wire band structure. The individual spiral layers are formed by selectively wrapping a single band to form the spiral structure, or by layering individual bands upon one another, with one of such bands being seen at 38. Preferably a plurality of individual bands 38 are layered upon one another to form the multi-layered structure. The ring prosthesis 36 may include from one to about 6 of these spiral layers. These bands 38 are formed from a biocompatible, anti-magnetic material.

- 18 -

5 This spiral structure is held within a cloth sheath 40 in a manner similar to the previously described embodiments. Preferably, in order to reduce friction between adjacently positioned bands, an elastomeric material is placed between the individual spiral layers, e.g. the individual bands 38, with such material seen at 37 in Figure 10. The elastomeric material 37 also surrounds the outside of the bands 38. As seen in Figures 10 and 11, the cloth sheath 40 bulges outwards along one side, with this bulge, as seen at 41, filled with the elastomeric material 37. This bulge 41 is preferentially positioned along the outside of the prosthesis 36. Sutures will be passed through the bulge 41.

10 The selectively flexible body element, as defined by the spiral band 38 structure is also formed about its circumference with one or more defined lengths, one of which is seen generally at 42, which are substantially more rigid than the remainder of the body element circumference. This aspect of prosthesis 36 is similar to the previously discussed embodiments, and will not be described great detail herein. The rigid length 42 is typically formed by crimping or spot welding the individual bands 38 together for the desired length.

20 As seen in Figure 11, none of the elastomeric material 37 is positioned between the bands 38 along the rigid length 42. This occurs because the individual bands 38 are overlapped at this location. That is the respective ends, not shown, of each band 38 are overlapped. Preferably the respective ends are tapered. This better distributes the stresses exerted upon the prosthesis 36 than if the respective ends were merely squared off.

25 The desired size of this rigid length 42 is also similar to that of the above described embodiments. Generally, this rigid length 42 is from about 1/8 to about 1/2 of the ring prosthesis 36 circumference. The flexibility of the body element also varies in a direction away from this rigid length 42 in a

- 19 -

manner similar to that described for the previous embodiments. That is, preferably a ratio of the stiffness of the body element, as defined by the spiraled bands 38 in the longitudinal direction over the stiffness in the lateral direction is from about 1.15 to about 2.77.

5 The use of a spiralled structure prepared by the overlaying of one or more bands 38 ensures that the force applied against the prosthesis 36 is better distributed over the various layers of the bands 38. That is, the application of force against the
10 prosthesis 36 is better distributed to the various band 38, than is distributed to the individual wire strands 24, in the embodiment of Figures 4-7, or strands 14, in the embodiment of Figures 1-3. The result is a more even application of load to the entire ring prosthesis 36 in both the longitudinal and
15 lateral directions.

The precise number of spiral windings forming the body element is dependent upon the materials used for the bands 38, as well as the thickness of the individual band 38 layers forming the multi-layered structure. Generally, from about 1
20 to about 6 spiral layers or individual bands 38 are used, while the thickness of each layer or band 38 may be from about 0.002 to about 0.008 of an inch.

While the preferred embodiments have been described, various modifications and substitutions may be made thereto without
25 departing from the scope of the invention. Accordingly, it is to be understood that the invention has been described by way of illustration and not limitation.

30

- 20 -

What is claimed is:

1. An annuloplasty ring prosthesis for suturing about a heart valve annulus comprising:

5 a selectively flexible body member having a substantially annular shape proportional to fit about the circumference of said heart valve annulus, which is formed at one or more positions about its circumference with defined lengths which are substantially more rigid than the remainder of said body circumference, said member gradually increasing in flexibility
10 about its circumference in a direction away from each of said defined rigid lengths; and

means for encapsulating said body member, which is formed to permit suturing of said ring prosthesis about said heart valve.

15 2. The annuloplasty ring prosthesis of claim 1 wherein said prosthesis comprises one of said defined rigid length, and wherein said defined rigid length comprises from about 1/8 to about 1/2 of the circumference of said member.

20 3. The annuloplasty ring prosthesis of claim 1 wherein said body member is dimensioned to be longer in a longitudinal direction than in a lateral direction, with said body member being stiffer in said longitudinal direction.

25 4. The annuloplasty ring prosthesis of claim 3 wherein said body member is formed in said longitudinal direction with one substantially straight side, and wherein said prosthesis comprises one of said defined rigid length, with said defined
30 rigid length comprising at least a part of said straight side.

5. The annuloplasty ring prosthesis of claim 4 wherein said straight side comprises from about 1/5 to about 1/3 of the circumference of said member.

- 21 -

6. The annuloplasty ring prosthesis of claim 5 wherein said rigid length comprises from about $5/8$ to about the entire length $3/2$ of said straight side.

5 7. The annuloplasty ring prosthesis of claim 3 wherein a ratio of said stiffness, as measured by the spring rate of said longitudinal direction over said stiffness, as measured by the spring rate of said lateral direction is from about 1.15 to about 2.77.

10 8. The annuloplasty ring prosthesis of claim 4 wherein a ratio of said stiffness, as measured by the spring rate of said longitudinal direction over said stiffness, as measured by the spring rate of said lateral direction is from about 1.15 to
15 about 2.77.

20 9. The annuloplasty ring prosthesis of claim 6 wherein a ratio of said stiffness, as measured by the spring rate of said longitudinal direction over said stiffness, as measured by the spring rate of said lateral direction is from about 1.15 to about 2.77.

25 10. The annuloplasty ring prosthesis of claim 4 wherein said body member is formed from a plurality of individual wire strands arranged in a bundle and fixed together at one location around said circumference to define said straight side, with said wire strands along at least part of said straight side defined being affixed together wire strands to define said rigid length.

30 11. The annuloplasty ring prosthesis of claim 10 wherein each of said individual wire strands are coated with polytetrafluoroethylene or an elastomeric material.

- 22 -

12. The annuloplasty ring prosthesis of claim 10 wherein said bundle of wire strands are arranged in an elastomeric material tube, with the strands embedded in an elastomeric material within said tube.

5

13. An annuloplasty ring prosthesis for suturing about a heart valve annulus comprising:

10

a selectively flexible body member having a substantially annular shape proportional to fit about the circumference of said heart valve annulus which is formed from a multi-lumen tubular enclosure, with individual wire strands positioned individually in each of said tubular enclosure lumens, said body member being formed at one or more positions about its circumference with defined lengths which are substantially more rigid than the remainder of said body circumference, said member gradually increasing in flexibility about its circumference in a direction away from each of said defined rigid lengths; and

15

20

means associated with said body member for enclosing said tubular structure, which is formed to permit suturing of said ring prosthesis about said heart valve.

25

14. The annuloplasty ring prosthesis of claim 13 wherein said prosthesis member includes only one of said defined rigid lengths, which comprises from about 1/8 to about 1/2 of the circumference of said member.

30

15. The annuloplasty ring prosthesis of claim 13 wherein said body member is dimensioned to be longer in a longitudinal direction than in a lateral direction, with said member being stiffer in said longitudinal direction.

16. The annuloplasty ring prosthesis of claim 15 wherein a portion of one side of said body member along said longitudinal

- 23 -

direction is substantially straight, and wherein said prosthesis member includes only one of said defined rigid lengths, with said defined rigid length comprising at least a part of said straight side.

5

17. The annuloplasty ring prosthesis of claim 16 wherein said straight side comprises from about 1/5 to about 1/3 of the circumference of said member.

10

18. The annuloplasty ring prosthesis of claim 17 wherein said defined rigid length comprises from about 5/8 to about 3/2 of said straight side.

15

19. The annuloplasty ring prosthesis of claim 15 wherein a ratio of said stiffness, as measured by the spring rate of said prosthesis in the longitudinal direction over said stiffness, as measured by the spring rate of said prosthesis in the lateral direction is from about 1.15 to about 2.77.

20

20. The annuloplasty ring prosthesis of claim 16 wherein a ratio of said stiffness, as measured by the spring rate of said prosthesis in the longitudinal direction over said stiffness, as measured by the spring rate of said prosthesis in the lateral direction is from about 1.15 to about 2.77.

25

21. The annuloplasty ring prosthesis of claim 18 wherein a ratio of said stiffness, as measured by the spring rate of said prosthesis in the longitudinal direction over said stiffness, as measured by the spring rate of said prosthesis in the lateral direction is from about 1.15 to about 2.77.

30

22. The annuloplasty ring prosthesis of claim 21 wherein said defined rigid length is formed by positioning a malleable

- 24 -

material around a portion of said body member which is to define said rigid length, and pinching said material down upon said body.

5 23. The annuloplasty ring prosthesis of claim 22 wherein said malleable material is pinched down upon said body member after a portion of said multi-lumen tube is removed to expose said wire strands.

10 24. An annuloplasty ring prosthesis for suturing about a heart valve annulus comprising:

15 a selectively flexible body member having a substantially annular shape proportional to fit about the circumference of said heart valve annulus which is formed from one or more individual substantially flat bands wrapped upon one another to form a spiral shaped structure or a multi-layered structure, said body member being formed at one or more positions about its circumference with defined lengths which are substantially more rigid than the remainder of said body circumference, said member gradually increasing in flexibility about its circumference in a direction away from each of said defined rigid lengths; and

20 means associated with said body member for enclosing said multi-layered structure which is formed to permit suturing of said ring prosthesis about said heart valve.

25

30 25. The annuloplasty ring prosthesis of claim 24 wherein said prosthesis member includes only one of said defined rigid lengths, which comprises from about 1/8 to about 1/2 of the circumference of said member.

26. The annuloplasty ring prosthesis of claim 24 wherein said body member is dimensioned to be longer in a longitudinal direction than in a lateral direction, with said member being stiffer in said longitudinal direction.

- 25 -

5 27. The annuloplasty ring prosthesis of claim 26 wherein a portion of one side of said body member along said longitudinal direction is substantially straight, and wherein said prosthesis member includes only one of said defined rigid lengths, which comprises at least a part of said straight side.

10 28 . The annuloplasty ring prosthesis of claim 27 wherein said straight side comprises from about 1/5 to about 1/3 of the circumference of said member.

15 29 . The annuloplasty ring prosthesis of claim 28 wherein said defined rigid length comprises from about 5/8 to about 3/2 of said straight side.

20 30. The annuloplasty ring prosthesis of claim 26 wherein a ratio of said stiffness, as measured by the spring rate of said prosthesis in the longitudinal direction over said stiffness, as measured by the spring rate of said prosthesis in the lateral direction is from about 1.15 to about 2.77.

25 31. The annuloplasty ring prosthesis of claim 27 wherein a ratio of said stiffness, as measured by the spring rate of said prosthesis in the longitudinal direction over said stiffness, as measured by the spring rate of said prosthesis in the lateral direction is from about 1.15 to about 2.77.

30 32. The annuloplasty ring prosthesis of claim 29 wherein a ratio of said stiffness, as measured by the spring rate of said prosthesis in the longitudinal direction over said stiffness, as measured by the spring rate of said prosthesis in the lateral direction is from about 1.15 to about 2.77.

33. The annuloplasty ring prosthesis of claim 32 wherein said spiral shaped structure is formed from a single band.

- 26 -

34. The annuloplasty ring prosthesis of claim 32 wherein said spiral shaped structure is formed from a plurality of individual bands.

5 35. The annuloplasty ring prosthesis of claim 32 wherein said defined rigid length is formed by crimping or welding together said individual band along a length of said spiral shaped structure.

10 36. The annuloplasty ring prosthesis of claim 34 wherein said defined rigid length is formed by crimping or welding together said individual bands along a length of said spiral shaped structure.




15 37. The annuloplasty ring prosthesis of claims 20, 21, 31 or 32 wherein said body member is formed with a shape proportional to the circumference of a heart aortic valve, and wherein said straight side curves outward from a plane in which the remainder of said prosthesis lies.



20 38. The annuloplasty ring prosthesis of claim 10, 23, 33, 34, 35, or 36 wherein said suturing means is a tubular cloth positioned about said body member.

25 39. The annuloplasty ring prosthesis of claim 38 wherein said substantially straight side bows outward.

30 40. The annuloplasty ring prosthesis of claims 37 wherein said suturing means is a tubular cloth positioned about said body member.

1/3





3/3




FIG. 8




FIG. 9





FIG. 11

INTERNATIONAL SEARCH REPORT

International Application No PCT/US 90/00641

I. CLASSIFICATION OF SUBJECT MATTER (if several classification symbols apply, indicate all) ⁶ According to International Patent Classification (IPC) or to both National Classification and IPC IPC5: A 61 F 2/24		
II. FIELDS SEARCHED		
Minimum Documentation Searched ⁷		
Classification System	Classification Symbols	
IPC5	A 61 F	
Documentation Searched other than Minimum Documentation to the Extent that such Documents are Included in Fields Searched ⁸		
III. DOCUMENTS CONSIDERED TO BE RELEVANT⁹		
Category *	Citation of Document, ¹¹ with indication, where appropriate, of the relevant passages ¹²	Relevant to Claim No. ¹³
X	EP, A1, 0257874 (BAXTER TRAVENOL LABORATORIES, INC.) 2 March 1988, see the whole document --- -----	1-9,24- 33,37, 38,40
* Special categories of cited documents:¹⁰ "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance, the claimed invention cannot be considered novel or cannot be considered to involve an inventive step "Y" document of particular relevance, the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. "&" document member of the same patent family		
IV. CERTIFICATION		
Date of the Actual Completion of the International Search		Date of Mailing of this International Search Report
5th June 1990		15 JUN 1990
International Searching Authority		Signature of Authorizing Officer
EUROPEAN PATENT OFFICE		 MISS T. TAZELAAR

ANNEX TO THE INTERNATIONAL SEARCH REPORT
ON INTERNATIONAL PATENT APPLICATION NO.PCT/US 90/00641

SA 34915

This annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report.
The members are as contained in the European Patent Office EDP file on 07/05/90
The European Patent office is in no way liable for these particulars which are merely given for the purpose of information.

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A1- 0257874	02/03/88	JP-A- 63109856	14/05/88

For more details about this annex : see Official Journal of the European patent Office, No. 12/82