

**(12) STANDARD PATENT  
(19) AUSTRALIAN PATENT OFFICE**

**(11) Application No. AU 2006238988 B2**

(54) Title  
**Acrylic blends**

(51) International Patent Classification(s)  
**C08L 33/04** (2006.01)

(21) Application No: **2006238988** (22) Date of Filing: **2006.04.18**

(87) WIPO No: **WO06/114576**

(30) Priority Data

(31) Number **0508255.7** (32) Date **2005.04.25** (33) Country **GB**

(43) Publication Date: **2006.11.02**

(44) Accepted Journal Date: **2012.07.19**

(71) Applicant(s)  
**Lucite International UK Ltd**

(72) Inventor(s)  
**Fraser, Ian;Robinson, Ian**

(74) Agent / Attorney  
**Griffith Hack, Level 29, Northpoint 100 Miller Street, North Sydney, NSW, 2060**

(56) Related Art  
**AU 66877/00 B2 (FM: DE 19927769 A1)**  
**WO 1986/05503 A**  
**EP 1013713 A**

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization  
International Bureau



PCT

(43) International Publication Date  
2 November 2006 (02.11.2006)

(10) International Publication Number  
WO 2006/114576 A1

(51) International Patent Classification:  
*C08L 33/04* (2006.01)

(74) Agents: WALSH, David, Patrick et al.; Appleyard Lees,  
15 Clare Road, Halifax, West Yorkshire HX1 2HY (GB).

(21) International Application Number:  
PCT/GB2006/001393

(81) Designated States (unless otherwise indicated, for every  
kind of national protection available): AE, AG, AL, AM,  
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,  
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,  
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,  
KG, KM, KN, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV,  
LY, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI,  
NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG,  
SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US,  
UZ, VC, VN, YU, ZA, ZM, ZW.

(22) International Filing Date: 18 April 2006 (18.04.2006)

(84) Designated States (unless otherwise indicated, for every  
kind of regional protection available): ARIPO (BW, GH,  
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,  
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),  
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,  
FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT,  
RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA,  
GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(25) Filing Language: English

English

(26) Publication Language: English

English

(30) Priority Data:  
0508255.7 25 April 2005 (25.04.2005) GB

(71) Applicant (for all designated States except US): LUCITE  
INTERNATIONAL UK LTD [GB/GB]; Queens Gate,  
15-17 Queens Terrace, Southampton, Hampshire SO14  
3BP (GB).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



WO 2006/114576 A1

(54) Title: ACRYLIC BLENDS

(57) **Abstract:** An acrylic polymeric composition comprising a melt blend of a thermoplastic high molecular weight acrylic material (HMWA) and a thermoplastic low molecular weight acrylic material (LMWA) is described. At least 70% w/w of the HMWA and the LMWA comprises an alkyl (alk) acrylate (co) polymer. The HMWA has a weight average molecular weight (Mw) of between 40k Daltons and 1000k Daltons and the LMWA has a weight average molecular weight (Mw) of between the entanglement molecular weight (Me) (expressed in k Daltons) and 250k Daltons. A method of producing an acrylic polymeric composition and the use of an acrylic polymeric composition are described together with thick section moulded products .

**ACRYLIC BLENDS**

The present invention relates to acrylic blends, more specifically blends of low molecular weight acrylic polymers with high molecular weight acrylic polymers.

Improving the processability of acrylic polymers for various applications is an important area of research with many commercial benefits. Processability of polymers can generally be improved by increasing the melt flow index (MFI) and in the acrylics industry this has been effected by adding various copolymers such as alkyl acrylates or methacrylic acid to a high molecular weight PMMA polymer. Although increases of MFI can be achieved in this manner they also result in significant reduction in the glass transition temperature of the PMMA polymer with the consequent restriction in its range of applications such as those requiring moderate to high temperature resistance.

EP 0588147 describes a two stage blending process mainly for use with polyolefins. The use of the two stage blending process is to remove fish eye problems in the final product. Specific molecular weights are not provided.

Hwang and Cho, Department of Chemical Engineering, Pohang University, in an internet disclosure entitled "Effect of chain entanglement on the bulk strength of glass polymer" report determination of critical chain entanglement density using fracture toughness estimates. They concluded that use of low MW PMMA adversely affected fracture energy of the polymer.

WO 086/05503 describes mixtures of high and low molecular weight alkyl acrylates which are produced from the same monomer. Alkyl (alk)acrylates are mentioned only as co-monomer components of a high or low molecular weight copolymer. The document relates to the use of these mixtures for pressure sensitive adhesives.

JP 56-008476 describes a pressure sensitive adhesive composition made by mixing (A) low mol. wt. acrylic such as PMMA and (B) an acrylic polymer. The composition is claimed to provide improved adhesion to roughened surfaces.

JP 07-174133 discloses low and high mol. wt. blends including alkyl(alk)acrylates as the high molecular weight component. The high mol. wt. content is less than the low mol. wt. content. The utility of the blends is in relation to low hardness rolls. The low molecular weight additive can be selected from:

Softeners  
Plasticizers  
Tackifiers  
Oligomers  
Or Lubricants

JP 07-174189 discloses a similar system to that in JP 07-174133 but applies it to improving vibration damping performance.

JP 54-23539 describes a toner with a colouring agent, an acrylic copolymer and optionally vinyl polymer. The copolymer preferably comprises (a) methacrylates such as methyl methacrylate, (b) vinyl monomer and (c) glycidyl methacrylate (2,3 epoxypropyl methacrylate).

EP 0144140 discloses a blend for mixing with bentonite as a drilling mud. The blend comprises a low molecular wt. water soluble non-ionic or anionic polymer and a high molecular wt. anionic polymer. The low mol. wt. component is below about 50K (page 2 line 31) and the high mol. wt. component is above about 500K. Acrylic acid polymers are given as examples of the low mol. wt. components (page 2 line 18) having mol. wt. up to 40K. Low alkyl (C<sub>1-4</sub>) acrylates are given as general examples and acrylic acid and methacrylic acid are given specifically. The presence of acid groups may assist solubility. Alkyl(alk)acrylate blends are not disclosed.

EP 1189987 B1 mentions that a particular set of properties including desirable Vicat softening can be achieved using cross-linked poly(meth)acrylate based impact modified high molecular weight acrylic polymers blended with lower molecular weight acrylic polymers.

US 6,388,017 relates to a process of contacting a narrow mol. wt. distribution ethylene base polymer with a high mol. wt. such that there is 0.1% → 10% by wt. of molecules with mol. wt. > 1 million. Blending is mentioned as a possible route although copolymerisation is preferred.

US 5,306,775, US 5,319,029 and US 5,380,803 disclose high and low mol. wt. polyolefine blends to improve crack resistance, clarity, etc.

FR 2749591 discloses a cleaning composition for plastic processing equipment. There are two PMMA components:

- (a) 95% - 25% w/w of a high mol. wt. non-thermoplastic pmma component; and
- (b) 5-75% w/w of a thermoplastic PMMA.

In the description, the term high mol. wt. is defined as "an average mol. wt. of more than 500[K], preferably more than 1,000[K] daltons ....".

Similarly, the description defines the term "thermoplastic [PMMA] ... to mean a [PMMA] having an average mol. wt. of 50[K] to 200[K] ..." The non-thermoplastic PMMA is likely to remain as a solid during the cleaning process.

2006238988 04 Jul 2012

4a

The present invention provides the following items 1 to 37:

1. An acrylic polymeric composition having less than 0.5% w/w of an impact strength modifier the said composition comprising a melt blend of a thermoplastic high molecular weight acrylic material (HMWA) and a thermoplastic low molecular weight acrylic material (LMWA), at least 70% w/w, based on the total weight of the HMWA, of the said HMWA comprising an alkyl (alk)acrylate (co)polymer, the said (co)polymer comprising at least 80% w/w of a first polymer unit derived from C<sub>1</sub>-C<sub>12</sub> alkyl (C<sub>1</sub>-C<sub>8</sub> alk)acrylate monomer units and optionally, up to 20% w/w, based on the said alkyl (alk)acrylate (co)polymer of a first copolymer unit derived from C<sub>1</sub>-C<sub>12</sub> alkyl(C<sub>0</sub>-C<sub>8</sub> alk)acrylate and/or (C<sub>0</sub>-C<sub>8</sub> alk)acrylic acid monomer units, the said HMWA having a weight average molecular weight of between 40k Daltons and 1000k Daltons, at least 70% w/w, based on the total weight of the LMWA, of the said LMWA comprising an alkyl(alk)acrylate (co)polymer, the said (co)polymer comprising at least 80% w/w of a second polymer unit derived from C<sub>1</sub>-C<sub>12</sub> alkyl (C<sub>1</sub>-C<sub>8</sub> alk)acrylate monomer units and optionally, up to 20% w/w, based on the said alkyl (alk)acrylate (co)polymer of a second copolymer unit derived from C<sub>1</sub>-C<sub>12</sub> alkyl(C<sub>0</sub>-C<sub>8</sub> alk)acrylate and/or (C<sub>0</sub>-C<sub>8</sub> alk)acrylic acid monomer units, the said LMWA having a weight average molecular weight of between the entanglement molecular weight (M<sub>e</sub>) (expressed in k Daltons) and 250k Daltons, with the proviso that the HMWA has a higher Mw than the LMWA, wherein the first polymer unit of the HMWA and the second polymer unit of the LMWA are the same.

2. An acrylic composition comprising
  - a. an acrylic polymeric composition according to item 1; and
  - b. a suitable solvent.
5. The use of an acrylic polymeric composition in accordance with any one preceding item to provide a higher MFI melt blended composition or moulded polymer product (as compared with the HMWA not blended with the LMWA).
10. The composition or use of any one of items 1-3, wherein the first copolymer unit and the second copolymer unit are the same.
15. The composition or use of any one of items 1-4, wherein the weight ratio of the first polymer unit:first copolymer unit is within  $\pm$  30% of the ratio of second polymer unit:second copolymer unit.
20. The composition or use of any one of items 1-5, wherein the weight ratio of HMWA:LMWA in the composition is greater than 1:1.
25. 7. The composition or use of any one of items 1-6, wherein the acrylic polymeric composition comprises, based on the weight of the acrylic polymeric composition, up to 55% w/w of LMWA and at least 40% w/w of HMWA.
30. 8. The composition or use of any one of items 1-7, wherein the melt blends are homogeneous melt blends.
9. The composition or use of any one of items 1 to 8, wherein the composition optionally includes a second or further HMWA component (defined in the same manner as the first HMWA) which has a weight average molecular

weight greater than the LMWA but which is less or greater than the other HMWA component(s).

10. The composition or use of item 9, wherein the second or  
5 further component is present at a level, based on the  
acrylic polymeric composition, of at least 5% w/w.

11. The composition or use of either item 9 or 10, wherein  
10 the second or further HMWA has a lower weight average  
molecular weight (Mw) than the first HMWA component.

12. The composition or use of any one of items 9-11, wherein  
15 the first polymer unit of the HMWA and the third or  
further polymer unit of the second or further HMWA are  
the same.

13. The composition or use of any one of items 9-12, wherein  
20 the first copolymer unit and third copolymer unit are  
the same.

14. The composition or use of any one of items 9 to 13,  
25 wherein the ratio of the first polymer unit:first  
copolymer unit is within  $\pm$  30% of the ratio of the third  
polymer unit:third copolymer unit.

25. The composition or use of any one of items 1 to 14,  
30 wherein the HMWA, including the second or further HMWA  
component when present, is present, based on the overall  
weight of the acrylic polymeric composition, at a level  
of up to 99% w/w.

35. The composition or use of any one of items 1 to 15,  
wherein the LMWA is present, based on the overall weight  
of the acrylic polymeric composition, at a level of at  
least 1% w/w.

4d

17. The composition or use of any one of items 1 to 16, wherein the LMWA has a weight average molecular weight (Mw) in excess of 11k Daltons.

5 18. The acrylic composition of any one of items 2 to 17, wherein the solvent (b):polymer (a) ratio w/w is between 10:90 and 60:40.

10 19. The use of an acrylic composition of any one of items 1 to 18, to provide a high Tg melt blended composition or moulded polymer product.

20. An impact modified acrylic polymer composition comprising

15 a. a base polymer in accordance with the acrylic polymeric composition of any one of items 1 to 19; and

20 b. a core-shell impact modifier wherein the level of component (b) in the impact modified acrylic polymer composition is greater than 30.5% w/w.

25 21. The impact modified acrylic polymer composition of item 20, wherein the level of component (b) in the impact modified acrylic polymer composition is in the range 32-50% w/w.

30 22. The impact modified acrylic polymer composition of item 21, wherein the level of component (b) in the impact modified acrylic polymer composition is in the range 32-40% w/w.

23. The impact modified acrylic polymer composition of any one of items 20-22, wherein the w/w ratio of (a):(b) is between 30:70 and 90:10.

35

2006238988 06 Jul 2012

4e

24. The use of compositions according to any one of items 1, 2, 3 or 4-23 in thick section moulding and de-moulding processes.
- 5 25. A thick section mould of the composition according to any one of items 1, 2, 3 or 4-23.
- 10 26. A moulded polymer product comprising an acrylic polymeric composition according to any one of items 1, 2, 3 or 4-23.
- 15 27. The composition or use according to any one of items 6-26, wherein the HMWA: LMWA ratio is at least 6:5.
- 20 28. The composition or use according to any one of items 1-27, wherein the HMWA and LMWA together form substantially 100% w/w of the acrylic monomer derived components of the acrylic polymeric composition.
- 25 29. The composition or use according to any one of items 1-28, wherein the HMWA and LMWA combine to form substantially 100% w/w of the acrylic polymeric composition.
- 30 30. The composition or use according to any one of items 1-28, wherein the balance of the acrylic polymeric composition consists of suitable additives.
- 35 31. A method of melt blending an impact modified acrylic polymer composition according to any one of items 20-23 comprising the steps of:-  
melt blending the following separate components in a single melt blending step:-
  1. a) a HMWA according to item 1;

4f

- b) a LMWA according to item 1; and
- c) a core-shell impact modifier; or

2. a) a HMWA according to item 1; and

- b) a LMWA according to item 1 pre blended with a core-shell impact modifier; or

3. a) a HMWA and LMWA blended according to item 1; and

- b) a core-shell impact modifier.

10 32. Use of a composition according to any one of items 1, 2, 3, 4-23 or 27-30 as a cycle time reduction composition.

15 33. Use of a composition according to any one of items 1, 2, 3, 4-23 or 27-30 as a reduced cooling cycle time composition.

20 34. A reduced cycle time moulding composition comprising a composition according to any one of items 1, 2, 3, 4-23 or 27-30.

25 35. A reduced cooling time moulding composition comprising a composition according to any one of items 1, 2, 3, 4-23 or 27-30.

30 36. A process for reducing cycle time of a moulding composition comprising the step of:  
injection moulding or extrusion moulding  
a composition according to any one of items 1, 2, 3, 4-23 or 27-30.

35 37. A process for reducing cooling cycle times of a moulding composition comprising the step of :  
injection moulding or extrusion moulding  
a composition according to any one of items 1, 2, 3, 4-23 or 27-30.

4g

38. A composition, process, method or use according to any one preceding item, wherein the HMWA and LMWA have been produced by bulk, emulsion or suspension polymerisation.

5 39. A composition, process, method or use according to any one preceding item, wherein the HMWA and the LMWA are simple single phase polymers.

According to a first aspect of the present invention there is  
10 provided an acrylic polymeric composition having less than 0.5% w/w of an impact strength modifier the said composition comprising a melt blend of a thermoplastic high molecular weight acrylic material (HMWA) and a thermoplastic low molecular weight acrylic material (LMWA), at least 70% w/w,  
15 based on the total weight of the HMWA, of the said HMWA comprising an alkyl (alk)acrylate (co)polymer, the said (co)polymer comprising at least 80% w/w of a first polymer unit derived from C<sub>1</sub>-C<sub>12</sub> alkyl (C<sub>1</sub>-C<sub>8</sub> alk)acrylate monomer units and optionally, up to 20% w/w, based on the said alkyl  
20 (alk)acrylate (co)polymer of a first copolymer unit derived from C<sub>1</sub>-C<sub>12</sub> alkyl(C<sub>0</sub>-C<sub>8</sub> alk)acrylate and/or (C<sub>0</sub>-C<sub>8</sub> alk)acrylic acid monomer units, the said HMWA having a weight average molecular weight of between 40k Daltons and 1000k Daltons,

at least 70% w/w, based on the total weight of the LMWA, of the said LMWA comprising an alkyl(alk)acrylate (co)polymer, the said (co)polymer comprising at least 80% w/w of a second polymer unit derived from C<sub>1</sub>-C<sub>12</sub> alkyl (C<sub>1</sub>-C<sub>8</sub> alk)acrylate monomer units and optionally, up to 20% w/w, based on the said alkyl (alk)acrylate (co)polymer of a second copolymer unit derived from C<sub>1</sub>-C<sub>12</sub> alkyl(C<sub>0</sub>-C<sub>8</sub> alk)acrylate and/or (C<sub>0</sub>-C<sub>8</sub> alk)acrylic acid monomer units, the said LMWA having a weight average molecular weight of between the entanglement molecular weight (M<sub>e</sub>) (expressed in k Daltons) and 250k Daltons, with the proviso that the HMWA has a higher Mw than the LMWA, wherein the first polymer unit of the HMWA and the second polymer unit of the LMWA are the same.

The first polymer unit of the HMWA and the second polymer unit of the LMWA are the same ie. if the first polymer unit is methyl(meth)acrylate, the second polymer unit is methyl(meth)acrylate, etc. Preferably, the first copolymer unit and the second copolymer unit are the same ie. if the first copolymer unit is ethyl acrylate the second copolymer unit is ethyl acrylate etc. Preferably, the weight ratio of the first polymer unit: first copolymer unit is within ± 30% of the ratio of second polymer unit:second copolymer unit, more preferably within ± 20%, most preferably within ± 10%.

Preferably, the weight ratio of HMWA:LMWA in the composition is greater than 1:1, more preferably, at least 6:5, most preferably, at least 7:3.

Preferably, the acrylic polymeric composition comprises, based on the weight of the acrylic polymeric composition, up to 55% w/w of LMWA and at least 40% w/w of HMWA , more preferably, up to 15% w/w of LMWA and at least 50% w/w of

HMWA, most preferably, up to 10% w/w of LMWA and at least 60% w/w of HMWA material.

By melt blend is meant a composition which has been produced by the method of melt blending. By melt blending is meant a method of melt mixing that reduces the nonuniformity of a binary (or greater) composition of different polymers (including polymers which only differ from each other in respect of their molecular weight). The mechanism of mixing is to induce physical motion of the ingredients at an elevated temperature (preferably,  $T >$  glass transition,  $T_g$ , for all polymer components). This involves ensuring sufficient distributive and dispersive mixing to enable the constituents in the blend to be regarded as homogeneous. This consequently requires the polymers to undergo convective mixing by laminar flow for a sufficiently long enough time such that the residence time for the polymers in the mixing process exceeds the time to achieve homogenisation by that process. (Preferably, good practice would ensure that the size and shape of the polymer components to be mixed will be broadly similar, thus aiding dispersive mixing). Suitable mixing procedures may include single or twin screw extrusion, or through the screw feed process in injection moulding.

Such a definition would preclude the use of blending via pressure only (even if the temperature were raised greatly above the glass transition) or blending via solution mixing and eventual evaporation (C Rauwendaal Polymer Extrusion Hanser Publishers, Munich (1994) ISBN 3 - 446 - 17960 - 7; page 322 & JM Deely and KF Wissbrun Melt Rheology and its role in plastics processing, Theory and

Applications Van Nostran Reinhold, New York (1990) ISBN 0-442-22099-5; page 480).

References to  $M_e$  herein should be taken to be determined by torsional melt rheology characterisation

Such characterisation is carried out according to ASTM D4440. Specifically  $M_e$  should be assumed to be determined for a sample of polymer as follows:

prior to mounting in the torsional rheometer, solid pre-form disks are prepared and dried in a vacuum oven overnight at 70°C, to remove residual moisture. They are then mounted in between parallel plates of 25 mm diameter, in a Rheometrics RDAII rotational rheometer.

The upper test fixture is lowered so it touches the bottom fixture at approximately the same normal force it experiences during testing. The gap indicator is then zeroed. The upper test fixture is then raised and the sample disk is placed on to the bottom test fixture.

The plate is gently lowered down onto the surface of the disk, and then heated to a temperature of typically 140°C, whilst maintaining the gap setting for a sample disk of 2mm thickness. Once the polymer disk has visibly melted, the excess polymer sample emerging from the side of the cone and plate is trimmed off, using a sharp knife. Torsional frequencies between 0.01 and 100 rads/s at a fixed strain amplitude of 5% are then applied to the sample by the rheometer at this fixed temperature. During this frequency sweep, the storage (elastic) modulus  $G'(\omega)$  and the loss (viscous) modulus  $G''(\omega)$  are determined at each frequency.

The temperature of the melt is then increased to a value typically 20-30°C higher than previously, with the experimental procedure being repeated. Measurements were normally made at 230°C, up to a maximum temperature of typically 250°C.

The measurement of the storage and loss moduli allows the calculation of the complex viscosity  $\eta^*(\omega)$  using the standard relationship (ref LA Utracki Polymer Alloys and Blends, p134 Hanser Publishers (1990) ):-

$$\eta^*(\omega) = \frac{\sqrt{G'^2(\omega) + G''^2(\omega)}}{\omega} \quad [4a]$$

The storage and loss moduli were then subjected to time temperature superposition to a reference temperature of 230°C using the Shiftt.exe computer program, described conceptually and with source code listing by GV Gordon and MT Shaw Computer Programs for Rheologists, Hanser Publishers (1994) .

The resulting 'master curves' were shifted to a reference temperature of 230°C, assuming a glass transition temperature of approximately 100°C, using either  $\tan \delta (G''(\omega) / G'(\omega))$  or the storage modulus  $G'(\omega)$  as the reference spectra to be superposed.

Figures [1-3] below give an example of basic rheological data for a test sample before and after superposition to the master curve.

Figure [1]: Torsional rheology data for a Test Sample measured between 0.01 and 100 Hz and between 140 to 250°C

Figure [2]: Torsional rheology data in the form of a 'master curve' for the Test Sample, superposed to 230°C. This shows the full rheological spectrum for this polymer between frequencies of  $10^{-2}$  to  $10^7$  rad/s.

Determination of entanglement molecular weight from master curves

The entanglement molecular weight is related to the plateau shear modulus, determined from data such as shown in Figure (2), according to the relationship

$$M_e = k \frac{\rho R T}{G_N^0} \quad [8]$$

Where  $\rho$  is the density of a polymer at temperature T. The values for PMMA polymer at specific temperatures are found in FN Cogswell Polymer Melt Rheology Appendix 9 p156,

Woodhead Publishing Ltd 1997 ),  $G_N^0$  is the plateau modulus and R is the gas constant ( $8.3144 \text{ J mol}^{-1} \text{ K}^{-1}$ ) and k is a constant, whose value is 4/5 (definitions of entanglement spacing and time constants in the tube model RG Larson et al Journal of Rheology 47 p809 (2003)).

The plateau modulus can be obtained from a master curve as the value of the storage modulus  $G'(\omega)$  of where  $\tan \delta$  reaches a local minimum (See S Wu 'Chain Structure and entanglements' Journal of Polymer Science: Pt B Polymer Physics 27 p723 (1989))

$$G_N^0 = G'(\omega) \Big|_{\omega \rightarrow \tan \delta = \min} \quad [9]$$

Thus taking the data in Figure (2) and plotting the  $\tan \delta$  function allows the identification of  $G_N^0$

Figure [3] Plateau modulus  $G_N^0$  calculated from  $G'(\omega)$  at  $\min \tan \delta (=G''(\omega)/G'(\omega))$  using the dataset in Figure [2].  $G_N^0$  by this definition is 0.46 MPa.

Preferably, the compositions of the present invention are thermoplastic and are not thermosetting compositions. Preferably, the melt blends are homogenous melt blends.

The composition may optionally include a second or further HMWA component (defined in the same manner as the first HMWA above) which has a weight average molecular weight greater than the LMWA but which may be less or greater than the other HMWA component(s). This second or further component may be present at a level, based on the acrylic polymeric composition, of at least 5% w/w, more preferably, at least 10% w/w, most preferably, at least 15% w/w. Preferably, the said second or further HMWA has

a lower weight average molecular weight than the first HMWA component. Otherwise, the second or further HMWA may include any of the preferred features of the first HMWA including any relative relationship to the LMWA such 5 as those of the nature and proportion of the third polymer unit and copolymer unit with respect to the LMWA second polymer unit and copolymer unit.

In addition, preferably, the first polymer unit of the 10 HMWA and the third or further polymer unit of the second or further HMWA are the same. Preferably, the first copolymer unit and third copolymer unit are the same. Preferably, the ratio of the first polymer unit:first 15 copolymer unit is within  $\pm$  30% of the ratio of the third polymer unit:third copolymer unit, more preferably, within  $\pm$  20%, most preferably within  $\pm$  10%.

The HMWA (including the second or further HMWA component when present) may be present, based on the overall weight of the acrylic polymeric composition, at a level of up to 99% w/w, more preferably, up to 96% w/w, most preferably, up to 94% w/w.

The LMWA may be present, based on the overall weight of the acrylic polymeric composition, at a level of at least 1% w/w, more preferably at least 2% w/w, most preferably at least 4% w/w.

The LMWA may be present, based on the overall weight of the acrylic polymer composition, in the range of 1-60% w/w, more preferably 2-55% w/w, most preferably 4-51% w/w, especially 4-40% w/w, more especially 4-30% w/w.

The HMWA (including the second or further HMWA component when present) may be present, based on the overall weight of the acrylic polymeric composition, in the range of 99-40% w/w, more preferably 98-49% w/w, most preferably, 98-70% w/w, especially 98-45% w/w, more especially 96-49% w/w, most especially 96-60% w/w or 96-70% w/w.

The HMWA and LMWA may together form 90% w/w, more preferably , 95% w/w, most preferably, 99% w/w, especially, substantially 100% w/w of the acrylic monomer derived components of the acrylic polymeric composition.

Preferably, the LMWA has a weight average molecular weight (Mw) in excess of 11K Daltons, more preferably in excess of 15k Daltons, most preferably, in excess of 20K Daltons.

2006238988 13 Dec 2011

In some embodiments it may be in excess of 50k or even 70k.

Preferably, the LMWA has a Mw less than 150K, more preferably, less than 70K, most preferably, less than 65K. An especially preferred Mw for the LMWA is less than 40k, even especially preferred is less than 25k.

The upper limits and lower limits as herein defined for LMWA Mw and HMWA Mw may be combined in any respective combination.

Preferably, the HMWA has a Mw in excess of 50K Daltons, more preferably, in excess of 70K Daltons, most preferably, in excess of 85K Daltons.

The HMWA first component may have a Mw in excess of 100K, more preferably, 120K, most preferably, 140K, whereas the HMWA second or further component may have a Mw in excess of 50k, more preferably in excess of 60k, most preferably in excess of 70K.

Preferably, the C<sub>1</sub>-C<sub>12</sub> alkyl(C<sub>0</sub>-C<sub>8</sub> alk)acrylate and/or (C<sub>0</sub>-C<sub>8</sub> alk)acrylic acid first or second copolymer unit, when present, comprises up to 15% w/w of the alkyl(alk)acrylate copolymer, more preferably up to 10% w/w, most preferably, up to 8% w/w. The first or second copolymer unit may be C<sub>1</sub>-C<sub>12</sub> alkyl(C<sub>0</sub>-C<sub>8</sub> alk)acrylate polymer or a (C<sub>0</sub>-C<sub>8</sub> alk)acrylic acid or a combination thereof and may be present at independent levels in the LMWA or the HMWA. Preferably, more than 80% w/w of the HMWA or the LMWA is the relevant alkyl(alk)acrylate (co)polymer, more preferably, more than 90% w/w, most preferably, more than

95% w/w of the LMWA or HMWA is the said relevant (co)polymer.

Preferably, the HMWA and the LMWA together form more than 80% w/w of the acrylic polymeric composition, more preferably, at least 90% w/w of the acrylic polymeric composition, most preferably, at least 95% w/w, especially 99% or 100% w/w of the acrylic polymeric composition.

The balance of the acrylic polymeric composition and/or HMWA and/or LMWA may consist of suitable additives, preferably, non acrylic additives. Preferably, the additives form less than 30% w/w, more preferably, less than 20% w/w, most preferably less than 10% w/w and especially less than 5% of the said composition and/or the HMWA and/or LMWA.

The additives may include thermal stabilisers, UV stabilisers, colouring agents, gloss control agents, diffusion agents, fire retardants and lubricants. Preferably, the additives do not include cross-linking agents. Preferably, the acrylates used in the present invention do not include functional groups capable of effecting substantial cross-linking in the composition or in further compositions comprising the composition. Preferably, any acrylic acid units having free hydroxyl groups present in the composition do not act as a cross linking agent or are not present in sufficient amount to effect substantial crosslinking. In particular, the compositions of the present invention preferably do not include substantive levels of non-acrylic or vinyl monomer units in the polymer chains (other than those vinyl monomer units derived from acrylic monomers). Preferably,

"acrylic monomers" or the like as used herein do not include any or substantive (for instance, greater than 1%) levels of acrylonitrile monomers but do include substituted or unsubstituted C<sub>1</sub>-C<sub>12</sub> alkyl (C<sub>0</sub>-C<sub>8</sub> alk) acrylate monomers and (C<sub>0</sub>-C<sub>8</sub> alk) acrylic acid monomers. Preferably, the substituted acrylic monomers or the like do not include any (or, if so, do not have a substantive level in the monomers) substituents capable of effecting crosslinking with the same or a different substituent on an acrylic monomer unit of a neighbouring or the same polymer chain. In particular, the acrylic monomer units of the polymers and copolymers of the present invention do not include any substantive level of monomer units with glycidyl or hydroxyl (other than (alk) acrylic acid) group substituents. By substantive as used above is meant less than 5% w/w in the HMWA or LMWA, more preferably, less than 1% w/w, most preferably, less than 0.1%, especially, less than 0.01% w/w, more especially 0.001% w/w.

The acrylic polymeric composition may also form the base polymer of a further system, requiring a base polymer such as an impact modified polymer or a resin dissolved or dispersed in a solvent.

Accordingly, the invention extends in a second aspect to an acrylic composition comprising

- (a) an acrylic polymeric composition according to the first aspect of the present invention and
- (b) a suitable solvent.

Preferably, the solvent (b):polymer (a) ratio w/w in the said second aspect is between 10:90 and 60:40, more

2006238988 06 Jul 2012

17

preferably, 20:80 and 50:50, most preferably between 30:70 and 45:55.

A suitable solvent is n butyl acetate.

5

The modification of cross-linked poly(meth)acrylate impact modified blends with a low molecular weight component is known at low levels of cross-linked poly(meth)acrylate. However, surprisingly, the inventors have discovered 10 advantageous properties, for example, high Tg at much higher levels of impact modifiers.

Accordingly, in a third aspect, the invention extends to an impact modified acrylic polymer composition comprising

15 (a) a base polymer in accordance with the acrylic polymeric composition of the first aspect of the present invention and  
(b) a core-shell impact modifier wherein the level of component (b) in the impact modified acrylic 20 polymer composition is greater than 30.5% w/w, preferably, having been blended therewith.

Preferably, the w/w ratio of (a):(b) in the third aspect is between 30:70 and 90:10, more preferably, between 40:60 25 and 80:20, most preferably between 50:50 and 70:30.

Particularly preferred levels of component (b) in the impact modified acrylic polymer composition are in the range 32-50% w/w, more preferably 32-40% w/w.

30

Suitable core-shell particles are discrete particles made by multi-stage graft copolymerisation normally by emulsion polymerisation techniques, each having a multi-layer structure and generally used to improve the impact

35

resistance of polymers such as acrylic materials. A wide variety of these particles is available which differ in the type of copolymers from which they are made and the number and volume of shells present around the core. Typically the core is made from a methacrylate homo or copolymer and the first shell provides the rubbery material having a low Tg, typically made from an alkyl acrylate / styrene copolymer. This shell is often formulated to provide a rubbery character for impact modification whilst being matched in refractive index to the acrylic substrate into which it is to be incorporated. A preferred type of copolymer to form the shell is based on n-butyl acrylate and an aromatic comonomer, e.g. styrene or a derivative thereof. A second or subsequent shell may also be present. Many suitable core-shell particles are commercially available, e.g. IR441 available from Mitsubishi Rayon Co., and some commercially available grades of acrylic moulding materials include similar materials pre-compounded in to the polymer. One suitable core-shell particle is described in WO96/37531, the contents of which are incorporated by reference, and comprises a (meth)acrylic polymer core, a first shell comprising a low Tg polymer comprising 0 - 25% by weight of a styrenic monomer and 75 - 100% by weight of an acrylic monomer, the (meth)acrylic monomer being capable of forming a homopolymer having a Tg in the range -75 to -5 °C, the first shell representing at least 65% by volume of the combined volume of the core and first shell, (as determined by transmission electron microscopy, to identify the shell by staining, and by assuming sphericity of the particles and using  $4/3 \pi r^3$  to determine the volume of the core and core/shell) and optionally a second shell which comprises a second (meth)acrylic polymer which

04 Jul 2012

2006238988

19

may be the same as or different from the first (meth)acrylic polymer and the core and first shell together contain from 0.5 - 1.0 % by weight of a graft cross-linker.

5

A suitable transmission electron microscopy technique and instrument is a Philips CM12 TEM.

10 The present invention is directed to acrylic polymeric compositions which are substantially free of impact strength modifier derived from cross-linked poly(meth)acrylates either pre-blended in the high molecular weight component or otherwise combined therewith and, optionally, free of such impact strength modifier 15 pre-blended in any of the components. In fact, a substantially impact modifier free acrylic polymer composition is envisaged. By substantially free is meant less than 0.5% w/w of acrylic polymeric composition of an impact strength modifier, more preferably less than 20 0.1% w/w.

Advantageously, the addition of an impact modifier component when used in the present invention can be carried out in a one step process ie. the HMWA, the LMWA 25 and the Impact Modifier component can be blended together in the appropriate quantities in a single melt blending step wherein they are introduced to the melt blending stage as separate components.

30 However, as an alternative, the impact modifier component can be pre-blended with the LMWA prior to melt blending the impact modified LMWA with the HMWA. The advantage of this approach is that the properties of the impact

modified LMWA will have more in common with the HMWA and thereby be easier to process and melt blend therewith. By this route the optimal blending conditions such as temperature for each component are likely to be closer.

Therefore, according to a further aspect of the present invention there is provided a method of melt blending an impact modified acrylic polymer composition according to the third aspect of the invention comprising the steps of:-

melt blending the following separate components in a single melt blending step:-

a HMWA according to the first aspect of the present invention;

a LMWA according to the first aspect of the present invention;

and a core-shell impact modifier.

As a still further alternative, the impact modifier can be blended with a pre-blended acrylic polymer composition of the first or any aspect of the invention. Advantageously, by this means, an acrylic polymeric composition of the invention can be impact modified after production.

For the avoidance of doubt, references to blending or melt blending herein optionally incorporate a tumble blending phase prior to the melt phase.

The HMWA and the LMWA are, preferably, simple single phase polymers, typically produced by the same polymerisation process. Prior to blending they may be in any suitable form for blending such as bead, pellet or granules.

Suitable processes for production of the HMWA or LMWA include bulk polymerisation and suspension polymerisation. Although, the HMWA and/or LMWA can be produced by emulsion polymerisation, it is preferably not so produced as the process introduces additional unnecessary steps into the process, may introduce non-single phase polymers and does not easily result in matched bead or granule sizes with a non-emulsion polymerised HMWA/LMWA.

Surprisingly, a polymeric melt blend in accordance with any of the aspects of the present invention has a much higher melt flow index (MFI) and comparable Tg when compared with the HMWA in isolation.

As the Tg is maintained at a comparable level to the HMWA the compositions can be used in a variety of similar applications but with improved processability due to the higher MFI. For instance, comparable processability can be maintained with reduced cycle times thus reducing the cost of production. Advantageously, the invention also provides processing advantages as high Tg blends require less processing time ie. cooling time during processing. Faster part cooling rates in the tool can therefore be achieved with the invention. Furthermore, structural integrity can be achieved at higher final part temperatures, effectively reducing the cooling cycle times. One application where this is advantageous is thick section moulding applications which require high melt flow polymers. Such high melt flow polymers can be de-moulded more quickly if the Tg of the polymer is higher.

Accordingly, the invention extends in another aspect to the use of the polymers of the invention in thick section moulding and de-moulding processes as well as to thick section moulds of compositions of the invention. By thick section moulds is meant an average thickness of the moulded product of between 3mm and 100mm, more preferably, between 5mm and 50mm, most preferably, between 5mm and 20mm. Especially preferred are sections in the range 5-10mm. Thick section may also extend to products wherein any parts of the section are more than 3mm from the nearest surface of the product, more preferably more than 4mm, most preferably more than 5mm, and especially greater than 6mm. The invention also extends to thick section moulded polymer products produced from a composition according to any of the 1<sup>st</sup>, 2<sup>nd</sup> and 3<sup>rd</sup> aspects of the present invention.

Another advantage of the ability to increase MFI means that new polymers with unique properties can be produced. High T<sub>g</sub> /high MFI polymers are particularly useful in heat exposure applications such as those of lighting fixtures. Heat exposure applications are applications which may expose the final moulded product to temperatures in excess of 50°C, more typically, in excess of 70°C. Such polymer blends are therefore useful in providing enhanced design flexibility in lighting applications or other applications where the polymer is exposed to a nearby heat source.

Therefore, according to a fourth aspect of the present invention there is provided a moulded polymer product comprising an acrylic polymeric composition according to the first, second or third aspect of the present

invention. The said moulded product may be injection moulded or extrusion moulded.

The increase in MFI should also provide a reduced viscosity in coating applications meaning that more polymer can be used without increasing viscosity or a reduced viscosity can be found with the same amount of polymer.

Accordingly, in a fifth aspect of the present invention, there is provided the use of an acrylic composition in accordance with any of the aspects of the present invention to provide a higher MFI melt blended composition or moulded polymer product (as compared with the HMWA not blended with the LMWA).

Preferably, the invention also provides a high Tg melt blended composition or moulded polymer product.

High Tg and/or higher MFI can be tested by the following method. The Tg and the MFI for the normal polymer is established by conventional means. For the avoidance of doubt, reference to MFI herein are references to MFI in grams/10 minutes determined at 230°C with a weight of 3.8kg in accordance with ASTM D1238-98, Procedure A.

The low molecular weight additives are blended into the normal polymer at such a level which preferably causes an increase in the melt flow index of the normal polymer, of for instance, 15 g/10 mins. If the Tg is measured for an MFI increase of 15g/10 mins, it is experimentally found that the Tg will typically only suffer a decrease in the range of 1 to 15°C, more typically 2-12°C, most typically

4-10°C, via this route. Even with an increase in MFI of 25g/10 mins, the Tg is typically only reduced by 1-20°C, more typically, 2-15°C, most typically 4-12°C. Preferably, for each MFI increase of 5g/10 mins, the reduction in Tg is less than 5°C, typically this is the case up to very high MFIs, for example up to 35g/10 mins, 40 or 45 g/10 mins.

This improvement distinguishes the invention from the alternative method for increasing the melt flow index by the same amount (e.g. 15 g/10 mins). This is done by keeping the molecular weight constant but increasing the level of acrylate comonomer used in the copolymer. This alternative strategy causes an increase in MFI of 15 g/10 mins at the expense of a suppression in the glass transition in the order of greater than 15°C.

Therefore, a high Tg may be taken as a Tg in a test (co)polymer of the invention which is higher than that for a comparative copolymer with the same MFI which is derived from the same type and equivalent amount of C<sub>1</sub>-C<sub>12</sub> alkyl(C<sub>1</sub>-C<sub>8</sub> alk) acrylate monomer(s) but a higher amount of C<sub>1</sub>-C<sub>12</sub> alkyl acrylate monomer(s) to thereby give the MFI increase necessary and which is not a melt blended HMWA and LMWA in accordance with the invention wherein the "equivalent amount" of C<sub>1</sub>-C<sub>12</sub> alkyl C<sub>1</sub>-C<sub>8</sub> alk acrylate is the same amount reduced by the proportionate increase in the C<sub>1</sub>-C<sub>12</sub> alkyl acrylate amount in the comparative copolymer, for example if the comparative copolymer comprises 5% w/w C<sub>1</sub>-C<sub>12</sub> alkyl acrylate more than the test polymer, then the C<sub>1</sub>-C<sub>12</sub> alkyl C<sub>1</sub>-C<sub>8</sub> alk acrylate in the comparative copolymer is reduced by 5% w/w.

Preferably, at an MFI of the polymer blend between 30-50g/10 min, the Tg is preferably between 80°C-110°C, more preferably, 85°C-110°C, most preferably, 90°C-110°C.

5 References to Tg herein should be taken to be determined using DSC procedure ASTM E1356-98, extrapolated onset temperature on 2<sup>nd</sup> reheat unless indicated otherwise.

10 Also described herein is a method of producing an acrylic polymeric composition comprising the steps of:-

a) contacting a thermoplastic high molecular weight acrylic material (HMWA) with a thermoplastic low molecular weight acrylic material (LMWA); and

15 b) mixing the said HMWA and LMWA at an elevated temperature until a melt blend is produced;

20 wherein the said elevated temperature is above the glass transition temperature of both the HMWA and LMWA.

25 Steps a) and b) may take place sequentially or simultaneously. Preferably, the acrylic polymer composition is in accordance with that defined by any of the other aspects of the present invention.

The melt blending may be carried out by extrusion or injection moulding techniques.

30 The invention will now be illustrated by the accompanying examples. Figure 1 shows comparative results with

equivalent amounts of alkyl acrylate and methacrylic acid additives. These results are also shown in table 1.

### Experimental

#### Polymerisation

Polymer samples were made by conventional free radical suspension polymerisation, resulting in a bead polymer of a given chemical composition and molecular weight distribution. The bead polymers were dried in a vacuum oven overnight at 70°C, to remove all residual moisture.

#### Melt blending

Blends of different homogenous molecular weight bead polymers were made by first weighing out a known quantity of each polymer using a pan balance. The correct amount of each polymer making up the blend composition were tumble mixed in a plastic bag for approximately five minutes to ensure thorough dispersion of the components. The tumble blended mixture were then placed in a fresh metal container and dried in a vacuum oven overnight at 70°C to remove any residual moisture.

The dried tumble blended mixtures were consolidated into an extruded continuous melt stream through the use of a DSM micro extruder twin screw mixer (15 cm<sup>3</sup> volume), heated in all zones at 230°C, (much higher than the glass transition at approximately 100°C) with a screw rate of at least 60 rpm. Residence times through the extruder were chosen to ensure homogenisation of the melt stream. The polymer 'lace' was hauled off and mechanically fractured

into chips approximately five mm in length using a conventional polymer processing shredding tool.

Description of MFI test method

The melt flow index measures the rate of extrusion of thermoplastics through a circular die at a prescribed temperature and fixed load. The amount of polymer which is extruded out under a set time is sampled, and the weight of the cooled extrudate is determined. From this the melt flow index is determined. It is simple method for measuring flow of a molten polymer, hence polymer processability at a fixed temperature.

Approximately 5-8 g of polymer is loaded into the barrel of the melt flow apparatus (Davenport 730A/77CR) which is heated to a specified temperature. A weight is then applied to the plunger which forces the molten polymer through the circular die. The test begins once the applied load forces the plunger past a scribed mark, and the test ends after a set time interval. The polymer which is extruded out of the die during this set time period, is allowed to cool and is weighed.

The test method and the apparatus used in the test is described in more detail in ASTM D1238 - procedure A. The values used for the PMMA and blend samples in this test were

Temperature (10mm above the die) = 230°C

Applied load = 3.8 kg

Circular die diameter = 2.0955 +/- 0.0051 mm

Test duration = 10 minutes

Weight = grams

Flow Rates = grams/10 minutes

Molecular Weight Determination

Molecular weight,  $M_w$ , was characterised using size exclusion chromatography (also referred to as gel permeation chromatography, GPC), using a Polymer Laboratory Caliber system, with PMMA standards.

Calibration of the GPC required the following procedure. PMMA standard solutions were made using 15mg of either  $M_p$  10.3k or  $M_p$  107k dissolved in 10 ml chloroform containing 5-10  $\mu$ l MMA marker. Approx 5mg of each standard was placed into a vial, dissolved in 10ml chloroform containing 5-8 $\mu$ l of MMA flow marker, filtered and 1-2ml transferred into autosampler vials for evaluation.

Test polymers were analysed as follows. 25-30 mg of polymer were weighed into a vial, and 10ml chloroform was added. The mixture was agitated until dissolved. The samples were filtered through a 0.2 $\mu$ m PTFE/syringe filter, without using excessive pressure before analysis.

The polymer sample was dissolved in the chloroform at a temperature of 30°C. The injection volume into the GPC was between 1 to 5 microlitres. A flow rate of 1 ml / min was used. Determination of molecular weight,  $M_w$ , was performed automatically using the analytical software used by the instrument.

Molecular weights were measured in chloroform relative to PMMA standard using GPC equipment fitted with an infra-red detector tuned to the carbonyl absorption at 5.90 microns.

Residual monomer levels were determined by reprocessing the raw data using LG/GC software. The GPC equipment and software were supplied by Polymer Laboratories Limited.

Solvent	Chloroform
Flow rate	1ml min-1
Sample concentration	25mg/10ml
Temperature	30°C
PC	IBM Compatible

#### Core Shell Volume Calculation

The specimens (of impact modified polymer) were trimmed to produce block faces for subsequent sectioning. They were then placed in a fresh solution of ruthenium trichloride in aqueous sodium hypochlorite. The resulting reaction produces ruthenium tetroxide and gives rise to preferential staining of any unsaturation present in the system. The stain gives enhanced contrast in the transmission electron microscope (TEM), thereby aiding interpretation. The blocks were soaked in the staining medium for one hour before being removed, washed with distilled water and allowed to dry at room temperature. After aligning in a Reichert Ultracut E ultramicrotome, approx 50nm sections were taken and examined in a Philips CM12 TEM.

#### Glass Transition Characterisation

The glass transition Tg for each polymer were characterised using differential scanning calorimetry (DSC), using the procedure outlined in ASTM E1356 - 98. The Tg characterisation method used is the extrapolated onset temperature on second reheat.

The equipment used was a Mettler Toledo TC15 TA controller, with a circular pan geometry approximately 5 mm in diameter by 1mm in depth, made from aluminium, with a nominal thickness of 15  $\mu\text{m}$ . The samples were heated at a scan rate of 20°C / min. Measurements were made using nitrogen of purity >99.9%, and 50ml/min as the flow rate. There were no indications of any side reactions during the glass transition measurement. After first heating the pan was cooled using liquid nitrogen before reheating using the previously described conditions.

Some samples (as indicated) were analysed for  $T_g$  using Heat Deflection Temperature (HDT) under a deformation of 1.82MPa using ASTM D648.

**Base Polymer 1   Base Polymer 2   Base Polymer 3**

Main Monomer	MMA	MMA	MMA
%w/w	97	97	97
Second Monomer	EA	EA	EA
%w/w	3	3	3
Mw (k)	90	142	22.1
Mn (k)	41	67	9.4
Product Form	Powder	Powder	Powder
Tg° (C) via DSC	106.7	110.3	96.3
MFI (g/10min) @230°C/3.8kgf /2.095mm die	5.4	1.2	Unmeasurable

Base polymers 1-3 are used in blending examples below

Comparitive Base Polymer Examples 4-8

**Base Polymer 4 Base Polymer 5 Base Polymer 6**

Main Monomer	MMA	MMA	MMA
%w/w	99	98.5	95
Second Monomer	EA	EA	EA
%w/w	1	1.5	5
Mw (k)	90	90	90
Mn (k)	45	45	45
Product Form	Compound	Compound	Compound
Tg° (C) via HDT	100.4	98.5	92.8
MFI (g/10min) @230°C/3.8kgf /2.095mm die	3.6	4.3	6.0

**Base Polymer 7 Base Polymer 8**

Main Monomer	MMA	MMA
%w/w	90	86
Second Monomer	EA	EA
%w/w	10	14
Mw (k)	88	90
Mn (k)	41	45
Product Form	Compound	Compound
Tg° (C) via HDT	82.8	75.9
MFI (g/10min) @230°C/3.8kgf /2.095mm die	15.5	27.0

**Compound 9 Compound 10 Compound 11**

Base Polymer	1	1	1
Parts	95	90	85
Base Polymer	3	3	3
Parts	5	10	15
Base Polymer	-	-	-
Parts	-	-	-
Mw (k)	85.0	82.5	77.4
Mn (k)	32.8	31.9	29.1

Product Form	Compound	Compound	Compound
Tg° (C) via DSC	106.1	104.2	102.4
MFI (g/10min) @230°C/3.8kgf /2.095mm die	6.1	7.4	8.5
Comments	Compound made from binary blend of base polymers (1 & 3)	Compound made from binary blend of base polymers (1 & 3)	Compound made from binary blend of base polymers (1 & 3)

	Compound 12	Compound 13	Compound 14
Base Polymer	1	2	2
Parts	50	50	33
Base Polymer	3	3	1
Parts	50	50	34
Base Polymer	-	-	3
Parts	-	-	33
Mw (k)	68.3	83.9	98.0
Mn (k)	22.9	21.1	30.4
Product Form	Compound	Compound	Compound
Tg° (C) via DSC	105.1	100.7	104.7
MFI (g/10min) @230°C/3.8kgf /2.095mm die	32.51	19.8	11.53
Comments	Compound made from binary blend of base polymers (1 & 3)	Compound made from binary blend of base polymers (2 & 3)	Compound made from binary blend of base polymers (1, 2 & 3)

	Compound 15	Compound 16	Compound 17
Base Polymer	2	2	2
Parts	20	60	90
Base Polymer	1	1	3
Parts	60	20	10
Base Polymer	3	3	-
Parts	20	20	-
Mw (k)	82.3	97.2	115.6
Mn (k)	24.0	26.3	36.8
Product Form	Compound	Compound	Compound
Tg° (C) via DSC	103.9	104.8	104.3

MFI(g/10min)	9.14	4.35	1.82
@230°C/3.8kgf			
/2.095mm die			

Comments	Compound made from ternary blend of base polymers (1, 2 & 3)	Compound made from ternary blend of base polymers (1, 2 & 3)	Compound made from ternary blend of base polymers (2 & 3)
----------	--	--	---

Example compound polymers 9-17 are binary or ternary blends of base polymers 1-3 and achieve enhanced melt flow without significantly reducing glass transition (as measured by DSC)

	Compound 18	Compound 19
Base Polymer	1	1
Parts	60	54
Base Polymer	-	3
Parts	-	6
Impact Modifier	Yes	Yes
Parts	40	40
Mw (k)	90	90
Mn (k)	41	41
Product Form	Compound	Compound
Tg° (C) via HDT	67.3	68.0
MFI(g/10min)	0.89	1.11
@230°C/3.8kgf		
/2.095mm die		
Comments	Compound made from binary blend of base polymer 1 & impact modifier	Compound made from ternary blend of base polymers 1 & 3 & impact modifier

Example compound polymers 19 is an impact modified binary blend of base polymers 1 & 3 and achieves enhanced melt flow without significantly reducing glass transition (as measured by DSC), compared to example 18.

The MFI and Tg values for these examples were measured and the results are shown in Figure 4. As can be seen the Tg

level of the high/low MW blended polymers are markedly higher than the copolymers for a corresponding MFI improvement.

Figure 4: Plot of MFI vs Tg for polymers listed in examples above. The Tg values were measured by DSC or HDT (see information in examples for details)

Attention is directed to all papers and documents which are filed concurrently with or previous to this specification in connection with this application and which are open to public inspection with this specification, and the contents of all such papers and documents are incorporated herein by reference.

All of the features disclosed in this specification (including any accompanying claims, abstract and drawings), and/or all of the steps of any method or process so disclosed, may be combined in any combination,

except combinations where at least some of such features and/or steps are mutually exclusive.

Each feature disclosed in this specification (including 5 any accompanying claims, abstract and drawings) may be replaced by alternative features serving the same, equivalent or similar purpose, unless expressly stated otherwise. Thus, unless expressly stated otherwise, each feature disclosed is one example only of a generic series 10 of equivalent or similar features.

The invention is not restricted to the details of the foregoing embodiment(s). The invention extends to any novel one, or any novel combination, of the features 15 disclosed in this specification (including any accompanying claims, abstract and drawings), or to any novel one, or any novel combination, of the steps of any method or process so disclosed.

20 It is to be understood that, if any prior art publication is referred to herein, such reference does not constitute an admission that the publication forms a part of the common general knowledge in the art, in Australia or any other country.

25 In the claims which follow and in the preceding description of the invention, except where the context requires otherwise due to express language or necessary implication, the word "comprise" or variations such as 30 "comprises" or "comprising" is used in an inclusive sense, i.e. to specify the presence of the stated features but not to preclude the presence or addition of further features in various embodiments of the invention.

2006238988 04 Jul 2012

36

The claims defining the invention are as follows:

1. An acrylic polymeric composition having less than 0.5% w/w of an impact strength modifier the said composition comprising a melt blend of a thermoplastic high molecular weight acrylic material (HMWA) and a thermoplastic low molecular weight acrylic material (LMWA), at least 70% w/w, based on the total weight of the HMWA, of the said HMWA comprising an alkyl (alk)acrylate (co)polymer, the said (co)polymer comprising at least 80% w/w of a first polymer unit derived from C<sub>1</sub>-C<sub>12</sub> alkyl (C<sub>1</sub>-C<sub>8</sub> alk)acrylate monomer units and optionally, up to 20% w/w, based on the said alkyl (alk)acrylate (co)polymer of a first copolymer unit derived from C<sub>1</sub>-C<sub>12</sub> alkyl(C<sub>0</sub>-C<sub>8</sub> alk)acrylate and/or (C<sub>0</sub>-C<sub>8</sub> alk)acrylic acid monomer units, the said HMWA having a weight average molecular weight of between 40k Daltons and 1000k Daltons, at least 70% w/w, based on the total weight of the LMWA, of the said LMWA comprising an alkyl(alk)acrylate (co)polymer, the said (co)polymer comprising at least 80% w/w of a second polymer unit derived from C<sub>1</sub>-C<sub>12</sub> alkyl (C<sub>1</sub>-C<sub>8</sub> alk)acrylate monomer units and optionally, up to 20% w/w, based on the said alkyl (alk)acrylate (co)polymer of a second copolymer unit derived from C<sub>1</sub>-C<sub>12</sub> alkyl(C<sub>0</sub>-C<sub>8</sub> alk)acrylate and/or (C<sub>0</sub>-C<sub>8</sub> alk)acrylic acid monomer units, the said LMWA having a weight average molecular weight of between the entanglement molecular weight (M<sub>e</sub>) (expressed in k Daltons) and 250k Daltons, with the proviso that the HMWA has a higher Mw than the LMWA, wherein the first polymer unit of the HMWA and the second polymer unit of the LMWA are the same.

2. An acrylic composition comprising
  - a. an acrylic polymeric composition according to claim 1; and
  - b. a suitable solvent.
- 5 3. The use of an acrylic polymeric composition in accordance with any one preceding claim to provide a higher MFI melt blended composition or moulded polymer product (as compared with the HMWA not blended with the LMWA).
- 10 4. The composition or use of any one of claims 1-3, wherein the first copolymer unit and the second copolymer unit are the same.
- 15 5. The composition or use of any one of claims 1-4, wherein the weight ratio of the first polymer unit:first copolymer unit is within  $\pm$  30% of the ratio of second polymer unit:second copolymer unit.
- 20 6. The composition or use of any one of claims 1-5, wherein the weight ratio of HMWA:LMWA in the composition is greater than 1:1.
- 25 7. The composition or use of any one of claims 1-6, wherein the acrylic polymeric composition comprises, based on the weight of the acrylic polymeric composition, up to 55% w/w of LMWA and at least 40% w/w of HMWA.
- 30 8. The composition or use of any one of claims 1-7, wherein the melt blends are homogeneous melt blends.
9. The composition or use of any one of claims 1 to 8, wherein the composition optionally includes a second or further HMWA component (defined in the same manner as the first HMWA) which has a weight average molecular

weight greater than the LMWA but which is less or greater than the other HMWA component(s).

10. The composition or use of claim 9, wherein the second or  
5 further component is present at a level, based on the  
acrylic polymeric composition, of at least 5% w/w.

11. The composition or use of either claim 9 or 10, wherein  
10 the second or further HMWA has a lower weight average  
molecular weight (Mw) than the first HMWA component.

12. The composition or use of any one of claims 9-11,  
wherein the first polymer unit of the HMWA and the third  
or further polymer unit of the second or further HMWA  
15 are the same.

13. The composition or use of any one of claims 9-12,  
wherein the first copolymer unit and third copolymer  
unit are the same.

20 14. The composition or use of any one of claims 9 to 13,  
wherein the ratio of the first polymer unit:first  
copolymer unit is within  $\pm$  30% of the ratio of the third  
polymer unit:third copolymer unit.

25 15. The composition or use of any one of claims 1 to 14,  
wherein the HMWA, including the second or further HMWA  
component when present, is present, based on the overall  
weight of the acrylic polymeric composition, at a level  
30 of up to 99% w/w.

16. The composition or use of any one of claims 1 to 15,  
wherein the LMWA is present, based on the overall weight  
of the acrylic polymeric composition, at a level of at  
35 least 1% w/w.

2006238988 06 Jul 2012

17. The composition or use of any one of claims 1 to 16, wherein the LMWA has a weight average molecular weight (Mw) in excess of 11k Daltons.

5 18. The acrylic composition of any one of claims 2 to 17, wherein the solvent (b):polymer (a) ratio w/w is between 10:90 and 60:40.

10 19. The use of an acrylic composition as claimed in any one of claims 1 to 18, to provide a high Tg melt blended composition or moulded polymer product.

15 20. An impact modified acrylic polymer composition comprising

15 a. a base polymer in accordance with the acrylic polymeric composition of any one of claims 1 to 19; and

20 b. a core-shell impact modifier wherein the level of component (b) in the impact modified acrylic polymer composition is greater than 30.5% w/w.

25 21. The impact modified acrylic polymer composition of claim 20, wherein the level of component (b) in the impact modified acrylic polymer composition is in the range 32-50% w/w.

30 22. The impact modified acrylic polymer composition of claim 21, wherein the level of component (b) in the impact modified acrylic polymer composition is in the range 32-40% w/w.

23. The impact modified acrylic polymer composition of any one of claims 20-22, wherein the w/w ratio of (a):(b) is between 30:70 and 90:10.

2006238988 06 Jul 2012

40

24. The use of compositions according to any one of claims 1, 2, 3 or 4-23 in thick section moulding and de-moulding processes.
- 5 25. A thick section mould of the composition according to any one of claims 1, 2, 3 or 4-23.
- 10 26. A moulded polymer product comprising an acrylic polymeric composition according to any one of claims 1, 2, 3 or 4-23.
- 15 27. The composition or use according to any one of claims 6-26, wherein the HMWA: LMWA ratio is at least 6:5.
- 20 28. The composition or use according to any one of claims 1-27, wherein the HMWA and LMWA together form substantially 100% w/w of the acrylic monomer derived components of the acrylic polymeric composition.
- 25 29. The composition or use according to any one of claims 1-28, wherein the HMWA and LMWA combine to form substantially 100% w/w of the acrylic polymeric composition.
- 30 30. The composition or use according to any one of claims 1-28, wherein the balance of the acrylic polymeric composition consists of suitable additives.
- 35 31. A method of melt blending an impact modified acrylic polymer composition according to any one of claims 20-23 comprising the steps of:-  
melt blending the following separate components in a single melt blending step:-
  1. a) a HMWA according to claim 1;

2006238988 06 Jul 2012

41

- b) a LMWA according to claim 1; and
- c) a core-shell impact modifier; or

5 2. a) a HMWA according to claim 1; and

- b) a LMWA according to claim 1 pre blended with a core-shell impact modifier; or

10 3. a) a HMWA and LMWA blended according to claim 1; and

- b) a core-shell impact modifier.

15 32. Use of a composition according to any one of claims 1, 2, 3, 4-23 or 27-30 as a cycle time reduction composition.

20 33. Use of a composition according to any one of claims 1, 2, 3, 4-23 or 27-30 as a reduced cooling cycle time composition.

25 34. A reduced cycle time moulding composition comprising a composition according to any one of claims 1, 2, 3, 4-23 or 27-30.

30 35. A reduced cooling time moulding composition comprising a composition according to any one of claims 1, 2, 3, 4-23 or 27-30.

35 36. A process for reducing cycle time of a moulding composition comprising the step of:

injection moulding or extrusion moulding

30 a composition according to any one of claims 1, 2, 3, 4-23 or 27-30.

35 37. A process for reducing cooling cycle times of a moulding composition comprising the step of :

injection moulding or extrusion moulding


30 a composition according to any one of claims 1, 2, 3, 4-23 or 27-30.

2006238988 06 Jul 2012

42

38. A composition, process, method or use according to any one preceding claim, wherein the HMWA and LMWA have been produced by bulk, emulsion or suspension polymerisation.
- 5 39. A composition, process, method or use according to any one preceding claim, wherein the HMWA and the LMWA are simple single phase polymers.
- 10 40. A composition, process, method or use according to any one preceding claim, substantially as herein described with reference to any one of the Examples.

Figure 1



5

Figure 2




Figure 3




Figure 4

