

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
9 December 2004 (09.12.2004)

PCT

(10) International Publication Number
WO 2004/106838 A1

(51) International Patent Classification⁷: **F41H 5/04**

(21) International Application Number:
PCT/CA2004/000779

(22) International Filing Date: 27 May 2004 (27.05.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/474,519 29 May 2003 (29.05.2003) US

(71) Applicant (for all designated States except US): **BARR-DAY, INC.** [CA/CA]; 75 Moorefield Street, P.O. Box 790, Cambridge, Ontario N1R 5W6 (CA).

(72) Inventor; and

(75) Inventor/Applicant (for US only): **CUNNINGHAM, David, Verlin** [CA/CA]; 1310 Godwick Drive, Mississauga, Ontario L5N 7X4 (CA).

(74) Agents: **STEWART, Michael, I.** et al.; Sim & McBurney, 6th Floor, 330 University Avenue, Toronto, Ontario M5G 1R7 (CA).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: UNIQUE BALLISTIC COMPOSITION

(57) Abstract: A ballistic composite comprises multiple layers of a fabric having unidirectional ballistic resistant yarns in at least two layers and a resin layer between each pair of such multiple layers adhered to the ballistic resistant yarns but not encapsulation the same and not penetrating the layer of fabric. The ballistic yarn layers are at $90^\circ \pm 5^\circ$ with respect to each other and the ballistic resistant yarns are stabilized by being woven in a second fabric. The second fabric is formed of yarns having a substantially lower tenacity and tensile modulus than the ballistic resistant yarn. The ballistic resistant yarns have a tenacity of at least about 15 grams per denier and a modulus of at least about 40 grams per denier. The resin in the resin layer has a modulus of at least about 7000 psi.



WO 2004/106838 A1

TITLE OF INVENTIONUNIQUE BALLISTIC COMPOSITIONREFERENCE TO RELATED APPLICATION

[0001] This application claims priority pursuant to 35 USC 119(e) from US Provisional Patent Application No. 60/474,519 filed May 29, 2003.

FIELD OF INVENTION

[0002] The present invention relates to ballistic resistant composites.

BACKGROUND TO THE INVENTION

[0003] The use of flexible resins with fabrics woven from high performance fibers to fabricate composite armor panels has been the subject of much research and many patents. The general consensus of this body of work is that the more flexible the resin system used in the fabrication of the composite, the better the ballistic properties of the resulting panel. In addition, adhesion of the resin to the ballistic yarn should be sufficiently poor that delamination in the composite occurs during the ballistic event. This requirement can be ignored if the resin in the composite ruptures at a sufficiently low strength to allow energy to dissipate during the ballistic event. Given this basic knowledge of armor design, the design of an armor laminate then becomes a tradeoff of ballistic properties of the panel against the structural requirements for the use of the panel. U.S. Patent No. 3,000,772, Lunn, 1961, is one of the first patents to discuss the requirement for a flexible resin system for superior ballistic performance. This patent covers the use of a polyethylene film with a unidirectional glass fabric. The glass fabric has glass yarn in the warp direction and a secondary yarn in the fill direction to form the fabric. The fabric then pressed into a laminate after orienting succeeding layers of fabric at 90 degrees to the fabric layer above and below it. This is a standard practice known as "cross plying" the layers. U.S. Patent No. 3,956,447, Denommee, 1976, discusses the fabrication of a ballistic helmet for the US military using a thermoset or thermoplastic resin. In this patent, the preferred resin system for the helmet is a PVB/phenolic system. Roy Liable, a researcher at the US Army's Research, Engineering and Development

Center in Natick, Massachusetts, in his book, *Ballistic Materials and Penetration Mechanics*, Elsevier Scientific Publishing Company, 1980, page 108, discusses that, during the helmet development, it was discovered that the phenolic resin by itself was too stiff to produce good ballistic results and that the PVB component of the system was added to introduce some elongation and flexibility into the resin to improve the ballistic properties while maintaining the rigidity required of a helmet.

[0004] Several patents cover the use of thermoplastic resins and films in the composites. Lancaster et al, U.S. Patent No. 4,678,702, 1987, teaches the use of Surlyn as the resin where a Surlyn film form flows into the woven fabric under heat and pressure to encapsulate the yarn and form flexible ballistic composite. Donovan, U.S. Patent No. 4,574,105, 1986, teaches the use of alternating layers of nylon and Kevlar where the nylon adheres to the woven Kevlar under heat and pressure to form the composite but the nylon does not penetrate the fabric. A series of patents by Andrew Park (U.S. Patents Nos. 5,437,905; 5,443,882; 5,443,883; 5,547,536; 5,635,288; 5,935,678) covers the use of films between the layers of unidirectional yarn where the film is used to hold cross-ply layers of the yarn together without substantially penetrating the layers. Allied-Signal, U.S. Patent No. 4,623,514, cover the substantial encapsulation of high performance yarns in cross-ply layers of unidirectional yarns with a resin with modulus less than 6000 psi.

SUMMARY OF INVENTION

[0005] The subject of this patent application is the use of thermoplastic resins with a unique fabric to produce a superior ballistic resistant composite. The resins have good adhesion to the ballistic resistant yarns and high tensile modulus. This combination of properties, when used with a conventional woven fabric or a cross-ply unidirectional fabric, would not result in a superior ballistic composite. The unique fabric of this invention is the subject of a US Patent Application No. 10/135,573 filed May 1, 2002 (WO 02/090866), assigned to the assignee hereof and the disclosure of which is incorporated herein by reference. This fabric is a quasi-unidirectional fabric with the ballistic yarns held in a 0/90 unidirectional orientation by a low modulus, high elongation yarn of relatively small diameter. This fabric is sold by Barrday Inc., the

assignee hereof, under the trade name Sentinel fabrics. The ballistic yarn woven in this fabric may be any high strength yarn with a tenacity of at least about 15 grams per denier and a modulus of at least about 400 grams per denier. All of the commercially-available ballistic resistant yarns have been woven into Sentinel fabrics. The available resins that perform adequately in this invention are any resin which will adhere to the high performance yarns and have a modulus of at least about 7,000 psi. Ballistic resistant composites have not previously been constructed using resin having such modulus values, including those described in the aforementioned 10/135,573 (WO 02/090866).

[0006] In one aspect of the present invention, there is provided a ballistic resistant composite comprising multiple layers of a fabric having unidirectional ballistic resistant yarns in at least two layers, the ballistic yarn layers being at $90^\circ \pm 5^\circ$ with respect to each other, the ballistic resistant yarns being stabilized by being woven in a second fabric, the second fabric being formed of yarns having a substantially lower tenacity and tensile modulus than the ballistic resistant yarn, the ballistic resistant yarn having a tenacity of at least about 15 grams per denier and a modulus of at least about 40 grams per denier, and a resin layer between each pair of such multiple layers adhered to the ballistic resistant yarns but not encapsulating the same and not penetrating the layer of fabric, the resin in the resin layer having a modulus of at least about 7000 psi.

GENERAL DESCRIPTION OF INVENTION

[0007] The basic requirement that the yarns be free to move and that the composite delaminate during the ballistic event has not been ignored in this invention. Rather the freedom for the yarn to move and for the composite to delaminate has been provided by the low modulus encapsulating yarn of the Sentinel fabric rather than the resin system between the fabric layers. Two layers of the very inflexible ballistic yarns, strongly adhered together, produce a rigid but very thin composite. A stack of such thin, rigid layers, even when the rigid layers are bonded by a flexible yarn produces a rigid, hard composite. In a composite composed of Sentinel fabric layers, one of the layers of yarn of this bonded pair is the top unidirectional layer of a Sentinel fabric and the other strongly adhered yarn layer is the bottom layer of a second Sentinel fabric. In the present invention, the Sentinel fabrics are layered with the same surface up and the

fabrics are all oriented with the warp yarns in the same direction. This arrangement results in a composite with the adjacent unidirectional ballistic yarn oriented 0/90 degrees. The resin adheres together adjacent fabric layers forming rigid layers of laminated 0/90 layers. These laminated 0/90 layers are connected by the low modulus encapsulating yarn to the layer above and below it. The integrity and properties of the resulting composite is determined by the resin, the amount of resin and the encapsulating yarns.

[0008] The flexible encapsulating yarn provides the required movement and delamination of the composite layers and allows the use of resins and adhesives with more aggressive adhesion than that previously seen in ballistic composites. The flexible encapsulating yarn also allows the use of resins and adhesives with much higher tensile modulus than previously employed. The strength of the delamination layer can be controlled by the encapsulating yarn while the stiffness and hardness of the composite is determined by the type and amount of the thermoplastic resin and its adhesion to the fibers. The use of a high modulus resin having a modulus of at least about 7,000 psi, preferably in the range of about 25,000 to about 30,000 psi, with an aggressive bond to the yarn requires that the resin not penetrate the fabric nor substantially encapsulate the ballistic yarn. Should either of these occur the freedom of the ballistic yarn to move is impaired and the ability of the yarn to dissipate energy is substantially impaired.

[0009] The placement of the resin between the layers of the Sentinel fabrics can be controlled by several means. One method is to restrict the amount of resin used such that there is insufficient resin to wet more than the surface of the fabrics. In general, the amount of resin used is less than about 20 wt% of the weight of the composite. To produce a rigid composite with such a low amount of resin requires that the resin adhere very, very well to the ballistic yarn. The stiffness in the composite is then provided by two layers of high modulus yarns strongly adhered together. A second method is to use a resin with a high viscosity such that it does not flow at the temperature required for adhesion. Many resins in film form meet this requirement. Low density polyethylene is one of those films. The low density polyethylene softens and adheres to Sentinel fabrics woven with ultra high molecular weight polyethylene yarns but it does not substantially penetrate the fabric at the temperature required for adhesion. The ultra high molecular

weight polyethylene in this case includes ballistic yarns of the type described in more detail below and sold under the trade name Spectra and Dyneema. Other films, including thermoplastic nylon films and ionomer and polyurethane films, perform in a similar fashion.

[0010] The ability to control the stiffness and the hardness of the laminate while maintaining the ballistic performance has several advantages. When the threat to be stopped is a relatively deformable threat, such as a 9 mm bullet, a hard laminate will deform the bullet more than a soft laminate and the larger deformed bullet is usually easier to stop. Similarly a relatively non-deforming bullet, such as a steel jacketed Tokarev bullet, is more easily stopped with a more flexible laminate where the bullet is more gradually stopped. The laminate may also be fabricated with layers of different hardness or stiffness. An example of this structure is a two component laminate used to back a ceramic armor plate. A stiff, hard laminate layer is placed directly behind the ceramic plate where it provides support to the ceramic during the ballistic event. The softer layers of the laminate form the back of the composite and absorb energy by delamination and thus minimize the energy transferred to the wearer of the armor plate.

[0011] The fabric layers used in the composite of the present invention have two unidirectional yarn layers at about 90 degrees to one another, stabilized by a second woven fabric and are fully described in the aforementioned US Patent Application No. 10/135,573 (WO 02/090866).

[0012] The ballistic resistant yarns used herein have a tenacity of about 15 grams per denier and a tensile modulus of at least about 400 grams per denier. Examples of ballistic resistant yarns which may be used herein are aramid fibers, extended chain polyethylene fibers, poly(p-phenylene-2, 6-benzobisoxazole) (PBO) fibers and glass fibers. Aramid and copolymer aramid fibers are produced commercially by Du Pont, Twaron Products and Teijin under the trade names Kevlar®, Twaron® and Technora®, respectively. Extended chain polyethylene fibers are produced commercially by Honeywell, DSM, Mitsui and Toyobo under the trade names Spectra®, Dyneema® and Telemilon® respectively. Polyethylene fiber and film are produced by Synthetic Industries and sold under the trade name Tensylon®. PBO is produced by Toyobo under

the trade name Zylon®. Liquid crystal polymers are produced by license under the trade name Vectron®. Other ballistic yarns may be used.

[0013] The stabilizing fibers, which may also be referred to as encapsulating yarns, may be selected from a wide range of fibers. Such fibers include natural fibers, such as cotton, wool, sisal, linen, jute and silk. The fibers also include manmade fibers and filaments, such as regenerated cellulose, rayon, polynosic rayon and cellulose esters. The fibers further include synthetic fibers and filaments, such as acrylics, for example, polyacrylonitrile, modacrylics, such as acrylonitrile-vinyl chloride copolymers, polyamide, for example, polyhexamethylene adipamide (nylon 66), polycaproamide (nylon 6), polyundecanoamide (nylon 11), polyolefin, for example, polyethylene and polypropylene, polyester, for example, polyethylene terephthalate, rubber, synthetic rubber and saran. Glass fiber also may be used. Denier of the encapsulating yarn may range from about 20 to about 1000 denier, depending on the sizes of the ballistic resistant fibers. In general, the encapsulating yarn has a diameter of up to about 14% of the diameter of the ballistic yarn, preferably about 2.5%. The encapsulating yarn generally has a maximum tensile modulus of 1777 grams per tex and a maximum strength at 3% elongation that is about 0.31% of the ballistic yarn.

[0014] In the fabric, the yarn count of the ballistic yarn per inch is about 40 to about 85%, preferably 50% plus or minus one, of the maximum tightness that can be woven in a plain weave fabric composed entirely of the same size ballistic yarn.

[0015] In the preferred embodiment of this invention, the fiber used is a high modulus polyethylene yarn (Spectra fiber) or polyaramid yarn (Kevlar fabric) having a tenacity of at least about 15 grams per denier and a tensile modulus of at least about 400 gram per denier and the resin is a low density polyethylene film, preferably with a density of about 0.92 to about 0.94 g/m³. The adhesion of low density polyethylene to high modulus extended chain polyethylene fibers is very good and cannot be explained by mere mechanical adhesion. The film appears to bond or diffuse into the structure of the extended chain. The laminate constructed of Spectra and low density polyethylene film shows remarkable improvements in performance over prior art structures. The total

thickness of the low density polyethylene film may have a thickness of about 0.35 to about 1.75 mil, which may be provided by a single ply or multiply plys.

EXAMPLES

Example 1

[0016] This Example is a comparative Example.

[0017] A plain weave Sentinel fabric, Barrday style number 4850, woven with 1200 denier Spectra® 900 yarn, was coated with a thermoplastic block copolymer, Kraton 1107D. The fabric had a pick count of 16 x 16 and an areal density of 184 g/m². This resin is the most common resin used in Spectra armor laminates and has a modulus of less than 6,000 psi. The Kraton coating was 18% by weight. A 16" x 16" laminate was fabricated using this coated fabric by consolidating 18 layers in a heated hydraulic press. The material was pressed at 150 PSI for 30 minutes at a temperature of 240 degrees Fahrenheit. The panel was cooled to 180 degrees Fahrenheit before the pressure was released. The finished composite was mounted in bracket and shot with no backing material with a 9 mm full metal jacket bullet. The V-50 of the panel was determined. The V-50 is the velocity where the probability of the bullet either stopping in the panel or passing through the panel was determined. The V-50 value is a common measure of the ballistic resistance of the panel and is known to those familiar to armor design. It is the velocity at which 50% of a given type of projectile, when striking the panel, will completely penetrate the target. The V50 of the panel was 1253 ft/sec.

Example 2

[0018] This Example illustrates one embodiment of the invention.

[0019] 18 layers of the fabric used in Example 1 were laminated with three layers of 0.35 mil low density polyethylene (PE) film between each layer of fabric. The low density polyethylene film had a density of 0.92 g/m³ and a modulus of 25,000 to 29,000 psi. The material was pressed at 150 PSI for 30 minutes at a temperature of 240 degrees Fahrenheit. The panel was cooled to 180 degrees Fahrenheit before the pressure was released. The finished composite was mounted in bracket and shot with no backing

material with a 9 mm full metal jacket bullet. The V-50 performance of the panel was determined. The V50 of the panel determined to be 1440 ft/sec., significantly high than the V-50 of Example 1.

Example 3

[0020] This Example illustrates a further embodiment of the invention.

[0021] 18 layers of the fabric used in Example 1 were laminated with one layer of 0.35 mil PE film between each layer of fabric. The PE film had the same properties as specified in Example 2. The material was pressed at 150 PSI for 30 minutes at a temperature of 240 degrees Fahrenheit. The panel was cooled to 180 degrees Fahrenheit before the pressure was released. The finished composite was mounted in bracket and shot with no backing material with a 9 mm full metal jacket bullet. The V-50 of the panel was determined. The V50 of the panel determined to be 1516 ft/sec. The V-50 of this panel was significantly high than the V-50 of Example 1.

Example 4

[0022] This Example illustrates a further embodiment of the invention.

[0023] 34 layers of a Sentinel fabric woven with 650 denier Spectra 1000 yarn were laminated with one layer of 0.35 mil PE film between each layer of fabric. The PE film had the same properties as specified in Example 2. The material was pressed at 150 PSI for 30 minutes at a temperature of 240 degrees Fahrenheit. The panel was cooled to 180 degrees Fahrenheit before the pressure was released. The finished composite was mounted in bracket and shot with no backing material with a 9 mm full metal jacket bullet. The V-50 of the panel was determined. The V50 of the panel determined to be 1699 ft/sec.

Example 5

[0024] This Example illustrates an additional embodiment of the invention.

[0025] 34 layers of the same Sentinel fabric as in Example 4, woven with 650 denier Spectra 1000 yarn, were laminated with three layers of 0.35 mil PE film between

each layer of fabric. The PE film had the same properties as specified in Example 2. The material was pressed at 150 PSI for 30 minutes at a temperature of 240 degrees Fahrenheit. The panel was cooled to 180 degrees Fahrenheit before the pressure was released. The finished composite was mounted in bracket and shot with no backing material with a 9 mm full metal jacket bullet. The V-50 of the panel was determined. The V50 of the panel determined to be 1440 ft/sec.

Example 6

[0026] This Example is a comparative Example.

[0027] A Spectra fabric, Barrday style number 4431, woven with 1200 denier Spectra 900 yarn, was laminated with a 0.35 mil PE film, having the same properties as specified in Example 1. A 16" x 16" laminate was fabricated using this laminated fabric by consolidating 15 layers in a heated hydraulic press. The material was pressed at 150 PSI for 30 minutes at a temperature of 240 degrees Fahrenheit. The panel was cooled to 180 degrees Fahrenheit before the pressure was released. The finished composite weighed 0.74 pounds per square foot. The composite was mounted in bracket and shot with no backing material with a 9 mm full metal jacket bullet. The V-50 of the panel was determined. The V50 of the panel was 1214 feet per second. The fabric of this construction is one of the more common Spectra fabrics commercially available.

Example 7

[0028] This Example illustrates a yet further embodiment of the invention.

[0029] 28 layers of a Sentinel fabric woven with 1200 denier Spectra 900 yarn were laminated with 1 layer of 0.35 mil PE film between each layer of fabric. The Spectra yarn and the PE film are the same as in the comparative Example 6. The material was pressed at 150 PSI for 30 minutes at a temperature of 240 degrees Fahrenheit. The panel was cooled to 180 degrees Fahrenheit before the pressure was released. The finished composite weighed 0.68 pounds per square foot. The composite was mounted in bracket and shot with no backing material with a 9 mm full metal jacket bullet. The V-50 of the panel was determined. The V-50 of the panel determined to be 1509 ft/sec. The V-50 of this panel was significantly high than the V-50 of the

comparative Example 6, even though the panel weighed 8% less than in the comparative Example 6.

Example 8

[0030] This Example is a comparative Example.

[0031] 12 layers of a Barrday fabric, style 2182, were laminated together with a proprietary Barrday resin system, Black Thermo. The fabric is a plain weave fabric woven from 3000 denier Kevlar 29 yarn. The Black Thermo resin system has a modulus of approximately 1000 psi. The material was pressed at 150 psi for 30 minutes at a temperature of 250 degrees Fahrenheit. The panel was cooled to 180 degrees Fahrenheit before the pressure was released. The pressed panel had a fiber areal density of 1.20 lbs/ft². The finished composite was mounted in a bracket and shot with no backing material with a 9 mm full metal bullet. The V-50 of the panel was determined. The V-50 of the panel was determined to be 1211 feet/second.

Example 9

[0032] This Example is a comparative Example.

[0033] 12 layers of a Barrday fabric, Style 2183, were laminated together with a proprietary Barrday resin system, Black Thermo. The fabric is a plain weave fabric woven from 3000 denier Twaron type 1000 yarn. The Black Thermo resin system has a modulus of approximately 1000 psi. The material was pressed at 150 psi for 30 minutes at a temperature of 250 degrees Fahrenheit. The panel was cooled to 180 degrees Fahrenheit before the pressure was released. The pressed panel had a fiber areal density of 1.20 lbs/ft². The finished composite was mounted in a bracket and shot with no backing material with a 9 mm full metal bullet. The V-50 of the panel was determined. The V-50 of the panel was determined to be 1188 feet/second.

Example 10

[0034] This Example illustrates a further embodiment of the invention.

[0035] 12 layers of a Barrday fabric, Style 2858, were laminated together with 1.75 mils of PE film having a density of 0.92 g/m^3 . The fabric is a Sentinel fabric woven from 3000 denier Kevlar 29 yarn. The PE film has a tensile modulus in the 25,000 to 29,000 psi range. The material was pressed at 150 psi for 30 minutes at a temperature of 240 degrees Fahrenheit. The panel was cooled to 180 degrees Fahrenheit before the pressure was released. The pressed panel had a fiber areal density of 0.99 lbs/ft^2 . The finished composite was mounted in a bracket and shot with no backing material with a 9 mm full metal bullet. The V-50 of the panel was determined. The V-50 of the panel was determined to be 1440 feet/second. The V-50 of this panel is significantly higher than that of the panels in Example 8 and Example 9 while the areal density of the panel is significantly lower.

SUMMARY OF DISCLOSURE

[0036] In summary of this disclosure, the present invention provides a novel ballistic composite with superior ballistic properties. Modifications are possible within the scope of this invention.

CLAIMS

What I claim is:

1. A ballistic resistant composite comprising:
multiple layers of a fabric having unidirectional ballistic resistant yarns in at least two layers, said ballistic yarn layers being at $90^\circ \pm 5^\circ$ with respect to each other, said ballistic resistant yarns being stabilized by being woven in a second fabric, said second fabric being formed of yarns having a substantially lower tenacity and tensile modulus than the ballistic resistant yarn, said ballistic resistant yarn having a tenacity of at least about 15 grams per denier and a modulus of at least about 40 grams per denier, and
a resin layer between each pair of such multiple layers adhered to said ballistic resistant yarns but not encapsulating the same and not penetrating the layer of fabric, the resin in said resin layer having a modulus of at least about 7000 psi.
2. The composite of claim 1 wherein the ballistic resistant yarn is selected from the group consisting of aramid fibers, extended chain polyethylene fibers poly(p-phenylene-2, 6-benzobisoxazole) (PBO) fibers and glass fibers.
3. The composite of claim 1 wherein the yarns of the second fabric having a denier in the range of about 20 to about 1000.
4. The composite of claim 1 wherein the yarns of the second fabric are selected from the group consisting of natural fibers and synthetic fibers.
5. The composite of claim 4 wherein the natural fiber is selected from the group consisting of cotton, wool, sisal, linen, jute and silk.
6. The composite of claim 4 wherein the synthetic fiber is selected from the group consisting of regenerated cellulose, rayon, polynosic rayon, cellulose ester, acrylics, modacrylics, polyamides, polyolefins, polyester, rubber, synthetic rubber and saran.
7. The composite of claim 4 wherein the yarns of the second fabric are glass.
8. The composite of claim 4 wherein the yarns of the second fabric are selected from the group consisting of polyacrylonitrile, acrylonitrile-vinyl chloride copolymers, polyhexamethylene adipamide, polycaproamide, polyundecanoamide, polyethylene

adipamide, polycaproamide, polyundecanoamide, polyethylene, polypropylene and polyethylene terephthalate.

9. The composite of claim 1 wherein the yarns of the second fabric have high elongation.

10. The composite of claim 1 wherein the second yarn breaks prior to ballistic resistant yarns on impact of a projectile on the composite.

11. The composite of claim 1 wherein yarn of the second fabric has a diameter that is up to about 14% of the diameter of the ballistic yarn.

12. The composite of claim 11 wherein the yarn of a second fabric has a diameter that is about 2.5% of the diameter of the ballistic yarn.

13. The composite of claim 1 wherein the yarn of the second fabric has a maximum tensile modulus of 1777 grams per tex and a maximum strength at 3% elongation that is 0.31% of the ballistic yarn.

14. The composite of claim 1 wherein the yarn of the second fabric has a maximum tensile modulus of 1777 grams per tex.

15. The composite of claim 1 wherein the yarn of the second fabric has a maximum strength at 3% elongation that is 0.31% of the ballistic yarn.

16. The composite of claim 1 wherein the yarn count of the ballistic yarn per inch is about 40 to about 85% of the maximum tightness that can be woven in a plain weave fabric composed entirely of the same size ballistic yarn.

17. The composite of claim 1 wherein the yarn count of the ballistic yarn per inch is 50% plus or minus one of the maximum tightness that can be woven in a plain weave fabric composed entirely of the same size ballistic yarn.

18. The composite of claim 1 wherein said resin layer is formed of resin having a modulus of about 25,000 to about 30,000.

19. The composite of claim 1 wherein the resin is the resin layer constitutes about 20 wt% or less of the weight of the composite.
20. The composite of claim 1 wherein the resin layer is formed from a film of the resin.
21. The composite of claim 1 wherein the ballistic resistant yarn is formed of polyethylene and the resin layer is formed from a film of low density polyethylene.
22. The composite of claim 21 wherein said low density polyethylene film has a thickness of about 0.35 to 1.75 mil.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/CA2004/000779

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 F41H5/04

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 F41H

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	WO 02/090866 A (CUNNINGHAM ; PRITCHARD (CA); BARRDAY INC (CA)) 14 November 2002 (2002-11-14) cited in the application abstract paragraphs '0018! - '0026!, '0053! - '0055!, '0063!, '0069!, '0072! claims 1-21	1-22
Y	US 5 677 029 A (PREVORSEK ET AL) 14 October 1997 (1997-10-14) abstract column 4, lines 34-60 column 11, lines 50-52 column 12, line 58 - column 13, line 58 column 18, line 66 - column 19, line 4 ----- -/--	1-22

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

° Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- * & * document member of the same patent family

Date of the actual completion of the international search

31 August 2004

Date of mailing of the international search report

08/09/2004

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Menier, R

INTERNATIONAL SEARCH REPORT

International Application No
PCT/CA2004/000779

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	<p>WO 02/14408 A (HONEYWELL INT INC) 21 February 2002 (2002-02-21) abstract page 1, line 24 - page 2, line 26 page 4, lines 8,9,30 page 7, lines 29,30 page 10, lines 14,15 page 13, lines 3,4</p>	18
A	<p>EP 0 683 374 A (PARK) 22 November 1995 (1995-11-22)</p>	
A	<p>US 3 000 772 A (LUNN RICHARD H) 19 September 1961 (1961-09-19)</p>	

INTERNATIONAL SEARCH REPORT

International Application No

PCT/CA2004/000779

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 02090866	A	14-11-2002	WO 02090866 A1	14-11-2002
			CA 2445774 A1	14-11-2002
			EP 1384041 A1	28-01-2004
			NZ 529472 A	19-12-2003
			US 2002164911 A1	07-11-2002
US 5677029	A	14-10-1997	NONE	
WO 0214408	A	21-02-2002	US 6642159 B1	04-11-2003
			AU 8481501 A	25-02-2002
			CA 2419755 A1	21-02-2002
			CN 1469803 T	21-01-2004
			EP 1315612 A2	04-06-2003
			JP 2004506539 T	04-03-2004
			WO 0214408 A2	21-02-2002
EP 0683374	A	22-11-1995	US 5437905 A	01-08-1995
			DE 69511001 D1	02-09-1999
			EP 0683374 A1	22-11-1995
			US 5952078 A	14-09-1999
			US 5443882 A	22-08-1995
			US 5443883 A	22-08-1995
			US 5547536 A	20-08-1996
			US 5635288 A	03-06-1997
			US 5935678 A	10-08-1999
US 3000772	A	19-09-1961	NONE	