



(12) **DEMANDE DE BREVET CANADIEN**
CANADIAN PATENT APPLICATION

(13) **A1**

(86) Date de dépôt PCT/PCT Filing Date: 2018/06/27
(87) Date publication PCT/PCT Publication Date: 2019/01/03
(85) Entrée phase nationale/National Entry: 2019/10/17
(86) N° demande PCT/PCT Application No.: IB 2018/054743
(87) N° publication PCT/PCT Publication No.: 2019/003130
(30) Priorité/Priority: 2017/06/27 (IT102017000071472)


(51) Cl.Int./Int.Cl. *B32B 5/02*(2006.01),
B32B 1/08(2006.01), *B32B 25/12*(2006.01),
B32B 25/14(2006.01), *B32B 25/16*(2006.01),
B32B 27/12(2006.01), *B32B 27/30*(2006.01),
B32B 27/36(2006.01), *B32B 27/40*(2006.01),
B32B 5/12(2006.01)

(71) Demandeur/Applicant:
FITT S.P.A., IT

(72) Inventeurs/Inventors:
CEGALIN, ALESSANDRO, IT;
BATTAGLIA, LUCA, IT;
VIGOLO, VALENTINO, IT

(74) Agent: RIDOUT & MAYBEE LLP

(54) Titre : TUYAU FLEXIBLE RENFORCE UTRALEGER
(54) Title: ULTRA-LIGHTWEIGHT REINFORCED FLEXIBLE HOSE



(57) Abrégé/Abstract:

A ultra-lightweight reinforced flexible hose for transporting fluids, in particular a flexible garden hose for transporting water, comprising: at least one inner tubular layer (2) made of at least one first elastomeric or thermoplastic elastomer material; at least one outer cover layer (3) made of at least one second elastomeric or thermoplastic elastomer material; and at least one reinforcement layer (4) interposed between the inner (2) and outer (3) layer. The at least one reinforcement layer (4) consists of rigid or slightly elastic textile threads having at least partially a respective first and second predetermined inclination (α , β) mutually opposite with respect to said axis (X), each of the first and second inclinations (α , β) being comprised between 45° and 55° with respect to said axis (X).

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
03 January 2019 (03.01.2019)

(10) International Publication Number
WO 2019/003130 A1

(51) International Patent Classification:

B32B 5/02 (2006.01) *B32B 27/12* (2006.01)
B32B 5/12 (2006.01) *B32B 27/30* (2006.01)
B32B 25/12 (2006.01) *B32B 27/36* (2006.01)
B32B 25/14 (2006.01) *B32B 27/40* (2006.01)
B32B 25/16 (2006.01) *B32B 1/08* (2006.01)

(74) Agent: **AUTUORI, Angelo**; C/O EUREKA IP CONSULTING, Via Monte Cengio, 32, 36100 Vicenza (IT).

(21) International Application Number:

PCT/IB2018/054743

(22) International Filing Date:

27 June 2018 (27.06.2018)

(25) Filing Language:

Italian

(26) Publication Language:

English

(30) Priority Data:

102017000071472 27 June 2017 (27.06.2017) IT

(71) Applicant: **FITT S.P.A.** [IT/IT]; Via Piave, 8, 36066 Sandrigo (VI) (IT).


(72) Inventors: **CEGALIN, Alessandro**; Via Cimone, 12, 36100 Vicenza (VI) (IT). **BATTAGLIA, Luca**; Via Romagna, 1, 36061 Bassano Del Grappa (VI) (IT). **VIGOLO, Valentino**; Via Molinetto, 56, 36030 Caldognio (VI) (IT).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JO, JP, KE, KG, KH, KN, KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

(54) Title: ULTRA-LIGHTWEIGHT REINFORCED FLEXIBLE HOSE

(57) **Abstract:** A ultra-lightweight reinforced flexible hose for transporting fluids, in particular a flexible garden hose for transporting water, comprising: at least one inner tubular layer (2) made of at least one first elastomeric or thermoplastic elastomer material; at least one outer cover layer (3) made of at least one second elastomeric or thermoplastic elastomer material; and at least one reinforcement layer (4) interposed between the inner (2) and outer (3) layer. The at least one reinforcement layer (4) consists of rigid or slightly elastic textile threads having at least partially a respective first and second predetermined inclination (α , β) mutually opposite with respect to said axis (X), each of the first and second inclinations (α , β) being comprised between 45° and 55° with respect to said axis (X).



WO 2019/003130 A1 

Published:

— *with international search report (Art. 21(3))*

ULTRA-LIGHTWEIGHT REINFORCED FLEXIBLE HOSE**DESCRIPTION**Field of the invention

The present invention generally regards the technical field of flexible hoses, and it generally regards a reinforced flexible hose for transporting fluids, in particular a garden hose for transporting water.

Definitions

In the present document, the expression "textile yarn" or its derivatives is used to indicate an elongated thread-like element of any shape and made of any material, as long as the dimension of the length considerably prevails over. For example, the textile yarn may be a polymeric yarn, which may have a unitary structure or it may in turn consist of the joining of several elementary yarns, or a textile band of any shape.

In the present document, the expression "spiralled textile layer" or "spiralling" or its derivatives is used to indicate a layer consisting of a single yarn spiral-wound on the load-bearing layer with a predetermined pitch or groups of yarns spiral-wound on the load-bearing layer not superimposed on each other and preferably parallel.

In the present document, the expression "cross-hatched textile layer" or "cross-hatching" or its derivatives is used to indicate a layer consisting of at least two yarns or groups of yarns spiral-wound on the load-bearing layer with opposite inclinations and mutually superimposed but not connected. Thus, a cross-hatching is made up of two or more superimposed spiralings.

In the present document, the expression "knitted textile layer with chain stitches of the tricot type" and the like is used to indicate a layer consisting of at least two yarns or groups of yarns arranged on the load-bearing layer and mutually intertwined to form a plurality of chain stitches of the "tricot" type.

In the present document, the expression "chain stitches of the tricot type" and the like is used to indicate the portion of textile yarn (or a set of yarns grouped in a single yarn) which is intertwined with adjacent wires to form a generally annular-shaped loop.

In the present document, the expression "row of stitches" and the like of a

knitted textile layer with chain stitches of the tricot type is used to indicate the line defined by the “chain stitches of the tricot type” concatenated to each other.

In the present document, the expression “courses of stitches” and the like of a knitted textile layer with chain stitches of the tricot type is used to indicate the portion of textile yarn (or set of yarns grouped into a single yarn) mutually connecting two consecutive “chain stitches of the tricot type” along the same yarn.

In the present document, the expression “compatible materials” or its derivatives is used to indicate materials chemically/physically compatible with each other, i.e. materials that, once coupled, form a joint suitable to support the transfer of pulling or cutting through the contact surfaces. Thus, the maximum compatibility will be observed in identical materials or materials having matrices of the same base.

In the present document, the expression “matrix” of a polymer or its derivatives is used to indicate a polymeric material capable of providing the molecular structure of the finished product.

In the present document, the expression “matrix based on” or its derivatives followed by the name of a given polymeric material is used to indicate a polymeric material capable of providing the molecular structure of the given polymeric material, whose name follows the phrase “matrix based on”, to the finished product.

In the present document unless otherwise specified, the expression “inclination” or its derivatives of a layer consisting of textile threads or part thereof is used to indicate the inclination of the textile layer or part thereof with respect to the axis of the hose.

In the present document, unless otherwise specified, the expression “rigid textile threads” or its derivatives is used to indicate textile threads having an elongation at break - measured according to BISFA (Cap 7) - lesser than 10%, and preferably lesser than 7%.

In the present document, unless otherwise specified, the expression “slightly elastic textile threads” or its derivatives is used to indicate textile threads having an elongation at break - measured according to BISFA (Cap 7) - higher than 10% and lesser than 25%, and preferably lesser than 20%.

State of the Art

Reinforced flexible hoses, in particular irrigation hoses or garden hoses, including at least one inner layer or substrate, at least one outer layer or cover and at least one reinforced textile layer, are known.

The inner and outer layers are generally made of polymeric material, for example plasticised PVC, while the reinforcement layer consists of textile threads made of polymeric material, for example polyester.

In order to resist to the stresses due to the overlying layers, the inner layer usually has a greater hardness than the outer layer. Generally, the Shore A hardness of an inner layer amounts to 75 – 85, while the Shore A hardness of the outer layer amounts to 60 – 70.

Such known hoses have the renowned disadvantage of excessive weight per linear metre. This makes the hose poorly practical to handle and generally poorly appealing to the user.

As a matter of fact, whereas the polymeric materials the hose is made of confer good mechanical features on the one hand, they all have a considerably high density on the other hand, which translates into the aforementioned high weight.

Summary of the invention

An object of the invention is to at least partly overcome the drawbacks outlined above, by providing a reinforced flexible hose that is highly efficient and relatively economic.

Another object of the invention is to provide a ultra-lightweight reinforced flexible hose.

Another object of the invention is to provide a reinforced flexible hose with a good dimensional stability.

These and other objects that will be more apparent hereinafter, are attained by the reinforced flexible hose according to what is described, illustrated and/or claimed herein.

Advantageous embodiments of the invention are defined according to the dependent claims.

Brief description of the drawings

Further characteristics and advantages of the invention will be more

apparent in light of the detailed description some preferred but non-exclusive embodiments of the invention, illustrated by way of non-limiting example with reference to the attached drawings, wherein:

FIG. 1 is a schematic view of a first embodiment of the reinforced flexible hose **1**;

FIG. 2 is a schematic view of a second embodiment of the reinforced flexible hose **1**.

Detailed description of a preferred embodiment

With reference to the aforementioned figures, the flexible hose according to the invention, indicated in its entirety with reference number **1**, may be particularly useful for transporting liquids in general. For example, the flexible hose **1** may be a garden hose or irrigation hose for transporting water, in particular potable water.

In a preferred but non-exclusive embodiment, the flexible hose **1** may consist of an inner tubular layer **2**, which may for example be made of elastomer or thermoplastic elastomer, an outer cover tubular layer **3**, which may for example be made of elastomer or thermoplastic elastomer and, interposed therebetween, one or more reinforcement layers **4**, which may for example be made of polyester yarn.

It is clear that the reinforcement layer **4** may be arranged on the layer which supports it, for example on the inner layer **2**, so as to leave the portions thereof - generally square-shaped, rectangular-shaped or rhomboid-shaped - free. Thus, the overlying layer, for example the outer layer **3**, may be coupled with the underlying one, for example by means of gluing or melting materials if compatible, at such free portions.

In other words, the inner **2** and outer **3** tubular layers may be integrally joined to each other to define a unitary tubular element, the reinforcement layer **4** being embedded therein.

The inner tubular layer **2**, which may define the axis **X** of the hose **1**, may be designated to come into contact with the liquid to be transported, while the outer cover layer **3** may be designated to be grasped by a user.

Other additional layers, both textile and polymeric, may also be provided for between the various layers, without departing from the scope of protection outlined by the attached claims.

The elastomer or thermoplastic elastomer of the inner layer **2** and of the outer layer **3** may be selected from the group consisting of: vulcanised thermoplastic elastomers (TPE-V), polyurethane-based thermoplastic elastomers (PU), polyester-based thermoplastic elastomers (TPE-E), styrene-based thermoplastic elastomers (TPE-S).

For example, the material of the inner layer **2** and outer **3** layers may be a styrene-based thermoplastic elastomer (TPE-S) having a polypropylene-based matrix (PP), for example Nilflex® SH (Taro Plast SpA).

It is clear that the materials that the inner **2** and outer **3** layers are made of could be more or less the same without departing from the scope of the attached claims.

The materials of the inner **2** and outer **3** layers may preferably be mutually compatible.

The materials of the inner **2** and outer **3** layers may advantageously have a maximum Shore A hardness of 60 measured in accordance with the ASTM D 2240 (3'') method. Thus, the materials will be soft to touch and particularly light.

More in particular, the material of the outer layer **3** may have a maximum Shore A hardness - measured in accordance with the ASTM D 2240 (3'') method - of 60, and preferably a maximum Shore A hardness - measured in accordance with the ASTM D 2240 (3'') method - of 55.

On the other hand, the material of the inner layer **2** may have a maximum Shore A hardness - measured in accordance with the ASTM D 2240 (3'') method - of 60 Shore A, and preferably a maximum Shore A hardness - measured in accordance with the ASTM D 2240 (3'') method - of 55 Shore A.

Preferably, the material of the inner layer **2** may have a maximum Shore A hardness - measured in accordance with the ASTM D 2240 (3'') method - of 50 Shore A, and even more preferably a maximum Shore A hardness - measured in accordance with the ASTM D 2240 (3'') method - of 45 Shore A.

The aforementioned hardness may be combined in any manner, without departing from the scope of protection of the attached claims.

For example, the material of the outer layer **3** may have a maximum Shore A hardness - in accordance with the ASTM D 2240 (3'') method - of 55, while the

material of the inner layer **2** may have a Shore A hardness - measured in accordance with the ASTM D 2240 (3'') method - of 60 Shore A.

In another example, the material of the outer layer **3** may have a maximum Shore A hardness - in accordance with the ASTM D 2240 (3'') method - of 50, while the material of the inner layer **2** may have a Shore A hardness - measured in accordance with the ASTM D 2240 (3'') method - comprised between 45 and 55 Shore A.

Generally, the material of the outer layer **3** may have a Shore A hardness - measured in accordance with the ASTM D 2240 (3'') method - comprised between 40 and 60, preferably a Shore A hardness - measured in accordance with the ASTM D 2240 (3'') method - comprised between 45 and 60, and even more preferably a Shore A hardness - measured in accordance with the ASTM D 2240 (3'') method - comprised between 50 and 60.

This enables obtaining a hose **1** with good resistance against abrasion, though with a material extremely soft to touch.

Suitably, the material of the inner layer **2** may have a maximum Shore A hardness - measured in accordance with the ASTM D 2240 (3'') method - of 50, preferably comprised between 30 and 50 and even more preferably comprised between 35 and 45.

This will enable lightening the hose **1**.

Advantageously, the material of the outer layer **3** may have a hardness higher than or equal to the hardness of the material of the inner layer **2**, so as to obtain a very light hose capable of resisting against abrasion.

For example, in such hose the material of the outer layer **3** may have a maximum Shore A hardness - in accordance with the ASTM D 2240 (3'') method - of 60, while the inner layer **2** may have a Shore A hardness - measured in accordance with the ASTM D 2240 (3'') method - of 50 Shore A.

Suitably, the materials of the inner **2** and outer **3** layer may have a density lesser than 1.20 g/cm³, preferably lesser than or equal to 1.05 g/cm³.

In a preferred but non-exclusive embodiment, the inner layer **2** may have a thickness **S2** comprised between 1.5 mm and 2.5 mm, and preferably comprised between 1.6 mm and 2 mm, while the outer layer **3** may be a film having a thickness

S3 comprised between 0.05 mm and 0.5 mm, and preferably comprised between 0.1 mm and 0.4 mm.

Preferably, the outer layer **3** may be obtained according to the disclosures outlined in the international patent application PCT/IB2014/067091.

Thanks to the characteristics outlined above, the flexible hose **1** will be particularly light and easy to use.

Furthermore, the materials used will be pleasant and soft to touch and they will avoid dirtying the hose when dragging it on wet grounds.

On the other hand, such materials under the internal pressure of the fluid transported by the hose would tend to dilate, extending and dilating the hose diametrically.

On the contrary, the reinforcement layer **4** is configured to oppose the dilation of such materials, so that the pressurised hose **1** is substantially inextensible.

In particular, the one or more reinforcement layers **4** may consist of rigid, i.e. non-elastic or slightly elastic textile threads, which may have an elongation at break - measured according to BISFA (Cap 7) - lesser than 25%, and a toughness - measured according to BISFA (Cap 7) - of at least 50 cN/tex.

Suitably, the rigid or slightly elastic textile threads may have at least partially one respective first and second predetermined inclination α , β mutually opposite with respect to the axis **X**.

For example, as illustrated in FIG. 1, in a first preferred but non-exclusive embodiment, the reinforcement layer **4** may be a braiding or double spiral.

In a further first preferred but non-exclusive embodiment, for example as illustrated in FIG. 2, the reinforcement layer **4** may be a double knitting with chain stitches of the tricot type obtained with plain stitch.

Advantageously, such double knitting may be obtained according to the disclosures provided for by the Italian patent application number 102017000002927, on behalf of the Applicant.

In such preferred but non-exclusive embodiment, the reinforcement layer **4** may include two textile layers **4'**, **5** of the knitted type with chain stitches of the tricot type, indicated with **6** for the first textile layer **4'** and with **6'** for the second

textile layer 5. Both textile layers 4', 5 may have rows of stitches, indicated with 7 for the first textile layer 4' and with 7' for the second textile layer 5, and rows of stitches respectively indicated with 8, 8'.

The courses of stitches 8 of the first textile layer 4' may all be substantially parallel to each other, same case applying to the courses of stitches 8' of the second textile layer 5, and they may all be substantially parallel to the axis X of the hose 1.

The rows of stitches 7, 7' of the textile layers 4', 5 may instead have mutually opposite inclinations α , β with respect to the axis X of the hose.

On the other hand, in a further preferred but non-exclusive embodiment, such double knitting may have chain stitches of the tricot type obtained according to the disclosures of the European patent application n° EP0527512.

On the other hand, in a further preferred but non-exclusive embodiment, such double knitting may have chain stitches of the tricot type obtained with lock stitch, and it may for example be obtained according to the disclosures of the patent application n° EP0623776.

In order to avoid deformations of the flexible hose 1 due to the internal pressure, the first and the second inclination α , β may be comprised between 45° and 55° with respect to the axis X.

As a matter of fact, such inclination will enable the reinforcement layer 4 to effectively oppose the deformations caused by the internal pressure both in the axial and radial direction.

As a matter of fact, as mentioned above, without the reinforcement layer 4 configured as described above, under pressure the flexible hose 1 would tend to extend and expand considerably due to the relatively low hardness of the materials used.

More in particular, the inclinations α , β described above will enable to obtain a hose 1 capable - under the operating pressure of 2 bars - of increasing the maximum length thereof by 1.1 times with respect to the initial length thereof, i.e. the length of the hose with no fluid flowing through it, preferably the maximum of 1.05 times with respect to the initial length thereof.

Furthermore, the inclinations α , β described above will enable to obtain a hose 1 capable - under the operating pressure of 2 bars - of increasing the maximum

inner diameter thereof by 1.1 times with respect to the initial inner diameter, preferably the maximum of 1.05 times with respect to the initial inner diameter.

Thus, thanks to the characteristics described above, the flexible hose **1** will be light and easy to handle, and it will simultaneously have a good dimensional stability.

In a per se known manner, the flexible hose **1** may be obtained by extruding the first elastomeric or thermoplastic elastomer material to obtain the inner **2**, obtaining the reinforcement layer **4** above the latter and extruding the second elastomeric or thermoplastic elastomer material above the latter to obtain the outer layer **3**.

In light of the above, it is clear that the invention attains the pre-set objectives.

The flexible hose **1** is susceptible to numerous modifications and variants all falling within the inventive concept outlined in the attached claims. All details can be replaced by other technically equivalent elements, and the materials can be different depending on the needs, without departing from the scope of protection defined by the attached claims.

CLAIMS

1. A ultra-lightweight reinforced flexible hose for transporting fluids, comprising:

- at least one inner tubular layer (2) defining a longitudinal axis (X) susceptible to come into contact with the fluid, said at least one inner tubular layer (2) being made of at least one first elastomeric or thermoplastic elastomer material;
- at least one outer cover tubular layer (3) made of at least one second elastomeric or thermoplastic elastomer material; and
- at least one reinforcement layer (4) interposed between said inner layer (2) and outer layer (3);

wherein said at least one first and one second elastomeric or thermoplastic elastomer material have a maximum Shore A hardness of 60 measured in accordance with the ASTM D 2240 (3'') method;

wherein said at least one reinforcement layer (4) consists of rigid or slightly elastic textile threads having at least partially a respective first and second predetermined inclination (α , β) mutually opposite with respect to said axis (X), each of said first and second inclinations (α , β) being comprised between 45° and 55° with respect to said axis (X), so as to oppose the extension and expansion of the hose under pressure.

2. Hose according to claim 1, wherein said at least one first elastomeric or thermoplastic elastomer material has a maximum Shore A hardness - measured in accordance with the ASTM D 2240 (3'') method - of 55 Shore A, preferably a maximum Shore A hardness - measured in accordance with the ASTM D 2240 (3'') method - of 50 Shore A, even more preferably a Shore A hardness - measured in accordance with the ASTM D 2240 (3'') method - of 45 Shore A.

3. Hose according to claim 1 or 2, wherein said at least one first elastomeric or thermoplastic elastomer material has a Shore A hardness - measured in accordance with the ASTM D 2240 (3'') method - of 30 to 50, and preferably comprised between 35 and 45.

4. Hose according to claim 1, 2 or 3, wherein said at least one second elastomeric or thermoplastic elastomer material has a Shore A hardness - measured

in accordance with the ASTM D 2240 (3'') method - comprised between 40 to 60, and preferably comprised between 45 and 60 and even more preferably comprised between 50 and 60.

5. Hose according to claim 1, 2, 3 or 4, wherein said at least one elastomeric or thermoplastic elastomer material has a lesser or higher hardness than said at least one second elastomeric or thermoplastic elastomer material.

6. Hose according to one or more of the preceding claims, wherein said at least one first and at least one second elastomeric or thermoplastic elastomer material have a density lesser than 1.20 g/cm^3 , preferably lesser than or equal to 1.05 g/cm^3 .

7. Hose according to one or more of the preceding claims, wherein said at least one inner layer (2) has a thickness comprised between 1.5 mm and 2.5 mm, and preferably comprised between 1.6 mm and 2 mm, said at least one outer layer (3) being a film having a thickness comprised between 0.05 mm and 0.5 mm, and preferably comprised between 0.1 mm and 0.4 mm.

8. Hose according to one or more of the preceding claims, wherein said first and second inclination (α , β) are selected so that the pressurised hose is substantially inextensible.

9. Hose according to one or more of the preceding claims, wherein said first and second inclination (α , β) are selected so that under an operating pressure of 2 bars the hose increases the maximum length thereof by 1.1 times with respect to the initial length thereof, preferably to the maximum of 1.05 times with respect to the initial length thereof.

10. Hose according to one or more of the preceding claims, wherein said first and second inclination (α , β) are selected so that under an operating pressure of 2 bars the hose increases the inner diameter thereof by 1.1 times with respect to the initial inner diameter thereof, preferably to the maximum of 1.05 times with respect to the initial inner diameter.

11. Hose according to one or more of the preceding claims, wherein said at least one first and/or at least one second elastomeric or thermoplastic elastomer material is selected from the group consisting of: vulcanised thermoplastic elastomers (TPE-V), polyurethane-based thermoplastic elastomers (PU), polyester-

based thermoplastic elastomers (TPE-E), styrene-based thermoplastic elastomers (TPE-S).

12. Hose according to one or more of the preceding claims, wherein said textile threads are slightly elastic threads having an elongation at break - measured according to BISFA (Cap 7) - lesser than 25%.

13. Hose according to one or more of the preceding claims, wherein said rigid or slightly elastic textile threads have a toughness - measured according to BISFA (Cap 7) - of at least 50 cN/tex.



14. Hose according to one or more of the preceding claims, wherein said at least one inner tubular layer (2) and said at least one outer cover tubular layer (3) are joined to each other to form a unitary tubular element, said at least one reinforcement layer (4) being embedded in the latter.

15. Hose according to one or more of the preceding claims, wherein said at least one outer cover tubular layer (3) is intended to be grasped by a user.

16. Hose according to one or more of the preceding claims, wherein said at least one reinforcement layer (4) is a braiding or a double spiral.

17. Hose according to one or more of the preceding claims, wherein said at least one reinforcement layer (4) is a double knitting with chain stitches of the tricot type, of the lock stitch type or plain stitch type.

18. Hose according to one or more of the preceding claims, wherein the hose is a garden flexible hose for transporting water.



1/1

