



(22) Date de dépôt/Filing Date: 2009/03/31

(41) Mise à la disp. pub./Open to Public Insp.: 2009/10/01

(45) Date de délivrance/Issue Date: 2014/06/17

(30) Priorités/Priorities: 2008/04/01 (US61/041,347);
2008/10/01 (US12/243,271)

(51) Cl.Int./Int.Cl. *A63B 71/12* (2006.01),
A41D 13/05 (2006.01), *A63B 71/08* (2006.01)


(72) Inventeurs/Inventors:
MURPHY, TIMOTHY, US;
CRAM, DANIEL, US

(73) Propriétaire/Owner:
RUSSELL BRANDS, LLC, US

(74) Agent: MACRAE & CO.

(54) Titre : COQUILLE PROTECTRICE

(54) Title: IMPROVED ATHLETIC PROTECTION DEVICE



(57) Abrégé/Abstract:

An athletic protector, such as an athletic cup, with regions formed of the same compositional material, which is more rigid in one such region than in another such region.

Abstract

An athletic protector, such as an athletic cup, with regions formed of the same compositional material, which is more rigid in one such region than in another such region.

IMPROVED ATHLETIC PROTECTION DEVICE

FIELD OF THE INVENTION

[001] This invention relates to athletic protective devices and more particularly an improved athletic cup for protecting the genital/groin region, typically used by males. A method of manufacturing the improved athletic cup is also disclosed.

BACKGROUND ART

[002] Devices protecting the human body against injury during strenuous physical activity, such as participation in sporting events, are well known in the art. A common protection device is an athletic “cup” designed to protect the genital/groin region from impact. For example, baseball players wear athletic cups to protect against injury, such as may occur if they were to be struck in the groin by a baseball while at bat.

[003] Traditionally, athletic cups have been made of two or more pieces of different materials joined together in some manner. One of the purposes of the dual-component construction is to provide a soft or resilient structure adjacent the body of the wearer for comfort and/or impact absorption or dissipation, while retaining a hard shell to protect the genitals or groin. Most typically, the hard portion is a rounded cup-like structure having a central cavity. To this hard shell is typically affixed an outer ring of more flexible material for cushioning and comfort where the device seats against the body. These two components are typically of different composition, such as PVC, TPU, or other rigid plastic for the shell, with the flexible material being a foam, EVA, or a relatively soft rubber. These components may be joined by gluing, heat bonding, radio frequency welding, co-molding, or other techniques. In order to achieve both the protective effect of the hard shell and the

comfort effect of the softer more resilient material, it is believed that typical prior athletic cups use two structures bonded during the manufacturing process (or thereafter).

SUMMARY OF THE INVENTION

[004] In some aspects, the invention relates to an athletic protector characterized by a structure in which a compositional material has a lower density at one location than the same material at another location. In a more detailed aspect of some embodiments, a compositional material of the athletic protector is less dense at a location worn near to, or facing toward, the body than it is at a location further from, or facing away from, the body. In another aspect, the athletic protector is characterized by a structure in which a compositional material is softer, or more resilient, or less rigid, at one location than the same material at another location. In a more detailed aspect of some embodiments, a compositional material of the athletic protector is softer or more resilient or less rigid at a location worn near to, or facing toward, the body than it is at a location further from, or facing away from, the body

[005] In other aspects, the invention relates to a method of creating an athletic protector having areas of different density, softness, resilience, or rigidity which areas are formed from basically the same compositional material.

[006] According to one aspect of the present invention there is provided an athletic cup comprising a first region and a second region, the first region and the second region being formed of the same compositional material, wherein the first region is more rigid than the second region and wherein the first region and the second region are portions of a single structure.

[006.1] According to a further aspect of the present invention there is provided an athletic cup comprising a frontal region formed of a compositional material

characterized by a first density; and a resilient comfort edge formed of the compositional material characterized by a second density, which second density is different from the first density, wherein the frontal region and the resilient comfort edge are portions of a single structure.

[006.2] According to another aspect of the present invention there is provided an athletic cup molded from a single compositional material comprising: (a) A frontal region comprising: (i) granular ethylene vinyl acetate copolymer with a density of about 70 kg/m^3 , (ii) a convex outer surface with an apex that is about one-half (0.50) to one (1.0) centimeters thick, (iii) a concave inner surface; (iv) and a volume sufficient to enclose the wearer's genitals; (b) a resilient comfort edge wherein a distance between the outer surface and the inner surface at an apex is between about one-half and one centimeters; (c) a resilient comfort edge adapted to contact a wearer's skin, comprising ethylene vinyl acetate copolymer with a density of about 40 kg/m^3 .

[007] Other aspects and advantages of the invention will be apparent from the following description and the appended claims.

BRIEF DESCRIPTION OF DRAWINGS

- [008] It should be noted that identical features in different drawings are shown with the same reference numeral.
- [009] FIG. 1 shows a front view of the intended position of the improved athletic cup on the male body.
- [0010] FIG.2 shows a side view of FIG. 1.
- [0011] FIG. 3 shows a frontal view of the improved athletic cup.
- [0012] FIG. 4 shows a side view of the improved athletic cup.
- [0013] FIG. 5 shows a cross sectional view of the improved athletic cup.

DETAILED DESCRIPTION

[0014] The invention relates to an improved athletic cup for protecting the male genital/groin region and a method of manufacturing same. In an embodiment disclosed herein, the improved athletic cup is made of a single basic composition (i.e., one type of material). It may be molded into a single structure or component (i.e., one piece) and manufactured in a way such that it has varying degrees of hardness and flexibility at different regions. While the invention has been described with respect to a limited number of embodiments, those skilled in the art, having benefit of this disclosure, will appreciate that other embodiments can be devised which do not depart from the scope of the invention as discussed. Accordingly, the scope of the invention should be limited only by the claims as issued.

[0015] FIGS. 1 and 2 illustrate an intended position of the improved athletic cup **10** when worn by a male athlete. A resilient comfort edge **12** is also shown where the improved athletic cup **10** contacts the wearer's body.

[0016] One embodiment of the improved athletic cup **10** is depicted in FIGS. 3, 4 and 5. The improved athletic cup **10** has a frontal region **14** having a generally convex outer surface, outer regions **13**, a generally concave inner surface **18** and a volume sufficient to enclose the wearer's genitals. The frontal region **14** possesses the necessary strength or hardness to withstand a blow to the genital/groin region without significantly deforming or collapsing, thereby protecting the sensitive region. In this particular embodiment the frontal region **14** is about 0.75 to 1.0 centimeters thick at its apex. Further, this embodiment has a resilient comfort edge **12** along the entire length of the contact or interface area between the improved athletic cup **10** and the wearer. In this particular embodiment the outer regions **13** include transitory regions **20** in which a transition from the "harder" material of the frontal region **14** to the "softer" resilient comfort edge **12** occurs. Transitory regions **20** that are gradient in nature (where the transition from "harder" material to "softer"

material occurs gradually in indistinct steps) as well as step-like transitory regions **20** (where the transition from “harder” material to “softer” material occurs in one or more distinct steps, such that a line or small discrete juncture can be identified between areas of different hardness) are both within the scope of this disclosure. This embodiment also has a plurality of air vents **16a** through **16j**. Air vents **16a** thru **16d** are located directly above the resilient comfort edge **12**. In this particular embodiment the improved athletic cup **10** has a total of ten air vents.

[0017] When the improved athletic cup **10** suffers a blow, for example by a baseball, the blow will generally occur in a nearly horizontal line to the frontal region **14**. The frontal region **14** dissipates the force from the blow and redirects any remaining force away from the genital/groin region by transferring the force to the resilient comfort edge **12** and the transitory regions **20** thereby lessening or dampening the blow as well as transferring the force thereof to a less sensitive area of the wearer’s body. The improved athletic cup **10** may be anatomically designed to contact the wearer’s body with rounded edges and without any sharp corner intersections that could contact the wearer’s body. If the improved athletic cup **10** is struck at an angle and force to be twisted there are no sharp corners to be forced into the wearer’s body. In one embodiment, the athletic cup **10** can withstand of blow of approximately thirty five (35) pounds while providing sufficient protection to the wearer. The disclosure herein could of course be employed to provide a greater or lesser degree of protection.

[0018] In one embodiment, the improved athletic cup **10** is thicker at the apex of the frontal region **14** than at the outer regions **13** or transitory regions **20**. The variation in thickness may be stepwise, or may be a smooth transition. The improved athletic cup **10** may be constructed with ridges (not shown) about its surface or a portion thereof, for cosmetic purposes or force-dissipation, or collapse-influencing purposes.

[0019] In another or the same embodiment, the improved athletic cup **10**, inclusive

of the frontal region **14** and the resilient comfort edge **12** is made of a single composition, for example Ethylene vinyl acetate copolymer (EVA). The use of EVA is particularly well-suited to the construction, as it facilitates constructing a rigid frontal region **14** that may, if desired, be characterized by an outer surface that is slightly compressible. This may serve to blunt the force of impact by an object and thereby cooperate with the effect of the resilient comfort edge **12**. The EVA (or other compositional material) may be varied in density at different points on the improved athletic cup **10**. In the shown embodiment, the apex of the frontal region **14** (and if desired the outer regions **13**) is more dense than the resilient comfort edge **12**. If desired, one may coordinate variations in density with variations in thickness, as discussed in the preceding paragraph, to further enhance the differences of the various areas of the cup in terms of resilience, resistance to impact, and/or comfort.

[0020] A method of manufacturing the improved athletic cup **10** is also disclosed. Generally, the athletic cup **10** is manufactured from a single compositional material in multiple steps including: (1) providing the compositional material, which may desirably be in a granulated form, (2) optionally coloring the compositional material, (3) forming the hard frontal region, (4) forming the resilient comfort edge, (5) joining the hard frontal region and the resilient comfort edge and (6) tempering the athletic cup.

[0021] In one embodiment the improved athletic cup **10** may be manufactured in the following manner:

- (a) providing and optionally foaming the compositional material;
- (b) forming the hard frontal region by introducing a first portion of a compositional material (for example, EVA or others) into a pre-heated mold at a frontal region forming temperature in which air has been removed from the mold and pressurizing the mold to a first pressure for a first time period;

(c) forming the resilient comfort edge by introducing a second portion of the compositional material into a pre-heated mold at a resilient comfort edge forming temperature in which air has been removed from the mold and pressurizing the mold to a second pressure for a second time period;

(d) bringing the mold containing the hard frontal region into contact with the mold containing the resilient comfort edge;

(e) joining the hard frontal region with the resilient comfort edge by exposing the molds to a fusing temperature at a third pressure for a third time period; and

(f) tempering the athletic cup.

[0022] In one embodiment, the compositional material is EVA, the first portion of compositional material is added to a pre-heated mold at a frontal region forming temperature of about two hundred (200) degrees Celsius at eight (8) Pascals (Pa) of pressure for about two (2) minutes; the EVA melts in the hot mold and flows to the bottom side of the mold forming the harder frontal region **14** of the improved athletic cup **10**, next, the second portion of compositional material to a pre-heated mold at a resilient comfort edge forming temperature of about three hundred (300) degrees Celsius at thirteen (13) Pa of pressure for approximately two (2) minutes; which after injection melts to form the resilient comfort edge **12**. Then, the mold containing the frontal region and the mold containing the resilient comfort edge are brought into contact with one another. The molds are exposed to a fusing temperature of about one hundred seventy-five degrees (175) Celsius at a pressure of about thirteen (13) Pa for approximately four (4) minutes. The region of contact or interface between the deposit of compositional material introduced in the first form and the deposit of compositional material introduced in the second form forms the transitory regions **20**. Finally, the fully formed improved athletic cup **10** is tempered.

[0023] In another embodiment, the compositional material is EVA, in one

embodiment being granular EVA of a density of about 75 kg/m^3 (hereinafter the measure of the density of the compositional material is referred to as “C”) granular form for the first form, and using a first temperature of about two hundred (200) degrees Celsius; the EVA melts in the hot mold and flows to the bottom side of the mold forming the harder frontal region **14** of the improved athletic cup **10**, the first temperature is raised to the second temperature of about three hundred (300) degrees Celsius. In this embodiment of the method, the second portion of the compositional material (which may be the same material as the first portion of the compositional material, e.g., again EVA) may be in the form of 40C granular EVA form, which after injection melts to form the resilient comfort edge **12**, and the second temperature is lowered to a curing temperature for about one (1) minute. The region of contact or interface between the deposit of compositional material introduced in the first form (such as 75C granular EVA) and the deposit of compositional material introduced in the second form (such as 40C granular EVA) forms a transitory region **20**.

[0024] In one embodiment, the hard frontal region **14** is made from granular EVA with a density of about 70C. In the same or an alternate embodiment, the resilient comfort edge **12** is made from granular EVA with a density of about 40C. The precise granular sizes or physical state of the moldable material may be varied in practice of other embodiments. Likewise, various other thermoplastic materials which are non-toxic and suitable for human contact may be used to form the improved athletic cup **10**. As disclosed, an improved athletic cup **10** may be provided that is made of a single compositional material (such as EVA), yet having different physical properties (such as strength, softness, rigidity, resilience).

[0025] As one of the possible alternative methods, the different densities among the regions of the improved athletic cup **10** might be created during the manufacturing process by “foaming” the compositional material introduced into some locations (such as in the area of the resilient comfort edge **12** created by the second portion of

compositional material), or “bubbling” air into or through such regions during the manufacturing process. In one embodiment, the density of the EVA material at the hard frontal region 14 and the resilient comfort edge 12 is varied through a dual density foaming process known to those skilled in the art.

[0026] The molding process creates a improved one piece athletic cup 10 that possess the requisite strength and hardness to protect the male groin area from injury in an athletic event while providing a comfortable, flexible fit to the body. The molding process creates regions of varying flexibility or rigidity throughout the one piece improved athletic cup. Further, the improved design is much lighter than the known art (approximately 53g compared to 100g). It should be understood that reference to a “single structure” or “one piece” construction does not necessarily mean that there is no line of demarcation between the regions of varying hardness and flexibility. Keeping this possibility of a line of demarcation in mind, the athletic cup 10 may be a “single structure”, and also a “single composition” construction (possibly, although not necessarily containing lines of demarcation in the transitory regions 20), in which the device could conceptually (or even physically) broken into different structural segments, but which segments are created from the same basic compositional material (e.g., EVA or others).

[0027] While this disclosure has been described with respect to a limited number of embodiments, those skilled in the art, having benefit of this disclosure, will appreciate that other embodiments can be devised.

THE EMBODIMENTS OF THE INVENTION IN WHICH AN EXCLUSIVE PROPERTY OR PRIVILEGE IS CLAIMED ARE DEFINED AS FOLLOWS:

1. An athletic cup comprising a first region and a second region, the first region and the second region being formed of the same compositional material, wherein the first region is more rigid than the second region and wherein the first region and the second region are portions of a single structure.
2. An athletic cup comprising
 - a frontal region formed of a compositional material characterized by a first density; and
 - a resilient comfort edge formed of the compositional material characterized by a second density, which second density is different from the first density;wherein the frontal region and the resilient comfort edge are portions of a single structure.
3. The athletic cup of claim 2 wherein the compositional material comprises ethylene vinyl acetate copolymer.
4. The athletic cup of claim 2 wherein the hard frontal region comprises ethylene vinyl acetate copolymer with a density of about 70 kg/m³.
5. The athletic cup of claim 2 wherein the resilient comfort edge comprises ethylene vinyl acetate copolymer with a density of about 40 kg/m³.
6. The athletic cup of claim 2 wherein an area between the frontal region and the resilient comfort edge is characterized by a gradient of density.

7. The athletic cup of claim 2 wherein the density along points between the frontal region and the resilient comfort edge varies in a discrete step-wise fashion.
8. An athletic cup molded from a single compositional material comprising:
 - (a) a frontal region comprising:
 - (i) granular ethylene vinyl acetate copolymer with a density of about 70 kg/m³,
 - (ii) a convex outer surface with an apex that is about one-half (0.50) to one (1.0) centimeters thick,
 - (iii) a concave inner surface;
 - (iv) and a volume sufficient to enclose the wearer's genitals;
 - (b) a resilient comfort edge wherein a distance between the outer surface and the inner surface at an apex is between about one-half and one centimeters;
 - (c) a resilient comfort edge adapted to contact a wearer's skin, comprising ethylene vinyl acetate copolymer with a density of about 40 kg/m³.




FIG. 1






FIG. 2






FIG. 5

