

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
15 January 2009 (15.01.2009)

PCT

(10) International Publication Number
WO 2009/009011 A1

(51) International Patent Classification:

C09C 1/30 (2006.01) *C01B 33/14* (2006.01)
C09C 3/12 (2006.01) *G03G 9/113* (2006.01)

(74) Agent: **LANDO, Michelle, B.**; Cabot Corporation, 157
Concord Road, Billerica, MA 01821-7001 (US).

(21) International Application Number:

PCT/US2008/008293

(22) International Filing Date: 2 July 2008 (02.07.2008)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:

11/774,478 6 July 2007 (06.07.2007) US

(71) Applicant (for all designated States except US): **CABOT CORPORATION** [US/US]; Two Seaport Lane, Suite 1300, Boston, MA 02210-2019 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **FOMITCHEV, Dmitry** [RU/US]; 105 Fifer Lane, Lexington, MA 02420 (US). **FLOESS, Joachim, K.** [US/US]; 305 East Sherwin Circle, Urbana, IL 61802 (US). **WILLIAMS, William, R.** [US/US]; 12 Pinevale Avenue, Reading, MA 01867 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MT, NL, NO, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

(54) Title: SURFACE-TREATED METAL OXIDE PARTICLES

(57) Abstract: The invention provides metal oxide particles surface-treated with at least one alkoxysilane compound, methods of making such, and toners comprising same.



WO 2009/009011 A1

SURFACE-TREATED METAL OXIDE PARTICLES

BACKGROUND OF THE INVENTION

[0001] Hydrophobic metal oxide particles possess physical properties that are useful in a number of applications requiring a high degree of dispersibility. Some hydrophobic metal oxide particles have physical properties that are desirable for use in toner compositions.

[0002] Untreated metal oxide particles are hydrophilic due to the presence of polar groups, such as hydroxyl groups (-OH), on the surface of the untreated silica particles. By treating hydrophilic metal oxide particles, the hydrophilic nature of the particles can be reduced, thereby imparting varying degrees of hydrophobicity to the particles. Many different methods are known for treating the surface of metal oxide particles. However, the direct treatment of an aqueous dispersion of metal oxide particles is often inefficient or difficult to achieve.

[0003] Thus, there remains a desire for additional treated metal oxide particles, especially those that are useful for modifying the charge of toner particles, and for additional methods of preparing such hydrophobic metal oxide particles, especially methods that can be used to prepare hydrophobic metal oxide particles directly from an aqueous dispersion. However, not all such particles afford the charge-controlling characteristics that are required for some applications.

BRIEF SUMMARY OF THE INVENTION

[0004] The invention provides a particle composition comprising metal oxide particles surface-treated with at least one alkoxysilane compound, which metal oxide particles are hydrophobic, non-aggregated, and have a tap density of about 110 g/l to about 420 g/l, and a BET surface area of less than about 200 m²/g.

[0005] The invention also provides a toner composition comprising toner particles and metal oxide particles surface-treated with at least one alkoxysilane compound, which metal oxide particles are hydrophobic, non-aggregated, and have a tap density of about 110 g/l to about 420 g/l and a BET surface area of less than about 200 m²/g.

[0006] The invention further provides a method of preparing hydrophobic metal oxide particles comprising (a) providing an aqueous dispersion of hydrophilic metal oxide particles,

(b) combining the dispersion with at least one alkoxysilane treating agent to provide a reaction mixture, wherein the reaction mixture is basic, and (c) drying the reaction mixture to provide hydrophobic metal oxide particles having a tap density of about 110 g/l to about 420 g/l and a BET surface area of less than about 200 m²/g.

[0007] The invention additionally provides a method of preparing hydrophobic metal oxide particles comprising (a) providing an aqueous dispersion of non-aggregated hydrophilic metal oxide particles, (b) combining the dispersion with at least one alkoxysilane treating agent to provide a reaction mixture, wherein the reaction mixture is basic, (c) drying the reaction mixture to provide hydrophobic metal oxide particles, and (d) reducing the agglomerate size of the hydrophobic metal oxide particles by jet milling or hammer milling.

BRIEF DESCRIPTION OF THE SEVERAL VIEWS OF THE DRAWING(S)

[0008] Figure 1 depicts the NMR spectra of untreated silica particles and silica particles treated with OTES (octyltriethoxysilane).

[0009] Figure 2 is a graph of particle size distribution by volume of volume % particles versus diameter of particles (μm) for silica particles treated with OTES (octyltriethoxysilane) that have been jet milled and silica particles treated with OTES that have not been jet milled.

DETAILED DESCRIPTION OF THE INVENTION

[0010] The invention provides a particle composition comprising metal oxide particles surface-treated with at least one alkoxysilane compound, which metal oxide particles are hydrophobic, non-aggregated, and have a tap density of about 110 g/l to about 420 g/l, and a BET surface area of less than about 200 m²/g. The inventive particles can be utilized in compositions containing toner particles. The method of preparing the inventive metal oxide particles comprises (a) providing an aqueous dispersion of hydrophilic metal oxide particles, (b) combining the dispersion with at least one alkoxysilane treating agent to provide a reaction mixture, wherein the reaction mixture is basic, and (c) drying the reaction mixture to provide hydrophobic metal oxide particles. The resulting hydrophobic metal oxide particles can have a tap density of about 110 g/l to about 420 g/l and a BET surface area of less than about 200 m²/g and/or the method can further comprise an additional step wherein the average particle size of the hydrophobic metal oxide particles is reduced.

[0011] “Hydrophobic” metal oxide particles, as the term is used herein, encompasses varying levels or degrees of hydrophobicity. The degree of hydrophobicity imparted to the metal oxide particles will vary depending upon the type and amount of treating agent used. Hydrophobic metal oxide particles according to the invention preferably, but not necessarily, have about 25% or more (e.g., about 35% or more, about 45% or more, or about 50% or more) of the available metal oxide surface hydroxyl groups reacted. Generally, the hydrophobic metal oxide particles according to the invention have about 85% or less (e.g., about 75% or less, or about 65% or less) of the available metal oxide surface hydroxyl groups reacted.

[0012] The metal oxide particle can comprise any suitable type of metal oxide particle, such as silica, alumina, ceria, or titania. Preferably, the metal oxide particle is a colloidal metal oxide particle, such as a colloidal silica particle. Colloidal metal oxide particles are non-aggregated, individually discrete particles, which typically are spherical or nearly spherical in shape, but can have other shapes (e.g., shapes with generally elliptical, square, or rectangular cross-sections). Such particles are structurally different from fumed or pyrogenically prepared particles, which are chain-like structures of aggregated primary particles.

[0013] Non-aggregated metal oxides (e.g., colloidal metal oxides), which can be treated to provide a surface treated metal oxide in accordance with the invention, are commercially available, or can be prepared by known methods from various starting materials (e.g., wet-process type metal oxides). Silica particles can be prepared, for example, from silicic acid derived from an alkali silicate solution having a pH of about 9 to about 11, wherein the silicate anions undergo polymerization to produce discrete silica particles having the desired average particle size in the form of an aqueous dispersion. Typically, the colloidal metal oxide starting material will be available as a sol, which is a dispersion of colloidal metal oxide in a suitable solvent, most often water alone or with a co-solvent and/or stabilizing agent. See, e.g., Akitoshi Yoshida, *Silica Nucleation, Polymerization, and Growth Preparation of Monodispersed Sols*, in *Colloidal Silica Fundamentals and Applications* 47-56 (H.E. Bergna & W.O. Roberts, eds., 2006). Non-limiting examples of commercially available colloidal silica suitable for use in the invention include SNOWTEX® products from Nissan Chemical, NexSil™ and NexSil A™ series products available from Nyacol Nanotechnologies, Inc., and Levasil® products available from H.C.Starck.

[0014] The colloidal silica from which the treated metal oxide particle can be prepared often contains alkali metal cations as a result of the method by which such colloidal silica was manufactured or stabilized in dispersion. The alkali metal cations may be present both in the interior portions of the particles, as well as on the surface of the particles. "Free alkali metal cation" refers to an alkali metal cation that is solubilized in the aqueous phase of a dispersion of colloidal silica, or that is present at the surface of the metal oxide particle, and does not refer to alkali metal cation that may be bound or trapped within the interior of the metal oxide particles and thus inaccessible to the aqueous phase. The alkali metal cation can be sodium, potassium, or any other Group I metal cation.

[0015] The free alkali metal cation content of the metal oxide dispersion of silica can be reduced, for example, by treatment of the aqueous colloidal dispersion with an acidic ion exchange resin. Alternatively, or in addition, the free alkali metal cation content of the base-stabilized dispersion of silica can be reduced by using ultrafiltration, e.g., diafiltration. Reduction of the free alkali metal cation content also may reduce the pH of the dispersion. If desired, the pH can be adjusted without increasing the alkali metal content by addition of an amine or ammonium hydroxide (NH_4OH). In this respect, it is also possible to avoid the need to reduce the alkali metal cation content of the dispersion, in accordance with this preferred aspect of the invention, by using an ammonium-stabilized aqueous dispersion of metal oxide as a starting material.

[0016] Reduction of the free alkali metal cation content of the aqueous dispersion of metal oxide, to the extent it is required, can be performed at any time before or after the at least one alkoxy silane is added to the aqueous dispersion of metal oxide. For example, the free alkali metal cation reducing treatment (e.g., ion exchange, ultrafiltration, or the like) can be performed as part of the production process of the metal oxide dispersion, or can be performed on a commercially available aqueous dispersion of metal oxide before use in the invention (e.g., about 1 hour or less before use, or about 1 day or less before use, or about 1 week or less before use). Alternatively, such treatment can be employed after the at least one alkoxy silane is combined with the dispersion of metal oxide particles. Instead, or in addition, free alkali metal cation reducing treatment also can be used to reduce the alkali metal content of the treated metal oxide particles at a later time, for example, by dispersing dried, treated metal oxide particles in water or an acceptable solvent and reducing the alkali metal content of the dispersion, after which the treated metal oxide particles can be isolated and/or dried by any suitable method.

[0017] An ion-exchanged aqueous dispersion is typically characterized by having a pH of about 1 to about 7 and having a content of free alkali metal cation of about 0.05 wt.% or less. The basic aqueous dispersion is typically characterized by having a pH of about 7 to about 12. Such a dispersion can be used to prepare the inventive particles, provided that the pH of the reaction mixture is adjusted to a pH of about 7 or more.

[0018] The hydrophilic metal oxide particle is treated with at least one alkoxysilane compound. The at least one alkoxysilane compound has the general formula: $R^1_xSi(OR^2)_{4-x}$ wherein R^1 is selected from the group consisting of C_1 - C_{30} branched and straight chain alkyl, aminoalkyl, alkenyl, and aminoalkenyl, C_3 - C_{10} cycloalkyl, and C_6 - C_{10} aryl, R^2 is a C_1 - C_{10} branched or straight chain alkyl, and x is an integer of 1-3. Examples of suitable alkoxysilane compounds include but are not limited to trimethylmethoxysilane, dimethyldimethoxysilane, methyltrimethoxysilane, and the like.

[0019] Preferably, the alkoxysilane compound is a trialkoxysilane compound. The trialkoxysilane compound can be any suitable trialkoxysilane. For example, the trialkoxysilane compound can have the formula: $R^1Si(OR^2)_3$ wherein R^1 is selected from the group consisting of C_1 - C_{30} branched and straight chain alkyl, aminoalkyl, alkenyl, and aminoalkenyl, and C_3 - C_{10} cycloalkyl, and R^2 is a C_1 - C_{10} branched or straight chain alkyl. Preferably, the trialkoxysilane compound is selected from the group consisting of methyltrimethoxysilane, ethyltrimethoxysilane, propyltrimethoxysilane, butyltrimethoxysilane, pentyltrimethoxysilane, hexyltrimethoxysilane, heptyltrimethoxysilane, octyltrimethoxysilane, nonyltrimethoxysilane, decyltrimethoxysilane, undecyltrimethoxysilane, dodecyltrimethoxysilane, tetradecyltrimethoxysilane, stearyltrimethoxysilane, methyltriethoxysilane, ethyltriethoxysilane, propyltriethoxysilane, butyltriethoxysilane, pentyltriethoxysilane, hexyltriethoxysilane, heptyltriethoxysilane, octyltriethoxysilane, nonyltriethoxysilane, decyltriethoxysilane, undecyltriethoxysilane, dodecyltriethoxysilane, tetradecyltriethoxysilane, stearyltriethoxysilane, and combinations thereof. More preferably, the trialkoxysilane compound is selected from the group consisting of hexyltrimethoxysilane, heptyltrimethoxysilane, octyltrimethoxysilane, nonyltrimethoxysilane, decyltrimethoxysilane, undecyltrimethoxysilane, dodecyltrimethoxysilane, tetradecyltrimethoxysilane, stearyltrimethoxysilane, methyltriethoxysilane, ethyltriethoxysilane, propyltriethoxysilane, butyltriethoxysilane, pentyltriethoxysilane, hexyltriethoxysilane, heptyltriethoxysilane, octyltriethoxysilane, nonyltriethoxysilane, decyltriethoxysilane, undecyltriethoxysilane, dodecyltriethoxysilane,

tetradecyltriethoxysilane, stearyltriethoxysilane, 3-aminopropyltriethoxysilane, 3-aminobutyltriethoxysilane, 3-aminobutyltriethoxysilane, and combinations thereof.

[0020] The metal oxide particle can be treated with more than one alkoxysilane compound (e.g., at least two alkoxysilane compounds, or at least three alkoxysilane compounds). For example, the metal oxide particles can be treated with octyltriethoxysilane and 3-aminopropyltriethoxysilane.

[0021] The hydrophobic metal oxide particle has a pour density of less than about 300 g/l. Typically, the metal oxide particle has a pour density of about 50 g/l or more (e.g., about 60 g/l or more, about 70 g/l or more, about 80 g/l or more, about 90 g/l or more, or about 100 g/l or more). The pour density of the metal oxide particle typically will be about 280 g/l or less, more typically will be about 270 g/l or less (e.g., about 250 g/l or less, about 240 g/l or less, about 230 g/l or less, about 220 g/l or less, or about 210 g/l or less). Preferably, the pour density of the metal oxide particle is about 20 g/l to about 300 g/l, and more preferably about 30 g/l to about 300 g/l (e.g., about 50 g/l to about 300 g/l, about 75 g/l to about 300 g/l, about 80 g/l to about 280 g/l, about 100 g/l to about 300 g/l, or about 100 g/l to about 280 g/l).

[0022] Typically, the metal oxide particle has a tap density of about 75 g/l or more, or about 100 g/l or more. The tap density of the metal oxide particle typically will be about 450 g/l or less, more typically will be about 420 g/l or less (e.g., about 400 g/l or less, about 380 g/l or less, about 350 g/l or less, about 320 g/l or less, about 300 g/l or less, about 280 g/l or less, about 250 g/l or less, about 230 g/l or less, about 210 g/l or less, or about 180 g/l or less). Preferably, the tap density of the metal oxide particle is about 50 g/l to about 420 g/l, about 75 g/l to about 400 g/l, about 80 g/l to about 380 g/l, about 110 g/l to about 420 g/l, or about 150 g/l to about 400 g/l. The tap density of the metal oxide particle can be determined using a tap volumeter and the following equation: tap density (g/l) = (weight of the treated metal oxide particles in grams) x (1000/(volume of the treated metal oxide particles in ml)). The ratio of pour to tap density is approximately 0.7. Any suitable number of taps can be taken by the tap volumeter. Preferably, the tap volumeter takes about 300 taps or more (e.g., about 600 taps or more, about 1250 taps or more, or 3000 taps or more) of the sample of treated metal oxide particles. All tap densities described herein, unless otherwise indicated, were measured after 3000 taps were taken.

[0023] The hydrophobic metal oxide particle has a BET surface area of less than about 200 m²/g (determined by the method of S. Brunauer, P.H. Emmet, and I. Teller, *J. Am. Chemical Society*, 60, 309 (1938), which is commonly referred to as the BET method).

Typically, the metal oxide particle has a BET surface area of about $10 \text{ m}^2/\text{g}$ or more (e.g., about $20 \text{ m}^2/\text{g}$ or more, about $30 \text{ m}^2/\text{g}$ or more, about $40 \text{ m}^2/\text{g}$ or more, about $50 \text{ m}^2/\text{g}$ or more, or about $60 \text{ m}^2/\text{g}$ or more). The BET surface area of the metal oxide particle typically will be about $180 \text{ m}^2/\text{g}$ or less, more typically will be about $160 \text{ m}^2/\text{g}$ or less (e.g., about $140 \text{ m}^2/\text{g}$ or less, about $120 \text{ m}^2/\text{g}$ or less, about $100 \text{ m}^2/\text{g}$ or less, about $80 \text{ m}^2/\text{g}$ or less, about $70 \text{ m}^2/\text{g}$ or less, or about $50 \text{ m}^2/\text{g}$ or less). Preferably, the BET surface area of the metal oxide particles is about $10 \text{ m}^2/\text{g}$ to about $200 \text{ m}^2/\text{g}$, and more preferably about $20 \text{ m}^2/\text{g}$ to about $180 \text{ m}^2/\text{g}$ (e.g., about $20 \text{ m}^2/\text{g}$ to about $160 \text{ m}^2/\text{g}$, about $20 \text{ m}^2/\text{g}$ to about $140 \text{ m}^2/\text{g}$, about $20 \text{ m}^2/\text{g}$ to about $130 \text{ m}^2/\text{g}$, about $20 \text{ m}^2/\text{g}$ to about $120 \text{ m}^2/\text{g}$, or about $20 \text{ m}^2/\text{g}$ to about $100 \text{ m}^2/\text{g}$).

[0024] The treated metal oxide particles can have any suitable average non-agglomerated particle size. The particle size refers to the diameter of the smallest sphere that encloses the non-agglomerated particle. Agglomerated particles (agglomerates) are composed of several primary particles loosely attached to each other, usually by van der Waals forces. This is in contrast to aggregated particles (aggregates), in which the bonds between primary particles are stronger, as is the case when the particles sinter. As a result, de-agglomeration can be easily achieved for agglomerates. For example, dispersion of treated metal oxide particles with toner particles (dry dispersion) or in a suitable liquid (e.g., tetrahydrofuran (THF)) using high speed agitation or sonication can be used to reverse agglomeration. However, it is considerably more difficult or even impossible to reverse aggregation to any significant extent. The average particle size of the non-agglomerated hydrophobic metal oxide particles can be, for example, less than about 1 micron (e.g., about 0.8 microns or less, about 0.7 microns or less, about 0.5 microns or less, or about 0.3 microns or less). The average particle size of the non-agglomerated hydrophobic metal oxide particles can be about 0.01 microns or more (e.g., about 0.05 microns or more, about 0.1 microns or more, about 0.2 microns or more, or about 0.3 microns or more). Thus, the average particle size of the non-agglomerated hydrophobic metal oxide particles can be, for example, from about 0.01 microns to about 5 microns (e.g., from about 0.05 microns to about 3 microns, from about 0.1 microns to about 1 micron, from about 0.2 microns to about 0.8 microns, or from about 0.3 microns to about 0.6 microns).

[0025] The hydrophilic metal oxide particle can have any suitable true density. Typically, the metal oxide particle has a true density of about 1.5 g/cm^3 or more (e.g., about 1.6 g/cm^3 or more, about 1.7 g/cm^3 or more, about 1.8 g/cm^3 or more, about 1.9 g/cm^3 or more, or about 2 g/cm^3 or more). The true density of the metal oxide particle typically will

be about 5 g/cm³ or less, more typically will be about 4 g/cm³ or less (e.g., about 3.5 g/cm³ or less, about 3 g/cm³ or less, about 2.8 g/cm³ or less, or about 2.5 g/cm³ or less). Preferably, the true density of the metal oxide particle is about 0.1 g/cm³ to about 5 g/cm³, and more preferably about 0.5 g/cm³ to about 4 g/cm³ (e.g., about 1 g/cm³ to about 3.5 g/cm³, about 1.5 g/cm³ to about 3 g/cm³, about 1.8 g/cm³ to about 2.8 g/cm³, about 2 g/cm³ to about 2.5 g/cm³, or about 2.2 g/cm³ to about 2.4 g/cm³).

[0026] The surface treatment of a hydrophilic metal oxide particle with an alkoxysilane generates various patterns of substituted silicon atoms attached to the surface of the metal oxide particle or attached indirectly to the surface of the metal oxide particle. These substitution patterns have been referred to in the literature as M sites, D sites, and T sites. See, for example, Sindorf, Dean William, "Silicon-29 and Carbon-13 CP/MAS NMR Studies of Silica Gel and Bonded Silane Phases," Department of Chemistry, Colorado State University, Fort Collins, Colorado, 1982. The correlation of the M sites, D sites, and T sites to the resonance signals in the CP/MAS ²⁹Si NMR spectrum also is discussed in Maciel, G., Sindorf, D.W., *J. Am. Chem. Soc.*, 102: 7607-7608 (1980), Sindorf, D.W., Maciel, G., *J. Phys. Chem.*, 86: 5208-5219 (1982), and Sindorf, D.W., Maciel, G., *J. Am. Chem. Soc.*, 105: 3767-3776 (1983).

[0027] In particular, the surface treatment of a hydrophilic metal oxide particle with at least one trialkoxysilane compound in accordance with one embodiment of the invention provides metal oxide particles having predominantly substitution patterns referred to as T2 and T3 sites. As used herein, T2 sites correspond to a silicon atom originating from the alkoxysilane compound having two bonds to oxygen atoms further bonded to silicon atoms, at least one of which is on the metal oxide particle surface, one bond to an oxygen atom comprising a silanol (Si-OH) group, and one bond to a carbon atom. T2 sites are represented by formula (I): R-Si(OH)-(OSi-P¹)(OSiP²) wherein the group R is as defined herein for the alkoxysilane compound, and P¹ and P² independently represent a bond to a silicon atom on a particle surface and/or a silicon atom of another silane-containing molecule. Si atoms corresponding to T2 sites have been correlated with the resonance signals with chemical shifts in the range from -56 ppm to -59 ppm in the CP/MAS ²⁹Si NMR spectrum, wherein the chemical shift in ppm is measured relative to the standard tetramethylsilane.

[0028] As used herein, T3 sites correspond to a silicon atom originating from the alkoxysilane compound having three bonds to an oxygen atom further bonded to silicon atoms. At least one of the silicon atoms is a silicon atom on a particle. The sites are

represented by the formula (II): $R-Si(OSi-P^1)(OSi-P^2)(OSi-P^3)$ wherein the group R is as herein defined for the alkoxysilane compound and wherein P^1 , P^2 , and P^3 independently represent a bond to a silicon atom on a particle surface and/or a silicon atom of another silane-containing molecule. Si atoms corresponding to T3 sites have been correlated with the resonance signals with chemical shifts in the range from -65 ppm to -69 ppm in the CP/MAS ^{29}Si NMR spectrum, wherein the chemical shift in ppm is measured relative to the standard tetramethylsilane.

[0029] As defined herein, T2 is the integrated intensity of a peak having a chemical shift in the CP/MAS ^{29}Si NMR spectrum centered within the range of -56 ppm to -59 ppm. T3 is the integrated intensity of a peak having a chemical shift in the CP/MAS ^{29}Si NMR spectrum centered within the range of -65 ppm to -69 ppm. The intensity of a peak refers to the maximum peak height of the signal at that approximate location or the area of the peak occurring within the recited ranges, as calculated using standard calculation methods well known to those skilled in the art.

[0030] The hydrophobic metal oxide particles preferably have a ratio of T3 to T2 (i.e., T3:T2), based on the integrated area of the peaks, of about 1.5 or more (e.g., about 2 or more, about 2.5 or more, about 3 or more, or about 3.5 or more), wherein T2 and T3 are as defined herein.

[0031] The hydrophobic metal oxide particles can be formulated as a dry particle composition (e.g., a dry powder) or as a wet particle composition (e.g., dispersion) comprising the hydrophobic metal oxide particles. The dispersion can comprise any suitable dispersant, preferably water alone or with a co-solvent, treating agents, or additives of any type commonly used in dispersions of hydrophobic metal oxide particles.

[0032] The hydrophobic metal oxide particles can be used for many different applications including but not limited to toner compositions, antiblocking agents, adhesion modifiers, polymer additives (e.g., for elastomers and rubbers, such as silicone rubbers), abrasion-resistant coatings and films, delustering coatings and films, rheological control agents (e.g., for epoxies or liquid polymers), and mechanical/optical control agents (e.g., for composites and plastics). The hydrophobic metal oxide particles are especially useful in toner compositions. In that regard, the invention provides a toner composition comprising toner particles and metal oxide particles surface-treated with at least one alkoxysilane compound, which metal oxide particles are hydrophobic, non-aggregated, and have a tap density of about 110 g/l to about 420 g/l or less and a BET surface area of about 200 m²/g or less.

[0033] All aspects of the hydrophobic metal oxide particles used in the toner composition are as described with respect to the particle composition of the invention.

[0034] The tribocharge of toner compositions containing the treated metal oxide particles can be either positive or negative. The tribocharge of a toner composition containing the inventive treated metal oxide particles is affected by the presence of the treated particles. Without wishing to be bound by a particular theory, it is thought that the presence of the treated metal oxide particles stabilizes and increases the positive or negative tribocharge of toner compositions containing the metal oxide particles.

[0035] Toner compositions containing the treated metal oxide particles can be formulated, for example, by mixing 4 wt.% of the treated particles in a laboratory blender with pulverized styrene acrylate toner particles free of any external additives and having an average diameter of 9 μm . Toner compositions containing the treated particles can be developed, for example, by rolling for 30 minutes at a 2/98 wt.% toner/carrier ratio in glass jars. The carrier can be 70 μm Cu-Zn ferrite coated with silicone resin. Samples can be conditioned in a standard humidity chamber at either a high humidity and high temperature (30° C and 80% relative humidity) or at a low humidity and low temperature (18° C and 15% relative humidity) overnight.

[0036] The tribocharge of toner compositions containing the treated metal oxide particles can be either positive or negative. Tribocharge measurements can be made using suitable techniques and equipment known in the art (e.g., Vertex T-150 tribocharger). Measurements can be made after conditioning the toner particles overnight in a standard humidity chamber at 30° C and 80% relative humidity (HH) and at 18° C and 15% relative humidity (LL). The toner particles (e.g., of a toner composition comprising about 4 wt.% treated metal oxide particles) preferably have a tribocharge at HH conditions of about -40 $\mu\text{C/g}$ to about +15 $\mu\text{C/g}$ (e.g., about -40 $\mu\text{C/g}$ to about -20 $\mu\text{C/g}$, about -40 $\mu\text{C/g}$ to about 0 $\mu\text{C/g}$, about -5 $\mu\text{C/g}$ to about +10 $\mu\text{C/g}$, about 0 $\mu\text{C/g}$ to about +5 $\mu\text{C/g}$, or about +5 $\mu\text{C/g}$ to about +10 $\mu\text{C/g}$). The toner particles preferably have a tribocharge at LL conditions of about -100 $\mu\text{C/g}$ to about +25 $\mu\text{C/g}$ (e.g., about -80 $\mu\text{C/g}$ to about -50 $\mu\text{C/g}$, about -80 $\mu\text{C/g}$ to about 0 $\mu\text{C/g}$, about -5 $\mu\text{C/g}$ to about +10 $\mu\text{C/g}$, about +5 $\mu\text{C/g}$ to about +35 $\mu\text{C/g}$, or about +10 $\mu\text{C/g}$ to about +25 $\mu\text{C/g}$).

[0037] The free flow of a toner composition containing the inventive treated metal oxide particles is affected by the presence of the treated particles. Without wishing to be bound by

a particular theory, it is thought that the presence of the treated metal oxide particles, especially particles which have been jet milled, improves the free flow of toner compositions containing the metal oxide particles due to the lower tap and pour densities of the treated particles. In the context of the invention, free flow is the percentage of toner discharged from a grounded metal role tube of 25 mm diameter and 350 mm in length, with seven 0.5 mm discharge holes, that contains 40g of the toner composition and is rotated at 30 rpm for one minute for a total of 30 rotations. The toner composition can have a free flow of about 0.5 wt.% loss or more (e.g., about 1 wt.% loss or more, about 1.5 wt.% loss or more, about 2 wt.% loss or more, or about 3.5 wt.% loss or more). The free flow of the toner composition typically will be about 8 wt.% loss or less (e.g., about 6 wt.% loss or less, about 5 wt.% loss or less, about 4 wt.% loss or less, or about 3 wt.% loss or less). Preferably, the free flow of the toner composition is about 0.5 wt.% loss to about 8 wt.% loss (e.g., about 1 wt.% loss to about 6 wt.% loss, about 1.5 wt.% loss to about 5 wt.% loss, or about 2 wt.% loss to about 4.5 wt.% loss).

[0038] The hydrophilic metal oxide particles that are treated with the alkoxysilane compound are in an aqueous dispersion. The aqueous dispersion of metal oxide particles preferably is colloidally stable. The colloidal stability of the dispersion prevents any substantial portion of the particles from irreversibly agglomerating or gelling, or from settling out of the dispersion during use. The aqueous dispersion of metal oxide particles used in conjunction with the invention preferably has a degree of colloidal stability such that the average overall particle size of the silica in dispersion, as measured by dynamic light scattering, does not change over a period of 1 hour or more (e.g., about 8 hours or more, or about 24 weeks or more), more preferably 2 weeks or more (e.g., about 4 weeks or more, or about 6 weeks or more), most preferably 8 weeks or more (e.g., about 10 weeks or more, or about 12 weeks or more), or even about even 16 weeks or more.

[0039] The invention provides a method of preparing hydrophobic metal oxide particles comprising (a) providing an aqueous dispersion of hydrophilic metal oxide particles, (b) combining the dispersion with at least one alkoxysilane treating agent to provide a reaction mixture, wherein the reaction mixture is basic, and (c) drying the reaction mixture to provide hydrophobic metal oxide particles. According to one aspect of the invention, the hydrophobic metal oxide particles have a tap density of about 110 g/l to about 420 g/l and a BET surface area of less than about 200 m²/g. According to another aspect of the invention,

the agglomerate size of the hydrophobic metal oxide particles can be reduced by jet milling or hammer milling.

[0040] The aqueous dispersion containing the hydrophilic metal oxide particles can be a commercially available metal oxide dispersion, as described herein. Alternatively, the aqueous dispersion can be prepared by any suitable technique. In one embodiment, the metal oxide particles can be prepared via a wet process, such as by mixing a metal oxide with water and a water-soluble organic solvent. The water-soluble organic solvent can be any suitable water-soluble organic solvent, such as an alcohol (e.g., methanol, ethanol, n-propanol, 2-propanol, n-butanol, isobutanol, sec-butanol, tert-butanol, n-propanol, ethylene glycol, and propylene glycol), ketone (e.g., acetone and 2-butanone), ether (e.g., tetrahydrofuran and 1,2-dimethoxyethane), and combinations thereof. The water and water-soluble organic solvent can be added in any order. For example, the water can be added before the water-soluble organic solvent, or vice versa. Although not wishing to be bound by a particular theory, it is thought that adding the water before the water-soluble organic solvent prevents the dispersion from gelling. Typically, the reaction mixture will comprise no more than about 50 wt.% of organic solvent, and preferably will comprise not more than about 40 wt.% of organic solvent.

[0041] The water-soluble organic solvent to water volume ratio can be any suitable ratio. The ratio typically is less than about 10 (e.g., about 8 or less, about 6 or less, about 5 or less, about 3 or less, or about 2 or less). The ratio can be about 0.05 or more (e.g., about 0.1 or more, about 0.5 or more, about 0.7 or more, about 1 or more, or about 1.2 or more). The ratio can be, for example, from about 0.05 to about 10 (e.g., from about 0.1 to about 5, or from about 0.2 to about 2).

[0042] The aqueous dispersion containing the hydrophilic metal oxide particles can contain any suitable amount of metal oxide particles. The aqueous dispersion typically comprises about 30 wt.% or less (e.g., about 25 wt.% or less, about 20 wt.% or less, about 15 wt.% or less, about 10 wt.% or less, or about 5 wt.% or less) metal oxide particles. The aqueous dispersion can comprise about 5 wt.% or more (e.g., about 10 wt.% or more, about 15 wt.% or more, about 20 wt.% or more, about 25 wt.% or more, or about 30 wt.% or more) metal oxide particles. Thus, the aqueous dispersion can comprise, for example, from about 5 wt.% to about 30 wt.% (e.g., from about 10 wt.% to about 25 wt.%, or from about 15 wt.% to about 20 wt.%) metal oxide particles.

[0043] The aqueous dispersion containing the hydrophilic metal oxide particles can be combined with at least one alkoxysilane treating agent to provide a reaction mixture in any suitable manner. The dispersion can be acidic or basic, and the pH of the dispersion can be altered by the addition of the at least one alkoxysilane treating agent.

[0044] The amount of the at least one alkoxysilane compound that is added to the aqueous dispersion containing the hydrophilic metal oxide particles can be any suitable amount. The amount of the at least one alkoxysilane compound typically comprises less than about 50 $\mu\text{mole}/\text{m}^2$ metal oxide particles (e.g., about 25 $\mu\text{mole}/\text{m}^2$ metal oxide particles or less, about 15 $\mu\text{mole}/\text{m}^2$ metal oxide particles or less, about 10 $\mu\text{mole}/\text{m}^2$ metal oxide particles or less, or about 5 $\mu\text{mole}/\text{m}^2$ metal oxide particles or less). The amount of the at least one alkoxysilane compound can comprise about 0.1 $\mu\text{mole}/\text{m}^2$ metal oxide particles or more (e.g., about 0.5 $\mu\text{mole}/\text{m}^2$ metal oxide particles or more, about 1 $\mu\text{mole}/\text{m}^2$ metal oxide particles or more, or about 2 $\mu\text{mole}/\text{m}^2$ metal oxide particles or more). Thus, the amount of the at least one alkoxysilane compound can comprise, for example, from about 0.1 $\mu\text{mole}/\text{m}^2$ metal oxide particles to about 50 $\mu\text{mole}/\text{m}^2$ metal oxide particles (e.g., from about 0.5 $\mu\text{mole}/\text{m}^2$ metal oxide particles to about 25 $\mu\text{mole}/\text{m}^2$ metal oxide particles, or from about 2 $\mu\text{mole}/\text{m}^2$ metal oxide particles to about 15 $\mu\text{mole}/\text{m}^2$ metal oxide particles).

[0045] The pH of the aqueous dispersion can be any suitable pH before the at least one alkoxysilane is added to the dispersion. Regardless of whether the starting dispersion is acidic, basic, or neutral, the reaction mixture should have a basic pH, i.e., a pH of about 7 or more. The pH of the reaction mixture can be, for example, about 7 or more (e.g., about 8 or more, about 9 or more, about 10 or more, about 11 or more, or about 12 or more). Generally, the pH of the reaction mixture will be from about 7 to about 12 (e.g., from about 8 to about 11, from about 9 to about 10.5, or from about 9.5 to about 10.5).

[0046] The reaction between the aqueous dispersion containing the metal oxide particles and the alkoxysilane compound can occur at any suitable temperature and for any suitable amount of time that allows the alkoxysilane compound to react completely, or to any extent desired, with the aqueous dispersion of metal oxide particles. Generally, the reaction mixture is maintained at a temperature of about 20° C to about 100° C (e.g., about 30° C to about 70° C, or about 45° C to about 75° C) for about 5 minutes or longer (e.g., about 30 minutes or longer, about 1 hour or longer), or even about 2 hours or longer (e.g., about 3 hours or longer, or about 4 hours or longer). Longer reaction times (e.g., 5 hours or more, 10 hours or more,

or even 20 hours or more) may be required depending on the particular reaction conditions (e.g., temperature and concentration of reagents).

[0047] Additional alkoxysilanes, silazanes, or other treating agents can be added (e.g., a second, third, or fourth alkoxysilane, silazane, or treating agent) at any suitable time before or after the addition of the first alkoxysilane compound. After the addition of another treating agent, the temperature of the reaction mixture can be adjusted to any suitable temperature for any suitable amount of time that allows the additional alkoxysilane compound to react completely, or to any extent desired, with the aqueous dispersion of metal oxide particles.

[0048] Preferably, the reaction mixture containing the hydrophobic metal oxide particles is dried to form a powder. The drying of the reaction mixture can be effected in any suitable manner. For example, spray drying can be used to dry the hydrophobic metal oxide particles. Spray drying involves spraying the reaction mixture, or some portion thereof, comprising the hydrophobic metal oxide particles as a fine mist into a drying chamber, wherein the fine mist is contacted with hot air causing the evaporation of volatile components of the reaction mixture. The temperature chosen for the hot air will depend, at least in part, on the specific components of the reaction mixture that require evaporation. Typically, the drying temperature will be about 40° C or higher (e.g., about 50° C or higher) such as about 70° C or higher (e.g., about 80° C or higher) or even about 120° C or higher (e.g., about 130° C or higher). Thus, the drying temperatures generally can be within the range of about 40-250° C (e.g., about 50-200° C), such as about 60-200° C (e.g., about 70-175° C), or about 80-150° C (e.g., about 90-130° C).

[0049] The hydrophobic metal oxide particles can be isolated from the reaction mixture prior to drying, or the hydrophobic metal oxide particles can be dried directly from the reaction mixture. Any suitable method can be used to isolate the hydrophobic metal oxide particles from the reaction mixture. Suitable methods include filtration and centrifugation.

[0050] The hydrophobic metal oxide particles can be dried after isolation from the reaction mixture, or directly from the reaction mixture, by any suitable technique, e.g., by evaporating the volatile components of the reaction mixture from the hydrophobic metal oxide particles. Evaporation of the volatile components of the reaction mixture can be accomplished using any suitable techniques, e.g., heat and/or reduced atmospheric pressure. When heat is used, the hydrophobic metal oxide particles can be heated to any suitable drying temperature, for example, by using an oven or other similar device. The temperature can be as recited for the spray drying embodiment of the invention.

[0051] The hydrophobic metal oxide particles can be dried at any pressure that will provide a useful rate of evaporation. When drying temperatures of about 120° C and higher (e.g., about 120-150° C) are used, drying pressures of about 125 kPa or less (e.g., about 75-125 kPa) are desirable. At drying temperatures lower than about 120° C (e.g., about 40-120° C), drying pressures of about 100 kPa or less (e.g., about 75 kPa or less) are desirable. Of course, reduced pressure (e.g., pressures of about 100 kPa or less, 75 kPa or less, or even 50 kPa or less) can be used as a sole method for evaporating the volatile components of the reaction mixture.

[0052] Alternatively, the hydrophobic metal oxide particles can be dried by lyophilization, wherein the liquid components of the reaction mixture are converted to a solid phase (i.e., frozen) and then to a gas phase by the application of a vacuum. For example, the reaction mixture comprising the hydrophobic metal oxide particles can be brought to a suitable temperature (e.g., about -20° C or less, or about -10° C or less, or even -5° C or less) to freeze the liquid components of the reaction mixture, and a vacuum can be applied to evaporate those components of the reaction mixture to provide dry hydrophobic metal oxide particles.

[0053] The hydrophobic metal oxide particles can be washed prior to or after isolation and/or drying from the reaction mixture. Washing the hydrophobic metal oxide particles can be performed using a suitable washing solvent, such as water, a water-miscible organic solvent, a water-immiscible solvent, or a mixture thereof. The washing solvent can be added to the reaction mixture and the resulting mixture suitably mixed, followed by filtration, centrifugation, or drying to isolate the washed hydrophobic metal oxide particles.

Alternatively, the hydrophobic metal oxide particles can be isolated from the reaction mixture prior to washing. The washed hydrophobic metal oxide particles can be further washed with additional washing steps followed by additional filtration, centrifugation, and/or drying steps.

[0054] The hydrophobic metal oxide particles have an overall particle size that is dependent, at least in part, on the overall particle size of the metal oxide particles in the initial dispersion. The average overall particle size of the hydrophobic metal oxide particles can be determined by any suitable method, many of which methods are known in the art, such as dynamic light scattering. Preferred average particle sizes of the hydrophobic metal oxide particles prepared in accordance with the method of the invention are as described with respect to the treated metal oxide particles of the invention. Desirably, the average particle size of the hydrophobic, non-aggregated particle prepared in accordance with the method of

the invention is within about 50%, preferably within about 30% (e.g., within about 20%, about 15%, about 10%, or even about 5%) of the average particle size of the metal oxide particle of the starting dispersion. Preferably, the average particle size of the hydrophobic metal oxide particles is further reduced after drying. The agglomerate size of the hydrophobic metal oxide particles is also preferably reduced after drying. Suitable processes for the reduction of the particle size and agglomerate size of the hydrophobic metal oxide particles include but are not limited to wet or dry grinding, hammer milling, and jet milling.

[0055] The carbon content of the hydrophobic metal oxide particles can be used as an indicator of the level of treatment of the hydrophobic metal oxide particles and, thus, as an indicator of the degree of hydrophobicity. The carbon content of the treated particles can be determined using commercially available carbon analyzers (e.g., Leco C-200). The hydrophobic metal oxide particles prepared in accordance with the invention desirably have a carbon content of about 0.1 wt.% or more (e.g., about 0.2 wt.% or more, about 0.3 wt.% or more, about 0.4 wt.% or more, about 0.5 wt.% or more, or about 0.8 wt.% or more). The carbon content of the treated metal oxide particles typically comprises less than about 10 wt.% (e.g., about 8 wt.% or less, about 7 wt.% or less, about 6 wt.% or less, or about 5 wt.% or less). Thus, the carbon content of the treated metal oxide particles can be, for example, from about 0.01 wt.% to about 10 wt.% (e.g., from about 0.05 wt.% to about 8 wt.%, from about 0.1 wt.% to about 7 wt.%, from about 0.3 wt.% to about 7 wt.%, or from about 0.5 wt.% to about 6 wt.%).

[0056] The following examples further illustrate the invention but, of course, should not be construed as in any way limiting its scope.

EXAMPLE 1

[0057] This example illustrates the preparation of hydrophobic metal oxide particles by treating colloidal silica particles with an alkoxysilane compound.

[0058] The reactor was charged with 41.6 kg of 40 wt.% colloidal silica in an aqueous solution at a pH of 9.4 (SNOWTEX MP-1040, Nissan Chemical Co.). 2.5 kg of deionized water and 27 kg of 2-propanol were added to the colloidal silica solution while continually agitating the mixture with a stirrer. The ratio of 2-propanol to water was 1.24 v/v.

[0059] 1.44 kg of OTES (octyltriethoxysilane) was added to the reaction mixture, and the mixture was heated to about 72° C. After the addition of the OTES, the agitation of the

mixture continued, and the mixture was re-circulated through a homogenizer for about 8 hours. The mixture was then held in the reactor and allowed to cool to room temperature while stirring overnight. The mixture was spray dried the following day at a temperature of about 110° C (dryer exit temperature). The inlet temperature to the dryer was 230° C. The resulting powder was collected from the cyclone collector. After drying, the powder was jet milled and packaged.

[0060] ²⁹Si CP/MAS NMR spectra of the inventive particles described in this example (bottom spectrum) and untreated silica particles (top spectrum) are shown in Figure 1. The change of the relative intensities of the Q3 and Q4 peaks in the spectra indicates that some of the single silanol groups present on the surface of treated silica particles are reacted with OTES. The T2 and T3 peaks in the spectrum of the treated silica are due to the Si atoms of the OTES molecules, which became immobilized on the surface of the silica particles. T3 is about 4 to about 5 times more intense than T2, suggesting that octyltrisilanol groups are well cross-linked on the surface.

[0061] The effect of jet milling on the agglomerate size distribution of the inventive particles described in this example is shown in Figure 2. As is apparent from Figure 2, jet milling results in significantly less agglomerated material, which is preferred for toner applications.

[0062] The amount of extractable carbon was determined by extracting 0.5-2 g treated silica with 100 ml toluene and boiling for three hours using the soxhlet method.

[0063] The toner was formulated by mixing 4 wt.% of the treated silica particles in a laboratory blender with a pulverized styrene acrylate black toner free of any external additives. The average diameter of toner particles was 9 μm. The toner was developed by rolling for 30 minutes at a 2/98 wt.% toner/carrier ratio in glass jars. The carrier was 70 μm Cu-Zn ferrite coated with silicone resin. Samples were conditioned in a standard humidity chamber at either a high humidity and high temperature (30° C and 80% relative humidity) or at a low humidity and low temperature (18° C and 15% relative humidity) overnight.

Tribocharge measurements were done using a Vertex T-150 tribo charger.

[0064] Free flow was calculated using a perforated grounded metal role tube by measuring the amount of toner discharged from the tube upon rotation. Measurements were taken after 30, 60, and 90 seconds, which were then averaged. The role tube was 25 mm in

diameter, 350 mm in length, had seven 0.5 mm discharge holes, and was rotated at 30 rpm. The initial charge to the tube was 40 g.

[0065] The properties of the treated silica particles are shown in Table 1.

Table 1

Carbon content (wt.%)	2.7
Carbon content after extraction (wt.%)	1.78
BET surface area (m ² /g)	28
Tap density (3000 taps) (g/l)	257
Tribocharge at high humidity & temperature (μC/g)	-13
T3:T2 ratio	4.7
Tribocharge at low humidity & temperature (μC/g)	-36
Free flow (wt.% loss)	1.57

EXAMPLE 2

[0066] This example illustrates the preparation of hydrophobic metal oxide particles by treating colloidal silica particles with an alkoxysilane compound.

[0067] The reactor was charged with 48.3 kg of 40 wt.% colloidal silica in an aqueous solution at a pH of 9.4 (SNOWTEX MP-1040, Nissan Chemical Co.). 10.1 kg of deionized water and 44.7 kg of 2-propanol were added to the colloidal silica solution while continually agitating the mixture with a stirrer. The ratio of 2-propanol to water was 1.45 v/v.

[0068] 1.78 kg of OTES was added to the reaction mixture and the mixture was heated to about 65° C. After the addition of the OTES, the agitation of the mixture continued, and the mixture was re-circulated through a homogenizer for about 7 hours. The mixture was then held in the reactor and allowed to cool to room temperature while stirring overnight. The mixture was spray dried the following day at a temperature of about 115° C (dryer exit

temperature). The inlet temperature to the dryer was 230° C. Composition 2A was dried in a cyclone drier, and composition 2B was dried in a baghouse drier. After drying, the powder was jet milled and packaged.

[0069] The amount of extractable carbon and tribocharge were measured as described in Example 1 for each of compositions 2A and 2B. The pour density was determined by obtaining a sample of the treated silica particles of composition 2A, pouring the treated silica particles into a calibrated container, and weighing them.

[0070] The properties of the treated silica particles are shown in Table 2.

Table 2

	Composition 2A	Composition 2B
Carbon content (wt.%)	2.41	2.07
Carbon content after extraction (wt.%)	1.83	1.79
Pour density (g/l)	234	not determined
Tribocharge at high humidity & temperature ($\mu\text{C/g}$)	-18	-19
Tribocharge at low humidity & temperature ($\mu\text{C/g}$)	-38	-45

EXAMPLE 3

[0071] This example illustrates the preparation of hydrophobic metal oxide particles by treating colloidal silica particles with an alkoxysilane compound.

[0072] A reactor (compositions 3A-3E) or a 3L 3-neck flask (composition 3F) was charged with 40 wt.% colloidal silica in an aqueous solution at a pH of about 9 to about 10 (SNOWTEX XL, Nissan Chemical Co.) in the amount indicated in Table 3. Deionized water and 2-propanol were added to the colloidal silica solution while continually agitating the mixture with a stirrer.

[0073] OTES alone or both OTES and APS ((3-aminopropyl)triethoxysilane) were added to the reaction mixture, and the mixture was heated to about 68° C to about 72° C. After the addition of the OTES alone or both OTES and APS, the agitation of the mixture continued,

and the mixture was re-circulated through a homogenizer for about 5 hours to about 9 hours. The mixture was then held in the reactor or flask and allowed to cool to room temperature while stirring overnight. The mixture was spray dried the following day at a temperature of about 118° C to about 127° C (dryer exit temperature). The inlet temperature to the dryer was 235° C. After drying, the resulting powder was jet milled and packaged. Compositions 3B and 3D were dried in a cyclone drier, and compositions 3C and 3E were dried in a baghouse drier. Composition 3F was dried in an oven at 120° C.

[0074] The amount of extractable carbon, tribocharge, and free flow of each composition were measured as described in Example 1. The pour density of composition 3A was measured as described in Example 2.

[0075] The properties of the treated silica particles are shown in Table 3.

Table 3

	Comp. 3A	Comp. 3B	Comp. 3C	Comp. 3D	Comp. 3E	Comp. 3F
Silica (kg)	39	60.3	60.3	35.7	35.7	0.9
OTES (kg)	2.92	3.51	3.51	1.83	1.83	.052
APS (kg)	-	-	-	0.283	0.283	.0024
IPA/water ratio (v/v)	1.25 (2.9 kg water, 24.2 kg IPA)	0.72 (30 kg water, 37.5 kg IPA)	0.72 (30 kg water, 37.5 kg IPA)	0.74 (30 kg water, 30.1 kg IPA)	0.74 (30 kg water, 30.1 kg IPA)	- (750 g water, 750 g IPA)
Carbon content (wt.%)	3.12	2.55	2.3	4.3	3.03	4.2
Carbon content after extraction (wt.%)	2.76	2.5	2.3	2.51	2.41	3.31

BET surface area (m ² /g)	45.9	-	-	-	-	-
Pour density (g/l)	230	-	-	-	-	-
Tap density (g/l)	-	269	254	-	-	-
Tribocharge at high humidity & temperature (μC/g)	-19	-24	-26	-11	-16	-17
Tribocharge at low humidity & temperature (μC/g)	-44	-59	-58	-16	-21	-31
Free flow (wt.% loss)	1.88	4.42	4.04	4.6	4.57	-

EXAMPLE 4

[0076] This example illustrates the preparation of hydrophobic metal oxide particles by treating colloidal silica particles with an alkoxysilane compound.

[0077] A 500 ml 3-neck round bottom flask with an overhead stirring motor and condenser was charged with 137 g of 40 wt.% colloidal silica in an aqueous solution at a pH of 9.2 (SNOWTEX YL, Nissan Chemical Co.). 87 g of 2-propanol was added to the colloidal silica solution while continually agitating the mixture with a stirrer.

[0078] 6.2 g of OTES was added to the reaction mixture, and the mixture was heated to about 70° C for about 3.5 hours. The mixture was then held in the flask and allowed to cool to room temperature. The mixture was transferred to a Pyrex tray and dried at a temperature of about 120° C.

[0079] The tribocharge and free flow of the resulting treated silica particles were measured as described in Example 1.

[0080] The properties of the treated silica particles are shown in Table 4.

Table 4

Tribocharge at high humidity & temperature ($\mu\text{C/g}$)	-20
Tribocharge at low humidity & temperature ($\mu\text{C/g}$)	-60
Free flow (wt.% loss)	1.2

EXAMPLE 5

[0081] This example illustrates the preparation of hydrophobic metal oxide particles by treating two different types of colloidal silica particles with an alkoxysilane compound.

[0082] A 500 ml 3-neck round bottom flask with an overhead stirring motor and condenser was charged with either 100 g of 40 wt.% colloidal silica in an aqueous solution at a pH of 9.2 (SNOWTEX XL, Nissan Chemical Co.) to which 50 ml of deionized water and 65 g of 2-propanol were added, or 75 g of 40 wt.% colloidal silica in an aqueous solution (NYACOL9950, Eka Chemicals), to which 75 ml of deionized water and 65 g of 2-propanol were added. Both compositions were continually agitated with a stirrer.

[0083] 5.8 g of OTES was added to each reaction mixture. The pH of the composition containing the SNOWTEX silica was 10.1, and the pH of the composition containing the NYACOL9950 silica was 9.7. The mixtures were heated to about 70° C for about 5.5 hours. The mixtures were allowed to cool to room temperature, then dried in an oven at a temperature of about 125° C. The dried mixtures were then milled using an IKA A 11 laboratory grinder.

[0084] The amount of extractable carbon and free flow of each composition were measured as described in Example 1.

[0085] The properties of the treated silica particles are shown in Table 5.

Table 5

	SNOWTEX XL silica	NYACOL9950 silica
Carbon content (wt.%)	3.9	3.4
Carbon content after extraction (wt.%)	3.7	3.4
BET surface area (m ² /g)	49	54
T3:T2 ratio	2.6	5.2
Free flow (wt.% loss)	2.5	1.9

COMPARATIVE EXAMPLE 6

[0086] This example illustrates the preparation of hydrophobic metal oxide particles by treating colloidal silica particles with an alkoxysilane compound.

[0087] A 500 ml 3-neck round bottom flask with an overhead stirring motor and condenser was charged with 113 g of 35 wt.% colloidal silica in an aqueous solution (PL-8L, Fusco Co.). 37 ml of deionized water and 65 g of 2-propanol were added to the colloidal silica solution while continually agitating the mixture with a stirrer.

[0088] 4.5 g of OTES was added to the reaction mixture. The pH of the reaction mixture was about 7.5. The mixture was heated to about 70° C for about 5.5 hours. The mixture was allowed to cool to room temperature, then dried in an oven at a temperature of about 125° C. The dried mixture was then milled using an IKA A 11 laboratory grinder.

[0089] The amount of extractable carbon and free flow of the resulting treated silica particles were measured as described in Example 1.

[0090] The properties of the treated silica particles are shown in Table 6.

Table 6

Carbon content (wt.%)	0.27
Free flow (wt.% loss)	0.6
T3:T2 ratio	Not detected

[0091] As is apparent from the data presented in Table 6, the carbon content of the treated particles was very low and the T3:T2 ratio could not be measured, indicating that treatment was unsuccessful.

EXAMPLE 7

[0092] This example illustrates the preparation of hydrophobic metal oxide particles by treating colloidal silica particles with an alkoxysilane compound.

[0093] Three different compositions containing hydrophobic colloidal silica particles were prepared as described herein. The reactor was charged with 40 wt.% colloidal silica in a basic aqueous solution (Nissan Chemical Co.) in the amounts indicated in Table 7. Deionized water and 2-propanol (IPA) were added to the colloidal silica solutions while continually agitating the mixtures with a stirrer in the amounts indicated in Table 7.

[0094] OTES was added to the reaction mixtures in the amounts indicated in Table 7, and the mixtures were heated to about 64° C. After the addition of the OTES, the agitation of the mixtures continued, and the mixtures were re-circulated through a homogenizer for about 8-9 hours. The mixtures were then held in the reactor and allowed to cool to room temperature while stirring overnight. The mixtures were spray dried the following day at a temperature of about 119°C to about 125° C (dryer exit temperature). The inlet temperature to the dryer was 235° C. The powder was collected from the cyclone collector. After drying, the powder was jet milled and packaged.

[0095] The properties of the treated silica particles are shown in Table 7.

Table 7

Composition	Silica	IPA/water ratio (v/v)	OTES (kg)	Tap Density (3000 taps) (g/l)
7A	40 kg SNOWTEX XL	1.38 (0.8 kg water, 27.1 kg IPA)	2.3	271
7B	39 kg SNOWTEX MP-1040	1.68 (0.8 kg water, 32.1 kg IPA)	1.47	265
7C	79.1 kg SNOWTEX XL	0.75 (40.9 kg water, 51.5 kg IPA)	4.65	220

EXAMPLE 8

[0096] This example illustrates the preparation of hydrophobic metal oxide particles by treating colloidal silica particles with an alkoxy silane compound.

[0097] A 5L 3-neck round bottom flask with an overhead stirring motor and condenser was charged with 1829 g of 41 wt.% colloidal silica in an aqueous solution stabilized with NaOH (NEXSIL 86, Eka Chemicals). 895 g of deionized water and 1136 g of 2-propanol were added to the colloidal silica solution while continually agitating the mixture with a stirrer.

[0098] 103.7 g of OTES was added to the reaction mixture, and the mixture was heated to about 70° C for about 6 hours. The mixture was then held in the flask overnight and allowed to cool to room temperature. The mixture was agitated to homogenize it, then the solid phase was separated by centrifugation and dried at a temperature of about 60° C overnight, then again at a temperature of about 120° C overnight. After drying, the resulting powder was jet milled and packaged.

[0099] The tap density of the colloidal silica particles, after 0, 300, 600, 1250, and 3000 taps, is shown in Table 8.

Table 8

Tap Density (0 taps) (g/l)	214
Tap Density (300 taps) (g/l)	277
Tap Density (600 taps) (g/l)	287
Tap Density (1250 taps) (g/l)	296
Tap Density (3000 taps) (g/l)	299

COMPARATIVE EXAMPLE 9

[00100] This example illustrates the tap density of hydrophobic fumed silica particles.

[00101] The tap density of commercially available fumed silica particles treated with OTES (AEROSIL R 805, Degussa) was measured after 0, 300, 600, 1250, and 3000 taps with a tap volumeter.

[00102] The tap density of the fumed silica particles is shown in Table 9.

Table 9

Tap Density (0 taps) (g/l)	51
Tap Density (300 taps) (g/l)	51
Tap Density (600 taps) (g/l)	55
Tap Density (1250 taps) (g/l)	59
Tap Density (3000 taps) (g/l)	63

EXAMPLE 10

[00103] This example illustrates the effect of jet milling a powder comprising hydrophobic metal oxide particles on pour density.

[00104] The reactor was charged with 40 wt.% colloidal silica in a basic aqueous solution (Nissan Chemical Co.) in the amounts indicated in Table 10. Deionized water and 2-propanol (IPA) were added to the colloidal silica solutions while continually agitating the mixtures with a stirrer in the amounts indicated in Table 10.

[00105] OTES was added to the reaction mixtures in the amounts indicated in Table 10, and the mixtures were heated to about 65 ° C to about 70° C. After the addition of the OTES, the agitation of the mixtures continued, and the mixtures were re-circulated through a homogenizer for about 8-9 hours. The mixtures were then held in the reactor and allowed to cool to room temperature while stirring overnight. The mixtures were spray dried the following day at a temperature of about 110° C to about 125° C (dryer exit temperature). The inlet temperature to the dryer was 235° C. The powder was collected from either the cyclone collector or the bag filter. After collection, the powder was jet milled.

[00106] The pour density was measured as described in Example 2.

[00107] The properties of the treated silica particles are shown in Table 10.

Table 10

Sample	Colloidal silica particle	Water (kg)	IPA (kg)	OTES (kg)	Unmilled pour density (g/l)	Unmilled tap (3000) density (g/l)	Milled pour density (g/l)	Milled tap (3000) density (g/l)
10A	41.6 kg SNOWTEX MP-1040	2.5	27	1.44	293	379	194	257
10B	39 kg SNOWTEX MP-1040	0.8	32	1.47	342	478	190	265
10C	59 kg SNOWTEX MP-1040	31	38	1.77	204	271	165	234
10D	40 kg SNOWTEX XL	0.8	27.1	2.3	354	508	185	271
10E	79 kg SNOWTEX XL	41	52	4.65	206	265	150	220

[00108] As is apparent from the data presented in Table 10, the pour density of the powder is significantly reduced by jet milling.

[00109] All references, including publications, patent applications, and patents, cited herein are hereby incorporated by reference to the same extent as if each reference were individually and specifically indicated to be incorporated by reference and were set forth in its entirety herein.

[00110] The use of the terms “a” and “an” and “the” and similar referents in the context of describing the invention (especially in the context of the following claims) are to be construed to cover both the singular and the plural, unless otherwise indicated herein or clearly contradicted by context. The terms “comprising,” “having,” “including,” and “containing” are to be construed as open-ended terms (i.e., meaning “including, but not limited to,”) unless otherwise noted. Recitation of ranges of values herein are merely

intended to serve as a shorthand method of referring individually to each separate value falling within the range, unless otherwise indicated herein, and each separate value is incorporated into the specification as if it were individually recited herein. All methods described herein can be performed in any suitable order unless otherwise indicated herein or otherwise clearly contradicted by context. The use of any and all examples, or exemplary language (e.g., "such as") provided herein, is intended merely to better illuminate the invention and does not pose a limitation on the scope of the invention unless otherwise claimed. No language in the specification should be construed as indicating any non-claimed element as essential to the practice of the invention.

Preferred embodiments of this invention are described herein, including the best mode known to the inventors for carrying out the invention. Variations of those preferred embodiments may become apparent to those of ordinary skill in the art upon reading the foregoing description. The inventors expect skilled artisans to employ such variations as appropriate, and the inventors intend for the invention to be practiced otherwise than as specifically described herein. Accordingly, this invention includes all modifications and equivalents of the subject matter recited in the claims appended hereto as permitted by applicable law. Moreover, any combination of the above-described elements in all possible variations thereof is encompassed by the invention unless otherwise indicated herein or otherwise clearly contradicted by context.

CLAIM(S):

1. A particle composition comprising metal oxide particles surface-treated with at least one alkoxysilane compound, which metal oxide particles are hydrophobic, non-aggregated, and have a tap density of about 110 g/l to about 420 g/l, and a BET surface area of about 200 m²/g or less.
2. The composition of claim 1, wherein the at least one alkoxysilane compound is octyltriethoxysilane.
3. The composition of claim 1, wherein the metal oxide particles are treated with two alkoxysilane compounds.
4. The composition of claim 3, wherein the two alkoxysilane compounds are octyltriethoxysilane and 3-aminopropyltriethoxysilane.
5. The composition of claim 1, wherein the metal oxide particles have an average non-agglomerated particle size of about 0.1 micron to about 1 micron.
6. The composition of claim 1, wherein the metal oxide particles have a BET surface area of about 100 m²/g or less.
7. The composition of claim 6, wherein the metal oxide particles have a BET surface area of about 80 m²/g or less.
8. The composition of claim 1, wherein the metal oxide particles are in the form of a dry powder.
9. The composition of claim 8, wherein the metal oxide particles have an average non-agglomerated particle size of about 0.3 microns to about 0.6 microns.
10. The composition of claim 1, wherein the metal oxide particles have a true density of about 2 g/cm³ to about 2.5 g/cm³.
11. The composition of claim 1, wherein a solid-state Si nuclear magnetic resonance spectrum of the metal oxide particles exhibits a ratio T3:T2 of about 2 or more, wherein T2 is the integrated intensity of a peak having a chemical shift in the CP/MAS²⁹Si

NMR spectrum centered within the range of -56 ppm to -59 ppm, and wherein T3 is the integrated intensity of a peak having a chemical shift in the CP/MAS ^{29}Si NMR spectrum centered within the range of -65 ppm to -69 ppm.

12. The composition of claim 1, wherein the metal oxide particles are colloidal silica particles.
13. A toner composition comprising toner particles and the particle composition of any of claims 1-12.
14. A method of preparing hydrophobic metal oxide particles comprising
 - (a) providing an aqueous dispersion of hydrophilic metal oxide particles,
 - (b) combining the dispersion with at least one alkoxysilane treating agent to provide a reaction mixture, wherein the reaction mixture is basic, and
 - (c) drying the reaction mixture to provide metal oxide particles, which metal oxide particles are hydrophobic, non-aggregated, and have a tap density of about 110 g/l to about 420 g/l, and a BET surface area of about 200 m²/g or less.
15. The method of claim 14, wherein the at least one alkoxysilane compound is octyltriethoxysilane.
16. The method of claim 14, wherein the metal oxide particles are treated with two alkoxysilane compounds.
17. The method of claim 16, wherein the two alkoxysilane compounds are octyltriethoxysilane and 3-aminopropyltriethoxysilane.
18. The method of claim 14, wherein the particle size of the hydrophobic metal oxide particles is reduced after the reaction mixture is dried.
19. The method of claim 18, wherein the particle size of the hydrophobic metal oxide particles is reduced by jet milling or hammer milling.

20. The method of claim 14, wherein the dispersion is prepared by mixing a metal oxide dispersion with water and then with a water-soluble organic solvent.

21. The method of claim 20, wherein the water-soluble organic solvent to water volume ratio is about 0.2 to about 2.

22. The method of claim 14, wherein the reaction mixture is maintained at a temperature of about 45° C to about 75° C for about 1 hour or longer.

23. The method of claim 14, wherein the dispersion comprises about 10 wt.% to about 25 wt.% metal oxide particles.

24. The method of claim 14, wherein the metal oxide particles are colloidal silica particles.

FIGURE 1





FIGURE 2



INTERNATIONAL SEARCH REPORT

International application No
PCT/US2008/008293

A. CLASSIFICATION OF SUBJECT MATTER

INV. C09C1/30 C09C3/12 C01B33/14 G03G9/113

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
C09C C01B G03G

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X A	US 5 415 936 A (DEUSSER HANS [DE] ET AL) 16 May 1995 (1995-05-16) column 1, line 50 - column 2, line 68; example 1	1-10, 13 12, 14-24
X	DE 196 16 781 A1 (DEGUSSA [DE]) 6 November 1997 (1997-11-06) example 1	1-4, 8
X	US 2005/241531 A1 (MEYER JURGEN [DE] ET AL) 3 November 2005 (2005-11-03) paragraphs [0005] - [0021], [0028] - [0040]; tables 1-6	1-4, 8
X	EP 1 591 490 A (DU PONT [US]) 2 November 2005 (2005-11-02) paragraphs [0015] - [0051]; example 1	14, 15, 18, 19
	-/--	

☒ Further documents are listed in the continuation of Box C.

☒ See patent family annex.

* Special categories of cited documents:

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

G document member of the same patent family

Date of the actual completion of the international search

10 October 2008

Date of mailing of the international search report

21/10/2008

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040,
Fax: (+31-70) 340-3016

Authorized officer

Corrias, M

INTERNATIONAL SEARCH REPORT

International application No

PCT/US2008/008293

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 2006/171872 A1 (ADAMS CURTIS E [US]) 3 August 2006 (2006-08-03) paragraphs [0007] - [0036]; claims 1-12; examples 1-7	1-10, 12-24
A	G. CHEN ET AL.: "Effects of surface properties of colloidal silica particles on redispersibility and properties of acrylic-based polyurethane/silica composites" JOURNAL OF COLLOID AND INTERFACE SCIENCE, vol. 281, 2005, pages 339-335, XP002499129 "Experimental", "Results and discussion"	1-10, 12-24

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

Continuation of Box II.2

Claims Nos.: 11

Present claim 11 relates to a product defined (inter alia) by reference to the following unusual parameter:

... a solid state Si nuclear magnetic spectrum of the metal oxide particles exhibits a ratio T3:T2 of about 2 or more, wherein T2 is the integrated intensity of a peak having a chemical shift in the CP/Mas ^{29}Si -NMR spectrum centered within the range of -56 ppm to -59 ppm, and wherein T3 is the integrated intensity of a peak having a chemical shift in the CP/Mas ^{29}Si -NMR spectrum centered within the range of -65 ppm to -69 ppm

The use of this unusual parameter in the present context is considered to lead to a lack of clarity because the claim does not clearly identify the products encompassed by it as the parameters cannot be clearly and reliably determined by indications in the description or by objective procedures which are usual in the art. This makes it impossible to compare the claim/s to the prior art. As a result, the application does not comply with the requirement of clarity under Article 6 PCT.

The applicant's attention is drawn to the fact that claims relating to inventions in respect of which no international search report has been established need not be the subject of an international preliminary examination (Rule 66.1(e) PCT). The applicant is advised that the EPO policy when acting as an International Preliminary Examining Authority is normally not to carry out a preliminary examination on matter which has not been searched. This is the case irrespective of whether or not the claims are amended following receipt of the search report or during any Chapter II procedure. If the application proceeds into the regional phase before the EPO, the applicant is reminded that a search may be carried out during examination before the EPO (see EPO Guideline C-VI, 8.2), should the problems which led to the Article 17(2)PCT declaration be overcome.

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US2008/008293

Box No. II Observations where certain claims were found unsearchable (Continuation of item 2 of first sheet)

This international search report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☒ Claims Nos.: 11
because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out, specifically:
see FURTHER INFORMATION sheet PCT/ISA/210
3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box No. III Observations where unity of invention is lacking (Continuation of item 3 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

1. ☐ As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fees, this Authority did not invite payment of additional fees.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest and, where applicable, the payment of a protest fee.
- ☐ The additional search fees were accompanied by the applicant's protest but the applicable protest fee was not paid within the time limit specified in the invitation.
- ☐ No protest accompanied the payment of additional search fees.

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/US2008/008293

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5415936 A	16-05-1995	DE 4202695 A1 JP 2509431 B2 JP 5279041 A	05-08-1993 19-06-1996 26-10-1993
DE 19616781 A1	06-11-1997	CA 2203726 A1 CN 1167729 A EP 0808880 A2 JP 3553315 B2 JP 10087317 A	26-10-1997 17-12-1997 26-11-1997 11-08-2004 07-04-1998
US 2005241531 A1	03-11-2005	AU 2003255310 A1 BR 0313967 A CA 2496914 A1 CN 1678695 A DE 10239424 A1 WO 2004020531 A1 EP 1530613 A1 JP 2005536611 T KR 20050059100 A KR 20070044077 A	19-03-2004 19-07-2005 11-03-2004 05-10-2005 11-03-2004 11-03-2004 18-05-2005 02-12-2005 17-06-2005 26-04-2007
EP 1591490 A	02-11-2005	AU 2005201697 A1 CA 2505084 A1 JP 2005314701 A KR 20060056219 A US 2005239921 A1	10-11-2005 27-10-2005 10-11-2005 24-05-2006 27-10-2005
US 2006171872 A1	03-08-2006	NONE	