



(51) International Patent Classification:
G11B 5/855 (2006.01) *B81C 1/00* (2006.01)
G03F 7/00 (2006.01)

(21) International Application Number:
PCT/US2009/064448

(22) International Filing Date:
13 November 2009 (13.11.2009)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
12/270,511 13 November 2008 (13.11.2008) US

(71) Applicant (for all designated States except US): **SEA-GATE TECHNOLOGY, LLC** [US/US]; 920 Disc Drive, Scotts Valley, CA 95066 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **LEE, Kim, Yang** [MY/US]; 2672 Benchmark Ave., Fremont, CA 94536 (US). **KUO, David, S.** [US/US]; 3308 Kipling St., Palo Alto, CA 94306 (US). **BUECHEL, Dorothea** [DE/US]; 1269 Avenida Las Brisas, San Jose, CA 95131 (US). **PELHOS, Kalman** [HU/US]; 5728 Solway Street, Pittsburgh, PA 15217 (US).

(74) Agent: **GWIN, H., Sanders, Jr.**; Shumaker & Sieffert, P.A., 1625 Radio Dr. Suite 300, Woodbury, MN 55125 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD,

[Continued on next page]

(54) Title: ULTRA THIN ALIGNMENT WALLS FOR DI-BLOCK COPOLYMER




Fig. 1a




Fig. 1b




Fig. 1c

Fig. 1

(57) Abstract: Methods comprising providing a pre-patterned substrate having an array of thick walls, depositing a conforming layer on the pre-patterned substrate, etching the conforming layer from the top of the thick walls and the space between the walls, and etching the thick walls while leaving thin walls of conforming layer.



ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ,

Published:

— *with international search report (Art. 21(3))*

ULTRA THIN ALIGNMENT WALLS FOR DI-BLOCK COPOLYMER

Background

[0001] The superparamagnetic effect poses a serious challenge for continuing to increase the areal density and storage capacity of disk drives. One of the most promising methods to circumvent the density limitations imposed by this is the use of patterned media. In conventional media, the magnetic recording layers is a thin film of magnetic alloy, which naturally forms a random mosaic of nanometer scale grains which behave as independent magnetic elements. Each recorded bit is made up of many of these random grains. In pattern and media, the magnetic layer is created as an ordered an array of highly uniform islands, each island capable of storing an individual bit.

[0002] In conventional media, bit cells are fabricated on circular tracks on a disk. Each bit cell comprises many tiny magnetic grains. Each grain behaves like an independent magnet whose magnetization can be flipped by a write head during the data writing process. These grains are irregularly shaped and randomly oriented. If the grains are small relative to the size of the bit cell, the magnetic transitions are straight enough so that it is easy to detect the boundary between adjacent bit cells. Shrinking the bit cells to increase areal density, however, without shrinking the grain size makes the magnetic transitions harder to detect.

[0003] The traditional solution to this problem has been to shrink the grain size. However, there is a practical limit. The magnetization of very small grains is unstable. According to the superparamagnetic effect, the magnetization of a grain

can flip spontaneously if the product of the grain volume and its anisotropy energy falls below a certain value. The result is a loss of data.

[0004] In patterned media, each bit is stored in a single deliberately formed magnetic switching volume. This may be one grain, or several exchange volume coupled grains, rather than a collection of random decoupled grains. Single switching volumes magnetic islands are formed along circular tracks with regular spacing. Magnetic transitions no longer meander between random grains but are distinct boundaries between precisely located islands.

Summary

[0005] An embodiment of the present invention provides a method comprising providing a pre-patterned substrate having an array of thick walls, depositing a conforming layer on the pre-patterned substrate, etching the conforming layer from the top of the thick walls and the space between the walls, and etching the thick walls while leaving thin walls of conforming layer.

[0006] Preferred embodiments of this invention is shown and described, simply by way of illustration of the best mode contemplated for carrying out this invention, in the following detailed description. As will be realized, this invention is capable of other and different embodiments, and its details are capable of modifications in various obvious respects, all without departing from this invention. Accordingly, the drawings and description are to be regarded as illustrative in nature and not as restrictive.

Brief Description of the Drawings

[0007] Fig. 1 is a schematic illustration of a method of fabricating patterned storage media according to one aspect of the invention.

[0008] Fig. 2a is a schematic illustration of a step in a method of fabricating thin walls for aligning diblock copolymers according to one aspect of the invention.

[0009] Fig. 2b is a schematic illustration of a step in a method of fabricating thin walls for aligning diblock copolymers according to one aspect of the invention.

[0010] Fig. 2c is a schematic illustration of a step in a method of fabricating thin walls for aligning diblock copolymers according to one aspect of the invention.

[0011] Fig. 2d is a schematic illustration of a step in a method of fabricating thin walls for aligning diblock copolymers according to one aspect of the invention.

[0012] Fig. 3 is a plan view of a step in a method of fabricating a hard mask according to one aspect of the invention.

[0013] Fig. 4 is a plan view of a step in a method of fabricating a hard mask according to one aspect of the invention.

[0014] Fig. 5 is a plan view of a step in a method of fabricating a hard mask according to one aspect of the invention.

[0015] Fig. 6 is a plan view of a step in a method of fabricating a hard mask according to one aspect of the invention.

[0016] Fig. 7a is a schematic illustration of a step in a method of fabricating a nano-stamper according to one aspect of the invention.

[0017] Fig. 7b is a schematic illustration of a step in a method of fabricating a nano-stamper according to one aspect of the invention.

[0018] Fig. 7c is a schematic illustration of a step in a method of fabricating a nano-stamper according to one aspect of the invention.

[0019] Fig. 7d is a schematic illustration of a step in a method of fabricating a nano-stamper according to one aspect of the invention.

[0020] Fig. 7e is a schematic illustration of a step in a method of fabricating a nano-stamper according to one aspect of the invention.

[0021] Fig. 7f is a schematic illustration of a step in a method of fabricating a nano-stamper according to one aspect of the invention.

[0022] Fig. 7g is a schematic illustration of a step in a method of fabricating a nano-stamper according to one aspect of the invention.

[0023] Fig. 7h is a schematic illustration of a step in a method of fabricating a nano-stamper according to one aspect of the invention.

[0024] Fig. 7i is a schematic illustration of a step in a method of fabricating a nano-stamper according to one aspect of the invention.

Detailed Description

[0025] An embodiment of the present invention provides a method comprising providing a pre-patterned substrate having an array of thick walls, depositing a conforming layer on the pre-patterned substrate, etching the conforming layer from the top of the thick walls and the space between the walls, and etching the thick walls while leaving thin walls of conforming layer.

[0026] Another embodiment of the present invention includes a device comprising a substrate and an array of thin walls on the substrate, wherein the thin walls have a thickness of about 5 nm or less.

[0027] Another embodiment of the present invention includes a device comprising a substrate a pattern transfer layer on the substrate and an array of holes in the pattern transfer layer, wherein the holes are aligned with an array of regions lacking holes, and wherein the regions lacking holes have a thickness of about 5 nm or less.

Examples

[0028] Figure 1 illustrates one proposed method for fabricating patterned media 100. A thin layer of UV-curable photoresist 120 is spread on the surface of a substrate 110. A transparent hard mask (or stamper) 130 is then pressed into the photoresist layer 120. While the hard mask 130 is in contact with the resist, UV light 140 is shown through the hard mask 130 onto the substrate 110. The photoresist 120 hardens, creating a relief pattern of hardened photoresist 125 matching the surface of the hard mask 130. The patterned resist 125 is then etched, typically with a reactive ion etching plasma 150, generating an array of pillars in the substrate 110. A magnetic recording material 170 is then deposited on the surface of the etched substrate. The magnetic material on top array of pillars forms discrete magnetic islands 160. Base magnetic material 165 at the bottom of the pillars does not play a role in the recording process because it is too far away from the magnetic write field.

[0029] Figures 2a to 2d illustrate a method of fabricating thin walls for aligning diblock copolymers according to one aspect of the invention. In this embodiment, a pre-patterned substrate 200 comprising a substrate 210, a pattern

transfer layer 220, an etch stop 230, and patterned thick walls 240 is provided (Fig 2a). Typically, the patterned thick walls 240 are approximately 50nm to 100nm thick, however, the patterned thick walls 240 may be larger. The pre-patterned substrate 200 may be produced by conventional semiconductor processes. These processes include, but are not limited to, chemical vapor deposition (CVD), organometallic chemical vapor deposition, (OMCVD), physical vapor deposition (PVD), atomic layer deposition (ALD), molecular beam epitaxy (MBE), liquid phase epitaxy (LPE), chemical etching, reactive ion etching (RIE), plasma etching, photolithography, and ion beam lithography.

[0030] A conforming layer 250 is deposited onto the pre-patterned substrate 200 (Fig. 2b). The conforming layer may be deposited by any deposition technique that provides essentially uniform thickness. Preferably, the conforming layer is uniformly thick along the sidewalls of the patterned thick walls 240. Deposition techniques include, but are not limited to, CVD, OMCVD, PVD, ALD, MBE, and LPE. In one aspect of the invention, the pattern transfer layer 220 comprises SiO_x , the etch stop 230 comprises Cr, the patterned thick walls 240 comprises Al, and the conforming layer 250 comprises SiN. These compositions are by way of example only and are not meant to be limiting.

[0031] In the next step (Fig. 2c), the conforming layer 250 is etched off the top of the patterned thick wall 240 and the etch stop 230. However, conforming layer material along the sidewalls of the patterned thick walls 240 remains. This results in the fabrication of thin walls 260 of conforming layer material.

[0032] In the final step of this embodiment of the invention, the patterned thick walls 240 are preferentially etched away. This results in an array of thin walls 260

of conforming layer material. Preferential etching may be performed by any suitable method, for example RIE. The thickness of the thin walls 260 is determined by the conforming film deposition process and may be extremely thin. Preferably, the thickness of the thin walls 260 may be approximately 5 nm or less. More preferably, the thickness of the thin walls 260 may be approximately 3 nm or less. Even more preferably, the thickness of the thin walls 260 may be approximately 1 nm or less.

[0033] Figures 3-6 illustrate another embodiment of the invention. Specifically, Figures 3-6 illustrate a method of fabricating a hard mask according to one aspect of the invention. In the first step of this embodiment, a pre-patterned substrate 205 with thin walls 260 is provided. Then, the pre-patterned substrate 205 is coated with a suitable diblock copolymer (DBCP), for example P(S-*block*-PFS). The DBCP is then allowed to microphase separate to form domains of a suitable shape. As illustrated in Figure 3, the DBCP separates to form a cylindrical phase 270 and continuous phase 275. Other known domain shapes include spherical, gyroidal, and lamellar. The choice of domain shape is controlled by the volume fraction of the various blocks in the DBCP and may be selected depending on the design of the hard mask.

[0034] In the next step, illustrated in Figure 4, the cylindrical phase 270 is preferentially etched down to the etch stop 230. The selective etching processes can be performed to leave either a positive or a negative image. In the figure, the positive image is produced.

[0035] In the next step, illustrated in Figure 5, a second preferential etch is performed. In this step, the exposed etch stop material 230 is removed as well as

the underlying pattern transfer layer 220. This may be accomplished in a single etching step or a series of steps depending on the etch stop material 230 and the pattern transfer layer 220.

[0036] In the last step, illustrated in Figure 6, the patterned thin walls 260 and the continuous DBCP phase 275 are removed. The resulting hard mask 280 comprises a substrate having arrays of regularly spaced holes in the pattern transfer layer 220. In another embodiment of the invention, the hard mask 280 can be used to fabricate patterned storage media having nanoscale domains.

[0037] Another embodiment of the invention is illustrated in Figures 7a-7i. In this embodiment, the final product is a nano-scale hard mask (or stamper) 330 similar to hard mask 130. That is, rather than having holes as in the last embodiment, nano-scale hard mask 300 has pillers suitable for pressing into a photoresist layer.

[0038] In this embodiment of the invention, a pre-patterned substrate 300 is provided. Pre-patterned substrate 300 comprises a transparent substrate 210, an etch stop layer 230, and patterned thick walls 240. Preferably, the substrate is quartz, however any suitable transparent material may be used. Preferably, the etch stop layer comprises chromium, however any suitable metal or alloy material may be used. If the etch stop layer is made of chromium, preferably it is approximately 5 nm thick. The thickness of the etch stop layer, however, may vary depending on the material used.

[0039] A conforming layer 250 is deposited onto pre-patterned substrate 300 (Fig. 7b). The conforming layer may be deposited by any deposition technique that provides essentially uniform thickness. Preferably, the conforming layer is

uniformly thick along the sidewalls of the patterned thick walls 240. Deposition techniques include, but are not limited to, CVD, OMCVD, PVD, ALD, MBE, and LPE. In one aspect of the invention, the patterned thick walls 240 comprises Al and the conforming layer 250 comprises SiN.

[0040] In the next step (Figure 7c), the conforming layer 250 is etched off the top of the patterned thick wall 240 and the etch stop 230. However, conforming layer material along the sidewalls of the patterned thick walls 240 remains. This results in the fabrication of thin walls 260 of conforming layer material.

[0041] In the next step (Figure 7d) of this embodiment of the invention, the patterned thick walls 240 are preferentially etched away. This results in an array of thin walls 260 of conforming layer material. Preferential etching may be performed by any suitable method, for example RIE. The thickness of the thin walls 260 is determined by the conforming film deposition process and may be extremely thin. Preferably, the thickness of the thin walls 260 may be approximately 5 nm or less. More preferably, the thickness of the thin walls 260 may be approximately 3 nm or less. Even more preferably, the thickness of the thin walls 260 may be approximately 1 nm or less.

[0042] In the next step (Figure 7e), a suitable diblock copolymer (DBCP) 272, for example P(S-*block*-PFS) is deposited on the etch stop 230 between the thin walls 260. The DBCP 272 is then allowed to microphase separate to form domains of a suitable shape. As illustrated in Figure 7f, the DBCP separates to form a cylindrical phase 270 and continuous phase 275. Other known domain shapes include spherical, gyroidal, and lamellar. The choice of domain shape is controlled by the volume fraction of the various blocks in the DBCP and may be selected

depending on the design of the hard mask.

[0043] In the next step, illustrated in Figure 7g, the continuous phase 275 is selectively etched down to the transparent substrate 210. That is, the etch stop 230 under the continuous phase 275 is etched away as well. Selective etching of the continuous phase 275 and the etch stop 230 may be performed with the same selective etch or in two steps under different etching conditions. The final result of this step is a pattern of cylindrical pillars comprising etch stop 230 material and cylindrical DBCP phase 270.

[0044] In the next step, illustrated in Figure 7h, another preferential etch is performed. In this step, the underlying transparent substrate 210 is etched. As illustrated, the cylindrical DBCP phase 270 is also removed in this step. The removal of the cylindrical DBCP phase 270, however, may be accomplished in a separate etching step.

[0045] In the final step, the etch stop 230 is removed from the substrate 210. The result is a transparent nano-scale hard mask 330. The nano-scale hard mask 330 is suitable for use in nano-imprint lithography. It can, for example, be used in the method illustrated in Figure 1 to produce storage media having nano-scale domains.

[0046] The implementations described above and other implementations are within the scope of the following claims.

Claims

1. A method comprising:
 - providing a pre-patterned substrate having an array of thick walls;
 - depositing a conforming layer on the pre-patterned substrate;
 - etching the conforming layer from the top of the thick walls and the region of substrate between the walls; and
 - removing the thick walls while leaving thin walls of conforming layer.
2. The method of claim 1, wherein the thin wall thickness is less than or equal to 10 nm.
3. The method of claim 1, where the think wall thickness is approximately 1 nm.
4. The method of claim 1, wherein the conforming layer comprises SiN.
5. The method of claim 1, wherein the thin walls of conforming layer have a thickness of about 5 nm or less.
6. The method of claim 1, wherein the thin walls of conforming layer have a thickness of about 3 nm or less.
7. The method of claim 1, wherein the thin walls of conforming layer have a thickness of about 1 nm or less.

8. The method of claim 1, further comprising:
 - depositing a diblock copolymer on the substrate between the thin wall;
 - allowing the diblock copolymer to phase separate into a continuous phase and an a discrete phase, the discrete comprising an array of regions aligned with the thin walls;
 - etching away one phase of the diblock copolymer;
 - etching the pre-patterned substrate using one phase of the diblock copolymer as a resist pattern; and
 - removing the diblock copolymer and the thin walls.
9. The method of claim 8, wherein the diblock copolymer phase separates into cylinders or spheres.
10. The method of claim 8, wherein etching away one component of the diblock copolymer leaves a negative image.
11. The method of claim 9, further comprising using the etched pre-patterned substrate to fabricate a media storage device.
12. The method of claim 11, wherein the media storage device comprises islands of magnetic material corresponding to the cylinders or spheres.
13. A device comprising:
 - a substrate; and
 - an array of thin walls on the substrate,
 - wherein the thin walls have a thickness of about 5 nm or less.
14. The device of claim 13, wherein the thin walls have a thickness of about 3 nm or less.
15. The device of claim 14, wherein the thin walls have a thickness of about 1 nm or less.

16. The device of claim 13, further comprising a diblock copolymer on the substrate.

17. The device of claim 16, wherein the diblock copolymer comprises a continuous phase and a discrete phase, the discrete phase comprising an array of regions aligned with the thin walls.

18. A device comprising:

a transparent substrate with an array of transparent pillars,
wherein the transparent pillars are aligned with an array of regions corresponding to sidewalls adjacent pre-patterned thick walls, the pre-patterned thick walls ranging from approximately 50 nm to 100 nm and the regions corresponding to the sidewalls have a thickness of about 5 nm or less.

19. The device of claim 18, wherein the regions corresponding to the sidewalls have a thickness of about 3 nm or less.

20. The device of claim 19, wherein the regions corresponding to sidewalls have a thickness of about 1 nm or less.




Fig. 1a




Fig. 1b




Fig. 1c

Fig. 1




Fig. 2a




Fig 2b

Fig. 2





Fig. 2

205




Fig. 3




Fig. 4




Fig. 5







Fig. 6




1) Starting substrate and layers (use same numbering as disclosure)




2) Conformal coating as described in disclosure




3) Thin wall formation




4) Thin wall formation (continued)




5) DBCP coating




6) DBCP microphase separation to form cylindrical pillars



7) Transfer pattern into Cr layer by reactive-ion etching



8) Transfer pattern into quartz by RIE (e.g. using CF₄ plasma)



9) Remove Cr mask by wet etching

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2009/064448

A. CLASSIFICATION OF SUBJECT MATTER

INV. G11B5/855 G03F7/00 B81C1/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

G11B G03F B81C H01L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2007/215960 A1 (ZHU ET AL.) 20 September 2007 (2007-09-20)	1-7, 13-15, 18-20
Y	paragraph [0106] - paragraph [0108]; figures 1,5	8-10, 16-17
X	US 2007/170146 A1 (HUANG ET AL.) 26 July 2007 (2007-07-26) paragraphs [0003], [0019] - [0021], [0026]; figure 3	1-7, 11-15
X	WO 2008/033695 A2 (MICRON TECHNOLOGY) 20 March 2008 (2008-03-20) page 12, line 3 page 14, line 9 - line 10 page 14, line 27 - page 15, line 3 page 16, line 29 - page 17, line 27; figures 10-14	1,4
	----- -/--	

☒ Further documents are listed in the continuation of Box C.

☒ See patent family annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

16 December 2009

Date of mailing of the international search report

22/12/2009

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040,
Fax: (+31-70) 340-3016

Authorized officer

Magrizo, Simeon

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2009/064448

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	WO 2008/097736 A2 (MICRON TECHNOLOGY) 14 August 2008 (2008-08-14) page 3, line 16 - page 4, line 2 page 6, line 4 - line 7 page 18, line 18 page 19, line 13 - line 29; figures 1-4 -----	8-10, 16-17

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/US2009/064448

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 2007215960 A1	20-09-2007	NONE	
US 2007170146 A1	26-07-2007	CN 101371336 A KR 20080097439 A US 2008017314 A1 WO 2007087159 A1	18-02-2009 05-11-2008 24-01-2008 02-08-2007
WO 2008033695 A2	20-03-2008	CN 101512726 A EP 2062288 A2 KR 20090073157 A US 2008070165 A1	19-08-2009 27-05-2009 02-07-2009 20-03-2008
WO 2008097736 A2	14-08-2008	CN 101578232 A EP 2121514 A2 US 2008193658 A1	11-11-2009 25-11-2009 14-08-2008