



(43) International Publication Date
29 October 2015 (29.10.2015)

(10) International Publication Number
WO 2015/164095 A2

- (51) International Patent Classification: Not classified
- (21) International Application Number:
PCT/US2015/025281
- (22) International Filing Date:
10 April 2015 (10.04.2015)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
61/982,069 21 April 2014 (21.04.2014) US
- (71) Applicant: **HENKEL IP & HOLDING GMBH**
[DE/DE]; Henkelstrasse 67, 40589 Duesseldorf (DE).
- (72) Inventors; and
- (71) Applicants (*for US only*): **LU, Victor** [US/US]; 60 Park-
side Circle, Marietta, Georgia 30068 (US). **LI, Chunzhao**
[CN/US]; 5 McMannus Drive, Hillsborough, New Jersey
08844 (US).
- (74) Agents: **LEHMANN, Sun Hee** et al.; Henkel Corporation,
One Henkel Way, Rocky Hill, Connecticut 06067 (US).
- (81) Designated States (*unless otherwise indicated, for every
kind of national protection available*): AE, AG, AL, AM,

AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY,
BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM,
DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT,
HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR,
KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG,
MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM,
PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC,
SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN,
TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

- (84) Designated States (*unless otherwise indicated, for every
kind of regional protection available*): ARIPO (BW, GH,
GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ,
TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU,
TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE,
DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU,
LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK,
SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,
GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— *without international search report and to be republished
upon receipt of that report (Rule 48.2(g))*

(54) Title: CURABLE ADHESIVE COMPOSITIONS AND USE THEREOF

(57) Abstract: A solvent-less hybrid curable composition is prepared from grafting polyesters or polyamides onto a (meth)acrylic copolymer backbone. Besides the many benefits of a solvent-less system, the hybrid curable composition forms strong adhesion to polar substrates, widens the use temperatures, and enables faster processing speeds than conventional hybrid curable compositions. The solvent-less hybrid curable composition forms an optically clear single phase that is suitable as tapes and labels, or in electronic, optoelectronic, OLED and photovoltaic devices, and the like.



WO 2015/164095 A2

CURABLE ADHESIVE COMPOSITIONS AND USE THEREOF

FIELD OF THE INVENTION

[0001] The present invention relates to curable hybrid acrylic-polyester or acrylic-polyamide adhesives and/or pressure sensitive adhesives. More particularly the hybrid adhesives are optically clear, making these adhesives particularly well suited for variety of bonding applications.

BACKGROUND OF THE INVENTION

[0002] Solvent-based curable adhesives, particularly solvent based pressure sensitive adhesives are widely known. However, solvent based curable adhesives suffer from a number of shortcomings, including longer production time, higher energy consumption, difficulties in the control of production process and final product quality. Moreover, complete removal of solvent from the solvent-based curable adhesives is challenging, which can result in emission of solvent vapors and outgassing issues in the final product and during use. The final product may not be aligned with current concerns for industry to reduce solvent and volatile organic solvents.

[0003] Another drawback associated with solvent-based curable adhesives is its inability to form a thicker coating layer at a single application pass. Multiple passes are typically required to remove solvent for coating thicknesses greater than 100 microns for solvent-based curable adhesives. Heat is often applied to drive the solvent off of the solvent-based curable adhesives, yet high application temperature or prolonged heating can lead to premature curing in the application equipment.

[0004] Solvent-less system is desirable for curable adhesives because it offers a 100% conversion rates with safer and more economical means.

[0005] While some solvent-less systems, such as hybrid adhesives, are available on the market, they have poor performances. Acrylic-polyester based hybrid copolymers have poor performances and appearances. Polyester portions of the copolymer can crystallize out of the copolymers, leading to incompatibility and poor performances as an adhesive.

[0006] U.S. Patents 4,181,752 and 4,364,972 describe a system wherein a coatable syrup is formed by small degree of prepolymerizing a monomer mixture. The syrup

contains a large quantity of unreacted monomers, which must be irradiated to undergo polymerization.

[0007] U.S. Patent 5,879,759 describes a copolymer formed by first partially polymerizing a monomer mixture with irradiation and then adding additional monomers or oligomers and further irradiating the mixture. The resultant polymer, however, cannot build high molecular weight in the curing time frames and thus, desirable high performances cannot be achieved.

[0008] EP 2548901 describes a radiation curable composition comprising a (meth)acrylic copolymer A and a radiation curable compound B, wherein the process involves a first copolymerization step and then a subsequent ring opening step. One major drawback to this composition is incompatibility of the radiation curable compound B with the (meth)acrylic copolymer A. In addition, the rheology profile of the radiation curable compound B has insufficient pressure sensitivity.

[0009] Similarly, U.S. Patent Publication 2013/0251912 describes a mixture of a (meth)acrylic copolymer and a UV curable oligomer. The mixture can lead to immiscibility over time, leading to poor adhesive performances.

[0010] There is a need in the art to overcome the disadvantages and limitations that exist with solvent-based and curable hybrid copolymer adhesives and/or pressure sensitive adhesives. The current invention fulfills this need.

BRIEF SUMMARY OF THE INVENTION

[0011] The present invention relates to solvent-less hybrid curable composition prepared from grafting polyesters or polyamides onto acrylic copolymer backbones. The solvent-less hybrid curable composition forms a single phase that is optically clear. Unlike the conventional linear hybrid curable compositions, the inventive grafted hybrid curable composition forms strong adhesion to polar substrates, widens use temperatures, and enables faster processing speeds than conventional non-hybrid compositions.

[0012] In one embodiment, there is provided a solvent-less, curable composition comprising a hybrid copolymer having a meth(acrylic copolymer) backbone and a plurality of a monomer or an oligomer grafted onto the meth(acrylic copolymer)

backbone. The monomer or the oligomer comprises at least one -O- or -NH- functional group.

[0013] Another embodiment provides a solvent-less, hybrid curable composition comprising a plurality of oligomeric side chains grafted onto a (meth)acrylic copolymer backbone. The (meth)acrylic copolymer backbone comprises (meth)acrylic monomers and hydroxyl group containing monomers. The oligomeric side chain is a polyester or a polyamide.

[0014] Yet another embodiment provides a process for forming a hybrid copolymer comprising the steps of (1) copolymerizing an acrylic copolymer backbone comprising: (i) a (meth)acrylic monomer, (ii) a hydroxyl group containing monomer and (iii) a cyclic compound having at least one functional group, -O- or -NH-, in the cyclic structure; and (2) opening the cyclic compound with a catalyst, whereby the cyclic compound is grafted on the acrylic copolymer backbone.

DETAILED DESCRIPTION OF THE INVENTION

[0015] All disclosure of all documents cited herein are incorporated in their entireties by reference.

[0016] Acrylic copolymers are incompatible with polyesters and polyamides, and when combined, they form a hazy appearance because one of the copolymers crystallize out of the mixture. Unlike the mixture, the solvent-less hybrid curable composition is completely miscible and forms a single phase without any separation or haziness. The hybrid may be used for optically clear applications and has superior adhesive performances than conventional mixtures of acrylic and other polymer systems.

[0017] The solvent-less, curable hybrid copolymer is prepared from a (meth)acrylic copolymer backbone and a plurality of monomers or oligomers that comprises an -O- or -NH- functional group. The backbone of the curable hybrid copolymer is formed by a meth(acrylic monomer) (A1) and a copolymerizable hydroxyl group containing monomer (A2).

[0018] The term "(meth)acryl" is to be understood as to encompass both the terms "acryl" and "methacryl" and refers to compounds comprising at least one acrylate group ($\text{CH}_2=\text{CHCOO}-$) and/or at least one methacrylate group ($\text{CH}_2=\text{CCH}_3\text{COO}-$). The

alkyl(meth)acrylates are preferably selected from linear and branched aliphatic alkyl(meth)acrylates.

[0019] The (meth)acrylic monomer (A1) is generally used in an amount from about 30 to about 99 wt% based on the sum of the hybrid copolymer mixture. The amount of (meth)acrylic monomer (A1) is preferably at least about 40 wt%, more preferably at least 50 wt%, preferably up to about 95 wt%, more preferably up to about 90 wt% based on the sum of the hybrid copolymer mixture.

[0020] The alkyl(meth)acrylates are preferably selected from linear and branched aliphatic alkyl(meth)acrylates, more preferably from those having from 3 to 20 carbon atoms in the alkyl group. Particularly preferred are methyl methacrylate, n-butylacrylate, iso-butylacrylate, 2-ethyl hexylacrylate, isobutyl methacrylate, methoxy polyethylene glycol acrylate (average Mn 350), and mixtures thereof.

[0021] The copolymerizable hydroxyl group containing monomer (A2) is generally used in an amount of about 1 to about 30 wt% based on the sum of the hybrid copolymer mixture. The amount of copolymerizable hydroxyl group containing monomer (A2) used is preferably at least about 1 wt%, more preferably at least about 5 wt%, and up to about 30 wt%, and more preferably up to about 20 wt% based on the sum of the hybrid copolymer mixture.

[0022] The copolymerizable hydroxyl group containing monomer (A2) contains at least one hydroxyl functional group that can react with the cyclic compound (B) during the ring opening reaction step. The copolymerizable hydroxyl group containing monomer contains a hydroxyl group either in an aromatic or an aliphatic form. Preferred hydroxyl group containing monomer (A2) include hydroxyalkyl(meth)acrylates, the ethoxylated and/or propoxylated derivatives thereof, the adducts thereof with lactones, polyalkoxy monohydroxy mono(meth)acrylates. Particularly preferred are hydroxyalkyl(meth)acrylates having from 1 to 20 carbon atoms in the alkyl group, the ethoxylated and/or propoxylated derivatives thereof, the adducts thereof with lactones, polyalkoxy monohydroxy mono(meth)acrylates. Examples of such compounds comprise hydroxyethyl(meth)acrylate, hydroxypropyl(meth)acrylate, hydroxybutyl(meth)acrylate, hydroxypentyl(meth)acrylate, hydroxyheptyl(meth)acrylate, hydroxynonyl(meth)acrylate, hydroxydecyl(meth)acrylate, their position isomers, the

ethoxylated and/or propoxylated derivatives thereof, the adducts thereof with lactones, diethylene glycol mono(meth)acrylate, polyethylene glycol mono(meth)acrylate, propylene glycol mono(meth)acrylate, polypropylene glycol mono(meth)acrylate.

[0023] Another preferred hydroxyl group containing monomer (A2) include phenol groups, such as 4-vinylphenol.

[0024] Another preferred hydroxyl group containing monomer (A2) are those containing carboxylic acid groups, and mixtures of any of them. Examples of such compounds are (meth)acrylic acid, β -carboxyethyl(meth)acrylate, crotonic acid, maleic acid, fumaric acid, itaconic acid. Mixtures of any of the above copolymerizable monomers can be used. More preferred copolymerizable monomers are 2-hydroxyethyl(meth)acrylate, 2-hydroxybutyl(meth)acrylate, 4-hydroxybutyl(meth)acrylate, and mixtures thereof. Most preferred are 2-hydroxyethylacrylate, 2-hydroxybutylacrylate, 4-hydroxybutylacrylate, and mixtures thereof.

[0025] Optionally, the backbone may further comprises additional copolymerizable monomers. The optional copolymerizable monomer (A3) may be added up to 60 wt % of the backbone, preferably up to 50 wt%, more preferably up to 40 wt % based on the sum of the hybrid copolymer mixture. The copolymerizable monomer (A3) is generally a compound containing at least one copolymerizable carbon-carbon double bond. Copolymerizable carbon-carbon double bonds are known to the skilled person and include (meth)acrylate, vinyl, allyl types of double bonds. Suitable copolymerizable monomers (A3) are linear and branched aliphatic alkyl(meth)acrylates, especially those having from 1 to 20 carbon atoms in the alkyl group, glycidyl(meth)acrylate, vinyl acetate, styrene and mixtures thereof. Particularly preferred are methyl(meth)acrylate, ethyl(meth)acrylate, tert-butyl(meth)acrylate, vinyl acetate, styrene and mixtures thereof.

[0026] In another embodiment, the optional copolymerizable monomer contains a photoinitiator group in the monomer, in an amount of up to about 10 wt%, and preferably up to about 3 wt%, based on the sum of the hybrid copolymer mixture. Exemplary copolymerizable monomers containing photoinitiator groups include 2-(4-benzoyl-3-hydroxyphenoxy)ethyl acrylate, benzoin acrylate, 2-hydroxy-1-[4-(2-acryloyloxyethoxy)phenyl]-2-methyl-1-propanone, 4-acryloyloxy benzophenone, and

mixture of 4-acryloyloxyoligoethylenoxy carbonyl-benzophenones. Also preferred photoinitiator containing coolymerizable monomers include those taught in EP 167870.

[0027] The backbone is formed by copolymerizing the (meth)acrylic monomer (A1) and the copolymerizable hydroxyl group containing monomer (A2). The copolymer may be a random, alternating or block copolymer. It is preferably a random copolymer. The copolymerization in the copolymerization step may take place by free-radical copolymerization. This may take place in a manner known to the skilled person by conventional methods, particularly by free-radical polymerization using thermal radical initiators. Examples of suitable thermal radical initiators include peroxides, such as benzoyl peroxide, azo compounds, such as azo-bis-isobutyronitrile, azo-bis-dimethylpentanenitrile, azo-bis-methylbutyronitrile, azo-bis-cyanocyclohexane. The initiators may be used, for example, in amounts from 0.05 to 2.0 wt % based on the sum of the hybrid copolymer mixture.

[0028] To achieve a good control of the molecular weight and its distribution, a chain transfer agent, preferably of the mercaptan type, such as n-dodecylmercaptan, tert-dodecanethiol, iso-octylmercaptan, n-octylmercaptan or of the carbon halide type, such as carbon tetrabromide, bromotrichloromethane, can also be added in the course of the reaction. The chain transfer agent is generally used in amounts of up to 5 wt% based on the sum of the hybrid copolymer mixture.

[0029] The copolymerization is generally carried out at a temperature from 60 to 150°C, preferably under an inert gas atmosphere. The copolymerization is preferably carried out at a temperature from 60 to 100°C.

[0030] The backbone copolymerization is followed by a subsequent step of opening the cyclic compound. The ring opening step grafts the cyclic compound B onto the (meth)acrylic polymer backbone. The cyclic compound is grafted at the hydroxyl group of the (meth)acrylic polymer backbone. The cyclic compound having at least one functional group X in the cyclic structure, where X is -O- or -NH-. The amount of cyclic compound having a functional group (B) used is preferably at least 5 wt%, more preferably at least 10 wt%, preferably up to 30 wt%, more preferably up to 60 wt%, based on the sum of the hybrid copolymer mixture. Preferred cyclic compounds include lactones, lactams, lactides, cyclic carbonates and mixtures thereof. Preferred

cyclic compounds B are lactones and lactides and mixtures thereof. Particularly preferred are lactones such as L(-)lactide, ϵ -caprolactone, δ -valerolactone, γ -butyrolactone, and lactones of hydroxycarboxylic acids such as 2-hydroxycarboxylic acids, e.g. glycolic acid and lactic acid, 3-hydroxycarboxylic acids, e.g. 3-hydroxypropionic acid, 3-hydroxybutyric acid, 3-hydroxyvaleric acid and hydroxypivalic acid. More preferred are ϵ -caprolactone, δ -valerolactone, γ -butyrolactone and mixtures thereof, most preferred is ϵ -caprolactone.

[0031] The ring opening step is generally carried out at room temperature to up to about 150°C. The ring opening reaction can take place without the use of a catalyst, but the reaction rate can be increased with the addition of the catalyst. Therefore, the ring opening reaction preferably takes place in the presence of at least one catalyst. Suitable catalysts include alkali or alkaline earth metal alkoxides, organic acids, inorganic acids and Lewis acids such as sodium methoxide, calcium methoxide, aluminum isopropoxide, tetraalkyl titanates, titanium chelates, titanium acylates, lead salts, lead oxides, zinc borate, antimony oxide, stannous octoate, tin laurate, tin octoate, dibutyl tin dilurate, sulfuric acid, hydrochloric acid, phosphoric acid, boron trifluoride. Another preferred catalyst include yttrium alkoxides and lanthanum alkoxides, both of which can be used to carry out the ring opening step at room temperature. The catalyst can be used in amounts of up to 1% based on the sum of the hybrid copolymer mixture.

[0032] The resultant hybrid copolymer contains a random copolymer of (meth)acrylic copolymers and a plurality oligomeric arms grafted onto the backbone. The backbone contains hydroxyl or amine terminal functional groups in the oligomeric arms.

[0033] The hybrid curable copolymer can be used as is, or can be further formulated and mixed with other components.

[0034] Additional monomers such as UV-curable monomer and UV-curable resin can be added to the hybrid curable copolymer. The mixture can then be irradiated to crosslink the mixture. In another embodiment, the hybrid curable copolymer backbone can be thermally cured with the addition of isocyanate and/or melamine crosslinkers.

[0035] Optionally, tackifier, photoinitiator, stabilizer, viscosity modifiers may be added to the hybrid curable copolymer. They may be added in amounts known in the art to impart specific performances to the cured composition.

[0036] The crosslinked hybrid composition forms strong bonds with polar substrates, and particularly with PVC, glass, polyester polyurethane foam, and the like. The grafted polyester or polyamide side chains of the crosslinked (meth)acrylic polymer forms hydrogen bonds with polar substrates and stronger adhesion is formed.

[0037] The crosslinked hybrid composition is also optically clear and remains in a single phase. Polyesters or polyamide in the hybrid composition does not crystallize out of the hybrid polymer. Due to the optically clear properties, the hybrid composition is suitable in many applications such as labels or tapes; electronics, optoelectronics, OLEDs, photovoltaic devices; and the like. Because the hybrid composition remains in a single phase, and peel, tack and shear performances remain superior, especially on polar substrates.

[0038] The hybrid composition also has wider use temperature since the viscosity of the grafted hybrid composition is lower than the non-hybrid, linear-chain copolymer at the same temperature. Some benefits associated with lower viscosity of the hybrid compositions include faster coating speeds, faster processing speeds, easier filtration, lower thermal degradation and better leveraging of the coated substrate surfaces. Moreover, the hybrid composition can be manufactured and coated at lower temperatures, which decreases overall carbon footprint.

[0039] Many modifications and variations of this invention can be made without departing from its spirit and scope, as will be apparent to those skilled in the art. The specific embodiments described herein are offered by way of example only, and the invention is to be limited only by the terms of the appended claims, along with the full scope of equivalents to which such claims are entitled.

EXAMPLES

[0040] Peel strength was measured by performing a 180° peel test on stainless steel panels using an Instron. About 1.0 mil thick coating of the adhesive was applied on to silicone release paper using heated rollers and bonded to Mylar film. Three specimens each 1" by 1" in dimensions were cut perpendicular to the machine direction from the coated Mylar. After conditioning overnight at 72°F. and 50% relative humidity, the release paper was removed and the specimens are bonded to stainless steel panels. The bonds are then rolled using a 4.5 lb. roller. After conditioning the bonds for about 20

minutes, the bonds were peeled in the Instron at 2"/minute. The stainless steel panel was in the stationary jaw, and the Mylar was in the movable jaw. The results are reported as an average load in oz/in. This test was repeated after conditioning for 24 hours.

[0041] For shear measurement, about 1.0 mil thick coating of the adhesive was applied on to silicone release paper using heated rollers and bonded to Mylar film. The lamination was cut to 1 by 1/2 inch strips. The release paper is removed and the Mylar bonded to stainless steel. A one mil transfer coating of the adhesive was made using heated rollers and a 1.0 by 0.5 inch strip of the specimen was bonded to a stainless steel plate. The bonds were then rolled using a 4.5 lb roller. After conditioning the bonds for about five hours, the plates are secured onto the shear test stand a 1000 gram weight is applied to each plate. The time that the specimen takes to slip from the plate was recorded as shear strength.

[0042] Solvent-less, curable hybrid compositions were made in accordance with the following components and processes and irradiated with UV radiation to form cured hybrid compositions.

Example 1:

[0043] In a one-liter, four-neck glass reaction flask equipped with a stirrer, a water cooled condenser and an inlet for nitrogen and a thermoprobe mounted in the flask which is attached to a thermoregulator for mass temperature control, Solution 1 was charged to the flask and the content was heated to 70°C. The temperature was kept at 70°C for 60 minutes under continuous agitation. The nitrogen purged through the flask at a moderate rate. The Solution 2 was then added to the reaction vessel over 80 minutes period while the temperature was continuously kept at 70°C. After the addition of the Solution 3, the reaction was kept at 70°C for 60 minutes and then at 80°C for another 60 minutes. The solution was then charged to the flask under agitation and the reaction was carried at 115°C for 5 hours.

Solution 1	Amounts (g)
caprolactone	80.0
2-ethylhexyl acrylate and/or Isobutyl methacrylate	104.0
2-hydroxethyl acrylate	12.0
photoinitiator	0.1

Chain transfer agent	0.4
Initiator	0.4

Solution 2	Amounts (g)
2-ethylhexyl acrylate and/or Isobutyl methacrylate	104.0
methoxy polyethylene glycol acrylate (350 mw),	2.0
2-hydroxethyl acrylate	12
photoinitiator	0.7
Chain transfer agent	0.7
initiator	0.4

Solution 3	Amounts (g)
Hydroxyl butyl acrylate	9.8
stabilizer	0.15
catalyst	0.015

[0044] The final polymer was a colorless and optically clear, without any separation of phases.

[0045] A 25 microns thick coating was first coated onto a PET film and then cured under H-bulb (Fusion System) with 40 mJ/cm² UVC radiation. The cured coating had the following properties:

- (a) 20min peel on stainless steel panel: about 41.1 oz/inch
- (b) 24h peel on stainless steel panel: about 44.0 oz/inch
- (c) Shear at room temperature (4.4psi): about 4.8 hours

[0046] The cured hybrid copolymer, when applied as coating was clean, water-white and remained clear at room temperature for over 6 months. The cured hybrid copolymer had good adhesion properties as adhesive coatings.

Example 2:

[0047] In a one-liter, four-neck glass reaction flask equipped with a stirrer, a water cooled condenser and an inlet for nitrogen and a thermoprobe mounted in the flask which is attached to a thermoregulator for mass temperature control, Solution 1 was charged to the flask and the content was heated to 70°C. The Solution 2 was then added to the reaction vessel over 180 minutes period while the temperature was continuously kept at 70°C. After the addition of the Solution 2, the reaction was kept at

70°C for 60 minutes and then at 80°C for another 60 minutes. Following the 60 minutes hold, Solution 3 was charged to the reaction mixture under agitation and the reaction was carried at 105°C for eight hours to finish the reaction.

Solution 1	Amounts (g)
Caprolactone	56.00
Initiator	0.28

Solution 2	Amounts (g)
One or more selected from: 2-ethylhexyl acrylate, Isobutyl methacrylate, hydroxyl butyl acrylate	286.72
Caprolactone	50.40
Chain transfer agent	67.20
Initiator	2.04
	1.48

Components to Solution 3	Amounts (g)
Viscosity modifier	21.00
Stabilizer	0.19
Catalyst	0.07

[0048] One hundred parts of the reaction products were then formulated with 5 parts crosslinking monomer, 5 parts tackifying monomer, 10 parts viscosity modifier, and 0.3 parts photoinitiator.

[0049] A 175 microns thick coating coated onto a PET substrate and then was cured under H-bulb (Fusion System) with 950 mJ/cm² UVA radiation.

[0050] The cured product was colorless and optically clear, without any separation of phases. The cured coating also had the following properties:

- (a) 20min peel on stainless steel panel: about 23.6 oz/inch; and
- (b) 24h peel on stainless steel panel: about 24.4 oz/inch.

[0051] Even with a thickness that is seven-folds greater than a typical adhesive coating, the cured product had good peel properties. The adhesive coating was then aged under each of the following conditions:

- (1) Thermal aging in 85°C oven for 500 hours;
- (2) Weathering oven (60°C and 95% RH) for 500 hours; or
- (3) Accelerated UV radiation aging (QUV) for 500 hours.

All the adhesives remained colorless and optically clear, without any phase separation.

CLAIMS

I/We claim:

1. A solvent-less, curable composition comprising a hybrid copolymer having a meth(acrylic copolymer) backbone and a plurality of a monomer or an oligomer grafted onto the meth(acrylic copolymer) backbone,
wherein the monomer or the oligomer comprises an -O- or -NH- functional group.
2. The curable composition of claim 1, wherein the meth(acrylic copolymer) backbone is prepared with at least two acrylic monomers, and wherein at least one of the two acrylic monomers contains a hydroxyl functional group.
3. The curable composition of claim 1, wherein the meth(acrylic copolymer) backbone further comprises less than about 10 wt% of a third (meth)acrylic monomer that contains a photoinitiator group.
4. The curable composition of claim 1, wherein the hybrid copolymer is an acrylic-polyester copolymer and the monomer or the oligomer comprises an -O- functional group.
5. The curable composition of claim 4, wherein the oligomer with the -O- functional group has a molecular weight of about 200 to about 5000 Daltons.
6. The curable composition of claim 1 further comprising an isocyanate monomer, melamine crosslinker, UV-curable monomer, UV-curable resin, tackifier, photoinitiator, cross-linker, chain transfer reagent, and/or stabilizer.
7. A cured composition comprising the curable composition of claim 1.
8. The cured composition of claim 7, which is a tape, label, electronic device, optoelectronic device, OLED, or photovoltaic device.

9. A solvent-less, hybrid curable composition comprising a plurality of oligomeric side chains grafted onto a (meth)acrylic copolymer backbone that comprises:
- (1) a first (meth)acrylic monomer and
 - (2) a hydroxyl group containing monomer;
- wherein the oligomeric side chain is a polyester or a polyamide.
10. The solvent-less, hybrid curable composition of claim 9, wherein the (meth)acrylic copolymer backbone further comprises less than about 10 wt% of a third (meth)acrylic monomer that contains a photoinitiator group.
11. The solvent-less, hybrid curable composition of claim 9, wherein the oligomeric copolymer is an polyester and comprises an -O- functional group.
12. The solvent-less, hybrid curable composition of claim 9, wherein the oligomer copolymer has a molecular weight of about 200 to about 5000 Daltons.
13. The solvent-less, hybrid curable composition of claim 9 further comprising an isocyanate monomer, melamine crosslinker, UV-curable monomer, UV-curable resin, tackifier, photoinitiator, cross-linker, chain transfer reagent, and/or stabilizer.
14. An article comprising the solvent-less, hybrid curable composition of claim 9.
15. The article of claim 14 which is a tape, label, electronic device, optoelectronic device, OLED, or photovoltaic device.
16. A process forming a hybrid copolymer comprising the steps of:
- a) copolymerizing an acrylic copolymer backbone comprising:
 - (i) a (meth)acrylic monomer,
 - (ii) a hydroxyl group containing monomer and

(iii) a cyclic compound having a functional group -O-, -NH- in the cyclic structure,

b) opening the cyclic compound with a catalyst, whereby the cyclic compound is grafted on the acrylic copolymer backbone.

17. The process of claim 16 wherein the hybrid copolymer comprises:

- (1) about 30 to about 99 wt% of the (meth)acrylic monomer;
 - (2) about 1 to about 30 wt% of the hydroxyl group containing monomer; and
 - (3) about 5 to about 60 wt% of the cyclic compound;
- wherein the total wt% is 100 wt%.

18. The process of claim 16 further comprising the steps of:

- (c) adding a UV-curable monomer, UV-curable resin, tackifier, plasticizer, photoinitiator, cross-linker, chain transfer reagent, and/or stabilizer; and
 - (d) irradiating the hybrid copolymer;
- whereby a cured hybrid copolymer is formed.

19. The process of claim 17 further comprising the steps of:

- (c) adding an isocyanate monomer, melamine crosslinker, tackifier, plasticizer, cross-linker, chain transfer reagent, and/or stabilizer; and
 - (d) thermally curing the hybrid copolymer;
- whereby a cured hybrid copolymer is formed.