

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : B32B 27/32, 27/18	A1	(11) International Publication Number: WO 00/32396 (43) International Publication Date: 8 June 2000 (08.06.00)
(21) International Application Number: PCT/US99/28439 (22) International Filing Date: 2 December 1999 (02.12.99) (30) Priority Data: 60/110,578 2 December 1998 (02.12.98) US 09/383,724 26 August 1999 (26.08.99) US (71) Applicant: TORAY PLASTICS (AMERICA), INC. [US/US]; 50 Belver Avenue, N. Kingstown, RI 02852-7500 (US). (72) Inventors: CHANG, Keunsuk, P.; 50 Belver Avenue, N. Kingstown, RI 02852-7500 (US). NAHMIAS, A., Michael; 50 Belver Avenue, N. Kingstown, RI 02852-7500 (US). (74) Agents: BRETSCHNEIDER, Barry, E. et al.; Morrison & Fo- erster LLP, 2000 Pennsylvania Avenue, N.W., Washington, DC 20006-1888 (US).		(81) Designated States: JP, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: BIAXIALLY ORIENTED POLYPROPYLENE SLIP FILM FOR PACKAGING WITH STABLE COEFFICIENT OF FRICTION (57) Abstract A polypropylene film contains a non-migratory slip package of an aluminosilicate additive and a silicone oil and/or a crosslinked silicone polymer resin. This film has excellent and stable COF (coefficient of friction) properties and exhibits a marked improvement in stable slipperiness, excellent transparency, and excellent printability.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

BIAXIALLY ORIENTED POLYPROPYLENE SLIP FILM FOR PACKAGING WITH STABLE COEFFICIENT OF FRICTION

Field of Invention

5

This invention relates to a polypropylene film containing a non-migratory slip package of an aluminosilicate additive and a silicone oil and/or a crosslinked silicone polymer resin. This film has excellent and stable coefficient of friction (COF) properties and exhibits a marked improvement in stable slipperiness, excellent transparency, and excellent printability.

10

Background of Invention

15

Biaxially oriented polypropylene slip films used for packaging applications often perform multiple functions. They must perform in laminations as slip films with low and stable COF; and they must perform as print films with good optical clarity, gloss, and ink adhesion.

20

Traditional methods for producing a functional slip film have often relied upon relatively high amide-type additives. These fatty amides (e.g. erucamide, stearamide, behenamide), typically in concentrations of 2000 - 5000 ppm, bloom to the surface of the film. The amide molecule form bumps on the polymer surface, thus reducing surface-to-surface contact and lowering the COF. However, the drawback of such additives is their migratory behavior in polyolefin films. The amount of additive bloom to the surface can vary with environmental conditions, and thus slip properties can vary greatly depending on storage conditions seasonal changes in humidity and temperature, or geographical differences in temperature and humidity. Warmer storage conditions tend to enhance blooming of these amides, whereas cool storage conditions tend to slow the migration process. If too little additive blooms, the laminated film may exhibit high COF and cause web breaks on the packaging machine's forming collar or

25

30

sealing bars from excessive friction. If too much additive blooms, the laminated film may exhibit a COF that is too low for the packaging machine's tension control system, causing wrinkling or "flooding" of the line. Because of the variability in storage conditions, the same slip film using these amide systems can exhibit both extremes of COF properties.

In addition, the use of fatty amide additives also tends to make the film hazy and less glossy. This is undesirable from the point of view of print graphics appeal. Moreover, the migratory nature of the amide additive packages make them prone to bloom to the print surface of the slip film or transfer from the slip surface to the print surface when in wound roll form. The presence of amides on the print surface can interfere with the wettability and adhesion of water-based inks and, especially for process print applications, cause bridging of ink dots or inconsistent dot sizes. This results in muddier colors or images and a loss of graphic appeal.

Summary of the Invention

An objective of this invention is to solve the aforesaid problems of conventional slip films by providing an additive system that is essentially non-migratory. This will result in a slip film with stable slip and COF properties. In addition, such a film will offer excellent printability and transparency.

One aspect of the present invention is a polyolefin-based laminate film comprising at least 2 layers:

- a) a first polyolefin-based resin layer having a surface treated by a discharge treatment method that imparts excellent printability; and
- b) a polyolefin-based mixed resin layer formed on one surface of the first polyolefin-based resin layer opposite of the surface treatment,

wherein the first polyolefin-based resin layer and the polyolefin-based mixed resin layer optionally contain up to 800 ppm of fatty

amides such as stearamide or erucamide and the polyolefin-based mixed resin layer contains a first additive material comprising at least one crosslinked silicone polymer in an amount of about 0.1% - 0.5% by weight of the polyolefin-based mixed resin layer and/or at least one
5 silicone oil in an amount of about 0.02% - 0.2% by weight of the polyolefin-based mixed resin layer, and a second additive material in an amount of about 0.10 - 0.50% by weight of the polyolefin-based mixed resin layer, which comprises at least one amorphous aluminosilicate.

10 According to this invention, this objective and other advantages are achieved by a propylene polymer film composed of a composition comprising of at least a 2-layer coextruded film, with the print surface modified with a discharge treatment method; and the slip surface modified with a non-migratory crosslinked silicone polymer resin and/or
15 a silicone oil and a non-migratory silicate powder additive for good slip and antiblock properties. Additionally, if amide-type additives are desired to be used, this invention allows the amount of amide additive used to be significantly reduced (less than 1000 ppm) compared to conventional slip film designs (2000 - 5000 ppm typical).

Detailed Description of the Invention

20 Materials that may be employed for the biaxially oriented layer are propylene homo-copolymers or copolymers of propylene and other α -olefins having 2 to 10 carbon atoms. In the case of copolymers, the
25 amount of α -olefin subjected to copolymerization is less than 5% based on the weight of the copolymer as a standard. If the amount of copolymer exceeds this level, the biaxially oriented layer becomes too soft, with consequent insufficient service strength of the laminate film. Into the biaxially oriented layer various additives may be introduced
30 (normally in the range of 0.01 to 2% based on the weight of the biaxially oriented layer as a standard). These include various additives known as additives for polypropylene, for example, stabilizers, anti-

oxidants, ultra-violet absorbers, plasticizers, antistatic agents, anti-blocking agents, organic lubricants, pigments, coloring agents, nucleating agents, etc. Similarly, other kinds of polymers known as suitable for mixing into polypropylene may be added, for example, polyethylene, polybutene-1, poly (4-methylpentene-1), etc. These may be added by mixing in an amount of about 0.1 to 5% based on the weight of the biaxially oriented layer.

The polyolefin-based laminate film has excellent and stable slip properties, low and stable coefficient of friction, low haze and excellent printability.

In a preferred embodiment, the first polyolefin-based resin layer has a thickness of about 6 - 40 μm . In another embodiment, this polyolefin-based resin layer is made of polypropylene-based resin. The polyolefin-based mixed resin layer has a thickness of about 0.2 - 5.0 μm .

In another embodiment, at least one component of the first additive material is a crosslinked silicone resin having a spherical average particle size of 2 - 5 μm , a specific gravity of 1.32 at 25°F, a bulk density of 0.15 - 0.50, and a linseed oil absorption rate of 50 - 90 ml/100g; and/or at least one component of the first additive material is a silicone oil having viscosity of 300 - 400 cSt., specific gravity at 77°F of 0.90 - 0.99, and volatile content of 0.001 - 0.005%.

In another embodiment, at least one component of the additives is an anti-block material which is an amorphous sodium calcium aluminosilicate having a particle size of 2 - 5 μm and a bulk density of 0.30 - 0.80 g/cm³ or an amorphous aluminosilicate having a particle size of 2 - 5 μm and a bulk density of 0.10 - 0.30 g/cm³.

In another embodiment, at least one component of the second additive material is an amorphous sodium calcium aluminosilicate having a particle size of 2 - 5 μm and a bulk density of 0.30 - 0.80 g/cm³; or an amorphous aluminosilicate having a particle size of 2 - 5 μm and a bulk density of 0.10 - 0.30 g/cm³.

Example 1:

One hundred parts by weight of a crystalline propylene homopolymer resin; 0.0004 parts by weight of a silicone oil having a viscosity of 350 cSt. and a specific gravity of 0.97; and 0.005 parts by weight of a sodium calcium aluminosilicate powder having a mean particle diameter of 3 μm were blended together for the mixed resin layer, coextruded, and biaxially oriented to produce a 2-layer film where the mixed resin layer was 0.5 μm thick and the accompanying coextruded propylene homopolymer layer was 17 μm in thickness. The total oriented film thickness was 17.5 μm (70G or 0.7 mil thick). The film was then treated on the homopolymer side (the print surface); the mixed resin layer side was also treated but to a lesser degree (the slip side); and wound in roll form. The COF static and dynamic, hot slip properties, haze, print surface wetting tension, and printability were tested after the film was produced.

Example 2:

Example 1 was repeated except that 0.003 parts by weight of a crosslinked silicone polymer of 3.0 μm size were used in place of the silicone oil.

Example 3:

Example 1 was repeated except that the amount of aluminosilicate added was changed to 0.0025 parts by weight.

Example 4:

Example 2 was repeated except that the amount of aluminosilicate added was changed to 0.0025 parts by weight.

Example 5:

Example 1 was repeated except that the amount of silicone oil was increased to 0.0008 parts by weight.

Example 6:

Example 1 was repeated except that 0.003 parts by weight of a crosslinked silicone polymer of 3.0 μm size were added.

5

Example 7:

Example 6 was repeated except that the amount of aluminosilicate added was changed to 0.0025 parts by weight.

10

Example 8:

Example 1 was repeated except that the accompanying coextruded propylene homopolymer layer additionally contained 0.0004 parts by weight of stearamide.

15

Example 9:

Example 8 was repeated except that the stearamide was replaced with erucamide.

Example 10:

20

Example 8 was repeated except that the mixed resin layer additionally contained 0.0006 parts by weight stearamide.

Comparative Example 1:

Example 1 was repeated except that no silicone oil was used.

25

Comparative Example 2:

One hundred parts by weight of a random ethylene propylene butylene terpolymer resin; 0.003 parts by weight of erucamide fatty amide; 0.0004 parts silicone oil; and 0.003 parts by weight of a crosslinked silicone polymer having a mean particle diameter of 4.5 μm were blended together for the mixed resin layer, coextruded, and biaxially oriented to produce a 2-layer film where the mixed resin layer was 0.5 μm thick and the accompanying coextruded propylene

30

homopolymer layer was 17 μ m in thickness. The accompanying coextruded propylene homopolymer layer also contained 0.0004 parts by weight steramide. The total oriented film thickness was 17.5 μ m (70G or 0.7 mil thick). The film was then treated on the homopolymer side (the print surface); the mixed resin layer side was also treated but to a lesser degree (the slip side); and wound in roll form. The COF static and dynamic, hot slip properties, haze, print surface wetting tension, and printability were tested after the film produced.

Comparative Example 3:

One hundred parts by weight of a crystalline propylene homopolymer resin; 0.003 parts by weight of behenamide and oleamide fatty amide were blended together with 0.0025 parts by weight of an amorphous silica for the mixed resin layer, coextruded, and biaxially oriented to produce a 2-layer film where the mixed resin layer was 0.5 μ m thick and the accompanying coextruded propylene homopolymer layer was 17 μ m in thickness. The total oriented film thickness was 17.5 μ m (70G or 0.7 mil thick). The film was then treated on the homopolymer side (the print surface); the mixed resin layer side was also treated but to a lesser degree (the slip side); and wound in roll form. The COF static and dynamic, hot slip properties, haze, print surface wetting tension, and printability were tested after the film produced.

The various properties of the films set forth in the Examples were measured by the following methods:

A) Transparency of the film was measured by measuring the haze of a single sheet of film measured substantially in accordance with ASTM D1003. In general, the preferred value was less than 3.0% haze.

B) Gloss of the film was measured via a surface reflectivity gloss meter at 60°/60° angle.

C) Wetting tension of the film was measured using dyne solutions substantially in accordance with ASTM D2578.

D) Printability was measured by drawing down blue ink onto a single sheet of film using a meyer rod; drying the sheet in a hot air convection oven at 60°C for 1 minute; and noting the amount of ink removal when a strip of 1-inch wide 610 tape was applied and removed from the inked surface. The amount of ink removed was rated qualitatively with 5 equaling no ink removed and 1 equaling total ink removal. In general, the preferred value was 4-5.

E) Slipperiness of the film was measured by measuring static and kinetic COF of sheets of film via a surface property tester substantially in accordance with ASTM D1894. A 4" x 4" sled was used at ambient conditions. In general, acceptable values of the dynamic COF ranges between 0.16 and 0.45; preferred values are between 0.25 and 0.35.

The properties of the films of the foregoing Examples ("Ex.") and Comparative Examples ("CEX.") are shown in Table 1.

Sample	Gauge	Haze (%)	Print Side	Print Side	Printability	Slip Side
			Gloss @ 60/60	Wetting Tension (dynes/cm)	Scale 1-5; 5=best, 1=worst	COF (st / dy)
Ex. 1	70	1.8	143.0	42	5	0.32 / 0.26
Ex. 2	70	2.2	140.3	44	5	0.28 / 0.25
Ex. 3	70	1.6	142.0	41	5	0.33 / 0.31
Ex. 4	70	2.0	141.6	41	5	0.31 / 0.28
Ex. 5	70	2.2	143.0	42	5	0.30 / 0.26
Ex. 6	70	2.7	138.0	42	5	0.23 / 0.20
Ex. 7	70	2.4	140.0	42	5	0.28 / 0.25
Ex. 8	70	2.5	141.7	42	4	0.29 / 0.25
Ex. 9	70	2.5	142.2	42	4	0.33 / 0.28
Ex. 10	70	2.6	140.1	41	4	0.32 / 0.28
CEX. 1	70	1.8	138.0	42	5	0.32 / 0.30
CEX. 2	70	2.7	129.2	41	3	0.20 / 0.18
CEX. 3	70	2.1	141.5	41	4	0.24 / 0.20

Table 1.

Table 2 shows the hot slip performance using a surface property tester modified with a 1" x 1" sled instead of a 4" x 4" sled of selected Examples and Comparative Examples. COF was measured at ambient conditions, 40°C, 60°C, 80°C, and 100°C. These conditions simulated performance under severe frictional heating that can be experienced on a packaging machine's forming collar. Test laminations of selected example films were produced for this comparison. In general, preferred hot slip performance indicated stable COF across the range of temperatures tested; at 100°C, the preference is for hot slip to be below 1.0 COF.

Sample	Hot Slip COF (st / dy)				
	20C	40C	60C	80C	100C
Ex. 1	0.33 / 0.27	0.32 / 0.28	0.30 / 0.23	0.34 / 0.24	0.55 / 0.34
Ex. 2	0.34 / 0.26	0.31 / 0.27	0.32 / 0.25	0.34 / 0.26	0.57 / 0.31
Ex. 6	0.23 / 0.20	0.25 / 0.20	0.26 / 0.21	0.33 / 0.27	0.60 / 0.36
CEx. 1	0.34 / 0.28	0.42 / 0.39	0.50 / 0.49	0.77 / 0.68	off-scale
CEx. 2	0.25 / 0.19	0.26 / 0.25	0.34 / 0.28	0.93 / 0.55	off-scale
CEx. 3	0.28 / 0.23	0.30 / 0.23	0.31 / 0.27	0.35 / 0.29	1.11 / 0.39

Table 2.

Table 3 shows the COF properties of selected samples aged for 6 months at ambient conditions in an outside warehouse under varying seasonal changes in temperature and humidity. The COF properties were compared between freshly-made film and aged film. The preferred performance should exhibit relatively stable COF performance between fresh and aged films.

Sample	COF (st / dy) "Fresh-made"	COF (st / dy) Aged 6 mos.
Ex. 1	0.32 / 0.26	0.32 / 0.29
Ex. 2	0.28 / 0.25	0.29 / 0.26
Ex. 6	0.30 / 0.26	0.31 / 0.28
CEx. 1	0.32 / 0.30	0.32 / 0.30
CEx. 2	0.19 / 0.18	0.15 / 0.13
CEx. 3	0.29 / 0.25	0.24 / 0.20

Table 3.

5 The above description is presented to enable a person skilled in
the art to make and use the invention, and is provided in the context of
a particular application and its requirements. Various modifications to
the preferred embodiments will be readily apparent to those skilled in
the art, and the generic principles defined herein may be applied to
10 other embodiments and applications without departing from the spirit
and scope of the invention. Thus, the present invention is not intended
to be limited to the embodiments shown, but is to be accorded the
widest scope consistent with the principles and features disclosed
herein.

Claims

1. A polyolefin-based laminate film comprising:

- a) a first polyolefin-based resin layer having a surface treated by a discharge treatment method that imparts excellent printability; and
- 5 b) a polyolefin-based mixed resin layer formed on one surface of said first polyolefin-based resin layer opposite of said surface treatment,

wherein the first polyolefin-based resin layer and the polyolefin-based mixed resin layer optionally contain up to 800 ppm of fatty amides comprising stearamide or erucamide and the polyolefin-based mixed resin layer contains a first additive material comprising at least one crosslinked silicone polymer in an amount of about 0.1% - 0.5% by weight of the polyolefin-based mixed resin layer and/or at least one silicone oil in an amount of about 0.02% - 0.2% by weight of the polyolefin-based mixed resin layer, and a second additive material in an amount of about 0.10 - 0.50% by weight of the polyolefin-based mixed resin layer, which comprises at least one amorphous aluminosilicate.

2. The polyolefin-based laminate film according to claim 1, wherein said first polyolefin-based resin layer has a thickness of about 6 - 40 μm .

3. The polyolefin-based laminate film according to claim 1 or 2, wherein said first polyolefin-based resin layer consists essentially of polypropylene-based resin.

4. The polyolefin-based laminate film according to claim 1 or 2, wherein said polyolefin-based mixed resin layer has a thickness of about 0.2 - 5.0 μm .

5. The polyolefin-based laminate film according to claim 1 or 2, wherein said polyolefin-based mixed resin layer consists essentially of polypropylene-based resin.

5 6. The polyolefin-based laminate film according to claim 1, wherein at least one component of said first additive material is a crosslinked silicone resin having a spherical average particle size of 2 - 5 μm , a specific gravity of 1.32 at 25°F, a bulk density of 0.15 - 0.50, and a linseed oil absorption rate of 50 - 90 ml/100g; and/or at least one
10 component of said first additive material is a silicone oil having viscosity of 300 - 400 cSt., specific gravity at 77°F of 0.90 - 0.99, and volatile content of 0.001 - 0.005%.

 7. The polyolefin-based laminate film according to claim 1,
15 further comprising an anti-block material which is an amorphous sodium calcium aluminosilicate having a particle size of 2 - 5 μm and a bulk density of 0.30 - 0.80 g/cm³ or an amorphous aluminosilicate having a particle size of 2 - 5 μm and a bulk density of 0.10 - 0.30 g/cm³.
20

 8. The polyolefin-based laminate film according to claim 1, wherein at least one component of said second additive material is an amorphous sodium calcium aluminosilicate having a particle size of 2 - 5 μm and a bulk density of 0.30 - 0.80 g/cm³; or an amorphous
25 aluminosilicate having a particle size of 2 - 5 μm and a bulk density of 0.10 - 0.30 g/cm³.

PCT/US 99/28439

IPC 7 B32B27/32 B32B27/18

B. FIELDS SEARCHED

IPC 7 B32B C08K

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Patent family members are listed in annex.

"&" document member of the same patent family

06/03/2000

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Girard, S

INTERNATIONAL SEARCH REPORT

Int. l. Application No

PCT/US 99/28439

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 353 368 A (TORAY INDUSTRIES) 7 February 1990 (1990-02-07) claims 5,6 page 3, line 13 - line 45 page 4, line 18 - line 27 example 2	1-8
A	WO 94 14606 A (MOBIL OIL CORP) 7 July 1994 (1994-07-07) page 14, line 32 -page 15, line 9	1

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 99/28439

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4659612 A	21-04-1987	AT 77302 T CA 1272114 A DE 3779771 A EP 0234758 A JP 62240547 A	15-07-1992 31-07-1990 23-07-1992 02-09-1987 21-10-1987
US 4590125 A	20-05-1986	AT 61543 T CA 1288569 A EP 0189242 A JP 61169245 A	15-03-1991 10-09-1991 30-07-1986 30-07-1986
EP 0353368 A	07-02-1990	JP 1995712 C JP 2041344 A JP 7017040 B DE 3889110 D DE 3889110 T US 4966933 A	08-12-1995 09-02-1990 01-03-1995 19-05-1994 28-07-1994 30-10-1990
WO 9414606 A	07-07-1994	CA 2150821 A	07-07-1994