

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : A44B 1/04, D06B 11/00	A1	(11) International Publication Number: WO 91/09548 (43) International Publication Date: 11 July 1991 (11.07.91)
(21) International Application Number: PCT/EP90/02326 (22) International Filing Date: 28 December 1990 (28.12.90) (30) Priority data: 19001 A/90 2 January 1990 (02.01.90) IT (71)(72) Applicant and Inventor: POZZOLI, Monica [IT/IT]; Via Fermi, 19, I-29100 Piacenza (IT). (74) Agent: MARIETTI, Giuseppe; Centro di Consulenza in Proprietà Industriale, Viale Caldara, 38, I-20122 Milan (IT). (81) Designated States: AT (European patent), BE (European patent), CA, CH (European patent), DE (European pa- tent), DK (European patent), ES (European patent), FR (European patent), GB (European patent), GR (Euro- pean patent), IT (European patent), JP, LU (European patent), NL (European patent), SE (European patent), SU, US.		Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: PROCESS FOR MULTICOLOR DYEING OF VEGETABLE IVORY PRODUCTS (57) Abstract Buttons or similar products in vegetable ivory undergo a first base dyeing, are then covered in preset areas with a temporary protecting film, and submitted to a second dyeing; the protecting film is eventually removed to obtain a multicolor product.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	ES	Spain	MG	Madagascar
AU	Australia	FI	Finland	ML	Mali
BB	Barbados	FR	France	MN	Mongolia
BE	Belgium	GA	Gabon	MR	Mauritania
BF	Burkina Faso	GB	United Kingdom	MW	Malawi
BG	Bulgaria	GN	Guinea	NL	Netherlands
BJ	Benin	GR	Greece	NO	Norway
BR	Brazil	HU	Hungary	PL	Poland
CA	Canada	IT	Italy	RO	Romania
CF	Central African Republic	JP	Japan	SD	Sudan
CG	Congo	KP	Democratic People's Republic of Korea	SE	Sweden
CH	Switzerland	KR	Republic of Korea	SN	Senegal
CI	Côte d'Ivoire	LI	Liechtenstein	SU	Soviet Union
CM	Cameroon	LK	Sri Lanka	TD	Chad
CS	Czechoslovakia	LU	Luxembourg	TG	Togo
DE	Germany	MC	Monaco	US	United States of America
DK	Denmark				

PROCESS FOR MULTICOLOR DYEING OF VEGETABLE IVORY PRODUCTS

The present invention concerns a process for the multicolor dyeing of items made of vegetable ivory, and namely for the dyeing of buttons made of said material, to which it will be referred to in the present description, without however limiting thereto the scope of the invention.

Vegetable ivory is the preferred raw material for the manufacture of buttons for quality clothing. In fact, though being more economic than nacre, it gives equally satisfactory aesthetic results. Vegetable ivory is constituted by the albumen of the seed of some palms and pandaceae, among which the major ones are those supplying corozo and dum nuts. Vegetable ivory, suitably dried and sliced, is then worked to obtain white buttons which are then dyed in aqueous bath similarly to what occurs for dyeing vegetable textile fibres.

A one-color button is thus easily obtained.

Obtaining a multicolor dyeing of the buttons is on the contrary much more difficult.

A known method for manufacturing multicolor buttons envisages to apply one or more dyes to selected areas of the surface of the still "white" button and to dye afterwards the button thus obtained into a bath of a

- 2 -

lighter color than those previously applied, the latter ones therefore remaining visible through the last applied dye.

This method has two major drawbacks: first, the originally imparted color of the selected areas is modified by the superimposition of the lighter dye. Secondly, a good fixing of the initially applied color can not be obtained, because said initial color is applied by techniques necessarily different from that of the aqueous bath.

There is therefore the need of a process for the multicolor dyeing of products made of vegetable ivory, and in particular of buttons, which is capable to solve the above reported problems.

Object of the present invention is to provide a dyeing process for vegetable ivory products allowing to dye lastingly said products in several colors in a simple, effective and economic way.

More in particular, the present invention provides a process for the multicolor dyeing of vegetable ivory products, in particular of buttons, characterized in that it comprises the following steps:

performing a first treatment in water of said products;
applying on a plurality of preselected areas of said products surface a solution of a water-insoluble protective resin;

evaporating the solvent from said solution until a film for temporarily protecting said areas is obtained; performing a second treatment in water to obtain the dyeing of the non protected areas; fixing the applied dye to said product; and removing said protecting film; the stages of protecting and dyeing being repeated for each desired color besides the base one.

The invention will be now described more in detail with reference to the accompanying figure which shows a block diagram of the process according to the invention.

As shown in said figure, the still "white" vegetable ivory button 1, i.e. still having its natural color and not yet dyed, first undergoes, step A, a treatment in water which, according to different needs, may be an actual dyeing to give a base color to the button, or only constitute a bath in water, should one prefer to maintain said natural ivory white as the base color. In both cases, the wet button impregnates with water and swells.

The subsequent stage B envisages to apply on preselected areas 2, 3 of the thus wetted (and possibly dyed) button a solution of water insoluble protective resin. The solution is preferably applied by spraying using stencils which prevent application of the solution to those portions of button 4,5 which are not to be protected.

It is necessary to perform said first treatment in water (stage A) in order to allow the button to swell. In fact the wetted button, at the end of a dyeing treatment, is approximately 15% larger than its original size when dry; should the film be applied on the dry button, the former might crack or in any case cover a smaller area than the desired one when the button afterwards is wetted and swells.

In stage C the solvent of the sprayed solution is allowed to evaporate until a film protecting the surface areas 2 and 3 is obtained. This film in fact serves to temporarily protect said areas 2 and 3 from the subsequent dyeing treatment in the bath 6, to which the button is submitted in stage D. At the end of said bath, only the non protected areas 4,5 of the button will have been dyed with the color of bath 6.

The button is then left to dry for a time sufficient to allow the dye fixing (stage E). Finally the protecting film is removed by plunging the button into a bath of solvent 7 which dissolves the protective film. In order to accelerate this stage of the process (stage F), the button is submitted to a mechanical action facilitating the dissolution of said film.

The stages of protection and dyeing are repeated for each desired color besides the base one, the base color herein meaning the ivory white of the natural button or the dye

applied in the first treatment in water (stage A). For example, a portion of areas 4 or 5 may be on its turn covered with said film of temporary protection and the button thus obtained submitted to a further dyeing bath and to the subsequent removal of the protective film from areas 2,3 and from said portion of areas 4 or 5.

The aforescribed process requires each dyeing treatment to be performed with a color lighter than that to be applied in the subsequent dyeing treatment, in order to allow the first applied color to be covered by the later applied one.

As mentioned above, the temporary protection film is removed in a solvent bath and, in order to accelerate this step, buttons are submitted to a mechanical action facilitating dissolution and detachment of the film.

It was found that it is possible to obtain excellent results, as far as cleanliness and quickness are concerned, if buttons are treated in a tumbler of the type normally used for their dry polishing, i.e. a tumbler containing wooden dices, in which a sufficient amount of solvent has been introduced; the wooden dices providing the required mechanical action.

The solvent to be used in this stage is obviously related to the type of resin used.

A final drying step is then carried out.

Since films insoluble in water and removable after dyeing have to be obtained, reversible resins soluble in organic solvents are generally adopted. "Reversible resin" as used herein means a resin of the type which can be dissolved by an appropriate solvent even after its polymerization and/or a film is formed on the surface of the button. Preferred classes of resins of this type are natural resins, namely shellac or lac resin, nitrocellulosic resins and polyurethanic resins or mixtures thereof.

Since the solution of resin, or resins, is applied on the button after a first treatment in water (stage B), organic solvents, partly compatible with water, are preferably used in order to ensure the solution adherence to the sprayed button even in presence of moisture on the button surface.

Preferred solutions are alcoholic solutions, and particularly ethanol solutions, i.e. solutions wherein the solvent is at least partly consisting of one or more alcohols, preferably ethanol.

A particularly suitable resin solution to be used according to the present invention is an ethanol solution containing 20 to 60% in weight of lac resin.

Said solution preferably consists of a mixture of three parts of a 40% by weight lac solution in ethanol and one part of a lac-containing nitrocellulosic resin, such as

for instance the product "Americana scura" or "Americana chiara" by the firm ARRIGONI-SADOLIN S.r.l. LODI (MI).

The invention also extends to the aforescribed solutions as far as their specific use therein is concerned, and to the products thus obtained, both finished and semi-finished products, such as for example buttons provided with a base dye and one or more surface areas protected by a reversible film obtained with a solution and according to a process as the aforescribed ones.

The invention will now be further disclosed by means of the following non-limitative examples.

EXAMPLE I

A plurality of vegetable ivory buttons, of the polished type, first underwent a base dyeing of beige color by means of an aqueous bath for 30 minutes at 70 C degrees. At the end of the dyeing bath, selected areas of swollen buttons were sprayed with a solution comprising 75% of a solution of shellac - 40% in ethanol - and 25% of Americana chiara. After solvent evaporation and forming of the protecting film, the buttons were again dyed in an aqueous brown dye bath for 20 minutes at 35C degrees.

The buttons were then dried at 35 C degrees for 40 minutes in order to allow complete fixing of the dyes. The dried buttons were put in an alcohol containing tumbler, together with a plurality of wooden dices to provide the

necessary mechanical action, and herein treated for about 15 minutes, up to complete removal of the protecting film. The final drying step was then carried out; the thus obtained buttons were provided with beige colored areas having sizes and dimensions corresponding to the areas previously temporarily protected by the film, and with alternated, brown colored, areas, without any blurring or smudging.

EXAMPLE II

The same steps as in Example I were carried out, but for the first bath, which was without dye and was effected at 20 C degrees for 120 minutes. The thus obtained buttons were provided with areas having the color of vegetable ivory alternated with brown colored areas obtained through the second bath.

CLAIMS

1. A process for the multicolor dyeing of vegetable ivory products, in particular of buttons, characterized in that it comprises the following steps:

performing a first treatment in water of said products;

applying on a plurality of preselected areas of said product surface a solution of a water-insoluble protective resin;

evaporating the solvent from said solution until a film for temporarily protecting said areas is obtained;

performing a second treatment in water to obtain the dyeing of the non protected areas;

fixing the applied dye to said product; and

removing said protecting film;

the stages of protecting and dyeing being repeated for each desired color besides the base one.

2. A process according to claim 1, characterized in that each dyeing is performed with a color lighter than that applied in the subsequent dyeing in order to be covered by the latter.

3. A process according to claim 1 or 2, wherein said protective film is removed in solvent containing polishing tumblers.

4. A process according to one of claims 1 to 3, characterized in that said solution of protective resins,

is a solution of reversible resin selected among the following ones: nitrocellulosic, natural, polyurethanic or mixtures thereof.

5. A process according to claim 4, wherein said solution is an alcoholic solution.

6. A process according to claim 5, wherein said solution is an ethanol solution containing 20 to 60% by weight of lac resin.

7. A process according to claim 6, characterized in that said solution is consisting of a mixture of three parts of an ethanol solution of 40% lac resin and one part of nitrocellulosic lac containing paint.


8. A vegetable ivory multicolor button, as obtainable by a process according to any claim 1 to 7.

9. A solution for the formation of a temporarily protecting film on a vegetable ivory product in a process according to any claim 1 to 7, characterized in that it is constituted by one or more reversible resins selected among: nitrocellulosic resins, natural resins, polyurethanic resins and mixtures thereof.

10. A solution according to claim 9, characterized in that it comprises one or more alcoholic solvents and 20 to 60% by weight of lac resin.

11. Use of a solution according to claim 9 or 10 for the manufacturing of multicolor vegetable ivory buttons.

12. A vegetable ivory button, characterized in that it is partially covered by a reversible protective film obtained from a solution according to claims 9 or 10.



INTERNATIONAL SEARCH REPORT

PCT/EP 90/02326

International Application No

I. CLASSIFICATION OF SUBJECT MATTER (if several classification symbols apply, indicate all) ⁶		
According to International Patent Classification (IPC) or to both National Classification and IPC		
Int.Cl. 5 A44B1/04 ; D06B11/00		
II. FIELDS SEARCHED		
Minimum Documentation Searched ⁷		
Classification System	Classification Symbols	
Int.Cl. 5	A44B ; D06B	
Documentation Searched other than Minimum Documentation to the Extent that such Documents are Included in the Fields Searched ⁸		
III. DOCUMENTS CONSIDERED TO BE RELEVANT⁹		
Category ¹⁰	Citation of Document, ¹¹ with indication, where appropriate, of the relevant passages ¹²	Relevant to Claim No. ¹³
X	FR,A,2014203 (BERG) 17 April 1970 see the whole document ---	1, 4
A	BE,A,743189 (VAN DEN BULKE) 28 May 1970 ---	
A	FR,A,2298641 (HOECHST) 20 August 1976 ---	
A	FR,A,477151 (MAGNESIA-WERKE WEISSENSEE) 25 July 1914 ---	
A	GB,A,862187 (HANS SCHÄFER & ARNOLD VON KOCH) 01 March 1961 ---	
¹⁰ Special categories of cited documents : "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "I" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. "&" document member of the same patent family		
IV. CERTIFICATION		
Date of the Actual Completion of the International Search	Date of Mailing of this International Search Report	
10 APRIL 1991	08. 05. 91	
International Searching Authority	Signature of Authorized Officer	
EUROPEAN PATENT OFFICE	PETIT J.P. 	

**ANNEX TO THE INTERNATIONAL SEARCH REPORT
ON INTERNATIONAL PATENT APPLICATION NO.**

PCT/EP 90/02326

SA 42879

This annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

10/04/91

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
FR-A-2014203	17-04-70	DE-A- 1931991 GB-A- 1269706	02-01-70 06-04-72
BE-A-743189	28-05-70	None	
FR-A-2298641	20-08-76	DE-A- 2502997 BE-A- 837901	22-07-76 26-07-76
FR-A-477151		None	
GB-A-862187		None	