

(12) STANDARD PATENT
(19) AUSTRALIAN PATENT OFFICE

(11) Application No. AU 2003289707 B2

(54) Title
Method and composition for reducing wear in a cutting head of a tunnel boring machine

(51) International Patent Classification(s)
E21B 10/00 (2006.01) **C10M 173/02** (2006.01)
C09K 8/38 (2006.01) **E21D 9/10** (2006.01)
C09K 8/54 (2006.01) **C10N 30/06** (2006.01)
C10M 103/06 (2006.01) **C10N 40/00** (2006.01)
C10M 107/34 (2006.01)

(21) Application No: **2003289707** (22) Date of Filing: **2003.09.02**

(87) WIPO No: **WO04/025080**

(30) Priority Data

(31) Number **0221171.2** (32) Date **2002.09.13** (33) Country **GB**

(43) Publication Date: **2004.04.30**
(43) Publication Journal Date: **2004.05.20**
(44) Accepted Journal Date: **2008.04.17**

(71) Applicant(s)
Construction Research & Technology GmbH

(72) Inventor(s)
Ellenberger, Peter;Egli, Herbert

(74) Agent / Attorney
Cullen & Co, 239 George Street, Brisbane, QLD, 4000

(56) Related Art
US 6287052 B1
WO 2001/12952 A1
WO 1999/18330 A1

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization International Bureau



(43) International Publication Date
25 March 2004 (25.03.2004)

PCT

(10) International Publication Number
WO 2004/025080 A3

(51) International Patent Classification⁷: **E21D 9/06**, C09K 7/08

(21) International Application Number: PCT/EP2003/009718

(22) International Filing Date: 2 September 2003 (02.09.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data: 0221171.2 13 September 2002 (13.09.2002) GB

(71) Applicant (for all designated States except US): **CONSTRUCTION RESEARCH & TECHNOLOGY GMBH** [DE/DE]; Patente, Marken, Postfach 1262, 83303 Trostberg (DE).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **EGLI, Herbert** [CH/CH]; Friedhofstrasse 35, CH-8048 Zürich (CH). **ELLENBERGER, Peter** [CH/CH]; Rebbergstrasse 97, CH-8706 Feldmeilen (CH).

(74) Common Representative: **CONSTRUCTION RESEARCH & TECHNOLOGY GMBH**; Patente, Marken, Postfach 1262, 83303 Trostberg (DE).

(81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CI, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SI, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:
— with international search report

(88) Date of publication of the international search report: 14 October 2004

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



WO 2004/025080 A3

(54) Title: METHOD AND COMPOSITION FOR REDUCING WEAR IN A CUTTING HEAD OF A TUNNEL BORING MACHINE

(57) Abstract: A method of reducing wear in a cutting head of a tunnel boring machine, by means of the addition at the cutting head of a foamed aqueous liquid composition, which comprises a foaming agent and a lubricant, the lubricant being selected from the group consisting of high molecular weight polyethylene oxides and bentonite. Preferred foaming agents are anionic and nonionic surfactants. Wear rates of cutting elements of TBMs boring in hard rock are considerably reduced. A wear-reducing foamable concentrate is also described.

METHOD AND COMPOSITION FOR REDUCING WEAR IN A CUTTING HEAD
OF A TUNNEL BORING MACHINE

This invention relates to a method of boring a tunnel in hard rock.

5 The boring of tunnels in hard rock, such as limestone and metamorphic or igneous rocks, has always presented more problems than has boring in softer rock. The most commonly used method of tunnel boring in such rock has been the drilling of blast holes, followed by blasting with explosives. It has been desired to use tunnel boring machines (TBMs), machines with large diameter cutting heads (sometimes in excess of
10 10m), for tunnelling in hard rock. The major problem of TBM use in such rock is the rapid wear of the cutting elements (hardened steel discs which protrude from the cutting head) and the necessity for frequent replacement, a disadvantage from both operational and economic points of view.

15 WO 99/18330A and WO 01/12952A both describe that the wear can be reduced by the use of a foamed aqueous solution.

It has now been discovered that the use of a particular composition can reduce this wear considerably, permitting more efficient and economic boring in hard rock with a TBM.
20 This invention therefore provides a method of boring hard rock by means of a tunnel boring machine comprising hardened steel discs which protrude from the cutting head, wherein wear in the cutting head is reduced by means of the addition at the cutting head of a foamed aqueous liquid composition, which comprises a foaming agent and a lubricant, the lubricant being selected from high molecular weight polyethylene oxides.
25 The foaming agent may be any foaming agent, that is, any material that, when agitated in water, will cause stable foam to form. It is possible to use more than one such foaming agent in a composition for use in this invention. A wide variety of such materials is known to the art. The preferred materials for use as foaming agents in this invention are surfactants, that is, materials that have both hydrophilic components and hydrophobic components. Although any suitable surfactant can be used, it has been found that, for the purposes of this invention, the surfactants that work best are anionic or nonionic types,

and these are the preferred surfactants.

If the surfactant is an anionic type, it is preferably a sulphate-containing surfactant, more preferably an alcohol sulphate, and most preferably a lauryl sulphate. Many suitable 5 materials are known to the art, an example of a particularly preferred material being monoisopropanolamine lauryl sulphate (available commercially, for example, under the trade name "Sulfetal" Cjot 60).

While the performance of anionic surfactants is excellent, their use is sometimes 10 undesirable if environmental considerations are important. For environmental reasons, it is preferred that the foam be short-lived, that is, that it remain a foam only for the time between its generation and the removal of the foamed liquid from the cutting face. The foam from anionic surfactants can be so stable and durable that it can be sometimes found in rivers remote from the job site. In such cases, nonionics are preferred; their 15 performance on the job site is no less excellent, but they biodegrade more quickly and any foam generated lasts for a relatively short time. In addition, the breakdown components of the nonionic surfactants are considerably less harmful than those of the anionics, and they therefore represent less of a toxicological hazard to plant and animal life.

20 Examples of effective nonionic surfactants suitable for use in this invention include alkanolamides, aminoxides, ethoxylated alcohols, ethoxylated alkylphenols, ethoxylated esters, glucose and sucrose esters and derivatives thereof. Especially effective are the glucose and sucrose esters and their derivatives, particularly alkyl polyglucosides. 25 Typical commercial examples of these include "Lutensol" (trade mark) GD 70 (ex BASF) and "Glucopon" (trade mark) (ex Cognis).

The lubricant is chosen from high molecular weight polyethylene oxides. By "high 30 molecular weight" polyethylene oxide (PEO) is meant a PEO with a weight-average molecular weight of at least 1,000,000. Preferably the molecular weight is from 2,000,000-8,000,000. Such materials have previously been used in the boring of tunnels with TBMs, but never in connection with hard rock boring. Typical commercial

materials include POLYOX (registered trade mark) WSR-301. A blend of different PEOs may be used, although, being a polymer, a PEO has a molecular weight distribution, and it is therefore already inherently a blend of different materials.

5 The compositions are prepared for use by the addition of a suitable amount of water. Although the supply of dry compositions is theoretically possible and is not excluded from this invention, it is impracticable. One reason for this is that it introduces the task of producing the liquid composition on the job site - this can be difficult, especially with PEOs of high MW, which, although water-soluble, can be difficult to dissolve. In
10 addition, other commercially-available additives (further described hereinunder) are often supplied only in solution or suspension form.

There are two methods of overcoming these difficulties. The first is to supply the compositions as a series of individual aqueous ingredients that can be metered in the
15 correct individual proportions to a relatively large quantity of water for foaming. Thus, the PEO, the foaming agent and any optional ingredients (further described hereinunder) are provided individually in aqueous form. The required containment and metering equipment is well known to the art and does not therefore need to be further described here. This method has the advantage of versatility - the quantities of ingredients can be
20 varied to suit local conditions as they arise and any optional components can be included or not included, as the case may be.

A more desirable method for most applications is to provide a concentrate, an aqueous solution or suspension with a suitable proportion of the necessary ingredients, which is
25 capable of being used quickly and easily. It is no problem to dilute such a concentrate and foam the diluted concentrate at a job site. Where the versatility of the metering approach previously outlined is not needed, this is much preferred, because of its simplicity of use and relative cheapness.

30 The quantities of ingredients referred to in the following paragraphs relate to an aqueous composition which comprises the dry ingredients plus sufficient water, either to render the individual ingredients in aqueous form for individual metering as hereinabove

described, or for the preparation of an aqueous concentrate, as hereinabove described. The compositions are made up to 100% with water. This does not include the final dilution and foaming water (for which quantities see p. 5).

- 5 The quantities of PEO used are from 0.1-3.0%, preferably from 0.4-2.0%, and more preferably from 0.5-1.0% by weight of the concentrate. The equivalent quantities of foaming agent are from 2-40%, preferably from 5-30%, and more preferably from 5-20%.
- 10 It is possible to add other ingredients to the compositions for use in this invention. Two particularly useful ones are sequestering agents and foam boosters. In addition, in the preferred cases, they are more often useful with anionic surfactants; they have little effect with nonionics. This is especially true of the sequestering agent.
- 15 The sequestering agent is present to counter any problems brought about by the use of hard water in the preparation of the final foamed solution - hard water can cause the precipitation of the foaming agent and render the composition useless. If there is no hard water present, a sequestering agent is naturally not needed, but the addition of such an agent provides a composition which may be used in any water conditions, and which is
- 20 therefore always ready for use in any circumstances. Any suitable sequestering agent may be used, the quantities used being in the range of up to 5%, preferably from 0.1-5%, more preferably from 0.5-2%, and most preferably from 1-1.5%. An example of a sequestering agent which is suitable for use in this invention is "Cublen" (trade mark) K2523.

25

The foam booster may likewise be any suitable material. The quantities used are up to 10%, preferably from 0.1-10%, and more preferably from 0.1-1%. An example of a foam booster which is suitable for use in this invention is "Aromox" (trade mark) MCD-W.

30

In connection with the invention it should be mentioned that the corresponding wear-reducing foamable liquid concentrate, consists of at least one lubricant being a high

molecular weight polyethylene oxide, and at least one foaming agent which gives rise to short-lived foams, optionally it also contains at least one sequestering agent and at least one foam booster, the quantities present being respectively

5 0.1-3% polyethylene oxide;
2-40% foaming agent;
up to 5% sequestering agent; and
up to 1% foam booster;

10 by weight of the concentrate, the remainder being water.

In use, in the case of a concentrate, the concentrate is added to a suitable quantity of water and foamed, before being pumped to the rotating cutting head and injected at the interface of cutting head and rock. In the case of an individual ingredient metering 15 system, the required quantities of aqueous ingredients are metered to a suitable quantity of water and foamed. Typically, the concentrate/individual ingredients previously described is or are diluted with water to give an aqueous composition having from 1-20%, preferably 1-10%, more preferably from 1-8% and most preferably from 1-6% of concentrate/individual ingredients.

20 This diluted composition is foamed by any convenient means to give a volume expansion of from 5-40, preferably from 5-20, more preferably from 8-20 times the volume of the unfoamed material.

25 The actual dilution of the concentrate/individual ingredients and the amount to which it is foamed will vary considerably, depending on the particular circumstances. Such factors as diameter of cutting head, number and location of injection nozzles and nature of rock will have a major effect. The essential requirement is to maintain a layer of foam in contact with the rock face across the entire area of the cutting head. Achieving this 30 requirement is a matter of routine experimentation and the skilled person will easily be able to do it. Typical figures for a concentrate of the type hereinabove described are from 0.5-10.0, preferably from 0.5-6.0, more preferably from 1-4 kg concentrate/m³ rock

removed. If individual aqueous ingredients are being added, equivalent quantities can easily be calculated. It is emphasized that these figures are given only as a general guideline, and that certain conditions may require lower or higher quantities of individual ingredients or concentrate.

5

It is a surprising feature of this invention that the use of an aqueous liquid composition as hereinabove described results in a considerable reduction in wear of cutting elements in hard rock, leading to longer cutting head life and less frequent replacement, and therefore better and more economical tunnel boring. It is believed, without restricting the 10 scope of this invention in any way, that the fine material produced at the drilling face of the TBM is bound together by the aqueous liquid composition and acts as a lubricant.

The invention is now illustrated by the following non-limiting examples.

15 Composition A (using anionic surfactant)

The following ingredients are used:

"Polyox" WSR 301 polyethylene oxide,

20	weight-average molecular weight 4,000, 000 ("PEO")	0.83%
	"Sulfetal" Cjot 60 surfactant	9.0%
	"Cublen" K 2523 sequestering agent ("SA")	0.3%
	"Aromox MCD-W foam booster ("FB")	0.15%
	water	to 100%

25

Compositions B and C (using nonionic surfactant)

The compositions are as follows:

	B	
30	"Lutensol" GD 70	10.0%
	"Polyox" WSR 301	0.9%
	water to	to 100%

Testing

5 A method of ascertaining the effectiveness of the compositions for use in this invention prior to use with a TBM, thereby saving time and money, requires the following apparatus:

PVC jar, 1 litre, wide mouth
test specimen
10 silicon carbide powder (0.841-1.19mm)

15 The test specimen consists of three wheels of ST 50 steel of 50 mm diameter and 14 mm thickness with a 10mm diameter axial hole, the three being secured to an M10 bolt by any suitable means (such as nuts and washers), such that there is about 14mm space between adjacent wheels.

The procedure is as follows:

20 400 g. of the silicon carbide is mixed with quantities of water and composition and added to the jar. A test specimen, of which the weights of the three individual wheels are accurately known, (to 0.001 g.) is then added to the jar, and the jar is sealed, placed on a mill and rolled for 3 hours at 125 rpm. The wheels are then weighed and the loss of weight (wear) is found.

25 The compositions A, and B are tested in this way. In each case, the compositions are diluted with water (5% composition in water) and 30 and 60 g samples are foamed to give a volume expansion of 10 times. As a control, 60 g water is added to a 400 g sample of the silicon carbide and tested. The wear rates of the test specimens are as follows:

30

SiC + water	204 mg
SiC+30gA	190"

SiC + 60 g A	157"
SiC+30gB	129"
SiC+60gB	115"

As can be seen, the wear rates are reduced, in some cases very substantially.

CLAIMS

1. A method of boring hard rock by means of a tunnel boring machine comprising hardened steel discs which protrude from the cutting head, wherein wear in the cutting head is reduced, by means of the addition at the cutting head of a foamed aqueous liquid composition, which comprises a foaming agent and a lubricant, the lubricant being selected high molecular weight polyethylene oxides.
5
2. A method according to claim 1, in which the individual ingredients of the foaming composition are metered in individual aqueous form into water and are converted to foam.
10
3. A method according to claim 1 or claim 2, in which the foaming agent is selected from anionic and nonionic surfactants.
15
4. A method according to claim 1, in which the composition is supplied as a concentrate, which is diluted with water in situ, to provide the foaming composition.