



(12) **DEMANDE DE BREVET CANADIEN  
CANADIAN PATENT APPLICATION**

(13) **A1**

(22) Date de dépôt/Filing Date: 2009/11/30  
(41) Mise à la disp. pub./Open to Public Insp.: 2010/06/17  
(62) Demande originale/Original Application: 2 745 327  
(30) Priorité/Priority: 2008/12/09 (ZA2008/10426)

(51) Cl.Int./Int.Cl. *A61K 33/30* (2006.01),  
*A61K 33/00* (2006.01), *A61K 33/04* (2006.01),  
*A61P 3/02* (2006.01)  
(71) Demandeur/Applicant:  
WARBURTON TECHNOLOGY LIMITED, IE  
(72) Inventeur/Inventor:  
SMITH, WILLIAM A., IE  
(74) Agent: PIASETZKI NENNIGER KVAS LLP

(54) Titre : ELEMENTS TRACES  
(54) Title: TRACE ELEMENTS

(57) **Abrégé/Abstract:**

The invention discloses a trace element solution, which comprises at least the following metals: zinc; manganese; and selenium; copper; and which comprises a concentration of the metals of at least 90 mg/ml. The solution may comprise the following concentrations: at least 60 mg/ml zinc; at least 10 mg/ml manganese; and at least 5 mg/ml selenium. The solution may comprise chromium, iodine, copper and chromium.

### ABSTRACT

The invention discloses a trace element solution, which comprises at least the following metals: zinc; manganese; and selenium; copper; and which comprises a concentration of the metals of at least 90 mg/ml. The solution  
5 may comprise the following concentrations: at least 60 mg/ml zinc; at least 10 mg/ml manganese; and at least 5 mg/ml selenium. The solution may comprise chromium, iodine, copper and chromium.

## TRACE ELEMENTS

### FIELD OF INVENTION

The present invention relates to trace elements.

### BACKGROUND TO INVENTION

5 It has been found that there is a deficiency of certain trace elements in pastures for livestock in particular areas around the world. Various suggestions have been made to provide the required trace elements to such animals. Different chemical compounds and complexes have been investigated for applying the trace elements by way of licks, drenches or  
10 injections.

In general the problem with injectable solutions is that the concentrations of the minerals in the solutions is too low. This means that relatively large quantities have to be injected, which in turn causes tissue damage and also abscesses at the site of injection. Furthermore, it is generally the case that  
15 different trace elements seldomly are individually sufficient. This means that two or more trace element solutions have to be provided by way of separate injections.

ZA 1982/6778 (Laurie) discloses a trace element solution and a method of providing the trace elements to livestock. These trace element solution include  
20 ethylene diamino tetra acetic acid complex of the required mineral in suitable quantities. However, the trace element solution includes no selenium or selenite compound.

In the specification and claims the expression EDTA refers to ethylene diaminotetraacetic acid ( $C_{10}H_{16}O_8N_2$  or  $(HO_2CH_2C)_2NCH_2CH_2N-(CH_2CO_2H)_2$ ).

US 4,335,116 (Howard) discloses mineral-containing therapeutic compositions containing EDTA complexes of trace elements. Notably, US 4,335,116 utilises tetra-sodium EDTA, a selenium glycine complex, and metal chlorides for the preparation of the EDTA complexes. Unfortunately, the chloride ions cause  
5 contamination and each complex solution is to be made individually. Furthermore, overnight time is required for complexing and heating up afterward to speed up the process, requires extra apparatus. If mixtures are required, the individual solutions are to be blended. If various concentrations as well as compositions are to be made, it can only be done in a cumbersome  
10 way, requiring extra apparatus. A further problem arises when mixtures of high concentration are needed. In certain cases it would be impossible to deliver them, because mixing is always accompanied by dilution. The maximum concentration achieved with this method was 13,5 mg/ml.

US 6,638,539 (Laurie et al) discloses a method of preparing a trace element  
15 solution, which includes the steps of providing at least one EDTA-complex, of providing a sodium selenite solution, and of combining the EDTA-complexes and the sodium selenite solution. However, the method enables production of a trace element solution of only about 55 mg/ml.

US 7,285,292 (Laurie et al) discloses a trace element solution, which  
20 comprises at least one metal selected from the group comprising selenium, copper, zinc, manganese and chromium and which comprises a concentration of the metal(s) of at least 60 mg/ml. The solution further comprises at least one compound selected from the group comprising iodine, potassium iodide, sodium iodide, iron, iron chloride, zinc oxide, manganese sulphate, sodium  
25 selenite, copper carbonate, sodium carbonate, anhydrous disodium EDTA and sodium hydroxide. The trace element solution is prepared by a method consisting essentially of the steps of preparing a  $\text{MnCO}_3$  mixture in a container; adding an EDTA/NaOH mixture to the container and subsequently adding at

least one metal compound; and adding  $\text{Na}_2\text{SeO}_3$  to the container to obtain the trace element solution. The method also comprises the step of adding  $\text{CrCl}_3 \cdot 6\text{H}_2\text{O}$  to the trace element solution.

Unfortunately the known solutions and methods therefore cannot provide  
5 solutions with suitable composition with high enough concentrations and sufficient ratios and sufficient concentrations of the various metals.

It is an object of the invention to suggest methods and means for overcoming these problems.

### **SUMMARY OF INVENTION**

10 According to the invention, a trace element solution, which comprises at least the following metals:

- (a) zinc;
- (b) manganese;
- (c) selenium; and
- 15 (d) copper;

and which comprises a concentration of the metals of at least 90 mg/ml.

Also according to the invention, a method of preparing a trace element solution comprising at least one metal selected from the group comprising zinc, manganese, selenium, and copper and comprising a concentration of the  
20 metals of at least 90 mg/ml, said method consisting essentially of the steps of:

- (a) heating water;
- (b) adding manganese carbonate to the water;
- (c) adding zinc oxide to the water; and

- (d) adding copper carbonate to the water to form a liquid mixture;
- (e) adding a dry mixture comprising EDTA and/or EDDS and NaOH to the liquid mixture; and
- (f) adding  $\text{Na}_2\text{SeO}_3$  to form the trace element solution.

5 Yet further according to the invention, a trace element solution as prepared by the method as described herein.

Yet further according to the invention, a method of providing trace elements to animals, such as livestock, which comprises the steps of preparing a trace element solution as described herein and of providing the solution in a suitable  
10 quantity to an animal.

The method of preparing a trace element solution may be a continuous batch process.

The solution may comprise the following concentrations:

- (a) at least 60 mg/ml zinc;
- 15 (b) at least 10 mg/ml manganese;
- (c) at least 5 mg/ml selenium; and
- (d) at least 15 mg/ml copper.

The solution may comprise chromium.

The solution may comprise iodine.

20 The solution may comprise at least 5 mg/ml chromium.

The solution may comprise at least 50-300 mg/ml iodine.

The ratio of zinc to manganese may be at least 2:1

The ratio of zinc to manganese may be at least 4:1

The ratio of zinc to copper may be at least 2:1 or 4:1

The ratio of zinc to selenium may be at least 4:1 or 12:1

The solution may comprise at least one compound selected from the group  
5 comprising chromium, iron, iodine, potassium iodide, sodium iodide, iron  
chloride, zinc oxide, manganese sulphate, manganese carbonate, sodium  
selenate, sodium selenite, copper carbonate, sodium carbonate, anhydrous  
disodium EDTA and sodium hydroxide.

At least one of the metal(s) may be provided in the form of an EDTA complex  
10 and/or an EDDS complex.

The EDTA source may be EDTA acid, disodium EDTA, tetra-sodium EDTA,  
calcium EDTA, potassium EDTA and/or any other EDTA source.

The solution may comprise chloro-cresol and/or benzyl alcohol as preservative.

The solution may be an injectable solution.

15 The solution may be a drenchable solution.

Step (a) may heat the water to 70 degrees Celcius.

The adding in step (e) may occur slowly to prevent excessive frothing.

The solution may be a clear blue solution.

The temperature of the solution may reach 100 degrees Celcius.

20 The solution may be allowed to cool.

The solution may after cooling have a temperature of 50 degrees Celcius.

Chloro-cresol may be added to the solution and stirred until dissolved.

The pH of the solution may be adjusted.

Water may be added to the solution.

The method may comprise the step of adding  $\text{CrCl}_3 \cdot 6\text{H}_2\text{O}$  to the trace element solution.

- 5 The method may comprise the step of adjusting the pH of the trace element solution to 6,0 to 8.0

The method may comprise the step of adjusting the pH of the trace element solution by adding at least one compound selected from the group comprising NaOH and EDTA.

- 10 The trace element solution may be diluted.

The temperature of the  $\text{MnCO}_3$  mixture may be at least 60 degrees Celsius.

Water having a temperature of at least 70 degrees Celsius may be added to the  $\text{MnCO}_3$  mixture.

- 15 The addition of the EDTA/NaOH mixture may occur gradually with small quantities.

The method may comprise the step of cooling the trace element solution prior to addition of the  $\text{Na}_2\text{SeO}_3$ .

The  $\text{MnCO}_3$  mixture may be obtained directly and/or prepared by mixing  $\text{MnSO}_4$  and  $\text{Na}_2\text{CO}_3$ .

- 20 The metal compound may be selected from the group comprising ZnO,  $\text{CuCO}_3$ ,  $\text{Na}_2\text{CO}_3$ ,  $\text{MnSO}_4$  and  $\text{FeCl}_3$ .

The metal compound may be selected from the group comprising metal oxides, metal hydroxides and metal carbonates.

**DESCRIPTION OF EXAMPLE**

The invention will now be described by way of an example of injectable solutions in accordance with the invention.

The example relates to a method to prepare a trace element solution predominantly to be used for cattle and includes the mineral elements zinc, manganese, selenium and copper.

The method enables preparation of 25 litres of the solution containing at least 60 mg Zn, 10 mg Mn, 5 mg Se, and 15 mg Cu per ml.

In a 25 litre plastic container, water is heated to a temperature of 70 degrees Celsius so that the process can proceed at a temperature of at least 60 degrees Celsius.

0.556 Kilogram of manganese carbonate is added to the heated water whilst mixing.

1.890 Kilogram of zinc oxide is added to the mixture.

0.700 Kilogram of copper carbonate is added to the mixture slowly to form a liquid mixture.

In a separate container 10.17 kilogram EDTA and 2.70 kilogram of NaOH are mixed to form a dry mixture.

The dry mixture is slowly added to the liquid mixture to prevent excessive frothing and allow the reaction to complete and to leave a clear blue solution.

The temperature of the solution may reach 100 degrees Celsius and is allowed to cool to 50 degrees Celsius.

26.25g of Chloro-cresol is added to the solution and is stirred until dissolved.

The solution is then cooled to room temperature.

The recorded pH of the solution is now 4.656.

0.303 Kilogram of  $\text{Na}_2\text{SeO}_3$  is added.

The recorded pH of the solution is now 5.115.

5 The pH is adjusted to 6.860 by adding a 50% NaOH solution.

The solution is now diluted with water to obtain the required weight, namely 1.300 kg/l.

The resultant trace element solution has a composition as follows:

- (a) 60 mg/ml of zinc;
- 10 (b) 10 mg/ml manganese;
- (c) 5 mg/ml selenium; and
- (d) 15 mg/ml copper.

The invention therefore provides a trace element solution which is tissue friendly, i.e. is not damaging or irritant to the tissue of animals and which  
15 comprises zinc, manganese, selenium and copper and at a concentration of the metals of at least 90 mg/ml.

The trace elements in solution are in a scientifically formulated ratio according to the post-absorption requirements of the animals.

As an example the trace element solution comprises

- 20 (a) at least 60 mg/ml of zinc;
- (b) at least 10 mg/ml manganese;

(c) at least 5 mg/ml selenium; and

(d) at least 15 mg/ml copper.

The solution may furthermore comprise at least 5 mg/ml chromium and at least 50-300 mg/ml iodine.

5 The method of preparing a trace element solution in accordance with the invention thus enables the production of a solution comprising an adequate trace mineral concentration so that a 5 to 10 millilitre injection can make a significant impact on the trace mineral status of the animal and an injection is provided at a rate of between 1 ml per 50 kg bodyweight (BW) and 1 ml per  
10 100kg BW, i.e. a practically applicable injectable supplement and a product that can improve the trace mineral status of an animal is provided. This is important as livestock producers will only inject livestock if a real benefit can be demonstrated. The subcutaneous injection is the preferred route to minimize tissue damage, but intra-muscular injection can also be used.

15

**THE EMBODIMENTS OF THE INVENTION IN WHICH AN EXCLUSIVE PROPERTY OR PRIVILEGE IS CLAIMED ARE DEFINED AS FOLLOWS:**

1. A trace element solution, which comprises at least the following metals:
  - (a) zinc, in a concentration of at least 60 mg/ml;
  - 5 (b) manganese; and
  - (c) selenium;and which comprises a concentration of the metals of at least 90 mg/ml.
2. The solution as claimed in claim 1, which comprises the following concentrations:
  - 10 (a) at least 10 mg/ml manganese; and
  - (b) at least 5 mg/ml selenium.
3. The solution as claimed in claim 1, which further comprises chromium.
4. The solution as claimed in claim 3, wherein the concentration of the chromium is at least 5 mg/ml.
- 15 5. The solution as claimed in claim 1, which further comprises iodine.
6. The solution as claimed in claim 5, wherein the concentration of the iodine is at least 50-300 mg/ml.
7. The solution as claimed in claim 1, in which the ratio of zinc to manganese is at least 2:1.
- 20 8. The solution as claimed in claim 1, in which the ratio of zinc to manganese is at least 4:1.
9. The solution as claimed in claim 1, in which the ratio of zinc to selenium is at least 12:1.
10. The solution as claimed in claim 1, in which at least one of the metals is  
25 provided in the form of an EDTA complex and/or an EDDS complex.

11. The solution as claimed in claim 11, in which the EDTA source is EDTA acid, disodium EDTA, tetra-sodium EDTA, calcium EDTA, potassium EDTA and/or any other EDTA source.
12. The solution as claimed in claim 1, which comprises chloro-cresol and/or  
5 benzyl alcohol as preservative.
13. The solution as claimed in claim 1, which is an injectable solution.
14. The solution as claimed in claim 1, which is a drenchable solution.
15. The solution as claimed in claim 1, wherein said selenium is provided in the form of sodiumselenite.
- 10 16. The solution as claimed in claim 1, wherein said manganese is derived from manganese carbonate dissolved in heated water.