



(22) Date de dépôt/Filing Date: 2004/10/15

(41) Mise à la disp. pub./Open to Public Insp.: 2005/04/24

(30) Priorité/Priority: 2003/10/24 (0324861.4) GB

(51) Cl.Int.⁷/Int.Cl.⁷ B22D 41/16, B22D 37/00


(71) Demandeur/Applicant:
PYROTEK INCORPORATED, US

(72) Inventeur/Inventor:
VINCENT, MARK, US

(74) Agent: GOWLING LAFLEUR HENDERSON LLP

(54) Titre : BROCHE DE COMMANDE

(54) Title: CONTROL PIN



(57) **Abrégé/Abstract:**

A control pin (12) for controlling the flow of liquid metal in a casting process includes an elongate body member (34), the body member being made at least partially of a composite ceramic material that includes a fibrous reinforcing material embedded within a ceramic matrix. The body member (34) is preferably hollow and includes a wear-resistant tip (36) at one end.

ABSTRACT**CONTROL PIN**

A control pin (12) for controlling the flow of liquid metal in a casting process includes an elongate body member (34), the body member being made at least partially of a composite ceramic material that includes a fibrous reinforcing material embedded within a ceramic matrix. The body member (34) is preferably hollow and includes a wear-resistant tip (36) at one end.

CONTROL PIN

The present invention relates to a control pin for controlling the flow of liquid metal in a casting process. In particular, but not exclusively, it relates to a control pin for
5 controlling the flow of nonferrous liquid metals such as aluminium and zinc.

A typical metal casting process is described in US Patent No. 3,111,732. In that process, liquid metal is poured through a spout (or "underpour outlet") into a mould, where the metal freezes to form a billet or slab. The flow of metal through the spout is controlled by a control pin (or "flow regulator") that is located within the spout. The
10 control pin may be raised to increase the rate of flow of metal through the spout, or lowered to decrease or interrupt the flow of metal.

Control pins are generally made of a refractory material, which is able to withstand the high temperature of the molten metal. The material must also be hard so as to resist wear on the end of the rod, where it presses against the seat in the spout. One of the
15 most commonly used materials is dense fused silica (DFS). This material is quite tough and has good thermal shock characteristics, but silica is wetted and attacked by liquid aluminium and control pins made of this material therefore have to be provided with a non-stick protective coating, for example of boron nitride. This coating has to be reapplied frequently (for example every one or two pouring operations) and such pins
20 therefore have a high maintenance requirement.

Further, although DFS is quite tough, it is susceptible to cracking and these cracks tend to propagate through the material during use. This can eventually cause part of the control pin to break away and block the pouring spout. As a precaution against this, a stainless steel wire is sometimes embedded in the DFS material to ensure that even if
25 the control pin breaks, the broken part can still be withdrawn from the spout.

Another disadvantage with control pins made of DFS is that they tend to have a high heat capacity and have to be pre-heated prior to commencement of the metal pouring operation, to bring them up to or close to the temperature of the molten metal. This adds considerably to the complexity of the pouring operation and gives rise to the risk

of a serious accident when transferring the hot control pin from the pre-heating oven to the spout. If the control pin is not pre-heated, the molten metal can solidify upon contact with the control pin, thus blocking the spout.

Other materials are sometimes used for the control pin including, for example, cement-based refractories. Such materials are not wetted by the aluminium and therefore suffer less damage and require less maintenance. However, they are fragile and are easily chipped or broken. Further, such pins have a high heat capacity and therefore need pre-heating.

It is also known to make control pins from graphite. However, graphite suffers from oxidation and erosion at the air-metal interface, which limits the useful life of the control pins made from this material. Also, like control pins made of DFS or cement-based refractories, graphite pins have a high heat capacity and so require pre-heating.

Another refractory material described in US 5,880,046 comprises an aqueous solution of phosphoric acid with a mixture of wollastonite and colloidal silica. The material is said to have good thermal insulation characteristics and very good behaviour with respect to molten aluminium. However, it is quite soft and therefore not very hard-wearing.

It is an object of the present invention to provide a control pin that mitigates at least some of the aforesaid disadvantages.

According to the present invention there is provided a control pin for controlling the flow of liquid metal in a casting process, the control pin including an elongate body member and a wear-resistant tip at one end of the elongate body member, the body member being made at least partially of a laminated composite ceramic material that includes multiple layers of a reinforcing fabric embedded within a cast ceramic matrix. In particular, but not exclusively, the invention relates to a control pin for controlling the flow of nonferrous liquid metals such as aluminium and zinc.

A control pin made of a laminated composite ceramic material is extremely tough owing to the presence of the reinforcing fabric, which prevents cracks propagating

through the material. Breakage of the control pin and blocking of the pouring spout is therefore prevented.

The control pin includes a wear-resistant tip at the lower end of the elongate body member, to reduce erosion by the liquid metal and wear from contact with the spout.

- 5 The composite ceramic material also has good thermal shock characteristics and is not wetted or attacked by liquid aluminium. A control pin made of this material therefore has a long life and a low maintenance requirement.

A control pin made of the composite ceramic material can also have a low heat capacity and so does not have to be pre-heated prior to commencement of the metal pouring
10 operation. This greatly simplifies the pouring operation and provides substantial cost savings and safety benefits.

Advantageously, the reinforcing fabric comprises a woven fabric, preferably made of glass.

The composite ceramic material may include between two and 25 layers, and preferably
15 between 4 and 10 layers, of reinforcing fabric.

The matrix material may be selected from a group comprising fused silica, alumina, mullite, silicon carbide, silicon nitride, silicon aluminium oxy-nitride, zircon, magnesia, zirconia, graphite, calcium silicate, boron nitride (solid BN), aluminium nitride (AlN) and titanium diboride (TiB₂), and mixtures of these materials. The matrix material is
20 preferably calcium based and may include calcium silicate and silica. More preferably, the matrix material includes Wollastonite and colloidal silica.

Advantageously, the control pin includes a non-stick surface coating, which may include boron nitride, to reduce wetting by the liquid metal and reduce or prevent the depositing of a skin or skull of metal on the surface of the control pin. Although the
25 provision of a non-stick coating is preferred, that coating does not have to be reapplied as frequently as with control pins made of other some materials such as DFS, since the composite ceramic material of the pin body is naturally non-wetted.

The control may be substantially cylindrical and is preferably constructed and arranged to be suspended substantially vertically in use. The control pin may have a suspension point at its upper end and a seating at its lower end.

5 The elongate body member is preferably at least partially hollow. This reduces the heat capacity of the pin, so that it heats rapidly on contact with the liquid metal, without causing the metal to freeze. It is particularly advantageous for the lower portion of the control pin, which is immersed in the liquid metal, to be hollow. The elongate body member may include a circumferential wall having a wall thickness in the range 1-10mm, preferably approximately 5mm, to provide a low heat capacity.

10 The wear-resistant tip is preferably inserted at least partially into one end of the elongate body member.

Advantageously, the elongate body member and the wear-resistant tip have complementary locking formations. The complementary locking formations may include complementary recesses on the elongate body member and the wear-resistant
15 tip, which are filled with an adhesive or cement.

The wear-resistant tip may be made of a ceramic material, and preferably from a material selected from a group comprising fused silica, alumina, mullite, silicon carbide, silicon nitride, silicon aluminium oxy-nitride, zircon, magnesia, zirconia, graphite, calcium silicate, boron nitride, aluminium titanate, aluminium nitride and
20 titanium diboride. Preferably, the tip is made of a non-wetting material with a low coefficient thermal expansion, for example a cement-bonded fused silica refractory. Advantageously, the wear-resistant tip is made from a material having a density in the range 1800-3000kg/m³, preferably 1900-2500kg/m³.

Advantageously, the control pin has a length in the range 200-1000mm (typically
25 750mm) and a diameter in the range 20-75mm (typically 40mm).

Various embodiments of the present invention will now be described, by way of example, with reference to the accompanying drawings, in which:

Figure 1 is a plan view showing schematically the main components of a typical aluminium casting installation;

Figure 2 is a side elevation of a control pin located in an operational position within a first kind of pouring spout (the pouring spout being shown in side section);

5 Figure 3 is a side sectional view of the control pin shown in Figure 2;

Figure 4 is a side elevation of a control pin located in an operational position above a second kind of pouring spout (the pouring spout again being shown in side section);

Figure 5 is a cross-section through a modified control pin, and

Figure 6 is a side-section on line A-A of figure 5.

10 A typical aluminium casting installation is shown schematically in Figure 1 and includes a furnace 2, from which molten metal flows through a set of launders 4a,4b,4c (or troughs) to a mould 6, which may for example be a direct chill mould. Between the furnace 2 and the mould 6 various additional metal processing units may be provided including, for example, a degassing unit 8 and a filter unit 10. Metal flows from the last
15 launder 4c into the mould 6 through a down spout 12, the flow through the spout being controlled by a control pin 14.

The down spout 12 and the associated control pin 14 are shown in more detail in Figure 2. The down spout 12 is made of a refractory material such as dense fused silica (DFS) and is conventional in design. The spout is tubular, having a cylindrical wall 16 with an
20 axial bore 17 and an outwardly extending flange 18 at its upper end. The lower part 20 of the spout has a frusto-conical external shape and internally has a frusto-conical seat 22, leading to a reduced diameter cylindrical bore 24. In use, the spout 12 is mounted in the bottom of a launder 4c, so that molten metal within the launder can flow out through the spout.

25 The control pin 14 is substantially cylindrical in shape, and in use is suspended vertically so that its lower end 26 is located within the cylindrical body 16 of the outlet spout 12. The edge 28 at the lower end of the control pin is bevelled to provide a seal when located against the seat 22 in the spout. The upper part 30 of the control pin is of

a slightly reduced diameter, and includes a horizontal mounting bore 32 from which the pin is suspended.

As shown in Figure 3, the control pin 14 includes a hollow tubular body member 34 having a hard wear-resistant tip 36 at its lower end. The tip 36 has a head 36a that protrudes beyond the end of the tubular body 34, and a body portion 36b that is
5 cemented or otherwise secured within the lower end 26 of the control pin 14.

The tubular body 34 of the control pin 14 is made of a composite ceramic material that includes numerous layers of a woven fibre reinforcing fabric embedded in a ceramic matrix. The woven fibre reinforcing fabric is preferably made of woven glass. Various
10 materials may be used for the ceramic matrix, including fused silica, alumina, mullite, silicon carbide, silicon nitride, silicon aluminium oxy-nitride, zircon, magnesia, zirconia, graphite, calcium silicate, boron nitride, aluminium nitride and titanium diboride, or a mixture of these materials. Preferably, the ceramic matrix includes calcium silicate (Wollastonite) and silica and comprises a mouldable refractory
15 composition as described in US Patent No: 5,880,046, which is sold by Pyrotek, Inc. under the trademark RFM.

In a preferred embodiment, the ceramic matrix is made from a composition consisting essentially of 8% to 25% by weight of an aqueous phosphoric acid solution having a concentration of phosphoric acid ranging from 40% to 85% by weight, said phosphoric
20 acid having up to 50% of its primary acidic functions neutralized by reaction with vermiculite; and 75% to 92% by weight of a mixture containing wollastonite and an aqueous suspension containing from 20% to about 40% by weight of colloidal silica, wherein the mixture has a weight ratio of said aqueous suspension to said wollastonite ranging from 0.5 to 1.2.

25 The tubular body 34 of the control pin 14 preferably has between 2 and 25 layers of the reinforcing fabric, typically approximately 4 to 10 layers.

The tip 36 is preferably made of a hard, wear-resistant material that resists erosion from the liquid metal and wear from contact with the spout 12. The material also preferably has good resistance to thermal shock, a low density (approx. 1900-2500 kg/m³) and a

low coefficient of thermal expansion (approx. $0.7-1.0 \times 10^{-6}$ mm/mm/°C). More particularly, the density and thermal expansion values should be similar to those of the matrix material, so that they are well matched. The tip 36 may be manufactured from a ceramic material, for example a fused silica refractory, dense fused silica (DFS), alumina, mullite, silicon carbide, silicon nitride, zircon, magnesia, zirconia, graphite, calcium silicate, boron nitride (solid BN), aluminium titanate, aluminium nitride (AlN), titanium diboride (TiB₂) or silicon aluminium oxynitride (Sialon).

A particularly preferred material for the wear-resistant tip 36 is a fused silica refractory such as that sold by Pyrotek Inc. under the trademark Pyrocast XL, which in addition to a fused silica aggregate also includes other ingredients such as non-wetting agents and cement. This material provides a number of significant performance advantages, including high resistance to thermal shock, high erosion resistance, good dimensional stability, easy cleaning and non-wetting properties.

The important physical characteristics of some of the above-mentioned materials are shown below in Table 1, together with the comparative characteristics of the preferred composite ceramic material, Pyrotek RFM™.

Table 1.

Material	Pyrotek Trademark	Density kg/m ³	Thermal expansion coefficient mm/mm/°C $\times 10^{-6}$	Max. service temperature °C
Composite ceramic	RFM	1600	0.9	1100
Fused silica refractory	Pyrocast XL	1900-1950	0.82	1000
Dense fused silica	Pyrocast DFS	1760-1950	0.5-0.7	1650
Silicon carbide	Pyrocast XL-SC	2563	4.9	1200
Alumina	Pyrocast AL2	2565	5.7	1650
Silicon aluminium oxynitride	O'-Sialon	2620	3.9	1500

Preferably, the control pin 14 is provided with a non-stick coating, for example of boron nitride, to enhance its non-wetting properties.

The dimensions of the spout 12 and the control pin 14 may of course be varied according to the capacity of the casting installation. Usually, the control pin will have a
5 length of approximately 200-1000mm (typically 750mm) and a diameter of 20-75mm (typically 40mm). The wall thickness of the tubular body 34 will normally be between 1 and 10mm, a thickness of 5mm being typical.

In the apparatus shown in Figure 4, the control pin 14 is identical to that shown in Figures 2 and 3. The outlet spout 112 is of a different design, having a frusto-conical
10 seat 122 at its upper end, above a cylindrical bore 117. The external wall of the spout 112 includes an upper part 116 that is frusto-conical in shape, and a lower cylindrical part 120. The control pin may be seated against the seat 122 to interrupt the flow of liquid metal, or raised to allow a controlled flow of metal through the spout.

Because the upper tubular part of the control pin 14 is made of a laminated composite
15 material, including a woven fibre reinforcing fabric, it is extremely strong and tough. Even if small cracks develop in the ceramic matrix material, these do not propagate owing to the presence of the woven glass reinforcing fabric.

The control pin 14 also has a low heat capacity, owing to the fact that the tubular body 34 is hollow and has a low mass. Although the tip 36 is solid, it is largely insulated by
20 the surrounding wall of the tubular body 34 and, being relatively small and of low mass, it also has a low heat capacity. The control pin 14 therefore draws very little heat from the molten metal flowing through the spout 12, with the result that it is not generally necessary to preheat the control pin 14 prior to pouring.

The ceramic matrix material is not wetted by the molten aluminium and, although the
25 provision of a non-stick coating (e.g. Boron Nitride) is preferred, this can be applied much less often than is necessary with control pins made of some other materials, such as DFS.

The ceramic tip 36 is very hard wearing, and therefore provides a good seal against the seat of the spout, even after many uses.

A method of manufacturing the control pin will now be described. First, the ceramic matrix material is made up by blending together the components of that material, for example as described in US Patent No: 5,880,046. The component materials may, for example, consist of approximately 60% by wt Wollastonite and 40% by wt solid colloidal silica. These materials are blended together to form a slurry.

The hollow body 34 of the control pin 14 is then constructed in a series of layers on a mandrel, by laying precut grades of woven E-glass cloth onto the mandrel and adding the slurry, working it into the fabric to ensure full wetting of the fabric. This is repeated to build up successive layers of fabric and matrix material, until the desired thickness is achieved. Each layer typically has a thickness of approximately 1mm and the control pin shown in Figures 2 and 3 would typically have approximately 5 layers of the glass reinforcing fabric.

Once the product has achieved the desired thickness, it is machined in green (unfired) form to shape the outer surface of the tubular body 34. The tubular body 34 is then removed from the mandrel and placed in a furnace to dry. After drying, the ceramic tip 36 is inserted and glued into place using a suitable adhesive. The control pin is then subjected to final finishing and fettling processes, and a non-stick coating, for example of boron nitride, is applied.

Although control pins of numerous different lengths are required by different foundries, we have found that in practice the tubular body 34 of the control pin 14 can be made up in advance to a limited number of standard lengths, and these tubular bodies can then be cut to length as required. After cutting, a ceramic tip 36 of the appropriate diameter is inserted into the open end of the tubular body 34 and glued in place with a suitable adhesive. A non-stick coating of boron nitride can then be applied to the complete pin 14. This method of production allows the tubular bodies 34 to be mass produced in advance and held in stock until required, thereby significantly reducing both the manufacturing and storage costs.

A modified form of the control pin 14 and the wear resistant tip 36 is shown in Figures 5 and 6. The control pin 14 has three annular grooves 40, which are provided on the

internal surface 42 of the tubular body 34 towards the lower end 26 of the control pin (only the lower end of the pin being shown). Each of these grooves 40 has a semi-circular cross-section. Three more annular grooves 44, also semi-circular in cross-section, are formed on the external surface of the body portion 36a of the wear-resistant tip 36. The two sets of grooves 40,44 are complementary to one another and are designed so that when the tip 36 is fully inserted into the end of the hollow control pin 14 they are aligned, forming three annular channels of circular cross-section. When the tip 36 is glued into place, the glue fills these channels, forming a mechanical lock that prevents removal of the tip 36 from the control pin 14.

Various other modifications of the invention are possible, some of which will now be described.

The ceramic tip 36 may be attached to the tubular body 34 in a number of different ways, for example by means of an adhesive, or complementary screw threads on the tip and the body, or by a locking pin that extends through complementary apertures in the tip and the body. Alternatively, the tubular body 34 may be cast *in situ* around the ceramic tip 36, the enclosed part of the tip having locking formations to prevent any separation of the two parts. It is also possible to provide a removable tip, secured for example by means of complementary screw threads, so that it can be replaced in the event of excessive wear or damage.

Although it is preferred that the whole of the body 34 is tubular, it may alternatively be solid or only partially tubular, and the tubular part may if desired be filled with another material. Further, although it is preferred that the whole of the body 34 is made of the same composite ceramic material, parts of the body may be made of other materials. For example, the upper part of the control pin, which does not come into contact the liquid metal, may be made of a wide variety of materials.

CLAIMS

1. A control pin for controlling the flow of liquid metal in a casting process, the control pin including an elongate body member and a wear-resistant tip at one end of the elongate body member, the body member being made at least partially of a laminated composite ceramic material that includes multiple layers of a reinforcing fabric embedded within a cast ceramic matrix.
2. A control pin according to claim 1, wherein the reinforcing fabric comprises a woven reinforcing fabric.
3. A control pin according to claim 1 or claim 2, wherein the reinforcing fabric is made of glass.
4. A control pin according to any one of the preceding claims, wherein the composite ceramic material includes between 2 and 25 layers, and preferably between 4 and 10 layers, of reinforcing fabric.
5. A control pin according to any one of the preceding claims, wherein the matrix material is selected from a group comprising fused silica, alumina, mullite, silicon carbide, silicon nitride, silicon aluminium oxy-nitride, zircon, magnesia, zirconia, graphite, calcium silicate, boron nitride, aluminium nitride and titanium diboride, and mixtures of these materials.
6. A control pin according to any one of the preceding claims, wherein the matrix material is calcium based.
7. A control pin according to any one of the preceding claims, wherein the matrix material includes calcium silicate and silica.
8. A control pin according to any one of the preceding claims, wherein the matrix material includes Wollastonite and colloidal silica.
9. A control pin according to any one of the preceding claims, wherein the control pin includes a non-stick surface coating.

10. A control pin according to claim 9, wherein the coating includes boron nitride.
11. A control pin according to any one of the preceding claims, wherein the elongate body member is substantially cylindrical.
12. A control pin according to any one of the preceding claims, wherein the elongate body member is at least partially hollow.
13. A control pin according to claim 12, wherein the elongate body member includes a circumferential wall having a wall thickness in the range 1-10mm.
14. A control pin according to any one of the preceding claims, wherein the wear-resistant tip is inserted at least partially into one end of the elongate body member.
15. A control pin according to any one of the preceding claims, wherein the elongate body member and the wear-resistant tip have complementary locking formations.
16. A control pin according to claim 15, wherein the complementary locking formations include complementary recesses on the elongate body member and the wear-resistant tip, which are filled with an adhesive or cement.
17. A control pin according to any one of the preceding claims, wherein the wear-resistant tip is made of a ceramic material.
18. A control pin according to claim 17, wherein the wear-resistant tip is made of a material selected from a group comprising fused silica, alumina, mullite, silicon carbide, silicon nitride, silicon aluminium oxy-nitride, zircon, magnesia, zirconia, graphite, calcium silicate, boron nitride, aluminium titanate, aluminium nitride and titanium diboride.
19. A control pin according to any one of the preceding claims, wherein the wear-resistant tip is made of a material having a density in the range 1800-3000kg/m³, preferably 1900-2500kg/m³.

20. A control pin according to any one of the preceding claims, wherein the control pin has a length in the range 200-1000mm.
21. A control pin according to any one of the preceding claims, wherein the control pin has a diameter in the range 20-75mm.

1/5




FIG. 1

2/5




FIG. 2

3/5




FIG. 3

4/5




FIG. 4




FIG. 5

Sect. A-A

FIG. 6

