

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
28 August 2008 (28.08.2008)

PCT

(10) International Publication Number
WO 2008/103695 A1

(51) International Patent Classification:
C09D 11/02 (2006.01)

(21) International Application Number:
PCT/US2008/054364

(22) International Filing Date:
20 February 2008 (20.02.2008)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
11/677,453 21 February 2007 (21.02.2007) US

(71) Applicant (for all designated States except US): **SAN-FORD, L.P.** [US/US]; 2707 Butterfield Road, Oak Brook, IL 60523 (US).

(72) Inventor; and

(75) Inventor/Applicant (for US only): **WANG, Xiaomang** [US/US]; 29652 N. Birch Avenue, Lake Bluff, IL 60044 (US).

(74) Agent: **LAWRENCE, Andrew, M.**; Marshall, Gerstein & Borun LLP, 233 S. Wacker Drive, Suite 6300, Sears Tower, Chicago, IL 60606-6357 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MT, NL, NO, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

(54) Title: PERMANENT INK COMPOSITIONS AND WRITING INSTRUMENTS CONTAINING SAME

(57) Abstract: The ink compositions comprise at least one solvent, at least one colorant, and at least one oil, and may be delivered from any of a variety of writing instruments including but not limited to ball pens, fountain pens, felt tip pens, and markers.



WO 2008/103695 A1

PERMANENT INK COMPOSITIONS AND WRITING INSTRUMENTS CONTAINING SAME

BACKGROUND OF THE DISCLOSURE

FIELD OF THE DISCLOSURE

[0001] The disclosure is generally related to permanent ink compositions and to writing instruments containing such ink compositions.

BRIEF DESCRIPTION OF RELATED TECHNOLOGY

[0002] The writing performance of writing instruments including but not limited to ball pens, felt tip pens, fountain pens, and markers can be negatively affected by a phenomenon referred to as "dry out." Dry out occurs because the ink composition contained in a writing instrument can evaporate from an exposed writing point, and leave a solid residue behind. The left over residue can result in the formation of a deposit that is capable of preventing a writing point, e.g., a ball point, from functioning properly, thereby causing the ball pen to write poorly or even fail. Similarly, the left over residue can clog the capillary tubes of fibrous ink reservoirs and/or fibrous nibs in writing instruments that rely upon capillary action, thereby causing such writing instruments to write poorly or even fail.

[0003] For this reason, consumers are often advised to cap writing instruments after use. Capping creates a substantially sealed atmosphere around the writing point, and thus lessens dry out. Alternatively, a writing instrument can be made to retract such that its writing point is substantially sealed after retraction - without need for a cap. Such capless retractable pens and markers are well known, and often use twisting or knock-type mechanisms to retract the writing point. However, dry out still can occur even when a cap is used or a point of a writing instrument is retracted.

[0004] Existing ink compositions often include slow evaporating solvents (e.g., solvents having boiling points greater than about 115°C), commonly referred to as humectants, in order to mitigate dry out. Such slow evaporating solvents, however, can negatively affect the permanence of marks written with such ink compositions.

DETAILED DESCRIPTION

[0005] One embodiment of the disclosure provides permanent ink compositions having reduced rates of ink evaporation (at least relative to other, comparable solvent-dye based ink compositions). Another embodiment of the disclosure provides writing instruments containing such ink compositions. Yet another embodiment provides methods of making written markings with the disclosed ink compositions.

[0006] The disclosed ink compositions may be used in various writing instruments. For example, the ink compositions may be used in various pens including but not limited to ball pens (e.g., ball point pens, gel pens, and roller ball pens) and fountain pens. The disclosed inks are also well-suited for delivery from writing instruments comprising fibrous ink reservoirs and/or fibrous nibs writing instruments, such as felt tip pens and markers (e.g., “free-ink” markers and markers comprising fibrous reservoirs). Advantageously, the ink compositions provide permanent written marks on both porous and non-porous substrates, and good color intensity on porous and non-porous substrates.

[0007] In one aspect, the ink compositions comprise at least one solvent, at least one colorant, and at least one oil. The ink compositions may optionally further comprise a resin and one or more additives.

[0008] The solvent may be any suitable solvent (or combination thereof), but its interaction with the oil contained in the ink composition is related to obtaining desired performance. Specifically, the oil should not be more than about 50 weight percent (“wt.%)” soluble in the employed solvent(s). The ink compositions typically comprise from about 20 wt.% to about 98 wt.%, about 30 wt.% to about 97 wt.%, about 40 wt.% to about 95 wt.%, and/or about 50 wt.% to about 94 wt.% of the solvent(s).

[0009] Representative solvents for use in the ink compositions include but are not limited to glycol ethers including but not limited to ethylene glycol monomethyl ether, ethylene glycol monoethyl ether, ethylene glycol monobutyl ether, ethylene glycol monophenyl ether, propylene glycol monomethyl ether, propylene glycol monoethyl ether, propylene glycol monobutyl ether, propylene glycol monophenyl ether, and similar solvents, alcohols including but not limited to ethanol, propanols (e.g., n-propanol and isopropanol), butanols

(e.g., n-butanol, sec-butanol, isobutanol, tert-butanol), pentanols, hexanols, octanols, and similar solvents, ketones including but not limited to 4-hydroxy-4-methyl-2-pentanone (also known as diacetone alcohol), methyl isobutyl ketone, methyl isopropyl ketone, 2-pentanone, and similar solvents, and mixtures thereof.

[0010] The colorant need not be specifically limited and may comprise at least one dye, at least one pigment (either “dry” or as a dispersion), or a combination of at least one dye and at least one pigment; however, dyes are generally preferred for use in the ink compositions. A solvent dye, a polymeric dye, and/or an encapsulated dye (e.g., microsphere encapsulated dyes) are generally used. Pigments and/or dyes can be added to the formulation as dried powders, pigment concentrate chips, granules, and/or (pre-dispersed) dispersions.

[0011] Suitable pigments which can be used include but are not limited to titanium dioxide pigments, e.g., titanium dioxide pigments available under the TIPURE[®] trade name (Du Pont de Nemours, DE), the KRONOS[™] trade name (Kronos Inc, Houston, TX), and the TIOXIDE[®] trade name (Huntsman Tioxide, IL). Preferred titanium pigments include TIPURE[®] R-931, KRONOS[™] 2131, KRONOS[™] 2102, TIOXIDE[®] R-XL, and TIOXIDE[®] TR50, but of course other titanium pigments may also be used.

[0012] Additionally, organic pigments may be used. Suitable organic pigments include but are not limited to red, green, blue, yellow, orange, and carbon black pigments (BASF Corporation, NJ; Clariant Corporation, NC; Emerald Hilton Davis, OH; Ciba Specialty Chemicals, Switzerland; Degussa Corporation, NJ; Cabot Corporation, MA; and, Columbian Chemicals Company, GA). Of course, any suitable organic pigment may be used.

[0013] Other pigments such as metallic pigments may also be used. Aluminum pigments and bronze pigments are exemplary metallic pigments (Schlenk-BOTH Metallic Pigments, MA; Wolstenholme International Inc., IL; Silberline Manufacturing Co., Inc., PA; Zuxing Enterprise Co., Ltd., China; and, Echart GmbH & Co. KG, Germany).

[0014] Further, pearlescent and other special effect pigments may be used (BASF Corporation, NJ; Ciba Specialty Chemicals, Switzerland; and Taizhu, China).

[0015] Inorganic colored pigments may also be used. Preferred inorganic colored pigments include but are not limited to colored titanium dioxide pigments available under the

TICO™ trade name (Heubach, Germany) and colored mixed metal oxides inorganic pigments (Heubach, Germany and Cerdec Corporation, PA). Other suitable inorganic colored pigments such as colored aluminum pigments can also be used (Showa Aluminum Powder, K.K., Japan).

[0016] Similarly, any pigment dispersion in oil or relatively non-polar solvent may be used. Pigment dispersions can either be prepared or purchased (commercially available pigment dispersions). The ink compositions generally comprise about 0.1 wt.% to about 60 wt.%, about 0.1 wt.% to about 50 wt.%, and/or about 0.5 wt.% to about 45 wt.% of the pigment (solids), when present.

[0017] Representative commercially available pigment dispersions include but are not limited to alkyd pigment dispersions available under the TINT-AYD® AL trade name (Elementis Specialty, NJ), long oil alkyd dispersions (e.g., Formulator 24 A pigment dispersions available from Emerald Hilton-Davis, LLC, OH), short or medium oil alkyd dispersions (e.g., Industrial 42 A alkyd dispersions available from Emerald Hilton-Davis, LLC, OH), and any other suitable pigment dispersion in oil(s) or hydrocarbon solvent(s), with or without polymer and/or additional dispersing agents.

[0018] Alternatively, suitable pigment dispersions can be prepared by dispersing one or more pigments in a relatively non-polar solvent and/or oil. The pigments dispersions can optionally include a polymer and/or a dispersing agent. Many of the pigments (e.g., metallic pigments and pearlescent pigments) do not require special treatment to form a dispersion and can instead be prepared by mixing with solvent and any desired additives.

[0019] Suitable dyes include but are not limited to anionic and cationic dyes. The dyes can be basic dyes, direct dyes, solvent dyes, disperse dyes, or reactive dyes. The ink composition typically comprises about 0.01 wt.% to about 30 wt.%, about 0.10 wt.% to about 25 wt.%, about 0.20 wt.% to about 20 wt.%, and/or about 0.50 wt.% to about 20 wt.% of the dye (actives), when present.

[0020] Examples of suitable dyes include but are not limited to direct black dyes (e.g., direct black dye nos. 4, 14, 17, 22, 27, 38, 51, 112, 117, 154, 168, and the like); direct blue dyes (e.g., direct blue dye nos. 1, 6, 8, 14, 15, 25, 71, 76, 78, 80, 86, 90, 106, 108, 123, 163,

165, 199, 226, and the like); direct red dyes (e.g., direct red dye nos. 1, 2, 16, 23, 24, 28, 39, 62, 72, 227, 236, and the like); direct yellow dyes (e.g., direct yellow dye nos. 4, 11, 12, 27, 28, 33, 34, 39, 50, 58, 86, 100, 106, 107, 118, 127, 132, 142, 157, and the like); anthraquinone dyes; monoazo dyes; disazo dyes; phthalocyanine derivatives, including, for example, various phthalocyanine sulfonate salts; aza annulenes; formazan copper complexes; triphenodioxazines; various reactive dyes, including but not limited to reactive black dyes, reactive blue dyes, reactive red dyes (e.g., reactive red dye nos. 4, 56, 180, and the like), reactive yellow dyes (e.g., reactive yellow dye no. 37, and the like); various solvent dyes including but not limited to solvent yellow dyes (e.g., solvent yellow dye nos. 62, 82, 90, 162, and the like), solvent orange dyes (e.g., solvent orange dye nos. 54, 56, 58, 99, and the like), solvent red dyes (e.g., solvent red dye nos. 89, 119, 122, 132, 160, and the like), solvent blues dyes (e.g., solvent blue dye nos. 45, 48, 70, and the like), solvent black dyes (e.g., solvent black dye nos. 27, 29, and the like), and mixtures thereof. Dyes available under the NEOPEN[®] trade name (BASF Corp., WI), the VALIFAST[®] trade name (Orient Corporation of America, NJ), the MORFAST[®] and NAVIPON[®] trade names (Sunbelt Corporation, SC), and the SEPISOL[™] trade name (Bima 83, FR). Polymeric dyes also are also suitable colorants.

[0021] The selected oil(s) typically has the solubility property mentioned above relative to the ink composition solvent(s), but otherwise need not be limited. It is generally suitable when the oil has a solubility in the solvent(s) of 0 wt.% to about 50 wt.%, about 1 wt.% to about 40 wt.%, about 2 wt.% to about 30 wt.%, about 3 wt.% to about 25 wt.%, about 5 wt.% to about 20 wt.%, and/or about 10 wt.% to about 20 wt.%. Additionally, the oil may have a solubility in the solvent of less than about 40 wt.%, less than about 30 wt.%, less than about 25 wt.%, less than about 20 wt.%, less than about 15 wt.%, less than about 10 wt.%, less than about 5 wt.%, less than about 5 wt.%, less than about 2.5 wt.%, and/or less than about 1 wt.%. The oil should not be emulsified into the ink composition. Generally, lower (oil(s) in solvent(s)) solubility values are more preferred for obtaining desired performance.

[0022] Suitable oils include but are not limited to semi-drying oils such as soybean oils, cottonseed oils, corn oils, and sesame oils, non-drying oils such as olive oils, peanut oils, mineral oils, and castor oils, petroleum-based oils such as naphthenic process oils and

paraffinic process oils, silicone oils, and combinations thereof. Generally, petroleum-based oils and/or non-drying oils are preferred for obtaining desired performance. The oil typically comprises about 0.1 wt.% to about 15 wt.%, about 0.5 wt.% to about 10 wt.%, about 1 wt.% to about 8 wt.%, and/or about 1 wt.% to about 5 wt.% of the ink compositions. Exemplary oils include oils available under the TELURA[®] trade name (ExxonMobil Lubricants and Petroleum Specialties Co., a division of ExxonMobil Corporation, TX), TUFFLO[®] trade name (Citgo Petroleum Corporation, TX), and various mineral oils (Penreco, TX).

[0023] The ink compositions may optionally further comprise a resin. Suitable resins include but are not limited to rosin and modified rosin resins, alkyd resins, hydrocarbon resins, ketone resins, phenolic resins, acrylic resins, terpene resins, polyamide resins, and combinations thereof. The resin typically comprises about 0.1 wt.% to about 50 wt.%, about 0.5 wt.% to about 35 wt.%, about 1 wt.% to about 25 wt.%, and/or about 2 wt.% to about 20 wt.% of the ink compositions.

[0024] Preferably, the resin is soluble in the oil of the ink composition, and this can be beneficial for obtaining markings having good permanency. Typically, the resin has a solubility of greater than about 0.01 grams/mL oil, greater than about 0.05 grams/mL oil, greater than about 0.10 grams/mL oil, greater than about 0.15 grams/mL oil, greater than about 0.20 grams/mL oil, greater than about 0.25 grams/mL oil, and/or greater than about 0.30 grams/mL oil.

[0025] Exemplary resins include acrylic resins available under the JONCRYL[®] trade name (BASF Corp., WI), phenolic resins available under the Bakelite trade name (various), other suitable phenolic resins, e.g., CK-2103, CK-2400, CK-2432, and CK-2500 (Georgia Pacific Resins, Inc., a division of Georgia Pacific, Corp., GA), rosin resins and modified rosin resins available under the SYLVACOTE[®] and SYLVAPRINT[®] trade names (Arizona Chemical, FL), hydrocarbon resins available under the SYLVAPRINT[®] trade name (Arizona Chemical, FL), polyamide resins available under the UNI-REZ[®] trade name (Arizona Chemical, FL), and mixtures thereof.

[0026] The ink compositions may optionally further comprise one or more additives. The additive(s) can be selected from the group consisting of plasticizers, biocides, surface tension modifiers, wetting agents, synergic resins, dispersing agents, defoamers, surfactants,

humectants, viscosity modifiers (e.g., thickeners), flow additives, and other additives known in the art. The additives can be added to the ink compositions in an amount such that the overall desired performance of the ink compositions is not adversely affected in any aspect. Preferred surfactants include polydimethylsiloxane surfactants such as those available under the SILWET[®] trade name (GE Silicones, a division of General Electric Company, CT).

[0027] Including slow evaporating solvents (e.g., solvents having boiling points greater than about 115°C) or humectants such as glycerine and propylene glycol can detrimentally affect the desired permanency of markings made with the ink compositions. Thus, in one aspect, the ink compositions are substantially free of such humectants.

[0028] As used herein, the term “substantially free” means that the ink compositions disclosed herein contain less than 2 wt.%, less than 1 wt.%, and/or less than 0.50 wt.% of a referenced component or ingredient.

[0029] By including various of the listed additives and/or colorants in the ink compositions, various ink compositions (including highlighting writing inks and other special purpose writing inks) may be formulated, and their viscosities varied from very low values, for example, such as in free ink marker systems and other marker systems (e.g., comprising a fibrous reservoir), to very high values such as in gel pens and in ball point pens. When the ink composition is intended for delivery from a marker system, it generally has a viscosity value at 200 rotations per minute of about 1 centipoise to about 40 centipoises (cps) and/or about 2 cps to about 15 cps. When ink composition is intended for delivery from a ball pen, it generally has a viscosity value of at least about 750 cps and more typically at least about 1000 cps.

[0030] The ink compositions in accordance with the disclosure and writing instruments comprising same can be better understood in light of the following examples, which are merely intended to illustrate the ink compositions, and are not meant to limit the scope thereof in any way.

EXAMPLE 1

MARKER INK COMPOSITION

[0031] An ink composition was made by dissolving 5.0 grams of a phenolic resin, 7.0 grams of a first dye, and 5.0 grams of a second dye, into a solvent solution comprising 40.20 grams of n-propyl alcohol and 40 grams of ethyl alcohol (200 proof).

[0032] 2.50 grams of a naphthenic process oil and 0.30 grams of a polydimethylsiloxane surfactant were then added.

[0033] The ink had a viscosity value (at 200 RPM) of about 2.8.

[0034] The ink composition was loaded into a marker (comprising a fibrous reservoir in fluid communication with a fibrous nib) and the marker wrote well.

EXAMPLE 2

MARKER INK COMPOSITION

[0035] An ink composition was made by dissolving 3.8 grams of a phenolic resin and 4.5 grams of a dye into a solvent solution comprising 44.3 grams of n-propyl alcohol and 44.5 grams of ethyl alcohol (200 proof).

[0036] 2.50 grams of a naphthenic process oil and 0.40 grams of a polydimethylsiloxane surfactant were then added.

[0037] The ink had a viscosity value (at 200 RPM) of about 2.2.

[0038] The ink composition was loaded into a marker (comprising a fibrous reservoir in fluid communication with a fibrous nib) and the marker wrote well.

[0039] Although the foregoing text is a detailed description of numerous different embodiments of a ink composition in accordance with the disclosure, the detailed description is to be construed as exemplary only and does not describe every possible embodiment of in accordance with the disclosure. Consequently only such limitations as appear in the appended claims should be placed on the invention.

WHAT IS CLAIMED IS:

1. An ink composition comprising:
at least one solvent;
at least one colorant; and,
at least one oil,
wherein the oil is less than 50 weight percent (wt.%) soluble in the solvent.
2. The ink composition of claim 1, wherein the colorant is selected from the group consisting of dyes and pigments.
3. The ink composition of claim 1, wherein the oil is selected from semi-drying oils, non-drying oils, petroleum-based oils, silicone oils, and combinations thereof.
4. The ink composition of claim 1, further comprising a resin.
5. The ink composition of claim 4, wherein the resin has a solubility of greater than about 0.01 grams resin per milliliter of the oil (g/mL oil).
6. The ink composition of claim 4, wherein the resin is selected from the group consisting of rosin and modified rosin resins, alkyd resins, hydrocarbon resins, ketone resins, phenolic resins, acrylic resins, terpene resins, polyamide resins, and combinations thereof.
7. The ink composition of claim 1, wherein the ink composition is substantially free of humectants.

8. The ink composition of claim 1, wherein the colorant is a dye, and the ink composition comprises about 20 wt.% to about 98 wt.% of the solvent, about 0.01 wt.% to about 30 wt.% of the dye, and about 0.5 wt.% to about 10 wt.% of the oil.

9. A writing instrument containing an ink composition comprising: at least one solvent, at least one colorant, and at least one oil, wherein the oil is less than 50 weight percent (wt.%) soluble in the solvent.

10. The writing instrument of claim 9, wherein the writing instrument is selected from the group consisting of ball pens, fountain pens, felt tip pens, and markers.

11. The writing instrument of claim 9, wherein the colorant is selected from the group consisting of dyes and pigments.

12. The writing instrument of claim 9, wherein the oil is selected from drying oils, semi-drying oils, non-drying oils, petroleum-based oils, silicone oils, and combinations thereof.

13. The writing instrument of claim 9, further comprising a resin.

14. The writing instrument of claim 13, wherein the resin has a solubility of greater than about 0.01 grams resin per milliliter of the oil (g/mL oil).

15. The writing instrument of claim 13, wherein the resin is selected from the group consisting of rosin and modified rosin resins, alkyd resins, hydrocarbon resins, ketone resins, phenolic resins, acrylic resins, terpene resins, polyamide resins, and combinations thereof.

16. The writing instrument of claim 9, wherein the ink composition is substantially free of humectants.

17. The writing instrument of claim 9, wherein the colorant is a dye, and the ink composition comprises about 20 wt.% to about 98 wt.% of the solvent, about 0.01 wt.% to about 30 wt.% of the dye, and about 0.5 wt.% to about 10 wt.% of the oil.

INTERNATIONAL SEARCH REPORT

International application No

PCT/US2008/054364

A. CLASSIFICATION OF SUBJECT MATTER
INV. C09D11/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
C09D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DATABASE WPI Week 200619 Derwent Publications Ltd., London, GB; AN 2006-178274 XP002483973 -& JP 2006 056931 A (TOHOKU RIKO KK) 2 March 2006 (2006-03-02) abstract	1-17
X	US 6 444 019 B1 (ZOU WAN KANG [US] ET AL) 3 September 2002 (2002-09-03) paragraph [0045]; claim 45; examples	1-9
X	US 2004/194658 A1 (KONNO YUKAKO [JP] ET AL) 7 October 2004 (2004-10-07) paragraph [0050]; claims; examples ----- -/--	1-9

☒ Further documents are listed in the continuation of Box C.

☒ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

12 June 2008

Date of mailing of the international search report

23/06/2008

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Ellrich, Klaus

INTERNATIONAL SEARCH REPORT

International application No

PCT/US2008/054364

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 00/63307 A (MARCONI CORP PLC [GB]) 26 October 2000 (2000-10-26) page 5, line 6; examples -----	1-9
X	US 6 165 258 A (ASADA KEISUKE [JP]) 26 December 2000 (2000-12-26) examples -----	1-9
X	WO 00/27935 A (GEN ELECTRIC CO PLC [GB]) 18 May 2000 (2000-05-18) page 4, line 19; examples -----	1-9

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/US2008/054364

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
JP 2006056931	A	02-03-2006	NONE	
US 6444019	B1	03-09-2002	NONE	
US 2004194658	A1	07-10-2004	CN 1526773 A	08-09-2004
WO 0063307	A	26-10-2000	AU 4130700 A	02-11-2000
US 6165258	A	26-12-2000	CN 1234420 A	10-11-1999
			JP 4080080 B2	23-04-2008
			JP 2000017215 A	18-01-2000
WO 0027935	A	18-05-2000	AT 247157 T	15-08-2003
			AU 770978 B2	11-03-2004
			AU 1058600 A	29-05-2000
			CA 2349591 A1	18-05-2000
			CN 1332773 A	23-01-2002
			DE 69910445 D1	18-09-2003
			DE 69910445 T2	01-07-2004
			EP 1157070 A1	28-11-2001
			JP 2002529572 T	10-09-2002