

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property

Organization

International Bureau

(43) International Publication Date

02 June 2022 (02.06.2022)



(10) International Publication Number

WO 2022/115751 A1

(51) International Patent Classification:

B01J 31/24 (2006.01) B01J 31/02 (2006.01)

B01J 31/22 (2006.01) C07C 2/08 (2006.01)

B01J 31/14 (2006.01) C07C 2/32 (2006.01)

(21) International Application Number:

PCT/US2021/061117

(22) International Filing Date:

30 November 2021 (30.11.2021)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

63/119,217 30 November 2020 (30.11.2020) US

63/119,136 30 November 2020 (30.11.2020) US

(71) Applicant: SAUDI ARABIAN OIL COMPANY

[SA/SA]; Post Office Box 5000, Dhahran, 31311 (SA).

(71) Applicant (for AG only): ARAMCO SERVICES COM-

PANY [US/US]; 1200 Smith Street, Two Allen Building, Houston, Texas 77002 (US).

(72) Inventors: SHAIKH, Sohail; c/o Saudi Arabian Oil Com-

pany, Post Office Box 5000, Dhahran, 31311 (SA). KHAWAJI, Motaz; c/o Saudi Arabian Oil Company, Post Office Box 5000, Dhahran, 31311 (SA). XU, Wei; c/o Saudi Arabian Oil Company, Post Office Box 5000, Dhahran, 31311 (SA).

(74) Agent: KANEL, Andrew S. et al.; DINSMORE &

SHOHL, Fifth Third Center, One South Main Street, Suite 1300, Dayton, Ohio 45402 (US).

(81) Designated States (unless otherwise indicated, for every

kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, IT, JO, JP, KE, KG, KH, KN, KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, WS, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every

kind of regional protection available): ARIPO (BW, GH,

GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) Title: CATALYST SYSTEMS

(57) Abstract: Catalyst systems suitable for tetramerizing ethylene to form 1-octene may include a catalyst having a structure according to Formula (VI) or Formula (VII). In Formulas (VI) and (VII), X is a halogen, a (C₂-C₃₀) carboxylate, acetylacetonate, or a (C₁-C₃₀) hydrocarbyl; L₁ is a neutral coordinating ligand; n is an integer from 0 to 6; Y is a (C₆-C₂₀)fluorine-substituted aryl, a (C₆-C₂₀)fluorine-substituted aryloxy, or a (C₁-C₂₀)fluorine-substituted alkoxy; and L₂ is a bidentate chelating ligand. The catalyst system may also include an aluminum containing agent which includes a reaction product of an organoaluminum compound and an antifouling compound. The antifouling compound may include one or more chlorinated hydrocarbons, chloro-aluminum alkyls, or combinations of these.



WO 2022/115751 A1

CATALYST SYSTEMS

CROSS REFERENCE TO RELATED APPLICATIONS

[0001] This application claims the benefit of and priority to U.S. Application Serial No. 63/119,217 filed on November 30, 2020 and entitled “Catalyst Systems,” the entire contents of which are incorporated by reference in the present disclosure. Additionally, this application claims the benefit of and priority to U.S. Application Serial No. 63/119,136 filed on November 30, 2020 and entitled “Catalyst Systems,” the entire contents of which are incorporated by reference in the present disclosure.

TECHNICAL FIELD

[0002] Embodiments of the present disclosure generally relate chemical processing and, more particularly, to catalyst systems utilized in such chemical processing.

BACKGROUND

[0003] Linear alpha-olefins (“LAOs”) were historically produced from cracking of refinery products or products of non-selective oligomerization of ethylene as a broad olefin fraction. Demand for these compounds is rising in North America, Western Europe, and Asia. Currently, there are several industrial processes that produce LAOs. Notably, the Shell Higher Olefin Process (SHOP), which has been in operation since 1977, can be used to produce LAOs. The SHOP process employs a combination of oligomerization and olefin metathesis chemistries to produce a variety of LAOs using a Ni-based catalyst. INEOS, a global manufacturer of petrochemicals has also developed a proprietary process for synthesizing a wide range of LAOs with the flexibility to change distributions of products to meet demand.

[0004] The demand for short chain alpha olefins, such as 1-octene and 1-hexene, has been rising as well. Specific chain length ranges of alpha-olefins are crucial for specific applications. For example, short chain-lengths (e.g., 1-butene to 1-octene) are used to improve the rheological melt and solid resin properties of polyethylene. The main consumer of 1-octene is the high-volume production of linear low-density polyethylene (LLDPE) and high-density polyethylene (HDPE),

-2-


which expands each year. Co-monomer alpha-olefin content is 1-2 % for HDPE grades and reach up to 30 % for some LLDPE grades.

[0005] As such, 1-octene is a very important chemical feedstock which is in market demand. Aside from the processes discussed above, various catalysts have been developed for the tetramerization of ethylene to form 1-octene. However, these catalysts have deficiencies in several respects. As such, improved catalysts which are suitable for tetramerization of ethylene to form 1-octene are desired in the industry.

SUMMARY

[0006] Fouling, as described herein, refers to the undesirable formation of polymers. Such polymers may form as side-products in the reaction of ethylene to form 1-octene when a catalyst system including chromium is used. However, as described herein, it has been discovered that the utilization of a co-catalyst that is a reaction product of an antifouling compound and an organoaluminum compound, may reduce fouling. As described herein, such antifouling compounds may include a chlorinated hydrocarbon, a chloro-aluminum alkyl, or combinations of these, and it is believed that the incorporation of this antifouling compound into the catalyst system may be responsible for reduced fouling. Moreover, in some embodiments, the utilization of the co-catalyst described herein may contribute to maintaining the selectivity of 1-octene, or even enhancing the selectivity of 1-octene, as compared with similar catalyst systems that do not include the antifouling compound.

[0007] According to one or more embodiments, a catalyst system suitable for tetramerizing ethylene to form 1-octene may include a catalyst having a structure according to Formula (VI) or Formula (VII).



[0008] In Formulas (VI) and (VII), X is a halogen, a (C₂-C₃₀) carboxylate, acetylacetonate, or a (C₁-C₃₀) hydrocarbyl; L₁ is a neutral coordinating ligand; n is an integer from 0 to 6; Y is a (C₆-C₂₀)fluorine-substituted aryl, a (C₆-C₂₀)fluorine-substituted aryloxy, or a (C₁-C₂₀)fluorine-

-3-

substituted alkoxy; and L $\cap$ L is a bidentate chelating ligand having the structure according to Formula (VIII).



[0009] In Formula (VIII), each R₁ and R₂ is independently chosen from a (C₁-C₅₀) alkyl group or a (C₆-C₅₀) aryl group, and Z is a (C₂-C₅₀) alkylene group, a (C₆-C₅₀) arylene group, —N(R₈)—, —P(R₈)—, —B(R₈)—, or —Si(R₈)₂— that links the two P atoms, where R₈ is a (C₁-C₅₀) alkyl group or a (C₆-C₅₀) aryl group. The catalyst system may further comprise at least one aluminum containing agent comprising a reaction product of an organoaluminum compound and an antifouling compound. The antifouling compound may comprise one or more chlorinated hydrocarbons, chloro-aluminum alkyls, or combinations of these.

[0010] According to one or more embodiments, a method of making a catalyst system suitable for tetramerizing ethylene to form 1-octene may include mixing a chromium compound, an anion-containing compound, a bidentate chelating ligand, and an aluminum containing agent to form the catalyst system. The aluminum containing agent is a reaction product of an organoaluminum compound and an antifouling compound, and wherein the antifouling compound comprises one or more chlorinated hydrocarbons, chloro-aluminum alkyls, or combinations of these.

[0011] Additional features and advantages of the described embodiments will be set forth in the detailed description which follows, and in part will be readily apparent to those skilled in the art from that description or recognized by practicing the described embodiments, including the detailed description which follows, as well as the claims.

DETAILED DESCRIPTION

[0012] Described herein are catalysts systems which may be utilized to produce 1-octene from ethylene by tetramerization. Also described herein are methods for utilizing such catalyst systems. The presently described catalyst systems may include a catalyst and a co-catalyst, as are described in detail herein. In one or more embodiments described herein, the catalyst may comprise chromium and, in some embodiments, may be the reaction product of a chromium

-4-

complex and a ligand. The co-catalyst may be the reaction product of at least an antifouling compound and an organoaluminum compound.

[0013] In one or more embodiments, the catalyst systems described herein may be used to selectively oligomerize ethylene to produce 1-octene, while reducing undesirable polymerization, sometimes referred to in this disclosure as “fouling.” For example, reactor fouling may occur at least partially due to the formation of solid polyethylene-based residues, which may reduce fluid flow and/or fully block or at least partially block fluids in a reactor system from flowing at a desired rate. Without being bound by any particular theory, it is believed that the incorporation of the antifouling compound into the catalyst system reduces fouling.

[0014] It should be understood that the catalyst systems presently described may not completely eliminate fouling during a reaction. However, in one or more embodiments, these catalyst systems reduce fouling as compared with catalyst systems which do not include the antifouling compound as described in the present disclosure. Also, it should be understood that, while the catalyst systems of the present disclosure may be useful in ethylene oligomerization reactions, such as ethylene dimerization to form 1-butene, they may also be useful for the catalysis of other chemical reactions, and the catalyst systems described in this disclosure should not be considered limited in their use to the tetramerization of ethylene to 1-octene. It should further be understood that the antifouling agents described in this disclosure may be incorporated with other catalyst systems which contain, for example, non-chromium based catalysts.

[0015] As used in this disclosure, a “catalyst” refers to any substance that increases the rate of a specific chemical reaction. Catalysts described in this disclosure may be utilized to promote various reactions, such as, but not limited to, tetramerization of ethylene to form 1-octene. Catalysts are generally not consumed in a reaction, but as would be understood in the art, may have reduced catalytic activity over time and need to be replaced and/or regenerated.

[0016] As used in this disclosure, a “co-catalyst” generally refers to any substance or chemical agent that brings about catalyst in conjunction with one or more catalysts. In some embodiments, a catalyst may have independent catalytic functionality, while in other embodiments, the catalyst may only have substantial catalytic functionality when paired with a co-catalyst. It should be understood that the catalyst and co-catalyst may be, in some embodiments, bonded or formed in a complex, but in other embodiments are not bonded or present

in a complex. Some co-catalysts may be said to “activate” a catalyst, which may increase catalytic functionality.

[0017] Additionally, as used in this disclosure, a “catalyst system” refers to any catalytically functional collection of chemical species. In some embodiments, a catalyst system may include a catalyst and a co-catalyst. In additional embodiments, a catalyst system may include additional components, such as, for example, additional co-catalysts or non-catalytic additives which may serve other purposes.

[0018] As described herein, a “reaction product” refers to a chemical species formed from the reaction of any two or more reactant species. A reaction product may result in a covalent or ionic bond, coordination, or other interaction between reactant species. In some embodiments, two or more reaction products may result from the reaction of the reactant species, and all of these possible produced chemical species are included in the reaction product as described herein.

[0019] When used to describe certain carbon atom-containing chemical groups, a parenthetical expression having the form “(C_x–C_y)” means that the unsubstituted form of the chemical group has from x carbon atoms to y carbon atoms, inclusive of x and y. For example, a (C₁–C₅₀) alkyl group is an alkyl group having from 1 to 50 carbon atoms in its unsubstituted form. In some embodiments and general structures, certain chemical groups may be substituted by one or more substituents. A substituted chemical group defined using the “(C_x–C_y)” parenthetical may contain more than y carbon atoms depending on the identity of any substituents. For example, a “(C₁–C₅₀) alkyl substituted with exactly one phenyl (–C₆H₅)” may contain from 7 to 56 carbon atoms. Thus, in general when a chemical group defined using the “(C_x–C_y)” parenthetical is substituted by one or more carbon atom-containing substituents, the minimum and maximum total number of carbon atoms of the chemical group is determined by adding to both x and y the combined sum of the number of carbon atoms from all of the carbon atom-containing substituents.

[0020] The term “substitution” means that at least one hydrogen atom (–H) bonded to a carbon atom or heteroatom of a corresponding unsubstituted compound or functional group is replaced by a substituent. Substituents may be any suitable functional group or radical that could replace a hydrogen atom bonded to a carbon atom or heteroatom of a corresponding unsubstituted

compound. For example, substituents may include, but are not limited to, hydrocarbyls, cyclohydrocarbyls, aryls, halogens, and amines.

[0021] The term “-H” means a hydrogen or hydrogen radical that is covalently bonded to another atom. “Hydrogen” and “-H” are interchangeable, and unless clearly specified have identical meanings.

[0022] The term “hydrocarbyl” means a monovalent radical resulting from removal of any hydrogen atom from a hydrocarbon, including aromatic hydrocarbons, non-aromatic hydrocarbons, cyclic or acyclic hydrocarbons, saturated or unsaturated hydrocarbons, straight chain or branched chain hydrocarbons, and substituted or unsubstituted hydrocarbons.

[0023] The term “heterohydrocarbyl” refers to a hydrocarbyl, from which at least one carbon atom has been replaced with a heteroatom. Examples of heteroatoms include, without limitation, oxygen, nitrogen, sulfur, and phosphorus.

[0024] The term “cyclohydrocarbyl” means an aromatic or non-aromatic, cyclic hydrocarbyl having at least three carbon atoms, including monocyclic and polycyclic hydrocarbyls, fused and non-fused polycyclic hydrocarbyls, and bicyclic hydrocarbyls, non-aromatic saturated or unsaturated cyclic hydrocarbyls, and substituted or unsubstituted hydrocarbyls.

[0025] The term “aryl” means an aromatic hydrocarbon radical, in which the carbon atoms of the aromatic system may be substituted or unsubstituted. Aryls include monocyclic, bicyclic and tricyclic aromatic hydrocarbon radicals. A monocyclic aromatic hydrocarbon radical includes one aromatic ring; a bicyclic aromatic hydrocarbon radical has two rings; and a tricyclic aromatic hydrocarbon radical has three rings. When the bicyclic or tricyclic aromatic hydrocarbon radical is present, at least one of the rings of the radical is aromatic. The other ring or rings of the aromatic radical may be independently fused or non-fused and aromatic or non-aromatic. Non-limiting examples of aryls include phenyl; fluorenyl; tetrahydrofluorenyl; indacenyl; hexahydroindacenyl; indenyl; dihydroindenyl; naphthyl; tetrahydronaphthyl; and phenanthrenyl.

[0026] The term “alkyl” means a saturated hydrocarbon radical that may be linear or branched. Accordingly, the term “(C₁-C₂₀) alkyl” means a saturated linear or branched hydrocarbon radical of from 1 to 20 carbon atoms that is unsubstituted or substituted. Examples of unsubstituted

-7-

(C₁-C₂₀) alkyl include methyl; ethyl; 1-propyl; 2-propyl; 1-butyl; 2-butyl; 2-methylpropyl; 1,1-dimethylethyl; 1-pentyl; 1-hexyl; 1-heptyl; 1-nonyl; and 1-decyl. Examples of substituted (C₁-C₂₀) alkyl include trifluoromethyl and trifluoroethyl.

[0027] The term “saturated” means lacking carbon–carbon double bonds, carbon–carbon triple bonds, and (in heteroatom-containing groups) carbon–nitrogen, carbon–phosphorous, and carbon–silicon double bonds. Where a saturated chemical group is substituted by one or more substituents, one or more double and/or triple bonds optionally may be present in substituents. The term “unsaturated” means containing one or more carbon–carbon double bonds or carbon–carbon triple bonds, or (in heteroatom-containing groups) one or more carbon–nitrogen double bonds, carbon–phosphorous double bonds, or carbon–silicon double bonds, not including double bonds that may be present in substituents, if any, or in aromatic rings or heteroaromatic rings, if any.

[0028] In one or more embodiments, the catalyst comprises chromium. It should be understood that, as contemplated herein, the catalyst may be any chemical compound that includes chromium that is catalytically functional for, without limitation, promoting the selective tetramerization of ethylene to form 1-octene.

[0029] In one or more embodiments, the catalyst includes a reaction product of a chromium complex and a boron-containing compound. In some embodiments, the catalyst includes a reaction product of the chromium complex and the boron-containing compound in, for example, an acetonitrile solvent.

[0030] In one or more embodiments, the catalyst system includes a reaction product of a chromium complex, a bidentate chelating ligand, an anion-containing compound, and an aluminum containing agent comprising the reaction product of an organoaluminum compound and an antifouling compound. In some embodiments, the catalyst system includes a reaction product of the chromium complex, the bidentate chelating ligand, the anion-containing compound, and the aluminum containing agent in a solvent, such as, for example, chlorobenzene.

[0031] It should be understood that the chromium complexes described herein are not necessarily limited in structure, but at least include chromium. In some embodiments, the chromium complex has a structure according to formula (I):



-8-

[0032] In formula (I), each X is independently chosen from a halogen, a (C₂-C₃₀) carboxylate, acetylacetonate (ACAC), or a (C₁-C₃₀) hydrocarbyl having or not having at least one of an ether group and an amine group. The term “carboxylate” refers to conjugate base of a carboxylic acid. In some embodiments, each X is fluorine (F), chlorine (Cl), bromine (Br), iodine (I), or combinations of these. In other embodiments, each X is a (C₁-C₃₀) alkyl group, a (C₁-C₃₀) alkyl group substituted by at least one of an ether group and an amine group, a (C₆-C₃₀) aryl group, or a (C₅-C₃₀) benzyl derivative. For example, X may be ethyl or ortho-(N,N-dimethylamino)benzyl.

[0033] In formula (I), each L₁ is a neutral coordinating ligand. In one or more embodiments, each L is independently chosen from a (C₂-C₃₀) nitrile, a (C₂-C₃₀) cyclic ether, a (C₂-C₃₀) acyclic ether, or an H₂O ligand. In some embodiments, L₁ may be acetonitrile, tetrahydrofuran (THF), diethylether, H₂O, or combinations of these. In embodiments, n is an integer of from 0 to 6. In one or more embodiments, n is an integer from 0 to 5, from 0 to 4, from 0 to 3, from 0 to 2, from 0 to 1, from 1 to 6, from 1 to 5, from 1 to 4, from 1 to 3, from 1 to 2, or any combination or subset of these ranges. However, it should be understood that n may vary depending on the method or the neutral coordinating agent added by which the catalyst is prepared. For example, n may vary depending on the degrees of vacuum drying that occurs during preparation.

[0034] In some embodiments, the chromium complex may be a chromium (III) chloride tetrahydrofuran complex (*i.e.*, Cr(THF)Cl₃).



[0035] In one or more embodiments, the catalyst may comprise the reaction product of the chromium compound and an anion-containing compound. It should be understood that the anion-containing compounds, described herein, which may coordinate with chromium of the chromium complex, are not necessarily limited in structure. However, in some embodiments, the anion-containing compound may have a structure according to formula (II) or formula (III):



[0036] In formula (II) and formula (III), each Y is independently chosen from a (C₆-C₂₀) fluorine-substituted aryl, a (C₆-C₂₀) fluorine-substituted aryloxy, or a (C₁-C₂₀) fluorine-substituted alkoxy. In one or more embodiments, Y is C₆F₅, 3,5-(CF₃)₂C₆H₃, OC(CF₃)₃, or combinations of these. For example, [BY₄]⁻ may be [B(C₆F₅)₄]⁻ or [B((3,5-(CF₃)₂C₆H₃)₄)]⁻. Formula (II) and


Formula (III) utilizes M^+ as a cation. In one or more embodiments, M^+ may be a metal inorganic cation. It is contemplated that any suitable metal may be used as M^+ . For example, M^+ may be Ag^+ in one or more embodiments. In one or more embodiments, M^+ may be an organic cation. For example, M^+ may be $[Ph_3C]$ or $[PhNHR_8R_9]$, where R_8 and R_9 are any (C_1 - C_{20}) hydrocarbyl.

[0037] In one or more embodiments, the reaction product of the chromium complex and the anion-containing compound is a chromium trivalent compound. In some embodiments, the chromium trivalent compound includes a non-coordinating anion and a chromium trivalent cation. In some embodiments, the chromium trivalent compound has a structure according to formula (IV) or formula (V):



[0038] In formula (IV) and formula (V), X, L_1 , n, and Y are the same as described previously with regard to formulas (I), (II), and (III).

[0039] In one or more embodiments, the catalyst may include the reaction product of a chromium trivalent compound having a structure according to formula (IV) or (V) and a bidentate chelating ligand. In some embodiments, the catalyst may include the reaction product of the chromium trivalent compound having a structure according to formula (IV) or (V) and the bidentate chelating ligand in, for example, a dichloromethane solvent. In such embodiments, one or more of the neutral coordinating ligands (L_1) of the chromium trivalent compound having a structure according to formula (IV) or (V) are substituted with the bidentate chelating ligand such that the resulting chromium trivalent compound has a structure according to formula (VI) or formula (VII):



[0040] In formula (IV), X, L_1 , n, and Y are the same as described previously with regard to formulas (I) to (V). In formulas (VI) and (VII) $L \cap L$ is a bidentate chelating ligand. In one or more embodiments, the bidentate chelating ligand is an organic compound having at least two atoms capable of coordinating with a metal. Examples of atoms capable of coordinating with a metal include phosphorus (P), nitrogen (N), oxygen (O), and combinations of these. In some embodiments, the bidentate chelating ligand has a structure according to formula (VIII):







[0041] In formula (V), each R_1 and R_2 is independently chosen from a (C_1 - C_{50}) alkyl group or a (C_6 - C_{50}) aryl group; and Z is a (C_2 - C_{50}) alkylene group, a (C_6 - C_{50}) arylene group, or $-N(R_8)-$, $-P(R_8)-$, $-B(R_8)-$, or $-Si(R_8)_2-$ that links the two P atoms, where R_8 is a (C_1 - C_{50}) alkyl group or a (C_6 - C_{50}) aryl group. The term “alkylene” refers to an alkyl comprise at least one unsaturated bond. The term “arylene” refers to a bivalent aryl. Without being bound by any particular theory, it is believed that chromium trivalent compounds that include a bidentate chelating ligand having a structure according to formula (V) provide increased catalytic activity and selectivity for 1-octene when used in ethylene tetramerization processes.

[0042] Without intending to be bound by theory, the bidentate chelating ligand may determine the electron density and stereo factors of the catalyst center. This may allow the catalyst to selectively oligomerize ethylene to the desired products, such as 1-octene. The bidentate chelating ligand may affect the stability of the catalyst, including the catalytic center and its surrounding environment. Furthermore, the bidentate chelating ligand may affect the activity and selectivity of the catalyst.




[0043] In one or more embodiments, the bidentate chelating ligand has a structure according to formula (VIII), where R_1 and R_2 are phenyl, and Z is $-N(R_8)-$ that links the two P atoms, where R_8 is a (C_1 - C_{50}) alkyl group or a (C_6 - C_{50}) aryl group. In such embodiments, the bidentate chelating ligand may be produced by reacting Ph_2PCl and R_8NH_2 . In some embodiments, the bidentate chelating ligand is $CH_3(CH_2)_5C(H)(Me)N(PPh_2)_2$. Without being bound by any particular theory, it is believed that embodiments where R_8 has 18 or more carbon atoms may be more suitable for use in large-scale ethylene tetramerization processes because the solubility of the resulting catalyst in aliphatic hydrocarbon solvents is improved.

[0044] In some embodiments, each R_1 and R_2 bonded to a single P may be bonded such that a cyclic moiety including P is formed. In one or more embodiments, R_1 , R_2 , and P may form a phospholane group. As described herein, a “phospholane group” refers to a cyclic organophosphorous compound comprising a five membered ring including phosphorous and four carbon atoms. In some embodiments, the phospholane compound may be unsubstituted or may be substituted by one or more hydrocarbyl groups. Cyclic moieties that may be formed from R_1 and P in some embodiments are depicted in formulas (IX) to (XVI).


-11-

**Formula (IX)****Formula (X)****Formula (XI)****Formula (XII)**

-12-

**Formula (XIII)****Formula (XIV)****Formula (XV)**


-13-

**Formula (XVI)**

[0045] As described herein, the catalyst system also includes an aluminum containing agent. In one or more embodiments, the aluminum containing agent may function as a co-catalyst, as described hereinabove, in the catalyst system. In the embodiments described herein, the aluminum containing agent may be the reaction product of an organoaluminum compound and the antifouling compound. It should be understood that the organoaluminum compound may comprise multiple chemical species, or a single chemical species. Likewise, the antifouling compound may comprise multiple chemical species, or a single chemical species.

[0046] In one or more embodiments, the aluminum containing agent may be formed from a organoaluminum compound. As described herein, an “organoaluminum compound” refers to any chemical compound that includes at least one aluminum atom and any organic moiety. It should be appreciated that the organoaluminum compound may include several chemical species, or may be a single chemical species.

[0047] In some embodiments, the organoaluminum compound may be an alkyl aluminum compound. The aluminum alkyl compounds described herein may have a generalized structure shown in formula (XVII):

**Formula (XVII)**

-14-

where R₃, R₄, and R₅ may each be a hydrogen atom, a (C₁-C₂₀) hydrocarbyl group, or a (C₁-C₂₀) heterohydrocarbyl group. In embodiments, the (C₁-C₂₀) hydrocarbyl group may be a substituted or unsubstituted (C₁-C₂₀) linear or branched hydrocarbyl group. In embodiments, the (C₁-C₂₀) heterohydrocarbyl group may be a substituted or unsubstituted (C₁-C₂₀) linear or branched heterohydrocarbyl group. In one or more embodiments, R₃, R₄, and R₅ may each be a hydrogen or a linear or branched (C₁-C₂₀) alkyl group. In additional embodiments, the alkyl aluminum compound may be an aluminosilane structure (i.e., a partial hydrolyzate of trialkylaluminum compounds). For example, and not by way of limitation, suitable aluminum alkyl compounds may include triethylaluminum, tripropylaluminum, tri-iso-butylaluminum, diisobutylaluminum hydride, and trihexylaluminum. In one or more embodiments, the organoaluminum compound of the catalyst system may comprise, consist essentially of, or consist of any of these compounds.

[0048] In one or more embodiments, the organoaluminum compound may comprise one or more of trimethylaluminum, triethylaluminum, tripropylaluminum, tri-iso-butylaluminum, diisobutylaluminum hydride, trihexylaluminum, tri-n-octylaluminum, methylaluminum dichloride, ethylaluminum dichloride, dimethylaluminum chloride, diethylaluminum chloride, aluminum isopropoxide, ethylaluminumsesquichloride, methylaluminumsesquichloride, methylaluminosilane (MAO), ethylaluminosilane (EAO), and modified methylaluminosilane (MMAO).


[0049] Without intending to be bound by theory, the alkyl aluminum compound may be operable to activate the chromium trivalent compound. Furthermore, the alkyl aluminum compound may be operable to alkylate the chromium trivalent compound.

[0050] In one or more embodiments, the aluminum containing agent may be formed from an antifouling compound. As described herein, an “antifouling compound” refers to any chemical compound that decreases fouling by polymer production. It should be appreciated that the antifouling compound may include several chemical species, or may be a single chemical species.

[0051] In some embodiments, the antifouling compound may be a chlorinated hydrocarbon, a chloro-aluminum alkyl, or combinations of these. As described herein, a “chlorinated hydrocarbon” refers to any organic chemical compound that includes at least one covalently bonded atom of chlorine that has an effect on the chemical behavior on the organic chemical compound. For example, a chlorinated hydrocarbon may be a chloroalkane (i.e., an

-15-

alkane with one or more hydrogens substituted by chlorine). The chloro-aluminum alkyls described herein may have a generalized structure shown in formula (XVIII):




Formula (XVIII)

[0052] In formula (XVIII), R₆ and R₇ are independently chosen from an unsubstituted hydrocarbyl group or a substituted hydrocarbyl group.

[0053] Without being bound by any particular theory, it is believed that the reaction between the organoaluminum compound and the antifouling compound may produce various chemical compounds. An example reaction of the aluminum alkyl compound of formula (XVII) and the chloro-aluminum alkyl of formula (XVIII) is shown in reaction scheme (I):

-16-



[0054] Without intending to be bound by theory, the reaction products of the organoaluminum compound and the antifouling compound (the chlorinated hydrocarbons or chloro-aluminum alkyls) may affect the ion-pair of the metal activation center of the catalyst. This may affect the coordination of ethylene with the metal activation center and the degree of chain-transfer predominant with respect to chain propagation. By controlling the chain propagation, the reaction products of the organoaluminum compound and the antifouling compound may increase the product selectivity of 1-octene and reduce the production of large polymers, resulting in reduced fouling. Furthermore, it is contemplated that in one or more embodiments the reactions between the quaternary salt and the organoaluminum compound are relatively fast and that there are little to no free quaternary salts remaining in the catalytic system once the quaternary salt and organoaluminum compound react.

[0055] It should be understood that the aluminum containing agents contemplated herein may include a number of different chemical species. However, as described in embodiments herein, these aluminum containing agent species share certain structures and can be commonly classified by moiety or structure.

[0056] In one or more embodiments described herein, the antifouling compound and organoaluminum compound may have a molar ratio of from 0.001 to 1, such as from 0.01 to 0.1. For example, according to embodiments, the molar ratio of antifouling compound to organoaluminum compound may be from 0.001 to 0.01, from 0.01 to 0.02, from 0.02 to 0.03, from 0.03 to 0.04, from 0.04 to 0.05, from 0.05 to 0.06, from 0.06 to 0.07, from 0.07 to 0.08, from 0.08 to 0.09, from 0.09 to 0.1, from 0.1, to 0.2, from 0.2 to 0.3, from 0.3 to 0.4, from 0.4 to 0.5, from 0.5 to 0.6, from 0.6 to 0.7, from 0.7 to 0.8, from 0.8 to 0.9, from 0.9 to 1, or any combination of these ranges, such as any subgroup encompassed by any combination of these ranges.

[0057] According to one or more embodiments, the catalyst system may further comprise additional co-catalysts and/or additives. It should be understood that these additional co-catalysts and/or additives are optional and are not included in all embodiments described herein. Examples of additional co-catalysts and/or additives include, without limitation, any of the organoaluminum compounds described herein which form the co-catalyst (e.g. diisobutylaluminum hydride or and TEAL) could also be added to the catalyst system. Such additional co-catalysts may be present if an excess amount of organoaluminum compound is added to form the co-catalyst, such that all antifouling complex is reacted by excess organoaluminum compound remains in the solution.

[0058] In one or more embodiments, methods for forming the catalyst system include mixing a chromium complex, a bidentate chelating ligand, an anion-containing compound, and an aluminum containing agent comprising the reaction product of an organoaluminum compound and an antifouling compound. In one or more embodiments, the chromium complex, bidentate chelating ligand, anion-containing compound, and aluminum containing agent may be mixed in the presence of a solvent, such as chlorobenzene. The chromium complex, bidentate chelating ligand, anion-containing compound, and aluminum containing agent may form a reaction product when mixed, and such reaction product may be a catalyst system suitable for tetramerizing ethylene to 1-octene.

[0059] It should be understood that the chromium complex, bidentate chelating ligand, anion-containing compound, and aluminum containing agent may be mixed simultaneously or in

any order. For example, in one or more embodiments, the chromium complex, bidentate chelating ligand, and anion-containing compound may be mixed to form a catalyst, and subsequently the aluminum containing agent may be mixed with the catalyst to form the catalyst system. In one or more embodiments, the chromium complex, the bidentate chelating ligand and the aluminum containing agent may be mixed initially and that mixture may be subsequently mixed with the anion-containing compound to form the catalyst system.

[0060] In one or more embodiments, ethylene may be contacted with the catalyst system described herein to form a product comprising 1-octene. Contacting may generally include any mixing, combining, etc. of the reactant ethylene with the catalyst system. In one or more embodiments, the catalyst and aluminum containing agent may be separately prepared, and then combined, prior to contacting of the catalyst system with ethylene. In one or more embodiments, the ethylene may be contacted with the catalyst system in the presence of hydrogen.

[0061] The reaction may be performed as a batch reaction or as a continuous process reaction, such as a continuous stir tank reactor process. According to further embodiments, the pressure of the reactor may be from 5 bar to 120 bar (such as from 20 bar to 40 bar), and the reactor temperature may be from 25 °C to 180 °C (such as from 30 °C to 60 °C). However, process conditions outside of these ranges are contemplated, especially in view of the specific design of the reactor system and concentrations of the reactants and catalysts.

[0062] It should be understood that, in one or more embodiments, similar or identical catalyst systems which do not include the antifouling compound may exhibit increased fouling. In one or more embodiments, the introduction of the antifouling agent into a catalyst system may suppress polymer formation while not greatly reducing catalytic activity of 1-octene formation. In one embodiment, polymer formation (fouling) may be reduced by at least 5%, 10%, 20%, 30%, 40%, 50%, 60%, 70%, 80%, 90%, or even 95% by the inclusion of an antifouling compound. In one embodiment, 1-octene production may be increased, stay the same, or may decrease by less than or equal to 50%, 40%, 30%, 20%, 10% or even 5% by the inclusion of an antifouling compound. In some embodiments, antifouling compounds may both reduce the polymer formation (such as by at least 5%, 10%, 20%, 30%, 40%, 50%, 60%, 70%, 80%, 90% or even 95%) and increase, not effect, or decrease 1-octene production rate by less than or equal to 50%, 40%, 30%, 20%, 10% or even 5%. Reduction in polymer formation rates and catalytic activity on a percentage

-19-


basis are based on catalyst systems which are formed from the antifouling compounds described herein as compared with catalyst systems which are void of an antifouling compound.

EXAMPLES

[0063] The various aspects of the present disclosure will be further clarified by the following examples. The examples are illustrative in nature and should not be understood to limit the subject matter of the present disclosure.

Catalyst Production Procedure

[0064] In the following examples, the catalyst has a structure according to formula (XIX):



Formula (XIX)

[0065] The catalyst was produced by the method described in U.S. Patent Application No. 16/346,735, the entire contents of which are incorporated by reference in their entirety.

Co-Catalyst Production Procedure

[0066] In the following examples, each co-catalyst was produced using the same general method. The general method included reacting an antifouling compound (AFC) and diisobutylaluminum hydride (DIBAL) (*i.e.*, an organoaluminum compound) in an oxygen and moisture-free atmosphere to produce a co-catalyst. Specifically, the AFC was added to 105 milligrams (mg) of a solution of DIBAL in methylcyclohexane (MCH) (1.0 molarity) such that the molar ratio of the AFC to aluminum (AFC:Al) was from 0.001 to 1 or from 0.01 to 0.1.

Ethylene Tetramerization Procedure

[0067] In the following examples, an ethylene tetramerization process (also referred to as a run) was conducted using the same general procedure. Each run was conducted in a 250 milliliter (ml) autoclave reactor unit. Before each run, the autoclave reactor unit was vacuum purged with ultrapure nitrogen to remove oxygen and moisture, which may be detrimental to the ethylene tetramerization reaction, and then filled with a desired amount of anhydrous MCH as a solvent. Once the autoclave reactor unit was prepared, 3.7 milligrams (mg) of the catalyst dissolved in 100 ml of anhydrous MCH and the co-catalyst were separately injected into the autoclave reactor unit. The amount of co-catalyst injected into the autoclave reactor unit was determined based on a desired molar ratio of co-catalyst to catalyst. Subsequently, approximately 3 bar of ultrapure molecular hydrogen was charged to the autoclave reactor unit, which was then heated to a temperature of from 30 °C to 60 °C. In order to initiate the run, from 20 bar to 40 bar of ethylene was charged to the autoclave reactor unit. Once a desired run time was reached, the run was terminated by injecting 2.0 ml of methanol into the autoclave reactor unit, which was then depressurized. Any solid polymer produced was collected from the autoclave reactor unit, filtered, dried overnight in an oven at 110 °C, and weighed.

Example 1


[0068] In Example 1, a co-catalyst was produced that included an AFC having a structure according to formula (XX):

Formula (XX)

[0069] An ethylene tetramerization process was then conducted using the catalyst and co-catalyst. The results of Example 1 are reported in Table 1.

Example 2

[0070] In Example 2, a co-catalyst was produced that included an AFC having a structure according to formula (XXI):

**Formula (XXI)**

[0071] An ethylene tetramerization process was then conducted using the catalyst and co-catalyst. The results of Example 2 are reported in Table 1.

Comparative Example 3

[0072] Comparative Example 3 was conducted in a manner similar to Example 1, except that the DIBAL was injected into the autoclave reactor unit without the addition of an AFC (*i.e.*, no co-catalyst was produced). The results of Comparative Example 3 are reported in Table 1.

Table 1

Example	Catalyst (mmol)	DIBAL (mmol)	Molar Ratio (Co-Cat:Cat)	Activity (mol 1-octene/mol catalyst/hour)	1-Hexene Selectivity (mol.%)	1-Octene Selectivity (mol.%)	Polymer (wt.%)
Example 1	0.001	0.150	0.1	2,027,916	31.26	50.29	1.28
Example 2	0.001	0.150	0.1	1,779,942	31.83	53.30	1.15
Comparative Example 3	0.001	0.150	-	2,649,953	19.31	62.36	2.08

Reaction Conditions – Temperature: 50 °C; C₂H₄ Pressure: 20 bar; H₂ Pressure: 3 bar; Run Time: 20 min.

[0073] As shown in Table 1, the catalyst systems of Examples 1 and 2 each resulted in lower production of polymer than the catalyst system of Comparative Example 3. Accordingly, the catalyst systems of Examples 1 and 2 provide a benefit over the catalyst system of Comparative Example 3 by providing a relatively low polymer selectivity. Furthermore, the catalyst systems of Examples 1 and 2 generally provided comparable activity and selectivity for 1-octene to the catalyst system of Comparative Example 3, despite the activity and selectivity for 1-octene being lower than Comparative Example 3.

[0074] In a first aspect of the present disclosure, a catalyst system suitable for tetramerizing ethylene to form 1-octene may include a catalyst having a structure according to Formula (VI) or Formula (VII). In Formulas (VI) and (VII), X is a halogen, a (C₂-C₃₀) carboxylate, acetylacetonate, or a (C₁-C₃₀) hydrocarbyl; L₁ is a neutral coordinating ligand; n is an integer from 0 to 6; Y is a (C₆-C₂₀)fluorine-substituted aryl, a (C₆-C₂₀)fluorine-substituted aryloxy, or a (C₁-C₂₀)fluorine-substituted alkoxy; and L₁L is a bidentate chelating ligand having the structure

-22-

according to Formula (VIII). In Formula (VIII), each R_1 and R_2 is independently chosen from a (C₁-C₅₀) alkyl group or a (C₆-C₅₀) aryl group, and Z is a (C₂-C₅₀) alkylene group, a (C₆-C₅₀) arylene group, —N(R₈)—, —P(R₈)—, —B(R₈)—, or —Si(R₈)₂— that links the two P atoms, where R₈ is a (C₁-C₅₀) alkyl group or a (C₆-C₅₀) aryl group. The catalyst system may further comprise at least one aluminum containing agent comprising a reaction product of an organoaluminum compound and an antifouling compound. The antifouling compound may comprise one or more chlorinated hydrocarbons, chloro-aluminum alkyls, or combinations of these.

[0075] A second aspect of the present disclosure may include the first aspect, where the catalyst has a structure according to Formula (VI).

[0076] A third aspect of the present disclosure may include either the first or second aspect, where the catalyst has a structure according to Formula (VII).

[0077] A fourth aspect of the present disclosure may include any of the first to third aspects, where the antifouling compound comprises chlorinated hydrocarbons.

[0078] A fifth aspect of the present disclosure may include any of the first to fourth aspects, where the antifouling compound comprises chloro-aluminum alkyls.

[0079] A sixth aspect of the present disclosure includes any of the first through fifth aspects, where each L₁ is a (C₂-C₃₀) nitrile, a (C₂-C₃₀) cyclic ether, a (C₂-C₃₀) acyclic ether, or an H₂O ligand.

[0080] A seventh aspect of the present disclosure includes any of the first through sixth aspects, where the organoaluminum compound has a structure according to formula (XVII) in which R₃, R₄, and R₅ are each selected from a hydrogen atom, a (C₁-C₂₀) hydrocarbyl group, and a (C₁-C₂₀) heterohydrocarbyl group.

[0081] An eighth aspect of the present disclosure includes any of the first through seventh aspects, where the organoaluminum compound comprises one or more of trimethylaluminum, triethylaluminum, tripropylaluminum, tri-iso-butylaluminum, diisobutylaluminum hydride, trihexylaluminum, tri-n-octylaluminum, methylaluminum dichloride, ethylaluminum

dichloride, dimethylaluminium chloride, diethylaluminium chloride, aluminium isopropoxide, ethylaluminiumsesquichloride, methylaluminiumsesquichloride, methylaluminoxane (MAO), ethylaluminoxane (EAO), and modified methylaluminoxane (MMAO).

[0082] A ninth aspect of the present disclosure includes any of the first through eighth aspects, where the molar ratio of the antifouling compound to the organoaluminum compound is from 0.001 to 1.

[0083] According to a tenth aspect of the present disclosure, a method for tetramerizing ethylene to form 1-octene may comprise contacting ethylene with a catalyst system of any of the first through ninth aspects to form a product comprising 1-octene.

[0084] An eleventh aspect of the present disclosure may include the tenth aspect, where ethylene is formed in conditions of a reactor pressure from 5 bar to 120 bar; and a reactor temperature from 25 °C to 180 °C.

[0085] According to a twelfth aspect of the present disclosure, a method of making a catalyst system suitable for tetramerizing ethylene to form 1-octene may include mixing a chromium compound, an anion-containing compound, a bidentate chelating ligand, and an aluminum containing agent to form the catalyst system. The aluminum containing agent is a reaction product of an organoaluminum compound and an antifouling compound, and wherein the antifouling compound comprises one or more chlorinated hydrocarbons, chloro-aluminum alkyls, or combinations of these.

[0086] A thirteenth aspect of the present disclosure may include the twelfth aspect, where the chromium compound has a structure according to Formula (I). In Formula (I), X is a halogen, a (C₂-C₃₀) carboxylate, acetylacetonate, or a (C₁-C₃₀) hydrocarbyl; L₁ is a ligand; and n is an integer from 0 to 6.

[0087] A fourteenth aspect of the present disclosure may include either the twelfth or thirteenth aspect, where the anion containing compound has a structure according to Formula (II). In Formula (II), Y is a (C₆-C₂₀)fluorine-substituted aryl, a (C₆-C₂₀)fluorine-substituted aryloxy, or a (C₁-C₂₀)fluorine-substituted alkoxy; and M⁺ is a metal inorganic cation, or an organic cation.

[0088] A fifteenth aspect of the present disclosure may include either the twelfth or thirteenth aspect, where the anion containing compound has a structure according to Formula (III). In Formula (III), Y is a (C₆-C₂₀)fluorine-substituted aryl, a (C₆-C₂₀)fluorine-substituted aryloxy, or a (C₁-C₂₀)fluorine-substituted alkoxy; and M⁺ is a metal inorganic cation, or an organic cation.

[0089] A sixteenth aspect of the present disclosure may include any of the twelfth to fifteenth aspects, where the bidentate chelating ligand has the structure according to Formula (VIII). In Formula (VIII), each R₁ and R₂ is independently chosen from a (C₁-C₅₀) alkyl group or a (C₆-C₅₀) aryl group, and Z is a (C₂-C₅₀) alkylene group, a (C₆-C₅₀) arylene group, —N(R₈)—, —P(R₈)—, —B(R₈)—, or —Si(R₈)₂— that links the two P atoms, where R₈ is a (C₁-C₅₀) alkyl group or a (C₆-C₅₀) aryl group.

[0090] The subject matter of the present disclosure has been described in detail and by reference to specific embodiments. It should be understood that any detailed description of a component or feature of an embodiment does not necessarily imply that the component or feature is essential to the particular embodiment or to any other embodiment. Further, it should be apparent to those skilled in the art that various modifications and variations can be made to the described embodiments without departing from the spirit and scope of the claimed subject matter.

[0091] For the purposes of describing and defining the present disclosure it is noted that the terms “about” or “approximately” are utilized in this disclosure to represent the inherent degree of uncertainty that may be attributed to any quantitative comparison, value, measurement, or other representation. The terms “about” and/or “approximately” are also utilized in this disclosure to represent the degree by which a quantitative representation may vary from a stated reference without resulting in a change in the basic function of the subject matter at issue.

[0092] It is noted that one or more of the following claims utilize the term “wherein” as a transitional phrase. For the purposes of defining the present technology, it is noted that this term is introduced in the claims as an open-ended transitional phrase that is used to introduce a recitation of a series of characteristics of the structure and should be interpreted in like manner as the more commonly used open-ended preamble term “comprising.”

[0093] It should be understood that where a first component is described as “comprising” a second component, it is contemplated that, in some embodiments, the first component “consists” or “consists essentially of” that second component. It should further be understood that where a first component is described as “comprising” a second component, it is contemplated that, in some embodiments, the first component comprises at least 10%, at least 20%, at least 30%, at least 40%, at least 50%, at least 60%, at least 70%, at least 80%, at least 90%, at least 95%, or even at least 99% that second component (where % can be weight % or molar %).

[0094] Additionally, the term “consisting essentially of” is used in this disclosure to refer to quantitative values that do not materially affect the basic and novel characteristic(s) of the disclosure. For example, a chemical composition “consisting essentially” of a particular chemical constituent or group of chemical constituents should be understood to mean that the composition includes at least about 99.5% of a that particular chemical constituent or group of chemical constituents.


[0095] It should be understood that any two quantitative values assigned to a property may constitute a range of that property, and all combinations of ranges formed from all stated quantitative values of a given property are contemplated in this disclosure. It should be appreciated that compositional ranges of a chemical constituent in a composition should be appreciated as containing, in some embodiments, a mixture of isomers of that constituent. In additional embodiments, the chemical compounds may be present in alternative forms such as derivatives, salts, hydroxides, etc.

-26-

CLAIMS

1. A catalyst system suitable for tetramerizing ethylene to form 1-octene, the catalyst system comprising:

a catalyst having the structure:



wherein:


X is a halogen, a (C₂-C₃₀) carboxylate, acetylacetonate, or a (C₁-C₃₀) hydrocarbyl;

L₁ is a neutral coordinating ligand;

n is an integer from 0 to 6;

Y is a (C₆-C₂₀)fluorine-substituted aryl, a (C₆-C₂₀)fluorine-substituted aryloxy, or a (C₁-C₂₀)fluorine-substituted alkoxy; and

L∩L is a bidentate chelating ligand having the structure:



wherein:

each R₁ and R₂ is independently chosen from a (C₁-C₅₀) alkyl group or a (C₆-C₅₀) aryl group; and


Z is a (C₂-C₅₀) alkylene group, a (C₆-C₅₀) arylene group, —N(R₈)—, —P(R₈)—, —B(R₈)—, or —Si(R₈)₂— that links the two P atoms, where

R₈ is a (C₁-C₅₀) alkyl group or a (C₆-C₅₀) aryl group; and


At least one aluminum containing agent comprising a reaction product of an organoaluminum compound and an antifouling compound, wherein the antifouling compound comprises one or more chlorinated hydrocarbons, chloro-aluminum alkyls, or combinations of these.

-27-

2. The catalyst system of claim 1, wherein the catalyst has the structure:



3. The catalyst system of claim 1, wherein the catalyst has the structure:




4. The catalyst system of claim 1, wherein the antifouling compound comprises chlorinated hydrocarbons.

5. The catalyst system of claim 1, wherein the antifouling compound comprises chloro-aluminum alkyls.


6. The catalyst system of any of the preceding claims, wherein each L_1 is a (C₂-C₃₀) nitrile, a (C₂-C₃₀) cyclic ether, a (C₂-C₃₀) acyclic ether, or an H₂O ligand.

7. The catalyst system of any of the preceding claims, wherein the organoaluminum compound has the structure:



wherein R_3 , R_4 , and R_5 are each selected from a hydrogen atom, a (C₁-C₂₀) hydrocarbyl group, or a (C₁-C₂₀) heterohydrocarbyl group.

8. The catalyst system of any of the preceding claims, wherein the molar ratio of the antifouling compound to the organoaluminum compound is from 0.001 to 1.
9. A method for tetramerizing ethylene to form 1-octene, the method comprising contacting ethylene with the catalyst system of any of the preceding claims to form a product comprising 1-octene.
10. The method of claim 9, wherein the ethylene is formed in conditions of:
a reactor pressure from 5 bar to 120 bar; and
a reactor temperature from 25 °C to 180 °C.
11. A method of making a catalyst system suitable for tetramerizing ethylene to form 1-octene, the method comprising mixing a chromium compound, an anion-containing compound, a bidentate chelating ligand, and an aluminum containing agent to form the catalyst system, wherein the aluminum containing agent is a reaction product of an organoaluminum compound and an antifouling compound, and wherein the antifouling compound comprises one or more chlorinated hydrocarbons, chloro-aluminum alkyls, or combinations of these.
12. The method of claim 11, wherein the chromium compound has the structure:



wherein:

X is a halogen, a (C₂-C₃₀) carboxylate, acetylacetonate, or a (C₁-C₃₀) hydrocarbyl;

L₁ is a ligand; and

-29-

n is an integer from 0 to 6.

13. The method of either claim 11 or claim 12, wherein the anion containing compound has a structure:



wherein:

Y is a (C₆-C₂₀)fluorine-substituted aryl, a (C₆-C₂₀)fluorine-substituted aryloxy, or a (C₁-C₂₀)fluorine-substituted alkoxy; and

M⁺ is a metal inorganic cation or an organic cation.

14. The method of any of either claim 11 or claim 12, wherein the anion containing compound has a structure:




wherein:

Y is a (C₆-C₂₀)fluorine-substituted aryl, a (C₆-C₂₀)fluorine-substituted aryloxy, or a (C₁-C₂₀)fluorine-substituted alkoxy; and

M⁺ is a metal inorganic cation or an organic.

15. The method of any of claims 11 to 14, wherein the bidentate chelating ligand has the structure:



wherein:

each R₁ and R₂ is independently chosen from a (C₁-C₅₀) alkyl group or a (C₆-C₅₀) aryl group; and

-30-

Z is a (C₂-C₅₀) alkylene group, a (C₆-C₅₀) arylene group, —N(R₈)—, —P(R₈)—, —B(R₈)—, or —Si(R₈)₂— that links the two P atoms, where R₈ is a (C₁-C₅₀) alkyl group or a (C₆-C₅₀) aryl group.

International application No
PCT/US2021/061117

A. CLASSIFICATION OF SUBJECT MATTER INV. B01J31/24 B01J31/22 B01J31/14 B01J31/02 C07C2/08 C07C2/32 ADD. According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) B01J C07C Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched Electronic data base consulted during the international search (name of data base and, where practicable, search terms used) EPO-Internal, WPI Data		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 3 536 696 A1 (UNIV AJOU IND ACADEMIC COOP FOUND [KR])	1, 2, 4, 6,
	11 September 2019 (2019-09-11)	7, 9-15
Y	claims 4-10; examples 3-5, 6-9; tables 1,2	1-10
	paragraphs [0012] - [0021], [0037] - [0049]	
	paragraphs [0050] - [0052]	

	-/--	
☒ Further documents are listed in the continuation of Box C. ☒ See patent family annex. * Special categories of cited documents : "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier application or patent but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art "&" document member of the same patent family Date of the actual completion of the international search 28 February 2022 Date of mailing of the international search report 11/03/2022 Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Fax: (+31-70) 340-3016 Authorized officer Bork, Ana-Maria		

INTERNATIONAL SEARCH REPORT

International application No

PCT/US2021/061117

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	KIM EUN HO ET AL: "Methylaluminoxane-Free Chromium Catalytic System for Ethylene Tetramerization", ACS OMEGA, vol. 2, no. 3, 31 March 2017 (2017-03-31), pages 765-773, XP055895652, US ISSN: 2470-1343, DOI: 10.1021/acsomega.6b00506	1, 2, 4, 6, 7, 9-15
Y	abstract table 1 Scheme 2; page 769, left-hand column, paragraph 1 Typical procedure for ethylene oligomerization; page 772, left-hand column -----	1-10
A	WO 2019/235799 A1 (UNIV AJOU IND ACADEMIC COOP FOUND [KR]) 12 December 2019 (2019-12-12) abstract & EP 3 805 240 A1 (UNIV AJOU IND ACADEMIC COOP FOUND [KR]; S PRECIOUS CATALYSTS INC [KR]) 14 April 2021 (2021-04-14) paragraphs [0001], [0012], [0049], [0068], [0091], [0097], [0098], [0102], [0103] comparative examples 2, 3 (complexes of formula 1-8 and 1-9); comparative examples 5, 6; claims 3-10; examples 1-7, 8; table 1 -----	1-15
Y	ZHANG Baojun et al: "Cr(III)-based catalyst system for oligomerization of ethylene to 1-octene with high selectivity", Chinese Journal of Catalysis, vol. 28, no. 4 1 January 2007 (2007-01-01), pages 317-320, XP002805714, Retrieved from the Internet: URL:https://www.cjcatal.com/EN/abstract/abstract17261.shtml [retrieved on 2022-02-16] abstract; figures 1-3; tables 1, 2 ----- -/--	1-4, 6-10

INTERNATIONAL SEARCH REPORT

International application No

PCT/US2021/061117

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	CHEN ET AL: "Effects of halide in homogeneous Cr(III)/PNP/MAO catalytic systems for ethylene tetramerization toward 1-octene", JOURNAL OF MOLECULAR CATALYSIS A: CHEMICAL, ELSEVIER, AMSTERDAM, NL, vol. 270, no. 1-2, 7 May 2007 (2007-05-07), pages 273-277, XP022044452, ISSN: 1381-1169, DOI: 10.1016/J.MOLCATA.2007.02.013 abstract pages 1-4 paragraphs [02.3], [0003], [0004] -----	1-4, 6-10
Y	TAO WANG ET AL: "Mixed aluminoxanes: efficient cocatalysts for bisphosphineamine/Cr(III) catalyzed ethylene tetramerization toward 1-octene", APPLIED PETROCHEMICAL RESEARCH, vol. 5, no. 2, 1 March 2015 (2015-03-01), pages 143-149, XP055374143, ISSN: 2190-5525, DOI: 10.1007/s13203-015-0103-4 abstract tables 5, 6 -----	1-3, 5-10

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US2021/061117

Box No. II Observations where certain claims were found unsearchable (Continuation of item 2 of first sheet)

This international search report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:

2. ☒ Claims Nos.: **11-15 (partially)**
because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out, specifically:
see FURTHER INFORMATION sheet PCT/ISA/210

3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box No. III Observations where unity of invention is lacking (Continuation of item 3 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

1. ☐ As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims.

2. ☐ As all searchable claims could be searched without effort justifying an additional fees, this Authority did not invite payment of additional fees.

3. ☐ As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims for which fees were paid, specifically claims Nos.:

4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest and, where applicable, the payment of a protest fee.
- ☐ The additional search fees were accompanied by the applicant's protest but the applicable protest fee was not paid within the time limit specified in the invitation.
- ☐ No protest accompanied the payment of additional search fees.

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

Continuation of Box II.2

Claims Nos.: 11-15 (partially)

Independent claim 11, directed to a method of making a catalyst system, does not refer back to the catalyst system of claim 1. Therefore, it concerns a method with the only step being mixing extremely broad defined compounds: 'Cr compound', 'anion-containing compound', bidentate chelating ligand', 'Al-containing agent which is the reaction product of an organoaluminum compound and a compound comprising one or more chlorinated hydrocarbons, chloro-aluminum alkyls, or combinations thereof'.

The non-compliance with the substantive provisions is to such an extent, that the search was performed taking into consideration the non-compliance in determining the extent of the search of claims 11-15 (PCT Guidelines 9.19 and 9.23).

The search of claims 11-15 has been restricted to the preparation of a catalyst system as defined in present claim 1.

The applicant's attention is drawn to the fact that claims relating to inventions in respect of which no international search report has been established need not be the subject of an international preliminary examination (Rule 66.1(e) PCT). The applicant is advised that the EPO policy when acting as an International Preliminary Examining Authority is normally not to carry out a preliminary examination on matter which has not been searched. This is the case irrespective of whether or not the claims are amended following receipt of the search report or during any Chapter II procedure. If the application proceeds into the regional phase before the EPO, the applicant is reminded that a search may be carried out during examination before the EPO (see EPO Guidelines C-IV, 7.2), should the problems which led to the Article 17(2) PCT declaration be overcome.

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/US2021/061117

Patent document cited in search report		Publication date		Patent family member(s)		Publication date
EP 3536696	A1	11-09-2019	CN	109906229 A		18-06-2019
			EP	3536696 A1		11-09-2019
			JP	6806973 B2		06-01-2021
			JP	2019535686 A		12-12-2019
			US	2019308179 A1		10-10-2019
			WO	2018084365 A1		11-05-2018

WO 2019235799	A1	12-12-2019	CN	112262147 A		22-01-2021
			EP	3805240 A1		14-04-2021
			JP	2021526540 A		07-10-2021
			US	2021229084 A1		29-07-2021
			WO	2019235799 A1		12-12-2019
