

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau**EP. 0047740**

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>3</sup>:</b> <b>C08L 27/16; H01L 41/18</b>	<b>A1</b>	<b>(11) International Publication Number:</b> WO 81/01567 <b>(43) International Publication Date:</b> 11 June 1981 (11.06.81)
<b>(21) International Application Number:</b> PCT/GB80/00207 <b>(22) International Filing Date:</b> 1 December 1980 (01.12.80)  <b>(31) Priority Application Number:</b> 7941419 <b>(32) Priority Date:</b> 30 November 1979 (30.11.79) <b>(33) Priority Country:</b> GB  <b>(71) Applicant (for all designated States except US):</b> NATIONAL RESEARCH DEVELOPMENT CORPORATION [GB/GB]; P.O. Box 236, Kingsgate House, 66-74 Victoria Street, London SW1 E6SL (GB).  <b>(72) Inventors; and</b> <b>(75) Inventors/Applicants (for US only):</b> WARD, Ian, MacMillan [GB/GB]; 2 Creskeld Drive, Bramhope, Leeds (GB). McGRATH, John, Charles [GB/GB]; 18 Malvern Road, Surbiton, Surrey (GB).		<b>(74) Agent:</b> COLMER, Stephen, Gary; Patent Department, P.O. Box 236, Kingsgate House, 66-74 Victoria Street, London SW1 E6SL (GB).  <b>(81) Designated States:</b> DE (European patent), FR (European patent), GB (European patent), JP, US.  <b>Published</b> <i>With international search report</i>
<b>(54) Title:</b> VINYLIDENE FLUORIDE POLYMERS  <b>(57) Abstract</b>  An elongated material comprising a vinylidene fluoride polymer and having a Young's modulus from 3 to 15 GPa and 15 nC cm <sup>-2</sup> K <sup>-1</sup> , or a hydrostatic piezoelectric constant greater than 10 pCm <sup>-1</sup> .		

***FOR THE PURPOSES OF INFORMATION ONLY***

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

<b>AT</b>	Austria	<b>KP</b>	Democratic People's Republic of Korea
<b>AU</b>	Australia	<b>LI</b>	Liechtenstein
<b>BR</b>	Brazil	<b>LU</b>	Luxembourg
<b>CF</b>	Central African Republic	<b>MC</b>	Monaco
<b>CG</b>	Congo	<b>MG</b>	Madagascar
<b>CH</b>	Switzerland	<b>MW</b>	Malawi
<b>CM</b>	Cameroon	<b>NL</b>	Netherlands
<b>DE</b>	Germany, Federal Republic of	<b>NO</b>	Norway
<b>DK</b>	Denmark	<b>RO</b>	Romania
<b>FI</b>	Finland	<b>SE</b>	Sweden
<b>FR</b>	France	<b>SN</b>	Senegal
<b>GA</b>	Gabon	<b>SU</b>	Soviet Union
<b>GB</b>	United Kingdom	<b>TD</b>	Chad
<b>HU</b>	Hungary	<b>TG</b>	Togo
<b>JP</b>	Japan	<b>US</b>	United States of America

- 1 -

VINYLLIDENE FLUORIDE POLYMERS

This invention relates to vinylidene fluoride polymers and in particular to such polymers having improved pyroelectric and piezoelectric properties.

It is known that vinylidene fluoride polymers can be  
05 polarised by subjecting them to an intense electric field to yield material having permanent pyroelectric and/or piezoelectric properties which can be utilised in certain electronic applications. Such a procedure is often referred to as "poling".

It is known that vinylidene fluoride polymers can exist in  
10 at least two distinct crystalline forms, known as Form I ( $\beta$ ) and Form II ( $\alpha$ ). These phases are readily distinguished by analysis of their X-ray diffraction patterns, and such measurements also provide an indication of the proportion of Form I material within a sample. Studies of this kind have shown that for a given  
15 applied polarizing field both the piezo- and pyroelectric properties are enhanced the greater the proportion of Form I material present. It has been previously accepted that the relative proportions of Form I and Form II materials are affected by temperature and that in order to achieve a high proportion of  
20 Form I material, relatively low temperatures (e.g. below 80°C) should be maintained.

Hitherto it has only been possible to prepare materials having a pyroelectric constant typically no greater than about  
3 nC cm<sup>-2</sup> K<sup>-1</sup> and a hydrostatic piezoelectric constant,  $d_h$ ,  
25 typically no greater than about 9 pC N<sup>-1</sup>.

It is therefore an object of the present invention to provide vinylidene fluoride polymers having improved pyroelectric and piezoelectric properties.

According to one aspect of the invention, we provide an  
30 elongated material of a vinylidene fluoride polymer, particularly a polyvinylidene fluoride, the material having a Young's modulus from 3 to 15, typically from 4 to 10, suitably from 5 to 8 GPa.



- 2 -

The Young's modulus of the elongated material is determined at 21°C by a dead-loading creep experiment, as described by Gupta & Ward in J. Macromol. Sci. Phys. B1, 373 (1967), taking the 10 second response at a strain of 0.1%.

- 05 According to a further aspect of the invention, there is provided an elongated material as hereinabove defined which, on poling, as hereinabove defined, has a pyroelectric constant of at least 4, for example, from 4 to 15, typically from 4 to 10, suitably from 5 to 8 nC cm<sup>-2</sup>K<sup>-1</sup>.
- 10 According to another aspect of the invention, there is provided an elongated material as hereinabove defined which on poling, as hereinabove defined, has a hydrostatic piezoelectric constant greater than 10 pCN<sup>-1</sup>, suitably greater than 12 pCN<sup>-1</sup>, preferably greater than 16 pCN<sup>-1</sup>.
- 15 Poling may be carried out at an elevated temperature up to 130°C, for example at 100°C, but may also be carried out at lower temperatures, for example room temperature. Typically, the electric field applied will range from 100 to 500 Volt/micron, more intense fields being required at lower temperatures. The
- 20 field is applied across the thickness of the polymer sample by corona discharge needle electrodes, by smooth flat conductive plates or by electrodes deposited on the sample itself.

- The elongated material may exhibit an X-ray diffraction pattern which, after poling, indicates the presence of at least
- 25 70%, and preferably at least 80%, by volume of the total crystalline material of Form I material. The percentage of Form I material in the elongated material is determined as a proportion of the total crystalline material present by comparing the intensities of the Form I (310) and (020)
- 30 reflections and the Form II (021) and (111) reflections. Appropriate corrections are made for the structure factors and angle factors: see Hasegawa et al: Polymer J. 3, p,600 (1972).



- 3 -

The crystallinity of the elongated material will depend on several factors including molecular weight and previous thermal history. However, it is generally found to be from 30% to 50%, usually from 35% to 45% by volume of the total elongated material.

The pyroelectric constant of the poled elongated material is determined by subjecting the unclamped sample to a linear temperature "ramp" of  $0.2^{\circ}$  per second over the interval  $10-30^{\circ}\text{C}$ . The "short-circuit" reversible polarisation current per unit area of electrode per unit rate of temperature rise is the pyroelectric coefficient.

The hydrostatic piezoelectric constant of the poled elongated material is determined by immersing the electroded sample in oil of high resistivity and subjecting it to a pressure "step" of 2 atmospheres supplied by compressed air above the oil surface. The piezoelectric charge generated per unit electrode area per unit pressure is the piezoelectric constant. This charge is stored on the feedback capacitor of the measurement electronics to give zero field in the piezoelectric sample. In this disclosure, no correction for the adiabatic heating of the immersion fluid has been made.

This invention also provides a process for the preparation of an elongated material of a vinylidene fluoride polymer, particularly a polyvinylidene fluoride, which process comprises drawing a material of a vinylidene fluoride polymer, at an elevated temperature such as from  $110^{\circ}\text{C}$  to  $170^{\circ}\text{C}$ , suitably from  $120^{\circ}\text{C}$  to  $160^{\circ}\text{C}$ , preferably from  $130^{\circ}\text{C}$  to  $150^{\circ}\text{C}$ , to a draw ratio of at least 4:1, suitably from 4:1 to 20:1, typically 5:1 to 15:1, suitably 6:1 to 10:1. The drawing may be carried out in more than one stage and is advantageously effected at the maximum rate possible without incidence of tensile failure.

The draw ratio is defined as the ratio of cross-sectional area of a body of the polymer before and after the drawing.



- 4 -

Particularly successful materials, yielding advantageous pyro and piezo electric properties, have been prepared by the process of this invention using tape extruded from polyvinylidene fluoride having a number average molecular weight ( $\bar{M}_n$ ) from 1.0 to  $1.9 \times 10^5$ , preferably from  $1.3$  to  $1.8 \times 10^5$ , and a weight average molecular weight ( $\bar{M}_w$ ) from  $2 \times 10^5$  to  $8 \times 10^5$ . Examples include "Kynar" calendered film grade 200 (ex Pennwalt Chem. Ind.:  $\bar{M}_n 1.71 \times 10^5$   $\bar{M}_w 7.64 \times 10^5$ ); "Solef" XION extruded sheet ( $\bar{M}_n 1.71 \times 10^5$   $\bar{M}_w 3.51 \times 10^5$ ) and "Solef" X8N pellets ( $\bar{M}_n 1.3 \times 10^5$   $\bar{M}_w 2.76 \times 10^5$ ), both ex Solvay et cie. The SOLEF XION commercial grade was found to be particularly useful, its chain structure was determined in accordance with the method of Wilson and Santee (J. Polymer Sci. C8, p. 97, 1965). The 56.4 Mc/s  $F^{19}$  spectrum obtained from a 10% solution in N, N - dimethylacetamide showed peaks listed by Wilson and Santee with intensities A 90.4%, B 3.3%, C 2.9%, D 3.4%.

It may be advantageous to subject the vinylidene fluoride polymer material prior to drawing to a thermal treatment. For example, a sheet of compression moulded, extruded or extruded and subsequently compression moulded material may be allowed to cool slowly, for example at  $1^\circ$  to  $5^\circ \text{C min}^{-1}$ , from above the crystalline melting point ( $160^\circ \text{C}$  for the "Kynar" grade;  $178^\circ \text{C}$  for the "Solef" grades) to ambient temperature; to cool, the rate not being critical, to a temperature (for example from  $160^\circ \text{C}$  to  $130^\circ \text{C}$ ) below the crystalline melting point where it is maintained until crystallisation is established and then quenched to ambient temperature; or may immediately be quenched to ambient temperature. The material may also be treated (heat set) after drawing by maintaining the drawn tape at a constant length and temperature (typically at the draw temperature or above).

The materials produced in this invention may typically have a thickness in the range  $20 \mu\text{m}$ , typically  $25 \mu\text{m}$  to  $1500 \mu\text{m}$ , although the invention is not limited to materials in this range.



- 5 -

The materials may be produced in the form of a sheet or foil typically 1 to 2 cms in width, although samples of up to 12 cms in width have been prepared.

05 Since the materials produced have particularly beneficial  
pyroelectric and piezoelectric properties they can be used in a  
wide range of applications. In particular films of the improved  
polymer can be used within the probes of ultrasonic scanners  
and especially ultrasonic medical scanners. They may also be  
used as sensing elements in infra red imaging or sensing devices  
10 or alternatively in ultrasonic imaging devices in which the  
polymer serves as the piezoelectric element in a Sokolov tube.  
Other applications include security devices (e.g. heat or pressure  
sensitive intruder or anti-theft devices, fire alarms, signature  
recognition devices); a range of strain gauges (e.g. diaphragm  
15 guages, barrel guages, shear transducers); deformation monitors  
for use with large structures such as bridges; pressure sensitive  
devices (e.g. traffic flow counters and monitors, touch and  
pressure wave switches, instrument key board devices, automatic  
machine control devices); seismic wave detectors; weighing  
20 devices, and a variety of hydrophones.

The following Examples illustrate the invention.

EXAMPLE 1

An isotropic sheet of thickness 0.6 mm was prepared by  
compression moulding 5 mm sheet of Solvay SOLEF XION  
25 polyvinylidene fluoride at 240°C for 80 min and then quenching  
the sheet in water at room temperature. From this sheet a  
dumb-bell sample was cut of 3 cm width and 3.5 cm gauge length.  
This was drawn uniaxially at 140°C in an Instron tensile testing  
machine in two stages: (1) at a cross-head speed of 0.2 cm/min  
30 to the limit of travel in the Instron oven, which gave a first  
stage draw ratio of 5.9; (2) the centre region of the draw  
material was cut out and redrawn at a drawing rate of 0.05 cm/min



- 6 -

to a total draw ratio of 6.46. X-ray characterisation of the sample, according to the method described, showed the Form I content was not less than 80%. The Young's modulus of the sample was 3.8 GPa.

05 The sample was poled using  $100\text{V}/\mu$  at  $100^{\circ}\text{C}$  for 30 min with the field applied. Electrodes were applied by spraying a suspension of colloidal silver on to the surfaces of the film.

The pyroelectric constant of the drawn film was determined to be  $4.5\text{nC}/\text{cm}^2/^{\circ}\text{K}$  and the hydrostatic piezoelectric constant was determined to be  $15\text{pC}/\text{N}$ .

10 EXAMPLE 2

Example 1 was repeated, save that the second stage drawing was effected to a total draw ratio of 6.24 giving a Form I content of not less than 80%. The Young's modulus, pyroelectric constant and hydrostatic piezoelectric constant were, respectively,  
15  $4.6\text{ GPa}$ ,  $4.0\text{ nC}/\text{cm}^2/^{\circ}\text{K}$  and  $13.75\text{ pC}/\text{N}$ .

EXAMPLE 3

From a sheet of material similar to that used in Example 1, but of thickness  $0.3\text{mm}$ , was cut a dumb-bell sample of  $8\text{cm}$  width and  $16\text{cm}$  gauge length. This sample was uniaxially drawn at  
20  $160^{\circ}$  at a drawing rate of  $3\text{cm}/\text{min}$ . to a first stage draw ratio of 4:1 and then a portion of this material was re-drawn at  $160^{\circ}\text{C}$  at a drawing rate of  $0.3\text{cm}/\text{min}$ . to a total draw ratio of 14:1. The Young's modulus was  $4.9\text{ GPa}$ .

The sample was poled at room temperature using a field of  
25  $456\text{V}/\text{micron}$  and had a pyroelectric constant of  $3.85\text{nC}/\text{cm}^2/^{\circ}\text{K}$  and a hydrostatic piezoelectric constant of  $12\text{ pC}/\text{N}$ . The poled sample had a Form I content of about 50%.





- 7 -

EXAMPLE 4

An isotropic sheet of Kynar polyvinylidene fluoride was prepared by compression moulding six 0.2 mm layers of the as-received film between copper plates at 230°C for 1 hour; each sheet was laid with the machine direction at right angles to the one below it. The moulded sheet was allowed to cool slowly to 140°C and then quenched in water at room temperature. From this sheet a dumb-bell sample of gauge length 2.22 cm, 0.47 cm wide and approximately 0.06 cm thick was cut using a standard die. The sample was drawn uniaxially at a temperature of 140°C in a three stage process in which the draw rate was 10 cm min<sup>-1</sup>, 0.2 cm min<sup>-1</sup> and 0.05 cm min<sup>-1</sup>, respectively.

A total draw ratio of 7.3 was obtained. The Young's modulus of the sample was 4.31 GPa.

15 EXAMPLE 5

An isotropic sheet of Kynar polyvinylidene fluoride was prepared essentially as in Example 4, save that the moulded sheet was immediately quenched in water at room temperature. A dumb-bell sample, prepared as in Example 4, was drawn uniaxially at 120°C in a two stage process in which the draw rate was 0.2 cm min<sup>-1</sup> and 0.05 cm min<sup>-1</sup>, respectively.

A total draw ratio of 6.6 was obtained. The Young's modulus of the sample was 4.14 GPa.

EXAMPLE 6

25 An isotropic sheet of Solef XION was prepared essentially as in Example 1, save that the moulded sheet was cooled slowly at room temperature. A dumb-bell sample, prepared as in Example 4, was drawn uniaxially at 140°C in a single stage process in which the draw rate was 0.2 cm min<sup>-1</sup>.

30 A draw ratio of 6.7 was obtained. The Young's modulus of the sample was 4.19 GPa.

EXAMPLE 7

An isotropic sheet of Solef X8N was prepared by compression



- 8 -

moulding pellets at 210°C for about one hour and immediately quenching the moulded sheet in water at room temperature. A dumb-bell sample, prepared as in Example 4, was drawn uniaxially at 140°C in a two stage process in which the draw rate was 10 cm min<sup>-1</sup> for 1.4 min and 0.02 cm min<sup>-1</sup> for 5 min.

A total draw ratio of 6.5 was obtained. The Young's modulus of the sample was 3.77 GPa.



- 9 -

CLAIMS

1. An elongated material comprising a vinylidene fluoride polymer and having a Young's modulus from 3 to 15 GPa.
2. An elongated material according to Claim 1 which comprises polyvinylidene fluoride.
- 05 3. An elongated material according to Claim 1 or 2 which has a Young's modulus from 3 to 10 GPa.
4. An elongated material according to any preceding claim which exhibits an X-ray diffraction pattern which indicates the presence of at least 70% by volume of the total crystalline
- 10 material of Form I material.
5. An elongated material according to any preceding claim which, on poling, has a pyroelectric constant from 4 to 15 nC cm<sup>-2</sup> K<sup>-1</sup>.
6. An elongated material according to Claim 5 which has a pyroelectric constant from 4 to 10 nC cm<sup>-2</sup> K<sup>-1</sup>.
- 15 7. An elongated material according to any preceding claim which, on poling, has hydrostatic piezoelectric constant greater than 10 pC N<sup>-1</sup>.
8. An elongated material according to Claim 7 which has a hydrostatic piezoelectric constant greater than 16 pC N<sup>-1</sup>.
- 20 9. A process for the preparation of an elongated material comprising a vinylidene fluoride polymer, which process comprises drawing the material at a temperature from 110°C to 170°C to a draw ratio of at least 4:1.
10. A process according to Claim 9 wherein the drawing
- 25 temperature is from 130°C to 150°C.
11. A process according to Claim 9 or 10 wherein the draw ratio is from 4:1 to 20:1.
12. A process according to Claim 11 wherein the draw ratio is from 4:1 to 8:1.
- 30 13. Elongated material whenever prepared by the process of any of Claims 9 to 12.



# INTERNATIONAL SEARCH REPORT

International Application No PCT/GB 80/00207

<b>I. CLASSIFICATION OF SUBJECT MATTER</b> (If several classification symbols apply, indicate all) <sup>3</sup> According to International Patent Classification (IPC) or to both National Classification and IPC <div style="text-align: center; font-family: monospace; font-size: 1.2em;">Int. Cl.<sup>3</sup>: C 08 L 27/16; H 01 L 41/18</div>																	
<b>II. FIELDS SEARCHED</b> <div style="text-align: center; font-size: 0.8em;">Minimum Documentation Searched <sup>4</sup></div> <table border="1" style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 25%; padding: 5px;">Classification System</td> <td style="padding: 5px;">Classification Symbols</td> </tr> <tr> <td style="padding: 5px;">Int.Cl.<sup>3</sup></td> <td style="padding: 5px;">C 08 L 27/16; H 01 L 41/18; H 01 L 37/02</td> </tr> </table> <div style="text-align: center; font-size: 0.8em; margin-top: 5px;">Documentation Searched other than Minimum Documentation to the Extent that such Documents are Included in the Fields Searched <sup>5</sup></div>			Classification System	Classification Symbols	Int.Cl. <sup>3</sup>	C 08 L 27/16; H 01 L 41/18; H 01 L 37/02											
Classification System	Classification Symbols																
Int.Cl. <sup>3</sup>	C 08 L 27/16; H 01 L 41/18; H 01 L 37/02																
<b>III. DOCUMENTS CONSIDERED TO BE RELEVANT</b> <sup>14</sup> <table border="1" style="width: 100%; border-collapse: collapse;"> <tr> <th style="width: 10%; padding: 5px;">Category <sup>6</sup></th> <th style="width: 60%; padding: 5px;">Citation of Document, <sup>16</sup> with indication, where appropriate, of the relevant passages <sup>17</sup></th> <th style="width: 30%; padding: 5px;">Relevant to Claim No. <sup>13</sup></th> </tr> <tr> <td style="text-align: center; vertical-align: top; padding: 5px;">A</td> <td style="padding: 5px;">Chemical Abstracts, volume 87, no. 10, September 5, 1977, (Columbus, Ohio, US) see page 641, abstract 77463g, JP, A, 7754999, May 4, 1977 Matsushita Electric Industrial Co., Ltd. -----</td> <td style="text-align: center; vertical-align: top; padding: 5px;">7,9,10</td> </tr> <tr> <td style="text-align: center; vertical-align: top; padding: 5px;">A</td> <td style="padding: 5px;">US, A, 3878274, published April 15, 1975, see claims 1-4, column 2, lines 52-58, column 4, lines 4-9, column 5, 2nd table, column 6, both tables, Kureha -----</td> <td style="text-align: center; vertical-align: top; padding: 5px;">5,7,9,10</td> </tr> <tr> <td style="text-align: center; vertical-align: top; padding: 5px;">A</td> <td style="padding: 5px;">US, A, 3798473, published March 19, 1974 see claims 1,2,9,10,11, Kureha -----</td> <td style="text-align: center; vertical-align: top; padding: 5px;">1-3</td> </tr> <tr> <td style="text-align: center; vertical-align: top; padding: 5px;">A</td> <td style="padding: 5px;">GB, A, 1173688, published December 10, 1969 see claims 1,2,6, Kureha -----</td> <td style="text-align: center; vertical-align: top; padding: 5px;">9,10</td> </tr> </table>			Category <sup>6</sup>	Citation of Document, <sup>16</sup> with indication, where appropriate, of the relevant passages <sup>17</sup>	Relevant to Claim No. <sup>13</sup>	A	Chemical Abstracts, volume 87, no. 10, September 5, 1977, (Columbus, Ohio, US) see page 641, abstract 77463g, JP, A, 7754999, May 4, 1977 Matsushita Electric Industrial Co., Ltd. -----	7,9,10	A	US, A, 3878274, published April 15, 1975, see claims 1-4, column 2, lines 52-58, column 4, lines 4-9, column 5, 2nd table, column 6, both tables, Kureha -----	5,7,9,10	A	US, A, 3798473, published March 19, 1974 see claims 1,2,9,10,11, Kureha -----	1-3	A	GB, A, 1173688, published December 10, 1969 see claims 1,2,6, Kureha -----	9,10
Category <sup>6</sup>	Citation of Document, <sup>16</sup> with indication, where appropriate, of the relevant passages <sup>17</sup>	Relevant to Claim No. <sup>13</sup>															
A	Chemical Abstracts, volume 87, no. 10, September 5, 1977, (Columbus, Ohio, US) see page 641, abstract 77463g, JP, A, 7754999, May 4, 1977 Matsushita Electric Industrial Co., Ltd. -----	7,9,10															
A	US, A, 3878274, published April 15, 1975, see claims 1-4, column 2, lines 52-58, column 4, lines 4-9, column 5, 2nd table, column 6, both tables, Kureha -----	5,7,9,10															
A	US, A, 3798473, published March 19, 1974 see claims 1,2,9,10,11, Kureha -----	1-3															
A	GB, A, 1173688, published December 10, 1969 see claims 1,2,6, Kureha -----	9,10															
<div style="font-size: 0.8em;"> <p><sup>15</sup> Special categories of cited documents:</p> <div style="display: flex; justify-content: space-between;"> <div style="width: 48%;"> <p>"A" document defining the general state of the art</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document cited for special reason other than those referred to in the other categories</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> </div> <div style="width: 48%;"> <p>"P" document published prior to the international filing date but on or after the priority date claimed</p> <p>"T" later document published on or after the international filing date or priority date and not in conflict with the application, but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance</p> </div> </div> </div>																	
<b>IV. CERTIFICATION</b> <table border="1" style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%; padding: 5px;">           Date of the Actual Completion of the International Search <sup>1</sup>  <div style="text-align: center; font-family: monospace; font-size: 1.2em;">February 16, 1981</div> </td> <td style="width: 50%; padding: 5px;">           Date of Mailing of this International Search Report <sup>2</sup>  <div style="text-align: center; font-family: monospace; font-size: 1.2em;">March 2, 1981</div> </td> </tr> <tr> <td style="padding: 5px;">           International Searching Authority <sup>1</sup>            EUROPEAN PATENT OFFICE Branch at The Hague            P.O.Box 5818 Patentlaan, 2            2280 HV RIJSWIJK (ZH) The Netherlands         </td> <td style="padding: 5px;">           Signature of Authorized Officer <sup>20</sup>  <div style="text-align: center; font-family: monospace; font-size: 1.2em;">G.L.M. KRUYDENBERG</div> <div style="text-align: right; margin-top: 10px;"> </div> </td> </tr> </table>			Date of the Actual Completion of the International Search <sup>1</sup> <div style="text-align: center; font-family: monospace; font-size: 1.2em;">February 16, 1981</div>	Date of Mailing of this International Search Report <sup>2</sup> <div style="text-align: center; font-family: monospace; font-size: 1.2em;">March 2, 1981</div>	International Searching Authority <sup>1</sup> EUROPEAN PATENT OFFICE Branch at The Hague P.O.Box 5818 Patentlaan, 2 2280 HV RIJSWIJK (ZH) The Netherlands	Signature of Authorized Officer <sup>20</sup> <div style="text-align: center; font-family: monospace; font-size: 1.2em;">G.L.M. KRUYDENBERG</div> <div style="text-align: right; margin-top: 10px;"> </div>											
Date of the Actual Completion of the International Search <sup>1</sup> <div style="text-align: center; font-family: monospace; font-size: 1.2em;">February 16, 1981</div>	Date of Mailing of this International Search Report <sup>2</sup> <div style="text-align: center; font-family: monospace; font-size: 1.2em;">March 2, 1981</div>																
International Searching Authority <sup>1</sup> EUROPEAN PATENT OFFICE Branch at The Hague P.O.Box 5818 Patentlaan, 2 2280 HV RIJSWIJK (ZH) The Netherlands	Signature of Authorized Officer <sup>20</sup> <div style="text-align: center; font-family: monospace; font-size: 1.2em;">G.L.M. KRUYDENBERG</div> <div style="text-align: right; margin-top: 10px;"> </div>																