




## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification <sup>7</sup> :  E01F 9/04	A1	(11) International Publication Number: <b>WO 00/23655</b>
		(43) International Publication Date: 27 April 2000 (27.04.00)

(21) International Application Number: PCT/US99/17562	(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).
(22) International Filing Date: 3 August 1999 (03.08.99)	
(30) Priority Data: 09/175,523 20 October 1998 (20.10.98) US	
(71) Applicant: 3M INNOVATIVE PROPERTIES COMPANY [US/US]; 3M Center, P.O. Box 33427, Saint Paul, MN 55133-3427 (US).	
(72) Inventors: HEDBLOM, Thomas, P.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). RICE, Eric, E.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). BESCUP, Terry, L.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). MCGRATH, Joseph, M.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US).	
(74) Agents: CLEVELAND, David, R. et al.; Office of Intellectual Property Counsel, P.O. Box 33427, Saint Paul, MN 55133-3427 (US).	

(54) Title: PAVEMENT MARKING ARTICLES HAVING ENHANCED RETROREFLECTIVITY UNDER DRY OR WET CONDITIONS AND METHOD FOR MAKING SAME



## (57) Abstract

Pavement marking articles comprising a monolayer of exposed-lens optical elements (12), a spacing layer (14), and a reflective layer (16) are retroreflective under dry or wet conditions.

***FOR THE PURPOSES OF INFORMATION ONLY***

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

<b>AL</b>	Albania	<b>ES</b>	Spain	<b>LS</b>	Lesotho	<b>SI</b>	Slovenia
<b>AM</b>	Armenia	<b>FI</b>	Finland	<b>LT</b>	Lithuania	<b>SK</b>	Slovakia
<b>AT</b>	Austria	<b>FR</b>	France	<b>LU</b>	Luxembourg	<b>SN</b>	Senegal
<b>AU</b>	Australia	<b>GA</b>	Gabon	<b>LV</b>	Latvia	<b>SZ</b>	Swaziland
<b>AZ</b>	Azerbaijan	<b>GB</b>	United Kingdom	<b>MC</b>	Monaco	<b>TD</b>	Chad
<b>BA</b>	Bosnia and Herzegovina	<b>GE</b>	Georgia	<b>MD</b>	Republic of Moldova	<b>TG</b>	Togo
<b>BB</b>	Barbados	<b>GH</b>	Ghana	<b>MG</b>	Madagascar	<b>TJ</b>	Tajikistan
<b>BE</b>	Belgium	<b>GN</b>	Guinea	<b>MK</b>	The former Yugoslav Republic of Macedonia	<b>TM</b>	Turkmenistan
<b>BF</b>	Burkina Faso	<b>GR</b>	Greece	<b>ML</b>	Mali	<b>TR</b>	Turkey
<b>BG</b>	Bulgaria	<b>HU</b>	Hungary	<b>MN</b>	Mongolia	<b>TT</b>	Trinidad and Tobago
<b>BJ</b>	Benin	<b>IE</b>	Ireland	<b>MR</b>	Mauritania	<b>UA</b>	Ukraine
<b>BR</b>	Brazil	<b>IL</b>	Israel	<b>MW</b>	Malawi	<b>UG</b>	Uganda
<b>BY</b>	Belarus	<b>IS</b>	Iceland	<b>MX</b>	Mexico	<b>US</b>	United States of America
<b>CA</b>	Canada	<b>IT</b>	Italy	<b>NE</b>	Niger	<b>UZ</b>	Uzbekistan
<b>CF</b>	Central African Republic	<b>JP</b>	Japan	<b>NL</b>	Netherlands	<b>VN</b>	Viet Nam
<b>CG</b>	Congo	<b>KE</b>	Kenya	<b>NO</b>	Norway	<b>YU</b>	Yugoslavia
<b>CH</b>	Switzerland	<b>KG</b>	Kyrgyzstan	<b>NZ</b>	New Zealand	<b>ZW</b>	Zimbabwe
<b>CI</b>	Côte d'Ivoire	<b>KP</b>	Democratic People's Republic of Korea	<b>PL</b>	Poland		
<b>CM</b>	Cameroon	<b>KR</b>	Republic of Korea	<b>PT</b>	Portugal		
<b>CN</b>	China	<b>KZ</b>	Kazakhstan	<b>RO</b>	Romania		
<b>CU</b>	Cuba	<b>LC</b>	Saint Lucia	<b>RU</b>	Russian Federation		
<b>CZ</b>	Czech Republic	<b>LI</b>	Liechtenstein	<b>SD</b>	Sudan		
<b>DE</b>	Germany	<b>LK</b>	Sri Lanka	<b>SE</b>	Sweden		
<b>DK</b>	Denmark	<b>LR</b>	Liberia	<b>SG</b>	Singapore		
<b>EE</b>	Estonia						

5 PAVEMENT MARKING ARTICLES HAVING ENHANCED  
RETROREFLECTIVITY UNDER DRY OR WET CONDITIONS  
AND METHOD FOR MAKING SAME

### **Field of the Invention**

The present invention relates to pavement markings containing optical elements or  
10 skid-resistant particles. The present invention also relates to pavement markings having  
enhanced retroreflectivity under dry or wet conditions.

## Background of the Invention

15 The use of pavement markings (e.g., paints, retroreflective elements, tapes, and raised pavement markings) to guide and direct motorists traveling along a roadway is well known. These pavement markings often are retroreflective so motorists can see the markings at night. However, when the roadway is wet, for example from rainfall, the pavement marking in turn becomes wet and often the retroreflective performance diminishes.

20                   Retroreflection describes the mechanism where light incident on a surface is reflected so that much of the incident beam is directed back toward its source. When the surface of the pavement marking becomes wet, the optical elements (which typically are transparent, substantially spherical, glass or ceramic lenses) become coated with water, which typically reduces retroreflection. When optical elements become wetted or covered 25 with water, the ratio of the refractive index at the exposed-lens surface changes which affects light gathering.

To maintain good retroreflectivity during wet conditions, raised pavement markings, preformed pavement marking tapes, particularly those having raised patterned surfaces, retroreflective elements, and large diameter optical elements have been developed.

Examples of raised pavement markers include, but are not limited to, U.S. Patent No. 4,875,798 (May et al.), U.S. Patent No. 5,667,335 (Khieu et al.), and U.S. Patent No. 5,667,334 (Boyce). Raised pavement markers may be used to elevate retroreflective sheeting (e.g., enclosed-lens, sealed-lens, or prismatic-lens sheeting) on one or more

surface(s) above any water or other liquids on the roadway. Raised pavement markings are often susceptible to scratching of the outer plastic surface. Typically, raised pavement markings are about 1 to 3 centimeters in height. These scratches significantly reduce retroreflectivity under dry conditions. In addition, raised pavement markers are subject to 5 damage from snowplows and often are used in combination with other forms of pavement markings to provide sufficient daytime guidance.

Preformed pavement marking tapes are generally classified as "flat" tapes or "patterned" tapes which have generally vertical surfaces, usually in the form of retroreflective protuberances or protrusions (see, e.g., U.S. Patent Nos. 4,388,359 (Ethen 10 et al.), 4,988,555 (Hedblom), 4,988,541 (Hedblom), 5,670,227 (Hedblom et al.) and 5,676,488 (Hedblom)). Many flat pavement marking tapes rely on an exposed-lens optical system containing transparent microspherical optical elements partially embedded in a binder layer containing reflective pigment particles such as titanium dioxide or lead chromate. Enclosed lens pavement marking tapes are also known (e.g., WO97/01677).

15 Generally, patterned pavement marking tapes have better recovery of retroreflectivity after the rain has stopped because the rain will run off the raised or vertical portions. However, water may still coat the optical elements affecting the ratio of the refractive index and thus altering (and typically decreasing) retroreflectivity.

Examples of retroreflective elements include, but are not limited to, U.S. Patent 20 No. 5,750,191 (Hachey et al.), U.S. Patent No. 5,774,265 (Mathers et al.), and WO97/28470 (Palazotto et al.).

U.S. Patent Nos. 4,072,403 (Eigenmann) and 5,268,789 (Bradshaw) describe 25 pavement markings having good wet and dry retroreflectivity. However, the outer surface of these pavement markings may be readily scratched which decreases the dry retroreflectivity. These pavement markings tend to be rather rigid, which can make adhesion to the road difficult. Further, these pavement markings may be difficult to manufacture. The pavement markings are discreet and thus, do not provide continuous wet or dry delineation.

U.S. Patent No. 4,145,112 (Crone) describes a wet retroreflective optical system 30 based on refracting and retroreflective optics. One disadvantage of this system is durability. The plastic surface may scratch which reduces dry and wet retroreflective

performance, particularly because this system relies on a refracting surface and on a total internal reflecting surface.

Pavement markings having a mixture of microspheres having different refractive indices have been used to obtain dry and wet retroreflectivity. See for example, U.S.

5 Patent No. 5,777,791 (Hedblom). Here, the higher refractive index microspheres tend to be glass which is not as durable and is more readily scratched than the lower refractive index ceramic microspheres.

EP Patent No. 385746 B1 (Kobayashi et al.) discloses a pavement marking having a layer of large glass microspheres embedded in the top of retroreflective enclosed-lens 10 type base sheeting. The retroreflective pavement marking is said to be particularly useful in rainy conditions because the larger glass microspheres are partially exposed in air.

### Summary of the Invention

Pavement markings containing large glass microspheres tend to recover 15 retroreflectivity quicker after rain has stopped falling. However, actual retroreflective performance during rain tends to be poor because water covers the microsphere surface. These larger glass microspheres often have a relatively low refractive index (e.g., 1.5), which yields lower dry and wet retroreflection.

The need exists for pavement marking articles having enhanced retroreflection 20 when wet and which provide delineation in dry and in wet conditions, and in low visibility conditions improving driver knowledge of vehicle position thereby increasing driver safety.

The present invention provides pavement marking articles which are retroreflective under dry or wet conditions. Surprisingly, some embodiments of the present invention 25 have enhanced retroreflection when exposed to water, for example, when wet by rainwater. These pavement marking articles can be preformed pavement marking tapes, retroreflective flakes, or retroreflective elements embedded in a preformed pavement marking tape or in a road binder.

The articles of the present invention comprise a monolayer of exposed-lens optical 30 elements and a reflective layer, characterized in that there is a spacing layer between the optical elements and the reflective layer.

When the articles are a preformed pavement marking tape, the articles typically further comprise one or more top layers, a base layer, and an adhesive layer.

When the articles are retroreflective elements, the articles further comprise a core layer.

5 The present invention also provides a means for making these retroreflective pavement marking articles. One method comprises the steps of:

(a) providing an exposed-lens film comprising a layer of exposed-lens optical elements and a reflective layer; and

10 (b) embossing said exposed-lens film onto a preformed pavement marking tape,

characterized in that there is a spacing layer between the optical elements and the reflective layer.

Alternatively, one or more binder materials can be applied to the exposed-lens film prior to embossing the exposed-lens film onto the preformed pavement marking tape.

15 The film may be selectively applied to a preformed tape. For example, the film may be applied to only the vertical surfaces, only the protrusions, in a continuous stripe down or crossweb, etc. when applied to a preformed pavement marking tape.

Alternatively, the exposed-lens film composite can be laminated to a base layer comprising a plurality of protuberances.

20

#### Detailed Description of the Drawing

FIG. 1 is a cross-section of a retroreflective pavement marking article 10 having a layer of optical elements 12 with an exposed-lens surface 11 and an embedded-lens surface 13, a spacing layer 14, and a reflective layer 16.

25

FIG. 2 is a cross-section of a retroreflective preformed pavement marking tape 20 having a layer of optical elements 12 with an exposed-lens surface 11 and an embedded-lens surface 13, a spacing 14, a reflective layer 16, a top layer 22, a base layer 24, and an adhesive layer 26 for bonding the preformed tape to a roadway surface 28.

30

FIG. 3 is a cross-section of a retroreflective pavement marking article 30 having a layer of optical elements 12 where the optical elements have different average diameters, a spacing layer 14, and a reflective layer 16.

FIG. 4 is a cross-section of a retroreflective pavement marking article 40 having a layer of optical elements 12 with substantially the same average diameter, a spacing layer 14 having a variable thickness and a reflective layer 16.

5 FIG. 5 is a cross-section of a retroreflective pavement marking article 50 having a layer of optical elements 12 with two different refractive indices, a spacing layer 14, and a reflective layer 16.

10 FIG. 6 is a cross-section of a preformed pavement marking tape 60 having protrusions where the protrusions have a layer of optical elements 12 with a spacing layer 14 on the embedded-lens surface side of the optical elements and a reflective layer 16 layered on the spacing layer embedded therein. The tape has a binder layer 64 and a base layer 62.

15 FIG. 7 is a cross-section of a preformed pavement marking tape 70 having protrusions, with a layer of optical elements 12 having a spacing layer 14 on the embedded-lens surface side of the optical elements and a reflective layer 16 layered on the spacing layer embedded in the binder layer 64 on the top surface of the preformed tape.

FIG. 8 is a cross-section of a preformed pavement marking 80 having protrusions, with a layer of optical elements 12 having a spacing layer 14 on the embedded-lens surface side of the optical elements and a reflective layer 16 layered on the spacing layer and retroreflective flake 82 adhered to the preformed tape 80 with a binder layer 64.

20 The figures, which are idealized and not to scale, are intended to be merely illustrative and non-limiting.

#### Detailed Description of Illustrative Embodiments

25 The present invention provides a retroreflective pavement marking article comprising a monolayer of exposed-lens optical elements, a spacing layer, and a reflective layer. The pavement markings are retroreflective under wet or dry conditions.

30 The pavement marking articles are attached to the surface of a road or other traffic-bearing surface. These articles can be preformed pavement marking tapes, retroreflective flakes, or retroreflective elements. The tapes are typically attached to the roadway with an adhesive. The retroreflective flakes may be adhered to a preformed pavement marking tape or attached to a traffic-bearing surface using a road binder material. The

retroreflective elements may be adhered to a preformed pavement marking tape or attached to the traffic-bearing surface using a road binder material.

Pavement marking articles and other substantially horizontal markings typically exhibit high retroreflective brightness when the light is incident at high entrance angles (typically greater than about 85°). Retroreflective sheeting and other retroreflective articles attached to vertical surfaces, on the other hand, tend to exhibit high retroreflective brightness at lower entrance angles (e.g., within 30° to 40° of normal). Thus, the optical requirements of pavement marking articles differ from the optical requirements of retroreflective sheeting.

10

#### Optical Element Layer

A wide variety of optical elements are suitable for use in the present invention. The optical elements are exposed-lens. Exposed-lens is defined herein as having at least a portion of the optical element open to the air upon initial application to a traffic-bearing surface. After use on the traffic-bearing surface, the exposed-lens portion may become coated with oil, dust, road debris, etc. The portion of the optical element that is in contact with the spacing layer, or not the exposed-lens portion, is the embedded-lens portion.

However, various surface treatments may be present on the exposed-lens surface of the optical elements. For example, these treatments may be residual coatings used to enhance the adhesion of the optical element to the spacing layer. In addition, low adhesion topsize materials may be present on the exposed-lens surface to allow a preformed pavement marking tape article having an adhesive to be rolled-up and unwound. For retroreflective flakes or elements, various surface treatments may be present in small quantities on the surface of exposed-lens or embedded-lens elements to enhance the adhesion of the retroreflective flake or element to the binder or road binder or to modify wicking of the binder or road binder around the retroreflective flake or element. In all these cases, the thin films or surface treatments on the exposed-lens optical elements may temporarily affect the wetting of rain on the surface of the marking.

Typically, for optimal retroreflective effect, the optical elements have a refractive index ranging from about 1.5 to about 2.0 for optimal dry retroreflectivity, preferably ranging from about 1.5 to about 1.8. For optimal wet retroreflectivity, the optical elements

have a refractive index ranging from about 1.7 to about 2.4, preferably ranging from about 1.9 to 2.4, and more preferably ranging from about 1.9 to about 2.1.

5 The layer of optical elements can contain optical elements having the same, or approximately the same refractive index. Alternatively, the layer of optical elements can contain optical elements having two or more refractive indices. Typically, optical elements having a higher refractive index perform better when wet and optical elements having a lower refractive index perform better when dry. When a blend of optical elements having different refractive indices is used, the ratio of the higher refractive index optical elements to the lower refractive index optical elements is preferably about 1.05 to 10 about 1.4, and more preferably from about 1.08 to about 1.3.

15 Generally, optical elements having about 50 to about 1000 micrometers average diameter (preferably about 50 to about 500 micrometers average diameter, and more preferably from about 150 to about 350 micrometers average diameter) are preferred for use in the present invention. The optical element layer may contain optical elements having the same, or approximately the same average diameter. Alternatively, the optical element layer may contain optical elements having two or more average diameters. Typically, optical elements having a larger average diameter perform better when dry, while optical elements having a smaller average diameter perform better when wet.

20 Blends of optical elements having both different average diameter and refractive index may be used. Typically, a larger average diameter lower refractive index optical element is used to achieve better dry retroreflectivity, while a smaller average diameter higher refractive index optical element is used to achieve better wet retroreflectivity.

25 The optical elements can contain an amorphous phase, a crystalline phase, or a combination, as desired. The optical elements preferably contain inorganic materials that are not readily susceptible to abrasion. Suitable optical elements include, for example, microspheres formed of glass such as soda-lime-silicate glasses.

30 Microcrystalline ceramic optical elements as disclosed in U.S. Patent Nos. 3,709,706; 4,166,147; 4,564,556; 4,758,469; and 4,772,511 have enhanced durability. Preferred ceramic optical elements are disclosed in U.S. Patent Nos. 4,564,556, 4,772,511 and 4,758,469. These optical elements are resistant to scratching and chipping, are relatively hard (above 700 Knoop hardness). These ceramic optical elements may contain zirconia, alumina, silica, titania, and mixtures thereof.

The optical elements can be colored to retroreflect a variety of colors. Techniques to prepare colored ceramic optical elements that can be used herein are described in U.S. Patent No. 4,564,556. Colorants such as ferric nitrate (for red or orange) may be added in an amount of about 1 to about 5 weight percent of the total metal oxide present. Color 5 may also be imparted by the interaction of two colorless compounds under certain processing conditions (e.g.,  $TiO_2$  and  $ZrO_2$  may interact to produce a yellow color). The optical elements may be colored so that, for example, colorless, yellow, orange, or some other color of light is retroreflected at night.

10 The optical elements are typically partially embedded in the spacing layer in a hexagonal close-packed arrangement. In certain product applications, it may be advantageous to have the optical elements applied at less than the close-packed rate.

#### Spacing Layer

15 The pavement marking articles of the present invention contain a spacing layer that preferably "cups" the optical elements. The spacing layer has two major surfaces. The first major surface is in contact with the embedded-lens surface of the optical elements. The second major surface of the spacing layer is next to the reflective layer and follows a radius of curvature (preferably the radius of curvature is such that the spacing layer forms 20 a concentric hemisphere with respect to the optical element) larger than the optical element with an origin approximately at the center of the optical element. This forms the "cup".

25 The spacing layer can be applied to the optical elements using various techniques, including, but not limited to, solution coating, curtain coating, extrusion, lamination, and powder coating. Processing the spacing layer into a cup may include, but is not limited to, solvent evaporation, sagging of the spacing layer under the forces of gravity, displacement of the spacing layer due to fluid forces, or electrostatic deposition. Solidification of the spacing layer can include, but is not limited to, drying, chemical reaction, temporary ionic bonds, or quenching.

30 Generally, the spacing layer contains a resin such as polyvinyl butyral, polyurethanes, polyesters, acrylics, acid olefin copolymers such as ethylene acrylic acid, ethylene methacrylic acid, acid olefin copolymers neutralized with a base "ionomer", polyvinyl chloride and its copolymers, epoxies, polycarbonates, and mixtures thereof.

When selecting polymer systems for the spacing layer, optical transparency typically is a requirement. Generally, the spacing layer preferably has a 70% or greater transparency to visible light, more preferably, 80% or greater, and most preferably 90% or greater.

5 Various additives such as stabilizers, colorants, ultraviolet absorbers, antioxidants, etc. can be added to the spacing layer material to affect the processing, weathering, or retroreflective color.

10 The refractive index of the spacing layer generally ranges from about 1.4 to about 1.7, preferably from about 1.4 to about 1.6, and more preferably from about 1.45 to about 1.55.

15 The thickness of the spacing layer varies with the refractive index and the size of the optical elements. In general, assuming the optical elements have the same refractive index and the same size or average diameter, then the thicker the spacing layer, the better the optics when the pavement marking article is wet. Typically, the relative thickness of the spacing layer to the optical element radius ranges from about 0.05 to about 1.4, preferably from about 0.1 to about 0.9, and more preferably from about 0.2 to about 0.9.

For dry retroreflectivity, the optimal spacing layer thickness relative to the average radius of the optical element (for a refractive index ranging from about 1.5 to about 1.85) is given by the following formula for a 1.5 refractive index spacing layer:

20 
$$\text{spacing layer thickness/optical element radius} = \exp[-6.89 * (\text{optical element refractive index}) + 10.2]$$

The preferred range of the relative spacing layer thickness is about  $\pm 0.15$  for low refractive index optical elements and about  $\pm 0.1$  for high refractive index optical elements.

25 For wet retroreflectivity, the optimal spacing layer thickness relative to the average radius of the optical element (for a refractive index ranging from about 1.7 to about 2.4) is given by the formula for a 1.5 refractive index spacing layer:

$$\text{spacing layer thickness/optical element radius} = \exp[-3.99 * (\text{optical element refractive index}) + 7.20]$$

30 The preferred range of the relative spacing layer thickness is about  $\pm 0.20$  for low refractive index optical elements and about  $\pm 0.1$  for high refractive index optical elements.

For other refractive indices for the spacing layer, some variation in the above equation will result. Lower refractive index spacing layers will lead to a decreased

spacing layer thickness. Higher refractive index spacing layers will lead to an increased spacing layer thickness. Thinner spacing layers will generally yield improved retroreflective angularity in the retroreflective article.

The spacing layer may have the same, or approximately the same, thickness throughout the pavement marking article. Alternatively, the spacing layer thickness may vary across the pavement marking article crossweb or downweb. The spacing layer thickness may also vary sinusoidally downweb or crossweb. Suitable methods to vary the spacing layer thickness include, but are not limited to, extrusion with variable drawings speeds; extrusion with a profiled die; powdercoating with different web conductivities downweb or crossweb; and solution coating with a multiple orifice die.

#### Reflective Layer

The reflective layer can contain a diffuse reflector or a specular reflector.

The diffuse reflector typically contains a diffuse pigment. Examples of useful diffuse pigments include, but are not limited to, titanium dioxide, zinc oxide, zinc sulfide, lithophane, zirconium silicate, zirconium oxide, natural and synthetic barium sulfates, and combinations thereof. The diffuse pigment is typically delivered to the back of the spacing layer via a polymeric coating. The polymeric coating may be applied using a variety of techniques such as knife coating, roll coating, extrusion, or powder coating.

Illustrative examples of suitable polymeric materials include thermoset materials and thermoplastic materials. Suitable polymeric materials include, but are not limited to, urethanes, epoxies, alkyds, acrylics, acid olefin copolymers such as ethylene/methacrylic acid, polyvinyl chloride/polyvinyl acetate copolymers, etc.

The specular reflector may be a specular pigment, a metallized layer, or multi-layered di-electric materials.

An example of a useful specular pigment is a pearlescent pigment. Useful pearlescent pigments include, but are not limited to, AFFLAIR™ 9103 and 9119 (obtained from EM Industries, Inc., New York), Mearlin Fine Pearl #139V and Bright Silver #139Z (obtained from The Mearl Corporation, Briarcliff Manor, New York).

The reflective layer may also contain a thin metallic film or films. These thin metallic films may be applied by precipitation (e.g., precipitation of silver nitrate), thermal evaporation in a vacuum (e.g., resistive heating of Ag, Al; exploding wire; laser

evaporation; and the like), sputtering (e.g., glow discharge) and chemical methods (e.g., electrodeposition, chemical vapor deposition). Resistive heating of aluminum is the presently preferred method of coating thin metallic films.

5 Another suitable reflective layer includes multi-quarter wavelength layers of various dielectric materials. An odd number of stacks of high and low refractive index films can yield reflectances close to 100 percent. These multilayer thin films can be applied by thermal evaporation and chemical methods.

10 Different combinations of spacing layer thickness, spacing layer refractive index, optical element diameter, and optical element refractive index may be used in the present invention. For example, two different refractive index optical elements having approximately the same average diameter may be combined with a spacing layer having a thickness which varies cross-web. Another example of a suitable combination is an optical element layer containing two different average diameter optical elements having different refractive indices with a spacing layer having approximately the same thickness 15 downweb and crossweb.

#### Preformed Pavement Marking Tapes

If desired, preformed pavement marking tapes may contain additional layers to improve the performance of the resultant pavement marking tape.

20 The tapes may contain a top layer that typically is a top coat or a top film. The top layer is beneath the reflective layer. The top layer preferably adheres well to the reflective layer. The top layer may function as the binder layer to adhere the retroreflective article to the preformed pavement marking tape. Alternatively, the top layer may be located beneath the binder layer when the binder layer is present.

25 Useful top layers are known in the art. Examples of suitable top layers include both thermoplastic and thermoset polymeric materials.

Suitable polymeric materials include, but are not limited to, urethanes, epoxies, alkyds, acrylics, acid olefin copolymers such as ethylene/methacrylic acid, polyvinyl chloride/polyvinyl acetate copolymers, etc.

30 The top layer material may contain pigments for color. Illustrative samples of common colorants include, but are not limited to Titanium Dioxide CI 77891 Pigment White 6 (E. I. duPont de Nemours, Wilmington, DE), Chrome Yellow CI 77603 Pigment

Yellow 34 (Cookson, Pigments, Newark, NJ), Arylide Yellow CI 11741 Pigment Yellow 74 (Hoechst Celanese, Charlotte, NC), Arylide Yellow CI 11740 Pigment Yellow 65 (Hoechst Celanese, Charlotte, NC), Diarylide Yellow HR CI 21108 Pigment Yellow 83 (Hoechst Celanese, Charlotte, NC), Naphthol Red CI 12475 Pigment Red 170 (Hoechst Celanese, Charlotte, NC), IRGАЗINE™ 3RLTN PY 110 CI Pigment Yellow (Ciba Specialty Chemical Corp., Tarrytown, NY), Benzimidazolone H2G CI Pigment Yellow 120 (Hoechst Celanese, Charlotte, NC), and Isoindolinone CI Pigment Yellow 139 (Bayer Corp., Pittsburgh, PA).

The preformed pavement marking tapes may also contain a base layer (e.g., a 10 conformance layer) or an adhesive layer. These layers are located beneath the top layer. Many useful examples of such layers of preformed pavement marking tapes are well known and selection of suitable choices for particular embodiments of the invention may be readily made by one with ordinary skill in the art. Examples of suitable base layers include, but are not limited to, those disclosed in U.S. Patent Nos. 4,117,192; 4,490,432; 15 5,114,193; 5,316,406; and 5,643,655. Suitable adhesives include, but are not limited to, pressure-sensitive adhesives, rubber resin adhesives, neoprene contact adhesives, etc.

Preformed pavement marking tapes of the present invention may be substantially flat or have protrusions.

Illustrative examples of substantially flat pavement marking tapes which may be 20 modified to include the invention described herein, include, but are not limited to, U.S. Patent Nos. 4,117,192; 4,248,932; 5,077,117; and 5,643,655.

Illustrative examples of tapes having protrusions which may be modified to include the invention described herein, include, but are not limited to U.S. Patent No. 4,388,359, 25 4,988,555, 5,557,461, 4,969,713, 5,139,590, 5,087,148, 5,108,218, and 4,681,401. A preferred pavement marking tape having protrusions is disclosed in U.S. Patent No. 5,670,227.

The tapes may also be removable for short-term usage.

#### Retroreflective Flakes

The retroreflective flakes can contain the optical layer, the spacing layer, and the 30 reflective layer. The retroreflective flakes may also include one or more bottom layers adhered to the reflective layer. Generally, the retroreflective flakes are discreet segments

of the retroreflective article which are attached to a preformed pavement marking tape or on a traffic-bearing substrate. The retroreflective flakes typically are adhered to a preformed pavement marking tape having protrusions. Preferably, the flakes are selectively adhered to just the vertical surfaces of the protrusions.

5

Preferred binder materials and road binder materials are described below.

The presently preferred area of the retroreflective flakes is approximately 0.04 to about 1 (millimeters)<sup>2</sup> and more preferably the flakes are about 0.04 to about 0.25 (millimeters)<sup>2</sup>.

10

#### Retroreflective Elements in a Road Binder

Another embodiment of the present invention is a retroreflective element attached to a preformed pavement marking tape or partially embedded in a road binder.

The retroreflective elements contain the optical layer, the spacing layer, the reflective layer, and the core layer.

15

Suitable core layer material includes polymeric materials, both thermoplastic and thermoset materials and mixtures thereof. Particular examples of suitable material can be readily selected by those skilled in the art. Potential core layer materials can be selected from a wide range of thermoplastic materials. For example, non-crosslinked elastomer precursors (e.g., nitrile rubber formulations), ethylene-vinylacetate copolymers, polyesters, polyvinylacetate, polyurethanes, polyureas, acrylic resins, methacrylic resins, ethylene-acrylate/methacrylate copolymers, ethylene-acrylic acid/methacrylic acid copolymers, polyvinyl butyral, and the like are useful. The core layer material can contain one or more resin materials.

20

25 Illustrative examples of thermoset materials useful for the core layer include amino resins, thermosetting acrylic resins, thermosetting methacrylic resins, polyester resins, drying oils, alkyd resins, epoxy and phenolic resins, polyurethanes based on isocyanates, polyureas based on isocyanates, and the like. Such compositions are described in detail in Organic Coatings: Science and Technology, Volume I: Film Formation, Components, and Appearance, Zeno W. Wicks, Jr., Frank N. Jones and S. Peter Pappas, ed., John Wiley & Sons, Inc., New York, 1992.

30

The presently preferred dimensions of the retroreflective elements are approximately about 1 to about 2.5 millimeters thickness, about 0.5 to about 1 centimeter

width, and about 0.5 to about 10 centimeters length. The retroreflective elements may be any shape. However, the shape typically is rectangular or square.

The retroreflective article is attached to at least one surface of the core layer, and is typically attached to two or more surfaces of the core layer.

5        The retroreflective elements may be attached to either a flat or a protrusioned preformed tape. When the preformed tape has protrusions, the retroreflective elements preferably are adhered only to the generally up-right or "vertical" surfaces of the protrusions, where they provide the most efficient retroreflection. However, the retroreflective elements may be attached to the top surface of the top layer of the  
10      preformed tape.

The retroreflective elements or flakes can be attached to the tape using a binder material. Suitable binder materials include, but are not limited to polyurethanes, polyureas, epoxy resins, polyamides, polyesters, and mixtures thereof and to those disclosed in U.S. Patent Nos. 4,248,932, and 5,077,117 incorporated by reference herein.

15      Alternatively, a magnetic layer may be applied to the reflective layer of the retroreflective flake or element. The retroreflective flake or element may then be applied to a preformed pavement marking tape in the present of a magnetic field to help orient the retroreflective flake or element.

Road binders for pavement marking articles are well-known in the art. Suitable  
20      road binder materials include, but are not limited to, wet paint, thermoset materials, or hot thermoplastic materials (e.g., U.S. Patent Nos. 3,849,351, 3,891,451, 3,935,158, 2,043,414, 2,440,584, 4,203,878, 5,478,596). Typically, retroreflective elements or flakes and skid-resistant particles are sprinkled or otherwise applied to a road binder material while it is in a liquid state. The retroreflective elements or flakes or particles become  
25      partially embedded in the road binder material while it is liquid. The road binder material subsequently becomes solid resulting in retroreflective elements or flakes or particles partially embedded therein. Typically, the paint or thermoset or thermoplastic material forms a matrix that serves to hold the pavement marking articles in a partially embedded and partially protruding orientation. The matrix can be formed from durable two  
30      component systems such as epoxies or polyurethanes, or from thermoplastic polyurethanes, alkyds, acrylics, polyesters, and the like. Alternate coating compositions

that serve as a matrix and include the pavement marking articles described herein are also contemplated to be within the scope of the present invention.

#### Skid-Resistant Particles

5       Typically a retroreflective preformed pavement marking tape also contains skid-resistant particles. Illustrative examples of particularly useful skid-resistant particles include those disclosed in U.S. Patent Nos. 5,124,178; 5,094,902; 4,937,127; and 5,053,253. Skid-resistant particles may also be embedded in a retroreflective element, or embedded in a road-binder.

10      Generally, skid-resistant particles are randomly sprinkled and become embedded in the binder material while it is in a softened state. The skid-resistant particles may also be embedded in the spacing layer.

#### Method of Making Pavement Marking Articles

15      The retroreflective pavement marking articles of the present invention may be made by first making exposed-lens film and then placing this film in a vertical orientation using an embossing process.

20      The exposed-lens retroreflective film can be made by first coating a cupping resin onto a liner such as polyethylene terephthalate (PET), paper, or the like. (See for example, U.S. Patent No. 4,505,967(Bailey) column 4, line 63). Suitable cupping resins include 25 resins which have significantly lower viscosity than the spacing layer at the process temperature and which also exhibit low adhesion to the spacing layer (e.g., VITEL™ 3300 resin available from Bostik, Middleton, MA). The cupping resin (generally about 0.05 to about 0.25 millimeters thick) can be placed on the liner (generally about 0.01 to about 0.10 millimeters thick) by bar coating and forced air drying, extrusion, or hot melt coating. 25 After drying, the cupping film can be wound up.

30      Next, the spacing layer (which typically is a substantially transparent film) is coated (e.g., extruded or powder coated) on top of the cupping film forming a composite spacing layer. The spacing layer may contain, for example PRIMACOR™ 3440 resin, (an extrusion grade thermoplastic, high molecular weight copolymer believed to contain a major portion of ethylene monomer and a minor portion of acrylic acid monomer, available from Dow Chemical Co. Midland, MI, and having a melt flow index of about

10), a weather stabilizing system, and an antioxidant. This composite spacing layer can then be wound up.

Several polymer processing techniques are useful for applying the spacing layer to the optical elements. When the optical elements have an average diameter less than about 5 100 microns, knife coating a polymeric solution on top of an optical element film will result in an adequately cupped spacing layer.

For larger retroreflective articles, powder coating produces a spacing layer having uniform thickness on the optical elements. In one example of powder coating, a polymer is made or ground to about 30 micron mean particle size. The powder is fluidized and 10 conveyed with compressed air to an electrostatic spray gun where the powder is charged by corona or triboelectric methods. The powder is then sprayed towards the optical element film which is over a conductive substrate or base plate that is maintained at electrical ground. When the charged powder comes close to the grounded optical element film, the powder particles adhere due to electrostatic attraction. The dynamics of the 15 electrostatic attraction are such that the powder tends to collect at a uniform thickness over the three dimensional optical element film. The powder coated optical element film is then passed through an oven to fuse the powder onto the substrate. Various fluidized bed powdercoating techniques can alternatively be employed to deliver a uniform thickness of powder over the optical element containing film prior to the powder fusing operation.

20 Further processing may then take place.

A second film (which usually serves as the optical element carrier) is made by extruding a polyolefin (e.g., polyethylene) onto a liner such as PET, paper, or the like. The thickness of the polyolefin is commensurate with the optical element average radius. The second film is heated to a temperature about the melting temperature of the film (e.g. 25 for polyethylene film, above 135°C). The optical elements are then dropped from a dispenser and partially embedded, preferably to about 30% or more of their average diameter, into the softened second film to form a monolayer of optical elements. This optical element film composite can then be wound up.

30 Optionally, the optical elements can be coated with a surface treatment such as silane to help the optical elements adhere to the spacing layer. For example, this surface treatment can be applied by reverse roll coating a solution of A1100 silane (available from Union Carbide, Danbury, CT) in deionized water and then drying.

The optical element film composite is then laminated to the composite spacing layer to partially embed the optical elements into the spacing layer. This may be accomplished by heating the composite spacing layer (e. g., run over a hot can or through an oven) and then laminating the two composites together using a nip to form "the laminate".

During the lamination step, the cupping film has a lower viscosity than the spacing layer. This helps the spacing layer form a more uniform cup around the optical element. The degree to which the spacing layer cups the optical element has an affect on the angularity of the retroreflective article.

10 Next, the cupping film is stripped away from the composite spacing layer which is now adhered to the optical elements. The spacing layer becomes exposed and is cured if desired (e.g., ultraviolet radiation, e-beam). A reflective layer (e.g., vapor coating an aluminum metallic layer) is formed on the exposed portion of the spacing layer. The optical element carrier is stripped away from the laminate, exposing the optical elements.

15 The resulting article can then be wound up. The resulting article includes the optical elements, and behind the optical elements is the spacing layer backed by a reflective layer (e.g., an aluminum vapor coat).

A top layer may be laminated to the reflective layer before or after removal of the optical element carrier. For example, a pigmented thermoplastic resin (e.g., EMAA film) 20 may be laminated to the bottom side of the reflective layer opposite the optical elements. The top layer may act as the binder layer or alternatively, a binder layer may be used to attach the retroreflective article (here a film) to a preformed pavement marking tape.

25 This retroreflective film can then be placed on the top surface of a preformed pavement marking tape by feeding the film into an embossing nip. Alternatively, the film can first be coated with a binder material and then be laminated to a preformed pavement marking tape having protrusions.

30 The film can be selectively placed on a preformed pavement marking tape by indexing. The film can be appropriately spaced such that when applied to the preformed tape, the film is located only on the vertical surfaces, only on the pattern of the tape, only on the protrusions, or only in stripes downweb or crossweb. Preferably at least 5 percent of the top surface area of the preformed pavement marking tape is covered with the retroreflective film.

Methods of Application

5 The preformed pavement marking tape articles of the present invention may be installed on a roadway or other location using any one of a variety of apparatus such as human pushable dispensers, "behind a truck" type dispensers, and "built into a truck" type dispensers. U.S. Pat. No. 4,030,958 (Stenemann) discloses a behind a truck type dispenser that can be used to apply articles of the invention in the form of adhesive-backed tapes to a surface.

10 Other means may be used to install the pavement marking tape articles of the invention, such as simple manual application, or use of the previously mentioned mechanical fasteners.

Examples

15 The following examples further illustrate various specific features, advantages, and other details of the invention. The particular materials and amounts recited in these examples, as well as other conditions and details, should not be construed in a manner that would unduly limit the scope of this invention. Percentages given are by weight, unless otherwise specified.

20 Pavement marking articles 5 through 66 and 76 through 102 were prepared as follows. The top surface of the exposed-lens optical elements was scrubbed with toothpaste and a toothbrush. This scrubbing removes any low surface energy contamination on top of the optical elements and facilitates the rain wetting out the optics. The reflective layer-side of the exposed-lens optical element films was laminated using a pressure-sensitive adhesive to LEXANT<sup>TM</sup> pieces measuring 10 centimeters long, 0.64 centimeters wide and 3.0 millimeters in height. The exposed-lens films were attached to the 3.0 millimeter by 10 centimeter side. The exposed-lens optical element films were then trimmed to 3.0 millimeters by 10 centimeters producing a retroreflective element. The retroreflective elements were then mounted with a spacing of about 5.8 centimeters onto an aluminum panel measuring 1.5 millimeters thick by 10 centimeters wide by 1.5 meters long to produce a pavement marking article.

## Optical Elements

Refractive Index	Type	Average Diameter	Distribution Range	Description
1.5	Glass	165 microns	150-180 microns	Potters Industries, Inc. Hasbrouck Heights, NJ
1.5	Glass	200 microns	180 – 210 microns	Potters Industries, Inc.
1.5	Glass	1350 microns	1000-1700 microns	Potters Industries, Inc.
1.75	Ceramic	200 microns	180 – 210 microns	Example 4 of U.S. Patent No. 4,564,556
1.75	Ceramic	220 microns	180 – 250 microns	Example 4 of U.S. Patent No. 4,564,556
1.75	Ceramic	250 microns	210 – 300 microns	Example 4 of U.S. Patent No. 4,564,556
1.75	Ceramic	350 microns	300 – 420 microns	Example 4, U.S. Patent No. 4,564,556
1.91	Ceramic	165 microns	150 – 180 microns	Example 1 of U.S. Patent No. 4,772,511
1.91	Glass	275 microns	250 – 300 microns	Potters Industries, Inc.
1.91	Glass	460 microns	420 – 500 microns	Potters Industries, Inc.
1.93	Glass	65 microns	53 – 74 microns	Nippon Electric Glass, Osaka, Japan Flex-O-Lite, St. Louis, MO
2.26	Glass	65 microns	53 – 74 microns	Nippon Electric Glass; Flex-O-Lite

Various methods of manufacturing 1.75 ceramic optical elements are available,  
 5 such as described in Example 4 of U.S. Patent No. 4,564,556. In that Example, a stable,  
 ion-exchanged zirconia sol was prepared by mixing a nitrate stabilized zirconia sol  
 containing about 20%  $ZrO_2$  by weight and about 0.83 M  $NO_3$  per mole  $ZrO_2$  (obtained  
 from Nyacol Products Company), with an ion exchange resin (Amberlyst A-21 resin made  
 by Rohm and Haas Company) in a ratio of about 100 g of sol to 15 g resin. To about 21 g  
 10 of the resulting stable zirconia sol were added about seven grams of silica sol (Ludox LS),  
 and then about 2.5 g of a 50% aqueous ammonium acetate solution were added to the sol  
 with agitation. The resulting mixture (having a  $ZrO_2:SiO_2$  mole ratio of about 1:1) was  
 immediately added to 500 ml of 2-ethylhexanol under agitation in a 600 ml beaker. After  
 stirring for about five minutes, the mixture was filtered to separate the gel particles from  
 15 the alcohol. Very transparent, rigid gelled spheres up to and exceeding 1 mm in diameter

were recovered. The particles were dried and subsequently fired to 1000°C. Intact, transparent to slightly translucent spheres up to and over 500 micrometers in diameter were obtained.

Various methods of manufacturing 1.91 ceramic optical elements are available, 5 such as described in Example 1 of U.S. Patent No. 4,772,511 as modified herein. In that Example, 90.0 grams of aqueous colloidal silica sol, while being rapidly stirred, was acidified by the addition of 0.75 milliliter concentrated nitric acid. The acidified colloidal silica was added to 320.0 grams of rapidly stirring zirconyl acetate solution. 52.05 grams of Niacet aluminum formoacetate (33.4% fired solids) were mixed in 300 milliliters 10 deionized water and dissolved by heating to 80° C. The solution, when cooled, was mixed with the zirconyl acetate-silica mixture described previously. The resulting mixture was concentrated by rotoevaporation to 35% fired solids. The concentrated optical element precursor solution was added dropwise to stirred, hot (88° - 90° C) peanut oil. The precursor droplets were reduced in size by the agitation of the oil and gelled.

15 Agitation was continued in order to suspend most of the resulting gelled droplets in the oil. After about one hour, agitation was stopped and the gelled microspheres were separated by filtration. The recovered gelled microspheres were dried in an oven for about 5 hours at about 78° C prior to firing. The dried microspheres were placed in a quartz dish and fired in air by raising the furnace temperature slowly to about 900°C over 10 hours, 20 maintaining about 900° for 1 hour, and cooling the microspheres with the furnace. The initial firing of all the samples was done in a box furnace with the door slightly open. The optical element constituents were in the molar ratio of  $ZrO_2:Al_2O_3:SiO_2$  of 3:00:1.00:0.81

25 The coefficient of retroreflection ( $R_A$ ), in  $cd/Lux/m^2$ , following Procedure B of ASTM Standard E 809-94a, was measured at an entrance angle of -4.0 degrees and an observation angle of 0.2 degrees. The photometer used for those measurements is described in U.S. Defensive Publication No. T987,003.

30 The coefficient of Retroreflective Luminance,  $R_L$ , was measured for each pavement marking article at a geometry which approximates an automobile at 30 meters distance from the sample. The pavement marking articles were placed onto a table in a dark room. Above the pavement marking articles was a plumbing system capable of delivering a uniform artificial rainfall at a rate of about 3.3 centimeters per hour. The

pavement marking articles were illuminated with projector lamps. The nominal entrance angle to the samples was 88.8 degrees. A photometer (IL 1700 Research Radiometer/Photometer by International Light, Inc.; Newburyport, Mass.) was used to measure the Illuminance on the sample. Typical illumination of the prototypes was about 5 70 Lux. A telephotometer (Digital Luminance Meter Series L 1000 by LMT; Berlin, Germany) was placed about 30 meters from the samples at a height corresponding to an observation angle of 1.05 degrees. The Luminance of each of the samples was measured with the telephotometer, units of  $\text{cd}/\text{m}^2$ .  $R_L$  is calculated by dividing the Luminance of the sample by the Illuminance.

10 The rainfall measurements were made two ways. The first was a fast draining experiment. The pavement marking articles were rained on. The rainfall was allowed to drain immediately off the aluminum panels onto which the pavement marking articles were attached. When a steady state rain Luminance was achieved, the rainfall was turned off. The Luminance was allowed to recover and the steady state recovered Luminance again was measured. Typically, the steady state recovered Luminance after the rain was turned on or off took about 3 minutes. In the second experiment, the pavement marking articles were contained within a trough. The trough was nominally 15 centimeters wide by about 1.5 meters long by about 1.5 millimeters deep. The pavement marking articles were thus elevated to a height of 1.5 millimeters and contained within a trough of about 1.5 15 millimeters deep. This trough resulted in a significantly slower drainage of water from the rainfall marking articles representing a higher rainfall rate. The steady state recovered Luminance was measured during the rainfall and after recovery.

#### Comparative Example 1

25 A piece of 3M STAMARK™ High Performance Pavement Marking Tape Series 380 (available from Minnesota Mining and Manufacturing Co. ("3M"), St. Paul, MN.) was installed on a low traffic volume roadway for several months to remove the low adhesion topsize from the surface of the product. The piece of tape was then removed from the roadway. If present, the topsize can help shed water from the pavement marking which 30 can give a false indication of overall wet retroreflective performance.

### Comparative Example 2

This sample is a piece of new 3M STAMARK™ High Performance Pavement Marking Tape Series 380.

5

### Comparative Example 3

This sample is a piece of 3M SCOTCHLANE™ Removable Tape Series 750 (available from 3M), which is a wet retroreflective product primarily for use in construction zones.

10

### Comparative Example 4

This sample is a flat preformed pavement marking tape having 1350 micron average diameter glass optical elements with a refractive index of 1.5. The optical elements were coated onto polyurethane (730 grams per square meter). The polyurethane contained 27 weight percent titanium dioxide pigment. A polyurethane solution was mixed using the following components:

15

27.0%	Rutile titanium dioxide pigment (available as TIPURE™ R-960, E.I. duPont de Nemours, New Johnsonville, TN.)
25.1%	TONE™ 0301 polyester polyol (available from Union Carbide Corp., Danbury, CT.)
20	47.9% DESMODUR™ N-100 aliphatic polyisocyanate (available from Bayer Corp., Pittsburgh, PA.)

The thickness and the viscosity of the polyurethane were adjusted to provide nominally 50 percent optical element embedment. The polyurethane was cured in an oven at about 120°C for about 15 minutes.

25

Comparative Examples 1 through 4 were mounted on aluminum panels (1.5 millimeters thick, 10 centimeters wide and 1.5 meters long). The  $R_L$  values were then measured for each example.

COMP. EX.	OPTICAL ELEMENT REFRACTIVE INDEX	AVG. SIZE MICRONS	PRODUCT	REFLECTIVE LAYER
1	1.75	220	WEATHERED STAMARK™ SERIES 380 TAPE	TiO <sub>2</sub>
2	1.75	220	NEW STAMARK™ SERIES 380 TAPE	TiO <sub>2</sub>
3	2.26	65	SCOTCHLANE™ SERIES 750 TAPE	Enclosed-lens Retroreflective Sheeting
4	1.5	1350	FLAT TAPE	TiO <sub>2</sub>

COMP. EX.	CALCULATED COEFFICIENT OF RETROREFLECTED LUMINANCE – R <sub>L</sub> (mCd/m <sup>2</sup> /Lx)					
	FAST WATER DRAINAGE			SLOW WATER DRAINAGE		
	DRY	RAIN	RECOVERY	DRY	RAIN	RECOVERY
1	980	32	48			
2	600	250	330	500	9	7
3	655	638	655	720	600	590
4	450	70	160	230	50	67

As witnessed during the slow rain experiment, R<sub>L</sub> values less than about 150 mCd/m<sup>2</sup>/Lx provide poor contrast and are not desirable for pavement marking articles. At R<sub>L</sub> values at about 300 mCd/m<sup>2</sup>/Lx adequate contrast was provided and acceptable pavement marking article delineation was provided. Excellent contrast and pavement marking delineation was obtained at R<sub>L</sub> values at about 600 mCd/m<sup>2</sup>/Lx. R<sub>L</sub> values greater than 1000 mCd/m<sup>2</sup>/Lx are highly desirable for pavement marking articles.

10

#### Comparative Examples 5-8

The polyurethane solution of Comparative Example 4 was coated onto a paper release liner using a notch bar. Optical elements having different refractive indices (as set forth in the following table) were then flood coated onto the surface of the polyurethane and oven cured at about 120°C for about 15 minutes. The coefficient of retroreflection (R<sub>A</sub>) was measured. Retroreflective elements were then made as previously described. A pavement marking article was then made from the retroreflective elements as previously described. The coefficient of retroreflected luminance R<sub>L</sub> was then measured for the pavement marking articles.

20

COMP. EX.	OPTICAL ELEMENT REFRACTIVE INDEX	OPTICAL ELEMENT TYPE	AVG. SIZE MICRONS	SPACING LAYER	REFLECTIVE LAYER
5	1.75	CERAMIC	220	NONE	TiO <sub>2</sub>
6	1.91	CERAMIC	165	NONE	TiO <sub>2</sub>
7	2.26	GLASS	65	NONE	TiO <sub>2</sub>
8	1.5	GLASS	200	NONE	TiO <sub>2</sub>

COMP. EX.	COEFFICIENT OF RETROREFLECTION (Cd/LX/M <sup>2</sup> )		CALCULATED COEFFICIENT OF RETROREFLECTED LUMINANCE - R <sub>L</sub> (mCd/m <sup>2</sup> /Lx)						
	DRY	WET	FAST WATER DRAINAGE			SLOW WATER DRAINAGE			
	-4/0.2	-4/0.2	DRY	RAIN	RECOVERY	DRY	RAIN	RECOVERY	
5	8.5	0.8	2400	480	250	950	140	100	
6	15.4	0.9	1500	300	390	1400	190	190	
7	1.4	4.2	520	550	800	570	590	590	
8	1.3	0.4	300	68	91	220	50	67	

These examples illustrate that even in patterned pavement markings with minimized nighttime shadows, titanium dioxide-filled systems do not have adequate wet contrast levels unless very high refractive index (2.26) optical elements are used. These very high refractive index optical elements are typically glass which typically has poor abrasion resistance.

10

### Comparative Examples 9-11

A polyurethane solution was mixed using the following components:

35.0%      pearlescent pigment (AFFLAIR™ 9119, available from EM Industries, Inc., Hawthorne, NY)

22.3%      TONE™ 0301 polyester

15

42.7%      DESMODUR™ N-100 aliphatic polyisocyanate

The polyurethane solution was coated onto a paper release liner using a notch bar.

Optical elements having different refractive indices (as set forth in the following table) were then flood coated onto the surface of the polyurethane and oven cured at about 120°C for about 15 minutes. The coefficient of retroreflection (R<sub>A</sub>) was measured.

20

Retroreflective elements were then made as previously described. A pavement marking article was then made from the retroreflective elements as previously described. The

coefficient of retroreflected luminance  $R_L$  was then measured for the pavement marking articles.

COMP. EXAMPLE	OPTICAL ELEMENT REFRACTIVE INDEX	OPTICAL ELEMENT TYPE	AVG. SIZE MICRONS	SPACING LAYER	REFLECTIVE LAYER
9	1.75	CERAMIC	220	NONE	PEARL
10	1.91	CERAMIC	165	NONE	PEARL
11	2.26	GLASS	65	NONE	PEARL

COMP. EX.	COEFFICIENT OF RETROREFLECTION (Cd/LX/M <sup>2</sup> )		CALCULATED COEFFICIENT OF RETROREFLECTED LUMINANCE - $R_L$ (mCd/m <sup>2</sup> /Lx)					
	DRY	WET	FAST WATER DRAINAGE			SLOW WATER DRAINAGE		
	-4/0.2	-4/0.2	DRY	RAIN	RECOVERY	DRY	RAIN	RECOVERY
9	18.9	0.7	4300	1300	1900	3400	220	220
10	61.3	1.0	2400	620	870	2100	370	320
11	1.1	14.9	390	1200	1700	400	1100	1100

5

These examples illustrate the magnitude of the impact that rain (slow water drainage) has on highly efficient patterned pavement marking articles having specular reflecting pigments and high refractive index optical elements (e.g., 1.91 refractive index). Very high refractive index optical elements (e.g., 2.26) provide excellent contrast in the rain.

10 These optical elements are typically glass which typically has poor abrasion resistance.

### Examples 12-17.

Glass optical elements having a 1.9 refractive index and an average diameter of 65 microns were embedded to approximately 40 percent of their average diameter in a

15 polyethylene coated paper. The polyethylene coated paper was heated to about 135 °C and flood coated with glass optical elements preheated to about 135°C. The optical element coated web was maintained at about 135°C for about an additional 3 minutes resulting in the glass optical elements becoming embedded to about 40 percent of their average diameter. A spacing layer solution was coated on top of the optical elements  
20 using a notch bar. The notch bar gap ranged from 0 to about 250 microns. The spacing layer solution consisted of:

23% DOWANOL™ EB ethylene glycol monobutyl ether solvent (Dow Chemical USA; Midland, MI)

48% CYCLO-SOL™ 53 #100 solvent (Shell Chemical Company; Baytown, TX)  
4% AROPLAZ™1351 (Reichhold Chemicals Inc.; Newark, NJ)  
18% BUTVAR™ B76 (Solutia Inc.; Trenton, MI)  
7% Beckamine P138 (Reichhold Chemicals Inc.; Newark, NJ)  
5 0.5% Tri-ethylamine (Air Products & Chemicals, Inc.; Shakopee, MN).

The spacing layer solution was dried and cured in a succession of ovens at about 65°C, about 77°C, about 150°C, about 155°C, and about 170°C for about one minute each. No spacing layer was applied to the optical elements in Example 12.

10 The exposed portion of the spacing layer was vapor coated with aluminum as follows: The vacuum evaporator used was a NRC 3115 purchased from the Norton Company, Vacuum Equipment Division, Palo Alto, California. A sample measuring roughly 15 centimeters x 15 centimeters was placed at the top of the chamber in the bell jar so that the back of the spacing layer was in direct sight of the aluminum source.

15 Aluminum wire was placed between the filament electrodes. The vacuum chamber was closed and then pumped down to a pressure of about  $10^{-6}$  torr ( $1.3 \times 10^{-3}$  dyne/cm<sup>2</sup>). The evaporation filament power supply was turned on and the power increased to a level necessary to vaporize the aluminum wire. A quartz-crystal oscillator was used to monitor the aluminum deposition. The shutter over the aluminum source was closed after about 900 Angstroms of aluminum was deposited. The retroreflective article was then removed.

20 The coefficient of retroreflection ( $R_A$ ) was measured. Retroreflective elements were then made as previously described. A pavement marking article was then made from the retroreflective elements as previously described. The coefficient of retroreflected luminance  $R_L$  was then measured for the pavement marking articles.

EXAMPLE	OPTICAL ELEMENT REFRACTIVE INDEX	OPTICAL ELEMENT TYPE	AVG. SIZE MICRONS	SPACING LAYER	REFLECTIVE LAYER
12	1.93	GLASS	65	NONE	Al VAPORCOAT
13	1.93	GLASS	65	50 MICRON BAR GAP SOLVENT COATED	Al VAPORCOAT
14	1.93	GLASS	65	100 MICRON BAR GAP SOLVENT COATED	Al VAPORCOAT
15	1.93	GLASS	65	150 MICRON BAR GAP SOLVENT COATED	Al VAPORCOAT
16	1.93	GLASS	65	200 MICRON BAR GAP SOLVENT COATED	Al VAPORCOAT
17	1.93	GLASS	65	250 MICRON BAR GAP SOLVENT COATED	Al VAPORCOAT

EXAMPLE	COEFFICIENT OF RETRO-REFLECTION (Cd/LX/M <sup>2</sup> )		CALCULATED COEFFICIENT OF RETROREFLECTED LUMINANCE - R <sub>L</sub> (mCd/m <sup>2</sup> /Lx)					
			FAST WATER DRAINAGE			SLOW WATER DRAINAGE		
	-4/0.2	-4/0.2	DRY	RAIN	RECOVERY	DRY	RAIN	RECOVERY
12	536	0.8	8400	150	190	9000	120	120
13	49.0	30.9	4100	650	1200	3300	780	810
14	13.1	35.6	1700	1700	2700	1400	1700	1600
15	11.6	115	870	2200	4100	900	2200	2600
16	11.1	133	710	2000	4000	860	2100	2400
17	10.5	46.0	600	940	1500	670	1000	1000
Comp. Ex. 6	15.4	0.9	1500	300	390	1400	190	190
Comp. Ex. 10	61.3	1.0	2400	620	870	2100	370	320
Comp. Ex. 11	1.1	14.9	390	1200	1700	400	1100	1100

These examples illustrate the highly desirable levels of R<sub>L</sub> that can be achieved in the rain (slow water drainage) using a spacing layer. These articles having a spacing layer have much higher dry R<sub>L</sub> values than specular reflective pigment systems with very high refractive index optical elements (Comparative Example 11).

### Examples 18-23

10 Samples were prepared as described in Examples 12-17 substituting 165 micron average diameter ceramic optical elements. In addition, the spacing layer bar gaps were varied from 0 to about 250 microns. The coefficient of retroreflection (R<sub>A</sub>) was measured. Retroreflective elements were then made as previously described. A pavement marking

article was then made from the retroreflective elements as previously described. The coefficient of retroreflected luminance  $R_L$  was then measured (the slow water drainage data was gathered at a later date) on the pavement marking article.

EXAMPLE	OPTICAL ELEMENT REFRACTIVE INDEX	OPTICAL ELEMENT TYPE	AVG. SIZE MICRONS	SPACING LAYER	REFLECTIVE LAYER
18	1.91	CERAMIC	165	NONE	Al VAPORCOAT
19	1.91	CERAMIC	165	50 MICRON BAR GAP SOLVENT COATED	Al VAPORCOAT
20	1.91	CERAMIC	165	100 MICRON BAR GAP SOLVENT COATED	Al VAPORCOAT
21	1.91	CERAMIC	165	150 MICRON BAR GAP SOLVENT COATED	Al VAPORCOAT
22	1.91	CERAMIC	165	200 MICRON BAR GAP SOLVENT COATED	Al VAPORCOAT
23	1.91	CERAMIC	165	250 MICRON BAR GAP SOLVENT COATED	Al VAPORCOAT

5

EXAMPLE	COEFFICIENT OF RETRO-REFLECTION (Cd/LX/M <sup>2</sup> )		CALCULATED COEFFICIENT OF RETROREFLECTED LUMINANCE – $R_L$ (mCd/m <sup>2</sup> /Lx)					
			FAST WATER DRAINAGE			SLOW WATER DRAINAGE		
	DRY	WET	DRY	RAIN	RECOVERY	DRY	RAIN	RECOVERY
18	100	0.6	4500	270	380	4500	160	260
19	290	0.9	2700	280	310	5100	280	290
20	46.7	2.9	2200	270	300	4100	330	330
21	33.6	3.9	2000	300	340	3700	330	350
22	9.1	10.5	1400	570	600	2200	740	780
23	7.0	12.6	960	830	970	1500	970	970
6 (Comparative)	15.4	0.9	1500	300	390	1400	190	190
10 (Comparative)	61.3	1.0	2400	620	870	2100	370	320
11 (Comparative)	1.1	14.9	390	1200	1700	400	1100	1100

These examples illustrate the excellent contrast that can be achieved in the rain (slow water drainage) using a spacing layer. These articles having a spacing layer have much higher dry  $R_L$  values than specular reflective pigment systems with very high refractive index optical elements (Comparative Example 11).

Examples 24-66

PRIMACOR™ 3440 resin (obtained from Dow Chemical USA, Midland, MI) was extruded onto a polyester film. The extruder conditions and web speeds were varied to produce film thickness ranging from about 50 to about 150 microns in 12.5 micron increments. The original extruded films were laminated together at a temperature of about 120°C to obtain a thickness ranging from about 175 to about 300 microns. Optical elements were coated with a spacing layer as follows. The extruded films were placed polyester side-down on a hot plate at a temperature of about 205°C. Optical elements having various sizes were previously heated to the same temperature and were then flooded over the surface of the extruded film. The optical elements were allowed partially to embed themselves in the extruded film for about 30 seconds. The optical element-coated films were then removed and cooled. The polyester liner was removed. The optical element-coated film was then placed optical element side-down on the hot plate at about 205°C surface for about 5 minutes. These conditions allowed the extrusion to sag down the optical element and form a concentric spacing layer by cupping. The spacing layer-coated optical elements (or spacing layer composite) was then removed and quenched in room temperature water.

20

Examples 24-33

Ceramic optical elements having a 165 micron average diameter were embedded in an extruded spacing layer having a thickness ranging from 0 to about 150 microns. After cupping the spacing layer, the films were vaporcoated with about 900 angstroms of aluminum as described in Examples 12-17. The coefficient of retroreflection ( $R_A$ ) was measured. Retroreflective elements were then made as previously described. A pavement marking article was then made from the retroreflective elements as previously described. The coefficient of retroreflected luminance  $R_L$  was then measured for the pavement marking articles.

EXAMPLE	OPTICAL ELEMENT REFRACTIVE INDEX	OPTICAL ELEMENT TYPE	AVG. SIZE MICRONS	SPACING LAYER	PIGMENT
24	1.91	CERAMIC	165	NONE	Al VAPORCOAT
25	1.91	CERAMIC	165	50 MICRON EXTRUDED	Al VAPORCOAT
26	1.91	CERAMIC	165	63 MICRON EXTRUDED	Al VAPORCOAT
27	1.91	CERAMIC	165	75 MICRON EXTRUDED	Al VAPORCOAT
28	1.91	CERAMIC	165	88 MICRON EXTRUDED	Al VAPORCOAT
29	1.91	CERAMIC	165	100 MICRON EXTRUDED	Al VAPORCOAT
30	1.91	CERAMIC	165	113 MICRON EXTRUDED	Al VAPORCOAT
31	1.91	CERAMIC	165	125 MICRON EXTRUDED	Al VAPORCOAT
32	1.91	CERAMIC	165	138 MICRON EXTRUDED	Al VAPORCOAT
33	1.91	CERAMIC	165	150 MICRON EXTRUDED	Al VAPORCOAT

EXAMPLE	COEFFICIENT OF RETRO-REFLECTION (Cd/LX/M <sup>2</sup> )		CALCULATED COEFFICIENT OF RETROREFLECTED LUMINANCE - R <sub>L</sub> (mCd/m <sup>2</sup> /Lx)					
			FAST WATER DRAINAGE			SLOW WATER DRAINAGE		
	-4/0.2	-4/0.2	DRY	RAIN	RECOVERY	DRY	RAIN	RECOVERY
24	100	0.6	4500	270	380	4500	160	260
25	19.0	1.0	2300	410	570	2300	300	370
26	18.0	3.0	1800	400	610	1600	330	460
27	15.0	7.0	980	540	860	910	520	690
28	9.0	22.0	570	1100	1700	570	1100	1400
29	8.0	57.0	520	1400	2200	500	1100	1200
30	8.0	78.0	470	950	1700	480	860	1600
31	7.0	38.0	430	380	820	420	270	370
32	7.0	41.0	470	470	980	470	440	660
33	5.0	9.0	520	300	590	510	180	240
Comp. Ex. 6	15.4	0.9	1500	300	390	1400	190	190
Comp. Ex. 10	61.3	1.0	2400	620	870	2100	370	320
Comp. Ex. 11	1.1	14.9	390	1200	1700	400	1100	1100

These examples illustrate that extruded spacing layers on larger optical elements (165 microns) provide improved  $R_L$  values in the rain (slow water drainage) than the solvent coated spacing layers of Examples 18-23. The examples also illustrate that the spacing layer articles can have better dry and raining  $R_L$  values than specular reflective pigment systems (Comparative Examples 10 and 11).

5

### Examples 34-39

Samples were prepared as described in Examples 24-33 substituting a diffuse reflective layer onto the back of the spacing layer in place of the aluminum vaporcoat.

10

The diffuse reflective layer consisted of a 27% by weight titanium dioxide-filled polyurethane as described in Comparative Example 4. The coefficient of retroreflection ( $R_A$ ) was measured. Retroreflective elements were then made as previously described. A pavement marking article was then made from the retroreflective elements as previously described. The coefficient of retroreflected luminance  $R_L$  was then measured for the

15

pavement marking articles.

EXAMPLE	OPTICAL ELEMENT REFRACTIVE INDEX	OPTICAL ELEMENT TYPE	AVG. SIZE MICRONS	SPACING LAYER	REFLECTIVE LAYER
34	1.91	CERAMIC	165	50 MICRON EXTRUDED	TiO <sub>2</sub>
35	1.91	CERAMIC	165	63 MICRON EXTRUDED	TiO <sub>2</sub>
36	1.91	CERAMIC	165	75 MICRON EXTRUDED	TiO <sub>2</sub>
37	1.91	CERAMIC	165	88 MICRON EXTRUDED	TiO <sub>2</sub>
38	1.91	CERAMIC	165	100 MICRON EXTRUDED	TiO <sub>2</sub>
39	1.91	CERAMIC	165	113 MICRON EXTRUDED	TiO <sub>2</sub>
Comp. Ex. 6	1.91	CERAMIC	165	113 MICRON EXTRUDED	TiO <sub>2</sub>

EXAMPLE	COEFFICIENT OF RETRO- REFLECTION (Cd/LX/M <sup>2</sup> )		CALCULATED COEFFICIENT OF RETROREFLECTED LUMINANCE - R <sub>L</sub> (mCd/m <sup>2</sup> /Lx)					
			FAST WATER DRAINAGE			SLOW WATER DRAINAGE		
	DRY	WET	DRY	RAIN	RECOVERY	DRY	RAIN	RECOVERY
34	8.9	1.6	1000	290	370	770	200	230
35	7.6	2.1	650	430	600	480	300	330
36	7.0	3.0	490	480	670	380	370	530
37	6.4	3.8	430	510	680	330	380	480
38	6.7	4.5	400	490	620	320	400	550
39	6.9	4.7	330	320	440	270	250	370
Comp. Ex. 6	15.4	0.9	1500	300	390	1400	190	190

These examples illustrate how highly efficient patterned pavement marking articles having titanium dioxide reflective layers (Comparative Example 6) can be improved using a spacing layer between the optical element layer and the reflective layer. Excellent contrast in the rain (slow water drainage) can be obtained with dry performance better than most newly painted lines.

#### Examples 40-45

Samples were prepared as described in Examples 34-39. A pearlescent pigmented polyurethane layer (35% by weight pearlescent pigment-filled polyurethane as described in Comparative Examples 9-11) was coated onto the back of the spacing layer in place of the aluminum vaporcoat. The coefficient of retroreflection (R<sub>A</sub>) was measured. Retroreflective elements were then made as previously described. A pavement marking article was then made from the retroreflective elements as previously described. The coefficient of retroreflected luminance R<sub>L</sub> was then measured for the pavement marking articles.

EXAMPLE	OPTICAL ELEMENT REFRACTIVE INDEX	OPTICAL ELEMENT TYPE	Avg. Size Microns	SPACING LAYER	REFLECTIVE LAYER
40	1.91	CERAMIC	165	50 MICRON EXTRUDED	PEARL
41	1.91	CERAMIC	165	63 MICRON EXTRUDED	PEARL
42	1.91	CERAMIC	165	75 MICRON EXTRUDED	PEARL
43	1.91	CERAMIC	165	88 MICRON EXTRUDED	PEARL
44	1.91	CERAMIC	165	100 MICRON EXTRUDED	PEARL
45	1.91	CERAMIC	165	113 MICRON EXTRUDED	PEARL
Comp. Ex 10	1.91	CERAMIC	165	NONE	PEARL

EXAMPLE	COEFFICIENT OF RETRO-REFLECTION (Cd/LX/M <sup>2</sup> )		CALCULATED COEFFICIENT OF RETROREFLECTED LUMINANCE - R <sub>L</sub> (mCd/m <sup>2</sup> /Lx)					
			FAST WATER DRAINAGE			SLOW WATER DRAINAGE		
	-4/0.2	-4/0.2	DRY	RAIN	RECOVERY	DRY	RAIN	RECOVERY
40	13.3	1.4	1400	330	430	1200	250	250
41	11.0	2.0	940	410	560	800	370	420
42	8.6	5.2	510	560	780	470	520	670
43	7.4	10.9	440	700	980	330	470	580
44	6.9	30.3	330	320	460	270	320	480
45	6.2	8.8	330	300	410	270	180	220
10 (Comparative)	61.3	1.0	2400	620	870	2100	370	320

These examples illustrate how highly efficient patterned pavement marking articles having specular reflective pigment reflective layers (Comparative Example 10) can be improved by using a spacing layer between the optical element layer and the reflective layer.

5

Excellent contrast in the rain (slow water drainage) can be obtained with dry performance being better than most newly painted lines.

#### Examples 46-55

10 Samples were prepared as described in Examples 24-33. 275 micron average diameter glass optical elements were substituted for the ceramic optical elements of Examples 24-33. The spacing layer thickness ranged from about 62.5 to about 225 microns. The coefficient of retroreflection (R<sub>A</sub>) was measured. Retroreflective elements were then made as previously described. A pavement marking article was then made from

the retroreflective elements as previously described. The coefficient of retroreflected luminance  $R_L$  was then measured on the pavement marking article.

EXAMPLE	OPTICAL ELEMENT REFRACTIVE INDEX	OPTICAL ELEMENT TYPE	AVG. SIZE MICRONS	SPACING LAYER	REFLECTIVE LAYER
46	1.91	GLASS	275	63 MICRON EXTRUDED	Al VAPORCOAT
47	1.91	GLASS	275	88 MICRON EXTRUDED	Al VAPORCOAT
48	1.91	GLASS	275	100 MICRON EXTRUDED	Al VAPORCOAT
49	1.91	GLASS	275	113 MICRON EXTRUDED	Al VAPORCOAT
50	1.91	GLASS	275	125 MICRON EXTRUDED	Al VAPORCOAT
51	1.91	GLASS	275	138 MICRON EXTRUDED	Al VAPORCOAT
52	1.91	GLASS	275	150 MICRON EXTRUDED	Al VAPORCOAT
53	1.91	GLASS	275	175 MICRON EXTRUDED	Al VAPORCOAT
54	1.91	GLASS	275	200 MICRON EXTRUDED	Al VAPORCOAT
55	1.91	GLASS	275	250 MICRON EXTRUDED	Al VAPORCOAT
Comp. Ex. 10	1.91	CERAMIC	165	NONE	PEARL

EXAMPLE	CALCULATED COEFFICIENT OF RETROREFLECTED LUMINANCE – $R_L$ (mCd/m <sup>2</sup> /Lx)							
	COEFFICIENT OF RETRO-REFLECTION (Cd/Lx/m <sup>2</sup> )		FAST WATER DRAINAGE			SLOW WATER DRAINAGE		
	DRY	WET	DRY	RAIN	RECOVERY	DRY	RAIN	RECOVERY
46	52.0	1.0	3400	410	720	3900	250	360
47	36.0	1.0	2700	420	750	3000	340	450
48	9.2	5.0	1400	570	990	1500	580	870
49	6.9	8.0	990	1200	1700	1100	1100	1500
50	4.8	15.0	830	1400	1800	920	1400	2200
51	4.2	24.0	630	1800	2100	680	1700	2700
52	3.4	54.0	610	1800	2400	610	1700	2700
53	3.0	69.0	510	1300	2100	590	1100	1300
54	2.9	17.6	500	580	850	590	390	710
55	2.8	5.1	480	300	470	630	250	280
Comp. Ex. 10	61.3	1.0	2400	620	870	2100	370	320

These examples illustrate that large (275 micron) optical elements can have a spacing layer successfully applied by extrusion. Highly desirably dry and raining  $R_L$  values can be obtained.

**Examples 56-66**

Samples were prepared as described in Examples 24-33. 460 micron average diameter glass optical elements were substituted for the ceramic optical elements of Examples 24-33. The spacing layer thickness ranged from about 100 to about 300 microns. The coefficient of retroreflection ( $R_A$ ) was measured. Retroreflective elements were then made as previously described. A pavement marking article was then made from the retroreflective elements as previously described. The coefficient of retroreflected luminance  $R_L$  was then measured for the pavement marking articles.

10

EXAMPLE	OPTICAL ELEMENT REFRACTIVE INDEX	OPTICAL ELEMENT TYPE	AVG. SIZE MICRONS	SPACING LAYER	REFLECTIVE LAYER
56	1.91	GLASS	460	100 MICRON EXTRUDED	Al VAPORCOAT
57	1.91	GLASS	460	113 MICRON EXTRUDED	Al VAPORCOAT
58	1.91	GLASS	460	125 MICRON EXTRUDED	Al VAPORCOAT
59	1.91	GLASS	460	138 MICRON EXTRUDED	Al VAPORCOAT
60	1.91	GLASS	460	150 MICRON EXTRUDED	Al VAPORCOAT
61	1.91	GLASS	460	175 MICRON EXTRUDED	Al VAPORCOAT
62	1.91	GLASS	460	200 MICRON EXTRUDED	Al VAPORCOAT
63	1.91	GLASS	460	225 MICRON EXTRUDED	Al VAPORCOAT
64	1.91	GLASS	460	250 MICRON EXTRUDED	Al VAPORCOAT
65	1.91	GLASS	460	275 MICRON EXTRUDED	Al VAPORCOAT
66	1.91	GLASS	460	300 MICRON EXTRUDED	Al VAPORCOAT
Comp. Ex. 10	1.91	CERAMIC	165	NONE	PEARL

EXAMPLE	COEFFICIENT OF RETRO-REFLECTION (Cd/LX/M <sup>2</sup> )		CALCULATED COEFFICIENT OF RETROREFLECTED LUMINANCE - R <sub>L</sub> (mCd/m <sup>2</sup> /Lx)					
	DRY	WET	FAST WATER DRAINAGE			SLOW WATER DRAINAGE		
	-4/0.2	-4/0.2	DRY	RAIN	RECOVERY	DRY	RAIN	RECOVERY
56	27.9	2.0	2700	650	760	3200	430	670
57	17.0	3.0	2100	650	750	2100	540	750
58	18.0	3.0	1900	660	700	2300	500	740
59	11.0	4.0	1500	690	840	1700	510	850
60	10.0	5.0	1200	740	870	1300	710	940
61	5.0	8.4	910	860	1300	1100	1000	1400
62	3.8	20.3	630	1300	1600	730	1200	1700
63	3.4	36.1	590	1500	2100	690	1200	2100
64	3.2	71.2	540	1100	2000	570	1100	1800
65	3.2	80.7	590	1600	2400	600	1000	2000
66	3.0	41.6	550	670	1000	570	460	800
Comp. Ex. 10	61.3	1.0	2400	620	870	2100	370	320

These examples illustrate that very large (460 micron) optical elements can have a spacing layer successfully applied by extrusion. Highly desirable dry and raining R<sub>L</sub> values can be obtained.

5

#### Examples 67-74

Ceramic optical elements (refractive index 1.91) having an average diameter of about 165 microns were partially embedded into a polyethylene coated polyester film by flood coating in an oven at 135°C to about 30% of their average diameter. The optical elements were wetted with a 0.15% dilute aqueous solution of gamma-aminopropyltriethoxysilane (obtained from Union Carbide Corporation; Danbury, CT), then dried in an oven at about 120°C. A pressure-sensitive adhesive was used to laminate the optical element film composite to an aluminum panel using a handroller. The aluminum panel was used to provide electrical grounding to the substrate during the powder coating operation. The aluminum panel measured about 15.2 centimeters by about 30.5 centimeters, roughly equivalent to a standard license plate. The optical element film was then electrostatically powder coated with a powder of approximate 30 micron particle size made from Elvacite™ 2013 (an acrylic copolymer available from ICI Acrylics Inc., Cordova, TN). A Nordson electrostatic powder spray gun operating at +80 kilovolts was mounted about 40 cm above electrically grounded rollers. The aluminum panel to which the optical element film was laminated was placed on the grounded rollers. The grounded

rollers were driven at different speeds to affect the powder coating weight. Powder coating weights ranged from about 3.4 grams to about 6.6 grams for the 15 centimeters by 30 centimeters panel.

Assuming a 165 micron optical element average diameter size, perfect packing of the 5 optical elements in the optical element carrier, a theoretical optimum spacing layer thickness of 71% of the radius, and a specific gravity of the Elvacite™ 2013 powder of 1.15, then the calculated theoretical mass of Elvacite™ 2013 powder is 5.5 grams per license plate.

Immediately after spraying, the powder coatings were fused onto the optical 10 elements, conveyed through a series of ovens having heater temperatures at about 245°C, about 255°C, and about 320°C for a total time of about 3 minutes. The web temperature ranged from about 120°C and 150°C. The spacing layer was then vaporcoated with about 900 angstroms of aluminum as described in Examples 12-17. The vaporcoat side was then coated with an epoxy onto a rigid piece of aluminum. After the epoxy was cured, the 15 polyethylene coated polyester optical element carrier was stripped off of the optical elements. The coefficient of retroreflection,  $R_A$ , was measured at -4.0/0.2 for both dry and under water conditions. The results are given in the following table:

Example	Powder coating weight per 15 cm by 30 cm	Coefficient of Retroreflection, $R_A$ , in cd/lx/m <sup>2</sup>	
		-4.0/0.2 Dry	-4.0/0.2 Wet
67	6.6 grams	6.9	7.2
68	6.1 grams	6.8	18
69	5.5 grams	4.9	27
70	5.0 grams	8.4	44
71	4.3 grams	15	34
72	4.0 grams	8.3	11
73	3.4 grams	23	3.2
74	3.0 grams	19	4.8

These examples illustrate that spacing layer can be applied to moderate sized optical elements (165 microns) by using powder coating.

**Example 75**

5 To form a white base layer material, the ingredients in the following table were mixed in a Banbury internal mixer where they reached an internal temperature of approximately 150°C. The material was then cooled on a rubber mill and calendered into a sheet having a thickness of about 1.4 millimeters.

COMPONENT	PARTS
Acrylonitrile-butadiene non-crosslinked elastomer precursor (NIPOLE™ 1022, Zeon Chemicals, Inc.; Louisville, KY)	100
Talc platelet filler particles averaging 2 microns in size (MISTRON SUPERFROST™, Luzenac America, Inc.; Englewood, CO)	100
3 denier polyester filament 6 mm long (SHORT STUFF™ 6-3025, Mini Fibers, Inc.; Johnson City, TN)	10
Fibers of high-density polyethylene having a molecular weight ranging between 30,000 and 150,000 (SHORT STUFF™ 13038F, Mini Fibers, Inc.)	20
Phenol type anti-oxidant (SANTO WHITE™ crystals, Monsanto Co.; Nitro, WV)	2
Chlorinated paraffin (CHLOREZ™ 700S, Dover Chemical Corp.; Dover, OH)	70
Chlorinated paraffin (PAROIL™ 140LV, Dover Chemical Corp.; Lake Charles, LA)	5
Spherical silica reinforcing filler (HISIL™ 233, PPG Industries, Inc.; Lake Charles, LA)	20
Stearic acid processing aide (Hamko Chemical; Memphis, TN)	1.0
Chelator (VANSTAY™ SC, R.T. Vanderbilt Company, Inc.; Norwalk, CT)	0.5
Ultramarine blue 5016 (Whittaker, Clark & Daniels, Inc.; South Plainfield, NJ)	0.5
Rutile titanium dioxide pigment (TIPURE™ R-960, E. I. duPont de Nemours; New Johnsonville, TN)	130
Transparent glass microspheres averaging about 100 microns in diameter and having a refractive index of 1.5 (Flex-O-Lite, Inc.; Muscatine, IA)	280
<b>TOTAL</b>	<b>739</b>

A thermoplastic topcoat was prepared by extruding a pigment concentrate blended with a thermoplastic. The pigment concentrate consists of 50% rutile titanium dioxide

compounded with 50% ethylene methacrylic acid copolymer (NUCREL™ 699, E. I. duPont de Nemours, Wilmington, Del.). The pigment concentrate was supplied by M.A. Hanna Color, Elk Grove Village, IL. 40% of the pigment concentrate was blended with 60% of additional NUCREL™ 699 and extruded to a thickness of about 1.1 millimeters.

5 The extrusion was trimmed to a width of about 15 centimeters.

The spacing layer-coated and vapor-coated optical elements of Example 15 were cut into stripes about 1 centimeters wide and 15 centimeters long. The vaporcoat side of the film was laminated transversely on the extruded thermoplastic topcoat. The spacing layer coated stripes were spaced about 6 centimeters apart. The thermoplastic topcoat was

10 heated to about 100°C. At this temperature the vaporcoat adhered tightly to the topcoat.

A 15 centimeters wide white base layer material was passed over a hot roll and heated to a temperature of about 140°C. The base layer was then passed through an embossing nip. The pattern on the embossing roll was the same as is used in the production of 3M STAMARK™ High Performance Pavement Marking Tape Series 380, available from 3M. The embossing roll was maintained at a temperature of about 40°C.

15 The anvil roll was maintained at a temperature of about 25°C. The base layer was embossed at a pressure of about 8000 Newtons/cm. The thermoplastic topcoat with the laminated spacing layer was fed over the pattern roll into the embossing nip. The spacing layer side of the topcoat was against the pattern roll. Immediately after embossing the thermoplastic topcoat to the base layer the pavement marking product was cooled to room temperature. When viewed with a flashlight, the spacing layer-coated optical elements had very good dry retroreflectivity. The pavement marking was then submersed in water. When viewed with a flashlight the spacing layer-coated optical elements had improved retroreflectivity.

20 25

#### Examples 76-84

Glass optical elements having a refractive index of about 1.5 were embedded in the extruded spacing layer of Examples 24-66. The spacing layer thickness was varied from about 50 to about 150 microns. The glass optical elements were embedded and cupped by the extruded spacing layer in a similar manner as Examples 24-66 except the temperature was about 175°C. After cupping the spacing layer, the films were vaporcoated with about 900 angstroms of aluminum. The coefficient of retroreflection ( $R_A$ ) was measured.

30

Retroreflective elements were then made as previously described. A pavement marking article was then made from the retroreflective elements as previously described. The coefficient of retroreflected luminance  $R_L$  was then measured for the pavement marking articles.

5

EXAMPLE	OPTICAL ELEMENT REFRACTIVE INDEX	OPTICAL ELEMENT TYPE	AVG. SIZE MICRONS	SPACING LAYER	REFLECTIVE LAYER
76	1.5	GLASS	200	50 MICRON EXTRUDED	Al VAPORCOAT
77	1.5	GLASS	200	63 MICRON EXTRUDED	Al VAPORCOAT
78	1.5	GLASS	200	75 MICRON EXTRUDED	Al VAPORCOAT
79	1.5	GLASS	200	88 MICRON EXTRUDED	Al VAPORCOAT
80	1.5	GLASS	200	100 MICRON EXTRUDED	Al VAPORCOAT
81	1.5	GLASS	200	113 MICRON EXTRUDED	Al VAPORCOAT
82	1.5	GLASS	200	125 MICRON EXTRUDED	Al VAPORCOAT
83	1.5	GLASS	200	138 MICRON EXTRUDED	Al VAPORCOAT
84	1.5	GLASS	200	150 MICRON EXTRUDED	Al VAPORCOAT

EXAMPLE	COEFFICIENT OF RETROREFLECTION IN Cd/LX/M <sup>2</sup>		CALCULATED COEFFICIENT OF RETROREFLECTED LUMINANCE - $R_L$ (mCd/m <sup>2</sup> /Lx)		
	DRY	WET	SLOW WATER DRAINAGE		
	-4.0/0.2	-4.0/0.2	DRY	RAIN	RECOVERY
76	5.3	0.5			
77	9.5	0.8			
78	11	1.0			
79	22	1.3			
80	37	1.6			
81	63	2.0			
82	150	2.5	1500	120	180
83	110	2.7			
84	51	3.1			
Comp. Ex. 8	1.3	0.4	220	50	67

These examples illustrate the large increase in dry  $R_L$  that can be achieved by inserting a spacing layer between a 1.5 refractive index optical element layer and a reflective layer.

10 By using a spacing layer, dry retroreflectivity can be significantly improved using conventional glass optical elements which are the industry standard.

Examples 85-92

Ceramic optical elements having a refractive index of about 1.75 were embedded in the extruded spacing layer of Examples 24-66. The spacing layer thickness was varied from about 50 to about 88 microns. The glass optical elements were embedded and cupped by the extruded spacing layer in a similar manner as Examples 24-66 except the temperature was about 175°C. After cupping the spacing layer, the films were vaporcoated with about 900 angstroms of aluminum as described in Examples 12-17. The coefficient of retroreflection ( $R_A$ ) was measured. Retroreflective elements were then made as previously described. A pavement marking article was then made from the retroreflective elements as previously described. The coefficient of retroreflected luminance  $R_L$  was then measured for the pavement marking articles.

EXAMPLE	OPTICAL ELEMENT REFRACTIVE INDEX	OPTICAL ELEMENT TYPE	AVG. SIZE MICRONS	SPACING LAYER	REFLECTIVE LAYER
85	1.75	CERAMIC	200	50 MICRON EXTRUDED	Al VAPORCOAT
86	1.75	CERAMIC	200	63 MICRON EXTRUDED	Al VAPORCOAT
87	1.75	CERAMIC	200	75 MICRON EXTRUDED	Al VAPORCOAT
88	1.75	CERAMIC	200	88 MICRON EXTRUDED	Al VAPORCOAT
89	1.75	CERAMIC	250	50 MICRON EXTRUDED	Al VAPORCOAT
90	1.75	CERAMIC	250	63 MICRON EXTRUDED	Al VAPORCOAT
91	1.75	CERAMIC	250	75 MICRON EXTRUDED	Al VAPORCOAT
92	1.75	CERAMIC	250	88 MICRON EXTRUDED	Al VAPORCOAT

EXAMPLE	COEFFICIENT OF RETROREFLECTION IN Cd/LX/M <sup>2</sup>		CALCULATED COEFFICIENT OF RETROREFLECTED LUMINANCE - R <sub>L</sub> (mCd/m <sup>2</sup> /Lx)		
	DRY	WET	SLOW WATER DRAINAGE		
	-4.0/0.2	-4.0/0.2	DRY	RAIN	RECOVERY
87	180	1.7	1700	130	130
88	60	2.3			
89	56	1.2			
90	12	5.0			
91	80	0.7			
92	130	1.0			
93	60	2.0			
94	60	2.5			
Comp. Ex. 5	8.5	0.8	950	140	100

These examples illustrate the large increase in dry R<sub>L</sub> that can be achieved by inserting a spacing layer between a 1.75 refractive index optical element and a reflective layer.

5

### Examples 93-97

Ceramic optical elements having a refractive index of about 1.91 were screened to an average size of about 165 microns. Glass optical elements having a refractive index of about 1.5 were screened to an average size of about 165 microns. Mixtures of the optical elements were embedded in the extruded spacing layer of Examples 24-66. The spacing layer thickness was about 113 microns. The optical element mixture was embedded and cupped by the extruded spacing layer in a similar manner as Examples 24-66. After cupping the spacing layer, the films were vaporcoated with about 900 angstroms of aluminum as described in Examples 12-17. The coefficient of retroreflection (R<sub>A</sub>) was measured. Retroreflective elements were then made as previously described. A pavement marking article was then made from the retroreflective elements as previously described. The coefficient of retroreflected luminance R<sub>L</sub> was then measured for the pavement marking articles.

EXAMPLE	WT. % 1.91 $N_D$ CERAMIC	WT. % 1.5 $N_D$ GLASS	AREA % 1.91 $N_D$ CERAMIC	AVG. SIZE MICRONS	SPACING LAYER	REFLECTIVE LAYER
93	0%	100%	0%	165	113 MICRON EXTRUDED	Al VAPORCOAT
94	34.8%	65.2%	25%	165	113 MICRON EXTRUDED	Al VAPORCOAT
95	61.5%	38.5%	50%	165	113 MICRON EXTRUDED	Al VAPORCOAT
96	82.8%	17.2%	75%	165	113 MICRON EXTRUDED	Al VAPORCOAT
97	100%	0%	100%	165	113 MICRON EXTRUDED	Al VAPORCOAT

EXAMPLE	COEFFICIENT OF RETROREFLECTION IN Cd/LX/M <sup>2</sup>		CALCULATED COEFFICIENT OF RETROREFLECTED LUMINANCE - $R_L$ (mCd/m <sup>2</sup> /Lx)		
	DRY	WET	SLOW WATER DRAINAGE		
	-4.0/0.2	-4.0/0.2	DRY	RAIN	RECOVERY
93	49	1.8			
94	31	8.6			
95	34	19			
96	17	35	530	200	280
97	3.0	57			
Comp. Ex. 5	8.5	0.8	950	140	100
Comp. Ex. 8	1.3	0.4	220	50	67

These examples illustrate that the dry and raining  $R_L$  performance for a diffuse reflecting optical system with low refractive index optical elements (Comparative Example 8) can be significantly increased by using a spacing layer between a mixture of low (1.5) and high (1.9) refractive index optical elements and the reflective layer.

### Examples 98-102

10 Ceramic optical elements having a refractive index of about 1.91 were screened to an average size of about 165 microns. Ceramic optical elements having a refractive index of about 1.75 were screened to an average size of about 350 microns. Mixtures of the optical elements were embedded in the extruded spacing layer of Examples 24-66. The spacing layer thickness was about 100 microns. The optical element mixture was 15 embedded and cupped by the extruded spacing layer in a manner similar to Examples 24-66. After cupping the spacing layer, the films were vaporcoated with about 900 angstroms of aluminum as described in Examples 12-17. The coefficient of retroreflection ( $R_A$ ) was measured. Retroreflective elements were then made as previously described. A pavement marking article was then made from the retroreflective elements as previously described.

The coefficient of retroreflected luminance  $R_L$  was then measured for the pavement marking articles.

EXAMPLE	WT. % 1.91 $N_D$ CERAMIC 165 MICRONS AVG. SIZE	WT. % 1.75 $N_D$ CERAMIC 350 MICRONS AVG. SIZE	AREA % 1.91 $N_D$ CERAMIC 165 MICRON AVG. SIZE	SPACING LAYER	REFLECTIVE LAYER
98	0%	100%	0%	100 MICRON EXTRUDED	Al VAPORCOAT
99	13.5%	86.5%	25%	100 MICRON EXTRUDED	Al VAPORCOAT
100	31.8%	68.2%	50%	100 MICRON EXTRUDED	Al VAPORCOAT
101	58.4%	41.6%	75%	100 MICRON EXTRUDED	Al VAPORCOAT
102	100%	0%	100%	100 MICRON EXTRUDED	Al VAPORCOAT

EXAMPLE	COEFFICIENT OF RETROREFLECTION IN $Cd/Lx/m^2$		CALCULATED COEFFICIENT OF RETROREFLECTED LUMINANCE - $R_L$ ( $mCd/m^2/Lx$ )		
	DRY	WET	SLOW WATER DRAINAGE		
	-4.0/0.2	-4.0/0.2	DRY	RAIN	RECOVERY
98	140	0.90			
99	110	14			
100	85	27			
101	46	47	730	480	600
102	7.4	51			
Comp. Ex. 5	8.5	0.8	950	140	100
Comp. Ex. 6	15.4	0.9	1400	190	190

5

These examples illustrate that excellent contrast (both dry and wet) can be obtained using a blend of small high refractive index optical elements (165 micron, 1.9 refractive index) with large medium refractive index (350 micron, 1.75 refractive index). Diffuse reflecting medium and high refractive index optical elements (5 and 6 comparative) cannot achieve this level of wet  $R_L$  performance.

10

Various modifications and alterations of this invention will become apparent to those skilled in the art without departing from the scope and spirit of this invention, and it should be understood that this invention is not to be unduly limited to the illustrative embodiments set forth herein.

15

**Claims:**

1. A pavement marking article comprising a monolayer of exposed-lens optical elements and a reflective layer, characterized in that there is a spacing layer between the optical elements and the reflective layer.  
5
2. A pavement marking article according to any preceding claim, further characterized in that said optical elements have an average diameter ranging from about 50 micrometers to about 1000 micrometers.  
10
3. A pavement marking article according to any preceding claim, further characterized in that said optical elements have an exposed surface and an embedded surface, and said spacing layer is layered on the embedded surface of said optical elements.  
15
4. A pavement marking article according to any preceding claim, further characterized in that said spacing layer comprises material selected from the group consisting of polyvinyl butyral, polyurethanes, polyesters, acrylics, acid olefin copolymers, polyvinyl chloride and its copolymers, epoxies, polycarbonates, and mixtures thereof.  
20
5. A pavement marking article according to any preceding claim, further characterized in that said spacing layer has a refractive index ranging from about 1.4 to about 1.7.  
25
6. A pavement marking article according to any preceding claim, further characterized in that said spacing layer has an average thickness of about 0.05 to about 1.4 times the average radius of said optical elements.
- 30 7. A pavement marking article according to any preceding claim, further characterized in that said spacing layer has the same average thickness downweb and crossweb.

8. A pavement marking article according to any of claims 1 to 6, further characterized in that said spacing layer has two or more thicknesses downweb.

5 9. A pavement marking article according to any of claims 1 to 6 or 8, further characterized in that said spacing layer has two or more thicknesses crossweb.

10 10. A pavement marking article according to any preceding claim, further characterized in that said spacing layer cups around said optical elements.




10 11. A pavement marking article according to any preceding claim, further characterized in that said reflective layer comprises a diffuse pigment selected from the group consisting of titanium dioxide, zinc oxide, zinc sulfide, lithophane, zirconium silicate, zirconium oxide, natural and synthetic barium sulfates, and mixtures thereof.


15 12. A pavement marking article according to any preceding claim, further characterized in that said reflective layer comprises a specular reflector selected from the group consisting of specular pigment, a metallized layer, or a dielectric material.

20 13. A pavement marking article according to any preceding claim, further characterized in that said article is a preformed flat or patterned pavement marking tape.


25 14. A pavement marking article according to any preceding claim, further characterized in that when said optical elements are coated with water the retroreflectivity of said article increases.

30 15. A method of making a retroreflective pavement marking tape comprising exposed lens optical elements, characterized by the step of embossing a film comprising a pavement article according to any of claims 1 to 12 or 14 onto a preformed pavement marking tape.

**Fig. 1****Fig. 2****Fig. 3**



**Fig. 4**



**Fig. 5**




Fig. 6




Fig. 7




Fig. 8

# INTERNATIONAL SEARCH REPORT

International Application No

T U I /US 99/17562

**A. CLASSIFICATION OF SUBJECT MATTER**  
IPC 7 E01F9/04

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 E01F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 683 403 A (MINNESOTA MINING & MFG) 22 November 1995 (1995-11-22) column 3, line 21 - line 57 column 4, line 55 -column 8, line 34; figures 2,4,5 ---	1-5, 10-13 6-9,14
A	EP 0 385 746 A (SEIBULITE INT INC) 5 September 1990 (1990-09-05) page 2, line 36 - line 55  page 3, line 21 -page 4, line 19 page 8, line 19 - line 23; figures 1,2 ---	1,2,4,14  3,5-13, 15  -/-
X		
A		



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

24 November 1999

Date of mailing of the international search report

01/12/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Verveer, D

## INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 99/17562

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 97 01676 A (MINNESOTA MINING & MFG) 16 January 1997 (1997-01-16) page 1, line 24 -page 2, line 4 page 12, line 4 - line 16 page 13, line 23 - line 28 page 14, line 23 -page 16, line 7 page 18, line 1 - line 14; figures 4-7 ----	1, 2, 5-9, 14
A	US 4 505 967 A (BAILEY TERRY R) 19 March 1985 (1985-03-19) column 1, line 29 - line 44 column 9, line 12 -column 11, line 28 ----	3, 4
A	US 5 759 928 A (HARPER JAMES H C) 2 June 1998 (1998-06-02) ----	1-14
A	US 5 417 515 A (K.A. HACHEY ET AL) 23 May 1995 (1995-05-23) -----	

**INTERNATIONAL SEARCH REPORT**

Information on patent family members

International Application No

PCT/US 99/17562

Patent document cited in search report	Publication date	Patent family member(s)		Publication date
EP 0683403	A 22-11-1995	CA 2147791 A		21-11-1995
		JP 8060627 A		05-03-1996
EP 0385746	A 05-09-1990	JP 2228692 A		11-09-1990
		JP 8023739 B		06-03-1996
		AT 82785 T		15-12-1992
		CA 2011055 A,C		01-09-1990
		DK 52690 A		02-09-1990
		HK 70793 A		30-07-1993
		NO 900938 A		03-09-1990
		PT 93295 A		15-10-1991
		SG 33393 G		21-05-1993
WO 9701676	A 16-01-1997	AT 184939 T		15-10-1999
		AT 184941 T		15-10-1999
		AU 6342896 A		30-01-1997
		AU 698325 B		29-10-1998
		AU 6397596 A		30-01-1997
		AU 6398996 A		30-01-1997
		BR 9608630 A		15-06-1999
		BR 9608636 A		15-06-1999
		BR 9609161 A		04-05-1999
		CA 2222565 A		16-01-1997
		CA 2224524 A		16-01-1997
		CA 2224650 A		16-01-1997
		DE 69604401 D		28-10-1999
		DE 69604404 D		28-10-1999
		EP 0835350 A		15-04-1998
		EP 0835346 A		15-04-1998
		EP 0835351 A		15-04-1998
		JP 11508979 T		03-08-1999
		JP 11508653 T		27-07-1999
		NO 975443 A		26-02-1998
		NO 975795 A		02-03-1998
		NO 975796 A		02-03-1998
		WO 9701673 A		16-01-1997
		WO 9701679 A		16-01-1997
		US 5880885 A		09-03-1999
		US 5837350 A		17-11-1998
		AT 184940 T		15-10-1999
		AU 6342596 A		30-01-1997
		BR 9609339 A		11-05-1999
		CA 2222587 A		16-01-1997
		DE 69604402 D		28-10-1999
		EP 0835349 A		15-04-1998
		JP 11508654 T		27-07-1999
		NO 975442 A		02-03-1998
		WO 9701677 A		16-01-1997
US 4505967	A 19-03-1985	AT 50423 T		15-02-1990
		AT 129578 T		15-11-1995
		AU 593713 B		15-02-1990
		AU 1137488 A		12-05-1988
		AU 568353 B		24-12-1987
		AU 2669184 A		18-10-1984
		BR 8401644 A		20-11-1984
		CA 1236720 A		17-05-1988
		DE 3486411 D		30-11-1995

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

F01/US 99/17562

Patent document cited in search report	Publication date	Patent family member(s)			Publication date
US 4505967	A	DE	3486411	T	20-06-1996
		EP	0125038	A	14-11-1984
		EP	0326186	A	02-08-1989
		JP	8027402	B	21-03-1996
		JP	59198402	A	10-11-1984
		JP	8211213	A	20-08-1996
		US	4950525	A	21-08-1990
		US	4648932	A	10-03-1987
-----					
US 5759928	A	02-06-1998	CA	2147711	A
			EP	0683268	A
			JP	8047995	A
-----					
US 5417515	A	23-05-1995	AU	683751	B
			AU	2429595	A
			BR	9507641	A
			CA	2189022	A
			CN	1148421	A
			EP	0760883	A
			JP	10504076	T
			WO	9532337	A
			US	5571362	A
			US	5750191	A
-----					