

(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
26 June 2008 (26.06.2008)

PCT

(10) International Publication Number
WO 2008/076071 A1

(51) International Patent Classification:

D21H 17/65 (2006.01) *D21H 17/67* (2006.01)
D21H 17/66 (2006.01) *D21H 21/10* (2006.01)

39 Kungälv (SE). **GUTKE, Katarina** [SE/SE]; Södra Bergsätervägen 8, S-430 33 Fjärås (SE).

(21) International Application Number:

PCT/SE2007/051032

(74) **Agent:** **NYANDER, Johan**; Eka Chemicals AB, Intellectual Property, P.O. Box 11556, S-100 61 Stockholm (SE).

(22) International Filing Date:

18 December 2007 (18.12.2007)

(81) **Designated States** (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

06126786.0 21 December 2006 (21.12.2006) EP
 60/876,369 21 December 2006 (21.12.2006) US

(71) **Applicant** (for all designated States except US): **AKZO NOBEL N.V.** [NL/NL]; P.O. Box 9300, NL-6800 SB Arnhem (NL).

(71) **Applicant** (for SE only): **EKA CHEMICALS AB** [SE/SE]; -, (no street address), S-445 80 Bohus (SE).

(72) **Inventors; and**

(75) **Inventors/Applicants** (for US only): **SIMONSSON, Patrik** [SE/SE]; Lundvägen 6, S-433 64 Sävedalen (SE). **TOKARZ, Marek** [SE/SE]; Håkons gata 4, S-442

(84) **Designated States** (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, MT, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

(54) Title: PROCESS FOR THE PRODUCTION OF CELLULOSIC PRODUCT

(57) **Abstract:** The present invention relates to a process for the production of a cellulosic product which comprises providing an aqueous thick suspension containing cellulosic fibers having a fiber concentration of at least about 2% by weight; adding to the thick suspension an aluminum compound, alkaline earth metal salt and acid; diluting the obtained thick suspension to form a thin suspension; adding to the thin suspension one or more drainage and retention aids; and dewatering the obtained thin suspension. The invention further relates to a process for the production of a cellulosic product which comprises providing an aqueous thick suspension containing cellulosic fibers having a fiber concentration of at least about 2% by weight and an alkaline earth metal ion concentration of at least about 100 mg/l; adding to the thick suspension an aluminum compound and optionally an acid to obtain a pH of from about 4 to about 5.5; diluting the obtained thick suspension to form a thin suspension; adding to the thin suspension one or more drainage and retention aids; and dewatering the obtained thin suspension. The invention also relates to an aqueous composition comprising a mixture of an aluminum compound, alkaline earth metal salt and acid and the use of the composition.

PROCESS FOR THE PRODUCTION OF CELLULOSIC PRODUCTField of the Invention

5 The present invention relates to a process for the production of a cellulosic product. More specifically, the invention relates to a process for the production of a cellulosic product which comprises adding certain additives to an aqueous suspension containing cellulosic fibers before it is dewatered to form the cellulosic product.

10

Background of the Invention

In the papermaking art, an aqueous suspension containing cellulosic fibers, and optional fillers and additives, is fed into a headbox which ejects the suspension onto a forming wire. Water is drained from the suspension through the forming wire so that a wet web of 15 paper is formed on the wire, and the paper web is further dewatered and dried in the drying section of the paper machine. Drainage and retention aids are conventionally introduced into the suspension in order to facilitate drainage and increase adsorption of fine particles onto the cellulosic fibers so that they are retained with the fibers on the wire.

20 Aqueous suspensions containing cellulosic fibers may contain, apart from cellulosic fibers, also compounds which have negative impact on the production process. Such compounds can be found both in suspensions originating from virgin pulp and from recycled pulp. Compounds which are released during the pulping and bleaching operations are commonly referred to as pitch. Examples of pitch include wood resins 25 such as lipophilic extractives (fatty and resin acids, sterols, stearyl esters, triglycerides) and also fats, terpenes, terpenoids, waxes etc. These compounds contribute to a high anionic charge of the suspensions.

30 Further, especially in closed mills where white water is extensively re-circulated, the suspensions may also comprise charged contaminants like salts and various wood polymers of which the charged, low charged and non-charged compounds compete with the cellulose with respect to the adsorption of and interaction with added performance chemicals such as drainage and retention aids, sizing agents, etc. Usually such disturbing compounds are referred to as anionic trash.

35

All the above-mentioned compounds interfere with the pulp and paper making processes in various ways. To compensate for the high anionic charge caused by disturbing

substances, increased amounts of cationic additives, which contribute to improved dewatering and retention, have been used in the papermaking processes.

US Patent No. 4,388,150 discloses the use of a cationic starch together with colloidal 5 silicic acid to improve retention and drainage and improve characteristics of resulting paper in a papermaking process in which mineral fillers are used.

EP-A 0 700 473 discloses a papermaking process in which retention and/or dewatering are improved by adding a cationic long-chain polyacrylamide to an aqueous suspension 10 containing cellulosic fibers and then a polymeric aluminum salt and a base or an acid.

Despite the fact that considerable improvements have been achieved in the drainage and retention of the aqueous suspensions containing cellulosic fibers, there is still a need for improvements, especially when producing cellulosic products from aqueous cellulosic 15 suspensions derived from mechanical pulps. Therefore, it is an object of this invention to provide a process for the production of a cellulosic product with further improvements in drainage and retention of the production process. Further objects will appear hereinafter.

Summary of the Invention

20

The present invention is directed to a process for the production of a cellulosic product which comprises:

- (i) providing an aqueous thick suspension containing cellulosic fibers having a fiber concentration of at least about 2% by weight;
- 25 (ii) adding to the thick suspension;
 - (I) an aluminum compound;
 - (II) an alkaline earth metal salt;
 - (III) an acid;
- (iii) diluting the obtained thick suspension to form a thin suspension;
- 30 (iv) adding to the thin suspension one or more drainage and retention aids; and
- (v) dewatering the obtained thin suspension.

The present invention is also directed to a process for the production of a cellulosic product which comprises:

- 35 (i) providing an aqueous thick suspension containing cellulosic fibers having:
 - (a) a fiber concentration of at least about 2% by weight;
 - (b) an alkaline earth metal ion concentration of at least about 100 mg/l;

- (ii) adding to the thick suspension an aluminum compound and optionally an acid to obtain a pH of from about 4 to about 5.5;
- (iii) diluting the obtained thick suspension to form a thin suspension;
- (iv) adding to the thin suspension one or more drainage and retention aids; and

5 (v) dewatering the obtained thin suspension.

The present invention is further directed to an aqueous composition comprising a mixture of:

- (I) an aluminum compound;
- 10 (II) an alkaline earth metal salt; and
- (III) an acid;

wherein the weight ratio of the aluminum compound, alkaline earth metal salt and acid ranges from about 60:1:0.1 to about 5:1:1.

15 The present invention is further directed to the use of the aqueous composition as an additive in a process for producing a cellulosic product.

Detailed Description of the Invention

20 According to the present invention it has been found that drainage and retention can be improved without any significant impairment of formation, or even with improvements in paper formation, by a process which comprises adding an aluminum compound, alkaline earth metal salt and acid to an aqueous suspension containing cellulosic fibers having a fiber concentration of at least about 2% by weight, herein also referred to as a thick suspension, diluting the thick suspension to form a thin suspension, herein also referred to as a diluted suspension, and adding to the thin suspension one or more drainage and retention aids and dewatering the obtained thin suspension to form the cellulosic product.

25

30 The present invention provides improvements in drainage, retention and yield in the production of cellulosic products from all types of cellulosic suspensions, in particular suspensions containing mechanical or recycled pulp, and suspensions having high contents of salts (high conductivity) and colloidal substances, and in papermaking processes with a high degree of white water closure, i.e. extensive white water recycling and limited fresh water supply. Hereby the present invention makes it possible to increase

35 the speed of the paper machine and to use lower dosages of additives to give corresponding drainage and/or retention effects, thereby leading to an improved paper-making process and economic benefits.

Aluminum compounds that can be used according to the invention include alum, aluminate, e.g. sodium or potassium aluminate, aluminum chloride, aluminum nitrate, and polyaluminum compounds, such as polyaluminum chloride, polyaluminum sulfate, and poly-
5 aluminum compounds containing both chloride and sulfate ions, polyaluminum silicate-sulfate, and mixtures thereof. The polyaluminum compounds may also contain other anions, for example anions from phosphoric acid, organic acids such as citric acid and oxalic acid. Alum, as used herein, includes not only a double salt of aluminum and potassium sulfate $K_2SO_4xAl_2(SO_4)_3x24H_2O$, but also aluminum sulfate $Al_2(SO_4)_3x14H_2O$, $Al_2(SO_4)_3x18H_2O$ and
10 mixtures thereof. Examples of suitable aluminum compounds include those disclosed in U.S. Pat. No. 5,127,994, which is hereby incorporated herein by reference. Suitably, the aluminum compound is selected from alum, aluminum chloride, polyaluminum compounds such as polyaluminum chloride and polyaluminum silicate sulfate, and aluminate, preferably alum.

15

Alkaline earth metal salts that can be used according to the invention include magnesium, calcium and barium salts. The salts can have an anion selected from halides, sulfates, carbonates, nitrates or organic acids. Suitably, the alkaline earth metal salt is selected from magnesium and calcium salts, e.g. magnesium chloride, magnesium sulfate,
20 calcium chloride and barium sulfate. Preferably, the alkaline earth metal salt is a magnesium salt. In a preferred embodiment of the invention, the alkaline earth metal salt is added to the thick suspension to obtain an alkaline earth metal ion concentration of at least about 100 mg/l, suitably at least about 150 mg/l and preferably at least 200 mg/l. The thick suspension can have a high concentration of alkaline earth metal salts based
25 on Ca^{2+} and Mg^{2+} ions which salts can be derived from the cellulosic fibers and fillers used to form the suspension, in particular in integrated mills where a concentrated aqueous fiber suspension from the pulp mill normally is mixed with water to form a diluted suspension suitable for paper manufacture in the paper mill. The salts may also be derived from various additives introduced into the thick suspension and from the fresh
30 water supplied to the process. The concentration of salts is usually higher in processes where white water is extensively recirculated, which may lead to considerable accumulation of salts in the water circulating in the process. Therefore, a thick suspension having an alkaline earth metal ion concentration of at least about 100 mg/l can be provided without any further addition of an alkaline earth metal salt.

35

Acids that can be used according to the invention include inorganic acids, for example sulfuric acid, hydrochloric acid, phosphoric acid, hydrochloric acid and nitric acid and

organic acids, such as carboxylic acids, for example oxalic acid and citric acid. Preferably, the acid is an inorganic acid, preferably hydrochloric acid or sulfuric acid. The acid is added to the thick suspension to obtain a pH within the range of from about 2 to about 6, for example within the range of from about 4 to about 5.5. The defined pH range 5 may also be obtained by only adding the aluminum compound to the thick suspension. In a further preferred embodiment of the invention, an acid is optionally added to the thick suspension to obtain a pH of from about 4 to about 5.5. Preferably, the addition of aluminum compound and optional acid according to the invention results in a pH reduction of the thick suspension to the indicated range. For instance, the think 10 suspension to which the aluminum compound and optional acid are added can have a pH of at least about 6, e.g. at least about 6.5.

According to a preferred embodiment of the invention, one or more of the aluminum compounds, alkaline earth metal salts and acids are added to a think suspension of a 15 pulp making process. The think suspension can be derived from several kinds of pulps, such as chemical pulp, such as sulfate and sulphite pulp, mechanical pulp, such as thermo-mechanical pulp, chemo-thermomechanical pulp, orgasolv pulp, refiner pulp or groundwood pulp from both softwood and hardwood, or fibers derived from one year plants like elephant grass, bagasse, flax, straw, etc., and suspensions based on recycled 20 fibers. In a preferred embodiment of the invention, the think suspension contains cellulosic fibers derived from mechanical pulp, and preferably the content of mechanical pulp is at least 50 % by weight, based on the total weight of the pulp. One or more of the aluminum compound, alkaline earth metal salt and/or acid can be added subsequent to chemical digestion, such as after the brown stock washer, or after refining of (chemo-) mechanical 25 pulp. Usually, the pulp is bleached in a multi stage bleaching process comprising different bleaching stages. Examples of suitable bleaching stages include chlorine bleaching stages, e.g. elementary chlorine and chlorine dioxide bleaching stages, non-chlorine bleaching stages, e.g. peroxide stages like ozone, hydrogen peroxide and peracetic acid, and combinations of chlorine and non-chlorine bleaching and oxidizing stages, optionally in 30 combination with reducing stages like treatment with dithionite. The pulp can be hydrogen peroxide bleached and one or more of the aluminum compound, alkaline earth metal salt and acid are added after the bleaching stages. In one preferred embodiment of the invention, one or more of the aluminum compound, alkaline earth metal salt and acid are added to the think suspension at the point of dilution after the bleaching stage. In another 35 preferred embodiment of the invention, one or more of the aluminum compound, alkaline earth metal salt and acid are added to the thick suspension present in a mixer before the thick suspension reaches the pulp storage tank. In a further preferred embodiment of the

invention, one or more of the aluminum compound, alkaline earth metal salt and acid are added to the think suspension after the storage tank on the way to paper mill mixing chest. At the point of addition of the aluminum compound, alkaline earth metal salt and acid, the think suspension has a fiber concentration of at least about 2%, suitably at least 5 about 3% and preferably at least about 3.5% by weight. The concentration can be up to about 10% by weight. Preferably, when adding the aluminum compound, alkaline earth metal salt and acid to the thick suspension of a pulp making process, the thick suspension obtained is subsequently used in a paper making process in an integrated mill.

10

The aluminum compound, alkaline earth metal salt and acid, herein also referred to as the components, can be separately or simultaneously added to the thick suspension. When separately adding the components, they can be added in any order. Suitably, the aluminum compound is added prior to adding the alkaline earth metal salt and/or acid, and the alkaline 15 earth metal salt can be added prior to, simultaneously with or after the acid. When simultaneously adding the components, they can be added separately and/or in the form of a mixture. Examples of suitable modes of simultaneous addition include adding the three components separately, in a composition comprising the components, and by adding one of the components separately and two of the components in the form of a mixture. The mixture 20 may comprise the aluminum compound and one or both of the alkaline earth metal salt and acid. In a preferred embodiment of the invention, the aluminum compound and alkaline earth metal salt are simultaneously added as a mixture and acid is optionally added to the thick suspension.

25 The present invention further relates to an aqueous composition comprising a mixture of the above-mentioned components as well as the use thereof. The aqueous composition is suitably used as an additive in a process for the production of a cellulosic product, preferably as a drainage and retention aid in such a process. Preferably, the composition is used in combination with one or more drainage and/or retention aids, which preferably 30 comprise at least one cationic polymeric retention agent and which are preferably added to the thin suspension. Preferably, the composition is aqueous. The aluminum compound, alkaline earth metal salt and acid can be present in a dry matter content varying within a wide range of from 5 to 99 % by weight, suitably from 20 to 90 % by weight. The components can be present in the composition in a weight ratio aluminum compound, 35 alkaline earth metal salt and acid of from about 60:1:0.01 to about 5:1:0.1. The composition according to the invention can be easily prepared by mixing the aluminum compound, alkaline earth metal salt and acid, preferably under stirring.

The components according to the invention can be added to the thick suspension in amounts which can vary within wide limits. Generally, the components are added in amounts that give better drainage, retention and/or yield in the papermaking process than 5 what is obtained when not adding the components. The aluminum compound is usually added in an amount of at least about 10 kg/ton, ton referring to a metric ton and based on the dry weight of the thick suspension, often at least about 30 kg/ton, and the upper limit is usually about 90 kg/ton and suitably about 40 kg/ton. Likewise, if used, the alkaline earth metal salt is usually added in an amount of at least about 0.5 kg/ton, often at least 10 about 1.0 kg/ton, and the upper limit is usually about 40 kg/ton and suitably about 35 kg/ton. Similarly, the acid is usually added in an amount of at least about 0.01 kg/ton, often at least about 0.05 kg/ton and the upper limit is usually about 2.0 kg/ton and suitably about 1.5 kg/ton. When using the aqueous composition according to the invention, it is usually added in an amount of at least about 10 kg/ton, often at least about 15 30 kg/ton, and the upper limit is usually about 120 kg/ton and suitably about 50 kg/ton.

Subsequent to adding to the thick suspension the aluminum compound, alkaline earth metal salt and acid according to the invention, the thick suspension is diluted to form an aqueous thin suspension containing cellulosic fibers having a fiber concentration of less 20 than 2% by weight, herein also referred to a thin suspension. The thin suspension usually has a fiber concentration of from about 0.2 to about 1.5 % by weight, for example from about 0.5 to about 1.0% by weight. The dilution can be effected by means of any aqueous phase such as, for example, water, aqueous solution and aqueous suspension, e.g. white water or clarified white water.

25

After adding the aluminum compound, alkaline earth metal salt and acid according to the invention, if desired, the pH of the aqueous thick or thin suspension can be increased to be in the range of from about 5.5 to about 10, suitably from about 6 to about 9, and preferably from about 6 to about 8, by adding a base. Examples of suitable bases include 30 bicarbonates and carbonates of alkali metals and alkali metal hydroxides, suitably sodium bicarbonate, sodium carbonate and sodium hydroxide, preferably sodium hydroxide. The base can be added prior to, simultaneously with or after the addition of drainage and retention aids. The base is preferably added prior to the addition of drainage and retention aids.

35

One or more drainage and retention aids are used according to the invention, preferably in a papermaking process. The process comprises diluting the thick suspension, which

may be obtained from the pulping process, to form a thin suspension, adding to the thin suspension one or more drainage and retention aids and dewatering the obtained suspension. The term "drainage and retention aids", as used herein, refers to one or more additives which, when added to a suspension containing cellulosic fibers, give better
5 drainage and retention than what is obtained when not adding the said one or more additives.

Examples of suitable drainage and retention aids include cationic and anionic, organic polymers, siliceous materials, and mixtures thereof. The use of organic polymers and
10 siliceous materials as drainage and retention aids, or as flocculating agents, is well known in the art. Preferably, at least one cationic polymer is used as a drainage and retention agent. The term "cationic polymer", as used herein, refers to an organic polymer having one or more cationic groups. The cationic polymer may also contain anionic groups, as long as the polymer has an overall cationic charge. The term "anionic polymer", as used
15 herein, refers to an organic polymer having one or more anionic groups. The anionic polymer may also contain cationic groups, as long as the polymer has an overall anionic charge.

Polymers suitable for use in the process can be derived from natural or synthetic sources,
20 and they can be linear, branched or cross-linked. Examples of suitable polymers include cationic polysaccharides, preferably starches; cationic and anionic chain-growth polymers, preferably cationic and anionic acrylamide-based polymers; as well as cationic poly(diallyl-dimethyl ammonium chloride); cationic polyethylene imines; cationic polyamines; cationic polyamideamines and vinylamide-based polymers. Cationic starch and cationic acrylamide-
25 based polymers are particularly preferred polymers and they can be used singly, together with each other or together with other polymers, e.g. other cationic and/or anionic polymers. The weight average molecular weight of the polymer is suitably above 1,000,000 and preferably above 2,000,000. The upper limit is not critical; it can be about 50,000,000, usually 30,000,000 and suitably about 25,000,000. However, the molecular weight of
30 polymers derived from natural sources may be higher.

Examples of suitable siliceous materials include anionic silica-based particles and anionic clays of the smectite type. Preferably, the siliceous material has particles in the colloidal range of particle size. Anionic silica-based particles, i.e. particles based on SiO₂ or silicic
35 acid, are preferably used and such particles are usually supplied in the form of aqueous colloidal dispersions, so-called sols. Examples of suitable silica-based particles include colloidal silica and different types of polysilicic acid, either homopolymerised or co-

polymerised, for example polymeric silicic acid, polysilicic acid microgel, polysilicate and polysilicate microgel. The silica-based sols can be modified and contain other elements, e.g. aluminum, boron, nitrogen, zirconium, gallium, titanium and the like, which can be present in the aqueous phase and/or in the silica-based particles. Examples of suitable silica-based particles of this type include colloidal aluminum-modified silica, aluminum silicates, polyaluminosilicate and polyaluminosilicate microgel. Mixtures of such suitable silica-based particles can also be used. Examples of suitable drainage and retention aids comprising anionic silica-based particles include those disclosed in U.S. Patent Nos. 4,388,150; 4,927,498; 4,954,220; 4,961,825; 4,980,025; 5,127,994; 5,176,891; 5,368,833; 5,447,604; 10 5,470,435; 5,543,014; 5,571,494; 5,573,674; 5,584,966; 5,603,805; 5,688,482; and 5,707,493; which are hereby incorporated herein by reference.

Examples of suitable anionic silica-based particles include those having an average particle size below about 100 nm, preferably below about 20 nm and more preferably in the range of 15 from about 1 to about 10 nm. As conventional in the silica chemistry, the particle size refers to the average size of the primary particles, which may be aggregated or non-aggregated. The specific surface area of the silica-based particles is suitably above 50 m²/g and preferably above 100 m²/g. Generally, the specific surface area can be up to about 1700 m²/g and preferably up to 1000 m²/g. The specific surface area is measured by means of 20 titration with NaOH in a well known manner, e.g. as described by G.W. Sears in Analytical Chemistry 28(1956): 12, 1981-1983 and U.S. Patent No. 5,176,891. The given area thus represents the average specific surface area of the particles.

In a preferred embodiment of the invention, use is made of the silica-based particles which 25 are present in a sol having a S-value in the range of from 8 to 50 %, preferably from 10 to 40%. The S-value can be measured and calculated as described by Iler & Dalton in J. Phys. Chem. 60(1956), 955-957. The S-value indicates the degree of aggregation or microgel formation and a lower S-value is indicative of a higher degree of aggregation.

30 Examples of suitable anionic clays of the smectite type include those carrying a negative charge at the surface, including montmorillonite/bentonite, hectorite, beidellite, nontronite, saponite, laponite, preferably bentonite. Examples of suitable anionic bentonite clays include those disclosed in U.S. Patent Nos. 4,753,710; 5,071,512; and 5,607,552, which are hereby incorporated herein by reference.

35

Cationic coagulants, also referred to as anionic trash catchers and fixatives, can of course also be used in the process according to the invention. Examples of suitable cationic

coagulants include water-soluble organic polymeric coagulants. The cationic coagulants can be used singly or together, i.e. a polymeric coagulant can be used in combination with an inorganic coagulant. Examples of suitable water-soluble organic polymeric cationic coagulants include cationic polyamines, polyamideamines, polyethylene imines, 5 dicyandiamide condensation polymers and polymers of water soluble ethylenically unsaturated monomer or monomer blend which is formed of 50 to 100 mole % cationic monomer and 0 to 50 mole % other monomer. The amount of cationic monomer is usually at least 80 mole %, suitably 100 %. Examples of suitable ethylenically unsaturated cationic monomers include dialkylaminoalkyl (meth)-acrylates and -acrylamides, preferably in 10 quaternised form, and diallyl dialkyl ammonium chlorides, e.g. diallyl dimethyl ammonium chloride (DADMAC), preferably homopolymers and copolymers of DADMAC. The organic polymeric cationic coagulants usually have a weight average molecular weight in the range of from 1,000 to 3,000,000, suitably from 5,000 to 700,000, and preferably from 10,000 to 500,000.

15

The drainage and retention aid(s) can be added to the thin suspension in conventional manner and in any order. When using a siliceous material, it is preferred to add a cationic polymer to the thin suspension before adding the siliceous material, even if the opposite order of addition may also be used. It is further preferred to add a cationic polymer before 20 a shear stage, which can be selected from pumping, mixing, cleaning, etc., and to add the siliceous material after that shear stage. When using a cationic coagulant, it is preferably introduced into the suspension prior to introducing cationic polymer and siliceous material, if used. Alternatively, the cationic coagulant and cationic polymer can be introduced into the suspension essentially simultaneously, either separately or in admixture, 25 e.g. as disclosed in U.S. Patent No. 5,858,174, which is hereby incorporated herein by reference.

The drainage and retention aid(s) can be added to the thin suspension to be dewatered in amounts which can vary within wide limits depending on, inter alia, type and number of 30 additives, type of cellulosic suspension, salt content, type of salts, filler content, type of filler, point of addition, degree of white water closure, etc. Generally, the retention and drainage aid(s) are added in amounts that give better drainage and/or retention than what is obtained when not using the additives. The cationic polymer is usually added in an amount of at least about 0.001% by weight, often at least about 0.005% by weight, based on dry 35 cellulosic suspension, and the upper limit is usually about 3% and suitably about 1.5% by weight. Commonly applied addition amounts of cationic polymer are from about 0.01% up to about 0.5% by weight. Anionic materials, e.g. siliceous materials, i.e. anionic silica-based

particles and anionic clays of the smectite type, and anionic organic polymers, are usually added in an amount of at least about 0.001% by weight, often at least about 0.005% by weight, based on dry cellulosic suspension, and the upper limit is usually about 1.0% and suitably about 0.6% by weight.

5

When using a cationic coagulant in the process, it can be added in an amount of at least about 0.001% by weight, calculated as dry coagulant on dry cellulosic suspension. Suitably, the amount is in the range of from about 0.05 up to about 3.0%, preferably in the range from about 0.1 up to about 2.0%.

10

In the process, other components may of course be introduced into the cellulosic suspension. Examples of such components include conventional fillers, optical brightening agents, sizing agents, dry strength agents, wet strength agents, etc. Examples of suitable conventional fillers include kaolin, china clay, titanium dioxide,

15 gypsum, talc, natural and synthetic calcium carbonates, e.g. chalk, ground marble and precipitated calcium carbonate, hydrogenated aluminum oxides (aluminum trihydroxides), calcium sulfate, barium sulfate, calcium oxalate, etc. Examples of suitable sizing agents include non-cellulose-reactive sizing agents, e.g. rosin-based sizing agents like rosin-based soaps, rosin-based emulsions/dispersions, and cellulose-reactive sizing agents, e.g. 20 emulsions/dispersions of acid anhydrides like alkenyl succinic anhydrides (ASA), alkenyl and alkyl ketene dimers (AKD) and multimers. Examples of suitable wet strength agents include polyamines and polyaminoamides.

The present invention further encompasses papermaking processes where white water is 25 extensively recycled, or recirculated, i.e. with a high degree of white water closure, for example where from 0 to 30 tons of fresh water are used per ton of dry paper produced, usually less than 20, preferably less than 15, more preferably less than 10 and notably less than 5 tons of fresh water per ton of paper. Fresh water can be introduced in the process at any stage; for example, fresh water can be mixed with cellulosic fibers in order to form a 30 cellulosic suspension, and fresh water can be mixed with a thick cellulosic suspension to dilute it so as to form a thin cellulosic suspension.

The process according to the invention is used for the production of a cellulosic product and 35 preferably paper. The term "paper", as used herein, includes not only paper and the production thereof, but also other web-like products, such as for example board and paperboard, and the production thereof. The process can be used in the production of paper from different types of suspensions of cellulosic fibers, as defined above, and the

suspensions should preferably contain at least 25% and more preferably at least 50% by weight of such fibers, based on dry substance.

Preferably, the invention is applied on paper machines producing wood-containing paper and paper based on recycled fibers, such as SC, LWC and different types of book and newsprint papers, and on machines producing wood-free printing and writing papers, the term wood-free meaning less than about 15% of wood-containing fibers. Examples of preferred applications of the invention include the production of paper and layer of multilayered paper from cellulosic suspensions containing at least 50 % by weight of mechanical and/or recycled fibers. Preferably the invention is applied on paper machines running at a speed of from 300 to 3000 m/min and more preferably from 500 to 2500 m/min.

The invention is further illustrated in the following Examples which, however, are not intended to limit the same. Parts and % relates to parts by weight and % by weight, respectively, unless otherwise stated.

Example 1

20 Drainage performance achieved by the present process was evaluated by means of a Dynamic Drainage Analyser (DDA), available from Akribi Kemikonsulter AB, Sweden, which measures the time for draining a set volume of an aqueous suspension containing cellulosic fibers through a wire when removing a plug and applying vacuum (0.35 bar) to that side of the wire that is opposite to the side on which the cellulosic suspension is present. First pass retention was evaluated by means of a nephelometer by measuring the turbidity of the filtrate, the white water, obtained by draining the suspension. The turbidity was measured in NTU (Nephelometric Turbidity Units). The higher the NTU, the less of the material is retained.

25

30 The cellulosic suspension used was derived from a mixture of thermo mechanical pulp (TMP) (70%) and stone groundwood pulp (SGW) (30%) which was hydrogen peroxide / sodium silicate bleached. The suspension was diluted with water to 4% fiber concentration and treated with a mixture comprising alum and magnesium sulfate salt in a weight ratio 35:1.87. After the treatment, the pH was reduced to about 5 by addition of

35 sulfuric acid (H_2SO_4) and kept at 40°C for 30 min. Then the suspension was diluted with water to a fiber concentration of 1% by weight and pH was maintained at 5 by additional sulfuric acid before making the DDA test.

The samples were put into the baffled DDA jar. The retention and dewatering aids were added as follows:

5 i) 15 seconds before draining the suspension, varying amounts of cationic polyacrylamide (Eka PL 1510).

ii) 5 seconds before draining the suspension, 0.5 kg/ton of anionic silica-based particles (Eka NP 320).

10 The amounts are based on the dry weight of the cellulosic suspension and ton refers to a metric ton in all examples. Test Nos. 1-3, 5-7, 9, 10 and 12 to 18 were used for comparison and Test Nos. 4, 8 and 11 show results obtained by the treatment according to the invention.

Table 1

Test No.	Addition of Alum [kg/ton]	Addition of Mixture (Alum:MgSO ₄) [kg/ton]	Addition of Cationic Polymer [kg/ton]	Drainage Time [s]	Turbidity [NTU]
1	0	0	0.5	19.3	214
2	15	0	0.5	17.9	214
3	35	0	0.5	15.0	196
4	0	35:1.87	0.5	12.0	176
5	0	0	1.0	15.3	205
6	15	0	1.0	15.3	197
7	35	0	1.0	11.9	172
8	0	35:1.87	1.0	9.3	124
9	15	0	1.25	14.7	190
10	35	0	1.25	10.5	148
11	0	35:1.87	1.25	7.1	101
12	0	0	1.5	14.4	165
13	15	0	1.5	14.0	190
14	35	0	1.5	9.2	126
15	0	0	2.0	12.2	146
16	15	0	2.0	10.5	164
17	0	0	3.0	9.6	121
18	15	0	3.0	8.2	137

As can be seen from the results presented in Table 1, the suspension treated with alum and magnesium sulfate according to the present invention resulted in a better drainage and retention performance than the suspension treated with only alum and the suspension that was not treated at all.

5

Example 2

In this example, drainage and retention performance was evaluated according to the general procedure of Example 1, except that a cationic coagulant was also used. The cationic 10 coagulant and retention and dewatering aids were added as follows:

- i) 30 seconds before draining the suspension, varying amounts of cationic polyacrylamide coagulant (Eka ATC 5439);
- ii) 15 seconds before draining the suspension, 0.5 kg/ton of cationic polyacrylamide 15 drainage and retention aid (Eka PL 1510)
- iii) 5 seconds before draining the suspension, 0.5 kg/ton of dry pulp of anionic silica-based particles (Eka NP 320).

Test Nos. 19-21, 24-26, 28-30 and 32-34 were used for comparison and Test Nos. 22, 20 23, 27 and 31 show the treatment according to the invention.

Table 2

Test No.	Addition of Alum [kg/t]	Addition of Mixture (Alum:MgSO ₄) [kg/ton]	Addition of Cationic Coagulant [kg/ton]	Drainage Time [s]	Turbidity [NTU]
19	0	0	0	19.3	214
20	15	0	0	15	214
21	35	0	0	17.9	196
22	0	35:1.87	0	12	176
23	0	35:1.87	0.25	11	130
24	0	0	0.5	16.1	200
25	15	0	0.5	11.3	202
26	35	0	0.5	15.3	160
27	0	35:1.87	0.5	8.8	99
28	0	0	0.75	15.7	178
29	15	0	0.75	9.9	200

Test No.	Addition of Alum [kg/t]	Addition of Mixture (Alum:MgSO ₄) [kg/ton]	Addition of Cationic Coagulant [kg/ton]	Drainage Time [s]	Turbidity [NTU]
30	35	0	0.75	14.9	129
31	0	35:1.87	0.75	7.3	85
32	0	0	1.0	14.2	171
33	15	0	1.0	8.5	178
34	35	0	1.0	13.8	103

As can be seen from the results presented in Table 2, the suspension treated with alum and magnesium sulfate according to the present invention resulted in a better drainage and retention performance than the suspension treated with only alum and the 5 suspension that was not treated at all.

Example 3

10 In this example, yield of the process was evaluated when using the composition according to the present invention comprising alum and magnesium sulfate.

15 A large batch of Hydrogen Peroxide / Sodium Silicate bleached TMP/SGW was diluted with water to a fiber concentration of 4%. This batch was well mixed and divided into four equal amounts. The obtained suspensions were treated in different ways. However, all suspensions were diluted in a constant manner and the change in paper basis weight was evaluated. The treatments of the suspensions are presented in Table 3.

Table 3

Test No.	Treatment
1	No treatment. pH was reduced to 5 by addition sulfuric acid and kept at 40°C for 30 min. Then the concentration of the suspension was decreased to 1% with a set volume. The set volume to reach 1% was used in all tests.
2	Treatment with alum at 4% pulp concentration. 35 kg/ton of alum was dosed and pH was adjusted to 5 by addition of sulfuric acid. This was then kept at 40°C for 30 min and then diluted according to Test No. 1.
3	Treatment with a mixture comprising alum and magnesium sulfate at 4% pulp concentration. The mixture was mixed in such a ratio that effective dose was 35

Test No.	Treatment
	kg/ton of alum and 1.87 kg/ton of magnesium sulphate, and pH was adjusted to 5 by addition of sulfuric acid. This was then kept at 40°C for 30 min and then diluted according to Test No. 1.
4	Treatment with the mixture comprising alum and magnesium sulfate at 1% pulp concentration. The mixture was mixed in such a ratio that effective dose is 35 kg/ton of alum and 1.87 kg/ton of magnesium sulphate, and pH was adjusted to 5 by addition of sulphuric acid. This was then kept at 40°C for 30 min.

All four samples had the same set dilution and were not compensated for solids change. Handsheets were prepared according to the method described in SCAN-CN 64:00 and 5 kg/ton of cationic starch was used as a drainage and retention aid. 25 sheets were made 5 with recirculation of white water. 10 last sheets were used for the evaluation of the yield obtained. The inorganic yield increase was evaluated as an increase in the ash content which was evaluated by the method according to ISO 2144-1977. The results are presented in Table 4.

10

Table 4

Test No.	Basis Weight [g/m ²]	Yield Increase [%]		
		Inorganic	Organic	Total
1	69.37	-	-	-
2	70.47	0.30	1.29	1.59
3	72.07	0.50	3.40	3.90
4	71.01	0.62	1.75	2.36

As can be seen from the results presented in Table 4, the papermaking process in which alum and magnesium sulfate were used according to the present invention (Test No. 3) resulted to an increased yield of the process.

15

Example 4

In this example, paper quality was evaluated in terms of basis weight, ash content, thickness, density, bulk, tensile index, tear index, air permeability, brightness, opacity, 20 light scattering and light absorption. Comparisons between paper sheets prepared from aqueous pulp suspensions derived from both unbleached and bleached pulp were made. The pulp suspensions were treated in different ways. The suspensions were derived from

TMP/SGW (70/30) and alternatively hydrogen peroxide / sodium silicate bleached TMP/SGW (70/30). The suspensions in the tests were not treated at all, treated with calcinated clay or with alum, magnesium sulfate and acid. Further comparisons were made in a similar manner when cationic starch was added as a drainage and retention aid to the suspensions. Sheets were prepared using the standard method SCAN-CM 64:00. The treatments of the suspensions are presented in Table 5.

Table 5

Test No.	Treatment
1	Unbleached TMP/SGW
2	Hydrogen peroxide / sodium silicate bleached TMP / SGW
3	Hydrogen peroxide / sodium silicate bleached TMP / SGW, addition of calcinated clay in an amount of 2.5% by weight, based on the dry weight of the suspension, to a diluted cellulosic suspension having a fiber concentration of 1% by weight.
4	Hydrogen peroxide / sodium silicate bleached TMP / SGW, addition of calcinated clay in an amount of 5.0% by weight, based on the dry weight of the suspension, to a diluted cellulosic suspension having a fiber concentration of 1% by weight.
5	Hydrogen peroxide / sodium silicate bleached TMP / SGW, treatment with a mixture comprising alum and magnesium sulfate at 4% pulp concentration. The mixture was used in such a ratio that effective dose was 35 kg/ton of alum and 1.87 kg/ton of magnesium sulphate, and pH was adjusted to 5 by addition of sulfuric acid. This was then kept at 40°C for 30 min and then diluted to a fiber concentration of 1% by weight.
6	Hydrogen peroxide / sodium silicate bleached TMP / SGW, 5 kg/t cationic starch added 20 seconds before drainage.
7	Hydrogen peroxide / sodium silicate bleached TMP / SGW, addition of calcinated clay in an amount of 2.5% by weight, based on the dry weight of the suspension, to a diluted cellulosic suspension having fiber concentration of 1% by weight, 5 kg/ton cationic starch added 20 seconds before drainage.
8	Hydrogen peroxide / sodium silicate bleached TMP / SGW, addition of calcinated clay in an amount of 5.0% by weight, based on the dry weight of the suspension, to a diluted cellulosic suspension having a fiber concentration of about 1% by weight, 5 kg/ton of cationic starch added 20 seconds before drainage.

Test No.	Treatment
9	Hydrogen peroxide / sodium silicate bleached TMP / SGW, treatment with a mixture comprising alum and magnesium sulfate at 4% pulp concentration. The mixture was mixed in such a ratio that effective dose was 35 kg/ton of alum and 1.87 kg/ton of magnesium sulphate, and pH was adjusted to 5 by addition of sulfuric acid. This was then kept at 40°C for 30 min, diluted to a fiber concentration of 1% by weight and then 5 kg/ton of cationic starch added 20 seconds before drainage.

Basis weight was evaluated according to standard ISO 536:1995, ash content according to ISO 2144-1977, thickness, bulk and density according to ISO 534:1988, tensile index according to SCAN-P 67:93 kN/kg, tear index according to ISO 1974:1990 and air 5 permeability according to ISO 5636-5:2003.

Table 6

Test No.	Basis Weight [g/m ²]	Ash Content [%]	Thickness [μm]	Density [kg/dm ³]	Bulk [dm ³ /kg]	Tensile Index [kN/kg]	Tear Index [mNm ² /g]	Air Permeability [s]
1	59,38	0,43	169	351	2,85	18,4	2,97	9,0
2	62,35	1,01	175	356	2,81	21,0	3,74	31,4
3	59,14	1,51	174	349	2,87	21,0	3,48	22,0
4	60,67	2,12	172	344	2,91	19,2	3,69	22,3
5	58,64	2,85	175	335	2,98	17,2	3,35	13,6
6	64,83	1,24	178	364	2,75	20,9	3,48	23,0
7	63,93	3,01	174	371	2,70	20,1	3,35	26,9
8	64,49	4,78	173	370	2,71	20,4	3,53	22,5
9	62,84	3,41	177	355	2,82	20,9	3,43	12,1

Paper quality was also evaluated in terms of brightness, opacity, light scattering and light 10 absorption. The measurements were made by means of equipment, Technidyne, Colour Touch, and according to standards ISO 2470 for brightness, ISO 2471 for opacity and ISO 9416 for light spreading and light absorption.

Table 7

Test No.	Brightness [%]	Opacity [%]	Light Scattering [m ² /kg]	Light Absorption [m ² /kg]
1	58,97	93,40	55,15	2,64
2	75,31	86,23	54,21	0,49
3	75,37	86,94	57,16	0,58
4	75,71	86,80	58,48	0,61
5	76,12	86,04	56,96	0,52
6	75,00	88,24	57,22	0,62
7	75,90	89,24	61,86	0,62
8	77,26	90,09	67,86	0,63
9	75,84	88,07	58,70	0,64

As can be seen from the results presented in Tables 6 and 7, Test No. 9, where the sheets were prepared with a process according to the present invention, showed about 5 the same or even better paper characteristics than the sheets prepared with a papermaking process using calcinated clay as an additive.

1. A process for the production of a cellulosic product which comprises:
 - (i) providing an aqueous thick suspension containing cellulosic fibers having a fiber concentration of at least about 2% by weight;
 - (ii) adding to the thick suspension:
 - (I) an aluminum compound;
 - (II) an alkaline earth metal salt;
 - (III) an acid;
 - (iii) diluting the obtained thick suspension to form a thin suspension;
 - (iv) adding to the thin suspension one or more drainage and retention aids; and
 - (v) dewatering the obtained thin suspension.
2. A process for the production of a cellulosic product which comprises:
 - (i) providing an aqueous thick suspension containing cellulosic fibers having:
 - (a) a fiber concentration of at least about 2% by weight;
 - (b) an alkaline earth metal ion concentration of at least about 100 mg/l;
 - (ii) adding to the thick suspension an aluminum compound and optionally an acid to obtain a pH of from about 4 to about 5.5;
 - (iii) diluting the obtained thick suspension to form a thin suspension;
 - (iv) adding to the thin suspension one or more drainage and retention aids; and
 - (v) dewatering the obtained thin suspension.
3. The process according to any one of claims 1 or 2, wherein the aluminum compound is alum, polyaluminumchloride, polyaluminumsilicate sulfate, aluminate, aluminum nitrate or a mixture thereof.
4. The process according to any one of claims 1 to 3, wherein the alkaline earth metal salt is added to the thick suspension to obtain an alkaline earth metal ion concentration of at least 100 mg/l.
5. The process according to any one of claims 1 to 4, wherein the alkaline earth metal salt is a magnesium, calcium or barium salt.
6. The process according to any one of claims 1 to 5, wherein the alkaline earth metal salt has an anion which is selected from halides, sulfates, carbonates, nitrates or organic acids.

7. The process according to any one of the preceding claims, wherein the alkaline earth metal salt is magnesium chloride, magnesium sulphate, calcium chloride or barium sulphate.

5

8. The process according to any one of the preceding claims, wherein the acid is an inorganic acid.

9. The process according to any one of the preceding claims, wherein the acid is
10 hydrochloric acid or sulphuric acid.

10. The process according to any one of the preceding claims, wherein the acid is added to the thick suspension to obtain a pH of from about 4 to about 5.5.

15 11. The process according to any one of the preceding claims, wherein after adding the aluminum compound, alkaline earth metal salt and acid, the pH of the thick suspension is increased to the range of from about 6 to about 8 by adding a base.

12. The process according to any one of the preceding claims, wherein the thick
20 suspension has a fiber concentration of at least about 3.5% by weight.

13. The process according to any one of the preceding claims, wherein the aqueous suspension contains cellulosic fibers derived from mechanical pulp.

25 14. The process according to claim 13, wherein the pulp is hydrogen peroxide bleached.

15. The process according to any one of the preceding claims, wherein:

- (I) the aluminum compound;
- (II) the alkaline earth metal salt, and
- 30 (III) the acid;

are separately added to the suspension.

16. The process according to any any one of the preceding claims, wherein:

- (I) the aluminum compound;
- 35 (II) the alkaline earth metal salt; and/or
- (III) the acid;

are added in the form of a mixture to the suspension.

17. The process according to any one of the preceding claims, wherein the drainage and retention aids comprise one or more cationic organic polymers.
- 5 18. The process according to any one of the preceding claims, wherein the drainage and retention aids comprise a siliceous material.
19. The process according to any one of the preceding claims, wherein the drainage and retention aids comprise a cationic organic polymer, which is added before a shear stage,
- 10 and a siliceous material, which is added after that shear stage.
20. The process according to any one of the preceding claims, wherein the drainage and retention aids comprise anionic silica-based particles.
- 15 21. The process according to any one of the preceding claims, wherein the cellulosic product is paper.
22. The process according to any one of the preceding claims, wherein the process for the production of a cellulosic product takes place in an integrated paper mill.
- 20 23. An aqueous composition comprising a mixture of:
 - (I) an aluminum compound;
 - (II) an alkaline earth metal salt; and
 - (III) an acid;
- 25 wherein the weight ratio of the aluminum compound, alkaline earth metal salt and acid ranges from about 60:1:0.1 to about 5:1:1.
24. The composition according to claim 23, wherein the aluminum compound is alum, polyaluminumchloride, polyaluminumsilicate sulfate, aluminate or a mixture thereof.
- 30 25. The composition according to claim 23 or 24, wherein the acid is an inorganic acid.
26. The composition according to any one of claims 23 to 25, wherein the acid is a hydrochloric acid or sulfuric acid.
- 35 27. The composition according to any one of claims 23 to 26, wherein the salt is magnesium, calcium or barium salt.

28. The composition according to any one of claims 23 to 27, wherein the salt has an anion which is selected from halides, sulfates, carbonates, nitrates or organic acids.

5 29. The composition according to any one of claims 23 to 27, wherein the salt is magnesium chloride, magnesium sulphate, calcium chloride or barium sulphate.

30. Use of the aqueous composition according to any one of claims 23 to 29 as an additive in a process for producing a cellulosic product.

10

31. Use according to claim 30, wherein the composition is used as a drainage and retention aid in a process for producing a cellulosic product.

32. Use according to claim 30 or 31, wherein the composition is used in combination with
15 one or more drainage and retention aids comprising at least one cationic polymeric retention agent.

INTERNATIONAL SEARCH REPORT

International application No

PCT/SE2007/051032

A. CLASSIFICATION OF SUBJECT MATTER

INV. D21H17/65 D21H17/66 D21H17/67 D21H21/10

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

D21H

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 01/44573 A (HERCULES INC [US]) 21 June 2001 (2001-06-21) page 17, line 8 - line 23 claim 1	1,2,23, 30
Y	examples	3-22, 24-29, 31,32
Y	US 5 127 994 A (JOHANSSON HANS E [SE]) 7 July 1992 (1992-07-07) cited in the application column 2, line 48 - line 59 claim 1	1-32
Y	US 5 755 930 A (SATTERFIELD BRIAN FREDERIC [US] ET AL) 26 May 1998 (1998-05-26) column 4, line 55 - line 68	1-32
		-/-

Further documents are listed in the continuation of Box C.

See patent family annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

19 March 2008

Date of mailing of the international search report

04/04/2008

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Naeslund, Per

INTERNATIONAL SEARCH REPORT

International application No
PCT/SE2007/051032

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 4 388 150 A (SUNDEN OLOF [FR] ET AL) 14 June 1983 (1983-06-14) cited in the application the whole document -----	1-32
A	US 4 961 825 A (ANDERSSON KJELL R [CA] ET AL) 9 October 1990 (1990-10-09) cited in the application the whole document -----	1-32
A	US 4 927 498 A (RUSHMERE JOHN D [US]) 22 May 1990 (1990-05-22) cited in the application the whole document -----	1-32
A	WO 01/40577 A (KEMIRA CHEMICALS OY [FI]; AHLGREN JONNI [FI]; STRENGELL KIMMO [FI]) 7 June 2001 (2001-06-07) the whole document -----	1-32
A	EP 0 348 366 A2 (EKA NOBEL AB [SE] EKA CHEMICALS AB [SE]) 27 December 1989 (1989-12-27) -----	
A	WO 93/14263 A (KEMIRA OY [FI]) 22 July 1993 (1993-07-22) -----	

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/SE2007/051032

Patent document cited in search report	Publication date	Patent family member(s)		Publication date
WO 0144573	A 21-06-2001	AR 026956 A1 AU 771731 B2 AU 2265101 A BR 0016330 A CA 2392699 A1 CN 1408038 A EP 1280960 A1 JP 2003517118 T MX PA02005853 A PL 356457 A1 TW 523563 B US 6379501 B1 ZA 200205636 A		05-03-2003 01-04-2004 25-06-2001 27-08-2002 21-06-2001 02-04-2003 05-02-2003 20-05-2003 23-10-2002 28-06-2004 11-03-2003 30-04-2002 15-10-2003
US 5127994	A 07-07-1992	AU 598416 B2 AU 3497089 A BR 8902336 A CA 1334325 C CN 1038678 A DE 68908972 D1 DE 68908972 T2 DK 254889 A EP 0348366 A2 ES 2043107 T3 FI 892475 A JP 1887533 C JP 2019593 A JP 6011957 B MX 170284 B NO 892091 A NZ 229227 A PT 90654 A SE 461156 B SU 1828474 A3 ZA 8903871 A		21-06-1990 30-11-1989 09-01-1990 14-02-1995 10-01-1990 14-10-1993 10-02-1994 26-11-1989 27-12-1989 16-12-1993 26-11-1989 22-11-1994 23-01-1990 16-02-1994 13-08-1993 27-11-1989 26-02-1991 30-11-1989 15-01-1990 15-07-1993 28-02-1990
US 5755930	A 26-05-1998	AT 174981 T AU 701663 B2 AU 1583195 A BR 9505772 A CA 2159593 A1 DE 69506799 D1 DE 69506799 T2 DK 693146 T3 EP 0693146 A1 ES 2125597 T3 FI 954677 A WO 9521296 A1 GR 3029339 T3 JP 3681070 B2 JP 8508796 T NO 953936 A NZ 279258 A PL 310979 A1 US 5538596 A ZA 9500924 A		15-01-1999 04-02-1999 21-08-1995 27-02-1996 10-08-1995 04-02-1999 20-05-1999 23-08-1999 24-01-1996 01-03-1999 02-10-1995 10-08-1995 28-05-1999 10-08-2005 17-09-1996 03-10-1995 27-04-1998 22-01-1996 23-07-1996 06-02-1996
US 4388150	A 14-06-1983	CA 1154563 A1		04-10-1983

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/SE2007/051032

Patent document cited in search report	Publication date		Patent family member(s)	Publication date
US 4388150	A		JP 1679274 C JP 3041598 B JP 62223395 A JP 1713993 C JP 57051900 A JP 62031120 B SE 432951 B SE 8003948 A	13-07-1992 24-06-1991 01-10-1987 27-11-1992 26-03-1982 07-07-1987 30-04-1984 29-11-1981
US 4961825	A	09-10-1990	AU 573360 B2 AU 4498585 A BR 8506769 A CA 1250703 A1 DE 3573282 D1 EP 0185068 A1 ES 8703954 A1 FI 860548 A JP 2019238 B JP 61502338 T NO 860422 A NZ 212332 A SE 8403062 A WO 8600100 A1 ZA 8504263 A	02-06-1988 10-01-1986 23-09-1986 07-03-1989 02-11-1989 25-06-1986 16-05-1987 06-02-1986 01-05-1990 16-10-1986 06-02-1986 29-11-1988 08-12-1985 03-01-1986 29-01-1986
US 4927498	A	22-05-1990	AT 119958 T AU 616027 B2 AU 3734589 A CA 1324703 C DE 68921731 D1 DE 68921731 T2 EP 0378605 A1 WO 8906638 A2	15-04-1995 17-10-1991 11-08-1989 30-11-1993 20-04-1995 19-10-1995 25-07-1990 27-07-1989
WO 0140577	A	07-06-2001	AT 331839 T AU 2374101 A CA 2393242 A1 DE 60029141 T2 EP 1266092 A1 ES 2267597 T3 FI 992598 A US 2003079848 A1	15-07-2006 12-06-2001 07-06-2001 11-01-2007 18-12-2002 16-03-2007 03-06-2001 01-05-2003
EP 0348366	A2	27-12-1989	AU 598416 B2 AU 3497089 A BR 8902336 A CA 1334325 C CN 1038678 A DE 68908972 D1 DE 68908972 T2 DK 254889 A ES 2043107 T3 FI 892475 A JP 1887533 C JP 2019593 A JP 6011957 B MX 170284 B	21-06-1990 30-11-1989 09-01-1990 14-02-1995 10-01-1990 14-10-1993 10-02-1994 26-11-1989 16-12-1993 26-11-1989 22-11-1994 23-01-1990 16-02-1994 13-08-1993

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/SE2007/051032

Patent document cited in search report	Publication date	Patent family member(s)		Publication date
		NO	892091 A	27-11-1989
EP 0348366	A2	NZ	229227 A	26-02-1991
		PT	90654 A	30-11-1989
		SE	461156 B	15-01-1990
		SU	1828474 A3	15-07-1993
		US	5127994 A	07-07-1992
		ZA	8903871 A	28-02-1990
WO 9314263	A 22-07-1993	AT	191524 T	15-04-2000
		AU	3354193 A	03-08-1993
		CA	2127992 A1	22-07-1993
		DE	69328311 D1	11-05-2000
		DE	69328311 T2	10-08-2000
		EP	0700473 A1	13-03-1996
		ES	2146609 T3	16-08-2000
		JP	3138475 B2	26-02-2001
		JP	7502791 T	23-03-1995
		PT	700473 T	31-07-2000