

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
26 February 2009 (26.02.2009)

PCT

(10) International Publication Number
WO 2009/026480 A1

(51) International Patent Classification:

D01F 6/76 (2006.01) D02G 3/04 (2006.01)
D01F 6/80 (2006.01)

(74) Agent: GOLIAN, Andrew, G.; E. I. du Pont de Nemours and Company, Legal Patent Records Center, 4417 Lancaster Pike, Wilmington, Delaware 19805 (US).

(21) International Application Number:

PCT/US2008/073940

(22) International Filing Date: 22 August 2008 (22.08.2008)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
11/894,944 22 August 2007 (22.08.2007) US

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MT, NL, NO, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report



WO 2009/026480 A1

(54) Title: FLAME RESISTANT SPUN STAPLE YARNS MADE FROM BLENDS OF FIBERS DERIVED FROM DIAMINO DIPHENYL SULFONE, LOW THERMAL SHRINKAGE FIBERS, FLAME RESISTANT FIBERS, AND ANTITSTATIC FIBERS AND FABRICS AND GARMENTS MADE THEREFROM AND METHODS FOR MAKING SAME

(57) Abstract: The invention concerns a flame-resistant spun staple yarns and fabrics and garments comprising these yarns and methods of making the same. The yarns have at least 25 parts by weight of a polymeric staple fiber containing a polymer or copolymer derived from a monomer selected from the group consisting of 4,4'diaminodiphenyl sulfone, 3,3'diaminodiphenyl sulfone, and mixtures thereof; 2 to 15 parts by weight of a fiber having low thermal shrinkage; 1 to 5 parts by weight of an antistatic fiber; and the remainder being flame resistant fibers having a limiting oxygen index of 21 or greater, based on 100 total parts by weight of the polymeric fiber, the low thermal shrinkage fiber, the antistatic fiber, and the flame resistant fibers in the yarn.

TITLE OF INVENTION

5

FLAME RESISTANT SPUN STAPLE YARNS MADE FROM BLENDS OF
FIBERS DERIVED FROM DIAMINO DIPHENYL SULFONE, LOW
THERMAL SHRINKAGE FIBERS, FLAME RESISTANT FIBERS, AND
10 ANTITSTATIC FIBERS AND FABRICS AND GARMENTS MADE
THEREFROM AND METHODS FOR MAKING SAME

FIELD OF THE INVENTION

The invention relates to flame-resistant spun staple yarns, and fabrics and
15 garments comprising these yarns, and methods of making the same. The yarns
contain a blend of polymeric staple fiber containing a polymer or copolymer
derived from a monomer selected from the group consisting of
4,4'diaminodiphenyl sulfone, 3,3'diaminodiphenyl sulfone, and mixtures thereof;
staple fiber having low thermal shrinkage; antistatic staple fiber; and flame
20 resistant fibers having a limiting oxygen index of 21 or greater.

BACKGROUND OF THE INVENTION

Workers that can be exposed to flames, high temperatures, and/or
electrical arcs and the like, need protective clothing and articles made from
thermally resistant fabrics. Any increase in the effectiveness of these protective
25 articles, or any increase in the comfort or durability of these articles while
maintaining protection performance, is welcomed.

E. I. du Pont de Nemours and Company of Wilmington, Delaware offers
several fiber blends for use in yarns, fabrics, and protective apparel. These are
currently available in several forms including blends offered under the trade
30 names Nomex® T-462, which is a staple blend of 93% Nomex® meta-aramid
fiber, 5% Kevlar® para-aramid fiber, and 2% antistatic carbon core nylon fiber;
and Nomex® N302, which is a staple blend of 93% producer colored Nomex®
meta-aramid fiber, 5% producer colored Kevlar® para-aramid fiber, and 2%
antistatic carbon core nylon fiber.

35 A fiber known as polysulfonamide fiber (PSA) is made from a poly
(sulfone-amide) polymer and has good thermal resistance due to its aromatic

content and also has low modulus, which imparts more flexibility to fabrics made from the fiber; however, the fiber has low tensile break strength. This low tensile strength in fibers has a major impact on the mechanical properties of fabrics made from these fibers with the most obvious result being a decrease in the durability of 5 the fabrics and articles made from the fabrics. This low durability limits the ability to utilize this comfortable fiber in protective apparel. Therefore what is needed is a way of incorporating PSA into yarns for use in protective apparel that utilizes the benefits of the PSA fiber while compensating for the limitations of the fiber.

SUMMARY OF THE INVENTION

10

In some embodiments, this invention relates to a flame-resistant spun yarn, woven fabric, and protective garment, comprising at least 25 parts by weight of a polymeric staple fiber containing a polymer or copolymer derived from a monomer selected from the group consisting of 4,4'diaminodiphenyl sulfone, 15 3,3'diaminodiphenyl sulfone, and mixtures thereof; 2 to 15 parts by weight of a fiber having low thermal shrinkage; 1 to 5 parts by weight of an antistatic fiber; and the remainder being flame resistant fibers having a limiting oxygen index of 21 or greater, based on 100 total parts by weight of the polymeric fiber, the low thermal shrinkage fiber, the antistatic fiber, and the flame resistant fibers in the 20 yarn.

In some other embodiments, this invention concerns a method of producing a flame-resistant spun yarn comprising forming a fiber mixture of at least 25 parts by weight of a polymeric staple fiber containing a polymer or copolymer derived from a monomer selected from the group consisting of 25 4,4'diaminodiphenyl sulfone, 3,3'diaminodiphenyl sulfone, and mixtures thereof; 2 to 15 parts by weight of a fiber having low thermal shrinkage; 1 to 5 parts by weight of an antistatic fiber; and the remainder being flame resistant fibers having a limiting oxygen index of 21 or greater, based on 100 total parts by weight of the polymeric fiber, the low thermal shrinkage fiber, the antistatic fiber, and the flame 30 resistant fibers in the yarn; and spinning the fiber mixture into a spun staple yarn.

DETAILED DESCRIPTION

This invention concerns a flame-resistant spun staple yarn made from a mixture comprising a polymeric staple fiber derived from a diamino diphenyl sulfone monomer, a staple fiber having low thermal shrinkage; and an antistatic staple fiber, with the remainder being flame resistant fiber having a limiting oxygen index of 21 or greater. By "flame resistant" it is meant the spun staple yarn, or fabrics made from the yarn, will not support a flame in air. In preferred embodiments the fabrics have a limiting oxygen index (LOI) of 26 and higher.

For purposes herein, the term "fiber" is defined as a relatively flexible, macroscopically homogeneous body having a high ratio of length to the width of the cross-sectional area perpendicular to that length. The fiber cross section can be any shape, but is typically round. Herein, the term "filament" or "continuous filament" is used interchangeably with the term "fiber."

As used herein, the term "staple fibers" refers to fibers that are cut to a desired length or are stretch broken, or fibers that occur naturally with or are made having a low ratio of length to the width of the cross-sectional area perpendicular to that length when compared with filaments. Man made staple fibers are cut or made to a length suitable for processing on cotton, woolen, or worsted yarn spinning equipment. The staple fibers can have (a) substantially uniform length, (b) variable or random length, or (c) subsets of the staple fibers have substantially uniform length and the staple fibers in the other subsets have different lengths, with the staple fibers in the subsets mixed together forming a substantially uniform distribution.

In some embodiments, suitable staple fibers have a length of 0.25 centimeters (0.1 inches) to 30 centimeters (12 inches). In some embodiments, the length of a staple fiber is from 1 cm (0.39 in) to about 20 cm (8 in). In some preferred embodiments the staple fibers made by short staple processes have a staple fiber length of 1 cm (0.39 in) to 6 cm (2.4 in).

The staple fibers can be made by any process. For example, the staple fibers can be cut from continuous straight fibers using a rotary cutter or a guillotine cutter resulting in straight (i.e., non crimped) staple fiber, or additionally cut from crimped continuous fibers having a saw tooth shaped crimp

along the length of the staple fiber, with a crimp (or repeating bend) frequency of preferably no more than 8 crimps per centimeter.

The staple fibers can also be formed by stretch breaking continuous fibers resulting in staple fibers with deformed sections that act as crimps. Stretch broken 5 staple fibers can be made by breaking a tow or a bundle of continuous filaments during a stretch break operation having one or more break zones that are a prescribed distance creating a random variable mass of fibers having an average cut length controlled by break zone adjustment.

Spun staple yarn can be made from staple fibers using traditional long and 10 short staple ring spinning processes that are well known in the art. For short staple, cotton system spinning fiber lengths from 1.9 to 5.7 cm (0.75 in to 2.25 in) are typically used. For long staple, worsted or woolen system spinning, fibers up to 16.5 cm (6.5 in) are typically used. However, this is not intended to be limiting to ring spinning because the yarns may also be spun using air jet spinning, open 15 end spinning, and many other types of spinning which converts staple fiber into useable yarns.

Spun staple yarns can also be made directly by stretch breaking using stretch-broken tow to top staple processes. The staple fibers in the yarns formed by traditional stretch break processes typically have length of up to 18 cm (7 in) 20 long. However spun staple yarns made by stretch breaking can also have staple fibers having maximum lengths of up to 50 cm (20 in.) through processes as described for example in PCT Patent Application No. WO 0077283. Stretch broken staple fibers normally do not require crimp because the stretch-breaking process imparts a degree of crimp into the fiber.

25 The term continuous filament refers to a flexible fiber having relatively small-diameter and whose length is longer than those indicated for staple fibers. Continuous filament fibers and multifilament yarns of continuous filaments can be made by processes well known to those skilled in the art.

By polymeric fibers containing a polymer or copolymer derived from a 30 amine monomer selected from the group consisting of 4,4'diaminodiphenyl sulfone, 3,3'diaminodiphenyl sulfone, and mixtures thereof, it is meant the polymer fibers were made from a monomer generally have the structure:



wherein Ar₁ and Ar₂ are any unsubstituted or substituted six-membered aromatic group of carbon atoms and Ar₁ and Ar₂ can be the same or different. In some preferred embodiments Ar₁ and Ar₂ are the same. Still more preferably, the six-
5 membered aromatic group of carbon atoms has *meta*- or *para*-oriented linkages versus the SO₂ group. This monomer or multiple monomers having this general structure are reacted with an acid monomer in a compatible solvent to create a polymer. Useful acids monomers generally have the structure of

10



wherein Ar₃ is any unsubstituted or substituted aromatic ring structure and can be the same or different from Ar₁ and/or Ar₂. In some preferred embodiments Ar₃ is a six-membered aromatic group of carbon atoms. Still more preferably, the six-
15 membered aromatic group of carbon atoms has *meta*- or *para*-oriented linkages. In some preferred embodiments Ar₁ and Ar₂ are the same and Ar₃ is different from both Ar₁ and Ar₂. For example, Ar₁ and Ar₂ can be both benzene rings having *meta*-oriented linkages while Ar₃ can be a benzene ring having *para*-oriented linkages. Examples of useful monomers include terephthaloyl chloride,
20 isophthaloyl chloride, and the like. In some preferred embodiments, the acid is terephthaloyl chloride or its mixture with isophthaloyl chloride and the amine monomer is 4,4'diaminodiphenyl sulfone. In some other preferred embodiments, the amine monomer is a mixture of 4,4'diaminodiphenyl sulfone and 3,3'diaminodiphenyl sulfone in a weight ratio of about 3:1, which creates a fiber
25 made from a copolymer having both sulfone monomers.

In still another preferred embodiment, the polymeric fibers contain a copolymer, the copolymer having both repeat units derived from sulfone amine monomer and an amine monomer derived from paraphenylene diamine and/or metaphenylene diamine. In some preferred embodiments the sulfone amide repeat units are present in a weight ratio of about 3:1 to other amide repeat units. In some embodiments, at least 80 mole percent of the amine monomers is a sulfone amine monomer or a mixture of sulfone amine monomers. For convenience, herein the abbreviation "PSA" will be used to represent all of the entire classes of fibers

made with polymer or copolymer derived from sulfone monomers as previously described.

In one embodiment, the polymer and copolymer derived from a sulfone monomer can preferably be made via polycondensation of one or more types of 5 diamine monomer with one or more types of chloride monomers in a dialkyl amide solvent suchs as N-methyl pyrrolidone, dimethyl acetamide, or mixtures thereof. In some embodiments of the polymerizations of this type an inorganic salt such as lithium chloride or calcium chloride is also present. If desired the polymer can be isolated by precipitation with non-solvent such as water, neutralized, 10 washed, and dried. The polymer can also be made via interfacial polymerization which produces polymer powder directly that can then be dissolved in a solvent for fiber production.

The polymer or copolymer can be spun into fibers via solution spinning, using a solution of the polymer or copolymer in either the polymerization solvent 15 or another solvent for the polymer or copolymer. Fiber spinning can be accomplished through a multi-hole spinneret by dry spinning, wet spinning, or dry-jet wet spinning (also known as air-gap spinning) to create a multi-filament yarn or tow as is known in the art. The fibers in the multi-filament yarn or tow after spinning can then be treated to neutralize, wash, dry, or heat treat the fibers 20 as needed using conventional technique to make stable and useful fibers.

Exemplary dry, wet, and dry-jet wet spinning processes are disclosed U.S. Patent Nos. 3,063,966; 3,227,793; 3,287,324; 3,414,645; 3,869,430; 3,869,429; 3,767,756; and 5,667,743.

Specific methods of making PSA fibers or copolymers containing sulfone 25 amine monomers are disclosed in Chinese Patent Publication 1389604A to Wang et al. This reference discloses a fiber known as polysulfonamide fiber (PSA) made by spinning a copolymer solution formed from a mixture of 50 to 95 weight percent 4,4'diaminodiphenyl sulfone and 5 to 50 weight percent 3,3'diaminodiphenyl sulfone copolymerized with equimolar amounts of 30 terephthaloyl chloride in dimethylacetamide. Chinese Patent Publication 1631941A to Chen et al. also discloses a method of preparing a PSA copolymer spinning solution formed from a mixture of 4,4'diaminodiphenyl sulfone and 3,3'diaminodiphenyl sulfone in a mass ratio of from 10:90 to 90:10 copolymerized with equimolar amounts of terephthaloyl chloride in

dimethylacetamide. Still another method of producing copolymers is disclosed in United States Patent No. 4,169,932 to Sokolov et al. This reference discloses preparation of poly(paraphenylene) terephthalamide (PPD-T) copolymers using tertiary amines to increase the rate of polycondensation. This patent also discloses 5 the PPD-T copolymer can be made by replacing 5 to 50 mole percent of the paraphenylene diamine (PPD) by another aromatic diamine such as 4,4'diaminodiphenyl sulfone.

The spun staple yarns have 2 to 15 parts by weight of a fiber having low thermal shrinkage. By "low thermal shrinkage" it is meant that the fiber does not 10 excessively shrink when exposed to a flame, that is, the length of the fiber will not shorten more than five percent when exposed to a flame in air. In some preferred embodiments, the fiber actually lengthens when exposed to a high heat flux. In some preferred embodiments, the fiber retains 90 percent of its fiber weight when heated in air to 500 C at a rate of 20 degrees C per minute. In some embodiments 15 the fibers are flame resistant organic fibers, with flame resistant meaning the fiber or a fabric made from the fiber has a Limiting Oxygen Index (LOI) such that the fiber or fabric will not support a flame in air, the preferred LOI of 26 or greater. Fabrics containing at least 2 percent by weight such low thermal shrinkage fibers, when combined with other flame resistant fibers, have limited amount of cracks 20 and openings or break open when burned by an impinging flame. Larger amounts of low thermal shrinkage fibers provide more protection to break open up to a practical limit of about 15 percent by weight. Above this amount the affect on shrinkage reaches a point of diminishing returns.

Useful low thermal shrinkage staple fibers include fiber made from para- 25 aramid, polybenzazole, polybenzimidazole, polypyridazole, and/or polyimide polymer. The preferred low thermal shrinkage fiber is made from para-aramid polymer.

By aramid is meant a polyamide wherein at least 85% of the amide (-CONH-) linkages are attached directly to two aromatic rings. Additives can be 30 used with the aramid and, in fact, it has been found that up to as much as 10 percent, by weight, of other polymeric material can be blended with the aramid or that copolymers can be used having as much as 10 percent of other diamine substituted for the diamine of the aramid or as much as 10 percent of other diacid chloride substituted for the diacid chloride of the aramid. In some embodiments,

the preferred para-aramid is poly(paraphenylene terephthalamide). Methods for making para-aramid fibers are generally disclosed in, for example, United States Patent Nos. 3,869,430; 3,869,429; and 3,767,756. Various forms of such aromatic polyamide organic fibers are sold under the trademarks of Kevlar® and Twaron®

5 by respectively, E. I. du Pont de Nemours and Company, of Wilmington, Delaware; and Teijin, Ltd, of Japan. Also, fibers based on copoly(p-phenylene/3,4'-diphenyl ether terephthalamide) are defined as para-aramid fibers as used herein. One commercially available version of these fibers is known as Technora® fiber also available from Teijin, Ltd.

10 Commercially available polybenzazole fibers useful in this invention include Zylon® PBO-AS (Poly(p-phenylene-2,6-benzobisoxazole) fiber, Zylon® PBO-HM (Poly(p-phenylene-2,6-benzobisoxazole)) fiber, available from Toyobo, Japan. Commercially available polybenzimidazole fibers useful in this invention include PBI® fiber available from Celanese Acetate LLC. Commercially 15 available polyimide fibers useful in this invention include P-84® fiber available from LaPlace Chemical.

20 The spun staple yarns also have 1 to 5 parts by weight of an antistatic fiber that reduce the propensity for static buildup on the fabric. In some preferred embodiments the fiber for imparting this antistatic property is a sheath-core fiber having a nylon sheath and a carbon core. Suitable materials for supplying antistatic properties are described in United States Patent Nos. 3,803,453 and 4,612,150.

25 The polymeric staple fiber derived from the sulfone monomers is combined with low thermal shrinkage fiber and antistatic fiber, with the remainder being flame resistant fibers having a limiting oxygen index of 21 or greater. In some preferred embodiments the flame resistant fiber is present in the yarn in an amount of from 25 to 50 parts by weight, in some other preferred embodiments the flame resistant fiber is present in an amount substantially equal to the amount of polymeric staple fiber derived from sulfone monomers in the spun yarn.

30 Suitable flame resistant fibers include such fibers as polyimide-amide fibers, melamine fibers, and phenolic fibers. Other possible flame resistant fibers include those made from polyoxadiazole, sheath-core fibers where the sheath polymer has a high LOI, polyphenylene sulfide, liquid crystalline polyesters, melt-processible fluoropolymers, polysulfones such as polyphenyl sulfone,

polyetherimides, polyimide, and polyazoles such as polybibenzimidazole and polybenzobisoxazole.

In some embodiments, this invention relates to a flame-resistant spun yarn, woven fabric, and protective garment, comprising at least 25 parts by weight of a 5 polymeric staple fiber containing a polymer or copolymer derived from a monomer selected from the group consisting of 4,4'diaminodiphenyl sulfone, 3,3'diaminodiphenyl sulfone, and mixtures thereof; 2 to 15 parts by weight of a fiber having low thermal shrinkage; 1 to 5 parts by weight of an antistatic fiber; and the remainder being flame resistant fibers having a limiting oxygen index of 10 21 or greater; based on the total amount (100 total parts) by weight of the polymeric fiber, the low thermal shrinkage fiber, the antistatic fiber, and the flame resistant fibers in the yarn. In some preferred embodiments the polymeric staple fiber is present in an amount of 50 to 75 parts by weight. In some other preferred embodiments the polymeric staple fiber is present in an amount of 60 to 70 parts 15 by weight.

In some preferred embodiments the various types of staple fibers are present as a staple fiber blend. By fiber blend it is meant the combination of two or more staple fiber types in any manner. Preferably the staple fiber blend is an "intimate blend", meaning the various staple fibers in the blend form a relatively 20 uniform mixture of the fibers. In some embodiments the two or more staple fiber types are blended prior to or while the yarn is being spun so that the various staple fibers are distributed homogeneously in the staple yarn bundle.

Fabrics can be made from the spun staple yarns and can include, but is not limited to, woven or knitted fabrics. General fabric designs and constructions are 25 well known to those skilled in the art. By "woven" fabric is meant a fabric usually formed on a loom by interlacing warp or lengthwise yarns and filling or crosswise yarns with each other to generate any fabric weave, such as plain weave, crowfoot weave, basket weave, satin weave, twill weave, and the like. Plain and twill weaves are believed to be the most common weaves used in the 30 trade and are preferred in many embodiments.

By "knitted" fabric is meant a fabric usually formed by interlooping yarn loops by the use of needles. In many instances, to make a knitted fabric spun staple yarn is fed to a knitting machine which converts the yarn to fabric. If desired, multiple ends or yarns can be supplied to the knitting machine either plied

of unplied; that is, a bundle of yarns or a bundle of plied yarns can be co-fed to the knitting machine and knitted into a fabric, or directly into a article of apparel such as a glove, using conventional techniques. In some embodiments it is desirable to add functionality to the knitted fabric by co-feeding one or more other 5 staple or continuous filament yarns with one or more spun staple yarns having the intimate blend of fibers. The tightness of the knit can be adjusted to meet any specific need. A very effective combination of properties for protective apparel has been found in for example, single jersey knit and terry knit patterns.

In some particularly useful embodiments, the spun staple yarns can be 10 used to make flame-resistant garments. In some embodiments the garments can have essentially one layer of the protective fabric made from the spun staple yarn. Exemplary garments of this type include jumpsuits and coveralls for fire fighters or for military personnel. Such suits are typically used over the firefighters clothing and can be used to parachute into an area to fight a forest fire. Other 15 garments can include pants, shirts, gloves, sleeves and the like that can be worn in situations such as chemical processing industries or industrial electrical/utility where an extreme thermal event might occur. In some preferred embodiments the fabrics have an arc resistance of at least 0.8 calories per square centimeter per ounce per square yard.

20 In another embodiment, this invention relates to a method of producing a flame-resistant spun yarn comprising forming a fiber mixture of at least 25 parts by weight of a polymeric staple fiber containing a polymer or copolymer derived from a monomer selected from the group consisting of 4,4'diaminodiphenyl sulfone, 3,3'diaminodiphenyl sulfone, and mixtures thereof; 2 to 15 parts by 25 weight of a fiber having low thermal shrinkage; 1 to 5 parts by weight of an antistatic fiber; and the remainder being flame resistant fibers having a limiting oxygen index of 21 or greater; based on the total amount (100 total parts) by weight of the polymeric fiber, the low thermal shrinkage fiber, the antistatic fiber, and the flame resistant fibers in the yarn; and spinning the fiber mixture into a 30 spun staple yarn. In some preferred embodiments the polymeric staple fiber is present in an amount of 50 to 75 parts by weight. In some other embodiments, the polymeric staple fiber is present in an amount of 60 to 70 parts by weight.

In one embodiment the fiber mixture is formed by making an intimate blend of the fibers. If desired, other staple fibers can be combined in this relatively

uniform mixture of staple fibers. The blending can be achieved by any number of ways known in the art, including processes that creel a number of bobbins of continuous filaments and concurrently cut the two or more types of filaments to form a blend of cut staple fibers; or processes that involve opening bales of

5 different staple fibers and then opening and blending the various fibers in openers, blenders, and cards; or processes that form slivers of various staple fibers which are then further processed to form a mixture, such as in a card to form a sliver of a mixture of fibers. Other processes of making an intimate fiber blend are possible as long as the various types of different fibers are relatively uniformly distributed

10 throughout the blend. If yarns are formed from the blend, the yarns have a relatively uniform mixture of the staple fibers also. Generally, in most preferred embodiments the individual staple fibers are opened or separated to a degree that is normal in fiber processing to make a useful fabric, such that fiber knots or slubs and other major defects due to poor opening of the staple fibers are not present in

15 an amount that detract from the final fabric quality.

In a preferred process, the intimate staple fiber blend is made by first mixing together staple fibers obtained from opened bales, along with any other staple fibers, if desired for additional functionality. The fiber blend is then formed into a sliver using a carding machine. A carding machine is commonly

20 used in the fiber industry to separate, align, and deliver fibers into a continuous strand of loosely assembled fibers without substantial twist, commonly known as carded sliver. The carded sliver is processed into drawn sliver, typically by, but not limited to, a two-step drawing process.

Spun staple yarns are then formed from the drawn sliver using techniques

25 including conventional cotton system or short-staple spinning processes such as open-end spinning and ring-spinning; or higher speed air spinning techniques such as Murata air-jet spinning where air is used to twist the staple fibers into a yarn. The formation of spun yarns can also be achieved by use of conventional woolen system or long-staple processes such as worsted or semi-worsted ring-spinning or

30 stretch-break spinning. Regardless of the processing system, ring-spinning is the generally preferred method for making the spun staple yarns.

TEST METHODS

Basis weight values were obtained according to FTMS 191A; 5041.

5 Abrasion Test. The abrasion performance of fabrics is determined in accordance with ASTM D-3884-01 “Standard Guide for Abrasion Resistance of Modacrylic Fabrics (Rotary Platform, Double Head Method)”.

Instrumented Thermal Manikin Test. Burn protection performance is determined using “Predicted Burn Injuries for a Person Wearing a Specific 10 Garment or System in a Simulated Flash Fire of Specific Intensity” in accordance with ASTM F 1930 Method (1999) using an instrumented thermal mannequin with standard pattern coverall made with the test fabric.

Arc Resistance Test. The arc resistance of fabrics is determined in accordance with ASTM F-1959-99 “Standard Test Method for Determining the 15 Arc Thermal Performance Value of Materials for Clothing”. The Arc Thermal Performance Value (ATPV) of each fabric, which is a measure of the amount of energy that a person wearing that fabric could be exposed to that would be equivalent to a 2nd degree burn from such exposure 50% of the time.

Grab Test. The grab resistance of fabrics (the break tensile strength) is 20 determined in accordance with ASTM D-5034-95 “Standard Test Method for Breaking Strength and Elongation of Fabrics (Grab Test)”.

Tear Test. The tear resistance of fabrics is determined in accordance with ASTM D-5587-03 “Standard Test Method for Tearing of Fabrics by Trapezoid Procedure”.

25 Thermal Protection Performance (TPP) Test. The thermal protection performance of fabrics is determined in accordance with NFPA 2112 “Standard on Flame Resistant Garments for Protection of Industrial Personnel Against Flash Fire”. The thermal protective performance relates to a fabric’s ability to provide continuous and reliable protection to a wearer’s skin beneath a fabric when the 30 fabric is exposed to a direct flame or radiant heat.

Vertical Flame Test. The char length of fabrics is determined in accordance with ASTM D-6413-99 “Standard Test Method for Flame Resistance of Textiles (Vertical Method)”.

Limiting Oxygen Index (LOI) is the minimum concentration of oxygen, expressed as a volume percent, in a mixture of oxygen and nitrogen that will just support the flaming combustion of a material initially at room temperature under the conditions of ASTM G125 / D2863.

5

Examples

The invention is illustrated by, but is not intended to be limited by the following examples. All parts and percentages are by weight unless otherwise indicated.

Example 1

10

This example illustrates flame-resistant spun yarns and fabrics of intimate blends of PSA staple fiber, m-aramid staple fiber, p-aramid staple fiber, and antistatic polyamide staple fiber. The PSA staple fiber is made from a polymer made from 4,4'diaminodiphenyl sulfone and 3,3'diaminodiphenyl sulfone 15 copolymerized with equimolar amounts of terephthaloyl chloride in dimethylacetamide and is known under the common designation of Tanlon®; The m-aramid fiber is made from poly(metaphenylene isophthalamide) polymer and is marketed by E. I. du Pont de Nemours & Company under the trademark NOMEX® fiber. The p-aramid fiber is made from poly(phenylene 20 terephthalamide) polymer and is marketed by E. I. du Pont de Nemours & Company under the trademark of Kevlar® 29. The antistatic polyamide staple fiber has a nylon sheath and carbon core and is known as P-140 nylon fiber (available from Invista).

A picker blend sliver of 33 wt.% of the m-aramid fiber, 5% wt.% of the p-25 aramid fiber, 2 wt. % of the antistatic fiber, and 60% of PSA fiber is prepared and processed by the conventional cotton system equipment and is then spun into a spun staple yarn having twist multiplier 4.0 and a single yarn size of about 21 tex (28 cotton count) using a ring spinning frame. Two such single yarns are then plied on a plying machine to make a flame resistant yarn for use as a fabric warp 30 yarn. Using a similar process and the same twist and blend ratio, a 24 tex (24 cotton count) singles yarn is made and two of these single yarns are plied to form a two-ply fabric fill yarn.

The ring spun yarns of intimate blends are then used as the warp and fill yarns and are woven into a fabric on a shuttle loom, making a greige fabric having a 2x1

twill weave and a construction of 26 ends x 17 picks per cm (72 ends x 52 picks per inch), and a basis weight of about 215 g/m² (6.5 oz/yd²). The greige twill fabric is then scoured in hot water and is dried under low tension. The scoured fabric is then jet dyed using basic dye. The resulting fabric has a basis weight of 5 about 231 g/m² (7 oz/yd²) and an LOI in excess of 28. Table 1 illustrates properties of the resulting fabric. A “+” indicates superior properties to those of the control fabric, while the notation “0” indicates the performance of the control fabric or performance equivalent to the control fabric. A “0/+” means the performance is slightly better than the control fabric.

10

Table 1

Property	100%PSA	Example 1
Nominal Basis Weight (opsy)	7	7
Grab Test Break Strength (lbf) W/F	0	+
Trap Tear (lbf) W/F	0	+
Taber Abrasion (Cycles)CS-10/1000 g	0	+
TPP (cal/cm²)	0	0/+
Vertical Flame (in) W/F	0	+
Instrumented Thermal Manikin Test (% of body burn)	0	+
ARC rating(cal/cm²)	0	+

Example 2

15

The fabric of Example 1 is made into protective articles, including garments, by cutting the fabric into fabric shapes per a pattern and sewing the shapes together to form a protective coverall for use as protective apparel in industry. Likewise, the fabric is cut into fabric shapes and the shapes sewn together to form a protective apparel combination comprising a protective shirt

and a pair of protective pants. If desired, the fabric is cut and sewn to form other protective apparel components such as, coveralls, hoods, sleeves, and aprons.

CLAIMS**What is Claimed:**

1. A flame-resistant spun yarn comprising:
 - 5 at least 25 parts by weight of a polymeric staple fiber containing a polymer or copolymer derived from a monomer selected from the group consisting of 4,4'diaminodiphenyl sulfone, 3,3'diaminodiphenyl sulfone, and mixtures thereof;
 - 10 2 to 15 parts by weight of a fiber having low thermal shrinkage;
 - 15 1 to 5 parts by weight of an antistatic fiber; and the remainder being flame resistant fibers having a limiting oxygen index of 21 or greater; based on 100 total parts by weight of the polymeric fiber, the low thermal shrinkage fiber, the antistatic fiber, and the flame resistant fibers in the yarn.
- 15 2. The flame-resistant spun yarn of claim 1 wherein the polymeric staple fiber is present in an amount of 50 to 75 parts by weight.
3. The flame-resistant spun yarn of claim 2 wherein the polymeric staple fiber is present in an amount of 60 to 70 parts by weight.
4. The flame-resistant spun yarn of claim 1 wherein at least 80 mole percent 20 of the polymer or copolymer used in the polymeric staple fiber is derived from a sulfone amine monomer or a mixture of sulfone amine monomers.
5. The flame-resistant spun yarn of claim 1 wherein the polymeric polymer further contains a polymer or copolymer derived from the monomer selected from the group of terephthaloyl chloride, isophthaloyl chloride, and mixtures thereof.
- 25 6. A woven fabric comprising the yarn of claim 1.
7. A protective garment comprising the yarn of claim 1.
8. A method of producing a flame-resistant spun yarn comprising:
 - a) forming a fiber mixture of at least 25 parts by weight of a polymeric staple fiber containing a polymer or copolymer derived from a

monomer selected from the group consisting of 4,4'diaminodiphenyl sulfone, 3,3'diaminodiphenyl sulfone, and mixtures thereof; 2 to 15 parts by weight of a fiber having low thermal shrinkage; 1 to 5 parts by weight of an antistatic fiber; and the remainder being flame resistant fibers having a limiting oxygen index of

5 21 or greater, based on 100 total parts by weight of the polymeric fiber, the low thermal shrinkage fiber, the antistatic fiber, and the flame resistant fibers in the yarn; and

b) spinning the fiber mixture into a spun staple yarn.

9. The method of producing a flame-resistant spun yarn of claim 8 wherein

10 the polymeric staple fiber is present in an amount of 50 to 75 parts by weight.

10. The method of producing a flame-resistant spun yarn of claim 9 wherein the polymeric staple fiber is present in an amount of 60 to 70 parts by weight.

11. The method of producing a flame-resistant spun yarn of claim 8 wherein at least 80 mole percent of the polymer or copolymer used in the polymeric staple

15 fiber is derived from a sulfone amine monomer or a mixture of sulfone amine monomers.

12. The method of producing a flame-resistant spun yarn of claim 8 wherein the polymeric polymer further contains a polymer or copolymer derived from the monomer selected from the group of terephthaloyl chloride, isophthaloyl chloride,

20 and mixtures thereof.

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2008/073940

A. CLASSIFICATION OF SUBJECT MATTER
INV. D01F6/76 D01F6/80 D02G3/04

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
D01F D02G

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	CN 1 389 604 A (SHANGHAI TEXTILE HOLDING GROUP [CN]) 8 January 2003 (2003-01-08) cited in the application abstract	1-12
A	GB 875 068 A (ICI LTD) 16 August 1961 (1961-08-16) the whole document	1-12
A	US 3 621 646 A (BOBKOWICZ EMILIAN ET AL) 23 November 1971 (1971-11-23) the whole document	1-12

Further documents are listed in the continuation of Box C:

See patent family annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

22 October 2008

Date of mailing of the international search report

07/11/2008

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040,
Fax: (+31-70) 340-3016

Authorized officer

Lux, Rudolf

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/US2008/073940

Patent document cited in search report	Publication date	Patent family member(s)		Publication date
CN 1389604	A	08-01-2003		NONE
GB 875068	A	16-08-1961		NONE
US 3621646	A	23-11-1971	BE	751703 A1
			CA	880988 A
			CH	519594 A
			DE	2042762 A1
			FR	2057698 A5
			GB	1285003 A
			JP	49009424 B
			NL	7013252 A