



US008937335B2

(12) **United States Patent**
Weeks, Jr. et al.

(10) **Patent No.:** **US 8,937,335 B2**
(45) **Date of Patent:** **Jan. 20, 2015**

(54) **GALLIUM NITRIDE DEVICES WITH
ALUMINUM NITRIDE INTERMEDIATE
LAYER**

H01L 21/0243 (2013.01); *H01L 21/02458*
(2013.01); *H01L 21/02507* (2013.01); *H01L*
21/0251 (2013.01); *H01L 21/0254* (2013.01);
H01L 33/007 (2013.01); *H01L 33/32*
(2013.01);

(71) Applicant: **International Rectifier Corporation**, El
Segundo, CA (US)

(Continued)

(72) Inventors: **T. Warren Weeks, Jr.**, Raleigh, NC
(US); **Edwin L. Piner**, Cary, NC (US);
Thomas Gehrke, Boise, ID (US); **Kevin**
J. Linthicum, Angier, NC (US)

(58) **Field of Classification Search**
USPC 257/180, 183, 191, 192, 200, 201
See application file for complete search history.

(73) Assignee: **International Rectifier Corporation**, El
Segundo, CA (US)

(56) **References Cited**

U.S. PATENT DOCUMENTS

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 0 days.

6,611,002 B2 8/2003 Weeks
6,617,060 B2 9/2003 Weeks

(Continued)

(21) Appl. No.: **14/083,923**

OTHER PUBLICATIONS

(22) Filed: **Nov. 19, 2013**

(65) **Prior Publication Data**

US 2014/0131659 A1 May 15, 2014

Related U.S. Application Data

F. Semond et al., "GaN grown on Si(III) substrate: From two-dimen-
sional growth to quantum well assessment," *Applied Physics Letters*,
vol. 75, No. 1, Jul. 5, 1999, pp. 82-84.

(Continued)

(60) Continuation of application No. 13/728,956, filed on
Dec. 27, 2012, now Pat. No. 8,592,862, which is a
continuation of application No. 13/359,892, filed on
Jan. 27, 2012, now Pat. No. 8,344,417, which is a
continuation of application No. 12/343,616, filed on
Dec. 24, 2008, now Pat. No. 8,105,921, which is a
division of application No. 10/675,798, filed on Sep.
30, 2003, now abandoned, which is a continuation of
application No. 09/736,972, filed on Dec. 14, 2000,
now Pat. No. 6,649,287.

Primary Examiner — Kevin M Picardat

(74) *Attorney, Agent, or Firm* — Farjami & Farjami LLP

(51) **Int. Cl.**
H01L 29/66 (2006.01)
H01L 29/15 (2006.01)


(Continued)

(52) **U.S. Cl.**
CPC *H01L 29/155* (2013.01); *C30B 23/02*
(2013.01); *C30B 25/02* (2013.01); *C30B 25/18*
(2013.01); *C30B 29/403* (2013.01); *C30B*
29/406 (2013.01); *H01L 21/02381* (2013.01);

(57) **ABSTRACT**

The invention provides semiconductor materials including a
gallium nitride material layer formed on a silicon substrate
and methods to form the semiconductor materials. The semi-
conductor materials include a transition layer formed
between the silicon substrate and the gallium nitride material
layer. The transition layer is compositionally-graded to lower
stresses in the gallium nitride material layer which can result
from differences in thermal expansion rates between the gal-
lium nitride material and the substrate. The lowering of
stresses in the gallium nitride material layer reduces the ten-
dency of cracks to form. Thus, the invention enables the
production of semiconductor materials including gallium
nitride material layers having few or no cracks. The semicon-
ductor materials may be used in a number of microelectronic
and optical applications.

20 Claims, 11 Drawing Sheets



(51)	Int. Cl.		7,687,888 B2	3/2010	Marchand	
	C30B 23/02	(2006.01)	7,816,764 B2	10/2010	Marchand	
	C30B 25/02	(2006.01)	8,105,921 B2 *	1/2012	Weeks et al.	438/483
	C30B 25/18	(2006.01)	8,344,417 B2 *	1/2013	Weeks et al.	257/183
	C30B 29/40	(2006.01)	8,525,230 B2	9/2013	Marchand	
	H01L 21/02	(2006.01)	8,592,862 B2 *	11/2013	Weeks et al.	257/183
	H01L 33/00	(2010.01)	2002/0020341 A1	2/2002	Marchand	
	H01L 33/32	(2010.01)				
	H01L 29/205	(2006.01)				
	H01L 29/225	(2006.01)				
	H01L 29/20	(2006.01)				

OTHER PUBLICATIONS

(52)	U.S. Cl.					
	CPC	H01L29/205	(2013.01);	H01L 29/225	
				(2013.01);	H01L 29/2003	(2013.01)
	USPC	257/183 ;	257/192;	257/200	

(56) **References Cited**

U.S. PATENT DOCUMENTS

6,649,287 B2 11/2003 Weeks
7,655,090 B2 2/2010 Marchand

M. Seon et al., "Selective growth of high quality GaN on Si(III) substrates," Applied Physics Letters, vol. 76, No. 14, Apr. 3, 2000, pp. 1842-1844.

S. Guha et al., "Ultraviolet and Violet GaN Light Emitting Diodes on Silicon," Applied Physics Letters, vol. 72, No. 4, Jan. 26, 1998, pp. 415-417.

U.S. Appl. No. 60/222,837, filed Aug. 4, 2000, Marchand.

* cited by examiner




Fig. 1




Fig. 2A




Fig. 2B




Fig. 2C




Fig. 2D




Fig. 2E




Fig. 2F




Fig. 2G




Fig. 2H




Fig. 2I




Fig. 3A




Fig. 3B




Fig. 4A




Fig. 4B




Fig. 5




Fig. 6




Fig. 7




Fig. 8




Fig. 9




Fig. 10




Fig. 11

1

GALLIUM NITRIDE DEVICES WITH ALUMINUM NITRIDE INTERMEDIATE LAYER

This is a continuation of application Ser. No. 12/343,616
filed Dec. 24, 2008.

RELATED APPLICATIONS

This application is a divisional of U.S. patent application
Ser. No. 10/675,798, filed Sep. 30, 2003, and entitled "Gal-
lium Nitride Materials and Methods", which is a continuation
of U.S. patent application Ser. No. 09/736,972, filed Dec. 14,
2000, and entitled "Gallium Nitride Materials and Methods",
both of which are incorporated herein by reference in their
entireties.

FIELD OF INVENTION

The invention relates generally to semiconductor materials
and, more particularly, to gallium nitride materials and meth-
ods of producing gallium nitride materials.

BACKGROUND OF INVENTION

Gallium nitride materials include gallium nitride (GaN)
and its alloys such as aluminum gallium nitride (AlGaN),
indium gallium nitride (InGaN), and aluminum indium gal-
lium nitride (AlInGaN). These materials are semiconductor
compounds that have a relatively wide, direct bandgap which
permits highly energetic electronic transitions to occur. Such
electronic transitions can result in gallium nitride materials
having a number of attractive properties including the ability
to efficiently emit blue light, the ability to transmit signals at
high frequency, and others. Accordingly, gallium nitride
materials are being widely investigated in many microelec-
tronic applications such as transistors, field emitters, and
optoelectronic devices.

In many applications, gallium nitride materials are grown
on a substrate. However, differences in the properties
between gallium nitride materials and substrates can lead to
difficulties in growing layers suitable for many applications.
For example, gallium nitride (GaN) has a different thermal
expansion coefficient (i.e., thermal expansion rate) than many
substrate materials including sapphire, silicon carbide, and
silicon. This difference in thermal expansion can lead to
cracking of a gallium nitride layer deposited on such sub-
strates when the structure is cooled, for example, during
processing. The cracking phenomena can prevent gallium
nitride materials from being suitable for use in many appli-
cations. Cracking can be particularly problematic for rela-
tively thick (e.g., >0.5 micron) gallium nitride layers.

Gallium nitride (GaN) also has a different lattice constant
than most substrate materials. The difference in lattice con-
stant may lead to the formation of defects in gallium nitride
material layers deposited on substrates. Such defects can
impair the performance of devices formed using the gallium
nitride material layers.

Prior art techniques have been developed to address crack
formation and defect formation in gallium nitride materials
deposited on sapphire substrates and silicon carbide sub-
strates. Such techniques, for example, may involve depositing
one or more buffer layers on the substrate and, then, depos-
iting the gallium nitride material on the buffer layer(s).

SUMMARY OF INVENTION

The invention provides semiconductor materials including
a gallium nitride material layer formed on a silicon substrate

2

and methods to form the semiconductor materials. The semi-
conductor materials include a transition layer formed
between the silicon substrate and the gallium nitride material
layer. The transition layer is compositionally-graded to lower
stresses in the gallium nitride material layer which can result
from differences in thermal expansion rates between the gal-
lium nitride material and the substrate. The lowering of
stresses in the gallium nitride material layer reduces the ten-
dency of cracks to form which enables the production of
semiconductor materials including gallium nitride material
layers having few or no cracks. The semiconductor materials
may be used in a number of microelectronic and optical
applications.

The invention has overcome the problem of growing gal-
lium nitride materials having few or no cracks on silicon
substrates which, due to the large differences in both thermal
expansion rate and lattice constant between gallium nitride
materials (e.g., GaN) and silicon, is considerably more chal-
lenging than on other types of substrates (e.g., SiC and sap-
phire).

In one aspect, the invention provides a semiconductor
material. The material includes a silicon substrate and a com-
positionally-graded transition layer formed over the silicon
substrate. The material further includes a gallium nitride
material layer formed over the transition layer.

In another aspect, the invention provides a semiconductor
material. The semiconductor material includes a silicon sub-
strate and a gallium nitride material layer formed over the
silicon substrate. The gallium nitride material layer has a
crack level of less than $0.005 \mu\text{m}/\mu\text{m}^2$.

In another aspect, the invention provides a semiconductor
structure. The semiconductor structure includes a silicon sub-
strate, and a gallium nitride material layer formed over the
silicon substrate. The gallium nitride material layer has a
thickness of greater than 0.5 micron. The semiconductor
structure forms a semiconductor device.

In another aspect, the invention provides a method of pro-
ducing a semiconductor material. The method includes the
steps of forming a compositionally-graded transition layer
over a silicon substrate, and forming a gallium nitride mate-
rial layer over the transition layer.

In another aspect, the invention provides a method of pro-
ducing a semiconductor material. The method includes form-
ing a gallium nitride material layer formed over a silicon
substrate. The gallium nitride material layer has a crack level
of less than $0.005 \mu\text{m}/\mu\text{m}^2$.

In another aspect, the invention provides a method of form-
ing a semiconductor structure. The method includes forming
a semiconductor structure comprising a silicon substrate, and
a gallium nitride material layer formed over the silicon sub-
strate. The gallium nitride material layer has a thickness of
greater than 0.5 micron.

In another aspect, the invention provides a semiconductor
material. The semiconductor material comprises a silicon
(100) substrate and a gallium nitride material layer having a
Wurtzite structure formed over the silicon substrate.

Other advantages, aspects, and features of the invention
will become apparent from the following detailed description
of the invention when considered in conjunction with the
accompanying drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 illustrates a semiconductor material including a
compositionally-graded transition layer according to one
embodiment of the present invention.

FIGS. 2A to 2I are exemplary profiles of the concentration of an element as a function of the thickness across the compositionally-graded transition layer.

FIGS. 3A and 3B illustrate a semiconductor material that includes a superlattice transition layer according to another embodiment of the present invention.

FIGS. 4A and 4B are exemplary profiles of the concentration of an element as a function of the thickness of the transition layers in the semiconductor materials of FIGS. 3A and 3B, respectively.

FIG. 5 illustrates a textured substrate used to form the semiconductor material according to one embodiment of the present invention.

FIG. 6 illustrates a semiconductor material including an intermediate layer between the substrate and the transition layer formed on a silicon substrate with a transition layer as described in Example 1.

FIG. 7 illustrates an LED formed from the semiconductor material according to another embodiment of the present invention.

FIG. 8 illustrates a laser diode formed from the semiconductor material according to another embodiment of the present invention.

FIG. 9 illustrates a FET formed from the semiconductor material according to another embodiment of the present invention.

FIG. 10 is a micrograph of the surface of a gallium nitride layer formed on a silicon substrate with a transition layer as described in Example 1.

FIG. 11 is a micrograph of the surface of a gallium nitride layer formed on a silicon substrate without a transition layer as described in comparative Example 2.

DETAILED DESCRIPTION OF THE INVENTION

The invention provides semiconductor materials including a gallium nitride material layer and a process to produce the semiconductor materials. As used herein, the phrase "gallium nitride material" refers to gallium nitride and any of its alloys, such as aluminum gallium nitride ($\text{Al}_x\text{Ga}_{(1-x)}\text{N}$), indium gallium nitride ($\text{In}_y\text{Ga}_{(1-y)}\text{N}$), aluminum indium gallium nitride ($\text{Al}_x\text{In}_y\text{Ga}_{(1-x-y)}\text{N}$), gallium arsenide phosphoride nitride ($\text{GaAs}_a\text{P}_b\text{N}_{(1-a-b)}$), aluminum indium gallium arsenide phosphoride nitride ($\text{Al}_x\text{In}_y\text{Ga}_{(1-x-y)}\text{As}_a\text{P}_b\text{N}_{(1-a-b)}$), amongst others. Typically, when present, arsenic and/or phosphorous are at low concentrations (i.e., less than 5 weight percent).

Referring to FIG. 1, a semiconductor material 10 according to one embodiment of the invention is shown. Semiconductor material 10 includes a transition layer 12 formed over a silicon substrate 14 and a gallium nitride material layer 16 formed over the transition layer. As described further below, transition layer 12 is compositionally-graded to reduce internal stresses within gallium nitride material layer 16 that can result from differences between the thermal expansion rates of substrate 14 and the gallium nitride material layer. The internal stresses may arise, for example, when semiconductor material 10 is cooled after the deposition of gallium nitride material layer 16 and substrate 14 contracts more rapidly than the gallium nitride material layer. As a result of the reduced internal stresses, gallium nitride material layer 16 can be formed with a low crack level making semiconductor material 10 suitable for use in a number of applications including FETs, LEDs, laser diodes, and the like.

It should be understood that when a layer is referred to as being "on" or "over" another layer or substrate, it can be directly on the layer or substrate, or an intervening layer may also be present. It should also be understood that when a layer

is referred to as being "on" or "over" another layer or substrate, it may cover the entire layer or substrate, or a portion of the layer or substrate.

As used herein, the term "compositionally-graded layer" refers to a layer having a composition that varies across at least a portion of the thickness of the layer. Thus, transition layer 12 includes at least two different compositions at different depths within the layer. As described further below, the composition of transition layer 12 can be varied in a number of ways. It is generally advantageous to vary the composition of transition layer 12 in a manner that provides sufficient strain relief to limit or prevent the formation of cracks in gallium nitride material layer 16.

According to one set of embodiments, transition layer 12 is composed of an alloy of gallium nitride such as $\text{Al}_x\text{In}_y\text{Ga}_{(1-x-y)}\text{N}$, $\text{Al}_x\text{Ga}_{(1-x)}\text{N}$, and $\text{In}_y\text{Ga}_{(1-y)}\text{N}$. It should be understood, however, that transition layers having other compositions may also be used. In embodiments which utilize alloys of gallium nitride, the concentration of at least one of the elements (e.g., Ga, Al, In) of the alloy is typically varied across at least a portion of the thickness of the transition layer. When transition layer 12 has an $\text{Al}_x\text{In}_y\text{Ga}_{(1-x-y)}\text{N}$ composition, x and/or y is varied. When transition layer 12 has a $\text{Al}_x\text{Ga}_{(1-x)}\text{N}$ composition, x is varied. When transition layer 12 has a $\text{In}_y\text{Ga}_{(1-y)}\text{N}$ composition, y is varied.

In certain preferred embodiments, it is desirable for transition layer 12 to have a low gallium concentration at back surface 18 and a high gallium concentration at front surface 20. It has been found that such transition layers are particularly effective in relieving internal stresses within gallium nitride material layer 16. Decreasing the gallium concentration of a gallium nitride alloy transition layer can make the thermal expansion rate of the alloy more similar to the thermal expansion rate of silicon. As described further below, gallium nitride material layer 16 typically includes a high gallium concentration. Thus, in these embodiments, increasing the concentration of gallium in transition layer 12 can make the thermal expansion rate of the alloy more similar to the thermal expansion rate of gallium nitride material layer 16. It is believed that in these preferred embodiments effective strain relief is achievable because back surface 18 has a relatively similar thermal expansion rate as substrate 14, while front surface 20 has a relatively similar thermal expansion rate as gallium nitride material layer 16.

In some cases, the sum of (x+y) at back surface 18 is greater than 0.4, greater than 0.6, greater than 0.8 or even higher. In some preferred embodiments, (x+y)=1 at back surface 18, so that transition layer 12 is free of gallium at the back surface. In some cases, the sum of (x+y) is less than 0.3, less than 0.2, or even less at front surface 20. In some preferred embodiments, the sum of (x+y)=0 at front surface 20, so that transition layer 12 has a composition of GaN at the front surface. It may be particularly preferred for transition layer 12 to have a composition of GaN at front surface 20, when gallium nitride material layer 16 has a composition of GaN. In other cases when gallium nitride material layer is composed of an alloy of GaN, it may be preferable for the composition of transition layer 12 at front surface 20 to be the same as the composition of gallium nitride material layer 16. In some cases, transition layer 12 is free of gallium at back surface 18 and has a composition of GaN at front surface 20.

In certain embodiments, it may be preferable for transition layer 12 to comprise $\text{Al}_x\text{Ga}_{(1-x)}\text{N}$. In these cases, the transition layer is free of indium. In other cases, transition layer 12 may include a small amount of indium, for example, less than 10 percent by weight. When indium is present in transition layer 12 (i.e., $\text{Al}_x\text{In}_y\text{Ga}_{(1-x-y)}\text{N}$), the concentration of indium (i.e.,

5

y) may remain constant throughout the transition layer, while the concentration of gallium and aluminum are graded.

The composition in transition layer 12 may be graded across its thickness in a number of different manners. For example, the composition may be graded continuously, discontinuously, across the entire thickness, or across only a portion of the thickness. As described above, the composition may be graded by varying the concentration of one or more of the elements (i.e., Ga, Al, In). FIGS. 2A to 2I illustrate exemplary manners in which the composition may be graded by varying the concentration of one of the elements as a function of thickness across transition layer 12. In certain preferred embodiments, the profiles represent the concentration of gallium across the thickness of transition layer 12, though it should be understood that in other embodiments the profiles may represent the concentration of other elements (i.e., Al or In). The convention in FIGS. 2A to 2I is that the thickness of transition layer 12 increases in the direction away from substrate 14 (i.e., $t=0$ at back surface 18 and $t=1$ at front surface 20).

FIG. 2A shows a step-wise variation of concentration as a function of thickness which includes multiple steps. FIG. 2B shows a step-wise variation of concentration as a function of thickness which includes two steps. FIG. 2C shows a saw tooth variation of concentration as a function of thickness. FIG. 2D shows continuous variations of concentration at a constant rate as a function of thickness. FIG. 2E shows a continuous variation of concentration at a constant rate starting from a non-zero concentration. FIGS. 2F and 2G show continuous variations of concentration as a function of thickness at exponential rates. FIG. 2H shows a discontinuous variation of concentration as a function of thickness. FIG. 2I shows a variation of the concentration across a portion of the thickness of the transition layer.

It should be understood that the profiles illustrated in FIGS. 2A to 2I are intended to be exemplary and that the composition of transition layer 12 may be graded in other manners that are within the scope of the present invention.

Referring to FIGS. 3A and 3B, transition layer 12 may be a compositionally-graded strained layer superlattice 22 according to another embodiment of the present invention. Superlattice 22 includes alternating layers 24a, 24b of semiconductor compounds having different compositions. In some cases, the composition across each individual layer 24a, 24b is varied according to any of the manners described above. In other cases, the composition of individual layers 24a, 24b is constant across the thickness of the individual layer as shown in the concentration profile of FIGS. 4A and 4B. As shown in FIGS. 3B (and 4B), the thicknesses of individual layers 24a, 24b is varied across transition layer 12 to provide compositional grading.

In one preferred set of embodiments, superlattice 22 comprises alternating layers of gallium nitride alloys having different compositions. For example, layer 24a has a composition of $\text{Al}_x\text{In}_y\text{Ga}_{(1-x-y)}\text{N}$ and layer 24b has a composition of $\text{Al}_a\text{In}_b\text{Ga}_{(1-a-b)}\text{N}$, wherein $x \neq a$ and $y \neq b$. In cases when the composition is graded across each individual layer, the concentration of at least one of the elements (i.e., Al, In, Ga) of the alloy can be varied according to any of the manners described above. In cases when the composition of individual layers 24a, 24b is constant (FIG. 3B), the gallium concentration is typically different in individual layers 24a, 24b.

As described above, it may be desirable to have a low gallium concentration at back surface 18 and a high gallium concentration at front surface 20. In embodiments that utilize superlattice 22 as transition layer 12, increasing the gallium concentration in a direction away from back surface 18 can be

6

accomplished by varying the thickness of individual layers. As shown in FIGS. 3B and 4B, layer 24a has a low gallium concentration and layer 24b has a high gallium concentration. As shown, layers 24a are relatively thick and layers 24b are relatively thin proximate back surface 18. The thickness of layers 24a is decreased and the thickness of layers 24b is increased in a direction away from back surface 18. Thus, layers 24a are relatively thin and layers 24b are relatively thick proximate front surface 20. This structure provides a low gallium concentration at back surface 18 and a high gallium concentration at front surface 20.

It should be understood that transition layer 12 may be formed of a combination of a single layer having a graded composition and a superlattice. In some cases, the superlattice is formed over the single compositionally-graded layer. In other cases, the single compositionally-graded layer is formed over the superlattice.

Transition layer 12 can have a variety of thicknesses depending on the application. Generally, though not always, transition layer 12 has a thickness of less than about 500 microns. In some cases, relatively thick transition layers are preferable, for example between about 2.0 microns and about 20 microns. Thick transition layers may be preferred when thick gallium nitride material layers (i.e., greater than 5 microns) are produced. In some cases, relatively thin transition layers are preferable, for example between about 0.03 micron and about 2.0 microns. When superlattice structures are used as transition layers, the thickness of individual layers 24a, 24b depends upon the particular application. Typically the thickness of individual layers 24a, 24b may be between about 0.001 microns and about 0.020 microns. As described above, the thicknesses of individual layers may vary across transition layer 12 (FIG. 3B).

Gallium nitride material layer 16 is formed of gallium nitride (GaN) or any of its alloys including aluminum gallium nitride ($\text{Al}_x\text{Ga}_{(1-x)}\text{N}$), indium gallium nitride ($\text{In}_y\text{Ga}_{(1-y)}\text{N}$), and aluminum indium gallium nitride ($\text{Al}_x\text{In}_y\text{Ga}_{(1-x-y)}\text{N}$). The composition of gallium nitride material layer 16 is generally constant across its thickness as distinguished with transition layer 12. Thus, x and/or y are generally fixed when gallium nitride material is formed of any of the aforementioned compound alloys. It should be understood that small variations in the composition of gallium nitride material layer 16 may occur, for example, as a result of slight non-uniformities and inhomogeneities during growth.

In certain preferred embodiments, gallium nitride material layer 16 has a high concentration of gallium and includes little or no amounts of aluminum and/or indium. In high gallium concentration embodiments, the sum of (x+y) may be less than 0.4, less than 0.2, less than 0.1, or even less. In some cases, it is preferable for gallium nitride material layer 16 to have a composition of GaN (i.e., $x+y=0$).

As described above, gallium nitride material layer 16 has a low crack level as a result of the ability of transition layer 12 to relieve stress arising from differences in thermal expansion rates between the silicon substrate and the gallium nitride material. A "crack," as used herein, is a linear fracture or a cleavage having a length to width ratio of greater than 5:1 that extends to the surface of the gallium nitride material. It should be understood that a crack may or may not extend through the entire thickness of the gallium nitride material. "Crack level" is defined as a total measure of all crack lengths in a gallium nitride material per unit surface area. Crack level can be expressed in units of $\mu\text{m}/\mu\text{m}^2$. The crack level of a gallium nitride material can be measured, for example, using optical microscopy techniques. To determine the crack level, the length of all of the cracks in a given area (i.e., 1 mm \times 1 mm)

are added together and divided by the total surface area. If necessary, this process may be repeated at a number of locations across the surface to provide a measurement representative of the entire gallium nitride material. The crack level at each location may be averaged to provide a crack level for the material. The number of locations depends upon the amount of surface area of the gallium nitride material. When measuring the crack level of a gallium nitride material, measurements are not made within a region proximate to edges of the material known as an edge exclusion. The nominal edge exclusion is 5 mm from the edge. Edge effects in such regions may lead to increased crack levels and are typically not used in device formation.

Gallium nitride material layer **16** advantageously has a low crack level. In some cases, gallium nitride material layer **16** has a crack level of less than $0.005 \mu\text{m}/\mu\text{m}^2$. In some cases, gallium nitride material has a very low crack level of less than $0.001 \mu\text{m}/\mu\text{m}^2$. In certain cases, it may be preferable for gallium nitride material layer **16** to be substantially crack-free as defined by a crack level of less than $0.0001 \mu\text{m}/\mu\text{m}^2$.

Gallium nitride material layer **16** preferably has a monocrystalline structure. In preferred cases, gallium nitride material layer **16** has a Wurtzite (hexagonal) structure. Preferably, the entire gallium nitride material layer has a Wurtzite structure. The gallium nitride material layer **16** is generally of high enough quality so as to permit the formation of devices therein. In some embodiments, gallium nitride material layer **16** has a relatively low amount of defects (e.g., less than 10^9 cm^{-2}) which, for example, result from the lattice mismatch between gallium nitride and silicon.

The thickness of gallium nitride material layer **16** is dictated, in part, by the requirements of the specific application. In applications when gallium nitride material is used as a device layer, the thickness is sufficient to permit formation of the device. Gallium nitride material layer **16** generally has a thickness of greater than 0.1 micron, though not always. In other cases, thicker gallium nitride material layers are desired such as thicknesses greater than 0.5 micron, greater than 0.75 micron, greater than 1.0 microns, greater than 2.0 microns, or even greater than 5.0 microns. Even thick gallium nitride material layers **16** are achievable at low crack densities because of the presence of transition layer **12**. In relatively thick gallium nitride layers, upper regions of the layer may include low amounts of defects due to the tendency of defects to annihilate one another as they propagate vertically through the layer. Thus, in these cases, the use of thick gallium nitride layers may improve device performance.

Silicon substrate **14** typically is formed of high-quality single-crystal silicon as readily available in the art. Silicon substrates **14** having different crystallographic orientations may be used. In some cases, silicon (111) substrates are preferred. In other cases, silicon (100) substrates are preferred. Gallium nitride material layer **16** having a Wurtzite structure may be grown on silicon (111) substrates and silicon (100) substrates using transition layer **12**. It is particularly surprising that gallium nitride material layer **16** having a Wurtzite structure may grown on silicon (100) substrates because conventional techniques generally result in gallium nitride materials having a mixture of zinc blend (cubic) and Wurtzite structures when grown on silicon (100) substrates.

Silicon substrate may have any dimensions as used in the art. Suitable diameters include, but are not limited to, 2 inches, 4 inches, 6 inches, and 8 inches. In some embodiments, silicon substrate **14** is relatively thick, for example, greater than 250 microns. Thicker substrates are generally able to resist bending which can occur, in some cases, in thinner substrates.

As used herein, silicon substrate **14** refers to any substrate that includes a silicon layer at its top surface. Examples of suitable silicon substrates include substrates that are composed entirely of silicon (e.g., silicon wafers), silicon-on-insulator (SOI) substrates, silicon-on-sapphire substrate (SOS), SIMOX substrates, amongst others.

Referring to FIG. 5, silicon substrate **14** is textured according to some embodiments of the present invention. As illustrated, textured substrate **14** includes a plurality of posts **24** which define trenches **26** therebetween. Such texturing can be provided using selective etching and/or selective epitaxial growth. Etching may be performed using standard dry or wet etching techniques, such as with a mask which later may be removed. In some cases, textured substrates are used in conjunction with the transition layers described herein to grow gallium nitride material layers with very low defect densities (e.g., less than 10^7 cm^{-2}). Silicon substrate **14** may also be pre-patterned to include mask areas which selectively expose regions of the substrate, while covering other regions. Such pre-patterned substrates enable selective area epitaxial growth which may be advantageous in minimizing defect densities.

Referring to FIG. 6, semiconductor material **10** includes an intermediate layer **28** between silicon substrate **14** and transition layer **12** according to another embodiment of the present invention. It should be understood that intermediate layer **28** may also be positioned between transition layer **12** and gallium nitride material layer **16**. Intermediate layer **28**, when provided, may further relieve stress in gallium nitride material layer **16**. Intermediate layer generally has a thickness of less than about 500 microns and, in some cases, between about 0.01 micron and about 2.0 microns. The presence of intermediate layer **28** may permit reduction of the thickness of transition layer **12**. The composition of the intermediate layer is generally constant throughout its thickness.

Intermediate layer **28**, for example, can be composed of a GaN alloy such as aluminum gallium nitride ($\text{Al}_x\text{Ga}_{(1-x)}\text{N}$), indium gallium nitride ($\text{In}_y\text{Ga}_{(1-y)}\text{N}$), and aluminum indium gallium nitride ($\text{Al}_x\text{In}_y\text{Ga}_{(1-x-y)}\text{N}$). In these cases, the sum of (x+y) in the intermediate layer may be greater than 0.4, greater than 0.6, greater than 0.8, greater than 0.9, or even more. In some preferred cases, the intermediate layer is free of gallium and is composed of $\text{Al}_x\text{In}_y\text{N}$ or AlN . GaN alloy intermediate layers with low Ga concentrations may be effective at relieving stresses because they have a thermal expansion rate relatively close to the thermal expansion rate of silicon substrate **14**.

It should be understood that intermediate layer **28** may be utilized in accordance with any of the embodiments described herein including embodiments that use a superlattice as a transition layer. In embodiments in which transition layer **12** includes a single compositionally-graded layer and a superlattice, the intermediate layer may be positioned between the compositionally-graded layer and the superlattice. In some embodiments of the invention, more than one intermediate layer **28** having different compositions may be provided.

According to one preferred method, transition layer **12** and gallium nitride material layer **16** are grown using a metalorganic chemical vapor deposition (MOCVD) process. It should be understood that other suitable techniques known in the art may also be utilized to deposit transition layer **12** and gallium nitride material layer **16** including molecular beam epitaxy (MBE), hydride vapor phase epitaxy (HVPE), and the like.

Generally, the MOCVD process involves introducing different source gases into an environment (e.g., a process system) around a substrate and providing conditions which pro-

mote a reaction between the gases to form a layer on the substrate surface. The reaction proceeds until a layer of desired thickness is achieved. The composition of the layer may be controlled, as described further below, by several factors including gas composition, gas concentration, and the reaction conditions (e.g. temperature and pressure).

Examples of suitable source gases for MOCVD growth of the transition layer include trimethylaluminum (TMA) or triethylaluminum (TEA) as sources of aluminum; trimethylindium (TMI) or triethylindium (TEI) as sources of indium; trimethylgallium (TMG) or triethylgallium (TEG) as sources of gallium; and ammonia (NH₃) as a source of nitrogen. The particular source gas used depends upon the desired composition of the transition layer. For example, an aluminum source (e.g., TMA or TEA), a gallium source (TMG or TEG), and a nitrogen source are used to deposit films having an Al_xGa_{1-x}N composition.

The flow rates of the source gases, the ratios of the source gases, and the absolute concentrations of the source gases may be controlled to provide transition layers having the desired composition. For the growth of Al_xGa_{1-x}N layers, typical TMA flow rates are between about 5 μmol/min and about 50 μmol/min with a flow rate of about 20 μmol/min being preferred in some cases; typical TMG flow rates are between about 5 μmol/min and 250 μmol/min, with a flow rate of 115 μmol/min being preferred in some cases; and the flow rate of ammonia is typically between about 3 slpm to about 10 slpm. The reaction temperatures are generally between about 900° C. and about 1200° C. and the process pressures are between about 1 Torr and about 760 Torr. It is to be understood that the process conditions, and in particular the flow rate, are highly dependent on the process system configuration. Typically, smaller throughput systems require less flow than larger throughput systems.

Process parameters are suitably adjusted to control the compositional grading of the transition layer. The composition may be graded by changing the process conditions to favor the growth of particular compositions. For example, to increase incorporation of gallium in the transition layer thereby increasing the gallium concentration, the flow rate and/or the concentration of the gallium source (e.g., TMG or TEG) may be increased. Similarly, to increase incorporation of aluminum into the transition layer thereby increasing the aluminum concentration, the flow rate and/or the concentration of the aluminum source (e.g., TMA or TEA) may be increased. The manner in which the flow rate and/or the concentration of the source is increased (or decreased) controls the manner in which the composition is graded. In other embodiments, the temperature and/or pressure is adjusted to favor the growth of a particular compound. Growth temperatures and pressures favoring the incorporation of gallium into the transition layer differ from the growth temperatures and pressures favoring the incorporation of aluminum into the transition layer. Thus, the composition may be graded by suitably adjusting temperature and pressure.

Typical growth rates of the transition layer are between about 0.01 μm/hr and about 3.0 μm/hr. The growth rate depends upon the process parameters as well as the composition of the layer.

The gallium nitride material layer (and intermediate layers, if present) may also be grown using an MOCVD process. The process may utilize source gases and process parameters similar to those described above for the deposition of the transition layer. The particular source gases and process parameters are selected based upon the desired composition. When depositing the gallium nitride material layer (or the

intermediate layer), however, the process parameters are maintained constant so as to provide a film having a constant composition.

The semiconductor materials of the invention may be used in a variety of applications. In some cases, semiconductor material **10** is processed using known techniques to form a semiconductor device. Doped regions may be formed within gallium nitride material layer **16** and additional layers may be deposited upon the gallium nitride material layer to produce the desired semiconductor structure. In some embodiments, gallium nitride material layer **16** is doped using known techniques to achieve a desired conductivity.

Any suitable semiconductor device known in the art including electronic and optical devices can be produced using semiconductor material **10**. Exemplary devices include LEDs, laser diodes, FETs (e.g., HFETs) amongst others.

FIG. **7** schematically illustrates an exemplary LED **30** formed from semiconductor material **10**. LED **30** includes silicon-doped gallium nitride material layer **16** formed on transition layer **12** on silicon substrate **14**. In the illustrative embodiment, the following layers are formed on gallium nitride material layer **16** in succession: a silicon-doped Al_xGa_(1-x)N layer **31** (containing 0-20% by weight Al), a GaN/InGaN single or multiple quantum well **32**, a magnesium-doped Al_xGa_(1-x)N layer **34** (containing 10-20% by weight Al), and a magnesium-doped GaN layer **36**. LED **30** includes a p-type metal contact **38** on magnesium-doped GaN layer **36** and an n-type metal contact pad **39** on silicon-doped gallium nitride material layer **16**. LED **30** may be provided as a variety of different structure including: a double heterostructure (e.g., Al>0% in layer **31**), a single heterostructure (e.g., Al=0% in layer **31**), a symmetric structure, or an asymmetric structure. It should be understood that LED may have a variety of different structures as known to those of ordinary skill in the art.

FIG. **8** schematically illustrates an exemplary laser diode **40** formed from semiconductor material **10**. Laser diode **40** includes silicon-doped gallium nitride material layer **16** formed on transition layer **12** on silicon substrate **14**. In the illustrative embodiment, the following layers are formed on gallium nitride material layer **16** in succession: a silicon-doped Al_xGa_(1-x)N layer **42** (containing 5-30% by weight Al), a silicon-doped Al_xGa_(1-x)N layer **44** (containing 0-20% by weight Al), a GaN/InGaN single or multiple quantum well **46**, a magnesium-doped Al_xGa_(1-x)N layer **48** (containing 5-20% by weight Al), a magnesium-doped Al_xGa_(1-x)N layer **50** (containing 5-30% by weight Al), and a magnesium-doped GaN layer **52**. Laser diode **40** includes a p-type metal contact **38** on magnesium-doped GaN layer **52** and an n-type metal contact pad **39** on silicon-doped gallium nitride material layer **16**. It should be understood that laser diode **40** may have a variety of different structures as known to those of ordinary skill in the art.

FIG. **9** schematically illustrates a FET **54** (e.g., HFET) formed from semiconductor material **10**. FET **54** includes intrinsic gallium nitride material layer **16** formed on transition layer **12** on silicon substrate **14**. FET **54** includes an Al_xGa_(1-x)N layer **56** (containing 10-40% by weight Al). It should be understood that FET **54** may have a variety of different structures as known to those of ordinary skill in the art.

The function and advantage of these and other embodiments of the present invention will be more fully understood from the examples below. The following examples are

11

intended to illustrate the benefits of the present invention, but do not exemplify the full scope of the invention.

EXAMPLE 1

Production of Gallium Nitride Layer Using A Compositionally Graded Transition Layer

This example illustrates the effectiveness of a compositionally-graded transition layer in limiting the number of cracks in a gallium nitride material grown on a silicon substrate.

An MOCVD process was used to grow an AlN intermediate layer, an $\text{Al}_x\text{Ga}_{1-x}\text{N}$ compositionally-graded transition layer, and a GaN layer in succession on a silicon substrate.

A silicon substrate having a 2-inch diameter and a thickness of 250 microns was positioned in an MOCVD system. To grow the AlN intermediate layer, trimethylaluminum gas (TMA) was introduced into the MOCVD system at a flow rate of about 50 $\mu\text{mol}/\text{min}$ and ammonia gas (NH_3) was introduced into the system at a flow rate of between about 3 and about 10 slpm. A growth temperature of between about 1000-1100° C. and a growth pressure 30-200 Torr were maintained in the system. After about 60 minutes, an AlN intermediate layer was formed having a thickness of about 0.3 micron on the silicon substrate.

After the growth of the intermediate layer, trimethylgallium (TMG) was introduced into the system at a flow rate of about 5 $\mu\text{mol}/\text{min}$ to provide a ratio of TMA:TMG of about 10:1. To form the compositionally-graded transition layer, the flow rate of the TMA was decreased to about 5 $\mu\text{mol}/\text{min}$, while the flow rate of TMG was increased to about 115 $\mu\text{mol}/\text{min}$. Over this time, the ratio of TMA:TMG was decreased from about 10:1 to about 1:23. After about 30 minutes, a compositionally-graded transition layer having a thickness of about 0.4 micron was grown on the intermediate layer.

To grow the gallium nitride layer on the transition layer, the introduction of TMA into the system was stopped and the TMG flow rate was adjusted to about 115 $\mu\text{mol}/\text{min}$. The flow rate of ammonia was maintained between about 3 and about 10 slpm. The growth temperature was maintained between about 1000 and about 1050° C. and the growth pressure between about 30 and about 200 Torr. After about 45 minutes, a GaN layer having a thickness of about 1.5 micron was grown on the compositionally-graded transition layer. The semiconductor material was furnace-cooled to room temperature and removed from the MOCVD system for analysis.

The resulting semiconductor material included a 0.3 micron AlN intermediate layer formed on the silicon substrate; a 0.4 micron thick continuously graded $\text{Al}_x\text{Ga}_{1-x}\text{N}$ transition layer formed on the intermediate layer; and a 1.5 micron GaN layer grown on the transition layer. The composition of the $\text{Al}_x\text{Ga}_{1-x}\text{N}$ transition layer was graded from $x=0.8$ at the juncture with the intermediate layer to $x=0$ at the juncture with the GaN layer. The GaN layer had a monocrystalline structure.

The crack level of the semiconductor material was measured using an optical microscopic technique. The microscope was equipped with the camera capable of taking micrographs of the surface of the GaN layer. FIG. 10 is a micrograph showing a representative area of slightly greater than 1 mm^2 on the surface of the GaN layer. No cracks are visible in the representative area. Measurements were repeated at several other locations on the surface of the GaN layer and similar results were achieved. The gallium nitride

12

material was found to be substantially crack-free as defined by a crack level of less than 0.0001 $\mu\text{m}/\mu\text{m}^2$.

This example illustrates the ability to grow gallium nitride layers having a low crack level on a silicon substrate using a compositionally-graded transition layer.

COMPARATIVE EXAMPLE 2

Production of Gallium Nitride Layer Without Using A Compositionally Graded Transition Layer

This example illustrates the generation of cracks in a gallium nitride material grown on a silicon substrate without using a compositionally-graded transition layer.

An MOCVD process was used to grow an AlN intermediate layer and a GaN layer in succession on a silicon substrate.

A silicon (111) substrate having a 2-inch diameter and a thickness of 250 microns was positioned in the same MOCVD system as used in Example 1. An AlN intermediate layer was formed using essentially the same processing conditions as the growth of the intermediate layer in Example 1. A GaN layer was grown on the intermediate layer using essentially the same processing conditions as the growth of the GaN layer in Example 1. A compositionally-graded transition layer was not grown. The semiconductor material was furnace-cooled to room temperature and removed from the MOCVD system for analysis.

The resulting semiconductor material included a 0.3 micron AlN intermediate layer formed on the silicon substrate, and a 1.5 micron GaN layer grown on the intermediate layer. The GaN layer had a monocrystalline structure.

The crack level of the GaN layer was measured using the same technique as described in Example 1. FIG. 11 is a micrograph showing a representative area of slightly greater than 1 mm^2 on the surface of the GaN layer. The length of each crack in the area was measured and added together to determine the total crack length. The total crack length was divided by the surface area to determine the crack level. Measurements were repeated at several other locations on the surface which were averaged to provide a crack level of the GaN layer of about 0.007 $\mu\text{m}/\mu\text{m}^2$.

This comparative example illustrates the presence of cracks in gallium nitride layers grown on a silicon substrate without using a compositionally-graded transition layer.

Those skilled in the art would readily appreciate that all parameters listed herein are meant to be exemplary and that the actual parameters would depend upon the specific application for which the semiconductor materials and methods of the invention are used. It is, therefore, to be understood that the foregoing embodiments are presented by way of example only and that, within the scope of the appended claims and equivalents thereto the invention may be practiced otherwise than as specifically described.

What is claimed is:

1. A semiconductor structure comprising:

a substrate;

an intermediate layer comprising aluminum nitride formed above said substrate, said intermediate layer being substantially free of gallium;

a transition layer including at least one compositionally-graded layer and a superlattice;

a gallium nitride layer formed over said transition layer.

2. The semiconductor structure of claim 1 wherein said intermediate layer comprises an aluminum nitride alloy situated between said aluminum nitride and said substrate.

13

3. The semiconductor structure of claim 1 wherein said at least one compositionally-graded layer is graded discontinuously across the thickness of the layer.

4. The semiconductor structure of claim 1 wherein said transition layer comprises an alloy of gallium nitride selected from the group consisting of $\text{Al}_x\text{In}_y\text{Ga}_{(1-x-y)}\text{N}$, $\text{In}_y\text{Ga}_{(1-y)}\text{N}$, and $\text{Al}_x\text{Ga}_{(1-x)}\text{N}$.

5. The semiconductor structure of claim 4 wherein a concentration of gallium in said transition layer is graded.

6. The semiconductor structure of claim 4 wherein x is varied from a first value at a back surface of said transition layer to a second value at a front surface of said transition layer.

7. The semiconductor structure of claim 4 wherein y is varied from a first value at a back surface of said transition layer to a second value at a front surface of said transition layer.

8. The semiconductor structure of claim 1 wherein said substrate comprises a silicon-on-insulator (SOI) substrate.

9. The semiconductor structure of claim 1 wherein said substrate comprises a silicon-on-sapphire (SOS) substrate.

10. The semiconductor structure of claim 1 wherein said substrate comprises a SIMOX substrate.

11. A semiconductor structure comprising:

a substrate;

an intermediate layer comprising aluminum nitride formed over at least one layer, said intermediate layer being substantially free of gallium, said at least one layer being situated over said substrate;

a transition layer comprising a superlattice, said transition layer not consisting entirely of said superlattice;

a gallium nitride layer formed over said transition layer.

14

12. The semiconductor structure of claim 11 wherein said at least one layer comprises an aluminum nitride alloy.

13. The semiconductor structure of claim 11 wherein said at least one compositionally-graded layer is graded discontinuously across the thickness of the layer.

14. The semiconductor structure of claim 11 wherein said transition layer comprises an alloy of gallium nitride selected from the group consisting of $\text{Al}_x\text{In}_y\text{Ga}_{(1-x-y)}\text{N}$, $\text{In}_y\text{Ga}_{(1-y)}\text{N}$, and $\text{Al}_x\text{Ga}_{(1-x)}\text{N}$.

15. The semiconductor structure of claim 14 wherein a concentration of gallium in said transition layer is graded.

16. The semiconductor structure of claim 11 wherein said substrate comprises a silicon-on-insulator (SOI) substrate.

17. The semiconductor structure of claim 11 wherein said substrate comprises a silicon-on-sapphire (SOS) substrate.

18. The semiconductor structure of claim 11 wherein said substrate comprises a SIMOX substrate.

19. A semiconductor structure comprising:

a substrate;

a substantially gallium free intermediate layer comprising first and second aluminum nitride layers formed over at least one layer, said at least one layer being situated over said substrate;

a transition layer comprising a superlattice, said transition layer not consisting entirely of said superlattice;

a gallium nitride layer formed over said transition layer.

20. The semiconductor structure of claim 19 wherein said first aluminum nitride layer is formed at a first temperature, and said second aluminum nitride layer is formed at a second temperature different from said first temperature.

* * * * *