

(10) **Patent No.:** US 6,858,523 B2  
(45) **Date of Patent:** Feb. 22, 2005

- |             |         |                  |
|-------------|---------|------------------|
| 4,764,247 A | 8/1988  | Leveriza et al.  |
| 4,805,683 A | 2/1989  | Magdo et al.     |
| 4,833,096 A | 5/1989  | Huang et al.     |
| 4,863,755 A | 9/1989  | Hess et al.      |
| 4,870,470 A | 9/1989  | Bass, Jr. et al. |
| 4,910,160 A | 3/1990  | Jennings et al.  |
| 4,940,509 A | 7/1990  | Tso et al.       |
| 4,954,867 A | 9/1990  | Hosaka           |
| 4,971,655 A | 11/1990 | Stefano et al.   |

(List continued on next page.)

FOREIGN PATENT DOCUMENTS

EP	0 471 185 A2	7/1991
EP	0 464 515 A3 B1	8/1992
EP	0 588 087 A2	8/1993

(List continued on next page.)

## OTHER PUBLICATIONS

Stanley Wolf, *Silicon Processing for the VLSI Era*, 1986, vol. 1, pp. 407–413.

Stanley Wolf, *Silicon Processing for the VLSI Era*, vol. 3, Lattice Press 1995, p. 635.

(List continued on next page.)

*Primary Examiner*—David S. Blum

(74) *Attorney, Agent, or Firm*—Wells St. John P.S.

(57)

## ABSTRACT

The invention includes a semiconductor processing method. A first material comprising silicon and nitrogen is formed. A second material is formed over the first material, and the second material comprises silicon and less nitrogen, by atom percent, than the first material. An imagable material is formed on the second material, and patterned. A pattern is then transferred from the patterned imagable material to the first and second materials. The invention also includes a structure comprising a first layer of silicon nitride over a substrate, and a second layer on the first layer. The second layer comprises silicon and is free of nitrogen. The structure further comprises a third layer consisting essentially of imagable material on the second layer.

### 5 Claims, 5 Drawing Sheets

[illegible]

## U.S. PATENT DOCUMENTS

4,992,306 A	2/1991	Hochberg et al.	5,874,367 A	2/1999	Dobson
5,034,348 A	7/1991	Hartswick et al.	5,883,011 A	3/1999	Lin et al.
5,036,383 A	7/1991	Mori	5,883,014 A	3/1999	Chen et al.
5,061,509 A	10/1991	Naito et al.	5,933,721 A	8/1999	Hause et al.
5,140,390 A	8/1992	Li et al.	5,948,482 A	9/1999	Brinker et al.
5,219,613 A	6/1993	Fabry et al.	5,960,289 A	9/1999	Tsui et al.
5,234,869 A	8/1993	Mikata et al.	5,962,581 A	10/1999	Hayase et al.
5,244,537 A	9/1993	Ohnstein	5,968,324 A	10/1999	Cheung et al.
5,260,600 A	11/1993	Harada	5,968,611 A	10/1999	Kaloyeros et al.
5,270,267 A	12/1993	Ouellet	5,981,368 A	11/1999	Gardner et al.
5,286,661 A	2/1994	de Fresart et al.	5,985,519 A	11/1999	Kakamu et al.
5,302,366 A	4/1994	Schuette et al.	5,986,318 A	11/1999	Kim et al.
5,312,768 A	5/1994	Gonzalez	5,994,217 A	11/1999	Ng
5,314,724 A	5/1994	Tsukune et al.	5,994,730 A	11/1999	Shrivastava et al.
5,340,621 A	8/1994	Matsumoto et al.	6,001,741 A	12/1999	Alers
5,356,515 A	10/1994	Tahara et al.	6,001,747 A	12/1999	Annapragada
5,376,591 A	12/1994	Maeda et al.	6,004,850 A	12/1999	Lucas et al.
5,405,489 A	4/1995	Kim et al.	6,008,121 A	12/1999	Yang et al.
5,413,963 A	5/1995	Yen et al.	6,008,124 A	12/1999	Sekiguchi et al.
5,429,987 A	7/1995	Allen	6,017,779 A	1/2000	Miyasaka
5,439,838 A	8/1995	Yang	6,020,243 A	2/2000	Wallace et al.
5,441,797 A	8/1995	Hogan et al.	6,022,404 A	2/2000	Ettlinger et al.
5,461,003 A	10/1995	Havemann et al.	6,028,015 A	2/2000	Wang et al.
5,470,772 A	11/1995	Woo	6,030,901 A	2/2000	Hopper et al.
5,472,827 A	12/1995	Ogawa et al.	6,040,619 A	3/2000	Wang et al.
5,472,829 A	12/1995	Ogawa	6,054,379 A	4/2000	Yau et al.
5,482,894 A	1/1996	Havemann	6,060,765 A	5/2000	Maeda
5,498,555 A	3/1996	Lin	6,060,766 A	5/2000	Mehta et al.
5,536,857 A	7/1996	Narula et al.	6,071,799 A	6/2000	Park et al.
5,541,445 A	7/1996	Quellet	6,072,227 A	6/2000	Yau et al.
5,543,654 A	8/1996	Dennen	6,087,064 A	7/2000	Lin et al.
5,554,567 A	9/1996	Wang	6,087,267 A	7/2000	Dockrey et al.
5,591,494 A	1/1997	Sato et al.	6,096,656 A	8/2000	Matzke et al.
5,591,566 A	1/1997	Ogawa	6,114,255 A	9/2000	Juengling
5,600,165 A	2/1997	Tsukamoto et al.	6,124,641 A	9/2000	Matsuura
5,639,687 A	6/1997	Roman	6,130,168 A	10/2000	Chu et al.
5,641,607 A	6/1997	Ogawa et al.	6,133,096 A	10/2000	Su et al.
5,648,202 A	7/1997	Ogawa et al.	6,133,613 A	10/2000	Yao et al.
5,652,187 A	7/1997	Kim et al.	6,133,618 A	10/2000	Steiner
5,656,330 A	8/1997	Niiyama et al.	6,136,636 A	10/2000	Wu
5,656,337 A	8/1997	Park et al.	6,140,151 A	10/2000	Akram
5,661,093 A	8/1997	Ravi et al.	6,140,677 A	10/2000	Gardner et al.
5,667,015 A	9/1997	Harestad et al.	6,143,670 A	11/2000	Cheng et al.
5,670,297 A	9/1997	Ogawa et al.	6,153,504 A	* 11/2000	Shields et al. .... 438/613
5,674,356 A	10/1997	Nagayama	6,156,674 A	12/2000	Li et al.
5,677,015 A	10/1997	Hasegawa	6,159,804 A	12/2000	Gardner et al.
5,677,111 A	10/1997	Ogawa	6,159,871 A	12/2000	Loboda et al.
5,691,212 A	11/1997	Tsai et al.	6,184,151 B1	2/2001	Adair et al.
5,698,352 A	12/1997	Ogawa et al.	6,184,158 B1	2/2001	Shufflebotham et al.
5,709,741 A	1/1998	Akamatsu et al.	6,187,657 B1	2/2001	Xiang et al.
5,710,067 A	1/1998	Foote et al.	6,187,694 B1	2/2001	Cheng et al.
5,731,242 A	3/1998	Parat et al.	6,198,144 B1	3/2001	Pan et al.
5,741,721 A	4/1998	Stevens	6,200,835 B1	3/2001	Manning
5,744,399 A	4/1998	Rostoker et al.	6,204,168 B1	3/2001	Naik et al.
5,747,388 A	5/1998	Kusters	6,209,484 B1	4/2001	Huang et al.
5,750,442 A	5/1998	Juengling	6,225,217 B1	5/2001	Usami et al.
5,753,320 A	5/1998	Mikoshiha et al.	6,235,568 B1	5/2001	Murthy et al.
5,759,755 A	6/1998	Park et al.	6,235,591 B1	5/2001	Balasubramanian et al.
5,783,493 A	7/1998	Yeh et al.	6,238,976 B1	5/2001	Noble et al.
5,786,039 A	7/1998	Brouquet	6,268,282 B1	7/2001	Sandhu et al.
5,792,689 A	8/1998	Yang et al.	6,274,292 B1	8/2001	Holscher et al.
5,800,877 A	9/1998	Maeda et al.	6,281,100 B1	8/2001	Yin et al.
5,801,399 A	9/1998	Hattori et al.	6,284,677 B1	9/2001	Hsiao et al.
5,807,660 A	9/1998	Lin et al.	6,323,101 B1	11/2001	Li et al.
5,817,549 A	10/1998	Yamazaki et al.	6,373,114 B1	4/2002	Jeng et al.
5,831,321 A	11/1998	Nagayama	6,403,464 B1	6/2002	Chang
5,838,052 A	11/1998	McTeer	6,429,115 B1	8/2002	Tsai et al.
5,858,880 A	1/1999	Dobson	6,435,943 B1	8/2002	Chang et al.
5,872,035 A	2/1999	Kim et al.	6,436,808 B1	8/2002	Ngo et al.
5,872,385 A	2/1999	Taft et al.	6,444,593 B1	9/2002	Ngo et al.
			6,465,372 B1	10/2002	Xia et al.

6,486,057	B1	11/2002	Yeh et al.
6,486,061	B1	11/2002	Xia et al.
6,492,688	B1	12/2002	Ilg
6,498,084	B2	12/2002	Bergemont
6,503,818	B1	1/2003	Jang
6,518,122	B1	2/2003	Chan et al.
2001/0003064	A1	6/2001	Ohio
2001/0019868	A1	9/2001	Gonzalez et al.
2001/0038919	A1	11/2001	Berry, III et al.
2002/0033486	A1	3/2002	Kim et al.
2002/0081834	A1	6/2002	Daniels et al.
2003/0013311	A1	1/2003	Chang et al.

## FOREIGN PATENT DOCUMENTS

EP	0 588 087	A3	8/1993
EP	0 778 496	A2	5/1996
EP	0 771 886	A1	7/1997
EP	0 942330		9/1999
EP	1 172 845	A2	1/2002
GB	593727		10/1947
JP	63-157443		6/1988
JP	63316476		12/1988
JP	5-263255		10/1993
JP	6232113		8/1994
JP	406244172	A	9/1994
JP	7201716		8/1995
JP	08-045926	A	2/1996
JP	8046186		2/1996
JP	8046188		2/1996
JP	8051058		2/1996
JP	8078322		3/1996
JP	08-213386	A	8/1996
JP	09-050993		2/1997
JP	09055351		2/1997
JP	10-163083		6/1998
JP	06067019	A	9/1999
JP	2000068261	A	3/2000
TW	368687	A	9/1999
TW	420844	A	2/2001
TW	429473	A	4/2001

## OTHER PUBLICATIONS

Wolf, S. "Silicon Processing for the VLSI Era", vol. 2. pp. 48-49 and 435.

TEXT: Jenkins, F. et al., "Fundamentals of Optics", Properties of Light, pp. 9-10. (No date).

TEXT: Wolf, S. et al., "Silicon Processing for the VLSI Era", vol. 1, pp. 437-441. (No date).

D.R. McKenzie et al., "New Technology for PACVD", Surface and Coatings Technology, 82 (1996), pp. 326-333.

S. McClatchie et al.; "Low Dielectric Constant Flowfil® Technology For IMD Applications"; undated; 7 pages.

K. Beekmann et al.; "Sub-micron Gap Fill and In-Situ Planarisation using Flowfil<sup>SM</sup> Technology"; Oct. 1995; pp. 1-7.

A. Kiermans et al.; "Planarisation for Sub-Micron Devices Utilising a New Chemistry"; Electrotech, Feb. 1995; 2 pages.

IBM Technical Disclosure Bulletin "Low-Temperature Deposition of SiO<sub>2</sub>, Si<sub>3</sub>N<sub>4</sub> or SiO<sub>2</sub>-Si<sub>3</sub>N<sub>4</sub>," vol. 28, No. 9, p. 4170, Feb. 1986.

ARTICLE: Bencher, C. et al., "Dielectric antireflective coatings for DUV lithography", Solid State Technology (Mar. 1997), pp. 109-114.

Noboru Shibata, "Plasma-Chemical Vapor-Deposited Silicon Oxide/Silicon Oxynitride Double-Layer Antireflective Coating for Solar Cells", Japanese Journal of Applied Physics, vol. 30, No. 5, May 1991, pp. 997-1001.

Ralls, Kenneth M., "Introduction to Materials Science and Engineering", John Wiley & Sons, © 1976, pp. 312-313.

Ravi K., Laxman, "Synthesizing Low-k CVD Materials for Fab Use", Semiconductor International, Nov. 2000, 10 pps.

Anonymous, New gas helps make faster IC's. Machine Design Cleveland, © Penton Meida, Inc., Nov. 4, 1999, pp. 118.

Lobada et al. "Using Trimethylsilane to Improve Safety Throughput and Versatility in PECVD Processes", 4th International Symposium on Silicon Nitride and Silicon Dioxide Thin Insulation Films, The Electrochemical Society, Abstract No. 358, p. 454, May 1997.

ARTICLE: Dammel, R. R. et al., "Dependence of Optical Constants of AZ® BARLi™ Bottom Coating on Back Conditions", SPIE vol. 3049 (1997), pp. 963-973.

TEXT: Heavens, O. S., "Optical Properties of Thin Solid Films", pp. 48-49.

Withmall, R. et al., "Matrix Reactions of Methyisilanes and Oxygen Atoms", Phys. Chem 1988, pp. 594-602.

Weidman, T. et al., "New photodefinable glass etch masks for entirely dry photolithography: Plasma deposited organosilicon hydride polymers", Appl. Phys. Lett. 1-25-93, pp. 372-374.

Weidman, et al., "All Dry Lithography: Applications of Plasma Polymerized Methysilane as a Single Layer Resist and Silicon Dioxide Precursor". Journal of Photopolymer Science and Technology, V. 8, #4, 1995, pp. 679-686.

Joubert et al., "Applications of Plasma Polymerized Methylsilane in an all dry resist process for 193 and 248 nm Lithography", Microelectric Engineering 30 (1996), pp. 275-278.

Joshi, A.M. et al., Plasma Deposited Organosilicon Hybrid Network Polymers as Versatile Resists for Entirely Dry Mid-Deep UV Photolithography, SPIE vol. 1925, pp. 709-720.

Matsuura, M. et al., "Highly Reliable Self-Planarizing Low-k Intermetal Dielectric for Sub-quarter Micron Interconnects", IEEE 1997, pp. 785-788.

Horie, O. et al., Kinetics and Mechanism of the Reactions of . . . J. Phys. Chem 1991, 4393-4400.




U.S. Appl. No. 09/234,233, filed 01/99, Li et al.




U.S. Appl. No. 09/773,462, filed 01/01, Rolfson et al.


S. Wolf and R.N. Tauber, Silicon Processing for the VLSI Era (vol. 1-Process Technology), pp. 189-190, 1986.

Julius Grant, "Hack's Chemical Dictionary", McGraw-Hill Book Company 1969, Fourth Edition, p. 27.


\* cited by examiner











II II II II



II II II II







1

# SEMICONDUCTOR PROCESSING METHODS OF TRANSFERRING PATTERNS FROM PATTERNED PHOTORESISTS TO MATERIALS, AND STRUCTURES COMPRISING SILICON NITRIDE

## CROSS REFERENCE TO RELATED APPLICATION

This application is a divisional of U.S. patent application Ser. No. 09/488,947 now U.S. Pat. No. 6,440,860, which was filed on Jan. 18, 2000 and which is incorporated by reference herein.

## TECHNICAL FIELD

The invention pertains to methods of transferring patterns from photoresists to materials, and also pertains to structures comprising silicon nitride.

## BACKGROUND OF THE INVENTION

A commonly utilized process for patterning structures utilized for integrated circuitry is photolithographic processing. An imagable material (typically photoresist) is provided over a mass which is ultimately to be patterned. Portions of the imagable material are then exposed to radiation, while other portions remain unexposed (in the case of photoresist, the radiation is light). After the exposure, the material is subjected to conditions which selectively remove either the portions of the exposed to radiation, or the portions which were not exposed to radiation. If the imagable material comprises photoresist and the portions exposed to radiation are removed, the photoresist is referred to as a positive photoresist, whereas if the portions which are not exposed to radiation are removed the photoresist is referred to as a negative photoresist. Once the imagable material is patterned, it is utilized as a masking layer for patterning the underlying mass. Specifically, the patterned imagable material covers some portions of the mass, while leaving other portions exposed to an etch which removes the exposed portions. Accordingly, the mass remaining after the etch is in approximately the same pattern as the patterned imagable material formed over the mass.

Photolithographic processing is utilized for patterning numerous materials, including silicon nitride. However, problems can occur during the utilization of photolithographic processing for patterning silicon nitride. Specifically, the pattern formed in silicon nitride is frequently not the same as the pattern which was intended to be formed in the photoresist. Such problem can be particularly severe when utilizing photoresist patterned with deep UV light processing, wherein deep UV light is defined as ultra-violet light having a wavelength of less than or equal to 248 nanometers. It would be desirable to develop methods for avoiding the above-discussed problems.

## SUMMARY OF THE INVENTION

In one aspect, the invention includes a semiconductor processing method. A first material comprising silicon and nitrogen is formed. A second material is formed over the first material, and the second material comprises silicon and less nitrogen (by atom percent) than the first material. An imagable material is formed on the second material, and patterned. A pattern is then transferred from the patterned imagable material to the first and second materials.

In another aspect, the invention encompasses a method of forming a patterned structure. A first layer comprising sili-

2

con and nitrogen is formed over a substrate. A sacrificial layer is formed on the first layer, and comprises less nitrogen (by atom percent) than the first layer. A layer of imagable material is formed on the sacrificial layer and patterned. The patterned structure has a pair of opposing sidewalls extending upwardly from the substrate. A pair of opposing corners are defined where the sidewalls join the substrate. The opposing corners are closer to one another than they would be if the sacrificial layer was absent and the imagable material was on the first layer during the patterning of the imagable material. The sacrificial layer is removed from the patterned structure.

In yet another aspect, the invention encompasses a structure comprising a first layer of silicon nitride over a substrate, and a second layer on the first layer. The second layer comprises silicon and is free of nitrogen. The structure further comprises a third layer consisting essentially of imagable material on the second layer.

## BRIEF DESCRIPTION OF THE DRAWINGS

Preferred embodiments of the invention are described below with reference to the following accompanying drawings.

FIG. 1 is a fragmentary, diagrammatic, cross-sectional view of a semiconductor wafer fragment.

FIG. 2 is a view of the FIG. 1 fragment shown at a processing step subsequent to that of FIG. 1.

FIG. 3 is a view of the FIG. 1 fragment shown at a processing step subsequent to that of FIG. 2.

FIG. 4 is a diagrammatic, fragmentary, cross-sectional view of a semiconductor wafer fragment.

FIG. 5 is a view of the FIG. 4 fragment shown at a processing step subsequent to that of FIG. 4.

FIG. 6 is a view of the FIG. 4 fragment shown at a processing step subsequent to that of FIG. 5.

FIG. 7 is a view of the FIG. 4 fragment shown at a processing step subsequent to that of FIG. 6.

FIG. 8 is a view of the FIG. 4 fragment shown at a processing step subsequent to that of FIG. 7.

FIG. 9 is a view of the FIG. 4 fragment shown at a processing step subsequent to that of FIG. 8 in accordance with an embodiment of the present invention.

FIG. 10 is a view of the FIG. 4 fragment shown at a processing step subsequent to that of FIG. 8 in accordance with another embodiment of the present invention.

FIG. 11 is a photograph of a semiconductor wafer fragment having structures formed thereover by a particular patterning method.

FIG. 12 is a view of a semiconductor wafer fragment having structures formed thereover by a processing method different than that utilized for forming the structures of FIG. 11.

## DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

This disclosure of the invention is submitted in furtherance of the constitutional purposes of the U.S. Patent Laws "to promote the progress of science and useful arts" (Article 1, Section 8).

A method of utilizing photoresist for patterning a silicon nitride material is described with reference to FIGS. 1-3. Referring to FIG. 1, a semiconductor wafer fragment 10 is illustrated at a preliminary step of the method. Fragment 10 comprises a substrate 12 having an upper surface 15. Sub-

3

strate 12 can comprise, for example, monocrystalline silicon. To aid in interpretation of the claims that follow, the terms "semiconductive substrate" and "semiconductor substrate" are defined to mean any construction comprising semiconductive material, including, but not limited to, bulk semiconductive materials such as a semiconductive wafer (either alone or in assemblies comprising other materials thereon), and semiconductive material layers (either alone or in assemblies comprising other materials). The term "substrate" refers to any supporting structure, including, but not limited to, the semiconductive substrates described above.

Layers 16, 18, 20, 22 and 24 are formed over upper surface 15, and are ultimately to be patterned into a wordline. Accordingly, layer 16 comprises silicon dioxide, layer 18 comprises conductively doped silicon (i.e., silicon doped to a concentration of at least about  $10^{18}$  atoms/cm<sup>3</sup> with a conductivity enhancing dopant), layer 20 comprises a metal (such as, for example, tungsten or titanium), and layer 22 comprises silicon nitride. Layer 22 has an upper surface 23, and layer 24 is formed on (i.e., against) such upper surface. Layer 24 comprises an imagable material, and is described herein to comprise photoresist. It is to be understood, however, that the term "imagable material" can encompass materials patterned by radiation (or energy) other than light, and can accordingly encompass materials other than photoresist.

Referring to FIG. 2, photoresist 24 is patterned to form blocks 26. Such patterning can comprise, for example, exposing portions of the photoresist to radiation while leaving other portions unexposed, and subsequently selectively removing either the exposed or unexposed portions with a solvent.

Blocks 26 comprise sidewalls 28 which are preferably substantially perpendicular to upper surface 23 of silicon nitride layer 22. However, a problem which occurs during the patterning of photoresist 24 is that photoresist adjacent blocks 26 does not remove as well as photoresist which is further removed from blocks 26. Such results in the formation of foot portions 30 at locations where sidewalls 28 join upper surface 23 of silicon nitride layer 22.

Referring to FIG. 3, blocks 26 are utilized as a mask during an etch of underlying layers 16, 18, 20 and 22 to form wordline stacks 40 from layers 16, 18, 20 and 22. Wordline stacks 40 comprise sidewalls 41 which are substantially perpendicular to upper surface 15 of substrate 12.

As shown, foot portions 30 (FIG. 2) are variably eroded during formation of wordline stacks 40 so that the stacks have laterally extending portions 42 where the stacks join with substrate 12. Foot portions 30 cause laterally extending portions 42 because the photoresist of foot portions 30 is etched by the conditions which etch layers 16, 18, 20 and 22, and is ultimately removed to allow portions of layers 16, 18, 20 and 22 beneath foot regions 30 to be removed. However, the portions of layers 16, 18, 20 and 22 beneath foot regions 30 are exposed to etching conditions for less time than are portions of layers 16, 18, 20 and 22 that are not beneath foot portions 30. Accordingly, the portions beneath foot portions 30 are etched less than are portions of layers 16, 18, 20 and 22 not beneath foot portions 30, causing formation of laterally extending portions 42. The laterally extending portions 42 extend into a gap between adjacent wordline stacks 40, and thus can affect a critical dimension of a structure (such as a conductive plug or capacitor) subsequently formed between stacks 40.

Sidewalls 41 join upper surface 15 of substrate 12 at a pair of opposing corners 43 relative to one of stacks 40, and a

4

pair of opposing corners 45 relative to another of stacks 40. In many applications it would be desirable if the opposing corners relative to a particular stack were as close together as possible after the patterning of layers 16, 18, 20 and 22. However, laterally extending portions 42 extend a distance between the opposing corners 43, and likewise extend a distance between opposing corners 45.

An aspect of the present invention is a recognition that foot portions 30 of FIG. 2 are due primarily to the formation of imagable material directly on silicon nitride layer 22, and accordingly can be alleviated (or even eliminated) by forming another material between silicon nitride layer 22 and imagable material 24. An embodiment of the present invention is described with reference to a wafer fragment 10a of FIG. 4. In referring to FIG. 4, similar numbering will be used as was used above in describing FIGS. 1-3, with differences indicated by the suffix "a", or by different numerals.

Wafer fragment 10a of FIG. 4, like wafer fragment 10 of FIG. 1, comprises a substrate 12, a silicon dioxide layer 16, a conductively-doped silicon layer 18, a metal layer 20, and a silicon nitride layer 22. However, fragment 10a of FIG. 4 differs from fragment 10 of FIG. 1 in that a imagable-material-supporting mass (or layer) 50 is provided over silicon nitride layer 22. Layer 50 comprises a different material than silicon nitride layer 22. In particular embodiments, layer 50 comprises less nitrogen (by atom percent) than silicon nitride layer 22. For instance, layer 50 can consist essentially of either silicon or conductively doped silicon, and can accordingly be substantially free of nitrogen (with the term "substantially free" understood to mean that layer 50 comprises less than about 10% of the atom percentage of nitrogen of layer 22, and can comprise no nitrogen). Alternatively, layer 50 can consist entirely of silicon or conductively doped silicon, and accordingly be entirely free of nitrogen.

If layer 50 is to comprise, consist of, or consist essentially of either silicon or conductively doped silicon, such layer can be formed by chemical vapor deposition of silicon or polysilicon over layer 22. For instance, the silicon can be deposited utilizing silane, dichlorosilane, or gases of the general formula  $\text{Si}_x\text{H}_{(2x+2)}$ . Preferably, if layer 50 comprises a conductive material, such layer is formed to be less than 150 Angstroms thick, and more preferably less than 100 Angstroms thick, to enable the layer to be easily removed in subsequent processing. Procedures which can be utilized to form such thin silicon layers are atomic layer deposition (ALD), or low pressure chemical vapor deposition (LPCVD) utilizing a pressure of less than 100 mTorr, at a temperature of less than 550° C. Alternative procedures which could be used for forming thin silicon layers include chemical vapor deposition utilizing a pressure of less than or equal to about 1 Torr, and a temperature of less than or equal to about 650° C.

In an alternative embodiment of the invention, layer 50 can comprise oxygen, and can, for example, comprise, consist of, or consist essentially of silicon dioxide. If layer 50 is to consist of, or consist essentially of silicon dioxide, such layer can be formed by depositing silicon dioxide over layer 22. Alternatively, if layer 50 is to comprise silicon dioxide, such layer can be formed by subjecting an upper surface of layer 22 to oxidizing conditions. The oxidation of silicon nitride layer 22 can comprise, for example, exposing such layer to an oxygen-containing gas, such as, for example,  $\text{O}_2$ ,  $\text{O}_3$ ,  $\text{N}_2\text{O}$ ,  $\text{NO}$ , etc.

If layer 50 is formed by oxidizing an upper portion of silicon nitride layer 22, the resulting structure can be con-

5

sidered to comprise a silicon nitride material which includes both layer **50** and layer **22**, with layer **50** being considered an oxidized portion of the silicon nitride material and layer **22** being considered a non-oxidized portion of the material. Further, the oxidized portion defined by layer **50** can be considered to be an oxide cap over the non-oxidized portion.

One method of improving the oxidation of an outer portion of a silicon nitride layer relative to an inner portion is to form the outer portion to have a higher relative concentration of silicon to nitrogen than does the inner portion. A silicon nitride material having a different relative concentration of silicon to nitrogen at one portion than at another portion can be formed by a chemical vapor deposition (CVD) process utilizing a silicon precursor gas (for example,  $\text{SiH}_2\text{Cl}_2$  (dichlorosilane)) and a nitrogen precursor gas (for example,  $\text{NH}_3$  (ammonia)). In an exemplary process, a substrate is provided within a CVD reaction chamber together with a first ratio of a silicon precursor gas to a nitrogen precursor gas. One portion of silicon nitride layer **22** is then deposited. Subsequently, the ratio of the silicon precursor gas to the nitrogen precursor gas is increased and the other portion of the silicon nitride layer is deposited. Exemplary processing conditions for the CVD process include a pressure of from about 100 mTorr to about 1 Torr, and a temperature of from about 700° C. to about 800° C.

In yet another embodiment, layer **50** can comprise silicon, oxygen, and nitrogen, but comprises less nitrogen (by atom percent) than does layer **22**. Layer **50** can be formed by, for example, depositing  $\text{Si}_x\text{O}_y\text{N}_z$  utilizing dichlorosilane and  $\text{N}_2\text{O}$ , wherein  $x$  is greater than 0 and less than 1,  $y$  is greater than 0 and less than 1, and  $z$  is greater than 0 and less than 1. Alternatively, layer **50** can be formed from bis-(tertiary butyl amino)-silane (BTBAS).

Referring to FIG. 5, an imagable material layer **24** is formed over imagable-material-supporting layer **50**. Imagable material layer **24** is referred to below as comprising photoresist, but it is to be understood that layer **24** can comprise other imagable materials besides photoresist.

Referring to FIG. 6, photoresist **24** is patterned by exposing some portions of resist **24** to radiation while leaving other portions unexposed, and then utilizing a solvent to selectively remove either the exposed or unexposed portions of the photoresist. The patterning forms photoresist **24** into blocks **26a**. Blocks **26a** comprise sidewalls **28a**. Blocks **26a** differ from blocks **26** of FIG. 4 in that foot portions **30** (FIG. 4) are missing from blocks **26a**. Accordingly, sidewalls **28a** of blocks **26a** extend substantially perpendicularly from an upper surface of material **50**.

Referring to FIG. 7, a pattern is transferred from blocks **26a** to underlying materials **16**, **18**, **20**, **22** and **50** to form patterned structures **60** comprising the materials of layers **16**, **18**, **20**, **22** and **50**. Patterned structures **60** comprise sidewalls **61** which are coextensive with sidewalls **28a** of blocks **26a**, and which extend perpendicularly relative to an upper surface of substrate **12**. A difference between sidewalls **61** of FIG. 7 and sidewalls **41** of FIG. 3 is that sidewalls **61** lack laterally extending portions (such as the laterally extending portions **42** shown in FIG. 3). Sidewalls **61** join substrate **12** to form opposing corners **63** relative to one of the stacks **60**, and opposing corners **65** relative to another of the stacks **60**. Opposing corners **63** are closer to one another than opposing corners **43** (FIG. 3), due to the lack of lateral extending portions **42** (FIG. 3) in the FIG. 7 structure. Likewise, opposing corners **65** are closer to one another than opposing corners **45** (FIG. 3). The structure

6

shown in FIG. 7 can be considered to comprise a first layer **22** of silicon nitride over a substrate **20**. Such structure can further comprise a second layer **50** which comprises silicon and is free of nitrogen on first layer **22**. Additionally, the structure can comprise a third layer **24** consisting essentially of imagable material on second layer **50**. Third layer **24** can be, for example, photoresist, and second layer **50** can consist essentially of silicon, conductively doped silicon, or silicon dioxide.

Referring to FIG. 8, photoresist blocks **26a** (FIG. 7) are removed and a material **66** is formed over patterned stacks **60**, as well as over substrate **12**. Material **66** can comprise, for example, an inorganic and electrically insulative material, such as, for example, silicon dioxide or silicon nitride. Material **66** can be formed by, for example, chemical vapor deposition.

The structure of FIG. 8 can be considered to comprise a layer of silicon nitride **22** over a substrate (with the substrate understood to comprise material **12** and layers **16**, **18**, and **20**). The structure further comprises layer **50** over silicon nitride layer **22**, and a layer **66** formed on (i.e., against) layer **50**. Layer **66** can consist essentially of inorganic material, such as, for example, silicon nitride, silicon dioxide, or  $\text{Si}_x\text{O}_y\text{N}_z$  (wherein  $x$ ,  $y$  and  $z$  are greater than 0), and can comprise a different chemical composition than layer **50**. In the structure of FIG. 8, layers **22** and **50** are part of a stack **60** comprising a pair of substantially planar opposing sidewalls **61**. Further in the structure of FIG. 8, layer **66** is over the stack **60** comprising layers **50** and **22**, as well as along sidewalls **61** of the stack.

FIGS. 9 and 10 illustrate alternative processing which can occur relative to the FIG. 8 structure. Referring first to FIG. 9, material **66** is subjected to anisotropic etching conditions which forms material **66** into spacers **70** extending along sidewalls **61** of stack **60**. Such anisotropic etching is conducted for a sufficient period of time to entirely remove material **50** (FIG. 8) from over silicon nitride material **22**. The processing of FIG. 9 can be preferred in embodiments in which material **50** comprises a conductive material, such as, for example, conductively doped silicon. If material **50** were not removed in such embodiments, it could short conductive components across an upper surface of stacks **60**. The processing of FIG. 9 can be easier to utilize if material **50** is kept thin (i.e., less than 150 Angstroms thick, and more preferably less than 100 Angstroms thick), as the material can then be removed with less etching than could a thicker material. It is noted that substrate **12** may be etched during the removal of material **50**. Such etching into substrate **12** is shown in FIG. 8 as trenches **72** formed within regions of substrate **12** that are not covered by spacers **70** or stacks **60**.

Material **50** can be considered a sacrificial material relative to the method of FIGS. 4–9. Specifically, the material is provided in the processing of FIGS. 4–6 to improve patterning of a photoresist material, and subsequently removed in the processing of FIG. 9.

The processing of FIG. 10 is similar to that of FIG. 9 in that material **66** of FIG. 8 is etched to form spacers **70**. However, the processing of FIG. 10 differs from that of FIG. 9 in that material **50** remains after the etch of material **66**. The processing of FIG. 10 can be preferred in embodiments in which material **50** consists of an electrically insulative material, such as, for example, silicon dioxide, or undoped silicon. If the processing of FIG. 10 is utilized, and if material **50** comprises an insulative material, there can be less preference to keeping the material to a thickness of less than 150 Angstroms relative to the advantages of keeping

material **50** to a thickness below 150 Angstroms if the material is electrically conductive and to be removed by the processing of FIG. **9**.

An improvement which can be obtained utilizing photoresist-supporting mask **50** between a layer of photoresist and a layer of silicon nitride during patterning of the photoresist is evidenced by the photographs of FIGS. **11** and **12**. Specifically, FIG. **11** shows a structure wherein photoresist is patterned while on silicon nitride, and FIG. **12** shows a structure wherein photoresist is patterned while on a layer of amorphous silicon that is conductively doped to concentration of about  $10^{20}$  atoms/cm<sup>3</sup> with phosphorus. The structure of FIG. **11** shows photoresist blocks which join an underlying substrate at corners which are less than 90° (and which specifically comprise foot portions at the locations where the sidewalls join the underlying substrate), whereas the structure of FIG. **12** shows photoresist blocks which join an underlying substrate at corners which are about 90°.

## EXAMPLES

### Example 1

A silicon nitride layer is formed by chemical vapor deposition with dichlorosilane and ammonia at a temperature of from about 600° C. to about 800° C. Subsequently, a layer of silicon is formed on the silicon nitride by chemical vapor deposition utilizing silane at a temperature of from about 500° C. to about 700° C. The silicon can then be utilized to support a layer of photoresist formed over the silicon nitride.

### Example 2

A silicon nitride layer is formed by chemical vapor deposition with dichlorosilane and ammonia at a temperature of from about 600° C. to about 800° C. Subsequently, a layer of silicon is formed on the silicon nitride by chemical vapor deposition utilizing silane at a temperature of from about 500° C. to about 700° C. Finally, the silicon is oxidized by exposure to one or more of N<sub>2</sub>O, NO, O<sub>2</sub>, O<sub>3</sub>, at a temperature of from 500° C. to about 800° C. Such forms a layer of silicon dioxide on the silicon nitride. The silicon dioxide can then be utilized to support a layer of photoresist formed over the silicon nitride.

In compliance with the statute, the invention has been described in language more or less specific as to structural and methodical features. It is to be understood, however, that the invention is not limited to the specific features shown and described, since the means herein disclosed comprise preferred forms of putting the invention into effect. The invention is, therefore, claimed in any of its forms or

modifications within the proper scope of the appended claims appropriately interpreted in accordance with the doctrine of equivalents.

What is claimed is:

1. A method of forming a patterned structure, comprising:
  - forming a first layer comprising silicone and nitrogen over a substrate;
  - depositing a silicon dioxide layer on an upper surface the first layer;
  - forming a layer of imagable material on the silicon dioxide layer;
  - patterning the imagable material;
  - transferring a pattern from the patterned imagable material to the underlying silicon dioxide layer and first layer;
  - removing the imagable material from on the silicon dioxide layer;
  - after removal of the imagable material, forming a layer of third material, a portion and less than an entirety of the third material being over the silicon dioxide layer; and
  - removing the portion of the third material from over the silicon dioxide layer, removing the silicon dioxide layer to expose the upper surface of the first layer and retaining the first layer.
2. The method of claim 1 wherein the imagable material is photoresist.
3. A method of forming a patterned structure, comprising:
  - forming a first layer comprising silicon and nitrogen over a substrate, the first layer having an exposed outer portion;
  - oxidizing the exposed outer portion of the first layer to form an oxide cap over an underlying non-oxidized portion of the first layer;
  - forming a layer of imagable material on the oxide cap;
  - patterning the imagable material;
  - transferring a pattern from the patterned imagable material to the underlying oxide cap and a non-oxidized portion of the first layer;
  - removing the imagable material; and
  - after removing the imagable material, forming an insulative material against the oxide cap and subsequently removing the entire oxide cap.
4. The method of claim 3 wherein the imagable material is photoresist.
5. The method of claim 3 wherein the exposed outer portion of the first layer comprises a higher relative concentration of silicon to nitrogen than a portion of the first layer under the exposed outer portion.

\* \* \* \* \*

UNITED STATES PATENT AND TRADEMARK OFFICE  
**CERTIFICATE OF CORRECTION**

PATENT NO. : 6,858,523 B2  
DATED : February 22, 2005  
INVENTOR(S) : DeBoer et al.

Page 1 of 1

It is certified that error appears in the above-identified patent and that said Letters Patent is hereby corrected as shown below:

Title page,

Item [56], **References Cited**, U.S. PATENT DOCUMENTS, insert

-- 6,627,535 B2	9/2003	MacNeil et al.
5,593,741 A	1/1997	Ikeda
6,723,631 B2	4/2004	Noguchi et al.
6,638,875 B2	10/2003	Han et al.
6,720,247 B2	4/2004	Kirkpatrick et al.
2003/0207594 A1	11/2003	Catabay et al.
2003/0077916 A1	4/2003	Xu et al.
2004/0071878 A1	4/2004	Schumacher et al. --.

Column 3,


Line 24, replace "encompasses" with -- encompass --.

Column 8,

Line 8, after "surface" insert -- of --.

Signed and Sealed this

Fifteenth Day of November, 2005

A handwritten signature in black ink on a light gray dotted background. The signature is written in a cursive style and appears to read "Jon W. Dudas".

JON W. DUDAS

*Director of the United States Patent and Trademark Office*