



(51) International Patent Classification:

C23F 11/00 (2006.01) C23F 11/04 (2006.01)

(21) International Application Number:

PCT/US2018/063753

(22) International Filing Date:

04 December 2018 (04.12.2018)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

62/594,335 04 December 2017 (04.12.2017) US

(71) Applicant: **CHEMTREAT, INC.** [US/US]; 5640 Cox Road, Glen Allen, Virginia 23060 (US).(72) Inventors: **KALAKODIMI, Rajendra Prasad**; c/o CHEMTREAT, INC., 5640 Cox Road, Glen Allen, Virginia 23060 (US). **POST, Raymond**; c/o CHEMTREAT, INC., 5640 Cox Road, Glen Allen, Virginia 23060 (US). **GODWIN, Douglas A.**; c/o CHEMTREAT, INC., 5640 Cox Road, Glen Allen, Virginia 23060 (US). **HATCHER,**

James; c/o CHEMTREAT, INC., 5640 Cox Road, Glen Allen, Virginia 23060 (US).

(74) Agent: **YOSICK, Joseph** et al.; c/o HACH COMPANY, Attention Legal - Patent and Trademark Department, 5600 Lindbergh Drive, P.O. Box 389, Loveland, Colorado 80539 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JO, JP, KE, KG, KH, KN, KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ,

(54) Title: METHODS AND COMPOSITIONS FOR INHIBITING CORROSION ON METAL SURFACES

Cyclic Polarization Graphs




FIG. 1

(57) **Abstract:** Methods and compositions for inhibiting corrosion of a metal product are provided. The metal product can be contacted with water that includes at least one carbonate and/or bicarbonate salt, or otherwise has components that increase the alkalinity of the water. In addition, or as an alternative, the water can include a stannous corrosion inhibitor. The water can be evaporated off of a surface of the metal product to provide a residual of the salt on the surface and/or a protective stannous film on the surface.



UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— *with international search report (Art. 21(3))*

METHODS AND COMPOSITIONS FOR INHIBITING CORROSION ON METAL SURFACES

[0001] This application claims the benefit of U.S. Provisional Application No. 62/594,335, filed December 4, 2017. The disclosure of the prior application is hereby incorporated by reference herein in its entirety.

TECHNICAL FIELD

[0002] This disclosure relates generally to the field of water treatment in metal production processes, such as those found in steelmaking facilities.

BACKGROUND

[0003] When storing or transporting surface sensitive products such as steel products and non-ferrous materials such as copper and brass, environmental conditions can create undesirable corrosion and/or staining of the finished product. Improper or inadequate treatment of the metal prior to coiling or finishing will impact the degree of corrosion and/or staining during storage or transport. This costs manufacturers millions of dollars in lost or downgraded product over the years.

SUMMARY

[0004] Corrosion, such as pitting corrosion, and staining of the metal surface remain persistent problems. Metal manufacturers have not approached solutions to these problems with chemical surface treatments. To date, there have not been robust solutions based on the conventional non-chemical approaches.

[0005] In accordance with one aspect of the present invention, there is provided a method for inhibiting corrosion of a metal product that includes (i) contacting a surface of the metal with water having at least one salt selected from the group consisting of carbonates, bicarbonates, and combinations thereof; and (ii) evaporating the water off of the surface so that a residual of the at least one salt remains on the surface. The method can optionally include a step of contacting the surface of the metal with water that includes a stannous corrosion inhibitor.

[0006] In accordance with another aspect, there is provided a method for inhibiting corrosion of a metal product that contacts a water stream during production of the metal product. The method can include (i) increasing the alkalinity of the water stream by adding at least one salt to the water stream; and (ii) then evaporating water off of the metal product so that a residual of the at least one salt remains on a surface of the metal product.

[0007] In accordance with another aspect, there is provided a method for inhibiting corrosion of a metal product that includes (i) contacting a surface of the metal with water that includes a stannous corrosion inhibitor, where the surface of the metal has a temperature of at least 500°C immediately before the surface is contacted with the water; and (ii) then evaporating the water off of the surface and forming a Sn (IV) film on the surface.

[0008] In accordance with yet another aspect, there is provided an aqueous composition that includes (i) from 0.1 wt.% to 25 wt.% of a stannous salt; and (ii) from 0.5 wt.% to 25 wt.% of at least one salt selected from the group consisting of carbonates, bicarbonates, and combinations thereof.

BRIEF DESCRIPTION OF THE DRAWINGS

[0009] Fig. 1 is a graph showing the cyclic polarization curves of test steel coupons;

[0010] Fig. 2 is a photograph showing the coupons after the cyclic polarization study; and

[0011] Fig. 3 is photograph showing steel coupons after being exposed to a humidity chamber for 12 hours.

DETAILED DESCRIPTION OF EMBODIMENTS

[0012] This disclosure describes methods and compositions for protecting surface sensitive materials from corrosion that may occur during manufacturing, storage, and transportation. The surface sensitive material can be metals such as steel products, galvanized steels, and non-ferrous materials such as copper, brass, aluminum, etc.

[0013] In one aspect, the invention mitigates corrosion problems by treating water that contacts the metal during its production. Water can be sprayed onto metal surfaces, or otherwise be contacted with metal surfaces, during the production of metal products. For example, water is often used as a cooling medium to cool the metal. But the water that is used for cooling typically contains various minerals such as calcium, magnesium, chlorides and sulfates, etc. Chlorides and sulfates can be very corrosive to metal surfaces such as steel. In some processes, the amount of chlorides in the water that contacts the metal surface can be in the range of 10 ppm to 1,000 ppm, from 50 ppm to 500 ppm, and from 100 ppm to 250 ppm. The amount of sulfates in the water that contacts the metal surface can be in the range of from 2 ppm to 500 ppm, from 5 ppm to 250 ppm, or from 10 ppm to 100 ppm.

[0014] Once the water is evaporated or dried off of the metal surface, the chlorides and sulfates can be retained as a residual on the metal surface, e.g., as residual salts. The chloride and sulfate salts are known to be deliquescent salts, meaning, they quickly adsorb humidity from the air and form a highly concentrated liquid solution on the surface of the

metal. Rain water and dew are slightly acidic forms of pure water (pH~5) which when combined with atmospheric CO₂, form carbonic acid, as well as stronger acids from adsorption of sulfur and nitrogen oxides. The combination of acidic water with chlorides and sulfates can cause very aggressive corrosion on the metal surface that degrades protective oxide coatings that naturally form on the surface, e.g., iron oxide coatings that form on steel surfaces. As the acidic chloride and sulfate solutions attack the metal, the pH of the solution can further be depressed by metal hydrolysis. For example, in the case of iron based metals, the Fe reacts with OH⁻ and leaves the water enriched in H⁺. At low pH, the H⁺ concentration is sufficient to become the dominant electron acceptor instead of oxygen reduction.

[0015] As described in detail below, in one aspect, these corrosion issues can be substantially mitigated by (i) increasing the alkalinity of water that contacts the metal surface; or (ii) by adding a stannous based passivating chemistry to the water; or (iii) a combination of both of these treatments.

[0016] The alkalinity of water can be increased by introducing into the water carbonate and bicarbonate salts, such as, but not limited to, sodium, potassium, magnesium, and calcium carbonate/bicarbonate. The alkalinity can also be increased by using chemistries, such as, but not limited to, hydroxide salts, amines, etc. The salts can be dissolved in the water as a solution, can be suspended in the water, or a combination of both. It is believed that an increase in alkalinity of the water leaves residual components on the metal surface that prevent corrosion attributable to chlorides and sulfates and/or to subsequent contact of the metal surface with acidic water or water vapor.

[0017] Without intending to be bound by theory, it is believed that when these salts, such as bicarbonate/carbonate salts, are subjected to high temperatures on the metal surface, they will produce residual products that create a local alkaline environment on the metal surface that protects against corrosion from acidic conditions. In this regard, when bicarbonate salts are exposed to high temperature, they release CO₂, forming carbonates or oxides. For example, sodium carbonate decomposes to sodium oxide (Na₂O) beginning at about 400 °C, which is in the range of temperatures metal is typically exposed to during processing, e.g., the temperature at which steel is coiled. Na₂O also adsorbs moisture from the air to become caustic soda.

[0018] It is believed that the high pH environment created by the sodium, calcium, and potassium carbonates and hydroxides can counter the low pH effects of atmospheric CO₂ and “acid rain”. Unexpectedly, the residuals of the carbonate/bicarbonate salt thus can remain on the metal surface even after being exposed to high temperatures and can create

basic conditions that prevent corrosion when the metal surface is later contacted with moisture, e.g., during storage and transportation (particularly overseas shipping). At high pH, metal surfaces generally become much less corrosive.

[0019] A corrosivity index can be developed based on the amount of chlorides and sulfates in the water whereby the amount of alkalinity that the water needs can be determined based on the amount of chlorides and sulfates in the water. The concentration of alkalinity in the water stream that contacts the metal surface can be controlled to be from about 5 ppm to 1,500 ppm, from 25 ppm to 1,000 ppm, from 50 ppm to 500 ppm, and from 100 ppm to 400 ppm. "Alkalinity" as used herein refers to M-alkalinity. The alkalinity can be provided by mixing a treatment composition with the water that includes at least one carbonate or bicarbonate salt. The treatment composition can be provided as an aqueous composition (i.e., containing mostly water). The salts can be present in the treatment composition in amounts of from 0.1 to 25 wt.%, 1 to 20 wt.%, or 5 to 15 wt.%.

[0020] Separately or in addition to the above step, a stannous corrosion inhibitor can be added to the water which contacts the metal surface. Stannous salts are known to inhibit corrosion but, unlike more conventional corrosion inhibitors, the mechanism by which the stannous salts inhibited corrosion has not been well understood. Without intending to be bound by theory, it is believed that stannous salts can form of a tenacious protective layer on metal surfaces. Stannous ions (Sn (II)) in the water solution are drawn to the active metal surfaces that are losing electrons as they oxidize or are forced into solution by electric potentials. The positively charged tin ion is drawn to the negative surfaces, and reduces the oxidized ions (rust and corrosion) and oxidizes itself to stannic Sn(IV) state, which is insoluble. This results in the formation of an inactive layer Sn(IV) on the metal surface, which protects the metal surface from further corrosion.

[0021] The stannous salt may be, for example, stannous chloride, stannous sulfate, stannous bromide, stannous oxide, stannous phosphate, stannous pyrophosphate, stannous tetrafluoroborate, or combinations of any of these salts.

[0022] The concentration of the stannous salt in the water stream that contacts the metal surface can be controlled to be in the range of from about 0.1 to 1000 ppm, from about 0.5 to 50 ppm, or from about 1.5 to 10 ppm.

[0023] In one aspect, the stannous treatment composition that is added to the water can be an aqueous solution. The amount of stannous salt in the treatment composition can be in the range of from 0.1 wt.% to 25 wt.%, from 1 wt.% to 20 wt.%, or from 5 wt.% to 10

wt.%. The amount of tin (from the stannous salt) in the corrosion inhibitor composition can range from 0.05 wt.% to 15 wt.%, from 0.1 wt.% to 10 wt.%, or from 1 wt.% to 5 wt.%.

[0024] The treatment composition can also include at least one chelating agent selected from the group consisting of citric acid, azole based copper corrosion inhibitors such as benzotriazole and 2-Butenedioic acid (Z), halogenated azoles and their derivatives, scale inhibitors and dispersants selected from the group consisting of one or more of unsaturated carboxylic acid polymers such as polyacrylic acid, homo or co-polymaleic acid (synthesized from solvent and aqueous routes); acrylate / 2-acrylamido-2-methylpropane sulfonic acid (APMS) copolymers, acrylate/acrylamide copolymers, acrylate homopolymers, terpolymers of carboxylate/sulfonate/maleate, terpolymers of acrylic acid/AMPS; phosphonates and phosphinates such as 2-phosphonobutane-1,2,4-tricarboxylic acid (PBTC), 1-hydroxy ethylidene-1,1-diphosphonic acid (HEDP), amino tris methylene phosphonic acid (ATMP), 2-hydroxyphosphonocarboxylic acid (HPA), diethylenetriamine penta(methylene phosphonic acid) (DETPMP), phosphinosuccinic oligomer (PSO); salts of molybdenum and tungsten including, for example, nitrates and nitrites; amines such as N,N-diethylhydroxylamine (DEHA), diethyl amino ethanol (DEAE), dimethylethanolamine (DMAE), cyclohexylamine, morpholine, monoethanolamine (MEA), a biocide, and combinations thereof.

[0025] The treatment composition can also include a secondary corrosion inhibitor, which comprises other metal ions with multiple oxidation states, ortho phosphates, pyro phosphates, molybdates, nitrites, of one or more of unsaturated carboxylic acid polymers such as polyacrylic acid, homo or co-polymaleic acid (synthesized from solvent and aqueous routes); acrylate / 2-acrylamido-2-methylpropane sulfonic acid (APMS) copolymers, acrylate/acrylamide copolymers, acrylate homopolymers, terpolymers of carboxylate/sulfonate/maleate, terpolymers of acrylic acid/AMPS; phosphonates and phosphinates such as 2-phosphonobutane-1,2,4-tricarboxylic acid (PBTC), 1-hydroxy ethylidene-1,1-diphosphonic acid (HEDP), amino tris methylene phosphonic acid (ATMP), 2-hydroxyphosphonocarboxylic acid (HPA), diethylenetriamine penta(methylene phosphonic acid) (DETPMP), phosphinosuccinic oligomer (PSO); salts of molybdenum and tungsten including, for example, nitrates and nitrites; amines such as N,N-diethylhydroxylamine (DEHA), diethyl amino ethanol (DEAE), dimethylethanolamine (DMAE), cyclohexylamine, morpholine, monoethanolamine (MEA); azoles such as tolyltriazole (TTA), benzotriazole (BZT), butylbenzotriazole (BBT), halogenated azoles, their salts, and combinations thereof.

[0026] One or both of the alkalinity and stannous treatment compositions can be added to the water that contacts the metal surface during or after production of a metal

product. In one aspect, these treatment compositions can be added to cooling water that contacts the metal surface in a step that cools the metal, e.g., by at least 50°C or 100°C, such as an annealing step in steelmaking. The compositions can be added during a stage where the temperature of the metal is high enough to evaporate off substantially all of the water and leave behind the stannous film and/or residuals of carbonate/bicarbonate salts. Such metal surface temperatures include those of at least 500°C, at least 800°C, or over 1000°C, as measured immediately before the surface is contacted with water. In one aspect, it was surprisingly discovered that the stannous film can form and remain intact even when subjected to these high temperatures, as it was expected that the film would degrade.

[0027] In accordance with some aspects, the water stream that contacts the metal can include both a stannous salt and a carbonate/bicarbonate salt, and, likewise, the treatment composition that is added to the water stream can include both of these components in the respective amounts identified above. In other aspects, these components can be added in separate stages where one water stream contacting the metal includes a stannous salt and another water stream that contacts the metal includes a salt that increases the alkalinity of the water. Advantageously, the corrosion-resistance effects of the stannous corrosion inhibitor composition are substantially more pronounced under high alkalinity conditions and have unexpectedly good performance.

[0028] One useful application of this invention is exemplified in the description below in connection with treating water that contacts steel during a steel making process.

[0029] The manufacturing process for steel production is time consuming. Conversion from liquid steel to solidified thick or thin slabs occurs in the continuous caster. The slabs are either cooled and then charged into a reheat furnace or directly charged from the caster into a furnace. Once the product is heated to the proper rolling temperature, it is removed from the furnace and introduced into the Rolling or Hot Strip Mill. The Rolling or Hot Strip Mill includes roughing stands and/or finishing stands which reduce the thickness of the product to the desired gauge of the finished product (strip or plate). After the gauge has been set, the product may undergo water cooling in a laminar or accelerated cooling process in order to finalize the desired metallurgical properties prior to packaging. This cooling process cools the product from a starting temperature of approximately 600°C – 1000°C, or 700°C- 800°C, depending on desired rolling properties. The water wall cools the strip temperature with a series of low pressure nozzle jets at both the bottom and the top of the strip surface.

[0030] The steel can be cooled to a set temperature range based on desired metallurgical properties (typically 400°C – 800°C) by multiple stages of water on the laminar table prior to being coiled. Additional water is also applied in the coiling process to maintain the integrity of the coil machinery. The water that has been sprayed on the steel for cooling typically contains various minerals such as calcium, magnesium, chlorides and sulfates, etc. As indicated above, chlorides and sulfates are especially known to be very corrosive to steel. These minerals can combine to form salts, which, through evaporation, can remain on the metal surface even at such elevated temperatures. Hardness ions, calcium and magnesium, combine with chloride ions in the water and can form calcium chloride and magnesium chloride salts, which are left on the strip due to evaporation at high temperatures. That is, in steel production, as well as other metal production processes, water containing salts dries out on the metal surface.

[0031] Then, while being transported long-distance, the salts adsorb humidity from the air and form a concentrated liquid solution on the surface of the metal, which in turn causes corrosion/staining on the steel surface. This combination of factors leads to rapid rusting and degradation of the steel surface. This has resulted in not only aesthetic issues, but has resulted in costly product losses amounting to millions of dollars in wastage of the steel products.

[0032] To combat this problem, one or both of the alkalinity and stannous treatment compositions described above can be added to the cooling water at the laminar table. Based on the high temperature of the steel the water will steam off. It is believed that the carbonates decompose to sodium oxide, for example, beginning at about 400°C, which is lower than the coiling temperature of the steel. Na₂O also adsorbs moisture from the air to become caustic soda, which can create a high pH environment to counter the low pH effects of atmospheric CO₂ and “acid rain”. This mechanism, optionally together with forming a stannous film on the metal surface, can provide a very effective mechanism for inhibiting corrosion and staining of steel products.

[0033] Examples

[0034] In a first example, stainless steel coupons were passivated for about 1 hour in a solution containing sodium bicarbonate in an amount corresponding to 250 ppm of alkalinity as CaCO₃ and 50 ppm of stannous corrosion treatment composition (which includes about 3-3.5 wt.% Sn). The water also included 75 ppm Ca as CaCO₃, 25 ppm Mg as CaCO₃, 130 ppm Chlorides and 15 ppm sulfates. These components were added to mimic water compositions that might be present in many steel production facilities. The coupons

were then placed in a furnace at 650°C for one hour, which evaporates the water on the coupons. A blank coupon, which was not exposed to any treatment program was also used for comparison. After the exposure to high temperature, one set of coupons was used to run electrochemical cyclic polarization and the other set was exposed to a humidity chamber for 12 hours.

[0035] Figure 1 shows the cyclic polarization curves of the coupons after exposure to high temperature, where the y-axis is a voltage compared to a Ag/AgCl reference electrode, and the x-axis is current. Passivation of the metal surface manifests itself as a more positive potential under this test. As can be seen in Fig. 1, at the flat part of the curves, the treated coupon is more anodic than the blank, which indicates that the stannous based treatment program provides a passive film on the surface of the metal under alkaline conditions and even after being subjected to high temperatures.

[0036] Figure 2 is a photograph of the coupons after the cyclic polarization studies. It is clear from Figure 2 that the coupon with no treatment program had corrosion/staining on the coupon surface, while the coupon which was exposed to a stannous-based treatment program along with increase in alkalinity, showed a clean surface with minimal corrosion/staining.

[0037] Fig. 3 is a photograph of the second set of coupons that had been exposed to the humidity chamber. For the coupons in Fig. 3, a similar passivation was conducted, but the water used for passivation included 215 ppm sulfates, as compared to the Example 1, which only had 15 ppm sulfates. Figure 3 shows the pictures of the coupons after exposing them to these passivating chemistries, followed by high temperature and humidity chamber.

[0038] It is clear from Figure 3 that the stannous based treatment program, coupled with increased alkalinity, will protect the metal from severely corrosive conditions, including both chlorides and sulfates.

WHAT IS CLAIMED IS

1. A method for inhibiting corrosion of a metal product comprising:
contacting a surface of the metal with water that includes at least one salt selected from the group consisting of carbonates, bicarbonates, and combinations thereof; and
evaporating the water off of the surface so that a residual of the at least one salt remains on the surface.
2. The method of claim 1, wherein the water that contacts the surface of the metal includes an amount of the at least one salt so that the alkalinity of the water is in the range of from 25 ppm to 1,000 ppm.
3. The method of claim 1, wherein the water that contacts the surface of the metal further includes a chloride content in the range of from 10 ppm to 1,000 ppm.
4. The method of claim 1, wherein the water that contacts the surface of the metal further includes a sulfate content in the range of from 2 ppm to 500 ppm.
5. The method of claim 1, wherein the metal is selected from steel, aluminum, copper, and brass.
6. The method of claim 1, wherein the metal is steel and the water is contacted with the surface of the steel during an annealing step.
7. The method of claim 1, further comprising a step of contacting the surface of the metal with water that includes a stannous corrosion inhibitor.
8. The method according to claim 7, wherein the stannous corrosion inhibitor is present in the water that includes the salt.
9. A method for inhibiting corrosion of a metal product that contacts a water stream during production of the metal product, the method comprising:
increasing the alkalinity of the water stream by adding at least one salt to the water stream; and
then evaporating water off of the metal product so that a residual of the at least one salt remains on a surface of the metal product.
10. The method of claim 9, further comprising determining a desired alkalinity level of the water stream that contacts the metal product based on an amount of at least one of (i) chlorides, and (ii) sulfates in the water stream.

11. A method for inhibiting corrosion of a metal product comprising:
contacting a surface of the metal with water that includes a stannous corrosion inhibitor, wherein the surface of the metal has a temperature of at least 500°C immediately before the surface is contacted with the water; and
then evaporating the water off of the surface and forming a Sn (IV) film on the surface.
12. An aqueous composition that includes:
from 0.1 wt.% to 25 wt.% of a stannous salt; and
from 0.5 wt.% to 25 wt.% of at least one salt selected from the group consisting of carbonates, bicarbonates, and combinations thereof.

Cyclic Polarization Graphs




FIG. 1



BLANK

100 ppm CL₅₇₃₇

FIG. 2




FIG. 3

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US 18/63753

A. CLASSIFICATION OF SUBJECT MATTER
 IPC(8) - C23F 11/00; C23F 11/04 (2019.01)
 CPC - C23F 11/00; C23F 11/04; C09K 2208/32

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

See Search History Document

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

See Search History Document

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

See Search History Document

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X ----- Y	US 8,784,629 B2 (Inbe et al.) 22 July 2014 (22.07.2011) entire document especially col 1 ln 49-50, col 2 ln 17 and 51-52, col 3 ln 33-34 and 37-43, col 11 ln 4-6, col 14 ln 39-41, col 16 ln 21-23	1-10 ----- 11
X	US 6,555,094 B1 (Glandorf et al.) 29 April 2003 (29.04.2003) entire document especially col 9 ln 46-col 10 ln 3, col 6 ln 35-38 and col 10 ln 33-47	12
Y	US 2017/0130340 A1 (CHEMTREAT INC.) 11 May 2017 (11.05.2017) entire document, especially Abstract, para[0006],[0014],[0021]	11
A	Ai et al. "Passivation Characteristics of Alloy Corrosion-Resistant Steel Cr10Mo1 in Simulating Concrete Pore Solutions: Combination Effects of pH and Chloride" Materials Vol 9(9), page 749 02 July 2016 (02.07.2016)	2
A	Metalsupermarkets.com "Difference between annealing and tempering" https://www.metalsupermarkets.com/difference-annealing-tempering/ 09 May 2016 (09.05.2016)	6
A	Corrosiondoctors.org "Corrosivity of a Water and Saturation Indices" https://corrosion-doctors.org/Cooling-Water-Towers/corrosivity.htm 24 July 2000 (24.07.2000)	10

☐ Further documents are listed in the continuation of Box C.

☐ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

21 January 2019

Date of mailing of the international search report

15 FEB 2019

Name and mailing address of the ISA/US

Mail Stop PCT, Attn: ISA/US, Commissioner for Patents
 P.O. Box 1450, Alexandria, Virginia 22313-1450

Facsimile No. 571-273-8300

Authorized officer:

Lee W. Young

PCT Helpdesk: 571-272-4300
 PCT OSP: 571-272-7774