




(11) (21) (C) **2,114,971**
(22) 1994/02/04
(43) 1994/08/17
(45) 2000/05/16

(72) Athey, Patricia Ruzakowski, US
(72) Dauson, Douglas Samuel, US
(72) Lecocq, David Emil, US
(72) Neuman, George Andrew, US
(72) Sopko, John Frank, US
(72) Stewart-Davis, Royann Lynn, US
(73) PPG INDUSTRIES OHIO, INC., US
(51) Int.Cl.⁵ C07F 7/22, C03C 17/30
(30) 1993/02/16 (017,930) US

(54) **APPAREIL DE REVETEMENT, METHODE SERVANT A
TRAITER LE VERRE, COMPOSITIONS ET COMPOSES
UTILISES DANS LE TRAITEMENT DU VERRE, ET
SUBSTRATS DE VERRE REFLECHISSANT**
(54) **COATING APPARATUS, METHOD OF COATING GLASS,
COMPOUNDS AND COMPOSITIONS FOR COATING GLASS
AND COATED GLASS SUBSTRATES**



(57) An apparatus for coating a glass ribbon has an exhaust on each side of a coating unit at different distances therefrom. With this arrangement, portions of the ribbon upstream and downstream of the coating unit are exposed to coating vapors from the coating unit for different periods of time. A coating mixture includes tin containing precursors and a silicon containing precursor. The silicon containing precursor has the structural formula (see formula I) where R₁ is a group which does not have an oxygen available to form a peroxide, R₂ is a functional group giving the silicon containing precursor the ability to be easily converted to silicon oxide coating, R₃ is a bridging group to provide for multiple silicon atoms and R₄ completes the bonding on the foundation silicon atom. An accelerant e.g. a phosphorus containing precursor may be used with the metal containing precursors to increase the deposition rate of the coating. The coating deposited on the glass has regions of continuously varying weight percent of silicon oxide and tin oxide as the distance from the glass-coating interface increases, with the surface of the coating farthest from the glass-coating interface being predominantly tin oxide. The regions within the coating provide the coating with different indices of refraction to eliminate iridescence resulting from increased thickness of the tin oxide at the outer coating surface and to provide the coated glass article with a neutral color. When phosphorus is used as the accelerant, the percent of crystallinity is reduced and approaches 0, thereby reducing or eliminating the coating haze.



2114971

ABSTRACT

An apparatus for coating a glass ribbon has an exhaust on each side of a coating unit at different distances therefrom. With this arrangement, portions of the ribbon upstream and downstream of the coating unit are exposed to coating vapors from the coating unit for different periods of time. A coating mixture includes tin containing precursors and a silicon containing precursor. The silicon containing precursor has the structural formula



where R₁ is a group which does not have an oxygen available to form a peroxide, R₂ is a functional group giving the silicon containing precursor the ability to be easily converted to silicon oxide coating, R₃ is a bridging group to provide for multiple silicon atoms and R₄ completes the bonding on the foundation silicon atom. An accelerant e.g. a phosphorus containing precursor may be used with the metal containing precursors to increase the deposition rate of the coating. The coating deposited on the glass has regions of continuously varying weight percent of silicon oxide and tin oxide as the distance from the glass-coating interface increases, with the surface of the coating farthest from the glass-coating interface being predominantly tin oxide. The regions within the coating provide the coating with different indices of refraction to eliminate iridescence resulting from increased thickness of the tin oxide at the outer coating surface and to provide the coated glass article with a neutral color. When phosphorus is used as the accelerant, the percent of crystallinity is reduced and approaches 0, thereby reducing or eliminating the coating haze.

COATING APPARATUS, METHOD OF COATING GLASS,
COMPOUNDS AND COMPOSITIONS FOR COATING GLASS
AND COATED GLASS SUBSTRATES

5 BACKGROUND OF THE INVENTION

1. Field of the Invention

This invention relates to a method of and an apparatus for the chemical vapor deposition of one or more metal oxides on a substrate e.g. glass, to silicon containing precursors used in the preparation of coating compositions containing silicon oxide and to the product(s) e.g. coated glass made thereby.

2. Description of the Relevant Art

15 It is known in the art that when a film of a transparent metal oxide, such as tin oxide, is deposited on a glass substrate, the coated glass substrate has non-uniform light-reflection across the visible spectrum because of the difference in the refractive index between the metal oxide and the glass substrate. In addition, when the thickness of the metal oxide coating is not uniform, the coating tends to display a multiplicity of interference color effects commonly referred to as iridescence. Such iridescence effects render the coated glass aesthetically unacceptable for most architectural applications. Thus, various methods to mask such iridescence effects and/or reduce reflectance have been proposed.

One technique for minimizing or eliminating the difference of the refractive index between a metal oxide and a glass substrate is disclosed in U.S. Patent No. 3,378,396 to Zaromb wherein a glass substrate is coated by simultaneously directing separate sprays of a tin chloride solution and of a silicon chloride solution onto a stationary heated glass piece in an oxidizing atmosphere e.g. air. The heat of the glass piece thermally converts the metal chlorides to their metal

oxides. The ratio of the sprays to each other are gradually varied to vary the ratio of the weight percent of the metal oxides in the coating. The resultant coating has a continuously-changing composition throughout its thickness, e.g. near the glass-coating interface, the coating is predominantly silicon oxide, the surface of the coating furthest from the glass-coating interface is predominantly tin oxide and there-between the coating is made up of varying weight percent amounts of silicon oxide and tin oxide. Strong in his publication entitled "Practical Applications of High and Low-Reflecting Films on Glass", pages 441-443 of Le Journal de Physique et Le Radium, Vol. 11, July 1950, teaches that a coating technique similar to that taught by Zaromb reduces the iridescence of the coated article.

Additional techniques using the Zaromb teachings to coat a moving substrate are taught in U.S. Patent Nos. 4,206,252 and 4,440,882. These patents further teach the depositing of a second coating composed of fluorine-doped tin oxide on the first coating of the type taught by Zaromb.

Gordon, in U.S. Patent Nos. 4,187,336 and 4,308,316 discloses the reduction of iridescence of a tin oxide coating on a glass substrate by the use of an intermediate coating between the tin oxide coating and the glass substrate having a thickness and refractive index satisfying the optical equation: the refractive index of the intermediate coating is equal to the square root of the refractive index of the glass substrate times the refractive index of the tin oxide coating.

U.S. Patent Nos. 4,377,613 and 4,419,386 to Gordon disclose a reduction in iridescence arising from a tin oxide film on a glass substrate by providing two intermediate coating layers between the glass substrate and the tin oxide. The intermediate layer next to the surface of the glass substrate has a high refractive index, while the intermediate layer farther from the surface of the glass substrate and next to the tin oxide film has a lower refractive index.

In general, the patents discussed above, except for U.S. Patent Nos. 4,206,252 and 4,440,822, teach coating a stationary glass substrate. Apparatuses for coating a moving glass substrate with metal oxides are disclosed in the above
5 discussed U.S. Patent Nos. 4,206,252 and 4,440,882 to Gordon, and in U.S. Patent No. 4,853,257 to Henery and U.S. Patent No. 4,386,117 to Gordon.

In U.S. Patent Nos. 4,206,252 and 4,440,882, the underside of a moving hot glass ribbon is coated by directing
10 coating compositions containing metal compounds toward the ribbon surface, whose compounds are converted to their corresponding metal oxides.

U.S. Patent No. 4,853,257 discloses an apparatus for depositing a low emissivity film on a glass ribbon by
15 directing metal-containing coating reactants in vapor form onto the upper surface of a glass ribbon while the glass ribbon is supported on a molten metal bath contained in a non-oxidizing atmosphere. The carrier gas, the unreacted coating composition and any decomposition by-products are
20 removed from the coating zone by an exhaust orifice on each side of, and equidistant from, the position where the coating reactants in vapor form are directed toward the glass ribbon.

U.S. Patent No. 4,386,117 discloses a process for depositing a mixed metal oxide coating on a glass substrate by
25 directing a gaseous mixture onto a moving glass ribbon and then exhausting gases from the coating zone at two locations equidistant from the entry of the gaseous mixture into the coating zone.

Although each of the apparatuses and processes
30 taught in the above-discussed patents is acceptable for its intended purpose, there are limitations when the apparatuses and processes are used to apply the coating of Zaromb to a moving heated glass substrate, e.g. a glass ribbon supported on a molten metal bath contained in a non-oxidizing
35 atmosphere. It would be advantageous, therefore, to provide

apparatuses and processes to deposit the coating of Zaromb on a moving heated substrate as well as the metal containing precursors used in the preparation of the coating.

One of the limitations of the presently available
5 vapor coating system for coating a glass ribbon moving at fast speeds e.g. about 600 inches/min. (15.24 meters/min.) is that the vapor coating mixture does not have sufficient time to deposit a coating of acceptable thickness on the glass ribbon. The article entitled "The LPCVD of Silicon Oxide Films Below
10 700°F (400°C) From Liquid Sources" by A. K. Hochberg and D. L. O'Meara published in J. Electrochem. Soc. Vol. 136, No. 6, June 1989 copyrighted by The Electrochemical Society, Inc. pps. 1843 and 1844 teaches the use of trimethylphosphite to accelerate coating deposition below 750°F (400°C). The
15 publication "User's Guide For: Glass Deposition with LTO-410™ Source Material" by Dr. A. Hochberg and Dr. B. Gelernt, copyrighted 1990 by Schumacher of Carlsbad, California, 92009 teaches that the LTO-410 process is not significantly changed with the addition of trimethylphosphite.

20 Although the use of accelerants is taught, there are no teachings that such accelerants are beneficial at elevated temperatures e.g. above 750°F (400°C). Therefore it would be advantageous to provide accelerants for coating systems that operate at temperatures above about 1000°F
25 (536°C).

SUMMARY OF THE INVENTION

The invention relates to a method of coating a moving substrate e.g. a glass ribbon supported and advancing
30 on a pool of molten metal e.g. tin, with a film or coating having a continuously changing chemical composition as the distance from the glass-coating interface increases. The method includes the steps of directing a vapor coating composition of metal containing precursors e.g. a silicon
35 containing precursor and a tin containing precursor onto the

surface of the glass ribbon, moving a first portion of the vapor along a first region of the ribbon surface in a first direction and a second portion of the vapor along a second region in a second opposite direction and maintaining the first portion of the coating composition on the first region for a longer period of time than the second portion of the coating composition on the second region to provide a coating on the glass ribbon having a varying composition of metal oxides as the distance from the coating-glass interface increases.

Further, the invention relates to an apparatus for carrying out the method. One embodiment of the inventive apparatus includes facilities for directing a vapor composed of mixed metal containing precursors onto a substrate e.g. the glass ribbon supported on a molten tin bath. A first exhaust is spaced from the vapor directing facility on one side thereof, and a second exhaust is spaced from the vapor directing facility on the other side thereof and in alignment with the vapor directing facility. The first exhaust is spaced from the vapor directing facility a different distance than the second exhaust is spaced from the vapor directing facility.

The invention further relates to a transparent substrate e.g. a glass substrate having a coating thereon composed of mixed metal oxides e.g. silicon oxide and tin oxide. The coating composition has a continuously changing ratio of silicon oxide to tin oxide as the distance from the glass-coating interface increases, e.g. substantially all silicon oxide at the glass coating interface and substantially all tin oxide at the opposite coating surface. Between the glass-coating interface and the opposite coating surface there are minimal, if any, strata of a fixed ratio of silicon oxide to metal oxide and there are dispersed in the coating small amounts of phosphorus, boron, and/or aluminum when compounds

containing those elements are used as accelerants to increase the coating deposition rate and control the coating morphology.

The invention still further relates to a vapor
 5 coating composition having a silicon containing precursor having the structural formula



where R_1 is selected from groups that include alkyl and alkenyl. R_2 is the functional group giving the silicon
 15 compound the ability to be easily converted to silicon oxide and includes hydrogen, halogen, alkenyl and halogenated alkyl radicals. R_3 is a bridging group to provide for multiple silicon atom compounds and includes -S- and -N- groups. R_4
 20 completes the bonding of the foundation silicon atom.

Also, the invention relates to a coating composition having mixed metal containing precursors e.g. tin and silicon containing presursors. The silicon metal
 25 precursor may include -Si-O- containing compounds described above and an accelerant capable of enhancing the reaction rate of the coating compounds. The accelerants include Lewis acids
 30 and Lewis bases.

BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 illustrates a coated substrate incorporating features of the invention and obtained using the
 35 apparatuses, processes, and coating materials of the invention.

Figure 2 is an elevation view of a coating system having two coating stations, one of which includes a coating apparatus having multiple coating zones incorporating features of the invention.

5 Figure 3 is a view similar to that of Figure 2 of a coating apparatus having one coating zone incorporating features of the invention.

 Figure 4 is a graph showing a gradient coating and an extended and improved gradient coating deposited in
10 accordance with the teachings of the invention.

 Figure 5 is a graph showing the effect of coating apparatus height from the surface of a glass substrate and carrier flow on the ratio of tin oxide to silicon oxide in the coating deposited on the glass substrate in accordance with
15 the teachings of the invention.

 Figure 6 is a graph showing the effect on film thickness using the accelerants of the instant invention.

DESCRIPTION OF PREFERRED EMBODIMENTS

20 Referring to Figure 1, there is shown a coated article 10 incorporating features of the invention that can be made using the apparatuses, processes, and coating materials, of the invention. In general, the article 10 includes a substrate 12, e.g. but not limiting to the invention, plastic
25 and/or clear or colored glass, having a coating 14 that exhibits minimum reflected color by having a continually varying refractive index, and preferably has an emissivity lower than the uncoated substrate. In the following discussion the substrate is a glass substrate. The coating
30 14, in general, is composed of a mixture of silicon oxide and a metal oxide, such as tin oxide. As with Zaromb, discussed above, the coating 14 has a continuously changing composition as the distance from the glass-coating interface 16 increases. Generally, near the glass-coating interface 16, the coating is
35 predominantly silicon oxide, while at the opposite surface 18

of the coating 14 e.g. the coating surface farthest from the glass-coating interface 16, the composition of the coating is predominantly tin oxide. The predominantly tin oxide region may continue as predominantly tin oxide for a thickness
5 required by the use of the article. For example when an article having a high emissivity is desired e.g. close to the emissivity of the glass substrate, the predominantly tin oxide region is thin; when an article having a low emissivity is desired, the predominantly tin oxide region is thicker. The
10 tin oxide region may be doped with fluorine or antimony as taught in U.S. Patent No. 3,677,814 to further reduce emissivity. Between the glass-coating interface 16 and opposite surface 18, the coating 14 is composed of continuously varying amounts of silicon oxide and tin oxide as
15 the distance from the glass-coating interface 16 increases. In other words, as the distance from the glass-coating interface 16 increases, each succeeding region of the continuously varying composition in the coating 14 contains a tin oxide to silicon oxide weight percent ratio different than
20 the preceding region and although not limiting to the invention, usually that ratio tends to increase as the distance from glass-coating interface 16 increases. The opposite surface 18 is predominantly tin oxide, i.e., the weight percent of silicon oxide in the outermost region
25 approaches zero, and the weight percent of tin oxide approaches 100.

Although the coating 14 was discussed using a coating of tin oxide and silicon oxide, the invention is not limited thereto and as will be appreciated from the discussion
30 below any two or more metal oxides may be used in the practice of the invention.

The coated article 10 of Figure 1 was produced using coating system 19 shown in Figure 2. A discussion of coating apparatus 20 in Figure 3 will now be presented for a
35 better appreciation of the features of the coating system 19

shown in Figure 2. The apparatus 20 of Figure 3 may be used to deposit a non-homogeneous coating of the type discussed above on the glass substrate 12. In Figure 3 as in Figure 2, the substrate 12 is a glass ribbon 22 or pieces cut therefrom.

5 With reference to Figure 3, coating apparatus 20 is supported in any convenient manner above and spaced from the glass ribbon 22 supported on a pool or bath 24 of molten metal contained in a chamber having a non-oxidizing atmosphere, not shown, e.g. of the type of chamber taught in U.S. Patent No.
10 4,853,257. As viewed in Figure 3, the glass ribbon 22 moves

from left to right beneath the coating apparatus 20 e.g. through a coating position. As will be appreciated the invention is not limited to the chamber, not shown, containing
15 the pool of molten metal, nor to a non-oxidizing atmosphere and any chamber design having any type of atmosphere as well as other processes for moving a heated substrate past a coating apparatus embodying features of the invention may be used in the practice of the invention.

20 In general and not limiting to the invention, the ribbon 22 has a thickness range from about 0.08 inch to about 0.50 inch (about 2 to about 13 millimeters) and moves at speeds of about 700 to about 100 inches (about 17.80 meters to about 2.54 meters) per minute, respectively. The molten tin
25 bath 24 has a temperature in the range of about 1000°F (538°C) to about 2000°F (1094°C).

The apparatus 20 includes an elongated coating unit
25, two elongated exhausts 28 and 26, one on each side of the coating unit 25, and two elongated discharge units 31 and 32,
30 one on each outboard side of an exhaust as shown in Figure 3. The term "elongated" as used herein means that the coating unit, exhausts and discharge units extend across the width of the ribbon i.e. transverse to the movement of the ribbon 22. The discharge units 31 and 32 provide an inert gas curtain to
35 prevent the coating vapors from the coating zone, i.e. the

zone between the discharge units 31 and 32, from moving into the chamber atmosphere and also to prevent the chamber atmosphere from moving into the coating zone. As can be appreciated the separation between the coating zone and chamber atmosphere is required because the atmosphere in the coating zone as will be discussed is an oxidizing atmosphere, and the chamber atmosphere as discussed above is a non-oxidizing atmosphere. In the practice of the invention, the inert gas was nitrogen.

10 The exhausts 26 and 28 in accordance with the teachings of the invention are not equally spaced from the coating unit 25. More particularly, with the glass ribbon moving from left to right as shown in Figure 3, the exhaust 28 is closer to the coating unit 25 than the exhaust 26. By
15 positioning the exhausts at different distances from the coating unit the coating vapors are in contact with the ribbon surface for different periods of time. Therefore, all other parameters being equal, e.g., glass temperature, spacing between the coating unit and glass ribbon surface and exhaust
20 pressures, a thicker coating will be deposited on the ribbon as it passes between the exhaust 26 and the coating unit 25, than between the coating unit 25 and the exhaust 28. This feature of the invention will be more fully appreciated in the discussion of the coating system 19 shown in Figure 2.

25 As can now be appreciated, the design of the discharge units 31 and 32, the exhausts 26 and 28 and coating unit 25 are not limiting to the invention. The invention has been practiced using the exhausts 26 and 28 with an elongated opening 36 connected to a collection chamber 38 and using the
30 discharge units 31 and 32 with an elongated opening 50 connected to a discharge chamber 46. The inert gas has uniform pressure and constant velocity along the length of the opening 50 to provide a curtain of inert gas, a portion of

which flows into the chamber (not shown) atmosphere and a portion toward the adjacent exhaust 26 or 28 as shown in Figure 3.

The coating unit 25 includes a discharge chamber
5 56. The coating vapor exits the chamber 56 by way of elongated opening 58 and is directed toward the surface of the glass ribbon 22 passing beneath the opening 58. The coating vapor has a uniform pressure and constant velocity along the length of the opening 58 and has sufficient pressure to allow
10 a portion of the coating vapor to flow upstream and a portion to flow downstream as viewed in Figure 3.

The amount of nitrogen typically introduced by each discharge unit 31 and 32 ranges from about 20 to about 300 standard cubic feet per minute for a ribbon having a width of
15 about 160 inches (4.06 meters). As can be appreciated the flow rate of the nitrogen is not limiting to the invention; however, it should be sufficient to provide an inert curtain separating the coating zone and the chamber atmosphere.

The openings 36 of the exhausts 26 and 28 and the
20 exhaust pressure is adjusted to exhaust a portion of the inert gas from the adjacent discharge unit 31 and 32, respectively, and a portion of the coating vapor from the coating unit 25. As seen in Figure 3 and as discussed above, the exhaust 26 is spaced further from the coating unit 25 than the exhaust 28.
25 With this arrangement and maintaining the exhaust pressure the same for each exhaust unit, the coating vapor residence time is greater for the glass ribbon 22 as it moves from the exhaust 26 toward the coater unit 25 than for the glass ribbon as it moves from the coater unit 25 toward the exhaust 28.

30 Although the above asymmetric arrangement is preferred, because of the simplicity thereof, the invention is not intended to be so bound, since the discovery herein resides in the fact that having different coating vapor residence times on different sides of a coater unit alters the
35 final composition of the coating. Therefore, other

apparatuses or processes suitable for obtaining such an effect can be used. It has been determined that the same effect achieved with asymmetrically arranged exhausts, as discussed above, can also be achieved, even with symmetric spacing of the coating unit 25 and the exhausts by, for example, adjustment of the height or level of the openings 36 of the exhausts 26 and 28 relative to one another and to the glass ribbon. Another method to vary the coating vapor residence time is to vary the ratio of the flow of the exhaust 26 to the exhaust 28.

By way of illustration only, in the instance when the spacing between the coating unit 25 and exhausts 26 and 28 is symmetrical, reducing the pressure of the exhaust 26 below the pressure of the exhaust 28, results in the coating vapor residence time between the coating unit 25 and exhaust 26 being greater than the coating vapor residence time between the coating unit 25 and the exhaust 28.

Referring now to Figure 2, the coating system 19 was used to apply the coating 14 of the coated article 10 shown in Figure 1. The coating system 19 includes a coating station 59 for applying a compositionally graded coating and coating station 60 for extending the thickness of the predominantly tin oxide region at the surface 18 of the coating 14 (see Figure 1). The coating station 59 includes coating units 61, 62 and 64, exhausts 66, 68, 70 and 72 and discharge units 31 and 32. The coating station 60 is not limiting to the invention; however the coating station used in the practice of the invention was the type of coating apparatus disclosed in U.S. Patent No. 4,853,257. Opening 50 of the discharge unit 31 is spaced about 25 inches (63.5 centimeters) from opening 50 of the discharge unit 32; opening 74 of the exhaust 66 is spaced about 22-1/2 inches (57 centimeters) from the opening 50 of the discharge unit 32; opening 76 of the coating unit 61 is spaced about 20 inches

(51 centimeters) from the opening 50 of the discharge unit 32; opening 78 of the exhaust 68 is spaced 17-1/2 inches (44.5 centimeters) from the opening 50 of the discharge unit 32; opening 80 of the coating unit 62 is spaced about 12-1/2 inches (32 centimeters) from the opening 50 of the discharge unit 32; opening 82 of the exhaust 70 is spaced about 10 inches (25.4 centimeters) from the opening 50 of the discharge unit 32; opening 84 of the coating unit 64 is spaced about 5 inches (12.7 centimeters) from the opening 50 of the discharge unit 32, and opening 86 of the exhaust 72 is spaced about 2-1/2 inches (6 centimeters) from the opening 50 of the discharge unit 32. The coating station 60 was spaced about 6 feet (1.8 meters) from the discharge unit 32.

The openings 50, 74, 76, 78, 80, 82, 84, and 86 were spaced, in a convenient manner, about 0.2 inches (0.51 centimeter) above the upper surface of the glass ribbon 22 as viewed in Figure 2. The length of the openings 50 was about 25 inches (64 centimeters); the length of the openings 74, 78, 82 and 86 was about 25 inches (64 centimeters) and the length of the openings 76, 80 and 84 was about 21 inches (53.34 centimeters). The width of the openings 50 was about 0.125 inch (0.32 centimeter); the width of the openings 74, 78, 82 and 86 was about 0.250 inch (0.64 centimeter) and the width of the openings 76, 80 and 84 was about 0.06 inch (0.15 centimeter). The flows of nitrogen and coating vapor were about 350 to about 700 SLPM (standard liters per minute). The exhaust flow was about 375 to about 770 SLPM. The glass ribbon speeds were between about 200-700 inches (5.08-17.78 meters) per minute, the temperature of the glass ribbon moving into, through and out of the coating stations 59 and 60 was between about 1170-1250°F (635-675°C).

The coating system 19 and in particular the coating station 59 and the method associated therewith are especially effective for the chemical vapor deposition (CVD) of coatings

from mixtures of silicon and metal containing precursors to provide the article 10 shown in Figure 1.

In the following discussion, the coating 14 is made from a mixture of tin containing precursors and silicon
5 containing precursors capable of being volatilized and converted to their corresponding oxides in the presence of oxygen at temperatures in the range of about 750° to about 1500°F (about 400°C to about 815°C). As will be appreciated the invention is not limited thereto and other metal
10 containing precursors may be used with the coating apparatus and in the coating processes discussed above.

Examples of silicon compounds that may be used in the practice of the invention include, but are not limited to, tetraethoxysilane, silane, diethylsilane,
15 di-t-butoxydiacetoxysilane and the silicon compounds disclosed in U.S. Patent No. 3,378,396 to Zaromb and U.S. Patent Nos. 4,187,336, 4,308,316, 4,377,613, 4,419,386, 4,206,252, 4,440,822, and 4,386,117.

20 Compounds that have been used in the practice of the invention include diethylsilane, tetramethoxysilane, tetraethoxysilane, tetraisopropoxysilane, diethyldichlorosilane, tetramethylcyclotetrasiloxane and triethoxysilane.

25 In addition to the silicon containing precursors discussed above, the invention contemplates silicon containing precursors that can be converted to their corresponding silicon oxides and can be used in admixture with the metal containing precursors to form the desired coating on a
30 substrate e.g. a glass substrate having a coating with the desired mixed oxide gradient.

When looking for a silicon containing precursor to form a silicon oxide coating, one skilled in the art would not normally choose a precursor having an Si-O bond because it is
35 one of the strongest bonds in nature to break, as is evidenced

by the stability of the mineral quartz (SiO_2). Therefore breaking the Si-O bond in the precursor and rearranging it into a network lattice containing the silicon oxide bonds desired for a coating is difficult e.g. the siloxane bond
5 requires high temperature and/or long periods of time to form a corresponding silicon oxide coating. For this reason silicon containing precursors having the siloxane structure would not be expected by one skilled in the art to be useful in the formation of a silicon oxide coating on a moving
10 substrate.

It has been determined, however, that if a compound carrying an Si-O bond also carries at least one specific functional group, the reactivity of the silicon containing precursor having the Si-O bond, and therefore its coating
15 formation rate, will be increased, even though the bond strengths would not seem to indicate any appreciable change in its coating formation behavior. The functional groups that are capable of giving the silicon containing precursor containing an Si-O bond the ability to be easily converted to
20 a silicon oxide coating include hydrogen, halogens, vinyls and α -chlorinated alkyls. The reactivity of the silicon containing precursor can then be tailored by the appropriate choice of functional groups. The silicon containing precursor of the instant invention is not limited to having only the
25 above-defined substituents thereon. As long as one or more of the above-defined functional groups is present on the silicon containing precursor carrying the Si-O bond, other groups, such as alkyls and other substituents more fully defined below, can also be present without a significant deleterious
30 effect on the overall reactivity of the silicon containing precursor.

Compounds bearing the Si-O bond can be exemplified by reference to the following structural formula I:

I



wherein R₁ is selected from a group of compounds not having an oxygen available to form the peroxide bond, including, for example,

alkyl, or substituted alkyl, radicals having from 1 to 10, preferably 1 to 4, carbon atoms, such as

-CH₃, -CH₂CH₂CH₃ and -CH₂CH₂OH;

halogenated or perhalogenated alkyl radicals having from 1 to 10, preferably 1 to 4, carbon atoms, such as -CCl₃, -CH₂CHClCH₃ and -CH₂CCl₂CCl₃;

alkenyl or substituted alkenyl radicals having from 2 to 10, preferably 2 to 4, carbon atoms, such as -CH=CHCH₃ and -CH=CH₂;

alkynyl or substituted alkynyl radicals having from 2 to 10, preferably 2 to 4, carbon atoms, such as -C≡C-CH₃ and -C≡CH; and

aryl or aralkyl or substituted aryl or aralkyl radicals having from 6 to 11, preferably 6 to 9, carbon atoms, such as -C₆H₅ and -C₆H₄CH₃;

wherein R₂ is a functional group that forms a bond with the Si atom which is easily thermally broken e.g. at temperatures between about 200°F-800°F (about 93.5°C-445°C) and preferably between about 400°F-700°F (205°C-370°C). The functional group (R₂) capable of giving the silicon containing precursor the ability to be easily converted to a silicon oxide coating may be selected from Group B consisting of:

hydrogen;

halogen, preferably Cl;

alkenyl or substituted alkenyl radicals as defined in Group A for R₁;

5 α-halogenated alkyl or perhalogenated alkyl, and
alkynyl or substituted alkynyl radicals as defined in Group A for R₁;

wherein R₃ is a bridging group to provide for multiple silicon atom compounds. R₃ may be selected from Group C consisting of:

10 -S-;

-N-R₅ wherein R₅ is an alkyl or substituted alkyl radical
|
having from 1 to 10, preferably 1 to 4, carbon atoms,
15 such as -CH₂CH₃ or -CH₂CH₂CH₃;

-N-;

|

20 -P-H;

|

-P-R₅ wherein R₅ is as defined above.


|

25

|

-P-

30



where n is 1 to 10 preferably 1 to 4, and

wherein R₄ completes the bonding on the foundation silicon atom. R₄ may be selected from the Groups A and B above and the following Group D consisting of:

- 5 alkoxide or substituted alkoxide radicals having from 1 to 10, preferably 1 to 4, carbon atoms, such as -OCH₂CH₃; alkyl or substituted alkyl radicals having from 1 to 10, preferably 1 to 5, carbon atoms, such as -CH₂CH₃; -CN; -OCN, and
- 10 -PH₂;
- alkylphosphines, and dialkylphosphines, wherein the alkyl radical has from 1 to 10, preferably 1 to 4, carbon atoms, such as -PHCH₃ and -P(CH₂CH₃)₂.
- Substituents for Groups A, B and D discussed above, can
- 15 be selected from following Group E consisting of:
- an alkoxide radical having from 1 to 10, preferably 1 to 4, carbon atoms, such as -OCH₂CH₂CH₂CH₃;
- an alkyl radical having from 1 to 10, preferably 1 to 4, carbon atoms, such as -CH₂CH₂CH₃;
- 20 a halogen or a halogenated alkyl radical having from 0 to 10, preferably 0 to 4, carbon atoms, such as Cl or -CCl₃;
- an alkenyl radical having from 2 to 10, preferably 2 to 4, carbon atoms, such as -CH=CH₂;
- an alkynyl radical having from 2 to 10, preferably 2 to
- 25 4, carbon atoms, such as -C≡CH;
- an aryl or aralkyl radical having from 6 to 11, preferably 6 to 9, carbon atoms, such as -C₆H₅;
- CN;
- OCN;
- 30 phosphine, alkylphosphine, and dialkyl phosphine radicals, wherein the alkyl group has from 1 to 10, preferably 1 to 4, carbon atoms, such as -PH₂, -PHCH₃, -P(CH₂CH₃)₂, and
- OH.

A variety of compounds can be formed from the base structure I. When a molecule containing a single silicon atom is desired, R₃ can be selected from Groups A, B or D. When multi-silicon atom molecules are desired, R₃ is a bridging group. In the multi-silicon atom molecule case, R₃ connects two silicon atoms directly. When the multi-silicon atom molecules are cyclic, R₄ is not present on any of the silicon atoms. When the multi-silicon molecules are straight or branched chain molecules, the R₄ groups are present only on the silicon atoms in the terminating position in the chain. When molecules with more than two silicon atoms are desired, the bridging groups, R₃, can be the same or different.

Another type of bonding is possible to create multi-silicon atom molecules with Si-O-Si bonds. In this case, R₁ is no longer selected from Group A and is instead another silicon bearing group from base structure I with the continued requirement of having an R₂ selected from Group B. The bonding between the silicon bearing groups is chosen so that a direct Si-O-Si bond is formed. If a molecule with more than two silicon atoms is desired, R₄ is only present on the terminating silicon atoms as described above. R₃ can now be selected from Groups A, B, C or D. By selecting R₃ from Group C we can create multi-silicon atom molecules with different bridging groups, i.e., Si-O-Si-N-Si.

As can now be appreciated, simple or complex silicon containing precursors are possible. The only requirement remains that each silicon atom have bonded directly to it an oxygen atom and a functional group selected from Group B.

Specific compounds that have been used in the practice of the invention include tetramethylcyclotetra-siloxane, tetramethyldisiloxane and triethoxysilane. Specific compounds that may be used in the practice of the invention, but not limiting thereto, are methyldimethoxysilane, dimethylmethoxysilane, trimethoxysilane, dimethylchloro-


methoxysilane, methylchlorodimethoxysilane, chlorotri-
methoxysilane, dichlorodimethoxysilane, trichloromethoxy-
silane, triethoxysilylacetylene, trimethylpropynylsilane,
tetramethyldisiloxane, tetramethyldichlorodisiloxane,
5 tetramethylcyclotetrasiloxane, triethoxysilane, chlorotri-
ethoxysilane, pentachloroethyltriethoxysilane and
vinyltriethoxysilane.

Metal containing precursors that can be used in
admixture with the silicon containing precursors defined above
10 in the chemical vapor deposition of mixed oxides on a glass
substrate include metal containing precursors that are
vaporizable at or below about 500°F (260°C) and that will react
with an oxygen-containing gas to form the corresponding metal
oxides. Preferably, but not limiting to the invention,
15 compounds that may be used include organometallic compounds
containing metals including but not limited to titanium,
vanadium, chromium, manganese, iron, cobalt, nickel, copper,
zinc, gallium, germanium, arsenic, selenium, yttrium,
zirconium, niobium, molybdenum, cadmium, rhodium, ruthenium,
20 palladium, indium, antimony, tellurium, tantalum, tungsten,
platinum, lead, bismuth, aluminum, and tin. Of these metal
compounds, tin compounds are most preferred. Examples of tin
compounds useable herein include those defined by the
following structural formula II:

25

II

30



wherein R₆, R₇, R₈, and R₉ are the same or different and
include but are not limited to halogens preferably Cl or F, an
alkyl radical having from 1 to 10, preferably 1 to 4, carbon

preferably 6 to 9, carbon atoms, such as $-C_6H_5$. In the practice of the invention any other organic or inorganic functional group can be used provided the vapor pressure of the resultant compound is at least 0.01 pounds per square inch absolute, below about 500°F (260°C).




The silicon containing precursors defined above, including those bearing the Si-O bond, can be used alone, or they can be used in admixture with the organometallic compounds discussed above in the chemical vapor deposition of the corresponding single or mixed oxides on a glass substrate. However, when the silicon containing precursor is used alone, or in admixture with other metal containing precursors, in the chemical vapor deposition of single or mixed oxides onto a moving substrate e.g. coating a ribbon of glass advancing along a molten metal bath or on a conveyor, it is desirable to have a rate of silicon oxide deposition sufficient to coat the moving glass substrate. For example, when coating an advancing glass ribbon and the deposition rate of silicon oxide is relatively low, the glass ribbon speed has to be reduced. More particularly, to deposit about a 1200 Å thick coating on a glass ribbon moving at a line speed of greater than about 300 inches (7.62 meters) per minute, the rate of deposition of all classes of silicon containing precursors used in the chemical vapor deposition processes has to be increased to attain a uniform coating.

A number of materials have been identified that can be used to accelerate the deposition rate of silicon oxides from their precursors. The type and functionality of each accelerant depends to some extent on the silicon containing precursors with which it will be used. Combinations have been determined for a specific coated article and for the process used to deposit the desired coating, in particular, the mixed oxide of the invention. It has further been determined that a synergistic effect occurs between certain combinations of

precursors and accelerants that result in a beneficial altering and control of the morphology of the coating.

Accelerants that can be used in the practice of the invention to increase the deposition rate of silicon oxide
 5 alone or in combination with another oxide, for example, tin oxide, can be defined as follows:

- (1) Lewis Acids, such as trifluoroacetic acid and hydrochloric acid.
- (2) Lewis Bases, such as NaOH, NaF, CH₃OH, CH₃OCH₃ and
 10 S(CH₃CH₂)₂.
- (3) Water.
- (4) Compounds of nitrogen, phosphorus, boron, and sulfur having the following structural formulae:



(d)



(e)




wherein Y is selected from the group consisting of nitrogen, boron and phosphorus and R₁₀, R₁₁, R₁₂, R₁₃ and R₁₄ are selected from the following list of functional groups, hereinafter referred to as Group F:

- hydrogen;
- halogens, preferably Cl;
- alkenyl or substituted alkenyl radicals having from 2 to 10, preferably 2 to 4, carbon atoms, such as -CH=CH₂;
- perhalogenated alkyl or substituted alkyl radicals having from 1 to 10, preferably 1 to 4, carbon atoms, such as -CClH₂ or halogenated alkyl or substituted alkyl radicals having from 1 to 10, preferably 1 to 4, carbon atoms, such as -CCl₂CH₂CH₃;
- acyloxy radicals having from 1 to 10, preferably 1 to 4, carbon atoms, such as -OCOCH₃;
- alkynyl or substituted alkynyl radicals having from 2 to 10, preferably 2 to 4, carbon atoms, such as -C≡CH;

- alkyl or substituted alkyl radicals having from 1 to 10, preferably 1 to 4, carbon atoms, such as -CH₃, -CH₂CH₂CH₃;
- 5 aryl or substituted aryl radicals having from 6 to 10, preferably 6 to 9, carbon atoms, such as -C₆H₄CH₃;
- alkoxide or substituted alkoxide radicals having from 1 to 10, preferably 1 to 4, carbon atoms, such as -OCH₂CH₂CH₃;
- 10 wherein said substituents are from Group E discussed above,
- examples of which compounds include but are not limited to triethylphosphite, trimethylphosphite, trimethylborate, PF₅, PCl₃, PBr₃, PCl₅, BCl₃, BF₃,
- 15 (CH₃)₂BBr, SF₄ and HO₃SF. In the practice of the invention triethylphosphite was used.
- (5) Compounds of aluminum having the following structural formula III may be used to accelerate the deposition rate of silicon containing
- 20 precursors alone or in combination with other metal containing precursors (the "other metal containing precursors", as can be appreciated, do not include aluminum containing precursors):

III

25



30

wherein R₁₅, R₁₆, and R₁₇ are the same or different and are selected from the following Group G:

hydrogen;

halogens, preferably Cl;

-O-R₁₇, wherein R₁₇ is a linear, branched or substituted alkyl radical having from 1 to 10

- carbon atoms, preferably 1 to 4, with substituents selected from Group E discussed above;
-S-R₁₈, where R₁₈ is equivalent to R₁₇ defined above;
5 -NH₂;
R₁₉-N-R₂₀, wherein R₁₉ and R₂₀ are linear or branched alkyl groups, or substituted alkyl groups having from 1 to 10, preferably 1 to 4, carbon atoms, with substituents selected from Group E
10 discussed above; (less the phosphine groups, such as -PH₂); and
N R₂₁, wherein R₂₁ forms cyclic group having from 2 to 10 preferably 2 to 6 carbon atoms, with substituents selected from Group E discussed above
15 (less the phosphine groups).
(6) Ozone.

The mechanism that causes the accelerants of the invention to increase the rate of deposition is not completely understood. Even though the mechanism is not completely
20 understood the results, discussed below, clearly demonstrate that the mixed oxide coating deposition rate was increased. With reference to Table 2 in Example I below, Run Nos. 11 and 12 contain the accelerant triethylphosphite. The growth rate of the silicon oxide coating was at least twice the rate of
25 the silicon oxide coating of Run No. 2 that did not have an accelerant.

A moving glass substrate was coated using the same precursor chemistry as used in Run Nos. 11 and 12 of Table 2 and similar deposition rates resulted. The precursors were
30 vaporized at a temperature of about 150°F (65°C) to about 500°F (260°C), and the gaseous mixture of the precursors, oxygen containing gases, and carrier gas and accelerant, were brought into contact with a glass ribbon supported on a molten metal bath and heated to a temperature of about 950°F (510°C) to

about 1350°F (730°C). The glass ribbon advanced at a speed of about 170 to 730 inches (4.25 to 18.00 meters) per minute.

The amounts of the components that may be used in the practice of the invention are defined below in Table 1.

5

Table 1

	<u>Compound</u>	<u>Mole Percent</u>	
		<u>Broad Range</u>	<u>Preferred Range</u>
10			
	Metal Containing Precursor	0.005 to 5.0	0.1 to 2.0
	Silicon Containing Precursor	0.0001 to 5.0	0.05 to 2.0
15	Oxygen-Containing Gas	1.0 to 99.0	5.0 to 50.0
	Accelerant	0.0001 to 10.00	0.01 to 2.0

When the substrate 12 (see Figure 1) e.g. glass substrate is subjected to chemical vapor deposition of mixed oxides, for example, a mixture of silicon oxide and tin oxide, to obtain the coating 14 thereon in accordance with the process of the invention, the coating 14, as discussed above, is characterized by having a continuously varying composition as the distance from the glass-coating interface 16 increases, resulting in a substantial reduction of iridescence in the coated product. Assuming a coating composed of substantially silicon oxide and tin oxide, that portion of the coating adjacent to the glass-coating interface 16 is composed largely of silicon oxide and as the distance from the glass-coating composition increases, each succeeding region of the continuously varying composition contains a silicon oxide to tin oxide ratio that varies as the distance from the glass-coating interface increases. More particularly, the

percent of silicon oxide decreases as the percent of tin oxide increases, so that as the opposite surface 18 is reached, the region is composed predominantly of tin oxide. Thereafter the thickness of the region of predominantly tin oxide may be
5 increased to reduce the emissivity of the coated article.

It has been determined that when chemical vapor deposition of mixed oxides on a glass substrate is carried out with the addition of one or more of the accelerants of the instant invention e.g. compounds of phosphorus, aluminum, or
10 boron, a small amount of the foundation atom e.g. phosphorus, aluminum or boron is found dispersed in the coating 14. The presence of phosphorus, aluminum and/or boron in the coating affects the morphology of the resultant coating so that the aforementioned continuously changing components have a
15 decreased probability of forming strata with discrete composition e.g. layers that have a fixed ratio of silicon oxide to tin oxide for thicknesses greater than about 70 Å. Additionally, the presence of phosphorus, aluminum and/or boron affects the morphology of the resultant coating by
20 decreasing the percent crystallinity (approaching 0% crystallinity) and thereby reduces the light scattering properties which can be observed as haze. The amount of the phosphorus, aluminum or boron compound incorporated in the layer is a function of process variables. In the practice of
25 the invention a glass ribbon moving at speeds between 175 to 730 inches (425 to 1800 centimeters) per minute, and having a temperature in the range of 1180°F (637°C) to 1220°F (660°C) was coated with a gaseous mixture having a phosphorus compound as an accelerant; the mole fraction of the accelerant was 0.01 to
30 0.5. One to 12 atomic percent of phosphorus was found dispersed in the coating. The invention encompasses using an amount of accelerant greater than 0 and up to 15 atomic percent with a preferred range of 1 to 5 atomic percent.

The present invention will be further appreciated and understood from the description of specific examples which follow:

5

EXAMPLE I

A number of compositions were prepared from silicon containing precursors and monobutyltinchloride to illustrate the increased growth rate of mixed oxide films on a glass substrate in accordance with the teachings of the invention.

10 In each composition, monobutyltinchloride was used with different silicon containing precursors. The precursors were vaporized, when necessary, and the resulting gaseous mixture of precursors, oxygen and nitrogen, were introduced into a quartz tube that was electrically heated and controlled to

15 maintain a temperature of 300°F (150°C). The concentration of the silicon containing precursors was in all instances 0.30 mole percent, the monobutyltinchloride 0.50 mole percent, oxygen 21 mole percent, with the remainder nitrogen. The velocity of the precursors and carrier gas was maintained at a

20 rate of 30 centimeters per second in the quartz tube. This gas mixture was passed over a glass substrate heated to about 1200°F (650°C), for 3 to 30 seconds after which the spent gas mixture was vented into a chemical hood. The film thickness for all the runs except Run No. 8 discussed below was measured

25 using a Tencor™ P1 profilometer. The film growth rate was calculated by dividing film thickness by the coating time. The data obtained are set forth below in Table 2.

Table 2

	<u>Run No.</u>	<u>Silicon Containing Precursors</u>	<u>Growth Rate, Å/Second</u>
5	1	diethylsilane	129
	2	tetraethoxysilane	43
	3	di-t-butoxydiacetosilane	64
	4	tetramethylcyclotetrasiloxane	181
	5	tetramethylcyclotetrasiloxane	205
10	6	tetramethylcyclotetrasiloxane	177
	7	tetramethyldisiloxane	164
	8	ethyltriacetoxysilane	110*
	9	triethoxysilane	139
	10	methyldiacetoxysilane	32
15	11	tetraethoxysilane + 0.31 mole percent triethylphosphite	136
	12	tetraethoxysilane + 0.09 mole percent triethylphosphite	87
20			

*estimated

Run No. 1 was used as the control because the
 25 diethylsilane is generally accepted as having an acceptable
 rate of deposition.

The tetramethylcyclotetrasiloxane precursors used
 in Run Nos. 4, 5 and 6 were obtained from different suppliers.
 Run Nos. 2, 3 and 10 using silicon containing precursors
 30 having an Si-O bond without the accelerants or the functional
 groups of the instant invention had an expected low growth
 rate. Run Nos. 4, 5, 6, 7 and 9 which had a Si-O bond with
 the functional group of the instant invention had a deposition
 rate equal to or better than the control Run No. 1.
 35 Additionally Run No. 2 when augmented with an accelerator as

taught in the instant invention (see Run Nos. 11 and 12) exhibited a deposition rate greater than Run No. 2 and approaching (Run No. 12) or exceeding (Run No. 11) the deposition rate of control Run No. 1.

5 Run No. 8 is a compound having the Si-O bond that does not contain a functional group or accelerant of the instant invention; however, it showed a deposition rate equal to the control Run No. 1. The film quality of Run No. 8 was extremely poor and the film thickness had to be estimated
10 using interference colors which was different from the measuring technique used for Run Nos. 1-7 and 9-12.

EXAMPLE II

Two runs were carried out showing the advantages
15 obtained using an asymmetric coater configuration of the instant invention in place of a symmetric coater configuration. Referring to Figure 3, in one run the exhausts 26 and 28 were positioned relative to the coating unit 25 such that $x/y=2$ where "x" is the distance between the exhaust 28
20 and the coating unit 25 and "y" is the distance between the coating unit 25 and the exhaust 28, while in the other embodiment, the exhausts 26 and 28 were positioned relative to the coating unit 25 such that $x/y=1$. The coating composition vapor was maintained at 337°F (166°C) and contained 1.2 mole
25 percent monobutyltinchloride, 0.3 mole percent tetraethoxysilane, 0.5 mole percent triethylphosphite, 1.0 mole percent water, 20 mole percent oxygen, and the balance nitrogen. The soda-lime-silica float glass ribbon supported by and moving along a molten metal bath had a thickness of
30 about 0.118 inch (0.300 centimeter), a temperature of about 1200°F (650°C), and a line speed of 510 inches (13 meters) per minute. The surface of the openings of the nitrogen curtain provided by the discharge units 31 and 32 and the exhausts 26

and 28 were maintained at a height of about 0.22 inch (0.55 centimeter) above the surface to be coated of the glass ribbon 2.

The tin depth profile of a film produced on the glass ribbon using both the asymmetric and symmetric coater configurations is shown in the graph in Figure 4. The film analysis was accomplished using the Rutherford Backscattering Spectrometry (RBS) technique for purposes of comparing the gradient film produced by the two coater configurations. The RBS spectra in Figure 4 were taken at a special angle in order to obtain optimum depth resolution of the tin atom distribution through the film.

A comparison of the asymmetric coater configuration (shown by solid line 210) with that of the symmetric coater configuration (shown by dotted line 212) is shown in the RBS spectra in Figure 4. Of significance between the two tin depth profiles 210 and 212 is the extended region of the tin signal from 2025 keV at 3.7 relative counts down to 1890 keV at 1.4 relative counts as compared to the symmetric coater which has its tin signal varying from 2025 KeVC at 3.6 relative counts down to 1940 keV at 1.4 relative counts. This difference shows an increase in film thickness for an asymmetric coater configuration. As can be seen from Figure 4 the asymmetric coater configuration provides the gradient coating with an extended range of varying composition.

EXAMPLE III

A series of runs was carried out using the coating apparatus 20 of Figure 3 where the exhausts 26 and 28 were positioned relative to the coating apparatus 20 such that $x/y=1$. The coating composition vapor was maintained at 320°F (165°C) and contained 0.8 mole percent monobutyltin chloride, 0.3 mole percent tetraethoxysilane, 0.1 mole percent triethylphosphite, 0.54 mole percent water, with the balance air. The total gas flow and coater height were varied while

the concentrations were held constant. The results obtained are set forth in the process contour chart in Figure 5. By altering coater height in inches and carrier flow in standard liters per minute, the boundary layer conditions are altered in the coating zone thereby altering the relative ratio of tin oxide and silicon oxide deposited. The process contour chart shows how these two other techniques i.e. coater height and volumetric feed, alter the coating composition on the glass substrate.

As shown in Figure 5 increasing the carrier flow for a given coating unit height, increases the ratio of tin oxide to silicon oxide. In other words, the weight percent of tin oxide increases as the weight percent of silicon oxide decreases. Raising the coating unit height for a given carrier flow decreases the ratio of tin oxide to silicon oxide i.e. the weight percent of tin oxide decreases as the weight percent of silicon oxide increases.

EXAMPLE IV

A number of runs were carried out to show the effects of water and triethylphosphite on the thickness of a mixed oxide film at a constant vapor residence time. The process chart, Figure 6, was developed using experimental design data. The coating unit 25 shown in Figure 3 was used with the exhausts 26 and 28 positioned relative to the coating unit 25 such that $x/y=1$. The precursor vapor was maintained at 320°F (165°C) and contained 0.8 mole percent monobutyltin chloride, 0.3 mole percent tetraethoxysilane. Triethylphosphite (TEP) and water were varied and sufficient air was added to obtain a volumetric feed rate of 500 standard liters per minute. The glass ribbon 22 had a thickness of 0.118 inch (0.300 centimeter), a temperature of 1200°F (650°C) and a line speed of 510 inches (13 meters) per minute. The coating unit 25 was maintained at a height of 0.22 inch (0.56 centimeter) above the surface of the glass ribbon. Note the

substantial effect exhibited by the presence of triethylphosphite on the coating thickness. As the mole percent of triethylphosphite was increased the coating thickness increased. Increasing the mole percent of the water
5 also increased the coating thickness.

EXAMPLE V

The article 12 of Figure 1 was produced using the coating station 59 shown in Figure 2, in conjunction with the
10 coating station 60 described in the teachings of Henery. Coated articles were produced at three glass thicknesses i.e. at three different glass ribbon speeds to demonstrate the flexibility of the process. The coating station 59 was used to produce a coating that varied in composition from
15 predominantly silicon oxide at the glass-coating interface 16 to predominantly pure tin oxide and the coating station 60 produced an extended thickness of predominantly tin oxide.

The coating station 59 had three coating units 61, 62 and 64 with openings 76, 80 and 84 respectively, and four
20 exhausts 66, 68, 70 and 72. The exhausts 66 and 68 were positioned relative to the coating unit 61 in a symmetric configuration while the exhausts 68 and 70 and the exhausts 70 and 72 were arranged in an asymmetric configuration about their respective coater units 62 and 64. In addition the
25 coating station 59 had two discharge units 31 and 32 each with opening 50. The distance between the openings 74 and 76, 76 and 78, 80 and 82, 84 and 86 was about 2-3/4 inches (7.08 centimeters). The distance between the openings 80 and 78, and between 84 and 82 was about 5-1/2 inches (14.0
30 centimeters).

To effect the desired change in composition of the coating, different chemical feed rate ranges are required in each of the coating units 61, 62 and 64. The chemical concentrations required to produce the desired compositional
35 change are also a function of the speed of the glass ribbon.

Examples of typical setpoints are given in Table 3. In each of these cases the carrier gas was air, maintained at a temperature of about 320°F (160°C). The total gas flow of the discharge units 31 and 32 was held at about 500 standard
 5 liters per minute. The coating station 59 was spaced about 0.22 inches (0.59 centimeter) above the moving glass ribbon 22. The extended region of predominantly tin oxide was deposited at the coating station 60 using the teachings of U.S. Patent No. 4,853,257.

10 The equation ($\sqrt{a^2 + b^2}$) usually used by those skilled in the art to quantify the observability of color of an object is discussed by Hunter in Food Technology, Vol. 32, pages 100-105, 1967 and in The Measurement of Appearance, Wiley and Sons, New York, 1975. A coated glass product having
 15 a Hunter value of 12 or less is considered to exhibit no appreciable observable color. Listed in Table 3 under the column entitled Color Saturation Index is the measured Hunter value for the samples. As can be seen, all the samples had a color saturation index below 12.

20

Table 3

	MBTC	MBTC	MBTC	TEOS	TEOS	TEOS
Sample	Unit 61	Unit 62	Unit 64	Unit 61	Unit 62	Cell 64
<u>#</u>	<u>mole %</u>	<u>mole %</u>	<u>mole %</u>	<u>mole %</u>	<u>mole %</u>	<u>mole %</u>
25						
1	0.280	0.190	0.490	0.050	0.050	0.020
2	0.290	0.300	0.600	0.100	0.160	0.300
3	0.350	0.200	0.940	0.300	0.300	0.270
4	0.400	0.200	0.940	0.300	0.300	0.330
30						
5	0.600	0.758	0.790	0.390	0.400	0.350
6	0.500	0.600	1.200	0.265	0.300	0.100

MBTC means monobutyltintrichloride

TEOS means tetraethoxysilane

Sample #	TEP Unit 61	TEP Unit 62	TEP Unit 64	WATER Unit 61	WATER Unit 62	WATER Unit 64
	mole %	mole %	mole %	mole %	mole %	mole %
1	0.300	0.100	0.025	0.170	0.600	0.600
2	0.280	0.110	0.039	0.180	0.330	0.630
3	0.280	0.120	0.070	0.150	0.610	0.370
4	0.280	0.100	0.050	0.150	0.610	0.370
5	0.266	0.120	0.066	0.150	0.180	0.640
6	0.400	0.300	0.288	0.400	1.000	1.000

TEP means triethyphosphite

15

Sample #	GLASS TEMPERATURE °F	GLASS SPEED inches/min.	COLOR SATURATION INDEX	Gradient Thickness Å	Tin Oxide Thickness Å
1	1230	340	5.0	1200	4000
2	1234	340	5.0	1100	4000
3	1194	340	2.3	1250	3700
4	1200	340	3.6	1150	3650
5	1190	490	8.9	850	1750
6	1200	700	4.6	1000	1700

Although several embodiments of the present invention have been described and illustrated, it will be apparent to those skilled in the art that various changes and further modifications may be made therein without departure from the spirit of the invention or from the scope of the appended claims.

CLAIMS

1. A method of coating a moving substrate to provide a coating having a continuously varying chemical composition as the distance from the substrate increases, comprising the steps of:

directing a vapor coating composition onto the surface of the substrate at a first position;

thereafter moving a first portion of the vapor coating composition along a first region of the substrate surface in a first direction and a second portion of the vapor coating composition along a second region of the substrate surface in a second direction opposite to the first direction, and

maintaining the first portion of the coating composition on the first region of the substrate surface for a longer period of time than the second portion of the vapor coating composition on the second region of the substrate surface in order to coat the substrate with the coating having the continuously varying chemical composition as the distance from the substrate increases.

2. The method of claim 1, wherein the substrate is a glass substrate, and said first direction is substantially parallel with the direction in which the substrate is moving.

3. The method of claim 1, further including practicing said directing step at a second position spaced from and on one side of the first position and a third position spaced from the first and second positions such that the second position is between the first and third positions.

4. The method of claim 3, wherein the substrate is coated in a chamber having a non-oxidizing atmosphere and further including providing a curtain of inert gas to prevent the non-oxidizing atmosphere from moving to the positions wherein the curtain of inert gas and the positions therebetween define a coating zone.

5. The method of claim 1, wherein said maintaining step is accomplished by providing exhaust means on each side of said first position wherein one exhaust means

is spaced a distance "x" from the first position and the other exhaust means is spaced a distance "y" from said first position, and further wherein the ratio of x/y is greater than 1.

6. The method of claim 1, further comprising practicing said step of directing at a second position spaced from the first position.

7. The method of claim 3, further comprising the step of exhausting vapor from both sides of the first and third positions.

8. The method of claim 5, wherein the ratio of x/y is greater than about 1.2.

9. The method of claim 8, wherein the ratio of x/y is from about 1.2 to about 50.

10. The method of claim 3, wherein the substrate is a glass ribbon which is coated in a chamber having a reducing atmosphere and is supported on a pool of molten oxidizable metal.

11. The method of claim 10, wherein the substrate is a glass ribbon and further comprising the step of depositing a tin oxide layer over a coating having a continuously varying chemical composition comprising tin oxide and silicon oxide.

12. A transparent substrate having an amorphous coating thereon composed of one or more mixed metal oxides and having up to 15 atomic percent of an element dispersed therethrough selected from the group consisting of phosphorus, aluminum and boron wherein the mixed metal oxide itself excludes phosphorus, aluminum and boron.

13. A transparent substrate having an amorphous coating thereon composed of mixed metal oxides with regions in the coating of continuously varying ratio of the metal oxides with the substantial absence of strata of a fixed ratio of the metal oxides and up to 15 atomic percent of an element dispersed therethrough selected from the group consisting of phosphorus, aluminum, and boron.

14. The substrate of claim 13, wherein the substrate is glass, mixed metal oxides are silicon oxide and tin oxide with a weight percent of 70-100% of silicon oxide at the glass-coating interface, and a weight percent of 70-100% of tin oxide at the opposite coating surface and the element therethrough is phosphorus.
15. The substrate according to claim 14, wherein one to twelve atomic percent of phosphorus is dispersed in the coating.
16. A transparent substrate according to claim 12, wherein said metal oxide is selected from the group consisting of the oxides of silicon, tin, titanium, tungsten, antimony and mixtures thereof.
17. A transparent substrate according to claim 16, wherein the element dispersed through the coating is phosphorus.
18. A transparent substrate according to claim 16, wherein the element is aluminum.
19. A transparent substrate according to claim 16, wherein the element is boron.
20. A transparent substrate according to claim 16, wherein the metal oxide is selected from the group consisting of the oxides of silicon, tin and mixtures thereof.
21. A transparent substrate according to claim 20, wherein the element dispersed through the coating is phosphorus.
22. A transparent substrate according to claim 20, wherein the element is aluminum.
23. A transparent substrate according to claim 20, wherein the element is boron.

24. A transparent substrate according to claim 13, wherein the mixed metal oxides are selected from the group consisting of the oxides of silicon, tin, titanium, tungsten and antimony.


25. A transparent substrate according to claim 24, wherein the mixed metal oxides are the oxides of silicon and tin.

26. A transparent substrate according to claim 25, wherein the element dispersed through the coating is phosphorus.

27. A transparent substrate according to claim 25, wherein the element is aluminum.

28. A transparent substrate according to claim 25, wherein the element is boron.

29. A silicon-containing precursor for a coating composition defined by the following structural formula:



wherein R_1 is selected from a group of radicals not having an oxygen available to form a peroxide bond, R_2 is a functional group giving the silicon-containing precursor the ability to be easily converted to a silicon oxide coating by providing that the bond between R_2 and the silicon atom is easily thermally broken and is selected from the group consisting of hydrogen, halogen, alkenyl, substituted alkenyl, α -halogenated alkyl, perhalogenated alkyl, alkynyl and substituted alkynyl, R_3 is a bridging group to make multiple silicon atom molecules and R_3 does not contain oxygen, and R_4 completes the bonding structure.

30. The silicon-containing precursor of claim 29, wherein R_2 is selected from the group consisting of halogens and α -halogenated alkyl or perhalogenated alkyl radicals and substituted derivatives having from 1 to 10 carbon atoms.

31. The silicon-containing precursor of claim 29, wherein R_1 is selected from the group consisting of alkyl or substituted alkyl radicals having from 1 to 10 carbon atoms; alkenyl or substituted alkenyl radicals having from 2 to 10 carbon atoms; alkynyl or substituted alkynyl radicals having from 2 to 10 carbon atoms; and aryl or aralkyl or substituted aryl or substituted aralkyl radicals having from 6 to 11 carbon atoms.

32. The silicon-containing precursor of claim 29, wherein R_3 is selected from the group consisting of:

-S-;


-N- R_5 wherein R_5 is an alkyl or substituted alkyl radical having from 1 to 10 carbon atoms;

-N-;

-P-H;

-P- R_5 wherein R_5 is as defined above;

-P-; and



33. The silicon-containing precursor of claim 29, wherein R_4 is selected from the group consisting of alkyl or substituted alkyl radicals having from 1 to 10 carbon atoms; alkenyl or substituted alkenyl radicals having from 2 to 10 carbon atoms; alkynyl or substituted alkynyl radicals having from 2 to 10 carbon atoms; and aryl or aralkyl or substituted aryl or substituted aralkyl radicals having from 6 to 11 carbon atoms.

34. The silicon-containing precursor of claim 29, wherein R_4 is selected from the group consisting of hydrogen; halogen; alkenyl or substituted alkenyl radicals having from 2 to 10 carbon atoms; α -halogenated alkyl or perhalogenated alkyl radicals and substituted derivatives having from 1 to 10 carbon atoms, and alkynyl or substituted alkynyl having from 2 to 10 carbon atoms.

35. The silicon-containing precursor of claim 29, wherein R_4 is selected from the group consisting of alkoxide or substituted alkoxide radicals having from 1 to 10 carbon atoms; alkyl or substituted alkyl radicals having from 1 to 10 carbon atoms; -CN; -OCN; and phosphine, alkylphosphines, and dialkylphosphines, wherein the alkyl radical has from 1 to 10 carbon atoms.


36. The silicon-containing precursor of claim 35, wherein R_4 is selected from the group consisting of -CN; -OCN; and phosphine, alkylphosphines, and dialkylphosphines, wherein the alkyl radical has from 1 to 10 carbon atoms.

37. The silicon-containing precursor of claim 29, wherein the silicon-containing precursor is selected from the group consisting of tetramethylcyclotetrasiloxane and tetramethyldisiloxane.

38. A coating composition comprising a silicon-containing precursor according to any one of claims 29 to 37 and an accelerant to increase the deposition rate of the silicon oxide.

39. The composition of claim 38, wherein the accelerant is selected from the group consisting essentially of a Lewis Acid, a Lewis Base and triethylphosphite.

40. A silicon-containing precursor for a coating composition defined by the following structural formula:



wherein R_1 , R_2 and R_3 are as defined in claim 29, and R_4 is selected from the group consisting of alkyl or substituted alkyl radicals having from 1 to 10 carbon atoms; alkenyl or substituted alkenyl radicals having from 2 to 10 carbon atoms; alkynyl or substituted alkynyl radicals having from 2 to 10 carbon atoms; and aryl or aralkyl or substituted aryl or aralkyl radicals having from 6 to 11 carbon atoms; hydrogen; halogen; α -halogenated alkyl or perhalogenated alkyl radicals and substituted derivatives having from 1 to 10 carbon atoms, and alkynyl or substituted alkynyl having from 2 to 10 carbon atoms; -CN; -OCN; and phosphine, alkylphosphines, and dialkylphosphines, wherein the alkyl radical has from 1 to 10 carbon atoms.

41. The silicon-containing precursor of claim 40, wherein R_1 is selected from the group consisting of alkyl or substituted alkyl radicals having from 1 to 10 carbon atoms; alkenyl or substituted alkenyl radicals having from 2 to 10 carbon atoms; alkynyl or substituted alkynyl radicals having from 2 to 10 carbon atoms; and aryl or aralkyl or substituted aryl or substituted aralkyl radicals having from 6 to 11 carbon atoms.

42. The silicon-containing precursor of claim 40, wherein the bond between R_2 and the silicon atom is easily thermally broken.

43. The silicon-containing precursor of claim 42, wherein R_2 is selected from the group consisting of hydrogen, halogens, alkenyl or substituted alkenyl radicals having from 2 to 10 carbon atoms; α -halogenated alkyl or perhalogenated alkyl radicals and substituted derivatives having from 1 to 10 carbon atoms; and alkynyl or substituted alkynyl radicals having from 2 to 10 carbon atoms.

44. The silicon-containing precursor of claim 43, wherein R_2 is selected from the group consisting of halogens; and α -halogenated alkyl or perhalogenated alkyl radicals and substituted derivatives having from 1 to 10 carbon atoms.

45. The silicon-containing precursor of claim 40, wherein R_3 is selected from the group consisting of:

-S-;


-N- R_5 wherein R_5 is an alkyl or substituted alkyl radical having from 1 to 10 carbon atoms;

-N-;

-P-H;

-P- R_5 wherein R_5 is defined above;

-P-; and



46. The silicon-containing precursor of claim 40, wherein R_4 is selected from the group consisting of alkyl or substituted alkyl radicals having from 1 to 10 carbon atoms; alkenyl or substituted alkenyl radicals having from 2 to 10 carbon atoms; alkynyl or substituted alkynyl radicals having from 2 to 10 carbon atoms; and aryl or aralkyl or substituted aryl or substituted aralkyl radicals having from 6 to 11 carbon atoms.

47. The silicon-containing precursor of claim 40, wherein R_4 is selected from the group consisting of hydrogen; halogen; alkenyl or substituted alkenyl radicals having from 2 to 10 carbon atoms; α -halogenated alkyl or perhalogenated alkyl radicals and substituted derivatives having from 1 to 10 carbon atoms, and alkynyl or substituted alkynyl having from 2 to 10 carbon atoms.
48. The silicon-containing precursor of claim 40, wherein R_4 is selected from the group consisting of -CN; -OCN; and phosphine, alkylphosphines, and dialkylphosphines, wherein the alkyl radical has from 1 to 10 carbon atoms.
49. The silicon-containing precursor of claim 40, wherein the silicon-containing precursor is selected from the group consisting of tetramethylcyclotetrasiloxane, tetramethyldisiloxane and triethoxysilane.
50. A coating composition comprising a first silicon-containing precursor according to any one of claims 40 to 49 and a second silicon-containing precursor.
51. A silicon-containing precursor according to any one of claims 29 to 37 and claims 40 to 49, wherein the coating composition is a vapor coating composition.
52. A coating composition according to claims 38, 39 or 50, wherein the coating composition is a vapor coating composition.
53. A coating apparatus, comprising:
means for directing a vapor toward a glass surface;
a first exhaust means spaced from said vapor directing means on one side thereof;
a second exhaust means spaced from said vapor directing means on the other side thereof and in alignment with said vapor directing means and said first exhaust means, and
means for positioning said first and second exhaust means and said directing means relative to one another such that the distance between said first exhaust means and said vapor directing means is defined as "x" and the distance between the second exhaust means and said vapor directing means is defined as "y" wherein the values of "x" and "y"

are different.

54. The coating apparatus of claim 53, wherein the ratio of x/y is in the range of about 1.2 to about 50.

55. A coating apparatus comprising:
means comprising a nozzle for directing a vapor toward a substrate wherein the nozzle has an opening;
a first exhaust means having an opening spaced from said vapor directing means on one side thereof;
a second exhaust means having an opening spaced from said vapor directing means on the other side thereof and in alignment with said vapor directing means, and
means for positioning said first and second exhaust means, and said vapor directing means relative to the substrate surface such that the surface of said opening of said vapor directing means and said opening of said first exhaust means is at a spaced distance different than the spaced distance between the opening of said second exhaust means and the substrate.

56. A coating apparatus comprising:
means for directing a vapor toward a substrate;
a first exhaust means spaced from said vapor directing means on one side thereof;
a second exhaust means spaced from said vapor directing means on the other side thereof and in alignment with said vapor directing means and said first exhaust means; and
means for controlling flow volume capacity of said vapor directing means and said first and second exhaust means such that the flow volume capacity of said vapor directing means is different than that of at least one of said exhaust means.

57. The silicon-containing precursor of claim 31 or 41 wherein R_1 is selected from the group consisting of alkyl or substituted alkyl radicals having from 1 to 4 carbon atoms, halogenated or perhalogenated alkyl radicals having from 1 to 4 carbon atoms, alkenyl or substituted alkenyl radicals having from 2 to 4 carbon atoms, alkynyl or substituted alkynyl radicals having from 2 to 4 carbon atoms, and aryl or aralkyl or substituted aryl or aralkyl radicals having from 6 to 9 carbon atoms.

58. The silicon-containing precursor of claim 57 wherein R_1 is selected from the group consisting of $-\text{CH}_3$, $-\text{CH}_2\text{CH}_2\text{CH}_3$, $-\text{CH}_2\text{CH}_2\text{OH}$, $-\text{CCl}_3$, $-\text{CH}_2\text{CHClCH}_3$, $-\text{CH}_2\text{CCl}_2\text{CCl}_3$, $-\text{CH}=\text{CHCH}_3$, $-\text{CH}=\text{CH}_2$, $-\text{C}\equiv\text{C}-\text{CH}_3$, $-\text{CH}\equiv\text{CH}$, $-\text{C}_6\text{H}_5$ and $-\text{C}_6\text{H}_4\text{CH}_3$.

59. The silicon-containing precursor of claim 29 or 40 wherein R_2 is selected from the group consisting of hydrogen, halogen, alkenyl or substituted alkenyl radicals having from 2 to 4 carbon atoms, α -halogenated alkyl or perhalogenated alkyl radicals having from 1 to 4 carbon atoms, alkynyl or substituted alkynyl radicals having from 2 to 4 carbon atoms.

60. The silicon-containing precursor of claim 59 wherein R_2 is selected from the group consisting of Cl , $-\text{CH}=\text{CHCH}_3$, $-\text{CH}=\text{CH}_2$, CCl_3 , $-\text{CH}_2\text{CHClCH}_3$, $-\text{CH}_2\text{CCl}_2\text{CCl}_3$, $-\text{C}\equiv\text{C}-\text{CH}_3$ and $-\text{CH}\equiv\text{CH}$.

61. The silicon-containing precursor of claims 32 and 45, wherein R_3 is selected from the group consisting of:

$-\text{S}-$;

$-\text{N}-\text{R}_5$ wherein R_5 is an alkyl or substituted alkyl radical having from 1 to 4 carbon atoms;


$-\text{N}-$;

$-\text{P}-\text{H}$;

-P-R₅ wherein R₅ is as defined above;

|

-P-; and



62. The silicon-containing precursor of claims 32 and 45, wherein R₃ is selected from the group consisting of:

-S-;

-N-CH₂CH₃ or -N-CH₂CH₂CH₃;

-N-;

|

-P-H;

-P-CH₂CH₃ or -P-CH₂CH₂CH₃; and

|

-P-.

63. The silicon-containing precursor of claim 35 wherein R₄ is selected from the group consisting of alkoxide or substituted alkoxide radicals having from 1 to 4 carbon atoms, alkyl or substituted alkyl radicals having from 1 to 5 carbon atoms -CN; -OCN; and phosphines, alkylphosphines and dialkylphosphines, wherein the alkyl radical has from 1 to 4 carbon atoms.




64. The silicon-containing precursor of claim 63 wherein R₄ is selected from the group consisting of -OCH₂CH₃, -CH₂CH₃, -CN, -OCN, PH₂, -PHCH₃ and -P(CH₂CH₃)₂.

65. The silicon-containing precursor of claim 29 or 40 wherein R_1 and R_4 are selected from the group consisting of alkyl or substituted alkyl radicals having from 1 to 4 carbon atoms, halogenated or perhalogenated alkyl radicals having from 1 to 4 carbon atoms, alkenyl or substituted alkenyl radicals having from 2 to 4 carbon atoms, alkynyl or substituted alkynyl radicals having from 2 to 4 carbon atoms, and aryl or aralkyl or substituted aryl or aralkyl radicals having from 6 to 9 carbon atoms.

66. The silicon-containing precursor of claim 65 wherein R_1 and R_4 are selected from the group consisting of $-CH_3$, $-CH_2CH_2CH_3$, $-CH_2CH_2OH$, $-CCl_3$, $-CH_2CHClCH_3$, $-CH_2CCl_2CCl_3$, $-CH=CHCH_3$, $-CH=CH_2$, $-C\equiv C-CH_3$, $-CH\equiv CH$, $-C_6H_5$ and $-C_6H_4CH_3$.

67. The silicon-containing precursor of claim 29 or 40 wherein R_2 and R_4 are selected from the group consisting of hydrogen, halogen, alkenyl or substituted alkenyl radicals having from 2 to 4 carbon atoms, α -halogenated alkyl or perhalogenated alkyl radicals having from 1 to 4 carbon atoms, alkynyl or substituted alkynyl radicals having from 2 to 4 carbon atoms.

68. The silicon-containing precursor of claim 67 wherein R_2 and R_4 are selected from the group consisting of Cl , $-CH=CHCH_3$, $-CH=CH_2$, CCl_3 , $-CH_2CHClCH_3$, $-CH_2CCl_2CCl_3$, $-C\equiv C-CH_3$ and $-CH\equiv CH$.



Scott & Sykes




FIG. 4

Scott & Aylen




FIG. 5

Scott & Sykes




FIG. 6

Scott & Sykes