



Office de la Propriété
Intellectuelle
du Canada

Un organisme
d'Industrie Canada

Canadian
Intellectual Property
Office

An agency of
Industry Canada

CA 2597918 C 2015/06/30

(11)(21) 2 597 918

(12) BREVET CANADIEN
CANADIAN PATENT

(13) C

(86) Date de dépôt PCT/PCT Filing Date: 2006/02/15
(87) Date publication PCT/PCT Publication Date: 2006/08/24
(45) Date de délivrance/Issue Date: 2015/06/30
(85) Entrée phase nationale/National Entry: 2007/08/15
(86) N° demande PCT/PCT Application No.: US 2006/005216
(87) N° publication PCT/PCT Publication No.: 2006/088889
(30) Priorité/Priority: 2005/02/15 (US60/652,888)



(51) CI.Int./Int.Cl. C08L 67/02 (2006.01),
B65D 81/26 (2006.01), C08K 3/08 (2006.01),
C08K 5/20 (2006.01)

(72) Inventeurs/Inventors:
DESHPANDE, GIRISH NILKANTH, US;
GOVINDARAJAN, VENKAT, US;
ROST, JOHN, US;
SILVERMAN, ALAN, US


(73) Propriétaire/Owner:
PLASTIPAK PACKAGING, INC., US

(74) Agent: GOWLING LAFLEUR HENDERSON LLP

(54) Titre : COMPOSITIONS DESOXYGENANTES ET EMBALLAGES COMPORTANT LESDITES COMPOSITIONS
(54) Title: OXYGEN SCAVENGING COMPOSITIONS AND PACKAGING COMPRISING SAID COMPOSITIONS



3 % Monomer



3% Nylon

(57) Abrégé/Abstract:

The instant invention concerns a composition comprising a base polymer, at least one compound of the formula E-(L-E)_x wherein: E is formula (I) or formula (II) and L is a linking group; and at least one transition metal in a positive oxidation state. The invention also concerns packages containing walls comprising such compositions, methods of forming such packages, and methods of

(57) Abrégé(suite)/Abstract(continued):

packaging an oxygen-sensitive item within such a package.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau

PCT

(43) International Publication Date
24 August 2006 (24.08.2006)(10) International Publication Number
WO 2006/088889 A2

(51) International Patent Classification:

C01B 3/00 (2006.01)

(21) International Application Number:

PCT/US2006/005216

(22) International Filing Date:

15 February 2006 (15.02.2006)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

60/652,888 15 February 2005 (15.02.2005) US

(71) Applicant (for all designated States except US): CON-STAR INTERNATIONAL, INC. [US/US]; One Crown Way, Philadelphia, Pennsylvania 19154 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): DESHPANDE, Girish, Nilkanth [IN/US]; 72 Ascot Lane, #2622, Willowbrook, Illinois 60527 (US). GOVINDARAJAN, Venkat [US/US]; 1562 Tara Belle Parkway, Naperville, Illinois 60564 (US). ROST, John [US/US]; 17221 Pointe Drive, Orland Park, Illinois 60467 (US). SILVERMAN, Alan [US/US]; 54 Van Arsdale Drive, Washington Crossing, Pennsylvania 18977 (US).

(74) Agents: HEIST, Dale, M. et al.; WOODCOCK WASH-BURN LLP, One Liberty Place - 46th Floor, Philadelphia, Pennsylvania 19103 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, LY, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.




(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:


— without international search report and to be republished upon receipt of that report

[Continued on next page]

(54) Title: OXYGEN SCAVENGING COMPOSITIONS AND PACKAGING COMPRISING SAID COMPOSITIONS



3 % Monomer



3% Nylon

WO 2006/088889 A2

(57) Abstract: The instant invention concerns a composition comprising a base polymer, at least one compound of the formula E-(L-E)_x wherein: E is formula (I) or formula (II) and L is a linking group; and at least one transition metal in a positive oxidation state. The invention also concerns packages containing walls comprising such compositions, methods of forming such packages, and methods of packaging an oxygen-sensitive item within such a package.

WO 2006/088889 A2



For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

OXYGEN SCAVENGING COMPOSITIONS AND PACKAGING COMPRISING SAID COMPOSITIONS

FIELD OF THE INVENTION

[0002] The present invention relates to substantially transparent compositions that comprise a base polymer, an oxidizable organic component, and a transition metal. The invention also concerns use of such compositions in the construction of packaging for oxygen sensitive materials.

BACKGROUND OF THE INVENTION

[0003] It is known in the art to include an oxygen scavenger in the packaging structure for the protection of oxygen sensitive materials. Such scavengers are believed to react with oxygen that is trapped in the package or that permeates from outside of the package, thus extending to life of package contents. These packages include films, bottles, containers, and the like. Food, beverages (such as beer and fruit juices), cosmetics, medicines, and the like are particularly sensitive to oxygen exposure and require high barrier properties to oxygen to preserve the freshness of the package contents and avoid changes in flavor, texture and color.

[0004] Use of certain polyamides in combination with a transition metal is known to be useful as the oxygen scavenging material. One particularly useful polyamide is MXD6 which

contains meta-xylene residues in the polymer chain. See, for example, U.S. Patent Nos. 5,639,815; 5,049,624; and 5,021,515.

[0005] Other oxygen scavengers include potassium sulfite (U.S. Patent No. 4,536,409), unsaturated hydrocarbons (U.S. Patent No. 5,211,875), and ascorbic acid derivatives (U.S. Patent No. 5,075,362).


[0006] In barrier layers of packaging walls that are made from blends of oxygen scavenging materials with base polymer resins such as PET, haze can result due to such factors as: the immiscibility of the scavenging materials with the base polymer resins, and the inability to create by mechanical blending means disperse-phase domains that are so small as not to interfere with the passage of light therethrough; and the adverse influence of the scavenging material on the crystallization behavior of PET base resin. One approach to minimizing such haze is careful selection of base resin to improve dispersibility of the scavenger material and, thus, reduce, but not substantially eliminate, haze; and to minimize the adverse crystallization effect. This approach may undesirably narrowly restrict the choice of base polymer resin. Another approach is to use compositions that serve as compatibilizers to reduce haze. These approaches add cost to the layer and the compatibilizer adds an additional material that must be evaluated for its suitability for contact with food. There is a need in the art for barrier materials which provide high oxygen scavenging capability and are substantially transparent without use of the aforementioned measures.


SUMMARY OF THE INVENTION

[0007] The invention relates to a composition which comprises:

- (a) at least one base polymer;
- (b) at least one non-polymeric oxidizable organic component present in an amount of about 0.10 to 10 weight percent of the composition and the component comprising at least one compound of the formula E-(L-E)_x wherein:

E is





L is a linking group of the formula $-(O-R_{21})_z-O-$, $-(NH-R_{21})_z-NH-$, $-(NH-C(=O)R_{22})_t-NH-$, $-NH-R_{25}-NH(C(=O)R_{26}NHR_{25}NH)_u-$, $-(O-R_{23}-O-R_{24}-C(=O)_s-O-$ where L is attached to a carbon atom of Ar (for example, replaces a H atom of the Ar) in structure (I) or where R₁₂ or R₁₃ of structure (II) is L;

x is 0, 1, or 2;

Ar is aryl or heteroaryl;

R₁, R₂, and R₁₁ are each independently, H, C₁-C₁₂ alkyl, C₁-C₆ alkoxy, C₆-C₂₀ aryloxy, hydroxy, C₂-C₆ alkenyl, NR₁₉R₂₀, acetyl, nitro, glyceryl, carbohydrate, -C(=O)H, L, or two R₁ or two R₂ groups can form a group of the formula $-O-R_{18}-O-$;

R₃, R₄, R₁₄, and R₁₅ are each H;

R₅ to R₁₀, R₁₆, and R₁₇ are each, independently, H or C₁-C₃ alkyl;

R₁₂ and R₁₃ are each, independently, H, C₁-C₆ alkyl, C₆-C₂₀ aryl, C₁-C₆ alkoxy, or L;

R₁₈ is C₂-C₆ alkyl;

R₁₉ and R₂₀ are each, independently, H, C₁-C₆ alkyl, or C₆-C₂₀ aryl;

R₂₁ and R₂₄ are each, independently, C₁-C₆ alkyl;

R₂₂, R₂₃, R₂₅ and R₂₆ are each, independently, C₁-C₆ alkyl or C₆-C₂₀ aryl;

n and p are independently 0 or an integer from 1 to 5;

q is 0 or an integer from 1 to 4;


s and z are, independently 1, 2, or 3;

t and u are, independently 1 or 2; and

(c) at least one transition metal in a positive oxidation state, the metal being present in the composition in an amount of 10 to 400 ppm.

[0008] Some compounds have R₁, R₂, and R₁₁ as C₁-C₆ alkyl.


[0009] In some embodiments, the composition is of the formula:




[0010] In some compounds, n and p are each 0, 1, or 2. In certain compounds, R₁ and R₂ are each independently H, C₁-C₄ alkyl, hydroxy, C₁-C₃ alkoxy, or carbohydrate. Some compositions have R₁ and R₂ are each independently H, methyl, ethyl, hydroxy, methoxy, ethoxy, or glucose.

[0011] In some embodiments, R₅ to R₁₀ are H. In certain embodiments, R₁ and R₂ are each H.

[0012] Some compositions are of the formula:




[0013] The invention also relates to compositions having the formula:



[0014] In some embodiments, R₁₆ and R₁₇ are H. In certain embodiments, each R₁₁ is independently H, C₁-C₄ alkyl, hydroxy, or C₁-C₃ alkoxy, or carbohydrate. In some compositions, each R₁₁ is independently H, methyl, ethyl, hydroxy, methoxy, or ethoxy.

[0015] Some compounds have the formula:



[0016] Some preferred embodiments have a concentration of transition metal of 30 to 150 ppm. In some embodiments, cobalt is the transition metal. In certain embodiments, the at least one transition metal comprises cobalt and zinc.

[0017] In some preferred embodiments, the base polymer comprises a polyester polymer. In certain of these embodiments, the polyester polymer is polyethylene terephthalate.

[0018] Some embodiments have the oxidizable organic component present in an amount of about 1 to about 10 weight percent based on the weight of the composition. In other embodiments, the oxidizable organic component is present in an amount of about 1 to about 5 weight percent based on the weight of the composition. In still other embodiments, the oxidizable organic component is present in an amount of about 1 to about 3 weight percent based on the weight of the composition.

[0019] The composition can additionally comprise one or more of colorant, filler, crystallization aid, impact modifier, surface lubricant, denesting agent, stabilizer, ultraviolet light absorbing agent, or dyestuff for example.

[0020] In some embodiments, the invention concerns a wall for a package, where the wall comprising a composition comprising:

- at least one base polymer;
- at least one non-polymeric oxidizable organic component that is present in an amount of about 0.10 to 10 weight present of the composition and the component comprising at least one compound described herein; and
- at least one transition metal in a positive oxidation state that is present in the composition in an amount of 10 to 400 ppm. In some compositions, the wall is a single layer. In some embodiments, the wall is multilayer. In the latter embodiment, a first layer can be disposed radially outward from a second layer that contains the oxidizable organic component.

[0021] In another embodiment, the invention relates to a method for packaging an oxygen sensitive material comprising:

- (a) preparing a packing having a wall which comprises a composition comprising:
 - a base polymer;
 - a non-polymeric oxidizable organic component that is present in an amount of about 0.10 to 10 weight present of the composition and the component comprising at least one compound described herein; and
 - at least one transition metal in a positive oxidation state that is present in the composition in an amount of 10 to 400 ppm;

- (b) introducing the oxygen sensitive material into the package; and
 - (c) closing the package.

[0022] In yet other embodiments, the invention concerns a method for producing a container having a wall with oxygen barrier properties comprising:

- (a) providing a polymer mixture comprising at least one base polymer containing at least one non-polymeric oxidizable organic component that is present in an amount of about 0.10 to

10 weight present of the composition and the component comprising at least one compound described herein; the mixture having at least one transition metal in a positive oxidation state, the metal being present in the composition in an amount of 10 to 400 ppm;

- (b) forming the product of step (a) into a wall; and
- (c) forming a container which comprises the wall.

[0023] In further embodiments, the invention concerns a process for making an article comprising:

- (a) forming a melt by combining the following ingredients in a melt processing zone:

- a base polymer,
 - a non-polymeric oxidizable organic component that is present in an amount of about 0.10 to 10 weight present of the composition and the component comprising at least one compound described herein;

- at least one transition metal in a positive oxidation state that is present in the composition in an amount of 10 to 400 ppm; and

- (b) forming an article from the melt.

[0024] In certain embodiments, the article is a preform, a sheet, a film, a cup, a jar, or a bottle.

[0025] In preferred embodiments of the invention, the compositions described herein are used in monolayer bottles. These compositions are advantageous in substantially eliminating haze in such compositions compared to other commercial oxygen scavengers used in monolayer applications. In other embodiments the compositions are used in one or more layers of a multi-layer wall of a package, giving protection of the contents against oxygen without adding haziness to the wall.

BRIEF DESCRIPTION OF THE DRAWINGS

[0026] Figure 1 shows dispersion of 3% monomer-1 in the PET matrix measured using standard SEM technique used for evaluating the dispersion of MXD6 nylon in PET versus a dispersion comprising MXD6 (a nylon that is made by Mitsubishi Gas Chem) at 3% nominal loading.

[0027] Figures 2 and 3 show the % oxygen depletion in the vials over time of samples having monomers I and II.

[0028] Figure 4 shows oxygen permeation of bottles containing monomer-I that were mounted 2 days after manufacture and 69 days after manufacture.

[0029] Figure 5 shows oxygen permeation of bottles containing monomer-II that were mounted 3 days after manufacture and 47 days after manufacture.

[0030] Figure 6 shows evidence of scavenging for compositions containing monomer-I.

[0031] Figure 7 shows the decrease in oxygen concentration over time for a 3% Monomer-I blend compared to a typical Monoxbar™ MXD6-Co⁺-PET blend composition used by Constar in packaging applications.

[0032] Figure 8 shows oxygen permeation rates for 16 and 20 oz hot-fill containers that were mounted on an oxygen permeation measuring device 10 days later after being stored empty at standard temperature and pressure (STP) conditions.

[0033] Figure 9 shows oxygen permeation rates for 20 oz bottles were blown from preforms and stored empty for 25 days at STP conditions prior to testing.

[0034] Figure 10 presents a thermogravimetric analysis (TGA) that shows the effect of residence time on the Monomer-I decomposition in the extruder.

[0035] Figure 11 shows a TGA analysis where a known weight sample of Monomer-I was placed in a sample pan and the sample quickly heated (40 °C/min heating rate was used) to 280 °C. The sample temperature was maintained at 280 °C for a period of 300 seconds (to simulate typical residence time in the extruder) and the resulting TGA scan was recorded.

[0036] Figures 12 and 13 show the percentage oxygen remaining in the vial after one day as a function of % diamide content and cobalt content.

[0037] Figures 14 and 15 illustrate the effect of diamine content and extruder temperatures on the oxygen remaining in the vial after 7 days.

[0038] Figures 16 and 17 show the interaction of diamide content, extruder temperatures, and injection cycle time.

[0039] Figure 18 shows oxygen scavenging performance over time.

[0040] Figure 19 shows the effect of PET type in oxygen scavenging performance.


DETAILED DESCRIPTION OF ILLUSTRATIVE EMBODIMENTS

[0041] The present invention concerns compositions that are useful in the manufacture of packaging for oxygen sensitive materials. In some embodiments, the invention concerns a polyester polymer composition, preforms, and blow molded containers with good oxygen scavenging properties as well as substantially reduced haze compared to current commercial PET compositions containing an oxygen scavenger comprised of MXD6 nylon or of Amosorb, an O₂ scavenger containing polybutadiene oligomers.

[0042] It is preferred that the non-polymeric oxidizable organic component of the instant invention have a high degree of affinity for polyesters.

[0043] In certain preferred embodiments, the invention concerns compositions that contain a base polymer, a transition metal in a positive oxygen state, and at least one non-polymeric oxidizable organic component present in an amount of about 0.10 to 10 weight present of the composition and the component comprising at least one compound of the formula E-(L-E)_x wherein:

E is



L is a linking group of the formula -(O-R₂₁)_z-O-, -(NH-R₂₁)_z-NH-, -(NH-C(=O)R₂₂)_x-NH, -NH-R₂₅-NH(C(=O)R₂₆NHR₂₅NH)_u-, -(O-R₂₃-O-R₂₄-C(=O)_s-O- where L is attached to a carbon atom of Ar in structure (I) or where R₁₂ or R₁₃ of structure (II) is L;

x is 0, 1, or 2;

Ar is aryl or heteroaryl;

R₁, R₂, and R₁₁ are each independently, H, C₁-C₁₂ alkyl, C₁-C₆ alkoxy, C₆-C₂₀ aryloxy, hydroxy, C₂-C₆ alkenyl, NR₁₉R₂₀, acetyl, nitro, glyceryl, carbohydrate, -C(=O)H, L, or two R₁ or two R₂ groups can form a group of the formula -O-R₁₈-O-;

R₃, R₄, R₁₄, and R₁₅ are each H;

R₅ to R₁₀ and R₁₆, and R₁₇ are each, independently, H or C₁-C₃ alkyl;

R₁₂ and R₁₃ are each, independently, H, C₁-C₆ alkyl, C₆-C₂₀ aryl, C₁-C₆ alkoxy, or L;

R₁₈ is C₂-C₆ alkyl;

R₁₉ and R₂₀ are each, independently, H, C₁-C₆ alkyl, or C₆-C₂₀ aryl;

R₂₁ and R₂₄ are each, independently, C₁-C₆ alkyl;

R₂₂, R₂₃, R₂₅ and R₂₆ are each, independently, C₁-C₆ alkyl or C₆-C₂₀ aryl;

n and p are independently 0 or an integer from 1 to 5;

q is 0 or an integer from 1 to 4;

s and z are, independently 1, 2, or 3; and

t and u are, independently 1 or 2.

[0044] The term “alkyl” refers to a substituted or unsubstituted aliphatic hydrocarbon chain. Alkyl groups have straight and branched chains. In some embodiments, alkyls have from 1 to 12 carbon atoms or 1 to 6 carbon atoms, unless explicitly specified otherwise. Alkyl groups include, but are not limited to methyl, ethyl, propyl, isopropyl, butyl, I-butyl and t-butyl. Specifically included within the definition of “alkyl” are those aliphatic hydrocarbon chains that are optionally substituted.

[0045] The term “alkoxy,” as used herein, refers to the group R-O- where R is an alkyl group as defined herein.

[0046] The term “aryl” is defined herein as an aromatic carbocyclic moiety of up to 20 carbon atoms. In some embodiments, aryl groups have 6-20 carbon atoms or 6-14 carbon atoms. Aryls may be a single ring (monocyclic) or multiple rings (bicyclic, up to three rings) fused together or linked covalently. Any suitable ring position of the aryl moiety may be covalently linked to the defined chemical structure. Aryl groups include, but are not limited to, phenyl, 1-naphthyl, 2-naphthyl, dihydronaphthyl, tetrahydronaphthyl, biphenyl, anthryl, phenanthryl, fluorenyl, indanyl, biphenylenyl, acenaphthenyl, and acenaphthylenyl. In some embodiments, phenyl is a preferred aryl. Aryl groups may also be optionally substituted with one or more substituents.

[0047] The term “aryloxy” refers to the group -O-Ar where Ar is an aryl group as defined herein.

[0048] The term “heteroaryl” refers to an aromatic heterocyclic ring system, which may be a single ring (monocyclic) or multiple rings (bicyclic, up to three rings) fused together or linked covalently and having for example 5 to 20 ring members. The rings may contain from one to four hetero atoms selected from nitrogen (N), oxygen (O), or sulfur (S), wherein the nitrogen or sulfur atom(s) are optionally oxidized, or the nitrogen atom(s) are optionally substituted (e.g., by alkyl such as methyl) or quarternized. Any suitable ring position of the heteroaryl moiety may be covalently linked to the defined chemical structure. Exemplary heteroaryl groups include, but are not limited to, pyrrolyl, furyl, pyridyl, pyridine-N-oxide, 1,2,4-thiadiazolyl, pyrimidyl, thienyl, isothiazolyl, imidazolyl, tetrazolyl, pyrazinyl, pyrimidyl, quinolyl, isoquinolyl, thiophenyl, benzothienyl, isobenzofuryl, pyrazolyl, indolyl, purinyl, carbazolyl, benzimidazolyl, and isoxazolyl.

[0049] Optional substituents for alkyl, alkenyl, aryl, or heteroaryl groups are well known to those skilled in the art. These substituents include alkyl, alkoxy,

-SR₁₉, aryloxy, hydroxy, NR₁₉R₂₀, acetyl, cyano, nitro, glyceryl, and carbohydrate, or two substituents taken together may be linked as an -alkylene- group to form a ring. R₁₉ and R₂₀ are as defined herein.

[0050] It is believed that some composition, under certain circumstances, can produce an amount of benzylaldehyde derivative upon decomposition. As such, it is desirable that any substituents on aryl groups be ones that do not produce a pronounced flavor or odor. Such compositions are easily determined by one skilled in the art and can be taken into considerations when selecting substituents for aryl groups.

[0051] A surprising result of the oxygen scavenging reaction of some of these oxygen scavenger materials comprising benzyl amides is that the decomposition products resulting from the catalytic oxidation by transition metal in the positive oxidation state, according to this invention, (some decomposition products may also result from melt processing of the materials) are benzyl aldehydes, which may be toxicologically innocuous. Benzaldehyde, from the oxidative decomposition of Monomer I, is a natural flavorant, and is generally recognized as safe for use in foods or for packaging in contact with foods. This innocuousness is highly desirable in food packaging. Other benzyl amines may be chosen such that the decomposition products are aldehydes that are believed to be innocuous. These include 3-methoxy-4-hydroxybenzaldehyde (also known as vanillaldehyde or vanillin), 3-ethoxy-2-hydroxybenzaldehyde, 4-hydroxy-3-methylbenzaldehyde, 4-hydroxy-3,5-dimethoxybenzaldehyde, 4-hydroxybenzaldehyde-3-sulfonic acid sodium salt, (1,1'-biphenyl)-4-carboxaldehyde, 2-methoxybenzaldehyde 4-nitropheynylhydrazone, 3,4,5-triacetoxybenzaldehyde, 2-hydroxy-5-methoxybenzaldehyde, 3-benzoxy-4-methoxybenzaldehyde, 2-formylbenzenesulfonic acid sodium salt, 4-dodecyloxybenzaldehyde, benzaldehyde-p-sulfonic acid sodium salt, 3-benzoxybenzaldehyde, 3-phenoxybenzaldehyde, 5-nitrovanillin, ethyl vanillin beta-D-glucopyranoside, 1,4-benzodioxan-6-carboxaldehyde, 3,4-didecyloxybenzaldehyde, 4-benzyloxy-3-methoxybenzaldehyde, N-ethyl-N-hydroxyethyl-2-methyl-4-aminobenzaldehyde, 2,4-dinitrobenzaldehyde, 4-methoxybenzaldehyde-3-sulfonic acid sodium salt, 4-benzyloxybenzaldehyde, 4-(4-nitrobenzyloxy)benzaldehyde, 4-octylbenzaldehyde, 2-hexyloxybenzaldehyde, 3,4-didodecyloxybenzaldehyde, 3,4-dioctyloxybenzaldehyde, 3,5-di-tert-butyl-4-hydroxybenzaldehyde, and 3-(4-tert-butylphenoxy)benzaldehyde. While the effectiveness in packaging applications as oxygen scavengers may be somewhat different from one substituted benzyl amine to another, the advantages in the aldehyde decomposition product having reduced sensory detection limits may be a good tradeoff, and this can be determined by reasonable experimentation and testing with the products to be packaged.

[0052] In general, it is believed that larger benzaldehydes and their salts have less intense flavors. It is also believed that benzaldehydes having at least one sugar substituent will have less flavor than unsubstituted analogs. Examples of suitable sugars include glucose, sucrose, and lactose.

[0053] “Carbohydrate” as used herein refers to monosaccharides, disaccharides, and trisaccharides. Suitable carbohydrates include glucose, sucrose, and lactose. A carbohydrate substituent may be bound at any suitable position.

[0054] The term “alkenyl” is defined herein as (C₂-C₂₀) straight chain or branched-chain bivalent hydrocarbon moiety derived from an alkane or alkene that is mono or polyunsaturated. Such groups include those in the E or Z configurations and all possible combinations of E and Z configurations. Some preferred alkylene chains have 2-7 carbon atoms.

[0055] The carbon number as used in the definitions recited herein refers to carbon backbone and carbon branching and does not include any carbon atoms that are contained in the optional substituents.

[0056] Compositions of the instant invention comprise a base polymer. In some embodiments, the base polymer is a polyester. In certain embodiments, the polyester polymers of the invention are thermoplastic and, thus, the form of the compositions are not limited and can include a composition in the melt phase polymerization, as an amorphous pellet, as a solid stated polymer, as a semi-crystalline particle, as a composition of matter in a melt processing zone, as a bottle preform, or in the form of a stretch blow molded bottle or other articles. In certain preferred embodiments, the polyester is polyethylene terephthalate (PET).

[0057] Examples of suitable polyester polymers include polyethylene terephthalate homopolymers and copolymers modified with one or more polycarboxylic acid modifiers in a cumulative amount of less than about 15 mole %, or about 10 mole % or less, or about 8 mole % or less, or one or more hydroxyl compound modifiers in an amount of less than about 60 mol %, or less than about 50 mole %, or less than about 40 mole %, or less than about 15 mole %, or about 10 mole % or less, or about 8 mole % or less (collectively referred to for brevity as “PET”) and polyethylene naphthalate homopolymers and copolymers modified with a cumulative amount of with less than about 15 mole %, or about 10 mole % or less, or about 8 mole % or less, of one or more polycarboxylic acid modifiers or modified less than about 60 mol %, or less than about 50 mole %, or less than about 40 mole %, or less than about 15 mole %, or about 10 mole % or less, or about 8 mole % or less of one or more hydroxyl compound modifiers (collectively referred to herein as “PEN”), and blends of PET and PEN. A modifier polycarboxylic acid compound or hydroxyl compound is a compound other than the compound

contained in an amount of at least about 85 mole %. The preferred polyester polymer is polyalkylene terephthalate, and most preferred is PET.

[0058] The polyester compositions can be prepared by polymerization procedures known in the art sufficient to effect esterification and polycondensation. Polyester melt phase manufacturing processes include direct condensation of a dicarboxylic acid with the diol, optionally in the presence of esterification catalysts, in the esterification zone, followed by polycondensation in the prepolymer and finishing zones in the presence of a polycondensation catalyst; or ester exchange usually in the presence of a transesterification catalyst in the ester exchange zone, followed by prepolymerization and finishing in the presence of a polycondensation catalyst, and each may optionally be solid stated according to known methods.

[0059] Other base polymers may be used with the instant invention. One example is polypropylene.

[0060] The transition metal used in the instant compositions is a metal in the positive oxidation state. It should be noted that it is contemplated that one or more such metals may be used. In some embodiments, cobalt is added in +2 or +3 oxidation state. In some embodiments, it is preferred to use cobalt in the +2 oxidation state. In certain embodiments, copper in the +2 oxidation state is utilized. In some embodiments, rhodium in the +2 oxidation state is used. In certain embodiments, zinc may also be added to the composition. Preferred zinc compounds include those in a positive oxidation state.


[0061] Suitable counter-ions to the transition metal cations include carboxylates, such as neodecanoates, octanoates, acetates, lactates, naphthalates, malates, stearates, acetylacetones, linoleates, oleates, palmitates, 2-ethylhexanoates, or ethylene glycolates; or as their oxides, borates, carbonates, chlorides, dioxides, hydroxides, nitrates, phosphates, sulfates, or silicates among others.

[0062] In some embodiments, levels of at least about 10 ppm, or at least about 50 ppm, or at least about 100 ppm of metal can achieve suitable oxygen scavenging levels. The exact amount of transition metal used in an application can be determined by trials that are well within the skill level of one skilled in the art. In some embodiments involving wall applications (as opposed to master batch applications where more catalyst is used), it is preferred to keep the level of metal below about 300 ppm and, in other embodiments, preferably below about 250 ppm. In master batch compositions, the level of transition metal may range from about 1000 to about 10,000 ppm. In some preferred embodiments, the range is from about 2000 to about 5000 ppm.

[0063] The transition metal or metals may be added neat or in a carrier (such as a liquid or wax) to an extruder or other device for making the article, or the metal may be present in a concentrate or carrier with the oxidizable organic component, in a concentrate or carrier with a base polymer, or in a concentrate or carrier with a base polymer/oxidizable organic component blend. Alternatively, at least a portion of the transition metal may be added as a polymerization catalyst to the melt phase reaction for making the base polymer (a polyester polymer in some embodiments) and be present as residual metals when the polymer is fed to the melting zone (e.g. the extrusion or injection molding zone) for making the article such as a preform or sheet. It is desirable that the addition of the transition metal does not substantially increase the intrinsic viscosity (It.V) of the melt in the melt processing zone. Thus, transition metal or metals may be added in two or more stages, such as once during the melt phase for the production of the polyester polymer and again once more to the melting zone for making the article.

[0064] The compositions of the instant invention comprise at least one non-polymeric oxidizable organic component present in an amount of about 0.10 to 10 weight present of the composition and the component comprising at least one compound of the formula $E-(L-E)_x$ wherein:

E is



L is a linking group of the formula $-(O-R_{21})_z-O-$, $-(NH-R_{21})_z-NH-$, $-(NH-C(=O)R_{22})_t-NH$, $-NH-R_{25}-NH(C(=O)R_{26}NHR_{25}NH)_u-$, $-(O-R_{23}-O-R_{24}-C(=O)_s-O-$ where L is attached to a carbon atom of Ar in structure (I) or where R_{12} or R_{13} of structure (II) is L ;

x is 0, 1, or 2;


Ar is aryl or heteroaryl;

R_1 , R_2 , and R_{11} are each independently, H, C_1-C_{12} alkyl, C_1-C_6 alkoxy, C_6-C_{20} aryloxy, hydroxy, C_2-C_6 alkenyl, $NR_{19}R_{20}$, acetyl, nitro, glyceryl, carbohydrate, $-C(=O)H$, L , or two R_1 or two R_2 groups can form a group of the formula $-O-R_{18}-O$;

R_3 , R_4 , R_{14} , and R_{15} are each H;


R_5 to R_{10} and R_{16} , and R_{17} are each, independently, H or C_1 - C_3 alkyl;
 R_{12} and R_{13} are each, independently, H, C_1 - C_6 alkyl, C_6 - C_{20} aryl, C_1 - C_6 alkoxy, or L;
 R_{18} is C_2 - C_6 alkyl;
 R_{19} and R_{20} are each, independently, H, C_1 - C_6 alkyl, or C_6 - C_{20} aryl;
 R_{21} and R_{24} are each, independently, C_1 - C_6 alkyl;
 R_{22} , R_{23} , R_{25} and R_{26} are each, independently, C_1 - C_6 alkyl or C_6 - C_{20} aryl;
n and p are independently 0 or an integer from 1 to 5;
q is 0 or an integer from 1 to 4;
s and z are, independently 1, 2, or 3; and
t and u are, independently 1 or 2.

[0065] In some embodiments, the compositions comprise at least one monomer of the formula:



(monomer -I)

or



(monomer -II).

[0066] At least one of these monomers described herein normally will be used in an amount of about 0.1 to about 10 weight percent in an article based on the weight of the composition. In some preferred embodiments, the monomer(s) will be present in an amount of about 1 to about 5 weight percent based on the weight of the composition. In other embodiments, the monomer(s) will be present in an amount of about 1 to about 3 weight percent based on the weight of the composition.

[0067] In master batch solutions the amount of monomer will typically be from about 10 to about 90 weight percent based on the weight of the composition. In some preferred embodiments, the amount of monomer will be from about 20 to about 80 weight percent based on the weight of the composition.

[0068] The compounds described herein, including monomers I and II, can be made by standard synthetic methods known to those skilled in the art. For example, one could derive monomer-I by reacting adipic acid and benzyl amine. Monomer-II could be made by reacting m-xylene diamine with a formic acid derivative.

[0069] In addition, to the monomers discussed in the preceding paragraph. The compositions of the invention can contain one or more additional oxygen scavenging materials. These materials may be polymeric, oligomeric, or monomeric in nature. One suitable material is MXD6, a polyamide, that is discussed in U.S. Patent No. 5,639,815. Other suitable materials are polyolefins which can be added as blended material or as a unit within the base polymer moiety. See, for example, U.S. Patent No. 6,083,585.

[0070] The composition may also include other components such as pigments, fillers, crystallization aids, impact modifiers, surface lubricants, denesting agents, stabilizers, ultraviolet light absorbing agents, metal deactivators, nucleating agents such as polyethylene and polypropylene, phosphate stabilizers and dyestuffs. Other additional components are well known to those skilled in the art and can be added to the existing composition so long as they do not negatively impact the performance of the compositions. In particular, it is known that certain metal ions are to be avoided since they tend to poison the catalytic effect of the transition metal catalysts of the here-in described invention. Typically, the total quantity of such components will be less than about 10% by weight relative to the whole composition. In some embodiments, the amount of these optional components is less than about 5%, by weight relative to the total composition.

[0071] A common additive used in the manufacture of polyester polymer compositions used to make stretch blow molded bottles is a reheat additive because the preforms made from the composition must be reheated prior to entering the mold for stretch blowing into a bottle. Any of the conventional reheat additives can be used, such additives include various forms of black particles, e.g. carbon black, activated carbon, black iron oxide, glassy carbon, and silicon carbide; the gray particles such as antimony, and other reheat additives such as silicas, red iron oxide, and so forth.

[0072] In many applications, not only are the packaging contents sensitive to the ingress of oxygen, but the contents may also be affected by UV light. Fruit juices and

pharmaceuticals are two examples of such contents. Accordingly, in some embodiments, it is desirable to incorporate into the polyester composition any one of the known UV absorbing compounds in amounts effective to protect the packaged contents so long as the compounds do not negatively impact performance.

[0073] The instant compositions can be made by mixing a base polymer (PET, for example) with the oxidizable organic component and the transition metal composition. Such compositions can be made by any method known to those skilled in the art. In certain embodiments, some or part of the transition metal may exist in the base polymer prior to mixing. This residual metal, for example, can exist from the manufacturing process of the base polymer. In some embodiments, the base polymer, the oxidizable organic component and the transition metal are mixed by tumbling in a hopper. Other optional ingredients can be added during this mixing process or added to the mixture after the aforementioned mixing or to an individual component prior to the aforementioned mixing step.

[0074] The instant composition can also be made by adding each ingredient separately and mixing the ingredients prior melt processing the composition to form an article. In some embodiments, the mixing can be just prior to the melt process zone. In other embodiments, one or more ingredients can be premixed in a separate step prior to bringing all of the ingredients together.

[0075] The oxidizable organic component can be added in pure form or may be treated with a low molecular weight organic wax like compound to prepare a prill or bead like material for ease of dosing during the injection molding process.

[0076] In some embodiments, the invention concerns use of the compositions described herein as a component of a wall that is used in a package for oxygen sensitive materials. The necessary scavenging capacity of a package will generally have to be greater for walls that have a greater permeance in the absence of scavenging additives. Accordingly, a commercially useful effect is harder to achieve when inherently higher permeance materials are used, unless the layer is protected, such as with a layer of polymer or other material, to reduce the O₂ flux reaching the scavenging composition. Such constructions may find particular applicability where the requirement is for rapid headspace-O₂ evacuation, or in containers for O₂-sensitive products that also require walls with low permeance to water vapor.

[0077] The wall may be a rigid one, a flexible sheet, or a clinging film. It may be homogenous or a laminate or coated with other polymers. If it is laminated or coated, then the scavenging property may reside in a layer of the wall the permeance of which is relatively high in the absence of scavenging and which alone would not perform very satisfactorily but which

performs satisfactorily in combination with one or more other layers which have a relatively low permeance but negligible or insufficient oxygen-scavenging properties. A single such layer could be used on the outside of the package since this is the side from which oxygen primarily comes when the package is filled and sealed. However, such a layer to either side of the scavenging layer would reduce consumption of scavenging capacity prior to filling and sealing.

[0078] When the instant compositions are used in a wall or as a layer of a wall, the permeability of the composition for oxygen is advantageously not more than about 3.0, or about 1.7, or about 0.7, or about 0.2, or about $0.03 \text{ cm}^3 \text{ mm}/(\text{m}^2 \text{ atm day})$. The permeability of the composition provided by the present invention is advantageously not more than about three-quarters of that in the absence of oxygen-scavenging properties. In some embodiments, the permeability is not more than about one half, one-tenth in certain embodiments, one twenty-fifth in other embodiments, and not more than one-hundredth in yet other embodiments of that in the absence of oxygen-scavenging properties. The permeability in the absence of oxygen-scavenging properties is advantageously not more than about $17 \text{ cm}^3 \text{ mm}/(\text{m}^2 \text{ atm day})$, or about 10, and or about 6. A particularly good effect can be achieved for such permeabilities in the range from about 0.5, or about 1.0, to 10, or about $6.0 \text{ cm}^3 \text{ mm}/(\text{m}^2 \text{ atm day})$. Measurements of oxygen permeation can be made by methods described, for example, in U.S. Patent No. 5,639,815.

[0079] In another aspect, the instant composition can be used as a master batch for blending with a polymer or a polymer containing component. In such compositions, the concentration of the oxidizable organic component and the transition metal will be higher to allow for the final blended product to have suitable amounts of these components. The master batch may also contain an amount of the polymer to which the master batch is to be blended with. In other embodiments, the master batch may contain a polymer that is compatible with the polymer that the master batch is to be blended with.

[0080] In yet another aspect, the compositions of the instant invention can be used for forming a layer of a wall which primarily provides oxygen-scavenging (another layer including polymer providing gas barrier without significant scavenging), or as a head-space scavenger (completely enclosed, together with the package contents, by a package wall). Such techniques are well known to those skilled in the art.

[0081] The time period for which the permeability is maintained can be extended by storing the articles in sealed containers or under an inert atmosphere such as nitrogen prior to use with oxygen sensitive materials. Such a scheme may prove beneficial where performs or rolls of film or sheet are to be stored for long periods prior to further packaging-conversion operations.

[0082] In another aspect, the invention provides a package, whether rigid, semi-rigid, collapsible, lidded, or flexible or a combination of these, comprising a wall as formed from the compositions described herein. Such packages can be formed by methods well known to those skilled in the art.

[0083] Among the techniques that may be used to make articles are molding generally, injection molding, stretch blow molding, extrusion, thermoforming, extrusion blow molding, and (specifically for multilayer structures) co-extrusion and lamination using adhesive tie layers. Orientation, e.g. by stretch blow molding, of the polymer is especially attractive with phthalate polyesters because of the known mechanical advantages that result.

[0084] Specific articles include preforms, containers and films for packaging of food, beverages, cosmetics, pharmaceuticals, and personal care products where a high oxygen barrier is needed. Examples of beverage containers for which the instant invention are particularly useful are bottles for containing juices, sport drinks, beer or any other beverage where oxygen detrimentally affects the flavor, fragrance, performance (prevent vitamin degradation), or color of the drink. The compositions of the instant invention are also particularly useful as a sheet for thermoforming into rigid packages, and as films for flexible-package structures. Rigid packages include food trays and lids. Examples of food tray applications include dual ovenable food trays, or cold storage food trays, both in the base container and in the lidding (whether a thermoformed lid or a flexible film), where the freshness of the food contents can decay with the ingress of oxygen. The compositions of the instant invention also find use in the manufacture of cosmetic containers and containers for pharmaceuticals or medical devices.

[0085] The package walls of the instant invention can be a single layer or a multilayer constructions. In some embodiments using multilayer walls, the outer and inner layers may be structural layers with one or more further layers. Any of the layers may contain the oxygen scavenging material of this invention. In some embodiments, the outer and inner layers comprise and polyolefin or a polyester. In the most-preferred embodiments, a single layer design is preferred. Such a design may have advantages in simplicity of manufacture and cost, without sacrifice of the transparency of the polyester base polymer.

[0086] As used herein, the terms "a", "an", "the" and the like refer to both the singular and plural unless the context clearly indicates otherwise. "A bottle", for example, refers to a single bottle or more than one bottle.

[0087] Also as used herein, the description of one or more method steps does not preclude the presence of additional method steps before or after the combined recited steps. Additional steps may also be intervening steps to those described. In addition, it is understood

that the lettering of process steps or ingredients is a convenient means for identifying discrete activities or ingredients and the recited lettering can be arranged in any sequence.


[0088] Where a range of numbers is presented in the application, it is understood that the range includes all integers and fractions thereof between the stated range limits. A range of numbers expressly includes numbers less than the stated endpoints and those in-between the stated range. A range of from 1-3, for example, includes the integers one, two, and three as well as any fractions that reside between these integers.

[0089] As used herein, "master batch" refers to a mixture of base polymer, oxidizable organic component, and transition metal that will be diluted, typically with at least additional base polymer, prior to forming an article. As such, the concentrations of oxidizable organic component and transition metal are higher than in the formed article.


[0090] As used herein, the term "combining" includes blending or reacting the components that are combined.

Examples

[0091] The instant invention is illustrated by the following examples that are not intended to limit the scope of the invention. N,N' - bis (phenylmethyl) Hexane diamide (referred to as Monomer -I, CAS Registry No: 25344 - 24- 5) and N,N' - [1,3-phenylenebis(methylene)] bis Acetamide (referred to as Monomer – II, CAS Registry No: 131711 - 99 – 4) were prepared by Sigma Aldrich.



Monomer -I



Monomer - II

Example 1

[0092] Extruded strips were prepared using a bench-top Killion extruder (with typical extruder output rate between 8-10 lbs / hour) for evaluating oxygen scavenging potential using oxy-senseTM for Monomer-I and Monomer-II. The temperature profile across different extruder zones used was typical to that used for PET (about 525 °F). Extruded films were cut into thin strips and about 2g samples for each formulation were sealed into 22 mL glass vials and stored at elevated temperature (70 °C). The % oxygen depletion inside the vials over time was monitored using commercially available oxy-senseTM instrument. Different formulations and their respective code names are given below:

1. PET + 3% 6007 + 100 ppm Co carboxylate powder (Code: **T10**)
2. PET + 3% Monomer - I + 100 ppm Co carboxylate powder (Code: **M-I 3-100**)
3. PET + 3% Monomer - I + 200 ppm Co carboxylate powder (Code: **M-I 3-200**)
4. PET + 5% Monomer - I + 100 ppm Co carboxylate powder (Code: **M-I 5-100**)
5. PET + 5% Monomer - I + 200 ppm Co carboxylate powder (Code: **M-I 5-200**)
6. PET + 3% Monomer - II + 100 ppm Co carboxylate powder (Code: **M-II 3-100**)
7. PET + 3% Monomer - II + 200 ppm Co carboxylate powder (Code: **M-II 3-200**)
8. PET + 5% Monomer - II + 100 ppm Co carboxylate powder (Code: **M-II 5-100**)
9. PET + 5% Monomer - II + 200 ppm Co carboxylate powder (Code: **M-II 5-200**)

[0093] Actual Monomer I and Monomer II content as well as the cobalt content in the extruded strips were not verified. Graphs in Figures 2 and 3 show the % oxygen depletion in the vials over time. It can be seen that while Monomer-I shows limited scavenging, some of the Monomer-II compositions scavenge as well as the MonoxbarTM control sample (T10).

[0094] It is evident that Monomer-I and Monomer-II have oxygen scavenging potential based on oxy-senseTM data and further testing was performed by manufacturing actual blown containers.

Example 2

[0095] Preforms were injection molded on a 2 cavity Husky LX160 PET injection molding machine. Preforms were made with the following formulations:

Heat WaveTM(Voridian) PET + 3% Monomer - I + 75 ppm Co carboxylate powder

Heat Wave PET + 3% Monomer - II + 75 ppm Co carboxylate powder

[0096] PET, Monomer-I (in powder form) and Cobalt carboxylate mixture (cobalt neodeconate (Co NDA, CAS # 27253-31-2) and cobalt propionate (CAS# 1560-69-6) mixture with a 20.5% Co metal content) were tumble blended in a bucket and fed into the machine hopper. Actual final composition in the preform was not verified. Bottles were blown on the unit cavity Re-heat and blow lab machine for oxygen transmission rate (OTR) and haze measurement.

Monomer - I Trial Results:

[0097] 20 oz bottles were blown from preforms and stored empty at STP conditions prior to testing. Two sets of the empty bottles were mounted on an oxygen permeation measuring device - similar to MoCon Oxtran analyzer. The first set (A) were mounted 2 days after manufacture, and the second set (B) were mounted 69 days after manufacture. Results are shown in Figure 4 where:

- A. 2 days after manufacture (-◊-)
- B. 69 days after manufacture (-□-).

Monomer - I Trial Results (Contd.):

[0098] A dispersion of Monomer-I in the PET matrix was measured using standard SEM technique used for evaluating the dispersion of nylon in PET. A comparison of dispersion for the Monomer-I / PET blend compared to MXD6 nylon / PET blend, each at 3% nominal loading, is shown in Figure 1. It appears that there is significant compatibilization between PET and monomer matrix compared to that of the MXD6 blend. Percent haze was measured using the hazemeter and the values for Monomer-I blend bottle compared to that of a plain PET bottle.

[0099] Typical haze levels for a 3% Monoxbar formulation would be > 15%. It is obvious that there has been significant improvement in the haze level using the Monomer -I as the barrier material. The blend formulation is not perceptibly different in transparency compared to plain PET container.

Composition	Haze, % (ASTM D1005)
97%PET, 3% MXD6 Blend	>15
97% PET, 3% Monomer -I blend	2.7
Control 100% PET	3.6

Monomer - II Trial Results:

[0100] Preforms were molded using Monomer - II material at 3% let down on the Husky molding machine and 16 oz bottles were blown using RHBL. Two sets of bottles were mounted on an oxygen permeation measuring device - similar to MoCon Oxtran analyzer- after being stored empty at STP conditions. The first set (C) were mounted 3 days after manufacture, and the second set (D) were mounted 47 days after manufacture. Results are shown in Figure 5.

Example 3

[0101] Preforms were made on Husky LX 160 PET, 2 cavity machine using the following formulation: VitivaTM PET + 3% N,N' Bis (phenylmethyl) hexane diamide (Monomer-I) + 75 ppm Co. Vitiva PET and Monomer-I powder were tumble blended in a bucket and fed into the machine hopper. Cobalt-NDA dispersed in a liquid hydrocarbon carrier, was introduced using a ColorMatrix brand positive displacement pump. Actual final composition in the preform was verified by performing Nitrogen and ICP analysis. Bottles were blown on a unit cavity 16 oz blow mold using a Sidel SBO-1 machine. Bottles were blown and were mounted on an oxygen permeation measuring device - similar to MoCon Oxtran analyzer- 13 days after manufacture.

Trial Results:

[0102] The graph in Figure 6 shows the OTR performance.

[0103] As can be seen from the graph in Figure 6, some scavenging is evidenced. In order to determine the scavenging potential, samples from the side wall of the container were sealed into a 20 mL vial and decrease in oxygen % over time was measured using oxy-sense. The graph in Figure 7 shows the decrease in oxygen concentration over time for a 3% Monomer-I blend compared to a typical MonoxbarTM MXD6-Co⁺⁺-PET blend composition used by Constar in packaging applications.

Trial Results:

[0104] Monomer-I content was measured by performing a nitrogen analysis (Leco method) while the cobalt content was determined using inductively coupled plasma emission spectroscopy (ICPES) analysis. The results are as follows:

Diamide content: 2.6 - 2.7%

Co content: 63 - 71 ppm

[0105] Decrease in oxygen concentration observed using the vial test provides evidence for the scavenging ability / potential of Monomer-I in a monolayer blend construction with PET as the base resin. It also suggests possible influences of processing conditions on scavenging.

Example 4

[0106] Further tests were performed to evaluate thermal effect in manufacturing preforms on an Arburg machine (different platform) to look at the effect of processing on scavenging. Differences between Husky and Arburg injection machines used for the trials are summarized below:

	Husky	Arburg
Screw Diameter	42 mm	25 mm
Injection unit	P type	RS type
Hot-runner	Yes	No
# of shots	12 – 13	2 – 3
Cycle time	25 – 26 s	37 – 39 s
Approx. Residence time	250-300 s	80 – 120 s

Trial results:

[0107] Preforms were manufactured using the 20 oz 38 g preform tooling on a single cavity, 70 ton Arburg injection machine. Preforms were made by tumbling PET pellets, Monomer-I powder and Cobalt carboxylate powder. The following formulations were used:

1. PET + 3% Monomer-I + 75 ppm Co
2. PET + 5% Monomer-I + 75 ppm Co

[0108] Preforms were converted into 16 and 20 oz hot-fill containers and were mounted on an oxygen permeation measuring device - similar to MoCon Oxtran analyzer- 10 days later after being stored empty at STP conditions. Results are shown in the graphs in Figure 8.

[0109] The clarity of the bottles produced are excellent with measured OTR results being as much as an order of magnitude better than the former examples, and the induction period is not evident.

[0110] Monomer-I content was measured by performing a nitrogen analysis (Leco method) while the cobalt content was determined using ICPES analysis for bottles tested on the oxygen permeation apparatus. The results are as follows:

Monomer %	Co (ppm)	OTR (mL/day) Day 7
2.89	72	0.0064
2.66	70	0.0121
4.28	67	0.0011
3.82	56	0.0004

Example 4

Trial results:

[0111] A validation trial was performed by manufacturing preforms with 4% monomer-1 content. As previously done, preforms were manufactured using the 20 oz 38 g preform tooling on a single cavity, 70 ton Arburg injection machine. Preforms were made by tumbling PET pellets, monomer-1 powder and Cobalt carboxylate powder. The following formulation was used: PET + 4% Monomer-I + 75 ppm Co.

[0112] 20 oz bottles were blown from preforms and stored empty at STP conditions prior to testing. Bottles were blown and were mounted on an oxygen permeation measuring device - similar to MoCon Oxtran analyzer 25 days later. Results are shown in Figure 9.

[0113] It is evident from the above examples that processing during injection molding (extruder sizing, residence time, screw type, injection set-up etc.) have a strong influence on oxygen scavenging performance. In order to understand the effect of residence time on the Monomer-I decomposition in the extruder, a thermogravimetric analysis (TGA) was performed.

A known sample weight was placed in the pan and the sample heated at a known rate of 10 Deg C/min. and the weight loss that occurs was recorded. This experiment was performed both in nitrogen and air atmosphere. The resultant scans are shown in Figure 10.

[0114] It is clear that the Monomer-I material would undergo some thermal decomposition in the extruder conditions typically used for the manufacture of PET preforms. In order to understand this further, a known weight sample of Monomer-I was placed in the sample pan and the sample quickly heated (40 °C/min heating rate was used) to 280 °C. The sample temperature was maintained at 280 °C for a period of 300 seconds (to simulate typical residence time in the extruder) and the resulting TGA scan was recorded. The scan is reproduced in Figure 11.

[0115] Results obtained from thermo gravimetric analyzer shown in the above examples, seem to suggest that the residence time would negatively influence the oxygen scavenging performance due to the Monomer-I partly undergoing thermal decomposition. This correlates well with the scavenging performance seen with Husky and Arburg injection platforms.

Example 5

[0116] A design of experiment (DOE) trial was performed on a production injection machine to evaluate the effect of monomer-1 content and process conditions on bottle performance particularly oxygen scavenging. A 9 run factorial experiment was performed with 4 factors - monomer-1 content, cobalt content, extruder temperature and cycle time. Previous work had shown that the material is sensitive to extruder temperature and residence time and the DOE was planned to study the effect of processing parameters as well as any interaction effect between the different factors.

Test Plan- Experiment #1

[0117] Preforms were made on Husky XL 300 PET machine equipped with a 48 cavity 38 g preform mold. The monomer-1 material was pre-blended with Cobalt NDA at desired let-downs and was fed using a suitable powder feeder (K-tron feeder). The DOE matrix is shown in the table below. The responses measured were oxygen transmission rate (Illiop), % oxygen remaining (oxy-sense), IV, and crystallization characteristics (onset).

Std	Run	Block	Factor 1	Factor 2	Factor 3	Factor 4
			A:Diamide %	B:Cobalt content ppm	C:Temperature Deg C	D:Cycle time sec
7	1	Block 1	1.5	150	285	27
6	2	Block 1	3	50	285	27
1	3	Block 1	1.5	50	265	27
8	4	Block 1	3	150	285	37
2	5	Block 1	3	50	265	37
3	6	Block 1	1.5	150	265	37
5	7	Block 1	1.5	50	285	37
9	8	Block 1	2.25	100	275	32
4	9	Block 1	3	150	265	27

[0118] The results were analyzed using a statistical program (Stat-Ease). Figure 12 shows the % oxygen remaining after Day 1 using oxy-sense (scavenging speed). Analysis shows that increasing the diamide content results in less oxygen remaining in the vial (more scavenging). Interestingly, increasing the cobalt content results in slight increase in oxygen remaining in the vial (Figure 13). This might indicate presence of an optimum cobalt level between 50 and 150 ppm for best scavenging.

[0119] Figures 14 and 15 below show the effect of diamide content and extruder temperatures on the amount of oxygen remaining in the vial after 7 days (scavenging capacity). Increasing the diamide content results in higher scavenging capacity. Interestingly, higher extruder temperatures show a slight reduction in % oxygen remaining in the vial. This could potentially be due to some of the diamide material being already reacted in the extruder and resulting in less material available for scavenging after bottle manufacture.

[0120] Bottles were also mounted on Illiop to get actual oxygen transmission rate (mL/pkg/day) measurements and were input into the DOE software for analysis. There were interaction effects between diamide content, extruder temperatures and injection cycle time. Interaction effect plots are shown in Figures 16 and 17.

[0121] It can be seen that both increasing the extruder temperature and cycle time (residence time) result in higher OTR (less effective scavenging). Again this seems to indicate that part of the material is already reacted in the extruder and less is actually available for scavenging after the bottle manufacture.

[0122] In order to understand the oxygen scavenging performance over a long time, bottles from Run #8 (2.25%) and Run #9 (3.0%) were mounted on the Illiop at regular time intervals and the oxygen scavenging performance monitored (Figure 18).

Test Plan: Experiment #2

[0123] In order to understand the effect of PET type (PET-1 is PET type 1, PET-2 is PET type 2, and PET-3 is PET type 3) on scavenging, bottles were made with following formulations:

PET-1 + 2.5 % monomer-1 + 75 ppm Co @ 270 Deg C extruder temperature

PET-1 + 2.5% monomer-1 + 75 ppm Co @ 290 Deg C extruder temperature

PET-2 + 2.5 % monomer-1 + 75 ppm Co @ 280 Deg C extruder temperature

PET-3 + 2.5% monomer-1 + 75 ppm Co @ 280 Deg C extruder temperature

PET-1 : High CHDM co-polymer resin with UVI / little re-heat additives

PET-2: IPA modified co-polymer no UVI / re-heat additives

PET-3: CHDM modified co-polymer with high amounts of re-heat additive

[0124] Samples were cut from the side-wall of the bottle and sealed in 20 mL vials and the scavenging performance was tested using oxy-sense (Figure 19). It is clear that proper selection of PET is important in achieving the optimum oxygen scavenging performance. PET-1 seems to be the preferred PET of choice for optimized performance for a given formulation.


What is claimed is:

1. A composition comprising:

(a) at least one base polymer;

(b) at least one non-polymeric oxidizable organic component present in an amount of about 0.10 to 10 weight percent of the composition and the component comprising at least one compound of the formula E-(L-E)_x wherein:

E is



L is a linking group of the formula -(O-R₂₁)_z-O-, -(NH-R₂₁)_z-NH-, -(NH-C(=O)R₂₂)_t-NH, -NH-R₂₅-NH(C(=O)R₂₆NHR₂₅NH)_u-, -(O-R₂₃-O-R₂₄-C(=O)_s-O- where L is attached to a carbon atom of Ar in structure (I);

x is 0, 1, or 2;

Ar is aryl or heteroaryl;

R₁ and R₂ are each independently, H, C₁-C₁₂ alkyl, C₁-C₆ alkoxy, C₆-C₂₀ aryloxy, hydroxy, C₂-C₆ alkenyl, NR₁₉R₂₀, acetyl, nitro, glyceryl, carbohydrate, -C(=O)H, L, or two R₁ or two R₂ groups can form a group of the formula -O-R₁₈-O;

R₃, and R₄ are each H;

R₅ to R₁₀ are each, independently, H or C₁-C₃ alkyl;

R₁₈ is C₂-C₆ alkyl;

R₁₉ and R₂₀ are each, independently, H, C₁-C₆ alkyl, or C₆-C₂₀ aryl;

R₂₁ and R₂₄ are each, independently, CrC₆ alkyl;

R_{22} , R_{23} , R_{25} and R_{26} are each, independently, C_1 - C_6 alkyl or C_6 - C_{20} aryl;


n and p are independently 0 or an integer from 1 to 5;

s and z are, independently 1, 2, or 3;

t and u are, independently 1 or 2; and

(c) at least one transition metal in a positive oxidation state, the metal being present in the composition in an amount of 10 to 400 ppm.

2. The composition of claim 1, wherein the oxidizable organic component of (b) comprises a compound having the formula:




3. The composition of claim 2 where n and p are each 0, 1, or 2 and R_1 and R_2 are each independently H, C_1 - C_4 alkyl, hydroxy, C_1 - C_3 alkoxy, or carbohydrate.

4. The composition of claim 3 wherein R_1 and R_2 are each independently H, methyl, ethyl, hydroxy, methoxy, ethoxy, or glucose.

5. The composition of claim 3 where R_5 to R_{10} are H.

6. The composition of claim 5 where R_1 and R_2 are each H.

7. The composition of claim 1, wherein the oxidizable organic component of (b) comprises a compound having the formula:




8. The composition of claim 1 wherein the at least one transition metal is cobalt.

9. The composition of claim 8 wherein the at least one transition metal further comprises zinc.

10. The composition of claim 1 wherein the base polymer comprises a polyester polymer.
11. The composition of claim 10 wherein the polyester polymer is polyethylene terephthalate.
12. The composition of claim 1 wherein the oxidizable organic component is present in an amount of about 1 to about 10 weight percent based on the weight of the composition.
13. The composition of claim 1 wherein the oxidizable organic component is present in an amount of about 1 to about 5 weight percent based on the weight of the composition.
14. The composition of claim 1 wherein the oxidizable organic component is present in an amount of about 1 to about 3 weight percent based on the weight of the composition.
15. The composition of claim 1 wherein the concentration of transition metal is 30 to 150 ppm.
16. A wall of a package comprising at least one layer, the layer comprising a composition, the composition comprising:
 - (a) at least one base polymer;
 - (b) at least one non-polymeric oxidizable organic component present in an amount of about 0.10 to 10 weight percent of the composition and the component comprising at least one compound of the formula $E-(L-E)_x$ wherein:

E is



L is a linking group of the formula $-(\text{O}-\text{R}_{21})_z-\text{O}-$, $-(\text{NH}-\text{R}_{21})_z-\text{NH}-$, $-(\text{NH}-\text{C}(=\text{O})\text{R}_{22})_t-\text{NH}-$, $-\text{NH}-\text{R}_{25}-\text{NH}(\text{C}(=\text{O})\text{R}_{26}\text{NHR}_{25}\text{NH})_u-$, $-(\text{O}-\text{R}_{23}-\text{O}-\text{R}_{24}-\text{C}(=\text{O})_s-\text{O}-$ where L is attached to a carbon atom of Ar in structure (I);

x is 0, 1, or 2;

Ar is aryl or heteroaryl;

R₁ and R₂ are each independently, H, C₁-C₁₂ alkyl, C₁-C₆ alkoxy, C₆-C₂₀ aryloxy, hydroxy, C₂-C₆ alkenyl, NR₁₉R₂₀, acetyl, nitro, glyceryl, carbohydrate, -C(=O)H, L, or two R₁ or two R₂ groups can form a group of the formula -O-R₁₈-O;

R₃, and R₄ are each H;

R₅ to R₁₀ are each, independently, H or C₁-C₃ alkyl;

R₁₈ is C₂-C₆ alkyl;

R₁₉ and R₂₀ are each, independently, H, C₁-C₆ alkyl, or C₆-C₂₀ aryl;

R₂₁ and R₂₄ are each, independently, CrC₆ alkyl;

R₂₂, R₂₃, R₂₅ and R₂₆ are each, independently, C₁-C₆ alkyl or C₆-C₂₀ aryl;

n and p are independently 0 or an integer from 1 to 5;

s and z are, independently 1, 2, or 3;

t and u are, independently 1 or 2; and

(c) at least one transition metal in a positive oxidation state, the metal being present in the composition in an amount of 10 to 400 ppm.


17. A process for making an article comprising:

(a) forming a melt by combining the following ingredients in a melt processing zone:

(i) at least one base polymer,

(ii) at least one non-polymeric oxidizable organic component present in an amount of about 0.10 to 10 weight percent of the composition and the component comprising at least one compound of the formula E-(L-E)_x wherein:

E is



L is a linking group of the formula $-(O-R_{21})_z-O-$, $-(NH-R_{21})_z-NH-$, $-(NH-C(=O)R_{22})_t-NH-$, $-NH-R_{25}-NH(C(=O)R_{26}NHR_{25}NH)_u-$, $-(O-R_{23}-O-R_{24}-C(=O)_s-O-$ where L is attached to a carbon atom of Ar in structure (I);

x is 0, 1, or 2;

Ar is aryl or heteroaryl;

R₁ and R₂ are each independently, H, C₁-C₁₂ alkyl, C₁-C₆ alkoxy, C₆-C₂₀ aryloxy, hydroxy, C₂-C₆ alkenyl, NR₁₉R₂₀, acetyl, nitro, glyceryl, carbohydrate, -C(=O)H, L, or two R₁ or two R₂ groups can form a group of the formula -O-R₁₈-O;

R₃, and R₄ are each H;

R₅ to R₁₀ are each, independently, H or C₁-C₃ alkyl;

R₁₈ is C₂-C₆ alkyl;

R₁₉ and R₂₀ are each, independently, H, C₁-C₆ alkyl, or C₆-C₂₀ aryl;

R₂₁ and R₂₄ are each, independently, CrC₆ alkyl;

R₂₂, R₂₃, R₂₅ and R₂₆ are each, independently, C₁-C₆ alkyl or C₆-C₂₀ aryl;

n and p are independently 0 or an integer from 1 to 5;

s and z are, independently 1, 2, or 3;

t and u are, independently 1 or 2; and

(iii) at least one transition metal in a positive oxidation state, the metal being present in the composition in an amount of 10 to 400 ppm;

(b) forming an article from the melt.


18. A method for packaging an oxygen sensitive material comprising:

(a) preparing a package having a wall comprising at least one layer, at least one of the layers comprising a composition, the composition comprising

(i) at least one base polymer,

(ii) at least one non-polymeric oxidizable organic component present in an amount of about 0.10 to 10 weight percent of the composition and the component comprising at least one compound of the formula $E-(L-E)_x$ wherein:

E is



L is a linking group of the formula $-(O-R_{21})_z-O-$, $-(NH-R_{21})_z-NH-$, $-(NH-C(=O)R_{22})_t-NH-$, $-NH-R_{25}-NH(C(=O)R_{26}NHR_{25}NH)_u-$, $-(O-R_{23}-O-R_{24}-C(=O)_s-O-$ where L is attached to a carbon atom of Ar in structure (I);

x is 0, 1, or 2;

Ar is aryl or heteroaryl;

R₁ and R₂ are each independently, H, C₁-C₁₂ alkyl, C₁-C₆ alkoxy, C₆-C₂₀ aryloxy, hydroxy, C₂-C₆ alkenyl, NR₁₉R₂₀, acetyl, nitro, glyceryl, carbohydrate, -C(=O)H, L, or two R₁ or two R₂ groups can form a group of the formula -O-R₁₈-O;

R₃, and R₄ are each H;

R₅ to R₁₀ are each, independently, H or C₁-C₃ alkyl;

R₁₈ is C₂-C₆ alkyl;

R_{19} and R_{20} are each, independently, H, C₁-C₆ alkyl, or C₆-C₂₀ aryl;

R_{21} and R_{24} are each, independently, CrC₆ alkyl;

R_{22} , R_{23} , R_{25} and R_{26} are each, independently, C₁-C₆ alkyl or C₆-C₂₀ aryl;

n and p are independently 0 or an integer from 1 to 5;

s and z are, independently 1, 2, or 3;

t and u are, independently 1 or 2; and

(iii) at least one transition metal in a positive oxidation state, the metal being present in the composition in an amount of 10 to 400 ppm;


(b) introducing the oxygen sensitive material into the package; and

(c) closing the package.

19. A method for producing a packaging material having a wall with oxygen barrier properties comprising:

(a) providing polymer mixture comprising at least one base polymer containing at least one non-polymeric oxidizable organic component present in an amount of about 0.10 to 10 weight percent of the composition and the component comprising at least one compound of the formula E-(L-E)_x wherein:

E is



L is a linking group of the formula -(O-R₂₁)_z-O-, -(NH-R₂₁)_z-NH-, -(NH-C(=O)R₂₂)_t-NH, -NH-R₂₅-NH(C(=O)R₂₆NHR₂₅NH)_u-, -(O-R₂₃-O-R₂₄-C(=O)_s-O- where L is attached to a carbon atom of Ar in structure (I);

x is 0, 1, or 2;

Ar is aryl or heteroaryl;

R₁ and R₂ are each independently, H, C₁-C₁₂ alkyl, C₁-C₆ alkoxy, C₆-C₂₀ aryloxy, hydroxy, C₂-C₆ alkenyl, NR₁₉R₂₀, acetyl, nitro, glyceryl, carbohydrate, -C(=O)H, L, or two R₁ or two R₂ groups can form a group of the formula -O-R₁₈-O;

R₃, and R₄ are each H;

R₅ to R₁₀ are each, independently, H or C₁-C₃ alkyl;

R₁₈ is C₂-C₆ alkyl;

R₁₉ and R₂₀ are each, independently, H, C₁-C₆ alkyl, or C₆-C₂₀ aryl;

R₂₁ and R₂₄ are each, independently, CrC₆ alkyl;

R₂₂, R₂₃, R₂₅ and R₂₆ are each, independently, C₁-C₆ alkyl or C₆-C₂₀ aryl;

n and p are independently 0 or an integer from 1 to 5;

s and z are, independently 1, 2, or 3;



t and u are, independently 1 or 2;

wherein the polymer mixture comprises at least one transition metal in a positive oxidation state, the metal being present in the composition in an amount of 10 to 400 ppm;

(b) forming the polymer mixture of step (a) into a wall; and


(c) forming a container which comprises the wall.

1/19


Figure 1**3 % Monomer****3% Nylon**

2/19


Figure 2




3/19

Figure 3


4/19

Figure 4


5/19

Figure 5


6/19

Figure 6


7/19

Figure 7

8/19


Figure 8

9/19

Figure 9

10/19

Figure 10



11/19

Figure 11




Figure 12

12/19




Figure 13

13/19




Figure 14

14/19




Figure 15

15/19




Figure 16

16/19




Figure 17

17/19




Figure 18
18/19









Figure 19

19/19

% O₂ remaining for different samples



3 % Monomer

3% Nylon