

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
14 April 2011 (14.04.2011)

PCT

(10) International Publication Number
WO 2011/042225 A1

(51) International Patent Classification:
G03F 7/32 (2006.01)

(21) International Application Number:
PCT/EP2010/058008

(22) International Filing Date:
8 June 2010 (08.06.2010)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
09172718.0 9 October 2009 (09.10.2009) EP

(71) Applicant (for all designated States except US): **FLEXO-CLEAN ENGINEERING B.V.** [NL/NL]; Blik 8, NL-4941 SG Raamsdonksveer (NL).

(72) Inventor; and

(75) Inventor/Applicant (for US only): **AYDOGAN, Figen** [NL/NL]; Zwaluwstraat 9, NL-4901 BC Oosterhout (nb) (NL).

(74) Agent: **ROELANDS, Olaf Siegfried**; Sweelinckplein 1, NL-2517 GK The Hague (NL).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) Title: A POLYMER WASHOUT SOLVENT, AND THE USE THEREOF FOR DEVELOPING A FLEXOGRAPHIC PRINTING PLATE

(57) Abstract: A polymer washout solvent for developing a flexographic printing plate comprising: - an ester hydrocarbon component, - an ether hydrocarbon component, - an alcoholic hydrocarbon component. The washout solvent of the invention has less hazardous properties than the known solvents. Use of a polymer washout solvent for developing a flexographic printing plate in a washing step.



WO 2011/042225 A1

**A polymer washout solvent, and the use thereof for
developing a flexographic printing plate.**

The present invention relates to a polymer washout solvent
5 and the use thereof for developing a flexographic printing
plate.

In the technical field of the invention, flexographic
printing plates are flexible, polymeric plates which have a
relief corresponding to an image to be printed. The relief
10 is present on top of a basic layer. The production of these
printing plates (also referred to as solvent printing
plates, or clichés) starts with sheets of soft
photopolymerizable material, which can be hardened under
influence of light. First the back side of the plate is
15 exposed uniformly to UV/A light to obtain a hardened basic
layer. Subsequently the front side of the plate is exposed
to UV/A light according to a certain pattern. This is
usually done by applying at the front side a mask with
openings which is the negative of the pattern to be printed.
20 The light passing through the openings of the mask thus
hardens specific regions of the front side of the plate.
The not hardened regions can be removed in various ways, to
obtain a so called developed flexographic plate. Usually the
removal of not hardened polymer is performed by washing the
25 plate in a solvent, a so called polymer washout solvent.
During the washing step not hardened polymer is removed, and
the remaining hardened regions (i.e. the relief) absorb some
solvent so that they swell. Special dryers are used to
remove solvent absorbed in the relief, before they are ready
30 for use.

In practice, well-known and widely used are polymer
washout solvents such as 'Haku' produced by the company
Kluthe, and 'Nylosolv A' produced by the company BASF. Both

solvents have in spite of their popularity, drawbacks. Nylosolv A was introduced in 1988 to substitute earlier solvents based on perchloroethylene (a CFC, an environmentally hazardous compound). A major ingredient (25-50 wt%) in Nylosolv A (obtained from Flint Group GmbH) is a heavy fraction of hydrated distillate of mineral oil. Also Haku (obtained from Kluthe) contains such a heavy fraction distillate (50-100 wt%, including aromatics). This component, also referred to as naphta, is classified as hazardous.

Apart from the heavy fraction distillate, Nylosolv A contains cyclohexanol (25-50 wt.%) and m-diisopropyl benzene (10-25 wt%). As second main ingredient Haku contains benzylalcohol (10-25wt.%). These components are also classified as hazardous.

Another example is Flexosol from the company Biesterveld B.V., which contains heavy fraction distillate and benzylalcohol.

Thus the known solvents are hazardous compositions, and are harmful in the sense that they present a threat to man and environment. For that reason, it is not allowed to keep in stock large amounts of these solvents, unless strict and cost-consuming measures are taken to prevent any accidents. Besides these unwanted properties, the solvents have an unpleasant odor. This unpleasant odor is also transmitted to the printing plates after washing with the solvent, which compromises the quality of the end-product. Furthermore, different sheets of soft photopolymerizable material, require different types of washout solvent to achieve the best washout result.

Apart from these drawbacks, there is a general interest in improving the steps of washing and drying of the flexographic plates, for instance by reducing the time

needed for these steps. In addition there is also a general interest in providing a solvent which is easily and economically re-usable. Finally, such washout solvent should be able to achieve a similar result in regard of the appearance and properties of the developed flexographic printing plate, when compared to known solvents.

Accordingly, the objective of the invention is to provide a less hazardous and less harmful polymer washout solvent which achieves at the same time one or more of the above indicated goals.

The objective of the invention is achieved by a polymer washout solvent for developing a flexographic printing plate which comprises:

- an ester hydrocarbon component,
- an ether hydrocarbon component,
- an alcoholic hydrocarbon component.

The washout solvent contains no heavy fraction distillates (i.e. naphta) as used in the known solvents. Instead, three main components are in the solvent which are not classified as hazardous or harmful. The solvent is thus intrinsically less hazardous than the known solvents. Also the bad odor is not present any longer.

Although the industry has been investigating for a long time how to formulate a solvent which does not have the drawbacks of naphta, it did not succeed in providing such solvent.

Furthermore, the solvent - as will be shown below - achieves a reduction of the time needed when washing and drying a flexographic plate. Most surprisingly, the solvent of the invention is only slightly absorbed in hardened regions so that swelling during the washing step is absent or very low. Obviously, this has a positive effect on the subsequent drying time, in that the time needed is reduced.

As the solvent is suitable for a wide range of different soft photopolymerizable materials, it is not longer required to keep stocks of different washout solvents, as they can be replaced by the single washout solvent of the invention.

5 Also, the solvent is a stable mixture, as it showed no precipitation effects during normal shelf life.

The solvent is after use as wash-out solvent, fit for re-use by distilling off used solvent (regeneration), because no major adjustments to the specific ratio of the components in the distilled solvent are needed. Furthermore,
10 because of the relatively low number of components, the solvent is easily adjusted, if needed.

During use, it was found that the solvent can be used for more than 40 washing cycles without the need of
15 regeneration. In contrast, Nylosolv is to be regenerated sooner, as it shows precipitation of particles of washed out polymer. This indicates that the solvent of the invention has a higher solubility value for the polymers to be washed out than known solvents.

20 Preferably, the solvent of the invention comprises

- 10-25wt.% ester hydrocarbon component
- 50-75wt.% ether hydrocarbon component, and
- 10-25wt.% alcoholic hydrocarbon component.

Particularly effective is a solvent wherein the ester
25 hydrocarbon component comprises a compound chosen from the group of ester compounds of a C1-C5 alkyl, a benzyl or a benzyl derivative and a C1-C5 alkanoate, as well as mixtures of these ester compounds. The C1-C5 groups may be branched or straight hydrocarbons, and preferred are straight
30 hydrocarbons.

Especially preferred for its effectiveness is a solvent wherein the ester hydrocarbon component includes acetate as alkanoate, and preferably benzyl or a benzyl derivative.

Preferably, in the polymer washout solvent of the invention, the ether hydrocarbon component comprises a di-ether of an C1-C8 alkane derived from a diol, and two C1-C3 alkoxy groups.

5 With more preference, in the polymer washout solvent according to the invention, the ether hydrocarbon component comprises a di-ether of an alkane having an internal ether group, and preferably two methoxy groups. Especially preferred is a di-ether such as dipropylene
10 glycol dimethyl ether.

Furthermore preferred is a solvent wherein the alcoholic hydrocarbon component comprises a compound chosen from the group of C1-C10 alcoholic compounds, as well as mixtures of these alcoholic compounds. The C1-C10 groups may
15 be branched or straight hydrocarbons. Again, such solvents prove to be effective in achieving the goals of the invention.

Preferably, the alcoholic hydrocarbon component comprises a compound chosen from the group of C3-C6
20 alcoholic compounds or a mixture thereof, a primary alcoholic group is present, and more preferably the hydrocarbon chain is straight. Especially preferred are n-butanol and/or n-pentanol.

Also preferred is a solvent of the invention wherein
25 the alcoholic hydrocarbon component comprises a compound containing a secondary alcoholic group, possibly also containing an ether group.

In particular, in the solvent of the invention, the alcoholic compound is a propanol, preferably propan-2-ol
30 and/or 1-methoxypropan-2-ol.

Advantageously, the washout solvent according to the invention contains additives for improving the odor of the solvent. For example known fragrances are used to mask any

unwanted odor from the solvent. In particular, D-Limonene is used as an additive.

In another aspect, the invention relates to the use of a polymer washout solvent according to the invention, for developing a flexographic printing plate in a washing step. As will be shown below, when using the solvent of the invention, the developing of a flexographic printing plate becomes less time consuming, in regard of the washing step, as well as the subsequent drying step.

The Example below shows a polymer washout solvent according to the invention, and its use for developing a flexographic printing plate.

Example

A mixture of the following components was prepared:

Component	Wt%
dipropylene glycol dimethyl ether	50-75
Benzyl acetate	10-25
n-butanol	10-25

The obtained mixture, a washout solvent according to the invention, has a boiling point of 116°C, a flash point of 48°C and a density of 0,92 kg/liter. The solvent is classified according to ADR for transportation safety as class 3, UN1120, group 3.

The washout solvent was used in a wash-out apparatus (from DuPont company) for developing flexographic printing plates (from Flint company). Regions on the front side of the plate were beforehand selectively photopolymerized under UV light by using a mask.

The time needed for washing off the non-hardened polymer from the plate (2.84 mm thickness), was 400-500 seconds, which is approximately half the time in comparison to a known solvent as Nylosolv A. Virtually no swelling occurred after performing the washing step.

The time needed for the subsequent drying step was 15-30 minutes, which is a reduction by 1.5 to 2 hours compared to using a known solvent.

The used solvent with the washed off non-hardened polymer, was distilled off to recover the solvent. The distilled solvent showed to have a ratio of components similar to the solvent before use, and is thus regenerable without the need of major adjustments to the relative amounts of the components. In contrast, known solvents need major adjustment of the relative amounts of the components, after distilling off after their use. The components have to be added in specific amounts to the distillate in order to obtain a suitable regenerated washout solvent for re-use. According to specific tables the amounts to be added have to be calculated in order to regenerate the solvent correctly.

Claims

1. A polymer washout solvent for developing a flexographic printing plate comprising:
- 5 - 10-25wt.% of an ester hydrocarbon component,
 - 50-75wt.% of an ether hydrocarbon component,
 - 10-25wt.% of an alcoholic hydrocarbon component.
- 10 2. A polymer washout solvent according to claim 1, wherein the ester hydrocarbon component comprises compounds chosen from the group of ester compounds of a C1-C5 alkyl, a benzyl or a benzyl derivative, and a C1-C5 alkanoate, as well as mixtures of these ester compounds.
- 15 3. A polymer washout solvent according to one of the preceding claims 1 or 2, wherein the ester hydrocarbon component includes acetate as alkanoate, and preferably a benzyl or a benzyl derivative.
- 20 4. A polymer washout solvent according to one of the preceding claims 1-3, wherein the ether hydrocarbon component comprises a di-ether of an C1-C8 alkane derived from a diol, and two C1-C3 alkoxy groups.
- 25 5. A polymer washout solvent according to one of the preceding claims 1-4, wherein the ether hydrocarbon component comprises a diether of an alkane having an internal ether group, and preferably two methoxy groups.
- 30 6. A polymer washout solvent according to one of the preceding claims 1-5, wherein the alcoholic hydrocarbon component comprises a compound chosen from the group of C3-C6 alcoholic compounds or a mixture thereof, contains a

primary alcoholic group, and wherein preferably the hydrocarbon chain is straight.

7. A polymer washout solvent according to one of the preceding claims 1-6, wherein the alcoholic hydrocarbon component comprises a compound chosen from the group of n-butanol and n-pentanol or a combination thereof.
8. A polymer washout solvent according to one of the preceding claims 1-7, wherein the alcoholic hydrocarbon component comprises a compound, wherein the alcoholic moiety of the alcoholic hydrocarbon component is a secondary alcoholic group, possibly also containing an ether group.
9. Use of a polymer washout solvent according to one of the preceding claims 1-8, for developing a flexographic printing plate in a washing step.

INTERNATIONAL SEARCH REPORT

International application No

PCT/EP2010/058008

A. CLASSIFICATION OF SUBJECT MATTER

INV. G03F7/32

ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

G03F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, BEILSTEIN Data, CHEM ABS Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 02/061506 A2 (BASF DRUCKSYSTEME GMBH [DE]; KNOELL ROLF [DE]) 8 August 2002 (2002-08-08) * abstract; claim 1 2; examples -----	1-9
A	EP 0 355 789 A (DU PONT [US]) 28 February 1990 (1990-02-28) * abstract; claims 1,6,9; examples -----	1-9
A	US 5 354 645 A (SCHOBBER MANFRED [US] ET AL) 11 October 1994 (1994-10-11) * abstract; claims 1,5,9 column 5, line 56 - line 60 -----	1-9
A	EP 1 085 003 A (DAICEL CHEM [JP]) 21 March 2001 (2001-03-21) * abstract examples II-5,II-6; tables II-1 -----	1-9
	-/--	



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

20 July 2010

Date of mailing of the international search report

02/08/2010

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040,
Fax: (+31-70) 340-3016

Authorized officer

Paisdor, Bernd

INTERNATIONAL SEARCH REPORT

International application No

PCT/EP2010/058008

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	JP 57 108851 A (NIPPON ELECTRIC CO) 7 July 1982 (1982-07-07) * abstract -----	1-9
A	US 2006/040218 A1 (WYATT MARION F [US] ET AL) 23 February 2006 (2006-02-23) * abstract; claims 1,6 -----	1-9
A	WO 03/046666 A1 (NUPRO TECHNOLOGIES INC [US]) 5 June 2003 (2003-06-05) page 6, line 8 - page 7, line 4 page 8, last paragraph -----	1-9

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP2010/058008

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 02061506	A2	08-08-2002	DE 10103823 A1	08-08-2002
EP 0355789	A	28-02-1990	AT 136661 T	15-04-1996
			AU 628399 B2	17-09-1992
			AU 4310389 A	23-03-1990
			CA 1336238 C	11-07-1995
			EP 0433374 A1	26-06-1991
			JP 2566326 B2	25-12-1996
			JP 4500278 T	16-01-1992
			WO 9002359 A1	08-03-1990
US 5354645	A	11-10-1994	NONE	
EP 1085003	A	21-03-2001	WO 0058252 A1	05-10-2000
			US 6610638 B1	26-08-2003
JP 57108851	A	07-07-1982	JP 1007651 B	09-02-1989
			JP 1527208 C	30-10-1989
US 2006040218	A1	23-02-2006	NONE	
WO 03046666	A1	05-06-2003	CA 2468239 A1	05-06-2003
			EP 1449034 A1	25-08-2004
			US 2003198900 A1	23-10-2003
			US 2003104315 A1	05-06-2003