



- (51) **International Patent Classification:**
C09D 121/02 (2006.01) *C09D 5/00* (2006.01)
- (21) **International Application Number:**
PCT/US20 12/069 108
- (22) **International Filing Date:**
12 December 2012 (12.12.2012)
- (25) **Filing Language:** English
- (26) **Publication Language:** English
- (30) **Priority Data:**
61/576,021 15 December 2011 (15.12.2011) US
- (71) **Applicant: VALSPAR SOURCING, INC.** [US/US]; P.O. Box 1461, 901 3rd Avenue South, Minneapolis, Minnesota 55440 (US).
- (72) **Inventors: HIBBEN, Mary Jane;** 40W782 Dillonfield Drive, Elburn, Illinois 60119 (US). **REBEL, Nicholas;** 562 Summer Blvd. Apt. 104, Lakemoor, Illinois 60051 (US). **HALLBERG, Steven;** 1850 Maple Lane, Elgin, Illinois 60123 (US).
- (74) **Agent: VISWANATHAN, Hema;** Valspar Property Counsel, P.O. Box 1461, 901 3rd Avenue S., Minneapolis, Minnesota 55440 (US).
- (81) **Designated States** (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM,

AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

- (84) **Designated States** (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report (Art. 21(3))
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments (Rule 48.2(h))

(54) **Title:** HIGH BLOCK, TACK AND SCRUB RESISTANT COATING COMPOSITION

(57) **Abstract:** The present invention is directed to a coating composition or paint comprising a multistage latex with at least first and second stages, wherein the composition or paint is substantially free of volatile organic compounds (VOC) and capable of film formation even in the absence of coalescent agents. The base paint formulation is capable of being tinted at a point-of-sale (i.e. in-store) using a colorant composition of a type and quantity required to produce a paint of desired color and finish. The paints, including deeply colored paints, show improved block resistance, scrub resistance and tack resistance.



WO 2013/090341 A1

HIGH BLOCK, TACK AND SCRUB RESISTANT COATING COMPOSITION

CROSS-REFERENCE TO RELATED APPLICATION(S)

- 5 **[001]** This application claims priority from U.S. Provisional Application Serial No. 61/576,021, filed 15 December 2011.

FIELD OF THE INVENTION

10 **[002]** Conventionally, paint compositions containing latex polymer particles also include a coalescent in addition to pigments and fillers. The coalescent functions as a solvent as well as a plasticizer for the polymer particles to soften the latex polymer particles and assist in the formation of a continuous coating or film after applying to a surface and allowing to dry.

15 **[003]** Useful coalescents are generally stable in the presence of water, compatible with other ingredients typically used in paint formulations, particularly the latex polymers, such that the stability of the latex-based composition is not compromised. Typical coalescent agents contain volatile organic compounds (VOC) and are sufficiently volatile to escape when the applied coating composition is allowed to dry, but sufficiently nonvolatile to evaporate more slowly than other ingredients (e.g., drying retarders, antifreezes) that delay film formation.

20 **[004]** For environmental and regulatory reasons, it has become imperative to develop latex polymers that can be used in paint and coating compositions without the use of volatile organic compounds (VOCs). Coalescent agents of the type described in U.S. Patent Nos. 6,762,230 and 7,812,079, for example, are low-VOC compounds that meet stringent environmental requirements, while facilitating film formation.

25 **[005]** To make paint formulations of a desired color and finish, base paint compositions are combined at a point-of-sale with low-VOC colorant compositions of the type described in U.S. Patent No. 7,659,340, for example. However, typical low VOC paints with low VOC colorants tend to form soft, tacky coatings that show poor performance characteristics, such as poor block resistance and poor scrub resistance,
30 for example. This situation is further complicated in deeply colored paint formulations

that require high loading of the low VOC or zero-VOC colorants, which generally have residual non-volatile soft components, making hard film formation even more difficult.

[006] From the foregoing, it will be appreciated that there is a need for latex compositions for use in paint formulations, including deeply colored formulations that form hard films in the presence of low VOC or zero-VOC components soft components, even in the absence of coalescent agents, and demonstrate excellent performance characteristics, including block, scrub and tack resistance.

SUMMARY OF THE INVENTION

[007] The present invention provides coating compositions that include multistage latex polymers, for use in low VOC, colored paint formulations. These formulations include deeply colored formulations, made by adding colorant compositions to base paint formulations at a point-of-sale. Surprisingly, and in contravention of industry bias, systems that include the latex polymer described herein are preferably capable of film formation in the absence of a coalescent agent, and the paints demonstrate excellent tack resistance, block resistance and scrub resistance.

[008] Accordingly, in one embodiment, the present invention provides base paints that include a multistage latex polymer having at least a first stage and a second stage. In another embodiment, the present invention provides a method of making a paint formulation of a desired color by adding a colorant composition to a base paint formulation at a point-of-sale, wherein the base paint formulation includes a multistage latex polymer having at least a first stage and a second stage. In another embodiment, the present invention provides a method comprising the steps of preparing a first monomer mixture for the first stage, preparing a second monomer mixture for the second stage, and feeding the first and second monomer mixtures in a sequential feed process to form the multistage latex polymer, wherein the latex polymer has low VOC content, and is preferably capable of film formation in the absence of a coalescent.

[009] The above summary of the present invention is not intended to describe each disclosed embodiment or every implementation of the present invention. The description that follows more particularly exemplifies illustrative embodiments. In several places throughout the application, guidance is provided through lists of examples, which examples can be used in various combinations. In each instance, the

recited list serves only as a representative group and should not be interpreted as an exclusive list.

[010] The details of one or more embodiments of the invention are set forth in the accompanying drawings and the description below. Other features, objects, and advantages of the invention will be apparent from the description and drawings, and from the claims.

SELECTED DEFINITIONS

[011] Unless otherwise specified, the following terms as used herein have the meanings provided below.

10 [012] The term "component" refers to any compound that includes a particular feature or structure. Examples of components include compounds, monomers, oligomers, polymers, and organic groups contained there.

[013] The term "double bond" is non-limiting and refers to any type of double bond between any suitable atoms (e.g., C, O, N, etc.). The term "ethylenically unsaturated" refers to compounds that include a carbon-carbon double bond (i.e. -C=C-).

15 [014] The term "volatile organic compound" ("VOC"), as defined by the Environmental Protection Agency (EPA) in 40 C.F.R. 51.100(s); refers to any compound of carbon, excluding carbon monoxide, carbon dioxide, carbonic acid, metallic carbides or carbonates, and ammonium carbonate, which participates in atmospheric photochemical reactions. Typically, volatile organic compounds have a vapor pressure equal to or greater than 0.1 mm Hg. As used herein, "volatile organic compound content" ("VOC content") is as measured by ASTM method D2369-90, and means the weight of VOC per volume of the coating solids, and is reported, for example, as grams VOC per liter (g/L).

25 [015] As used herein, the term "glass transition temperature" or "T_g" refers to the temperature at which an amorphous, solid material undergoes a reversible transition to a molten, rubber-like state. Unless otherwise indicated, the T_g values described herein are theoretical values predicted using the Fox equation. Application of the Fox equation to estimate the T_g of polymers is well known in the art.

30 [016] The term "substantially free of VOC" means that the compositions of the present invention contain less than about 50 g/L VOC. Unless otherwise indicated, the terms "low VOC" and "substantially free of VOC" are used interchangeably herein.

The term "essentially free of VOC" means that the compositions of the present invention contain less than 5 g/L of VOCs. The terms, "zero VOC" and "essentially free of VOC" are used interchangeably herein.

[017] The term "substantially free," when applied to components of a composition and not to VOC levels, means that the compositions of the present invention contain no more than about 5 wt% of a particular component, based on total weight of solids in the composition. For example, a composition of the present invention that is substantially free of coalescent contains no more than about 5 wt% coalescent. A composition of the present invention that is essentially free of coalescent contains no more than about 0.5 wt% of coalescent.

[018] The term "water-dispersible" in the context of a water-dispersible polymer means that the polymer can be mixed into water (or an aqueous carrier) to form a stable mixture. For example, a mixture that readily separates into immiscible layers is not a stable mixture. Unless otherwise indicated, the term "water-dispersible" is intended to include the term "water-soluble." In other words, by definition, a water-soluble polymer is also considered to be a water-dispersible polymer.

[019] The term "dispersion," as used herein, in the context of a dispersible polymer refers to the mixture of a dispersible polymer and a carrier. Unless otherwise indicated, the term "dispersion" is intended to include the term "solution."

[020] As used herein, the term "pigment" refers to an organic or inorganic material, and is typically (but not exclusively) in solid form.

[021] As used herein, the term "colorant" refers to a dispersion of pigment in a mobile phase, typically in liquid form, which is added to a coating composition to modify or alter its color or hue, typically at a point-of-sale. As the term is used herein, a colorant may include one or more pigments, dyes and/or inks, along with other additives.

[022] As used herein, the term "base paint" means a composition that includes a vehicle component containing a binder or resin component, and a pigment or filler component dispersed into the vehicle component. As used herein, the base paint formulation includes water as the vehicle, a latex polymer as the binder or resin component, and one or more pigments or fillers used to tone or opacify the base paint as the pigment component.

[023] The base paints described herein are "in-store tintable," meaning that the base paints are present in containers (such as paint cans, for example) and can be tinted or

colored by adding a colorant composition in the store, i.e. at a point of sale, to provide a paint formulation of a desired color and finish.

[024] As used herein, the term "container" means any vessel (either with or without a lid or other type of closure) used to store, mix, tint or color a paint formulation, and

5 includes the vessels in which paints are typically marketed and sold. Suitable containers include paint cans, paint bottles, containers made of metal, containers made of plastic and/or other polymeric materials, and the like.

[025] The term "headspace," as used herein, refers to the volume remaining in a container after the container has been filled with a base paint.

10 **[026]** The term "scrub resistance," as used herein, refers to the ability of the surface of a coating film or paint film to resist being worn away or to maintain its original appearance when rubbed with or against an abrasive surface, typically during cleaning. To measure scrub resistance, a standard test method, ASTM D2486-96 (Standard Test Method for Scrub Resistance of Wall Paints).

15 **[027]** As used herein, the term "block resistance" means the ability of a coating film or paint film, when applied to two surfaces, not to stick to itself on prolonged contact when pressure is applied for a defined period of time. It is a measure of the degree of hardness and/or degree of cure of a film of a coating composition or paint formulation, and is measured by a standard test method, ASTM D4946-89 (Standard Test Method
20 for Blocking Resistance of Architectural Paints).

[028] The term "tack resistance," as used herein, refers to the residual tack of a coating film or paint film after it has been applied to a substrate surface and dried. Tack resistance is typically measured by the Zapon tack test, as further described below.

25 **[029]** Unless otherwise indicated, a reference to a "(meth)acrylate" compound (where "meth" is bracketed) is meant to include both acrylate and methacrylate compounds.

[030] The term "on", when used in the context of a coating applied on a surface or substrate, includes both coatings applied directly or indirectly to the surface or substrate. Thus, for example, a coating applied to a primer layer overlying a substrate constitutes a coating applied on the substrate.

30 **[031]** Unless otherwise indicated, the term "polymer" includes both homopolymers and copolymers (i.e., polymers of two or more different monomers).

[032] The term "comprises" and variations thereof do not have a limiting meaning where these terms appear in the description and claims.

[033] The terms "preferred" and "preferably" refer to embodiments of the invention that may afford certain benefits, under certain circumstances. However, other embodiments may also be preferred, under the same or other circumstances. Furthermore, the recitation of one or more preferred embodiments does not imply that other embodiments are not useful, and is not intended to exclude other embodiments from the scope of the invention.

[034] As used herein, "a," "an," "the," "at least one," and "one or more" are used interchangeably. Thus, for example, a coating composition that comprises "an" additive can be interpreted to mean that the coating composition includes "one or more" additives.

[035] Also herein, the recitations of numerical ranges by endpoints include all numbers subsumed within that range (e.g., 1 to 5 includes 1, 1.5, 2, 2.75, 3, 3.80, 4, 5, etc.). Furthermore, disclosure of a range includes disclosure of all subranges included within the broader range (e.g., 1 to 5 discloses 1 to 4, 1.5 to 4.5, 1 to 2, etc.).

DETAILED DESCRIPTION

[036] Embodiments of the invention described herein feature an in-store tintable base paint formulation that includes a multistage latex polymer having at least a first stage and a second stage, wherein the latex is preferably capable of forming a film even in the absence of a coalescent agent. The base paint formulation as described herein is preferably substantially free of volatile organic compounds (VOC), and is used to make coating compositions or paints, including deeply colored paints, by the addition of colorant compositions to the base paint at the point-of-sale. Preferred paints demonstrate excellent performance characteristics, such as optimal block resistance, and superior scrub resistance and tack resistance, for example.

[037] In an embodiment, the invention described herein includes an in-store tintable base paint that comprises a multistage latex polymer. The term "multistage," as used herein with respect to a latex means the latex polymer was made using discrete, sequential charges of two or more monomers or monomer mixtures, or was made using a continuously-varied charge of two or more monomers.

[038] A multistage latex does not necessarily exhibit a single T_g inflection point as measured by differential scanning calorimetry (DSC). For example, a DSC curve for a multistage latex made using discrete charges of two or more monomers may exhibit

two or more Tg inflection points. In cases where a DSC curve shows only a single Tg inflection point, or even no Tg inflection points, it may be difficult to determine whether the latex is single stage or multistage, as the observation of a Tg inflection point depends on various factors, including the relative concentration of monomers in a particular stage. The presence or absence of Tg inflection points on a DSC curve is not
5 dispositive, but a multistage latex may be described in terms of the theoretical Tg values for each monomer stage, as determined by the Fox equation.

[039] In an embodiment, a method of making a multistage having at least a first stage and a second stage is described herein. The method includes steps of providing a first
10 monomer or mixture for the first stage, providing a second monomer or mixture for the second stage; and feeding the first and second monomers or mixtures into a reaction vessel to form a multistage latex that is capable of film formation in the absence of a coalescent agent.

[040] Various methods can be used to prepare the multistage latex described herein, including for example, sequential monomer feed and continuously varying monomer
15 feed techniques. In a sequential monomer feed process, a first monomer or monomer mixture is fed during the early stages of polymerization, and a second monomer (i.e. a different monomer, or a mixture of monomers present in different ratios than in the first monomer mixture) is fed during later stages of polymerization. In a varying monomer
20 feed process, a first monomer composition is fed, followed by the addition of a second monomer at certain points in the polymerization process, and at different speeds. By controlling the type of monomers selected for the feed process, a multistage latex suitable for low VOC, coating compositions or paints may be formed, and the latex preferably provides excellent performance characteristics, such as, for example, block
25 resistance, scrub resistance, tack resistance, and the like, for such coating or paint formulations.

[041] In an embodiment, the multistage latex composition described herein is made by a sequential monomer feed process. In an aspect, polymerization begins with a high Tg monomer feed followed by a low Tg monomer feed, and vice-versa. In a preferred
30 aspect, polymerization with a high Tg monomer feed, followed by a low Tg monomer feed.

[042] In an embodiment, the multistage latex composition described herein is made using varying monomer feeds. The resulting polymer will typically have a DSC curve that exhibits no Tg inflection points, and could be said to have an essentially infinite

number of Tg stages. The resultant multistage latex will have a gradient Tg from high to low, or vice-versa, depending on the order that monomers of high Tg are fed into the reaction.

[043] In a preferred aspect, the multistage latex described herein is made by a

5 sequential monomer feed process using at least two distinct feeds of monomers. In an aspect, a high Tg stage (i.e. a hard stage) is fed first into a reactor vessel, and a low Tg stage (i.e. a soft stage) is added at a later stage in the process. A multistage latex may be formed, and after coalescence, the composition will typically display two distinct Tg values, or at least one Tg corresponding to the monomer stage present at higher
10 concentration. Without being bound to theory, it is expected that no distinct Tg will be observed or detected by DSC for a monomer or monomer mixture in a particular stage that is present in very small quantities relative to the other monomer or monomer mixture.

[044] In an aspect, the multistage latex optionally includes a seed phase, i.e. a

15 relatively small monomer or polymer particle, but the seed is not required, nor essential for preparation or optimal performance of the multistage latex when used in a coating composition or paint formulation.

[045] In an aspect, the relative positions of the first and second phases may be internal and external respectively, or vice-versa. In another aspect, the first and second phases

20 may be neighboring or adjacent. Without being bound by theory, it is believed that the relative position of the stages of the multistage latex is influenced by the method used to make the latex. By controlling the monomers used in each stage of the sequential monomer feed process, the multistage latex described herein will contain about 10 wt% to 50 wt%, preferably about 20 to 40 wt%, more preferably about 25 to 35 wt% of
25 monomers of the first stage, i.e. high Tg or hard stage monomers, and about 50 wt% to 90 wt%, preferably about 60 to 80 wt%, more preferably about 65 to 75 wt% of monomers of the second stage, i.e. low Tg or soft stage monomers, based on the total weight of the composition.

[046] In an embodiment, by controlling the monomers used for each stage of the

30 sequential monomer feed process, a multistage latex composition with optimal minimum film forming temperature (MFFT) is obtained. The MFFT is the minimum temperature at which the multistage latex composition will form a continuous film, i.e. the temperature below which coalescence does not occur. The MFFT of the multistage latex composition as described herein is preferably less than about 20°C, more

preferably less than about 10°C, and most preferably less than about 5°C. A base paint or other paint that includes the multistage latex described herein has MFFT of less than about 20°C, preferably less than about 10°C.

[047] In an embodiment, the multistage latex described herein preferably includes at least two polymer portions. In a preferred embodiment, the multistage latex includes at least a first stage and a second stage. In an aspect, the multistage latex includes up to about 50%, preferably about 10% to 40%, more preferably 15% to 35% of one or more monomers or a mixture of monomers comprising the first stage. In an aspect, the multistage latex includes about 50%, preferably 60% to 90%, more preferably 75% to 85% of one or more monomers or a mixture of monomers comprising the second stage.

[048] In an embodiment, the multistage latex described herein preferably includes at least two polymer portions with different Tg values. In a preferred embodiment, the multistage latex includes at least a first stage and a second stage. The first stage preferably has a Tg of about 0°C to 120°C, more preferably about 80°C to about 110°C. The second stage preferably has a Tg of greater than about -35°C to 0°C, more preferably about -20°C to -10°C. In an embodiment, where the multistage latex is intended for use in a pigmented high gloss or semi-gloss paint, the first stage preferably has Tg of about 0° to 120°C, more preferably 25° to 75°C, most preferably 45° to 55°C.

[049] In an embodiment, the multistage latex described herein preferably includes at least two polymer portions, i.e. a first stage and a second stage, with different Tg values, where the difference in Tg (ΔT_g) is about 35°C, preferably about 65°C, more preferably about 95°C, and most preferably about 125°C. In an embodiment, where the multistage latex is intended for use in a pigmented high gloss or semi-gloss paint, the difference in $T_g(\Delta T_g)$ is preferably about 35°C, more preferably about 65°C.

[050] In an embodiment, the invention described herein includes a multistage latex polymer having at least a first stage and a second stage. In an aspect, the first stage and second stage of the multistage latex separately and preferably include one or more ethylenically unsaturated monomers. In another aspect, the first and second stage of the multistage latex separately and preferably includes the one or more polymerization product(s) of (i) ethylenically unsaturated monomers, such as, for example, alkyl and alkoxy (meth)acrylates, vinyl esters of saturated carboxylic acids, monoolefins, conjugated dienes, optionally with (ii) one or more monomers, such as, for example, styrene, methyl methacrylate, butyl acrylate, 2-ethylhexyl acrylate, vinyl acetate,

acrylonitrile, vinyl chloride, and the like. In an embodiment, the first stage or second stage of the multistage latex optionally includes one or more polyfunctional (meth)acrylate monomers. In an embodiment, the first stage and second stage separately and preferably also include one or more ethylenically unsaturated carboxy-
 5 functional amide monomers, e.g., ureido-functional monomers, such as monomers formed as the product of the reaction between aminoalkyl alkylene urea (e.g., amino ethylene urea, for example) with an ethylenically unsaturated carboxylic acid or anhydride (e.g., maleic anhydride, for example).

[051] Suitable ethylenically unsaturated monomers of the first and second stage
 10 include, for example, acrylic acid, methacrylic acid, methyl acrylate, ethyl acrylate, propyl acrylate, butyl acrylate, 2-ethylhexyl acrylate, methyl methacrylate, ethyl methacrylate, propyl methacrylate, butyl methacrylate, 2-ethylhexyl methacrylate, hydroxyethyl acrylate, hydroxyethyl methacrylate, hydroxybutyl acrylate, hydroxybutyl methacrylate, glycidyl methacrylate, 4-hydroxybutyl acrylate glycidyl ether, 2-
 15' (acetoacetoxy)ethyl methacrylate (AAEM), diacetone acrylamide, acrylamide, methacrylamide, methylol (meth)acrylamide, styrene, *a*-methyl styrene, vinyl toluene, vinyl acetate, vinyl propionate, allyl methacrylate, and mixtures thereof. Preferred monomers include styrene, methyl methacrylate, methacrylic acid, acetoacetoxy ethyl methacrylate, butyl acrylate, and the like.

[052] Suitable polyfunctional acrylates include, for example, di-, tri- and tetra-
 20 functional acrylates such as dipropylene glycol diacrylate (DPGDA), propoxylated glyceryl triacrylate (GPTA), pentaerythritol tetraacrylate, dipentaerythritol tetraacrylate, mixtures thereof, and the like. Preferred polyfunctional acrylate monomers include pentaerythritol tetraacrylate, dipentaerythritol tetraacrylate, and the
 25 like,

[053] Suitable ureido-functional monomers include, for example, monomers with the -NR—(C=O)—NH— functionality, where R may be H, substituted or unsubstituted C₁-C₁₀ alkyl, substituted or unsubstituted C₃-C₆ cycloalkyl or heteroalkyl, and the like. Without being bound by theory, ureido-functional monomers are believed to promote
 30 the wet adhesion of a paint formulation to a substrate, where the formulation includes the multistage latex described herein.

[054] In an embodiment, the first or second stage of the multistage latex each separately and preferably include about 90 to 99 wt%, more preferably about 94 to 96 wt% . and most preferably about 97 to 98 wt% of one or more ethylenically unsaturated

monomers, and preferably up to about 5 wt%, more preferably about 1 to 4 wt%, and most preferably about 2 to 3 wt% of one or more ureido-functional monomers, based on the total weight of the monomers in the first or second stage respectively. For example, in a preferred embodiment, the first stage includes about 95 wt% methyl methacrylate, 2 wt% methacrylic acid, 2 wt% AAEM, and about 1 wt% ureido-functional monomer. In a preferred embodiment, the second stage includes about 30 wt% methyl methacrylate, 60 wt% butyl acrylate, about 4 wt% AAEM, about 2 wt% methacrylic acid, and about 1 wt% ureido-functional monomer.

[055] In an embodiment, the multistage latex described herein includes, optionally and preferably, a fluorosurfactant. As used herein, the term "fluorosurfactant" refers to synthetic organofluorine compounds with multiple fluorine atoms. Such compounds can be polyfluorinated, perfluorinated (i.e. fluorocarbons), or partially fluorinated, and typically include a hydrophilic head and a fluorinated/hydrophobic tail. Suitable fluorosurfactants may be anionic or nonionic. Commonly used fluorosurfactants include, for example, fluoroalkanes, perfluoroalkanes, their derivatives, and the like. In an aspect, short chain fluorinated compounds are preferred, such as, for example, *ci-cio* fluorinated compounds. In a preferred aspect, the fluorosurfactant is an anionic C_6 -fluorocarbon compound, and is preferably substantially free of PFOS and PFOA, and more preferably, essentially free of PFOS and PFOA. In a preferred aspect, the multistage latex preferably includes up to about 0.5 wt%, more preferably about 0.1 to 0.3 wt%, based on the total weight of the multistage latex composition.

[056] The composition described herein may include other components or additives, added to either the reaction mixture of monomers used to make the multistage latex, to the latex, or to a coating composition or base paint that includes the latex. Suitable additives are known to those of skill in the art and include, for example, surfactants, open time agents, pH adjustors, initiator and chaser solutions, cross-linking agents, preservatives, defoaming agents, anticorrosive agents, and combinations thereof.

[057] In an aspect, the multistage latex composition described herein may include a coalescing agent that aids in film formation. Suitable coalescing agents or coalescent compounds are dispersible in a coating composition or paint that includes the latex described herein, and facilitate film formation at temperatures of less than about 25°C, and even at temperatures of 5 to 10°C. Preferred coalescing agents have VOC content of less than about 50%, preferably less than about 30%, more preferably, less than

about 20%, and most preferably, less than about 15%. Exemplary suitable coalescing agents include low VOC compounds of the type described in detail at least in U.S.

Patent No. 6,762,230 and 7,812,079. Other suitable low VOC coalescents include

Optifilm (Eastman Chemical, Kingsport TN), Loxanol (Cognis, Kankakee IL, now

5 BASF), Archer RC (ADM, Decatur IL), and the like. Conventional coalescing agents such as, Texanol (Eastman Chemical) and the like can also be used, either alone or in combination with other solvents such as, for example, 2-butoxyethanol (butyl cellosolve), diethylene glycol monobutyl ether (butyl carbitol), and the like, provided low VOC levels are maintained in the coating composition or paint.

10 [058] Although coalescing agents are typically used in paint to aid in film formation, the paint made with the multistage latex described herein is oftentimes capable of film formation at low levels of coalescent, or even in the absence of coalescing agents, at film-forming temperatures of 20°C or less, more preferably at temperatures of 10°C or less. Accordingly, in an aspect, the coalescing agent is an optional ingredient in coating
15 compositions or paints that include the latex described herein, and in a preferred aspect, the coating composition or paint is substantially free, and more preferably, essentially free of coalescing agents.

[059] In an embodiment, the multistage latex composition described herein is suitable for use in a low-VOC or zero-VOC coating composition or a paint to be colored or

20 tinted to a desired color and finish, such as an in-store tintable base paint, for example.

In an aspect, the coating composition or paint may include one or more pigments,

including pigments or fillers used to tone or opacify the in-store tintable base paint.

Suitable examples of pigments include, without limitation, titanium dioxide white, carbon black, lamp black, black iron oxide, red iron oxide, yellow iron oxide, brown

25 iron oxide (a blend of yellow and red oxide with black oxide), phthalocyanine green, phthalocyanine blue, organic reds (such as naphthol red, quinacridone red and toluidine red), quinacridone magenta, quinacridone violet, DNA orange, and/or organic yellows (such as Hansa yellow), for example.

[060] In an embodiment, the multistage latex composition can be used in a coating

30 composition, such as a paint, especially a base paint to be colored or tinted at the point-of-sale of a paint of desired color and finish. In an aspect, the base paint may be clear (unpigmented) or pigmented prior to being colored or tinted. In an aspect, the base paint is tinted or colored in-store using one or more commercially available colorants.

Suitable colorants which can be used in a coating composition or paint formulation include, for example, NovoColor (Color Corp. of America, Louisville KY) colorants, i.e. zero-VOC colorants compatible with water-based coating compositions as described herein. Preferred colorant compositions include a colorant component, i.e. a pigment dispersed in a liquid phase, a surfactant package that includes a latex-compatible surfactant, a carrier, and other optional additives. Exemplary colorant compositions include single colorant formulations compatible with latex paints, of the kind described in U.S. Patent Nos. 6,488,760 and 7,659,340. These colorant compositions are uniform and do not require mixing before addition to a base paint formulation, have extended shelf-life, and show viscosity increase of less than about 15 KU, more preferably less than about 10 KU, when stored over an extended period of time at temperatures of about 40° to 50°.

[061] In an aspect, the multistage latex composition can be used in a base paint formulation to be tinted to produce a dark or deeply colored paint. To produce such dark or deeply colored paint requires a high colorant load. In an aspect, the amount of colorant to be added to the base paint is determined by the desired color and finish (i.e. glossy, semi-gloss, satin, etc) of the colored paint. Preferably, the paint includes up to about 20 wt% colorant, more preferably about 5 to 15 wt% colorant, and most preferably about 8 to 12 wt% colorant.

[062] Typically, the viscosity of the base paint decreases when the colorant composition is added. A deeply colored paint requires a high colorant load, and therefore, the colored paint will have a lower viscosity and may have poor properties on application to a substrate. Moreover, as base paints are made to have low or no VOC by using softer polymers, and low or no VOC-containing colorants added to the base paint have a high percentage of non-volatile soft components, it is difficult to form a hard acrylic film or coating, with good mechanical properties, i.e. block resistance, and scrub resistance, for example. Surprisingly, the multistage latex described herein, when used in a base paint to be tinted to a colored paint, and especially a deeply colored paint, resists softening even at the high colorant load, with a correspondingly high percentage of non-volatile soft components, needed to make a deeply colored paint. Contrary to expectation, deeply colored paints made using the multistage latex described herein provide excellent block resistance while maintaining superior scrub resistance when compared to commercially available latex polymers.

[063] In contravention of industry bias, when used in paint applied at high temperatures and/or in very humid environments, the paint including multistage latex described herein displays excellent performance characteristics, with optimal scrub resistance and tack resistance, along with superior block resistance relative to formulations made using commercially available latex polymers.

[064] In an embodiment, paints made with the multistage latex described herein demonstrate excellent block resistance. Block resistance is measured by a standard test as described below, and block ratings are assigned on a scale from 0 to 10, where a rating of 0 corresponds to very poor block resistance, and a rating of 10 corresponds to excellent block resistance. In an aspect, the paints described herein show 1-day and 7-day block ratings of preferably at least 6, more preferably at least 7, and most preferably at least 8.

[065] In an embodiment, paints made with the multistage latex described herein demonstrate superior scrub resistance, when compared to commercially available formulations. Scrub resistance is measured by a standard test as described below. The film is cured for seven (7) days, and scrub resistance is reported as a number of scrubs applied before the film failed, i.e. scrubbed off the substrate surface. In an aspect, the paints described herein display scrub resistance of at least about 600 scrubs, more preferably about 800 to 1300, and most preferably about 900 to 1200.

[066] In an embodiment, paints made with the multistage latex described herein demonstrate excellent tack resistance. Tack resistance is measured by a standard test as described below, and reported as the time following initial cure that the surface of the film is no longer sticky to the touch. In an aspect, the paints described herein preferably display tack resistance of no more than about 60 seconds, more preferably no more than about 15 seconds, and most preferably no more than about 5 seconds.

[067] In an aspect, the multistage latex composition described herein can be used in a coating composition or paint that further includes one or more additives. Suitable additives include, without limitation, fillers, thixotropes, rheological modifiers, matting agents, and the like. The additives may include one or more ingredients added to a paint to modify the properties or enhance paint performance during storage, handling, application and other or subsequent stages. Desirable performance characteristics of a paint formulation include, for example, chemical resistance, abrasion resistance (i.e. scrub resistance), tack resistance, hardness, gloss, reflectivity, appearance and/or a combination of such properties and similar other properties. Preferred performance

enhancing additives include lacquers, waxes, flattening agents, additives to prevent mar, abrasion, and the like.

[068] The invention is illustrated by the following examples. It is to be understood that the particular examples, materials, amounts, and procedures are to be interpreted
5 broadly in accordance with the scope and spirit of the inventions as set forth herein. Unless otherwise indicated, all parts and percentages are by weight and all molecular weights are weight average molecular weight. Unless otherwise specified, all chemicals used are commercially available from, for example, Sigma-Aldrich, St. Louis, Missouri.

10

EXAMPLES

[069] Unless indicated otherwise, the following test methods were utilized in the Example(s) that follow(s).

Scrub Resistance

[070] The scrub resistance of the paint formulations is tested using ASTM D2486-96
15 (Standard Test Method for Scrub Resistance of Wall Paints).

Block Resistance

[071] The block resistance of the paint formulations is tested using ASTM D4946-89 (Standard Test Method for Blocking Resistance of Architectural Paints).

Tack Resistance

20 [072] Tack resistance of the paint formulations is measured by the Zapon tack test. An aluminum lever of 3" (7.62 cm) in length and 1" (2.54 cm) wide is bent at a 40D angle from the vertical, creating a 1" (2.54 cm) platform and 2" (5.08 cm) lever. A drawdown is made using 4 mil (0.10 mm) Bird bar and allowed to cure overnight. The Zapon tack tester is then set on the film and weighted with a specific weight and
25 allowed to stand for a specific period of time (i.e. a 1000 g weight for 30 seconds). Upon removal of the weight, the time taken for the Zapon tack tester to fall over is observed and recorded. A film that has no tack will cause the tack tester to fall over instantly.

Example 1

[073] Multistage latex compositions #1 to #9 were prepared by a sequential monomer feed process, as described above, including at least a first stage and a second stage. The multistage latex compositions were included in a clear (unpigmented) base paint. The base paint was tinted using black colorant at a concentration of 12 ounces of colorant per gallon of the base paint (i.e. 7.5 g/L of colorant) to provide black test paint formulations with a semi-gloss finish. The paints were tested alongside control paint made from a commercially available latex polymer system known to provide optimal block resistance (Rhoplex™ HG706, available from Dow). This latex is included in a control base paint, and the control paint is tinted to a black color and semi-gloss finish by adding 12 oz. of colorant per gallon of the control base paint. Testing results are shown in Table 1, where the stage ratio represents the ratio of "hard" monomers to "soft" monomers.

Table 1. Performance properties of Multistage latex

	Commercial Latex	#1	#2	#3	#4	#5	#6	#7	#8	#9
Stage ratio		30/70	30/70	30/70	30/70	30/70	40/60	20/80	70/30	30/70
Hard T _g		106°C	106°C	75°C	75°C	106°C	106°C	106°C	106°C	106°C
Soft T _g		-10°C	-25°C	-10°C	-25°C	-10°C	-10°C	-10°C	-10°C	-10°C
MFFT	12°C	14°C	0°C	12°C	0°C	12°C	18°C	11°C	>18°C	<5°C
Gloss(60°/85°)	48/85	46/82	48/84	45/81	46/83	45/82	43/80	47/83	47/80	29/75
24 hr Block	8/8	7/3	6/3	8/5	7/4	7/4	8.5/7	8/6	9/8	7/7
7 day Block	8/8	7.5/8	7.5/7	8/8	8/8	7/7	9/9	8/8	9/9	10/10
24 hr Tack	3 sec	3 sec	60 sec	2 sec	60 sec	2 sec	1 sec	16 sec	instant	2 sec
Scrub	460	640	1250	345	535	540	520	885	95	285

15 Example 2

[074] Multistage latex compositions #1B to #4B were prepared by a sequential monomer feed process, as described above, including at least a first stage and a second stage, with a ratio of "hard" to "soft" monomers of 30/70 for each composition. The multistage latex compositions were included in a pigmented base paint. The base paint was tinted using black colorant at a concentration of 12 ounces of colorant per gallon of the base paint (i.e. 7.5 g/L of colorant) to provide black test paint formulations with a semi-gloss finish. Test results were compared with a control base paint made as described in Example 1. Results are shown in Table 2.

Table 2. Performance properties of Multistage latex

	Control	#1B	#2B	#3B	#4B
Tg hard stage	NA	106	60	50	37
Tg soft stage	NA	-12	-12	-12	-12
MFFT	10	10	11	9	7
Gloss (60°/85°)	45/80	39/79	46/78	45/70	40/78
Tack	24 seconds	Instant	Instant	5 seconds	60+ seconds
24 hr Block (oven)	8.5	9	8.5	8.5	8

[075] The complete disclosure of all patents, patent applications, and publications, and electronically available material cited herein are incorporated by reference. The foregoing detailed description and examples have been given for clarity of understanding only. No unnecessary limitations are to be understood therefrom. The invention is not limited to the exact details shown and described, for variations obvious to one skilled in the art will be included within the invention defined by the claims. The invention illustratively disclosed herein suitably may be practiced, in some embodiments, in the absence of any element which is not specifically disclosed herein.

1. A coating composition, comprising:

an in-store tintable liquid base paint formulation, comprising

- 5 a multistage latex polymer having at least a first stage with a Tg of greater than about 0 to 120°C and at least a second stage with a Tg of -35 to 0°C; and

optionally, up to about 0.5 wt% fluorosurfactant; and

- 10 about 0.05 to 15 wt% of one or more colorant compositions having volatile organic content (VOC) of less than about 5 wt%; which colorants are added to the base paint formulation at a point-of-sale to achieve a desired color,

wherein the coating composition has scrub resistance of at least about 600 scrubs.

2. A colored coating composition, made by a process comprising the steps of:

- 15 providing a container with a quantity of an in-store tintable base paint formulation and headspace sufficient to receive a quantity of one or more low VOC colorants;

providing instructions for dispensing the low VOC colorant into the base paint formulation at a point-of-sale, and in a particular amount, to obtain a coating composition of a desired color,

- 20 wherein the base paint formulation comprises a multistage latex polymer having at least a first stage with a Tg of greater than about 0 to 120°C and at least a second stage with a Tg of -35 to 0°C; and optionally, up to about 0.5 wt% fluorosurfactant.

3. A method, comprising:

- 25 providing a container with a quantity of an in-store tintable liquid base paint formulation and headspace sufficient to receive a quantity of a low VOC colorant; and

providing instructions for dispensing the low VOC colorant into the base paint formulation at a point-of-sale, and in a particular amount to obtain a paint formulation of a desired color,

5 wherein the base paint formulation comprises a multistage latex polymer having at least a first stage with a T_g greater than about 0 to 120°C and at least a second stage with a T_g of -35 to 0°C; and optionally, up to about 0.5 wt% fluorosurfactant.

4. A method of making a multistage latex polymer, the method comprising:

10 preparing a first mixture of monomers for a first stage, the first mixture comprising about 94 to 98 wt% methyl methacrylate, 1 to 3 wt% methacrylic acid, about 1 to 3 wt% ureido-functional monomer, and optionally, about 1 to 3 wt% acetoacetoxy ethyl methacrylate, based on the total weight of the monomers in the first mixture;

15 preparing a second mixture of monomers for a second stage, the second mixture comprising about 30 to 40 wt% methyl methacrylate, about 50 to 60 wt% butyl acrylate, about 1 to 3% methacrylic acid, about 1 to 5 wt% acetoacetoxy ethyl methacrylate, and about 1 to 3 wt% ureido-functional monomers, based on the total weight of the monomers in the second mixture;

feeding the first mixture into a reactor vessel;

initiating a free radical polymerization of at least the first mixture; and

20 feeding the second mixture into the reactor vessel,

wherein the multistage latex has at least two distinct theoretical T_g values.

5. The composition or method of any of the above claims, wherein the multistage latex is capable of forming a film at a temperature of 4°C or less.

25 6. The composition or method of any of the above claims, wherein the multistage latex is capable of forming a film at a temperature of 10°C or less, in the absence of a separate coalescing agent.

7. The composition or method of any of the above claims, wherein the composition further includes up to about 2 wt% coalescing agent, and is capable of forming a film at a temperature of 20°C or less.
8. The composition or method of any of the above claims, wherein the monomers forming the first stage or second stage comprise one or more ethylenically unsaturated monomers selected from the group consisting of acrylic acid, C₁-C₈ esters of acrylic acid, substituted C_i-C₈ esters of acrylic acid, methacrylic acid, C_i-C₈ ester of methacrylic acid, substituted C_i-C₈ esters of methacrylic acid, styrene, α-methyl styrene, vinyl toluene, vinyl acetate, vinyl propionate, allyl methacrylate, and mixtures thereof.
9. The composition or method of any of the above claims, wherein the monomers forming the first stage or second stage further comprise one or more ureido-functional monomers.
10. The composition or method of any of the above claims, wherein the monomers forming the first stage or second stage further comprise one or more polyfunctional acrylate monomers.
11. The composition or method of any of the above claims, wherein the difference in T_g of the first and second stage monomers is at least about 65°C.
12. The composition or method of any of the above claims, wherein the composition exhibits block resistance rating of at least 6.
13. The composition or method of any of the above claims, wherein the composition exhibits tack resistance of up to about 3 s.
14. The composition or method of any of the above claims, wherein the composition is capable of forming a film at temperature of less than about 15°C.
15. The composition or method of any of the above claims, wherein the colorant comprises:
 - a colorant component;
 - a surfactant package comprising at least one latex-compatible surfactant; and

a carrier,

wherein the colorant has less than about 20 g/L VOC.

16. The composition or method any of the above claims, wherein the composition comprises about 0.1 to 0.3 wt% fluorosurfactant, based on the total weight of the composition.
- 5

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US2012/069108**A. CLASSIFICATION OF SUBJECT MATTER****C09D 121/02(2006.01)i, C09D 5/00(2006.01)1**

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

C09D 121/02; C09D 151/04; B05D 3/00; C08F 20/18; C09D 151/00; B05D 7/00; B32B 13/12; C09D 133/08; C08F 20/00; C08L 33/10; B32B 33/00; C08L 7/02; B60C 1/00

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Korean utility models and applications for utility models

Japanese utility models and applications for utility models

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

eKOMPASS(KFPO internal) & Keywords: coat, latex polymer, multistage, colorant, colourant, VOC, methacrylic acid, methyl methacrylate, butyl acrylate

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2011-0151265 Al (KILLILEA, T. H. et al.) 23 June 2011 . See abstract ; claims 1,2,30 ; paragraphs [0004]-[0005] , [0038] , [0041] , [0043]	1-3
A	-[0044] , [0063H0064] and [0069]-[0070] .	4,5
A	wo 03-031526 Al (AVECIABV.) 17 April 2003 . See abstract ; claims 1,8,9,26,27,29 ; page 4, lines 1-13 ; page 5, lines 32-37 ; and page 9, lines 3-19 .	1-5
A	US 2007-0282046 Al (KILLILEA, T. H. et al.) 6 December 2007 . See abstract ; claims 1,2,3,9 ; paragraphs [0005] , [0007] , [0019] , [0028] , [0052H0053] and [0065] .	1-5
A	US 2009-0143528 Al (MESTACH, D. E. P. et al.) 4 June 2009 . See abstract ; claims 1,2 ; paragraphs [0001] , [0012H0016] , [0020] , [0030] and [0035] .	1-5
A	US 2010-0003442 Al (EVEN, R. C. et al.) 7 January 2010 . See abstract ; claims 1,7 ; paragraphs [0002] , [0005] , [0008] , [0012H0013] and [0024] .	1-5



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

29 April 2013 (29.04.2013)

Date of mailing of the international search report

29 April 2013 (29.04.2013)

Name and mailing address of the ISA/KR

Korean Intellectual Property Office
189 Cheongsu-ro, Seo-gu, Daejeon Metropolitan
City, 302-701, Republic of Korea

Facsimile No. 82-42-472-7140

Authorized officer

HONG, Sung Ran

Telephone No. 82-42-481-5405



INTERNATIONAL SEARCH REPORT

International application No.

PCT/US2012/069108

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	KR 10-2010-0117609 A (RHODIA INC.) 23 November 2010. See abstract ; claims 34, 59, 63 ; paragraphs [0028] , [0030H0031] , [0048] , [0087] -[0088] , [0177] and [0181] .	1-5

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US2012/069108

Box No. II Observations where certain claims were found unsearchable (Continuation of item 2 of first sheet)

This international search report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☐ Claims Nos.:
because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out, specifically:
3. ☒ Claims Nos.: 6-16
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box No. III Observations where unity of invention is lacking (Continuation of item 3 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

1. ☒ As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☒ As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest and, where applicable, the payment of a protest fee.
- ☒ The additional search fees were accompanied by the applicant's protest but the applicable protest fee was not paid within the time limit specified in the invitation.
- ☒ No protest accompanied the payment of additional search fees.

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT/US2012/069108

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 201 1-0151265 A1	23.06.2011	AU 2009-28 1835 A1 CA 2732835 A1 CN 102186936 A EP 2326691 A2 MX 201 1001736 A WO 2010-019825 A2 WO 2010-019825 A3	18.02.2010 18.02.2010 14.09.2011 01.06.2011 10.05.2011 18.02.2010 07.10.2010
WO 03-031526 A1	17.04.2003	AT 426007 T DE 60231637 D1 DK 1448734T3 EP 1448734 A1 EP 1448734 B1 ES 2323452 T3 GB 0124280 D0 US 2004-0260005 A1 US 7049352 B2	15.04.2009 30.04.2009 29.06.2009 25.08.2004 18.03.2009 16.07.2009 28.11.2001 23.12.2004 23.05.2006
US 2007-0282046 A1	06.12.2007	AT 499417 T CA 2655125 A1 DE 6020070 12700 D1 EP 2035516 A1 EP 2035516 B1 MX 2008015356 A US 2009-0035587 A1 US 201 1-0033709 A1 US 7812090 B2 US 7834086 B2 WO 2007-143622 A1	15.03.2011 13.12.2007 07.04.2011 18.03.2009 23.02.2011 30.01.2009 05.02.2009 10.02.2011 12.10.2010 16.11.2010 13.12.2007
US 2009-0143528 A1	04.06.2009	AT 376575 T AU 2005-252388 A1 AU 2005-252388 B2 CN 100551983 C CN 1965042 A DE 602005003025 D1 DE 602005003025 T2 EP 1758961 A2 EP 1758961 B1 ES 2294725 T3 JP 2008-50 1840 A KR 10-1 115083 B1 KR 10-20070-038969 A NZ 551339A US 8013050 B2 WO 2005-12 1595 A2 WO 2005-12 1595 A3	15.11.2007 22.12.2005 12.08.2010 21.10.2009 16.05.2007 06.12.2007 14.08.2008 07.03.2007 24.10.2007 01.04.2008 24.01.2008 28.02.2012 11.04.2007 26.06.2009 06.09.2011 22.12.2005 04.05.2006
US 2010-0003442 A1	07.01.2010	CN 101619172 A	06.01.2010

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT/US2012/069108

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
KR 10-2010-0117609 A	03. 11. 2010	EP 2147935 A2	27. 01. 2010
		EP 2147935 A3	10. 03. 2010
		EP 2147935 B 1	28. 12. 2011
		JP 2010-013641 A	21. 01. 2010
		KR 10-1072403 B 1	11. 10. 2011
		KR 20-100004061 A	12. 01. 2010
		AU 2009-205657 A 1	23. 07. 2009
		AU 2009-337114 A 1	22. 07. 2010
		CA 2711915 A 1	23. 07. 2009
		CA 2748810 A 1	22. 07. 2010
		CN 101977974 A	16. 02. 2011
		EP 2245087 A 1	03. 11. 2010
		EP 2379629 A 1	26. 10. 2011
		JP 2011-510135 A	31. 03. 2011
		JP 2012-515247 A	05. 07. 2012
		KR 10-2011-0110778 A	07. 10. 2011
		US 2009-0186968 A 1	23. 07. 2009
		US 2010-0016485 A 1	21. 01. 2010
		US 2011-0086961 A 1	14. 04. 2011
		US 7906577 B2	15. 03. 2011
		WO 2010-082918 A 1	22. 07. 2010