

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
18 December 2003 (18.12.2003)

PCT

(10) International Publication Number
WO 03/103815 A1

(51) International Patent Classification⁷: **B01D 039/16**

(74) Agent: **GRIFFITH HACK**; Level 3, 509 St Kilda Road,
Melbourne, Victoria 3004 (AU).

(21) International Application Number: PCT/AU03/00726

(22) International Filing Date: 11 June 2003 (11.06.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
PS 2897 11 June 2002 (11.06.2002) AU

(71) Applicants (*for all designated States except US*): **COMMONWEALTH SCIENTIFIC AND INDUSTRIAL RESEARCH ORGANISATION** [AU/AU]; Limestone Avenue, Campbell, Australian Capital Territory 2612 (AU). **ACORDIS KELHEIM GMBH** [DE/DE]; Regensburger Strasse 109, 93309 Kelheim (DE).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **HUBER, Bernd** [DE/DE]; C/- Acordis Kelheim GmbH, Regensburger Strasse 109, 93309 Kelheim (DE). **HELSTROOM, Robert** [AU/AU]; 40 Terminus Street, Petersham, New South Wales 2049 (AU).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: METHODS OF REDUCING THERMO-OXIDATION OF POLYMERS SUCH AS POLYACRYLONITRILE

(57) Abstract: A filter comprising a polymer material comprising a polymer matrix such as polyacrylonitrile containing dispersed metal oxide particles. The metal oxide particles are for example ferric oxide particles, and the polymer material contains generally 0.25-3% by weight of these particles. The filters are resistant to thermo-oxidation and have reduced shrinkage or degradation.



WO 03/103815 A1

METHODS OF REDUCING THERMO-OXIDATION OF POLYMERS SUCH AS
POLYACRYLONITRILE

5 Field of the Invention

The present invention relates to methods of reducing oxidation and/or shrinkage of polymers in high temperature environments. The present invention relates to a broad range of polymers, including acrylic polymers.

Background of Invention

Polyacrylonitrile (PAN) is an acrylic polymer commonly used in many forms. It is manufactured by polymerisation of acrylonitrile monomer ($\text{CH}_2\text{.CHCN}$) using the solution, suspension or emulsion methods. Typically, a small percentage of co-monomer (such as methacrylate - $\text{CH}_2\text{:CHCOOCH}_3$, or vinyl acetate - $\text{CH}_2\text{:CH-O-CO-CH}_3$) is incorporated into the polymer chain to control crystallinity and hence to modify some physical properties of the polymer. The amount of co-monomer in PAN usually ranges from 0 to 15%. Generally PAN is considered to be a homopolymer (ie: $(\text{CH}_2\text{.CHCN})_n$) when it contains less than 2% co-monomer.

Molecular weight of PAN can range from 10,000 to 500,000 or more and is closely controlled within the polymerisation process as it has a strong effect on both the efficiency of the polymer production process and the physical properties of the end product.

The basic form of PAN is a fine white powder. In manufacturing PAN materials, this powder is usually dissolved in a solvent (eg, dimethyl formamide, dimethyl acetamide or water-based sodium rhodanide) and the resulting polymer solution (or "dope") is either cast in

- 2 -

the form of a film or spun as a fine fibre. Fibres based on a copolymer PAN are used for a wide variety of textile applications - as knitwear or as a woven fabric for clothing or home textiles. The fibrous form of
5 homopolymer PAN is commonly used for manufacturing a wide variety of woven or felted materials for technical end uses or as a reinforcing element in composite materials (such as brake linings or concrete).

10 Because of its high level of chemical resistance, homopolymer PAN is also used in various industrial processes and products. Filter materials for both dry and wet applications are commonly made out of PAN.

15 Fabric filters using PAN fibres for particle collection are seeing widespread use for gas cleaning in many industrial processes. They have a high collection efficiency and produce a gas stream with a very low level of particulates. Operating costs may, however, be
20 considerable as the filter bags must be replaced when either the pressure drop across the filter, or the rate of bag failures, or the level of dust emissions become excessive. The removal of particles of unburnt ash from coal-fired power station exhaust gases is one specific
25 example. Depending on the design of the plant, such a filter material might have to operate at temperatures of up to 135 °C in a flue gas environment containing gaseous oxides of nitrogen and sulphur as well as water, carbon dioxide, nitrogen and oxygen. PAN filter material is well
30 suited to this purpose and has been widely employed in the filters of large power stations of Australia, South Africa, and elsewhere.

One disadvantage of polyacrylonitrile is its
35 susceptibility to shrinkage. The shrinkage of polyacrylonitrile and other polymers used in high extreme conditions (such as high temperature and oxidative

- 3 -

conditions) is generally a consequence of oxidation of the polymer. Even in the reduced oxygen environment of combustion flue gas, the rate of PAN oxidation is significant at temperatures above 115 °C. Such oxidation causes the PAN to shrink and to become brittle and lose strength. It frequently leads to premature physical failure of the filter media under the combined effects of growing tensile forces and reduced tensile strength.

While it is possible to introduce standard organic antioxidants into PAN, these are quickly decomposed or migrate out of the crystalline structures in the polymer matrix at high temperatures.

Filters for use in high temperature environments are also made from other polymer materials that are, to a greater or lesser degree, also prone to shrinkage due to oxidation. These include polyesters, polyamides, polyolefins such as polypropylene, polyaramids such as NomexTM, fluorocarbon fibres such as polytetrafluoroethylene and polyphenylene-based polymers such as polyphenylene sulphide.

Summary of Invention

According to one embodiment, the present invention provides a filter comprising a polymer material comprising a polymer matrix containing dispersed metal oxide particles.

According to another embodiment, there is provided a use of a polymer material comprising a polymer matrix and a metal oxide in the manufacture of a filter.

According to a third embodiment, the present invention provides for the use of a polymer material comprising:

- 4 -

- a polymer matrix selected from polyacrylics, polyesters, polyamides, polyolefins, polyaramids, fluorocarbon polymers and polyphenylene polymers, including copolymers and derivatives thereof, and mixtures thereof, and
 - a metal oxide,
- in an environment having a temperature of at least 100 °C.

An example of such an environment is a flue gas environment. Accordingly, the polymer material may be used in a component of flue gas treatment plant.

Detailed Description of the Invention

The present applicants have surprisingly found that the inclusion of metal oxide in materials formed from polymeric materials such as filters intended to be used in high temperature environments, protects the polymer from oxidation (ie thermo-oxidation) and/or degradation, such as shrinkage.

The term filter is used in its broadest sense and encompasses a filter unit, as well as the filtering component of such units. This filtering component is also referred to as the "filter material" or "filter media".

The term metal oxide refers to the class of metal oxides having more than one possible oxidation state. This therefore excludes the alkali and alkaline earth metal oxides such as magnesium oxide, and encompasses the transition metal oxides including, notably, zinc oxide, nickel oxide, iron oxide, copper oxide and cobalt oxide. A mixture of metal oxides or a mixed metal oxide may be used.

Iron oxide is suitably the metal oxide used. The iron oxide is preferably ferric oxide (Fe_2O_3).

- 5 -

The metal oxide is present in the polymer matrix in particulate form. Although any particle size will have an affect on the preservation of the polymer, it has been
5 found that the metal oxide is particularly effective in the form of fine particles. Such particles are preferably less than 1 μm (10^{-6} metre) in size, and more preferably less than 500 nm in size. For best effect, the particles may be as small as 10 nm (10^{-8} metre) in diameter.

10

Such particles can be produced standard ultra-fine grinding techniques or variants thereof using standard equipment, such as a ball mill. Processes which maximise particle dispersion are advantageous to avoid
15 clumping and improve homogeneity in the product. Some of the more recently developed methods are suitable for forming the particles, including the following:

Gonsalves K. E., et al., Synthesis of Acicular Iron
20 Oxide Particles and their Dispersion in a Polymeric Matrix. *J. Mater. Sci.* 2001: 36: 2461-71.

Janzen C., et al., Characteristics of Fe₂O₃ Nanoparticles from Doped Low Pressure H₂/O₂/Ar
25 Flames. *J. Nanopart. Res.* 1999: 1:163-7.

Puntes V. F., et al., Synthesis of Colloidal Cobalt Nanoparticles with Controlled Size and Shapes. *Top. Catal.* 2002: 19(2): 145-8.

30

Xia B. I., et al., Novel Route to Nanoparticle Synthesis by Salt-Assisted Aerosol Decomposition. *Adv. Mater.* 2001: 13(20): 1579-82.

35 Mori Y., et al., Titanium Dioxide Nanoparticles Produced in Water-In-Oil Emulsion. *J. Nanopart. Res.* 2001: 3: 219-25.

- 6 -

Unlike conventional organic antioxidants, these metal oxides, such as Fe_2O_3 , are stable at high temperatures and have been found not to migrate out of the polymeric structure.

Greater concentrations and finer particle size dispersion of metal oxides increase the resistance of the polymer matrix to oxidation.

The amount of metal oxide in the polymer material should be an amount sufficient to reduce the tendency of the polymer to oxidise in high temperature environments when compared with the same polymer not including the metal oxide.

Preferably, the metal oxide constitutes a maximum of 5% by weight of the polymer material. At higher levels, the metal oxide can lead to brittleness of the polymer material reducing the mechanical strength and elasticity. Preferably, the metal oxide constitutes a minimum of 0.1% by weight of the polymer material. The preferred range of inclusion of the metal oxide is from 0.25% to 3% by weight of the polymer material.

The polymer matrix is suitably chosen from one or more of the range of polymers which are prone to oxidation. This includes polyacrylics, polyesters, polyamides, polyolefins, fluorocarbon fibres and polyphenylene polymers, including copolymers and derivatives thereof and mixtures thereof. References to "polymers" encompasses co-polymers, unless the context is to the contrary. The term "polyacrylics" encompasses monodacrylics, and any acrylic-containing polymers, notably those based on acrylic acid and its esters and derivatives. The term "polyolefins" encompasses the broad range of vinyl polymers including polypropylene, polyvinyl

- 7 -

esters, polyvinyl ethers, polyvinyl acetates, polystyrenes, and halogenated polyvinyls, including polyvinylidene chloride. An example of a polyaramid is NomexTM. Fluorocarbon polymers encompass those polymers containing fluorine atoms, such as polytetrafluoroethylene. Such polymers may also be classified in ether polymer classes such as polyolefins. Polyphenylene polymers encompass polymers such as polyphenylene sulphide.

According to one embodiment, the polymer is a polyacrylonitrile-containing polymer, or a derivatives thereof such as methacrylonitrile. The polymer may be polyacrylonitrile (PAN) or a copolymer of acrylonitrile with one or more other monomers. Suitable comonomers include acrylics other than acrylonitrile (such as methacrylonitrile); acrylamides and their derivatives (including methacrylamide); acrylic acid and its esters and derivatives thereof (including methacrylic acid and its esters); olefins and derivatives thereof including vinyl esters and ethers such as vinyl acetate, vinyl butyrate or vinylbutylether, together with styrene and vinyl halogens such as vinyl chloride and vinylidene chloride; and maleimides.

In the situation where the polymer matrix is based on acrylonitrile, it is preferred that the polymer material comprises at least 85% acrylonitrile, more preferably at least 95% and most preferably at least 99% acrylonitrile by weight. Preferably the co-monomer content ranges from 0 to 10%, and more preferably from 0 to 5% by weight of the polymer material. Preferably, the average molecular weight of the polymer is between 100,000 and 300,000.

Suitably, the components made from the polymer materials are in the form of filaments, fibres, yarns,

- 8 -

webs, fabrics, mats, films or sheets, or a combination of these. The nature of these polymers is such that they are suitable for production into fibres or yarns, which may then be woven into flexible materials. Accordingly, they are most suitable for formation into flexible fabric-type filter media.

According to a further embodiment, the present invention provides a method of forming a filter, the method comprising:

- providing a polymer matrix;
- incorporating particulate metal oxide into the polymer matrix;
- casting or spinning the product into a film or a fibre; and
- forming the film or fibre into a filter material.

In dispersing the metal oxide into the polymer melt or solution, the best results are achieved when the individual particles of metal oxide are separated and distributed widely throughout the polymer matrix.

According to the present invention, there is provided a filter formed at least partly from a polymer material comprising:

- a polymer matrix, and
- a metal oxide, the metal oxide being incorporated into the polymer matrix in an amount to provide a polymer material that has a characteristic shrinkage rate of 0.2% or less per 1000 test hours in a flue gas environment of approximately 125 °C.

The shrinkage test used to calculate the "characteristic shrinkage rate" involves the following:

- (i) Forming a yarn from the polymer having a breaking strength of approximately 20 N (plus or minus 5 N);
- (ii) Positioning the yarn in a flue gas environment at

- 9 -

- 125 °C (plus or minus 5 °C) and of approximately 7% oxygen content and under light tension that is no more than 2% of the breaking strength of the yarn;
- (iii) Measuring and recording the changes in the length of the yarn at intervals of 24 hours for a period of up to 5,000 hours of flue gas exposure; and
- (iv) Calculating the percentage change in length of the yarn between two points in time separated by at least 500 hours and between which the length of the yarn has varied at a measurable and approximately constant rate. Preferably, the yarn length between the 4,000 hour point and the 5,000 hour point will be taken as an ideal indicator of the characteristic shrinkage rate of the polymer.

15

To comply with requirement (ii) set out above, the yarn is preferably positioned in a duct or a filter chamber of a flue gas cleaning system and subjected to the following steps:

- (v) Attaching one end of a 5 metre length of the yarn to a fixed mounting point on the floor of the duct or filter chamber; and
- (vi) Looping the free end of the yarn over a pulley above the fixed end of the yarn, and tying an appropriately-sized weight to the free end of the yarn to apply to the yarn a tensile force no greater than 2% of the breaking strength of the yarn.

25

30

The change in length of the yarn is preferably measured by:

- (vii) Coupling the pulley to a rotary position sensor that will turn freely as the length of the yarn changes to detect the change in length of the yarn.

35

It will be understood that the pulley used in the test set out above must be capable of turning freely as

- 10 -

the length of the yarn changes so that the change in length of the yarn can be measured accurately, for example up to 0.02% of the length. It will also be appreciated that the diameter of the pulley should be chosen so that
5 the sum of the frictional torques applied to the pulley shaft by its bearings, and by the rotary transducer (part of the rotary position sensor) does not impede the rotation of the pulley or significantly change the constant tension experienced by the yarn under the action
10 of the tensioning weight.

The pulley and rotary position sensor must also be capable of withstanding the flue gas conditions for several thousand hours of uninterrupted testing.
15 Preferably the output signal from the sensor is connected to an automatic data recording system for ease of testing and calculation of the characteristic shrinkage rate of the polymer. Other details concerning this test are set out in the Examples below.

20 In the aforementioned test for shrinkage under real operating conditions, a shrinkage rate for polyacrylonitrile of 0.5% per 1,000 test hours at 125 °C would be considered normal. To significantly reduce or
25 prevent shrinkage, the incorporation of a metal oxide additive into such a polymer in the manner of the invention would suitably reduce that rate to less than 0.2% per 1,000 test hours.

30 The present invention also provides a filter formed at least partly from a polymer material comprising:
- a polymer matrix, and
- a metal oxide, the metal oxide being incorporated into the polymer matrix in an amount to provide a polymer
35 material that has a characteristic shrinkage rate that is 40% or less compared to the characteristic shrinkage rate of a polymer material without the metal oxide

- 11 -

measured over a test period of 1000 hours in a flue gas environment at approximately 125 °C.

Although shrinkage is one notable example of degradation that impacts on filter performance, other forms of degradation are also evidence of oxidation of the polymer, including cracking and reduction in tensile strength.

10 Detailed Description of the Invention

The present invention will now be described in further detail with reference to a non-limiting example of a polymer material of one embodiment of the invention.
15 For the assistance in understanding the benefits of the polymer materials of the present invention, reference will also be made to a number of drawings, in which:

Figure 1 is a graph illustrating the shrinkage results for a polymer of the prior art compared with
20 a polymer of a preferred embodiment of the present invention;

Figure 2 illustrates FTIR spectra for the polymer materials of the prior art and of the preferred embodiment of the invention prior to and post
25 exposure to flue gas in a power station; and
Figure 3 is a graph comparing the results illustrated in Figure 2 in another format.

Example 1

30 20 kg of a polymer containing 99.5% by weight acrylonitrile and 0.5% by weight of methylacrylate with a relative viscosity of 3.0 was dissolved in 80 kg of dimethylformamide solvent at 90 °C. 200 g of a fine ferric
35 oxide (Fe_2O_3) powder with an average particle size of 200 nm was added to the dope and mixed in well. The dope was pressed through a spinneret with 5,000 holes of 60 μm

- 12 -

diameter in a coagulation bath containing a mixture of solvent and water. The filaments were washed with water, 5-fold stretched in boiling water, treated with a fibre finish, dried on heated rollers, 2-fold stretched, heat-set, crimped and cut. The resultant fibres had a red-brown colour and textile properties of 2.1 dtex (decitex; corresponding to a diameter of approximately 15 μm as polyacrylonitrile has a density of approx 1.18 g/cm^3), 49 cN/tex (c=centi) and an elongation of 15%. The fibres were then spun into a folded yarn with a count of Nm 24/2, a strength of 29.5 cN/tex and an elongation of 13.5%. This yarn was then used in the production of a filter material.

15 Example 2

A yarn was made by the method outlined in Example 1 so as to include a concentration of 1% by weight ferric oxide (200 nm) in conventional PAN. This polymer was found to have a reduced tendency to shrink when exposed to a high temperature environment for an extended period of time, and to exhibit significantly less oxidation (by between 30% to 40%) when compared to conventional PAN.

The tendency of the yarn of Example 2 to shrink was measured by the "characteristic shrinkage test" which is described in further detail below. The same yarn not including the metal oxide additive was also subjected to this test. Figure 1 illustrates the results of this test. It is noted that the two yarns were suspended under a light tension inside a filter chamber of a coal-fired power station where they were exposed to 125 °C flue gas (containing approximately 7% oxygen) for an initial period of more than 600 hours while their rate of shrinkage was continuously recorded. Ideally, this test would continue for several thousand hours to accurately determine the

- 13 -

shrinkage rates of the yarns under the test conditions. In Figure 1, the shrinkage rate of the yarn containing 1% Fe_2O_3 is seen to be negligible compared to that of the conventional yarn.

5

Further evidence of the effectiveness of this method for preserving polyacrylonitrile can be drawn from infra-red spectroscopic analysis of the modified and conventional PAN both before and after exposure to the high temperature atmosphere of the power station flue gas. Such evidence is presented in Figure 2. The FTIR (Fourier Transform Infra-red) absorption spectra of the "new" (unexposed) conventional and modified yarns (the upper and lower charts respectively at the left-side of the figure, labelled (a) and (b)) are compared with the FTIR spectra (the upper and lower charts respectively at the right-side of the figure labelled (c) and (d)) taken after more than 1000 hours of exposure in the power station flue gas atmosphere.

10
15
20

In these spectra, the peaks centred on 1700 cm^{-1} wavenumber represent carboxyl and carbonyl functional groups arising from oxidation of the PAN. The peaks at for example 1450 and 2919 cm^{-1} represent the CH_2 groups of the polymer. Because these peaks are relatively unaffected by such oxidation, they can serve as reference point for assessing the levels of absorbance. The strong peak corresponding to the nitrile group of the PAN molecule at 2242 cm^{-1} can also serve as a satisfactory reference.

25
30

As shown in Figure 3, a comparison of the ratios of oxidation to reference peaks in the spectra of the two exposed yarns shows that degree of oxidation of the modified polymer of Example 2 is between 60% to 70% that of the conventional yarn.

35

- 14 -

Greater concentrations and finer particle size dispersion of Fe_2O_3 increase the resistance of PAN to oxidation.

5 CHARACTERISTIC SHRINKAGE RATE TEST

A test was devised to assess the susceptibility of polyacrylonitrile and other polymers to shrinkage under extreme conditions. This test involves measuring the shrinkage rate, in a combustion flue gas environment, of a
10 yarn formed from the polymer. This test is described in detail below.

The yarn to be tested preferably has a breaking strength of approximately 20 N and is of 5 metres (or
15 greater) in length. In the test, one end of the yarn is attached to a fixed mounting point on the floor of a duct or filter chamber of the flue gas cleaning system. From this mounting point, the yarn travels vertically upwards for most of its length. At its upper reaches, the yarn is
20 draped over a pulley and tied to a small weight. This weight applies a small tensile force of preferably no more than 2% of the ultimate tensile strength of the yarn. The pulley is attached to the shaft of a rotary position sensor that will turn freely as the length of the yarn
25 changes. The diameter of the pulley is chosen so that the sum of the frictional torques applied to the pulley shaft by its bearings, and by the rotary transducer, does not impede the rotation of the pulley or significantly change the constant tension experienced by the yarn under the
30 action of the tensioning weight. The rotary position sensor is preferably chosen so that it can resolve a 0.02% change in the length of the yarn. It must also be capable of withstanding the flue gas conditions for several thousand hours of uninterrupted testing. The output
35 signal from the sensor is preferably connected to an automatic data recording system.

- 15 -

After being installed into the flue gas environment, the length of the test yarn is recorded in the aforementioned manner at regular intervals of preferably 24 hours or shorter over a test period that would preferably extend for a period of at least 5,000 hours (approximately seven months) of flue gas exposure. The temperature of the flue gas environment is also regularly measured and recorded.

10 A record of the length of the test yarn and the temperature of its environment is built up in this way and charted as a function of test time.

Over an initial period of the test that might extend to 1,000 hours or more, it is not uncommon to observe some degree of lengthening of the test yarn due to relaxation of mechanical stresses in the polymer under the applied tension. At a temperature of 125 °C, such extension might be more than 1% of the length of the yarn. Beyond this point, however, the effect of thermo-oxidative degradation of the polymer will become apparent as the test yarn begins to shrink. At this point, it has been commonly (but not exclusively) found that the rate of shrinkage increases over the next thousand hours of the test as the effect of mechanical relaxation subsides and thermally-driven chemical reactions alter the structure of the polymer material. By the time an additional 1,000 to 2,000 hours of testing (at a temperature of 125 °C) have elapsed, it is commonly (but not exclusively) found that the rate of shrinkage becomes approximately constant. When more than 5,000 hours of total test time has elapsed at a temperature of preferably 125 °C or higher, an essentially constant rate of shrinkage is considered to be a characteristic property of the test material under conditions of stress arising from the thermo-oxidative test environment.

- 16 -

In the aforementioned test for shrinkage under real operating conditions, a shrinkage rate for polyacrylonitrile of 0.5% per 1,000 test hours at 125 °C is considered normal. To significantly reduce or prevent shrinkage, the incorporation of a metal oxide additive into such a polymer in the manner of this invention would reduce that rate to preferably less than 0.2% per 1,000 test hours.

The above examples serve to illustrate the principle of the invention only, and are not intended to limit the scope thereof. Various modifications can be made to the materials and methods described in the examples without departing from the spirit and scope of the invention.

In the claims which follow and in the preceding description of the invention, except where the context requires otherwise due to express language or necessary implication, the word "comprise" or variations such as "comprises" or "comprising" is used in an inclusive sense, i.e. to specify the presence of the stated features but not to preclude the presence or addition of further features in various embodiments of the invention

CLAIMS:

1. A filter comprising a polymer material comprising a polymer matrix containing dispersed metal oxide particles.
- 5
2. The filter according to claim 1, wherein the metal oxide is selected from the group consisting of zinc oxide, nickel oxide, iron oxide, copper oxide, cobalt oxide and mixtures thereof.
- 10
3. The filter according to claim 2, wherein the metal oxide is iron oxide.
4. The filter according to claim 3, wherein the metal oxide is ferric oxide.
- 15
5. The filter according to any one of claims 1 to 4, wherein the metal oxide is in the form of particles less than 1 μm in size.
- 20
6. The filter according to claim 5, wherein the metal oxide is in the form of particles less than 500 nm in size.
- 25
7. The filter according to any one of claims 1 to 6, wherein the metal oxide constitutes a maximum of 5% by weight of the polymer material.
8. The filter according to any one of claims 1 to 7, wherein the metal oxide constitutes a minimum of 0.1% by weight of the polymer material.
- 30
9. The filter according to any one of claims 1 to 8, wherein metal oxide constitutes from 0.25% to 3% by weight of the polymer material.
- 35
10. The filter according to any one of claims 1 to 9,

- 18 -

wherein the polymer matrix is selected from the group consisting of polyacrylics, polyesters, polyamides, polyolefins, fluorocarbon fibres and polyphenylene polymers, copolymers and derivatives thereof and mixtures thereof.

11. The filter according to any one of claims 1 to 10, wherein the polymer matrix is a polyacrylonitrile-containing polymer, or a derivative thereof.

12. The filter according to any one of claims 1 to 11, wherein the polymer matrix is polyacrylonitrile (PAN) or a copolymer of acrylonitrile with one or more other monomers.

13. The filter according to claim 11, wherein the polymer matrix is a copolymer of acrylonitrile and methacrylonitrile.

14. The filter according to claim 11 or claim 12, wherein material comprises at least 85% acrylonitrile.

15. The filter according to claim 13, wherein the polymer matrix comprises at least 95% acrylonitrile by weight.

16. The filter according to claim 13, wherein the polymer material comprises at least 99% acrylonitrile by weight.

17. The filter according to any one of claims 11 to 16, wherein the co-monomer content ranges from 0 to 10%, by weight of the polymer material.

18. The filter according to any one of the preceding claims, wherein the average molecular weight of the polymer is between 100,000 and 300,000.

19. The filter according to any one of claims 1 to 18,

- 19 -

wherein the polymer material is in the form of filaments, fibres, yarn, web, fabric, mat, film or sheet, or a combination of these forms.

5 20. The filter according to claim 19, wherein the polymer material is in the form of a flexible fabric, web or mat.

21. A filter formed at least partly from a polymer material comprising:

- 10 - a polymer matrix, and
- a metal oxide, the metal oxide being incorporated into the polymer matrix in an amount to provide a polymer material that has a characteristic shrinkage rate of 0.2% or less per 1000 test hours in a flue gas environment of
15 approximately 125 °C.

22. A filter formed at least partly from a polymer material comprising:

- a polymer matrix, and
20 a metal oxide, the metal oxide being incorporated into the polymer matrix in an amount to provide a polymer material that has a characteristic shrinkage rate that is 40% or less compared to the characteristic shrinkage rate of the polymer material without the metal oxide measured over a
25 test period of 1000 hours in a flue gas environment at approximately 125 °C.

23. Use of a polymer material comprising:

- a polymer matrix selected from the group consisting of
30 polyacrylics, polyesters, polyamides, polyolefins, polyaramids, fluorocarbon fibres and polyphenylene polymers, co-polymers and derivatives thereof, and mixtures thereof, and
- a metal oxide,
35 in an environment having a temperature of at least 100°C.

24. Use according to claim 23, wherein the environment is

- 20 -

a flue gas environment.

25. Use of a polymer material comprising a polymer matrix and a metal oxide in the manufacture of a filter.

5

26. A method of forming a filter, the method comprising the steps of:

- providing a polymer matrix;
- incorporating particulate metal oxide into the polymer
10 matrix;
- casting or spinning the product into a film or a fibre;
and
- forming the film or fibre into a filter material.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/AU03/00726

A. CLASSIFICATION OF SUBJECT MATTER												
Int. Cl. ⁷ : B01D 039/16												
According to International Patent Classification (IPC) or to both national classification and IPC												
B. FIELDS SEARCHED												
Minimum documentation searched (classification system followed by classification symbols) SEE ELECTRONIC DATA BASE BELOW												
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched												
Electronic data base consulted during the international search (name of data base and, where practicable, search terms used) DWPI/IPC B01D 039/16 and Keywords (Oxide+)												
C. DOCUMENTS CONSIDERED TO BE RELEVANT												
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.										
X	Derwent Abstract Accession No 2001-074952/09 Class A97 D22 F07 J01 JP 2000312809-A (TORAY IND INC) See whole document	1-26										
X	Derwent Abstract Accession No 2001-105543/12 Class A88E32 JP 2000273324 -A (TOYO ROKI SEIZO KK) See whole document.	1-26										
X	EP 0920897 A (Toda Kogyo Corp.) 9 June 1999 See whole document.	1-26										
☒ Further documents are listed in the continuation of Box C ☒ See patent family annex												
* Special categories of cited documents: <table border="0"> <tr> <td>"A" document defining the general state of the art which is not considered to be of particular relevance</td> <td>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</td> </tr> <tr> <td>"E" earlier application or patent but published on or after the international filing date</td> <td>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone</td> </tr> <tr> <td>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</td> <td>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art</td> </tr> <tr> <td>"O" document referring to an oral disclosure, use, exhibition or other means</td> <td>"&" document member of the same patent family</td> </tr> <tr> <td>"P" document published prior to the international filing date but later than the priority date claimed</td> <td></td> </tr> </table>			"A" document defining the general state of the art which is not considered to be of particular relevance	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention	"E" earlier application or patent but published on or after the international filing date	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone	"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art	"O" document referring to an oral disclosure, use, exhibition or other means	"&" document member of the same patent family	"P" document published prior to the international filing date but later than the priority date claimed	
"A" document defining the general state of the art which is not considered to be of particular relevance	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention											
"E" earlier application or patent but published on or after the international filing date	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone											
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art											
"O" document referring to an oral disclosure, use, exhibition or other means	"&" document member of the same patent family											
"P" document published prior to the international filing date but later than the priority date claimed												
Date of the actual completion of the international search 3 July 2003		Date of mailing of the international search report 17 JUL 2003										
Name and mailing address of the ISA/AU AUSTRALIAN PATENT OFFICE PO BOX 200, WODEN ACT 2606, AUSTRALIA E-mail address: pct@ipaaustralia.gov.au Facsimile No. (02) 6285 3929		Authorized officer G. CARTER Telephone No : (02) 6283 2154										

INTERNATIONAL SEARCH REPORT

International application No.

PCT/AU03/00726

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO94/11556 A (Hoechst Celanese Corporation) 26 May 1994 See whole document .	1-26

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT/AU03/00726

This Annex lists the known "A" publication level patent family members relating to the patent documents cited in the above-mentioned international search report. The Australian Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

Patent Document Cited in Search Report		Patent Family Member
JP	2000312809	NIL
JP	2000273324	NIL
EP	09200897	NIL
WO	94/11556	NIL
		END OF ANNEX