



(51) International Patent Classification:

A61K 9/48 (2006.01) *A61K 47/36* (2006.01)
A61K 31/765 (2006.01) *A61P 1/10* (2006.01)
A61K 33/00 (2006.01)

(21) International Application Number:

PCT/US2018/035506

(22) International Filing Date:

31 May 2018 (31.05.2018)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

62/513,952 01 June 2017 (01.06.2017) US

(71) Applicants: STC.UNM [US/US]; Lobo Rainforest Building, 101 Broadway Blvd., Suite 1100, Albuquerque, New Mexico 87102 (US). SWINBURNE UNIVERSITY OF TECHNOLOGY [AU/AU]; John Street, Hawthorn, Victoria 3122 (AU).

(72) Inventors: CANAVAN, Heather; Lobo Rainforest Building, Darnell Leon Cuylear, Albuquerque, New Mexico 87102 (US). NGUYEN, Phuong A.H.; Lobo Rainforest Building, 101 Broadway Blvd., NE, Suite 1100, Albuquerque, New Mexico 87102 (US). MCARTHUR, Sal-

ly; John St., Hawthorne, Victoria 3122 (AU). CUYLEAR, Darnell, Leon; Lobo Rainforest Building, 101 Broadway Blvd., NE, Suite 1100, Albuquerque, New Mexico 87102 (US).

(74) Agent: VOGT, Keith, A.; Vogt IP, Suite 200, 1033 South Blvd., Oak Park, Illinois 60302 (US).

(81) Designated States (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JO, JP, KE, KG, KH, KN, KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM,

(54) Title: BUBBLYTE




FIG. 2

(57) Abstract: A preparation comprised of one or more pellets having an outer shell and core. The outer shell is made of dissolvable material and said core containing poly (ethylene glycol).

TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW,
KM, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

— *of inventorship (Rule 4.17(iv))*

Published:

— *with international search report (Art. 21(3))*

TITLE

BUBBLYTE

RELATED APPLICATIONS

[0001] This application claims the benefit of U.S. Provisional Application

5 No. 62/513,952 filed on June 1, 2017 and herein incorporated by reference.

STATEMENT REGARDING FEDERALLY SPONSORED

RESEARCH & DEVELOPMENT

[0002] This invention was made with government support under GM008751

awarded by the National Institutes of Health (NIH). The government has certain

10 rights in the invention.

BACKGROUND OF THE INVENTION

[0003] Colorectal cancer (CRC) is the second leading cause of cancer death in the

United States. It is now the 4th in the top 10 list of the most common types of

cancer in the United States with an estimated 100,000 new cases per year. The

15 most reliable screening method of CRCs is colonoscopy, a procedure that allows

for the visualization and removal of benign polyps that cause 75 to 80% of CRCs.

A complete colonoscopy screening can reduce CRC incidents by 83%, and CRC

mortality rates by 89%.

[0004] Although screening for CRC has been shown to reduce the incidence rate

20 and mortality rate of the disease and is recommended by the CDC, only 58% of

adults from 50-75 are up-to-date with their CRC screening (as of 2013). This

disparity is often attributed to the anxiety surrounding the procedure, as well as the discomfort associated with the procedure.

[0005] In fact, a large proportion of patients and physicians who are interviewed on the reasons why patients do not perform colonoscopy report that patients are
5 afraid of the preparation required for the procedure. Approximately 34% of all patients who do obtain the procedure reported that they experience moderate to significant discomfort in association with the preparation.

[0006] The standard colonoscopy preparation technique is to drink 4L (~1 gallon) of poly(ethylene glycol) electrolyte lavage solution (PEG-ELS) (see Table
10 1) the night prior to the procedure. The mixture is frequently described as foul tasting, with side effects of nausea, vomiting, abdominal bloating, abdominal pain, rectal irritation, etc. Frequently, patients cannot complete their required dose due to these side effects, which leads to incomplete bowel cleansing, poorly visualized colons that can result in insufficient removal of polyps. In some cases,
15 this leads to canceled colonoscopies which must be rescheduled, and the entire process repeated. Table 1 includes bowel preparation products currently on the market, including the four most commonly used preparations: 1) PEG-ELS, 2) SF-PED-ELS (sulfate-free, for patients with sulfa allergy), 3) PEG-ELS with ascorbic acid (vitamin C, for electrolyte balance), and 4) low-volume PEG-3350-SD (1/2
20 the water necessary for prep).

PEG-ELS		SF-PEG-ELS	Low-volume PEG-ELS with ascorbic acid	Low-volume PEG-3350-SD
Brand name	GoLYTELY	NuLYTELY; Trilyte	Moviprep	Miralax
Company (location)	Braintree Laboratories (Braintree, Mass)	Braintree Laboratories	Salix Pharmaceuticals (Raleigh, NC)	Merck (Boston, MA)
Composition	PEG, sodium sulfate, sodium bicarbonate, sodium chloride, potassium chloride	PEG, sodium bicarbonate, sodium chloride, potassium chloride	PEG-3350, sodium sulfate, sodium chloride, ascorbic acid	PEG-3350
Purgative volume/amount; recommended minimum additional fluid (per prescribing information) for FDA approved products)	4 L; none	4 L; none	2 L; 1 L clear liquid	238 g PEG-3350 in 2 L SD; regimens vary
FDA approval	Yes	Yes	Yes	Yes
Average wholesale price, US\$	24.56	26.89 (NuLYTELY) 27.98 (Trilyte)	81.17	10.08
Dosing regimens	Split-dose: 2-3 L day before and 1-2 L day of procedure Single dose: 4L day before	Split-dose: 2-3 L day before and 1-2 L day of procedure Single dose: 4L day before	Split-dose: 1 L day before and 1 L day of procedure Single dose: 2 L day before	Split-dose: 1 L day before and 1 L day of procedure Single dose: 2L day before
Specific comments	Criterion standard; least palatable preparation	More palatable than PEG-ELS	Avoid in patients with glucose-6-phosphate dehydrogenase deficiency	Not balanced ELS; unclear whether electrolyte shifts may occur

Table 1

BRIEF SUMMARY OF THE INVENTION

[0007] In one embodiment, the present invention provides a method, approach and solution that can transfer poly(ethylene glycol) or PEG in a solid form that then dissolves in the stomach to achieve its goals.

5 BRIEF DESCRIPTION OF THE SEVERAL VIEWS OF THE DRAWINGS

[0008] In the drawings, which are not necessarily drawn to scale, like numerals may describe substantially similar components throughout the several views.

Like numerals having different letter suffixes may represent different instances of substantially similar components. The drawings illustrate generally, by way of

10 example, but not by way of limitation, a detailed description of certain embodiments discussed in the present document.

[0009] Figure 1 illustrates an exemplary delivery system for an embodiment of the present invention.

[00010] Figure 2 illustrates drug release for an embodiment of the present
15 invention.

DETAILED DESCRIPTION OF THE INVENTION

[00011] Detailed embodiments of the present invention are disclosed herein;

however, it is to be understood that the disclosed embodiments are merely

20 exemplary of the invention, which may be embodied in various forms. Therefore,

specific structural and functional details disclosed herein are not to be

interpreted as limiting, but merely as a representative basis for teaching one

skilled in the art to variously employ the present invention in virtually any

appropriately detailed method, structure or system. Further, the terms and phrases used herein are not intended to be limiting, but rather to provide an understandable description of the invention.

[00012] In one embodiment, the present invention provides a method, approach
5 and solution that can transfer poly(ethylene glycol) or PEG in a solid form that then dissolves in the stomach to achieve its goals. In a preferred embodiment, the present invention provides a hydrogel pellet as the solid form and is configured to contain PEG-3350. Using a pellet form makes it easier to ingest, without the side effects associated with the unpalatable nature of PEG-3350 in liquid form.

10 [00013] Each individual pellet may be adapted to provide a unit or standard dosage. In a preferred embodiment, the unit dosage contains 17g of PEG 3350, a dosage similar to those found in Miralax, a product used to aid in chronic constipation.

[00014] For use in bowel preparation, a standard dose may consist of a total of
15 around 13 pellets to be ingested by the patient throughout the day with their drink of choice. This dose may be adjusted for variations in patient height and weight, unlike the currently available products. Each pellet may also contain sulfate, 0.518 g of sodium bicarbonate, 0.451 g of sodium chloride, 0.228 g of potassium chloride) to prevent symptoms of dehydration in association with
20 bowel preparation for colonoscopies.

[00015] As shown in Figure 1, a preferred embodiment of the present invention uses a hydrogel pellet as the solid form 100. Hydrogel pellet 100 has a pH-

sensitive shell 110 defining an inner core 120. PEG-3350 200 and other compounds may be located in core 120.

[00016] The outer shell 110 of the hydrogel may be composed of chitosan and alginate, two materials that have been FDA approved in the past due to their biocompatible properties. As shown in Figure 2, chitosan and alginate may be cross-linked to form a mesh 300 that encapsulates the PEG-3350 305.

[00017] In the acidic conditions of the stomach, the gel forming mesh 300 will swell. Swelling causes mesh 300 to widen and PEG-3350 305 will be released for bowel cleansing.

[00018] Chitosan and alginate have been cross-linked in a variety of methods to produce a pH-responsive hydrogel for targeted intestinal drug delivery. This selective pH response permits selective release of the compound. For example, different commonly used drinks (e.g., sodas, carbonated drinks, juices, etc.) and their pH may also be used as triggers. Thus, giving patients freedom to choose a drink of their choice for bowel preparation.

[00019] Pellet size may also be optimized to ensure hydrogels are approximately pill-sized, no larger than the typical over the counter drug found in pharmacies throughout the United States.

[00020] In yet another embodiment, the present invention provides a hydrogel that is pH responsive and will release PEG-3350 at stomach pH levels.

[00021] In yet other embodiments, the present invention provides pellet sizes that are easy to ingest -no larger than the size of over the counter drugs found in

pharmacies throughout the U.S. The embodiment may also contain PEG-3350 with electrolytes that are ideal for bowel cleansing.

[00022] While the foregoing written description enables one of ordinary skill to make and use what is considered presently to be the best mode thereof, those of
5 ordinary skill will understand and appreciate the existence of variations, combinations, and equivalents of the specific embodiment, method, and examples herein. The disclosure should therefore not be limited by the above described embodiments, methods, and examples, but by all embodiments and methods within the scope and spirit of the disclosure.

WHAT IS CLAIMED IS:

1. A preparation comprising: a pellet having an outer shell and core, said outer shell made of a dissolvable material and said core containing PEG-3350.

5 2. The preparation of claim 1 wherein said dissolvable material is a hydrogel.

3. The preparation of claim 2 wherein said hydrogel is composed of chitosan and alginate.

10 4. The preparation of claim 2 wherein said hydrogel is composed of chitosan and alginate which are cross-linked to encapsulate the PEG-3350.

5. The preparation of claim 1 wherein the preparation is pH responsive.

6. The preparation of claim 1 wherein the preparation is pH responsive at a pH of 1-3.

15 7. The preparation of claim 4 further including a plurality of pellets, each of said pellet contains 17g of PEG 3350, sulfate, 0.518 g of sodium bicarbonate, 0.451 g of sodium chloride, and 0.228 g of potassium chloride.

20 8. The preparation of claim 4 wherein the preparation is configured to form a mesh, said mesh swells at a pH of 1-3 to release said PEG-3350 from said core.

9. The preparation of claim 8 wherein the preparation releases said PEG-3350 as the hydrogel swells and the mesh widens causing said PEG-3350 to be released from said core.

10. A preparation comprising: a pellet having an outer shell and core,
5 said outer shell made of a dissolvable material and said core containing poly(ethylene glycol).

11. The preparation of claim 10 wherein said dissolvable material is a hydrogel.

12. The preparation of claim 11 wherein said outer shell of said
10 hydrogel is composed of chitosan and alginate.

13. The preparation of claim 11 wherein said outer shell of the hydrogel is composed of chitosan and alginate which are cross-linked to encapsulate said poly(ethylene glycol).

14. The preparation of claim 10 wherein the preparation is pH
15 responsive.

15. The preparation of claim 10 wherein the preparation is pH responsive at a pH of 1-3.

16. The preparation of claim 13 further including a plurality of pellets, each of said pellet contains 17g of poly(ethylene glycol), sulfate, 0.518 g of
20 sodium bicarbonate, 0.451 g of sodium chloride, and 0.228 g of potassium chloride.

17. The preparation of claim 13 wherein the preparation is configured to swell at a pH of 1-3 to release said poly(ethylene glycol) from said core.

18. The preparation of claim 17 wherein the preparation releases said poly(ethylene glycol) as the hydrogel swells and the mesh widens causing said
5 poly(ethylene glycol) to be released from said core.



19. A method of bowel preparation for colonoscopies comprising the steps of: administering an effective amount of a preparation, said preparation comprising a pellet having an outer shell and core, said outer shell made of a dissolvable material and said core containing poly(ethylene glycol).

10 20. The method of claim 19 wherein said dissolvable material is a hydrogel and said preparation releases said poly(ethylene glycol) as said hydrogel swells and a mesh formed by said hydrogel widens causing said poly(ethylene glycol) to be released from said core.

21. The method of claim 20 further including the step of administering
15 an effective amount of a liquid that triggers the swelling of the mesh formed by said hydrogel.

22. The method of claim 20 further including the step of administering an effective amount of a liquid having a pH that triggers the swelling of the mesh formed by said hydrogel.

20

**FIG. 1****FIG. 2**

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US 2018/035506

A. CLASSIFICATION OF SUBJECT MATTER

A61K 9/48 (2006.01)
A61K 31/765 (2006.01)
A61K 33/00 (2006.01)
A61K 47/36 (2006.01)
A61P 1/10 (2006.01)

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

A61K, A61P

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

ESP@CENET, PATENTSCOPE, PatSearch, PubMed, RUPTO, Reaxys, USPTO

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 2004/091622 A1 (PROGENICS PHARMACEUTICALS, INC.) 28.10.2004, p.10 lines 26-31, p.17 lines 24-30, p.26 lines 26-27, p.27 lines 1-4, 25-30	1-3, 5, 7, 10-12, 14, 16
Y		4, 6, 8, 9, 13, 15, 17-22
Y	US 2014/0010895 A1 (NORGINE BV) 09.01.2014, claim 58, [0407]	19-22
Y	M. RIZWAN et al. PH SENSITIVE HYDROGELS IN DRUG DELIVERY: BRIEF HISTORY, PROPERTIES, SWELLING, AND RELEASE MECHANISM, MATERIAL SELECTION AND APPLICATIONS, POLYMERS, 12.04.2017, 9, 137, p.17, phara 1, fig.. 4b	4, 6, 8, 9, 13, 15, 17, 18, 20-22



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

06 August 2018 (06.08.2018)

Date of mailing of the international search report

20 September 2018 (20.09.2018)

Name and mailing address of the ISA/RU:

Federal Institute of Industrial Property,
 Berezhkovskaya nab., 30-1, Moscow, G-59,
 GSP-3, Russia, 125993
 Facsimile No: (8-495) 531-63-18, (8-499) 243-33-37

Authorized officer

N. Antonova

Telephone No. (8-499) 240-25-91