

AUSTRALIA  
Patents Act 1990

**NOTICE OF ENTITLEMENT**

We **BLOCK DRUG COMPANY, INC.**

of 257 Cornelison Avenue, Jersey City, New Jersey 07302-3198, USA

being the Applicant and Nominated Person, in respect of Application No. 69636/94, entitled "Denture Adhesive" state the following:

Robert C Gasman, Eddie Wong, Hal C Clarke and Hyung-kook Ahn are the actual inventors of the invention the subject of the Application.

The applicant and nominated person is the assignee of the invention from the actual inventors.

The applicant and nominated person is entitled to rely on the application listed in the declaration under Article 8 of the PCT.

Basic Applicants	Application Number	Application Date	Country	Country Code
Robert C Gasman, Eddie Wong, Hal C Clarke and Hyung-kook Ahn	08/076,810	14 June 1993	United States of America	US

The basic application referred to in the declaration under Article 8 of the PCT was the first application made in a Convention country in respect of the invention the subject of the Application.

DATED this 4th day of August 1998

**BLOCK DRUG COMPANY, INC.**  
By their Patent Attorney



**GRIFFITH HACK**

GH REF: P14610AX/TPG



AU9469636

(12) PATENT ABRIDGMENT (11) Document No. AU-B-69636/94  
(19) AUSTRALIAN PATENT OFFICE (10) Acceptance No. 697016

- (54) Title  
DENTURE ADHESIVE
- International Patent Classification(s)  
(51)<sup>5</sup> A61K 006/00 C08K 003/10 C08K 003/18
- (21) Application No. : 69636/94 (22) Application Date : 03.06.94
- (87) PCT Publication Number : WO94/28858
- (30) Priority Data
- |             |           |                             |
|-------------|-----------|-----------------------------|
| (31) Number | (32) Date | (33) Country                |
| 08/076810   | 14.06.93  | US UNITED STATES OF AMERICA |
- (43) Publication Date : 03.01.95
- (44) Publication Date of Accepted Application : 24.09.98
- (71) Applicant(s)  
BLOCK DRUG COMPANY, INC.
- (72) Inventor(s)  
ROBERT C GASMAN; EDDIE WONG; HAL C CLARKE; HYUNG-KOOK AHN
- (74) Attorney or Agent  
GRIFFITH HACK, GPO Box 4154, SYDNEY NSW 2001
- (57) Claim

1. A denture adhesive composition comprising:

(a) a salt comprising (i) a copolymer of (A) a vinyl alkyl ether and (B) maleic anhydride or maleic acid and (ii) a cation from Group IA or Group IIA of the Periodic Table; and

(b) a zinc compound, nonionically associated with said salt.

18. A denture adhesive comprising a mixture of (a) a partially neutralized sodium salt of a copolymer of an alkyl vinyl ether and maleic anhydride or maleic acid and (b) a compound selected from the group consisting of zinc oxide, zinc carbonate, zinc chloride, zinc fluoride and zinc bromide.

19. A method for making a denture adhesive comprising the steps of: (a) preparing a salt of a vinyl alkyl ether/maleic anhydride or acid copolymer with a cation from Group IA or Group IIA of the Periodic Table; and (b) combining the salt with a zinc compound in a nonionic manner to form the denture adhesive compound.



(51) International Patent Classification <sup>5</sup> : A61K 6/00, C08K 3/18, 3/10	A1	(11) International Publication Number: <b>WO 94/28858</b> (43) International Publication Date: 22 December 1994 (22.12.94)
---	----	---

(21) International Application Number: PCT/US94/06327  
(22) International Filing Date: 3 June 1994 (03.06.94)

(30) Priority Data:  
08/076,810 14 June 1993 (14.06.93) US

(71) Applicant: BLOCK DRUG COMPANY, INC. [US/US]; 257  
Cornelison Avenue, Jersey City, NJ 07302-3198 (US).

(72) Inventors: GASMAN, Robert, C.; 60 Kitchell Lake Drive,  
West Milford, NJ 07480 (US). WONG, Eddie; 54-18 90th  
Street, Elmhurst, NY 11373 (US). CLARKE, Hal, C.; 83  
Joan Court, Elmont, NY 11003 (US). AHN, Hyung-kook;  
307 Avenue B, Bayonne, NJ 07002 (US).

(74) Agents: MEILMAN, Edward, A. et al.; Ostrolenk, Faber, Gerb  
& Soffen, 1180 Avenue of the Americas, New York, NY  
10036 (US).

(81) Designated States: AU, BR, CA, JP, KR, NZ, European patent  
(AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC,  
NL, PT, SE).

Published  
With international search report.

(54) Title: DENTURE ADHESIVE

(57) Abstract

A denture adhesive composition contains an adhesive mixture comprising carboxymethyl cellulose and partially neutralized sodium, a salt of an alkyl vinyl ether or maleic acid copolymer that forms crosslinked polymer complex compounds in situ with zinc cations.

- 1 -

## DENTURE ADHESIVE

BACKGROUND OF THE INVENTION1. Field of the Invention

5 This invention relates to denture adhesives and methods of making and using denture adhesives.

2. Description of Related Art

10 Dentures are usually secured in the mouth using creams or powders having adhesive properties. These powders or creams serve both to adhere the dentures to the gums but also to provide a cushion and sealant between the gums and the dentures to permit a comfortable fit.

15 Denture adhesives must have acceptable organoleptic qualities and need to be sufficiently strong so that a daily application of the adhesive is sufficient for a full day's use. But, the adhesive must not prevent or hinder denture removal at the end of the day.

20 Most presently available commercial denture adhesives comprise vinyl alkyl ether/maleic acid (or anhydride) copolymers. This class of compounds was set out as a potential denture adhesive in U.S. Patent No. 3,003,988 to Germann et al., issued October 10, 1961. That patent is directed to synthetic, water sensitized, but water insoluble, materials comprising mixed, partial salts of lower alkyl vinyl ether-maleic anhydride copolymers for stabilizing dentures. The salts mentioned  
25 in the patent are a mixture of (a) calcium and (b) alkalis, including sodium, potassium and quaternary ammonium compounds, in a 1:1 to 5:1 mole ratio. The

SUBSTITUTE SHEET (RULE 26)

calcium and alkali materials are added to the copolymer to form the mixed salt.

Others have adopted the use of calcium in combination with alkali (especially sodium) salts of the copolymer of Germann et al. Examples of formulations using this combination are: U.S. Patent No. 4,980,391 to Kumar et al., issued December 25, 1990; U.S. Patent No. 5,037,924 to Tazi et al.; and U.S. Patent No. 4,910,247 to Haldar et al., issued March 20, 1990. European Patent Application No 406,643, filed June 22, 1990, is directed to aluminum, calcium and sodium salts of a lower alkyl vinyl ether/maleic acid copolymer.

These salts, however, have not proven to be fully effective at securing the denture and are susceptible to "washout," the erosion of the adhesive from under the denture during use. As a result, these formulations provided less than the twelve hours of holding power that denture wearers have begun to demand.

In order to provide additional adhesive and cohesive properties, others have turned to zinc and strontium salts. Examples of these salts are found in, for example, PCT application No. WO 92/22280, published December 23, 1992, assigned to Richardson-Vicks, Inc. (the cations may also include calcium cations, sodium cations or both); U.S. Patent No. 4,758,630 to Shah et al., issued July 19, 1988 (zinc partial salts or strontium partial salts); U.S. Patent No. 5,073,604 to Holeva et al., issued December 17, 1991 (partial calcium salts in combination with either partial zinc or partial strontium salts); PCT application No. WO 92/10988, published July 9, 1992, assigned to Richardson-Vicks, Inc. (the salts may comprise zinc, strontium, sodium, calcium, magnesium, potassium or ammonium cations and

mixtures thereof); and PCT Application No. WO 92/10987, published July 9, 1992, assigned to Richardson-Vicks, Inc. (the salts may include zinc or strontium in combination with sodium and calcium cations).

5           Moreover, PCT Application No. WO 92/10986 is directed to mixed partial salts of lower alkyl vinyl ether-maleic anhydride copolymers. The salts are zinc or strontium cations with calcium cations.

10           Salts of vinyl alkyl ether/maleic acid copolymers have also found use outside the denture adhesive field. U.K. Patent Specification No. 1,492,038 filed September 19, 1974, assigned to Smith & Nephew Research, Ltd., is directed to orthopedic bandages comprising a vinyl alkyl ether/maleic anhydride copolymer with zinc, aluminum or magnesium oxides. U.S. Patent No. 15   4,138,477 to Gaffar, issued February 6, 1979, is directed to mouth odor control using zinc salts of vinyl alkyl ether/maleic anhydride copolymers. Begala, A. & Strauss, U., "Dilatometric Studies of Counterion Binding by 20   Polycarboxylates," J. Phys. Chem., 76, p 254-60 (1972), investigates the volume changes associated with bonding of hydrogen and magnesium ions to, inter alia, a vinyl methyl ether/maleic anhydride copolymer. And Crisp, S, et al., "Zinc Polycarboxylate Cements: A Chemical Study 25   of Erosion and Its Relationship to Molecular Structure," J. Dental Rsch., 55(2), p. 299-308 (1976), reports on magnesium or zinc salts of lower alkyl vinyl ether/maleic acid copolymers.

30           Despite the effort put into improving the properties of the copolymer and the salts derived from the copolymers, these formulations do not provide the full measure of adhesion, cohesion, and resistance to

washout from beneath the denture necessary for a completely successful product.

SUMMARY OF THE INVENTION

5 The principal object of the present invention therefore is to provide a denture adhesive composition having both strong adhesive properties and good washout resistance to provide long holding properties. The denture adhesive must exhibit sufficient tack initially upon contact with oral mucosa and build up cohesive  
10 strength quickly when hydrated with moisture or saliva and be able to resist stresses such as those that occur upon mastication. The denture adhesive must retain its adhesive properties for prolonged periods of time.

15 Another object of the invention is to provide a method for making the denture adhesive composition to achieve in situ zinc bonding.

Still another object of the invention is to provide a method for using the denture adhesive to secure dentures in the mouth.

20 Additional objects and advantages of the invention will be set forth in part in the description that follows, and in part will be obvious from this description, or may be learned by practice of the invention. The objects and advantages of the invention  
25 may be realized and attained by means of the instrumentalities and combinations particularly pointed out in the appended claims.

To achieve the foregoing objects and in accordance with the purpose of the invention, as embodied  
30 and broadly described herein, the invention provides a denture adhesive composition comprising: (a) a salt of a vinyl alkyl ether/maleic anhydride or acid copolymer and

a cation from Group I or Group II of the Periodic Table; and (b) a zinc compound, nonionically associated with the salt.

To further achieve the foregoing objects and in accordance with the purpose of the invention, the invention further provides a method for making a denture adhesive compound comprising the steps of: (a) preparing a salt of a vinyl alkyl ether/maleic anhydride or acid copolymer with a cation from Group I or Group II of the Periodic Table; (b) combining the salt with a zinc compound in a nonionic manner in a suitable carrier material to form the denture adhesive compound.

To further achieve the foregoing objects and in accordance with the purpose of the invention, as embodied and broadly described herein, the invention provides a method for adhering dentures to gums comprising the steps of: (a) treating the dentures with a denture adhesive composition comprising: (i) a salt of a vinyl alkyl ether/maleic anhydride or acid copolymer and a cation from Group I or Group II of the Periodic Table; and (ii) a zinc compound, nonionically associated with the salt; and (b) placing the dentures in close proximity to gum tissue thereby engaging the denture adhesive composition.

Other features and advantages of the present invention will become apparent from the following description of the invention which refers to the accompanying drawings.

#### DESCRIPTION OF THE PREFERRED EMBODIMENTS

Reference will now be made in detail to the presently preferred embodiments of the invention.

The denture adhesive composition of the invention is most suitable in liquid and cream forms.

The composition preferably contains both active and nonactive ingredients.

5 The active ingredients are cations, alkyl vinyl ether/maleic anhydride copolymer salts, preferably with 70-40% unreacted carboxylic acid groups, carboxy methyl cellulose gum, zinc oxide and/or zinc salts organic or inorganic zinc salts).

10 The copolymer of the invention is a vinyl alkyl ether/maleic acid or anhydride copolymer. The preferred copolymer is a copolymer available from GAF corporation, Wayne, New Jersey, under the trademark "GANTREZ" in two forms: the acid form is sold under the trademark GANTREZ S" Series, and the preferred type of acid is identified as "GANTREZ S95" or "GANTREZ S97." The anhydride form is  
15 sold as the "GANTREZ AN" Series, and the preferred anhydride is "GANTREZ AN169."

20 The preferred alkali cations are alkali cations, although cations from Group I and Group II of the Periodic Table may be selected. Acceptable cations include sodium, potassium, magnesium, calcium, and strontium. Preferred are sodium and potassium, and most preferred is sodium.

25 When the salt is prepared, the cations associate with ionic bonding sites on the copolymer and are neutralized. Preferably less than all the ionic bonding sites on the copolymer are used. More preferably, the cations occupy from about 5% to about 60%, and most preferably from about 20% to about 60% of the bonding sites on the copolymer, leading to a  
30 "partially neutralized" copolymer. 40% partial neutralization is most preferred.

Preferably, the salt comprises from about 10% to about 50% by weight of the total denture adhesive

composition. More preferably the salt comprises from about 20% to about 40% of the final denture adhesive composition and most preferably about 30% by weight of the denture adhesive composition.

5 Carboxymethyl cellulose gum is used for sensitizing the adhesive to moisture, enhancing the cohesive properties of the formulation and improving gel strength. Acceptable substitutes may be selected from carboxyethyl cellulose and carboxypropyl cellulose  
10 materials. The carboxymethyl cellulose gum preferably comprises from about 10% to about 30% by weight of the denture adhesive composition, more preferably from about 15% to about 25% and most preferably about 20% of the composition. The carboxymethyl cellulose may be present  
15 in the form of a full or partial salt, preferably a sodium salt. During use, zinc from the added salt of the invention will replace at least some of the sodium and from crosslinks in the carboxymethyl cellulose or crosslinks with the copolymer.

20 Acceptable zinc compounds include oxides, carbonates and halides. While other anions of Group VI of the Periodic Table may be used in place of oxides, oxides are preferred for their ease of handling and organoleptic qualities. Preferred halides include  
25 fluorides, chlorides and bromides. Chlorides are most preferred.

Nonactive ingredients present in the denture adhesive include thickening agents and carriers, such as petrolatum and mineral oil, flavors, colors,  
30 preservatives, thickeners and nontoxic anticaking agents such as silica, magnesium stearate and talc. Acceptable nonactive ingredients, and the appropriate levels at which the ingredients should be present in a particular

formulation for a specific purpose are well known in the art.

5 For a cream base, the mineral oil or other carrier preferably comprises from about 10% to about 30% by weight of the denture adhesive, preferably from about 15% to about 25% by weight. Petrolatum or some other thickening agent comprises from about 15% to about 30% by weight of the denture adhesive composition, preferably from about 20% to about 30% by weight.

10 Other nonactive ingredients comprise colorants, flavors and preservatives and may comprise up to about 10% by weight of the denture adhesive composition.

15 In use, the partially neutralized copolymer salt will provide the initial tack quickly when it comes in contact with moisture in the oral mucosa. When it is hydrated with moisture or saliva, zinc oxide and/or the other zinc salts present in the oil phase of the adhesive become available to form zinc copolymer complexes. Zinc from zinc oxide will react more favorably with acidic carboxylic acid groups by means of an acid-base interaction while the zinc from zinc halide salts would be more effective in replacing sodium cations from carboxylate groups.

25 The method of making the denture adhesive composition is a two-step process of making the copolymer salt and then incorporating the salt into the denture adhesive composition.

30 The copolymer salt is made by heating a suitable solvent, such as water (deionized or distilled water is preferable) to a temperature sufficient to hasten dissolution of the copolymer in the solvent. In the case of methyl vinyl ether/maleic anhydride copolymer being dissolved in water, the temperature is about 90°C.

Separately, a donor solution for the cation can be prepared. Preferably the solvent for the solution is identical to, or compatible with, the solvent for the copolymer. Preferably the donor solution comprises the cation or cations to be used to form the salt and an initiator, such as a Lewis acid or base, to facilitate the partial substitution of the cation for the hydrogen in the copolymer. In the event that the cation is sodium or potassium, suitable solutions would include solutions of sodium or potassium hydroxide, compounds that provide both the cation and a Lewis base.

After the copolymer solution has cooled sufficiently, the cation donor solution and the copolymer solution are allowed to react. The product is dried in a drier to form a dried material that is then milled to a small size (about 100 mesh) and further processed to form the denture adhesive of the invention using techniques well known in the art.

The following non-limiting examples will serve to illustrate the invention.

#### Example 1

3.25 Kg of purified water were heated in a reaction vessel equipped with a high speed stirrer to 90°C. 260 grams of methyl vinyl ether/maleic anhydride copolymer were slowly added to the reaction vessel and mixing was continued until a clear solution was obtained. The solution was then cooled to 65-75°C.

7.41% (by weight) NaOH solution was prepared in a separate container. When the temperature of the copolymer solution reached 65-75°C., 539.8 grams of 7.41% NaOH solution was added while mixing at high speed (to prevent localized reaction).

- 10 -

The combination was then mixed for 15 minutes after the addition of the NaOH solution. The sodium salt of methyl vinyl ether/maleic anhydride copolymer was then transferred to a series of shallow steel drying trays, and the trays were placed in a hot air convection oven at 75°C. for 18-20 hours. The dried sodium salt was then milled through a suitable mill. The milled salt is then screened through a 100 mesh sieve. The powder had a bulk density of about 0.5 - 0.9 g/cc and the pH of one percent solution is 4-5. This salt was identified as a 30% Na partial salt of MVE/MA copolymer.

#### Example 2

3.25 kg purified water was heated in a reaction vessel equipped with a high speed stirrer to 90°C. 248.9 g methyl vinyl ether/maleic anhydride copolymer was slowly added to the reaction vessel, and mixing was continued until a clear solution was obtained. The heat was then turned off and the solution was cooled to 65-75°C.

In a separate container, a 9.26% NaOH solution was prepared. 551.1 g of the NaOH solution were slowly added to the cooled solution while mixing. Mixing was continued for 15 minutes.

The sodium salt/copolymer solution was then transferred to shallow stainless steel drying trays and placed in a hot air convection oven at 75°C. for 18-20 hours. The dried sodium Gantrez salt was then milled through a suitable mill. The milled salt is then screened through a 100 mesh sieve. The powder had a bulk density of about 0.5 to 0.9 g/cc, and the pH of a one percent solution was 4-6. The salt was a 40% Na partial salt of MVE/MA copolymer.

Example 3

3.25 kg purified water was heated in a reaction vessel equipped with a high speed stirrer to 90°C. 238.8 g methyl vinyl ether/maleic anhydride copolymer was slowly added to the reaction vessel and mixing was continued until a clear solution was obtained. The heat was then turned off and the solution was cooled to 65-75°C. In a separate container, a 10.91% NaOH solution was prepared. 561.2 g of the NaOH solution were slowly added to the cooled solution while mixing. Mixing was continued for 15 minutes.

The sodium salt/copolymer solution was then transferred to shallow stainless steel drying trays and placed in a hot air convection oven at 75°C. for 18-20 hours. The dried sodium salt is then milled through a suitable mill. The milled salt is then screened through a 100 mesh sieve. The powder would have a bulk density of about 0.5 to 0.9 g/cc, and the pH of a one percent solution is 5-7. The salt is a 50% Na partial salt of MVE/MA copolymer.

Example 4

3.25 kg purified water was heated in a reaction vessel equipped with a high speed stirrer to 90°C. 229.4 g methyl vinyl ether/maleic anhydride copolymer was slowly added to the reaction vessel and mixing was continued until a clear solution was obtained. The heat was then turned off and the solution was cooled to 65-75°C. In a separate container, a 12.37% NaOH solution was prepared. 570.4 g of the NaOH solution were slowly added to the cooled solution while mixing. Mixing was continued for 15 minutes.

The sodium salt/copolymer solution was then transferred to shallow stainless steel drying trays and placed in a hot air convection oven at 75°C. for 18-20 hours. The dried sodium salt is then milled through a suitable mill. The milled salt is then screened through a 100 mesh sieve. The powder would have a bulk density of about 0.5 to 0.9 g/cc, and the pH of a one percent solution is 6-8. The salt is a 60% Na partial salt of MVE/MA copolymer.

10

Example 5

Denture adhesive creams were prepared using the sodium salts of Examples 1-4. The respective salts were blended with the other ingredients in Table 1 in the following manner.

15

Mineral Oil was heated to a temperature of about 165°F. Petrolatum of about the same temperature was added to the mineral oil and blended until a uniform consistency was reached. Sodium carboxymethyl cellulose (CMC), colorant, zinc oxide, zinc chloride and flavoring were added to the mixture, as appropriate, while the mixture slowly cooled to about 120°F. The respective salts were added at about 120°F. The combination was then cooled to room temperature and tested for shear strength.

20

25

The shear strength was measured as follows: three homogeneously mixed samples of adhesive/water combinations were prepared at weight ratios of 1:1, 1:0.75 and 1:0.5. Each combination was spread on about 1 square inch of a separate transparent acrylic slide. A second slide with 3/8" diameter hole in one end was placed over the first slide. 20 lbs. pressure was placed on the slide and was held at that level for 5 seconds.

30

The slides were set aside for hydration for about 1 or about 5 minutes.

20 lbs. pressure was again applied for 5 seconds, and the shear strength was measured on an Instron Model 1122 machine. The results of the measurements were averaged. The results at 1 minute and at 5 minutes hydration are reported in Table 1.

#### Example 6

As a comparison to Example 5, commercial denture adhesives were tested for shear strength. The results are shown in Table 2.

Table 1

Test Formulation Number

Ingredient	1	2	3	4	5	6
Mineral Oil	23.0	19.0	16.5	16.5	16.5	20.0
Petrolatum	22.0	26.0	27.0	27.0	28.0	26.0
Colorant	0.05	0.05	0.05	0.05	0.05	0.05
MC (sodium)	19.0	19.0	20.0	20.0	19.0	19.0
30% Na - Gantrez Salt	29.5	-	-	-	-	-
40% Na Gantrez Salt	-	29.5	-	-	30.0	29.5
50% Na Gantrez Salt	-	-	30.0	-	-	-
60% Na Gantrez Salt	-	-	-	30.0	-	-
Zinc Oxide	6.0	6.0	6.0	6.0	3.0	5.0
Zinc Chloride	-	-	-	-	3.0	-
Preservative	0.05	0.05	0.05	0.05	0.05	0.05
Flavor	0.4	0.4	0.4	0.4	0.4	0.4
Shear (1 minutes) g/in <sup>2</sup>	715	953	1180	1816	1135	1249
Shear (5 minute) g/in <sup>2</sup>	1498	2088	2361	2542	1385	2043

TABLE 2

Shear Rate	Commercial Formulation U.S. Pat. 3,003,988	Commercial Formulation U.S. Pats. 4,758,630 5,073,604
5 Shear (1 minute) g/in <sup>2</sup>	397	1158
Shear (5 minutes) g/in <sup>2</sup>	658	1271

10 The purpose of the above description is to illustrate some embodiments of the present invention without implying a limitation. It will be apparent to those skilled in the art that various modifications and variations may be made in the apparatus or procedure of the invention without departing from the scope or spirit  
15 of the invention.

Although the present invention has been described in relation to particular embodiments thereof, many other variations and modifications and other uses will become apparent to those skilled in the art. It is  
20 preferred, therefore, that the present invention be limited not by the specific disclosure herein, but only by the appended claims.

THE CLAIMS DEFINING THE INVENTION ARE AS FOLLOWS:

1. A denture adhesive composition comprising:

5 (a) a salt comprising (i) a copolymer of (A) a vinyl alkyl ether and (B) maleic anhydride or maleic acid and (ii) a cation from Group IA or Group IIA of the Periodic Table; and

(b) a zinc compound, nonionically associated with said salt.

10 2. The denture adhesive of claim 1, wherein said cation is selected from the group consisting of: sodium, potassium, magnesium, calcium, and strontium cations.

15 3. The denture adhesive of claim 2, wherein said cation is selected from the group consisting of sodium and potassium.

20 4. The denture adhesive of claim 1, wherein the copolymer is an alkali metal salt or methyl vinyl ether-co-maleic acid.

25 5. The denture adhesive of claim 1, wherein the copolymer is partially neutralised.

6. The denture adhesive of claim 5, wherein the copolymer is from about 5% to about 60% neutralized.

30 7. The denture adhesive of claim 6, wherein the copolymer is from about 20% to about 60% neutralized.



8. The denture adhesive of claim 1, wherein said salt comprises from about 10% to about 50% by weight of the total denture adhesive composition.

5 9. The denture adhesive of claim 8, wherein the salt comprises from about 20% to about 40% of the denture adhesive composition.

10 10. The denture adhesive of claim 9, wherein the salt comprises about 30% by weight of the denture adhesive.

15 11. The denture adhesive of claim 1, further comprising carboxy methyl cellulose gum.

12. The denture adhesive of claim 11, wherein said carboxy methyl cellulose gum comprises from about 10% to about 30% by weight of the denture adhesive.

20 13. The denture adhesive of claim 12, wherein said carboxy methyl cellulose gum comprises from about 15% to about 25% by weight of the denture adhesive.

25 14. The denture adhesive of claim 13, wherein said carboxy methyl cellulose gum comprises about 20% by weight of the composition.

30 15. The denture adhesive of claim 1, wherein said zinc compound is selected from the group consisting of oxides and halides.



16. The denture adhesive of claim 15, wherein said zinc compound is selected from the group consisting of fluorides, chlorides and bromides.

17. The denture adhesive of claim 16, wherein said zinc compound is zinc chloride.

5 18. A denture adhesive comprising a mixture of (a) a partially neutralized sodium salt of a copolymer of an alkyl vinyl ether and maleic anhydride or maleic acid and (b) a compound selected from the group consisting of zinc oxide, zinc carbonate, zinc chloride, zinc fluoride and zinc bromide.

5 19. A method for making a denture adhesive comprising the steps of: (a) preparing a salt of a vinyl alkyl ether/maleic anhydride or acid copolymer with a cation from Group IA or Group IIA of the Periodic Table; and (b) combining the salt with a zinc compound in a nonionic manner to form the denture adhesive compound.

20. The method of claim 19 wherein said copolymer comprises maleic anhydride.

21. The method of claim 19, wherein said copolymer comprises maleic acid.

22. The method of claim 19, wherein said cation is selected from the group consisting of: sodium, potassium, magnesium, calcium, and strontium cations.

SUBSTITUTE SHEET

AMENDED SHEET



23. The method of claim 22, wherein said cation is selected from the group consisting of sodium and potassium.

5           24. The method of claim 23, wherein said cation is sodium.

25. The method of claim 19, wherein the copolymer comprises methyl vinyl ether.

10

26. The method of claim 19, wherein the copolymer is partially neutralized.

15

27. The method of claim 26, wherein the copolymer is from about 5% to about 60% neutralized.

28. The method of claim 27, wherein the copolymer is from about 20% to about 60% neutralized.

20

29. The method of claim 19, wherein said salt comprises from about 20% to about 50% by weight of the total denture adhesive composition.

25

30. The method of claim 29, wherein the salt comprises from about 25% to about 40% of the denture adhesive composition.

30

31. The method of claim 30, wherein the salt comprises about 30% by weight of the denture adhesive.

32. The method of claim 19, further comprising carboxy methyl cellulose gum.



33. The method of claim 32, wherein said carboxy methyl cellulose gum comprises from about 5% to about 55% by weight of the denture adhesive.

34. The method of claim 33, wherein said carboxy methyl cellulose gum comprises from about 15% to about 25% by weight of the denture adhesive.

35. The method of claim 34, wherein said carboxy methyl cellulose gum comprises about 20% by weight of the composition.

36. The method of claim 23, wherein said zinc compound is selected from the group consisting of oxides and halides.

37. The method of claim 36, wherein said zinc compound is selected from the group consisting of fluorides, chlorides and bromides.

38. The method of claim 37, wherein said zinc compound is zinc chloride.

5 39. A method for adhering dentures to gums comprising the steps of: (a) treating the dentures with a denture adhesive composition comprising: (i) a salt of a vinyl alkyl ether/maleic anhydride or acid copolymer and a cation from Group IA or Group IIA of the Periodic Table; and (ii) a zinc compound, nonionically associated with the salt; and (b) placing the dentures in close proximity to gum tissue thereby engaging the denture adhesive composition.

40. The method of claim 39, wherein said salt comprises a partially neutralized sodium salt of a methyl vinyl ether/maleic anhydride copolymer.

5 41. The method of claim 39, wherein said zinc compound is selected from the group consisting of zinc oxide and zinc chloride.

10 42. A denture adhesive, the adhesive being substantially as described herein with reference to Example 5.

15 43. A method for making a denture adhesive, the method being substantially as described herein with reference to any one of Examples 1 to 5.

DATED this 4th day of August 1998

BLOCK DRUG COMPANY, INC.

20

by their Patent Attorneys

GRIFFITH HACK



INTERNATIONAL SEARCH REPORT.

International application No.  
PCT/US94/06327

A. CLASSIFICATION OF SUBJECT MATTER

IPC(5) : A61K 6/00; C08K 3/18, 3/10

US CL : 524/45, 400, 439, 432, 433, 436; 523/120

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 524/45, 400, 439, 432, 433, 436; 523/120

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO, A, WO 92/10986 (RICHARDSON-VICKS INC.) 09 July 1992, see entire document.	1-41
A	WO, A, WO 92/22280 (RICHARDSON-VICKS INC.) 23 December 1992, see entire document.	1-41

Further documents are listed in the continuation of Box C.

See patent family annex.

*A*	document defining the general state of the art which is not considered to be part of particular relevance	*T*	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
*E*	earlier document published on or after the international filing date	*X*	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
*L*	document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*Y*	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
*O*	document referring to an oral disclosure, use, exhibition or other means	*Z*	dependent member of the same patent family
*P*	document published prior to the international filing date but later than the priority date claimed		

Date of the actual completion of the international search

22 JULY 1994

Date of mailing of the international search report

22 SEP 1994

Name and mailing address of the ISA/US  
Commissioner of Patents and Trademarks  
Box PCT  
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

LaVONDA DEWITT

Telephone No. (703) 308-2351