



- (51) **International Patent Classification:**
C09K 8/03 (2006.01) *E21B 43/22* (2006.01)
C09K 8/04 (2006.01)
- (21) **International Application Number:**
PCT/US2013/048940
- (22) **International Filing Date:**
1 July 2013 (01.07.2013)
- (25) **Filing Language:** English
- (26) **Publication Language:** English
- (30) **Priority Data:**
61/667,179 2 July 2012 (02.07.2012) US
61/787,807 15 March 2013 (15.03.2013) US
61/789,263 15 March 2013 (15.03.2013) US
- (71) **Applicant:** **M-I L.L.C.** [US/US]; 5950 North Course Drive, Houston, Texas 77072 (US).
- (72) **Inventors:** **ARIAS PRADA, Jorge**; 21415 Cimarron Pkwy, Katy, Texas 77450 (US). **YOUNG, Steven Philip**; 14418 Laumar Court, Cypress, Texas 77429 (US). **GUO, Quanxin**; 5939 Union Springs, Sugar Land, Texas 77479 (US). **MOFFITT, John D.**; 1423 Pinecroft Drive, Sugar Land, Texas 77498 (US).
- (74) **Agents:** **HINKLEY, Sara K.M.** et al.; 10001 Richmond Avenue, IP Administration Center of Excellence, Room 4720, Houston, Texas 77042 (US).

- (81) **Designated States** (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.
- (84) **Designated States** (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) **Title:** ENHANCED WELLBORE STRENGTHENING SOLUTION

(57) **Abstract:** Wellbore fluid compositions containing a base fluid; at least one synthetic fiber; and a particulate solid are provided. In another aspect, methods of reducing loss of wellbore fluid into and strengthening of a formation are provided, including: introducing into the wellbore a fluid composition comprising one or more synthetic fibers and one or more particulate solids.



ENHANCED WELLBORE STRENGTHENING SOLUTION

BACKGROUND

[0001] During the drilling of a wellbore, various fluids are typically used in the well for a variety of functions. The fluids may be circulated through a drill pipe and drill bit into the wellbore, and then may subsequently flow upward through the wellbore to the surface. During this circulation, the drilling fluid may act to remove drill cuttings from the bottom of the hole to the surface, to suspend cuttings and weighting material when circulation is interrupted, to control subsurface pressures, to maintain the integrity of the wellbore until the well section is cased and cemented, to isolate the fluids from the formation by providing sufficient hydrostatic pressure to prevent the ingress of formation fluids into the wellbore, to cool and lubricate the drill string and bit, and/or to maximize penetration rate.

[0002] Wellbore fluids may also be used to provide sufficient hydrostatic pressure in the well to prevent the influx and efflux of formation fluids and wellbore fluids, respectively. When the pore pressure (the pressure in the formation pore space provided by the formation fluids) exceeds the pressure in the open wellbore, the formation fluids tend to flow from the formation into the open wellbore. Therefore, the pressure in the open wellbore is typically maintained at a higher pressure than the pore pressure. While it is highly advantageous to maintain the wellbore pressures above the pore pressure, on the other hand, if the pressure exerted by the wellbore fluids exceeds the fracture resistance of the formation, a formation fracture and thus induced mud losses may occur. Further, with a formation fracture, when the wellbore fluid in the annulus flows into the fracture, the loss of wellbore fluid may cause the hydrostatic pressure in the wellbore to decrease, which may in turn also allow formation fluids to enter the wellbore. As a result, the formation fracture pressure typically defines an upper limit for allowable wellbore pressure in an open wellbore while the pore pressure defines a lower limit. Therefore, a major constraint on well design and selection of drilling fluids is the balance between varying pore pressures and formation fracture pressures or fracture gradients though the depth of the well.

[0003] Wellbore fluids are circulated downhole to remove rock, and may deliver agents to combat the variety of issues described above. Fluid compositions may be water- or oil-based and may comprise weighting agents, surfactants, proppants, viscosifiers, fluid loss additives, and polymers. However, for a wellbore fluid to perform all of its functions and allow wellbore operations to continue, the fluid must stay in the borehole. Frequently, undesirable formation conditions are encountered in which substantial amounts or, in some cases, practically all of the wellbore fluid may be lost to the formation. For example, wellbore fluid can leave the borehole through large or small fissures or fractures in the formation or through a highly porous rock matrix surrounding the borehole.

[0004] Lost circulation is a recurring drilling problem, characterized by loss of drilling mud into downhole formations. However, in addition to drilling fluids, lost circulation may remain an issue for other wellbore fluids such as including completion, drill-in, production fluid, etc. Fluid loss can occur naturally in earthen formations that are fractured, highly permeable, porous, cavernous, or vugular. These earth formations can include shale, sands, gravel, shell beds, reef deposits, limestone, dolomite, and chalk, among others.

[0005] Lost circulation may result from induced pressure during drilling. Specifically, induced mud losses may occur when the mud weight, required for well control and to maintain a stable wellbore, exceeds the fracture resistance of the formations. A particularly challenging situation arises in depleted reservoirs, in which the drop in pore pressure weakens hydrocarbon-bearing rocks, but neighboring or inter-bedded low permeability rocks, such as shales, maintain their pore pressure. This can make the drilling of certain depleted zones impossible because the mud weight required to support the shale exceeds the fracture resistance of nearby zones composed of weakly consolidated sands and silts. Another unintentional method by which lost circulation can result is through the inability to remove low and high gravity solids from fluids. Without being able to remove such solids, the fluid density can increase, thereby increasing the hole pressure, and if such hole pressure exceeds the formation fracture pressure, fractures and fluid loss can result.

[0006] Various methods have been used to restore circulation of a drilling fluid when a lost circulation event has occurred, particularly the use of lost circulation material (LCM) to seal or block further loss of circulation. These materials may generally be classified into several categories: surface plugging, interstitial bridging, and/or combinations thereof. In addition to traditional LCM pills, polymers that crosslink or absorb fluids and cement or gunk squeezes have also been employed.

[0007] Accordingly, there exists a continuing need for developments for new LCM treatments that may be used during a lost circulation event so that circulation may be more readily resumed.

SUMMARY

[0008] This summary is provided to introduce a selection of concepts that are further described below in the detailed description. This summary is not intended to identify key or essential features of the claimed subject matter, nor is it intended to be used as an aid in limiting the scope of the claimed subject matter.

[0009] In one aspect, embodiments of the present disclosure are directed to wellbore fluid compositions containing a base fluid; at least one synthetic fiber; and a particulate solid.

[0010] In another aspect, embodiments of the present disclosure are directed to methods of strengthening a wellbore or reducing fluid loss in a downhole formation that include: preparing a fluid composition, wherein the fluid loss composition contains a base fluid, one or more synthetic fibers, and one or more particulate solids; and emplacing the fluid loss composition in an interval of the downhole formation.

[0011] In another aspect, embodiments of the present disclosure are directed to methods of strengthening a wellbore or reducing fluid loss into a downhole formation that include: introducing into the wellbore a fluid composition comprising one or more synthetic fibers; and introducing a second fluid composition comprising one or more particulate solids.

[0012] Other aspects and advantages of the invention will be apparent from the following description and the appended claims.

DETAILED DESCRIPTION

- [0013]** Embodiments disclosed herein relate to engineered fluid loss control and wellbore strengthening compositions. In particular, embodiments disclosed herein relate to fluid compositions that may enter weakly consolidated intervals of the formation, leaving behind a filtercake, plug, or seal that reduces the loss of fluids into the formation.
- [0014]** By plugging porous or vugular zones of the formation, fluid compositions containing engineered combinations of fibrous materials may provide an immediate blockage, preventing further fluid loss and facilitating further drilling operations. By utilizing the unique properties of three-dimensional shapes of the fibrous materials and the combination of fiber types, the materials may interact synergistically to form a seal that arrests the flow of wellbore fluids into the formation. As used herein, the terms “fiber” and “fibrous” are used to denote a high aspect ratio molecular or macromolecular structure, which may have a length greater than either its diameter or width.
- [0015]** Without being limited by any particular theory, it is believed that as fibrous materials present in the fluid composition enter fractures in the formation, the fibers trap and entangle other particles present in the surrounding fluid, creating an impermeable barrier that prevents further fluid loss to the formation. These fibers may act to create a heterogeneous three-dimensional network that can trap particulates of varying sizes, generating a filtercake that prevents fluid flow in or out of the wellbore. Because of the interweaving of the network created by synthetic fibers and particulate solids, a synergistic effect is achieved where reduced amounts of each of the individual components are necessary to reduce fluid losses downhole and/or strengthen the formation. In addition, the overall reduction of materials incorporated into the fluids allows the formulation of a wellbore fluid effective in preventing fluid loss and/or strengthen the formation that is still pumpable through standard delivery means such as drill strings and coiled tubing, as opposed to specialized delivery methods normally required to emplace concentrated slurries in thief zones or fluid loss sites.
- [0016]** In embodiments, the fluid composition may include a synthetic fiber and a particulate solid. In other embodiments, fluid compositions may include a number of

other additives known to those of ordinary skill in the art of wellbore fluid formulations, such as wetting agents, viscosifiers, surfactants, dispersants, interfacial tension reducers, pH buffers, mutual solvents, thinners, thinning agents, gelling agents, rheological additives and cleaning agents.

[0017] In some embodiments, wellbore fluid compositions in accordance with the instant disclosure may be applied to an interval of a wellbore as a fluid “pill.” As used herein, the term “pill” is used to refer to a relatively small quantity (typically less than 200 bbl) of a special blend of wellbore fluid to accomplish a specific task that the regular wellbore fluid cannot perform. In one specific embodiment, the fluid composition may be used to plug thief zones or other regions where circulating fluids are being lost into the formation.

[0018] Upon emplacement within the wellbore, a pill may be defluidized and lose a substantial portion of the base fluid to the formation such materials present in the pill form a plug or seal having sufficient compressive and shear strength for the particular application. Advantageously, upon placing the pill in the wellbore, the pill may be defluidized to lose a substantial portion of the base fluid to the formation such that the fiber blend of the present disclosure may form a plug or seal having sufficient compressive strength for the particular application, and which may increase the tensile strength of the rock.

[0019] Synthetic Fibers

[0020] One or more embodiments may incorporate at least one synthetic fiber type into the fluid loss compositions. In particular embodiments, the synthetic fibers may include high aspect ratio polymeric fibers.

[0021] In some embodiments, the diameter of the synthetic fiber may be varied to alter the flexibility and durability of the resulting seal or plug formed when the fibers contact walls of a downhole formation. For example, in various embodiments, the fiber diameter may range from any lower limit selected from the group of 0.5 μm , 1 μm , 5 μm , and 10 μm to an upper limit selected from the group of 10 μm , 15 μm , 20 μm , and 50 μm .

[0022] In one or more embodiments, synthetic fibers may include, for example, vinyl polymers, ethylene, tetrafluoroethylene, vinylidene fluoride, propylene, butene, 1-butene, 4-methyl-1-pentene, polyaromatics, styrene, p-phenylene-2,6-benzobisoxazole, polyvinyl alcohol, polyacrylic, polyacrylamide, partially hydrolyzed polyacrylamide, polyvinyl acetate, partially hydrolyzed polyvinyl acetate, polyamide, polyurethanes, and combinations thereof. In other embodiments, the synthetic fiber may be a polyolefin that may include, for example, propylene based homopolymers, copolymers, and multi-block interpolymers, and ethylene based homopolymers, copolymers, and multi-block interpolymers, and combinations thereof.

[0023] The one or more synthetic fibers may be added to the fluid composition in an amount ranging from a lower limit selected from the group of 0.25 ppb, 0.5 ppb, 1 ppb, 3 ppb, and 5 ppb to an upper limit selected from the group of 5 ppb, 8 ppb, 10 ppb, 15 ppb, and 20 ppb. In some embodiments; however, more or less may be desired depending on the particular application and downhole conditions.

[0024] In one or more embodiments, the length of the fibers may be kept below a length of 8 mm or the composition may become undesirably viscous and unpumpable through standard wellbore fluid delivery means. In one or more embodiments, the fibers may range in length from any lower limit selected from 0.5 mm, 1 mm, 3 mm, and 5 mm to any upper limit selected from 3 mm, 5 mm, 6 mm, and 7 mm.

[0025] Particulate Solids

[0026] Wellbore fluid formulations in accordance with the present disclosure include particulate solids that may interact in concert with the synthetic fiber to reduce fluid loss by incorporating into the interstitial spaces of a network created by the synthetic fiber. Particulate solids that may be used in accordance with the present disclosure may include any material that may aid in weighting up a fluid to a desired density, including the use of particles frequently referred to in the art as weighting materials, as well as particulates known in the art as lost circulation materials.

[0027] Particulate solids may be selected from one or more of the materials including, for example, barium sulfate (barite), ilmenite, hematite or other iron ores, olivine, siderite,

and strontium sulfate. Other examples include graphite, calcium carbonate (preferably, marble), dolomite ($\text{MgCO}_3 \cdot \text{CaCO}_3$), celluloses, micas, proppant materials such as sands, ceramic particles, diatomaceous earth, calcium silicates, nut hulls, and combinations thereof. It is also envisaged that a portion of the particulate solids may comprise drill cuttings having an average particle diameter in the range of 25 to 3000 microns. In other embodiments, the particulate weighting agent may be composed of an acid soluble material such as calcium carbonate (calcite), magnesium oxide, dolomite, and the like. One having ordinary skill in the art would recognize that selection of a particular material may depend largely on the density of the material as typically, the lowest wellbore fluid viscosity at any particular density is obtained by using the highest density particles.

[0028] Particulate solids may comprise substantially spherical particles; however, it is also envisaged that the particulate solids may comprise elongate particles, for example, rods or ellipsoids, as well as flat or sheet-like particles. Where the particulate solids comprise elongate particles, the average length of the elongate particles should be such that the elongate particles are capable of entering the induced fractures at or near the mouth thereof. Typically, elongate particles may have an average length in the range 25 to 3000 microns, or 50 to 1500 microns in some embodiments, and 250 to 1000 microns in other embodiments.

[0029] The particle size of the particulate solids may be selected depending on the particular application, the level of fluid loss, formation type, and/or the size of fractures predicted for a given formation. The size may also depend on the other particles selected for use in the fluid composition. In one or more embodiments, the particulate solids may have an average diameter that ranges from a lower limit selected from the group of 100 μm , 250 μm , 500 μm , and 750 μm to an upper limit selected from the group of 400 μm , 500 μm , 750 μm , 1000 μm , 1500 μm , and 2000 μm , and 3000 μm . In yet other embodiments, combinations of particulate solids having different average size ranges may be combined in a single fluid composition.

[0030] The amount of particulate solid present in the fluid composition may depend on the fluid loss levels, the anticipated fractures, the density limits for a given wellbore

and/or pumping limitations, etc. In some embodiments, the particulate solids may be added to the wellbore fluid compositions such that the final density of the fluid may range from 9 ppg up to 23 ppg in some embodiments; however, more or less may be desired depending on the particular application.

[0031] In one or more embodiments, the ratio of the synthetic fibers to particulate solids may be controlled such that the fluid compositions have a comparative weigh percent (wt%) of synthetic fibers to particulate solids [$100 \times (\text{weight synthetic fibers} / \text{weight particulate solids})$] that ranges from a lower limit selected from the group of 0.25 wt%, 0.5 wt%, and 1 wt% to an upper limit selected from the group of 1 wt%, 3 wt%, 5 wt%, and 7 wt%.

[0032] Base Fluids

[0033] The base fluid may be an aqueous fluid or an oleaginous fluid. The aqueous fluid may include at least one of fresh water, sea water, brine, mixtures of water and water-soluble organic compounds and mixtures thereof. For example, the aqueous fluid may be formulated with mixtures of desired salts in fresh water. Such salts may include, but are not limited to alkali metal chlorides, hydroxides, or carboxylates, for example. In various embodiments of the drilling fluid disclosed herein, the brine may include seawater, aqueous solutions wherein the salt concentration is less than that of sea water, or aqueous solutions wherein the salt concentration is greater than that of sea water. Salts that may be found in seawater include, but are not limited to, sodium, calcium, aluminum, magnesium, potassium, strontium, and lithium, salts of chlorides, bromides, carbonates, iodides, chlorates, bromates, formates, nitrates, oxides, phosphates, sulfates, silicates, and fluorides. Salts that may be incorporated in a brine include any one or more of those present in natural seawater or any other organic or inorganic dissolved salts. Additionally, brines that may be used in the pills disclosed herein may be natural or synthetic, with synthetic brines tending to be much simpler in constitution. In one embodiment, the density of the pill may be controlled by increasing the salt concentration in the brine (up to saturation). In a particular embodiment, a brine may include halide or

carboxylate salts of mono- or divalent cations of metals, such as cesium, potassium, calcium, zinc, and/or sodium.

[0034] The oleaginous fluid may be a liquid, more preferably a natural or synthetic oil, and more preferably the oleaginous fluid is selected from the group including diesel oil; mineral oil; a synthetic oil, such as hydrogenated and unhydrogenated olefins including polyalpha olefins, linear and branch olefins and the like, polydiorganosiloxanes, siloxanes, or organosiloxanes, esters of fatty acids, specifically straight chain, branched and cyclical alkyl ethers of fatty acids; similar compounds known to one of skill in the art; and mixtures thereof. Selection between an aqueous fluid and an oleaginous fluid may depend, for example, the type of drilling fluid being used in the well when the lost circulation event. Use of the same fluid type may reduce contamination and allow drilling to continue upon plugging of the formation fractures / fissures, etc.

[0035] Wellbore fluids compositions may be added in a discrete amount, for example as a pill, or added continuously until lost circulation is reduced to an acceptable level. When formulated as a pill, the wellbore fluid compositions are preferably spotted adjacent to the location of the lost circulation using methods known in the art. Spotting may be accomplished by methods known in the art. For example, the permeable formation will often be at or near the bottom of the wellbore because when the permeable formation is encountered the formation will immediately begin to take drilling fluid and the loss of drilling fluid will increase as the permeable formation is penetrated eventually resulting in a lost circulation condition. In such situations, the wellbore fluid compositions may be spotted adjacent the permeable formation by pumping a slug or pill of the slurry down and out of the drill pipe as is known in the art. It may be, however, that the permeable formation is at a point farther up in the wellbore, which may result, for example, from failure of a previous seal. In such cases, the drill pipe may be raised as is known in the art so that the pill or slug of the wellbore fluid composition may be deposited adjacent the permeable formation. The volume of the slug or pill that is spotted adjacent the permeable formation may range from less than that of the open hole to more than double that of the open hole. In some instances, it may be necessary to use more than one pill. Such need may arise when the first pill was insufficient to plug the fissures and thief zone

or was placed incorrectly. Further, in some instances, the first pill may have sufficiently plugged the first lost circulation zone, but a second (or more) lost circulation zone also exists needed treatment.

[0036] In some embodiments, wellbore fluid compositions may be added and the wellbore may be sealed and pressurized to defluidize the compositions. Defluidization may be accomplished either by hydrostatic pressure or by exerting a low squeeze pressure as is known in the art. Hydrostatic pressure will complete the seal; however, a low squeeze pressure may be desirable because incipient fractures or other areas of high permeability can be thereby opened and plugged immediately, thus reinforcing the zone and reducing or avoiding the possibility of later losses. After the defluidization is completed, the drilling fluid may be re-circulated through the wellbore to deposit a filtercake on the formation seal, and drilling may be resumed. Injection of the particles into the formation may be achieved by an overbalance pressure (*i.e.*, an overbalance pressure greater than the formation pressure). While in particular embodiments, the injection pressure may range from 100 to 400 psi, any overbalance pressure level, including less than 100 psi or greater than 400 psi may alternatively be used. The selection of the injection pressure may simply affect the level of injection of the wellbore fluid compositions into the formation.

[0037] The fibers and particulate solids are added to the treatment fluid, such as a water- or oil-based wellbore fluid, in any order with any suitable equipment to form the fluid composition. In some embodiments, the synthetic fiber and particulate solids may be added to the fluid while pumping using specialized shakers. Wellbore fluid compositions formulated with a synthetic fiber and particulate solids may be mixed before pumping downhole in some embodiments. In other embodiments, a wellbore fluid containing the synthetic fiber may be introduced into the wellbore before a second wellbore fluid containing the particulate solids or *vice versa* in yet other embodiments.

[0038] It is also within the scope of the present disclosure that one or more spacer pills may be used in conjunction with the pills of the present disclosure. A spacer is generally

characterized as a thickened composition that functions primarily as a fluid piston in displacing fluids present in the wellbore and/or separating two fluids from each other.

[0039] EXAMPLES

[0040] The following example is provided to further illustrate the application and the use of the methods and compositions of the present disclosure. In order to assay the ability of the composition to seal fractures a number of samples were prepared containing varying solids volume fraction (SVF) of wellbore fluid compositions containing varying percentages by weight of synthetic fibers and particulate solids. Wellbore fluids were formulated as shown below in Table 1, where the synthetic fiber is polyvinyl alcohol (PVA). Particulate solids surveyed include G-Seal-PlusTM Coarse (GSPC), with a median particle size of 600-1000; Nut-PlugTM Coarse (NPC), with a median particle size of 1600-2000 microns; and Nut-Plug FineTM (NPF), with a median particle size of 400-500 microns; all of which are available from MI SWACO (Houston, TX).

[0041] Tests were performed in a modified lost circulation cell. The cell was equipped with a cylinder approximately 50 mm high having a 5 mm slot. The experimental apparatus consisted essentially of a high-pressure, high-temperature fluid loss cell equipped with a cylinder at the bottom. Pressure was applied from the top of the cell onto sample formulations placed within the cell (as in a standard fluid loss experiments known in the art). A valve at the bottom was closed, and a cylinder having a slot was placed inside the cell. 500 mL of fiber-laden fluid was poured into the test cell, and the cell was closed and pressurized to 100 psi. Once the cell was pressurized, the bottom valve was opened quickly enough to eliminate filtration of fibers through the bottom pipe. If the slot was sealed, pressure was increased from 100 psi to 1500 psi, in steps of 50 psi. The pressure was held constant for at least 30 minutes, unless no plug formed or the plug failed. Mud loss monitored by collecting filtrate in a container. The container was placed on a balance connected to a computer, allowing one to record fluid loss over time.

[0042] Results are presented in Table 1 below.

Table 1 Wellbore fluid formulations and fluid loss results for Example 1.

SVF	LCM	Analysis of Fiber Effect (PVA)								
	%	Formulation					Test Results			
5.20	0.33		H2O	PVA	GSPC	NPC	NPF	500 psi	1000 psi	1500 psi
		S.G.	1.00	1.31	2.00	1.40	1.40	Yes	Yes	Yes
		Weight	331.79	1.00	6.60	16.50	3.30			
		Volume	331.79	0.76	3.30	11.79	2.36			
		W Total	355.89					Observations = Lost about 80% of fluid but did hold at 1500psi		
		VTotals	350.00	18.21						
		Weight %		3.65	24.09	60.22	12.04			
		Volume %	94.80	4.19	18.13	64.73	12.95			
3.99	0.25		H2O	PVA	GSPC	NPC	NPF	500 psi	1000 psi	1500 psi
		S.G.	1.00	1.31	2.00	1.40	1.40	No		
		Weight	336.02	1.00	5.00	12.50	2.50			
		Volume	336.02	0.76	2.50	8.93	1.79			
		W Total	354.52					Observations = All fluid loss		
		VTotals	350.00	13.98						
		Weight %		4.76	23.81	59.52	11.90			
		Volume %	96.01	5.46	17.89	63.88	12.78			
4.21	0.25		H2O	PVA	GSPC	NPC	NPF	500 psi	1000 psi	1500 psi
		S.G.	1.00	1.31	2.00	1.40	1.40	No		
		Weight	335.26	2.00	5.00	12.50	2.50			
		Volume	335.26	1.53	2.50	8.93	1.79			
		W Total	354.76					Observations = All fluid loss		
		VTotals	350.00	14.74						
		Weight %		9.09	22.73	56.82	11.36			
		Volume %	95.79	10.36	16.96	60.57	12.11			
4.43	0.25		H2O	PVA	GSPC	NPC	NPF	500 psi	1000 psi	1500 psi
		S.G.	1.00	1.31	2.00	1.40	1.40	No		
		Weight	334.50	3.00	5.00	12.50	2.50			
		Volume	334.50	2.29	2.50	8.93	1.79			
		W Total	355.00					Observations = All fluid loss		
		VTotals	350.00	15.50						
		Weight %		13.04	21.74	54.35	10.87			
		Volume %	95.57	14.77	16.12	57.59	11.52			

[0043] Applicant has discovered that, by controlling the ratio of loss control materials based upon their microscopic shapes, improved packing within fractures and loss control performance can be obtained. Because of the interweaving of the fiber components additives and optional particulate weighting agents, reduced amounts of each of the individual components are necessary to plug fissures within the formation, with that added benefit that the resulting fluid remains pumpable thorough conventional drill strings.

[0044] Further, while not all fibers are capable of blocking fluid loss under given conditions, as the selection and use of the wrong fiber can cause great complications in mixing and pumping and ultimately with no blocking effect to cure losses, the applicant has identified materials that are both capable of reducing or eliminating fluid loss in a subterranean formation. In addition, the selected fiber materials may also be dissolved upon exposure to acid to such a degree that the seal formed by fiber blend may be partially or completely removed prior to production operations.

[0045] In cases of high fluid loss downhole, large quantities of lost circulation materials are required to seal fissures and formation. However, when lost circulation materials become sufficiently concentrated, placement of the lost circulation materials becomes more difficult because standard placement means such as drill strings and coiled tubing require that fluids be pumpable, *i.e.*, where the viscosity is below a range where pressures required to deliver the fluids becomes too great and hazardous to on site workers. However, Applicant has discovered that a synergistic combination of geometrically defined synthetic fibers and particulate solids may be used in instances of high fluid loss. The synergistic combination is not only effective in reducing fluid loss, but overcomes the difficulties associated with placement and decrease the total amount of materials required. Increasing the efficiency of material usage may also carry advantages in remote worksites like offshore drilling where delivery costs are a substantial concern.

[0046] Although only a few example embodiments have been described in detail above, those skilled in the art will readily appreciate that many modifications are possible in the example embodiments without materially departing from this invention. Accordingly, all

such modifications are intended to be included within the scope of this disclosure as defined in the following claims. Moreover, embodiments described may be practiced in the absence of any element that is not specifically disclosed herein.

CLAIMS

What is claimed:

1. A wellbore fluid composition comprising:
a base fluid;
at least one synthetic fiber; and
a particulate solid.
2. The wellbore fluid composition of claim 1, wherein the base fluid comprises an oleaginous fluid.
3. The wellbore fluid composition of claim 1, wherein the base fluid comprises a non-oleaginous fluid.
4. The wellbore fluid composition of any of the above claims, wherein the at least one synthetic fiber has a length within the range of 4 mm to 7 mm.
5. The wellbore fluid composition of any of the above claims 1-3, wherein the at least one synthetic fiber has a length within the range of 5 mm to 6 mm.
6. The wellbore fluid composition of any of the above claims, wherein the at least one synthetic fiber is added to the wellbore fluid composition at 1% to 5% of the weight of the added particulate solid.
7. The wellbore fluid composition of any of the above claims, wherein the particulate solid added to the wellbore fluid composition ranges from 5 ppb to 100 ppb.
8. The fluid loss composition of any of the above claims, wherein the one or more synthetic fibers are polyvinyl alcohol.
9. The wellbore fluid composition of claim any of the above claims, wherein the at least one synthetic fiber has a diameter within the range of 5 microns to 15 microns.

10. A method of strengthening a wellbore or reducing fluid loss in a downhole formation, the method comprising:
preparing a fluid composition, wherein the fluid loss composition comprises a base fluid,
one or more synthetic fibers, and one or more particulate solids; and
emplacing the fluid loss composition in an interval of the downhole formation.
11. The method of claim 10, further comprising applying pressure to the wellbore to drive the fluid loss composition into the formation.
12. The method of claim 11, further comprising allowing the fluid composition to form a plug or seal in at least one interval of the downhole formation.
13. The method of claim 13, wherein the plug or seal formed is sufficient to withstand applied pressures of up to 1500 psi.
14. The method of claim 10, wherein the one or more synthetic fibers have a length within the range of 4 mm to 7 mm.
15. The method of claim 10 or 11, further comprising:
introducing at least one spacer pill into the wellbore before introducing the fluid loss composition.
16. The method of any one of claims 10 or 11, further comprising:
introducing at least one spacer pill after the fluid loss composition is introduced into the wellbore.
17. The method of any one of claims 10 or 11, further comprising:
introducing a second fluid composition in a second interval of the wellbore.
18. A method of strengthening a wellbore or reducing fluid loss into a downhole formation, comprising:
introducing into the wellbore a fluid composition comprising one or more synthetic fibers; and
introducing a second fluid composition comprising one or more particulate solids.

19. The method of claim 17, wherein the method further comprises applying pressure to drive the fluid composition into the formation.
20. The method of claim 17, wherein the one or more synthetic fibers have a length within the range of 4 mm to 7 mm.

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US2013/048940**A. CLASSIFICATION OF SUBJECT MATTER****C09K 8/03(2006.01)i, C09K 8/04(2006.01)i, E21B 43/22(2006.01)i**

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

C09K 8/03; C09K 8/02; C04B 16/12; C09K 8/035; B32B 5/16; E21B 33/13; C09K 8/58; C09K 8/588; C09K 8/04; E21B 43/22

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Korean utility models and applications for utility models

Japanese utility models and applications for utility models

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

eKOMPASS(KIPO internal) & Keywords: wellbore, fluid, synthetic fiber, particulate solid, strengthening, fluid loss

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2011-0278006 A1 (SANDERS, M. W. et al.) 17 November 2011 See claims 1, 4-10, 12, 14, 15, 17-19; paragraphs [0017], [0024], [0025], [0028], [0029], [0032], [0040]-[0042], [0046]-[0048], [0059].	1-5, 10-20
X	US 2010-0230164 A1 (POMERLEAU, D. G.) 16 September 2010 See abstract; claims 1-3, 8-13, 15, 29; paragraph [0064].	1-5
A		10-20
X	US 2010-0152070 A1 (GHASSEMZADEH, J.) 05 August 2010 See claims 1, 3-5, 9, 14, 18, 19, 27.	1-5
A		10-20
X	US 2008-0110627 A1 (KEESE, R. et al.) 15 May 2008 See claims 1, 3, 6, 7.	1,3-5
A		2,10-20
X	US 2011-0042088 A1 (GASSEMZADEH, J. et al.) 24 February 2011 See abstract; claims 1, 6, 9, 25, 27; paragraphs [0001], [0028], [0030].	1,3-5
A		2,10-20



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

26 September 2013 (26.09.2013)

Date of mailing of the international search report

26 September 2013 (26.09.2013)

Name and mailing address of the ISA/KR

Korean Intellectual Property Office
189 Cheongsu-ro, Seo-gu, Daejeon Metropolitan City,
302-701, Republic of Korea

Facsimile No. +82-42-472-7140

Authorized officer

HONG Sung Ran

Telephone No. +82-42-481-5405



INTERNATIONAL SEARCH REPORT

International application No.
PCT/US2013/048940

Box No. II Observations where certain claims were found unsearchable (Continuation of item 2 of first sheet)

This international search report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☐ Claims Nos.:
because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out, specifically:
3. ☒ Claims Nos.: 6-9
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box No. III Observations where unity of invention is lacking (Continuation of item 3 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

1. ☐ As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest and, where applicable, the payment of a protest fee.
- ☐ The additional search fees were accompanied by the applicant's protest but the applicable protest fee was not paid within the time limit specified in the invitation.
- ☐ No protest accompanied the payment of additional search fees.

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT/US2013/048940

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 2011-0278006 A1	17/11/2011	CA 2750898 A1 CN 102300953 A EA 201101137A1 EP 2398866 A2 MX 2011008001 A WO 2010-088484 A2 WO 2010-088484 A3	05/08/2010 28/12/2011 28/02/2012 28/12/2011 15/09/2011 05/08/2010 02/12/2010
US 2010-0230164 A1	16/09/2010	None	
US 2010-0152070 A1	17/06/2010	EP 2196516 A1	16/06/2010
US 2008-0110627 A1	15/05/2008	AU 2004-238982 A1 AU 238982 B2 BR PI0410234 A CA 2523472 A1 CN 1788066 A EA 008095 B1 EA 200501804 A EC SP056217 A EP 1622991 A1 JP 2007-501319 A JP 4842132 B2 MX PA05011606 A US 2007-056730 A1 US 7331391 B2 US 8002049 B2 WO 2004-101704 A1	25/11/2004 07/05/2009 09/05/2006 25/11/2004 14/06/2006 27/02/2007 27/10/2006 19/04/2006 08/02/2006 25/01/2007 21/12/2011 27/04/2006 15/03/2007 19/02/2008 23/08/2011 25/11/2004
US 2011-0042088 A1	24/02/2011	EP 2083059 A1 WO 2009-083236 A1 WO 2009-083236 A4	29/07/2009 09/07/2009 27/08/2009