



Office de la Propriété
Intellectuelle
du Canada

Un organisme
d'Industrie Canada

Canadian
Intellectual Property
Office

An agency of
Industry Canada

CA 2053656 C 2003/06/24

(11)(21) **2 053 656**

(12) **BREVET CANADIEN
CANADIAN PATENT**

(13) **C**

(22) Date de dépôt/Filing Date: 1991/10/17

(41) Mise à la disp. pub./Open to Public Insp.: 1992/04/23

(45) Date de délivrance/Issue Date: 2003/06/24

(30) Priorité/Priority: 1990/10/22 (600,745) US

(51) Cl.Int.⁵/Int.Cl.⁵ C08L 93/00, C08L 71/12

(72) Inventeurs/Inventors:
BURDICK, CHARLES L., US;
PULLIG, JACKIE N., US

(73) Propriétaire/Owner:
AQUALON COMPANY, US

(74) Agent: FETHERSTONHAUGH & CO.

(54) Titre : SUSPENSIONS POLYMERIQUES FLUIDISEES, PREPAREES AVEC DU FORMIATE DE SODIUM

(54) Title: SODIUM FORMATE FLUIDIZED POLYMER SUSPENSIONS

(57) **Abrégé/Abstract:**

Fluidized aqueous suspensions of 15% or more by weight hydroxyethylcellulose, hydrophobically modified cellulose ether, hydrophobically modified hydroxyethylcellulose, methylcellulose, hydroxypropylmethylcellulose and polyethylene oxide are prepared by addition of the polymer to a concentrated sodium formate solution containing xanthan gum as a stabilizer.



2053656

SODIUM FORMATE FLUIDIZED POLYMER SUSPENSIONS**ABSTRACT OF THE DISCLOSURE**

Fluidized aqueous suspensions of 15% or more by weight hydroxyethylcellulose, hydrophobically modified cellulose ether, hydrophobically modified hydroxyethylcellulose, methylcellulose, hydroxypropylmethylcellulose and polyethylene oxide are prepared by addition of the polymer to a concentrated sodium formate solution containing xanthan gum as a stabilizer.

22124-1790

The invention relates to aqueous suspensions of nonionic polymers in a salt medium. In particular, the invention relates to the aqueous suspension of nonionic polymers in aqueous sodium formate.

5 U.S. Patent 4,883,536 "Suspension of Water Soluble Polymers in Aqueous Media Containing Dissolved Salts" and U.S. Patent 4,883,537, "Aqueous Suspension of Carboxymethylcellulose" both issued in the name of C. L. Burdick and assigned to the Aqualon Company teach that salts
10 with divalent or trivalent anions are useful for suspension of cellulose ether derivatives. However, these and other references in the prior art gave no indication that a single monobasic acid salt would be similarly useful for fluidized polymer suspensions. Thus, it remained for the present
15 invention to provide such an advance in the state of the art.

It is an object of the invention to provide fluidized polymer suspensions for paint, paper, mining, construction and oil and gas recovery uses for nonionic cellulose ethers in water and salt; characterized in that the salt is sodium
20 formate. Sodium formate is a suspending salt for hydroxyethylcellulose, hydrophobically modified hydroxyethylcellulose, methylcellulose, methylhydroxypropylcellulose and derivatives thereof, e.g., hydrophobically modified ethylhydroxyethylcellulose, etc.

25 Thus, in one aspect the invention provides a fluidized suspension of a nonionic polymer in an aqueous salt solution, characterized in that the salt is sodium formate and the suspension comprises at least 28% by weight sodium formate and the polymer is one or more selected from the group
30 consisting of hydroxyethylcellulose, hydrophobically modified cellulose ether, hydrophobically modified

22124-1790

hydroxyethylcellulose, hydrophobically modified ethylhydroxyethylcellulose, methylcellulose, methylhydroxypropylcellulose or polyethylene oxide.

In another aspect, the invention provides a process
5 for preparing an aqueous fluidized suspension of a nonionic polymer in xanthan gum and sodium formate, comprising the steps of: (1) preparing a xanthan gum solution; (2) adding 28% by weight or more sodium formate, and (3) adding a nonionic polymer selected from the group consisting of
10 hydroxyethylcellulose, hydrophobically modified cellulose ether, hydrophobically modified hydroxyethylcellulose, hydrophobically modified ethylhydroxyethylcellulose, methylcellulose or methylhydroxypropylcellulose to prepare a fluidized polymer suspension which is stable for one month or
15 longer.

The invention also provides for the use of a combination of sodium formate and xanthan gum as suspending agent for nonionic polymers, selected from the group consisting of hydroxyethylcellulose, hydrophobically modified cellulose
20 ether, hydrophobically modified hydroxyethylcellulose, hydrophobically modified ethylhydroxyethylcellulose, methylcellulose, methylhydroxypropylcellulose or polyethylene oxide.

22124-1790

In a preferred process of the invention xanthan gum is dissolved in water prior to the addition of sodium formate, then at least one nonionic polymer selected from the group of hydroxyethylcellulose, methylcellulose or derived ethers is
5 added to the aqueous xanthan/sodium formate solution to form a fluid suspension of the polymers.

In view of the success which had been achieved with aqueous polymer suspensions in carbonates, sulfates and

phosphates; it was unexpected to discover that one and only one monobasic acid salt could provide such suspending benefit. Further it was found that a particular material, i.e., sodium formate, which was previously considered to be a low value byproduct, could actually provide such dramatic benefits in a before unknown application. Not only was sodium formate readily available, but the process of preparing fluidized polymer suspensions was less critical than previously experienced with multibasic acid salts.

While other salts such as potassium formate, calcium formate and acetates and/or bicarbonates might be expected to function in the same manner as sodium formate, such was not the case in actual comparison tests for preparing fluid suspensions of 15 parts or more hydroxyethylcellulose in a total suspension composition of 100 parts.

	Salt	Salt	Natrosol		Result
		Amount	Water	250GR	
		g	g		
	Sodium Formate	30	55	15	Fluid Suspension
	Potassium Formate	30	55	15	Thick Gel
20	Sodium Acetate	30	55	15	Thick Gel
	Calcium Formate	30	55	15	Thick Gel
	Potassium Bicarbonate	30	55	15	Thick Gel
	Sodium Bicarbonate	30	55	15	Thick Gel

In addition to the discovery of the unique behavior of sodium formate in relation to other monovalent anion salts, it was surprising to also discover that not all nonionic polymers could be suspended. Suitable nonionic polymers for sodium formate suspension were hydroxyethylcellulose, hydrophobically modified hydroxyethylcellulose, hydrophobically modified ethyl hydroxyethylcellulose, methylcellulose, methylhydroxypropylcellulose and polyethylene oxide (PEO). Neither anionic or cationic cellulose ethers were satisfactorily suspended and neither were nonionic guar gum or polyacrylamide.

It was observed that the ability of sodium formate solutions in water to be an effective suspending medium for water soluble polymer was dependent upon a certain concentration of the sodium formate in water being present. It was found for example that greater than 30% sodium formate concentration in water was required to prepare a fluid suspension of hydroxyethylcellulose as shown in the following table:

	<u>Sodium</u> <u>Formate</u> g	<u>Water</u> g	<u>Result</u>
	20	65	Thick Gel
	25	60	Thick Gel
	30	55	Fluid Suspension

The following is a model fluid polymer suspension according to the invention in which the ingredients are listed in order of their addition to a mixing container.

	<u>Ingredient</u>	<u>Parts By</u> <u>Weight Range</u>	<u>Ideal</u>
	Water	45-55	49.85
	Xanthan Gum	0.10-0.20	0.15
	Sodium Formate	28-35	30
	Polymer	10-25	20

While it is possible to suspend the polymer in just sodium formate, the suspension must be restirred periodically if no xanthan gum is incorporated as a suspension stabilizer. In this respect it was also surprising to find that xanthan gum was the most satisfactory agent for this purpose. Attempts to use other suspending agents such as carboxymethylcellulose (CMC), guar gum and sodium alginate were not as successful. However, in the case where the suspension is intended for use within a relatively short time after preparation, it would be possible to omit the xanthan gum and simply prepare a sodium formate solution and mix in the polymer to form a fluid suspension which could be employed in either a continuous or batch process.

The invention has industrial applicability in paint, construction materials, paper, mining, oil and gas recovery and other fields yet to be explored. The following examples illustrate the practice of the invention without being
5 limiting.

Example 1

Into 5485 g of deionized water stirred vigorously a 15 g portion of xanthan gum available from Kelco Inc. was added. Stirring continued for 30 minutes until a hazy,
10 slightly viscous solution was obtained. Then 3000g, sodium formate available from Aqualon Company was added and allowed to dissolve. Finally, 1500 g of Aqualon Natrosol® 250GR hydroxyethylcellulose was added over 10-20 minutes to form a
15 fluid suspension which had a Brookfield viscosity of 3000 mPa.s at 25°C. After one month the fluid suspension was again measured as having the same viscosity without any signs of settling.

Portions of this sodium formate/xanthan/HEC fluid
20 suspension can be successfully employed for the paint, paper coatings and construction applications described with prior art fluidized polymer suspensions in US 4,883,536 and 4,883,537.

Example 2

Fluidized polymer suspensions were prepared as in Example 1 except that the xanthan gum was not added and the nonionic polymers tested included hydroxyethylcellulose, hydrophobically modified hydroxyethylcellulose,
30 methylcellulose, methyl hydroxypropylcellulose all available from Aqualon, hydrophobically modified ethylhydroxyethylcellulose available from Berol Nobel as Bermocol® EHM 100, hydrophobically modified polymer available from Union Carbide Company as Cellosize® HEC SPATTER GUARD
35 100 and polyethylene oxide available as Polyox® 301 from Union Carbide.

In all cases it was possible to prepare fluidized polymer suspensions with Brookfield viscosities ranging from 1000 to 10,000 mPa.s at 25°C.

5 Noticeable settling was observed after stirring was stopped in about 24 to 72 hours.

Example 3

The nonionic polymers of Example 2 were all prepared as fluidized polymer suspensions using from 0.10 to 0.20 parts by weight xanthan gum per 100 parts of total suspension as per the general procedure of Example 1. Suspensions
10 stable for at least one month were obtained in all cases.

Example 4

The procedure of Example 1 was repeated except that water and sodium formate levels were varied in an attempt to prepare fluidized polymer suspensions with nonionic guar gum, polyacrylamide, sodium carboxymethylcellulose and cationic
15 hydroxyethylcellulose. Thick gels were obtained in all tests.

Example 5

Example 1 was repeated except that a salt believed to have similar properties was substituted for sodium formate.
20 Only thick gels were obtained in test varying amounts and type of salt, water and polymer for the following salts: calcium formate, potassium formate, sodium acetate, potassium bicarbonate and sodium bicarbonate.

Example 6

25 Example 1 was repeated except that water and sodium formate ratios were varied as shown in Table 1.

Table 1

	<u>Sodium Formate</u>	<u>Water</u>	<u>HEC</u>	<u>Result</u>
	20	65	15	Thick Gel
30	25	60	15	Thick Gel
	30	55	15	Fluid Suspension

Table 1 illustrates the production of a fluid suspension in a concentrated sodium formate solution (30%), whereas 20% and 25% solution produced only an unsatisfactory gel.

5

EXAMPLE 7

Example 6 was repeated except that 28g sodium formate was added to 57g water and 15g HEC added. A fluid suspension was obtained.

10

This example illustrates that a minimum of 28% by weight sodium formate salt is required to prepare fluidized polymer suspensions according to the invention.

22124-1790

CLAIMS:

1. A fluidized suspension of a nonionic polymer in an aqueous salt solution, characterized in that the salt is sodium formate and the suspension comprises at least 28% by weight sodium formate and the polymer is one or more selected from the group consisting of hydroxyethylcellulose, hydrophobically modified cellulose ether, hydrophobically modified hydroxyethylcellulose, hydrophobically modified ethylhydroxyethylcellulose, methylcellulose, methylhydroxypropylcellulose or polyethylene oxide.
2. The suspension of claim 1 where xanthan gum is added as a suspending agent in an amount of from 0.1 to 0.5% by weight based on the weight of the total fluidized polymer suspension.
3. The suspension of claim 1 or 2 where the polymer comprises 15% by weight or higher.
4. A process for preparing an aqueous fluidized suspension of a nonionic polymer in xanthan gum and sodium formate, comprising the steps of:
 - (1) preparing a xanthan gum solution;
 - (2) adding 28% by weight or more sodium formate, and
 - (3) adding a nonionic polymer selected from the group consisting of hydroxyethylcellulose, hydrophobically modified cellulose ether, hydrophobically modified hydroxyethylcellulose, hydrophobically modified ethylhydroxyethylcellulose, methylcellulose or

22124-1790

methylhydroxypropylcellulose to prepare a fluidized polymer suspension which is stable for one month or longer.

5. The process of claim 4 where 30% by weight sodium formate is added in step (2).

5 6. The fluidized polymer suspension obtainable by a process according to claim 4 or 5 containing xanthan gum as a stabilizing agent in an amount of 0.1 to 0.5% by weight based on the total weight of the fluidized polymer suspension.

7. Use of a combination of sodium formate and xanthan
10 gum as suspending agent for nonionic polymers, selected from the group consisting of hydroxyethylcellulose, hydrophobically modified cellulose ether, hydrophobically modified hydroxyethylcellulose, hydrophobically modified ethylhydroxyethylcellulose, methylcellulose,
15 methylhydroxypropylcellulose or polyethylene oxide.

FETHERSTONHAUGH & CO.

OTTAWA, CANADA

PATENT AGENTS