

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
2 May 2002 (02.05.2002)

PCT

(10) International Publication Number
WO 02/34851 A1

- (51) **International Patent Classification⁷:** C09J 4/00, C08F 220/18, 4/52
- (21) **International Application Number:** PCT/IE01/00133
- (22) **International Filing Date:** 23 October 2001 (23.10.2001)
- (25) **Filing Language:** English
- (26) **Publication Language:** English
- (30) **Priority Data:**
00650166.2 23 October 2000 (23.10.2000) EP
- (71) **Applicant (for all designated States except US):** LOC-TITE (R & D) LIMITED [IE/IE]; Tallaght Business Park, Whitestown, Dublin 24 (IE).
- (72) **Inventors; and**
- (75) **Inventors/Applicants (for US only):** KNEAFSEY, Brendan, J. [IE/IE]; 75 Hermitage Park, Lucan, Co. Dublin (IE). COUGHLAN, Gerard [IE/IE]; 4 Parkhill West, Kilmamanagh, Tallaght, Dublin 24 (IE). HARTY, Thomas [IE/IE]; Lisduff, Ballyheigue, Co. Kerry (IE).
- (74) **Agents:** LANE, Cathal, Michael et al.; Tomkins & Co., 5 Dartmouth Road, Dublin 6 (IE).
- (81) **Designated States (national):** AE, AG, AL, AM, AT, AT (utility model), AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, CZ (utility model), DE, DE (utility model), DK, DK (utility model), DM, DZ, EC, EE, EE (utility model), ES, FI, FI (utility model), GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SK (utility model), SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (84) **Designated States (regional):** ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- with amended claims

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



WO 02/34851 A1

(54) **Title:** QUATERNARY BORON COMPOUND POLYMERISATION INITIATORS, POLYMERISABLE COMPOSITIONS, AND USES THEREOF FOR BONDING LOW SURFACE ENERGY SUBSTRATES

(57) **Abstract:** Quaternary boron salts are used as initiators of polymerisation in adhesive compositions for bonding low surface energy substrates such as polyolefins. The quaternary boron salts are of the formula (1) wherein R¹ is C₁-C₁₀ alkyl, R², R³ and R⁴, which may be the same or different, are C₁-C₁₀ alkyl or C₃-C₁₀ cycloalkyl, phenyl, or phenyl-substituted C₁-C₁₀ alkyl or C₃-C₁₀ cycloalkyl, provided that any two of R¹-R⁴ may optionally be part of a carbocyclic ring, and M⁺ is a metal ion or a quaternary ammonium ion. Particular examples of initiator compounds include sodium tetraethyl borate and lithium tetraethyl borate, lithium phenyl triethyl borate and tetramethylammonium phenyl triethyl borate.

QUATERNARY BORON COMPOUND POLYMERISATION INITIATORS, POLYMERISABLE COMPOSITIONS , AND USES THEREOF FOR BONDING LOW SURFACE ENERGY SUBSTRATES

10 Cross Reference to Related Application

This application is related to the application entitled "Polymerisation Initiators, Polymerisable Compositions, and Uses Thereof" filed on even date herewith as International application No. (Agent's file PM961PCT) claiming priority from
15 European Patent Application No. 00650166.2 filed on 23 October 2000; the contents of the said International application are incorporated herein by reference.

Field of the Invention

20 This invention relates to polymerisation initiators, polymerisable compositions particularly acrylic adhesive compositions and uses thereof for bonding low surface energy substrates such as polyolefins to each other or to other substrates such as metals.

Brief Description of Related Technology

25

It is well known that the bonding of polyolefin substrates and other low surface energy substrates causes particular difficulties. Attempts have been made to overcome this problem by extensive and expensive substrate surface preparation, for example by oxidation, plasma treatment, corona treatment or flame treatment, or by priming the
30 surface with a high surface energy primer. However it is desired to develop adhesive compositions which will bond low surface energy substrates without such surface preparation.

The chemistry of organic boron compounds has been studied in detail (see
35 "Comprehensive Organic Chemistry" by Barton D. and Ollis W.D., Volume 3, Edited by Jones D.N., Pergamon Press, 1979, Part 14). The use of organoboranes such as the

5 trialkylboranes including triethylborane and tributylborane for initiating and catalyzing the polymerisation of vinyl monomers is well known. However such organoborane compounds are known to be flammable in air so that the compounds and compositions containing them require special handling and the compositions have poor shelf stability (see for example US Patent No. 3,236,823 Jennes et al., and the Background section of
10 US Patent No. 5,935,711 Pocius et al., at column 2).

Certain boron alkyl compounds and their use as initiators of polymerisation are described in a series of patents of Wolfgang Ritter assigned to Henkel KgaA, including U.S. Patents Nos. 4,515,724, 4,638,092, 4,638,498, 4,676,858 and 4,921,921
15 (hereinafter referred to as "the Ritter patents"). However the adhesive systems developed from these patents require the manufacture of trialkyl boranes from long chain fatty acids.

A series of patents of Skoultchi or Skoultchi et al. disclose a two-part initiator
20 system for acrylic adhesive compositions in which the first part includes a stable organoborane amine complex and the second part includes a destabilizer or activator such as an organic acid or an aldehyde (U.S. Patents Nos. 5,106,928; 5,143,884; 5,286,821; 5,310,835 and 5,367,746).


25 Japanese patent publication No. S48-18928 describes a method for adhering polyolefin or vinyl polymers using an adhesive obtained by adding trialkylboron to a vinyl monomer or vinyl monomer and vinyl polymer. Examples of trialkylboron include triisopropylboron, tri-n-butylboron, tripropylboron and tri-tert.-butylboron.

30 US Patent No., 3,275,611, Mottus et al. describes a process for polymerising unsaturated monomers with a catalyst comprising an organoboron compound, a peroxygen compound with an amine complexing agent for the boron compound. Use of the polymerisation products as adhesives is not discussed.

35 U.S. Patent No. 5,539,070 of Zharov et al. assigned to Minnesota Mining and Manufacturing Company and a series of patents of Alphonsus V. Pocius or Pocius et al.


5 also assigned to Minnesota Mining and Manufacturing Company, including in particular U.S. Patents Nos. 5,616,796, 5,621,143, 5,681,910, 5,684,102, 5,686,544, 5,718,977, 5,795,657 and 5,935,711 describe organoborane amine complexes which can be used in systems that initiate the polymerisation of acrylic monomers in compositions useful for bonding low surface energy plastics substrates such as polyethylene, polypropylene and
 10 polytetrafluoroethylene. PCT Publication No. WO 99/64528 also of Minnesota Mining and Manufacturing Company describes low odour polymerisable compositions comprising monomer blends and organoborane amine complex initiators. However these systems require the preparation of trialkyl borane amine complexes to achieve the desired performance and shelf stability. The manufacture of such complexes is an undesirably
 15 complicated process. Furthermore the presence of the amines results in cured adhesives that have a tendency to become yellow in colour on ageing.

In the unrelated field of photopolymerisation for colour imaging materials, it is common to use cationic dye - borate anion complexes as photopolymerisation initiators
 20 (see for example US Patent Nos. 4,772,530, 4,772,541 and 5,151,520 of Gottschalk et al., assigned to The Mead Corporation). As particularly described in US Patent No 4,772,530, the complexes can be represented by the general formula:



25 where D^+ is a cationic dye; and R^1 , R^2 , R^3 and R^4 are independently selected from the group consisting of alkyl, aryl, alkaryl, allyl, aralkyl, alkenyl, alkynyl, alicyclic and saturated or unsaturated heterocyclic groups. The borate anion is designed such that the borate radical generated from exposure to light and after electronic transfer to the dye readily dissociates with the formation of a radical as follows:

30




5 It is stated that particularly preferred anions are triphenylbutylborate and trianisylbutylborate anions because they readily dissociate to triphenylborane or trianisylborane and a butyl radical. On the other hand it is stated that tetrabutylborate anion does not work well presumably because the tetrabutylborate radical is not stable and it readily accepts an electron back from the dye in a back electron transfer and does
 10 not dissociate efficiently. Likewise, tetraphenylborate anion is very poor because the phenyl radical is not easily formed.

The photopolymerisable compositions of the above-mentioned patents assigned to The Mead Corporation are used in imaging materials, not adhesive compositions.

15

US Patent No. 4,950,581 Koike et al, assigned to Fuji Photo Film Co. Ltd, describes a photopolymerisation initiator for use in the field of imaging, comprising a combination of (a) an organic compound represented by the formula:



20 wherein R^1 , R^2 , R^3 , and R^4 , which may be the same or different, each represents a substituted or unsubstituted alkyl group, a substituted or unsubstituted aryl group, a substituted or unsubstituted alkenyl group, a substituted or unsubstituted alkynyl group, or a substituted or unsubstituted heterocyclic group, and at least two of said R^1 , R^2 , R^3 , and R^4 may combine to form a cyclic structure, with the proviso that at least R^1 , R^2 , R^3 ,
 25 and R^4 is an alkyl group, and wherein Z^+ represents an alkali metal cation or a quaternary ammonium cation, and (b) an organic dye having no counter anion.


5 Examples of such organic boron compounds include tetraethylammonium triphenylbutyl borate, tetramethylammonium triphenylbutyl borate, tetra-n-butylammonium tri-4-methoxyphenyl butyl borate, tetra-n-butylammonium triphenyl butyl borate, tetra-n-butylammonium tetra-n-butyl borate, sodium triphenyl-n-butylborate, tetramethylammonium triphenylbenzylborate.

10

Suitable organic dyes having no pair anion for the photopolymerisation initiator include merocyanine series dyes, coumarin series dyes, and xanthene or thioxanthene dyes. The Koike et al. patent is not concerned with adhesive compositions.

15

US Patent No. 6, 110, 987 Kamata et al. assigned to Showa Denko K.K. describes a photocurable composition comprising an ultraviolet radical polymerisation initiator, a cationic dye with absorptions in the visible light region, a quaternary boron salt and optionally a polymerisation accelerator. The quaternary boron salt sensitizer is represented by the general formula



20 wherein R_1 , R_2 , R_3 , and R_4 each independently represent an alkyl group which may have a substituent, an aryl group which may have a substituent, an allyl group which may have a substituent, an aralkyl group which may have a substituent, an alkenyl group which may have a substituent, an alkynyl group which may have a substituent, a silyl group which may have a substituent, a heterocyclic group or a halogen atom, and Z^+ represents
25 a quaternary ammonium cation, quaternary pyridinium cation, quaternary quinolinium cation, phosphonium cation, sulfonium cation, oxosulfonium cation, iodonium cation or metal cation, and mixing these with a compound which has a radical polymerizable unsaturated group.

30

Examples of the cation portion mentioned include tetramethylammonium, tetraethylammonium, tetra-n-butylammonium, tetraoctylammonium, lithium cation and sodium cation. In the working examples, the cation portions are all tetra-n-

- 5 butylammonium, and the anion portions are n-butyltriphenyl borate, n-butyltri(4-t-butylphenyl) borate, n-butyltri(2-tolyl) borate, n-butyltri(4-tolyl) borate, n-butyltri(4-fluoro-2 methylphenyl) borate.

In the above described photopolymerizable compositions, cationic dyes or other
10 organic dyes are used to absorb light and to facilitate transfer of energy or electrons. The distinction between triorganylboranes and organoborate salts is well illustrated in “Comprehensive Organic Chemistry” by Barton D. & Ollis W.D. (Ed. D Neville Jones) cited above, Volume 3, in which separate chapters, Chapters 14.3 and 14.4, are devoted to them. The photopolymerisable compositions of the above-mentioned patents are not
15 intended for use as adhesives, sealants and the like. Photopolymerisation systems operate by absorption of light energy, and the characteristic feature of such systems is that they have light-absorbing ability. It is not predictable whether photopolymerisation initiators will be suitable for other cure systems or for bonding substrates having particular surface energy conditions. In particular, the above-mentioned patents
20 concerning photopolymerisation initiators do not provide any disclosure or teaching relating to the bonding of low surface energy substrates.

US Patent No. 6,171,700 Sugita et al. assigned to Showa Denko K.K. and Showa Highpolymer Ltd. describes a curable composite material comprising

25

(A) a fibre reinforcing material eg carbon cloth, aramid fibre cloth, or continuous glass mat, and/or fibre filler eg. glass roving,

(B) a polymerizable unsaturated compound,

30

(C) a polymerisation initiator comprising

(a) an organic boron compound similar to that described in the above-mentioned US Patent No. 6,110,987,

(b) an acidic compound, and

35

(c) a hexaarylbiimidazole.

5 The acidic compound may be a latent acid-generating agent. In the working examples a light/heat induced latent acid generator (sulfonium compound) is used. The process for curing the composite material composition in the working examples comprises irradiating it. This patent is concerned with particular problems of photocuring compositions containing fibre reinforcing material and/or filler, particularly

10 when the composite material composition is relatively thick or is a construction that inhibits light permeation. It does not contain any teaching relevant to the bonding of low surface energy substrates.


 There is a need for commercially acceptable compositions for bonding low

15 surface energy substrates such as polyolefins and for end users to have a variety of such compositions which achieve that result through different technical strategies. Despite the work of many researchers in this field, there is a need for polymerisation initiators which reduce the problems described above and which provide alternative systems to those available hitherto. It is desirable to provide initiators which are commercially available

20 compounds and/or which are relatively easy to handle compared to compounds of the prior art.

Summary of the Invention

25 This invention relates to the use of a compound of the formula I:



wherein R¹ is C₁ - C₁₀ alkyl,

R², R³ and R⁴, which may be the same or different, are C₁ - C₁₀ alkyl or C₃ - C₁₀ cycloalkyl, phenyl, or phenyl-substituted C₁ - C₁₀ alkyl or C₃ - C₁₀

30 cycloalkyl, provided that any two of R¹ - R⁴ may optionally be part of a carbocyclic ring, and


M⁺ is a metal ion, or a quaternary ammonium cation,

5 as an initiator of polymerisation in an adhesive composition for bonding a low surface energy substrate.

The applicants are not aware of any disclosure or teaching of the use of ionic
 compounds of this kind as polymerisation initiators in adhesive compositions for
 10 bonding low surface energy substrates.

The initiator compounds of formula I are quaternary boron salts. According to one aspect of the invention, M^+ is a metal ion. If M^+ is a quaternary ammonium cation, it may suitably be of the formula II:

15



wherein R^5 - R^8 , which may be the same or different, are C_1 - C_{10} alkyl, C_1 - C_{10} alkenyl, C_3 - C_{10} cycloalkyl, aryl, C_1 - C_{10} alkylaryl, aryl C_1 - C_{10} alkyl or aryl C_1 - C_{10} cycloalkyl, provided that any two of R^5 - R^8 may be part of an optionally unsaturated carbocyclic ring.
 20 Aryl is suitably optionally substituted phenyl, wherein the phenyl ring may be substituted, for example with C_1 - C_{10} alkyl, particularly C_1 - C_6 alkyl, or halo, particularly Cl, Br or F. Examples of a quaternary ammonium cation include a tetra C_1 - C_{10} alkylammonium cation, particularly a tetra C_1 - C_5 alkylammonium cation, for example tetramethylammonium, tetraethylammonium or tetra-n-butylammonium, or a tri C_1 - C_{10}
 25 alkylaryl ammonium cation wherein aryl is phenyl, substituted phenyl (with phenyl being substituted as above), or phenyl-substituted C_1 - C_{10} alkyl or C_3 - C_{10} cycloalkyl.

An alkyl group may suitably have 1-6 carbon atoms, for example 1-4 carbon atoms. An alkyl group may be straight-chain or branched. A carbocyclic ring may be
 30 bridged by the boron atom in formula I.

5 The initiator compounds used in the present invention are commercially available or are readily prepared by available methods. One exemplary compound, sodium tetraethyl borate is available in solid form, thus enabling the formulation of solvent-free adhesives, which is a significant advantage for environmental and labelling reasons, as well as reducing potential flammability.. The initiator compounds of the invention do not
10 require the use of amines which have been used in the past to form covalent complexes with organoboranes. Once the organoborane of such complexes has reacted in a polymerisable composition, the amine can cause yellowing of a cured composition after ageing. A reduction or elimination of yellowing is a particular advantage for adhesives which are to be used in locations where appearance is important, e.g. in automobile
15 manufacture. Amines may also give rise to odour problems.

 The invention provides a polymerisable adhesive composition for bonding a low surface energy substrate to a similar or different substrate, which includes:

- 20 a) at least one free-radically polymerisable monomer component, and
 b) an effective amount of an initiator system for initiating polymerisation of the free-radically polymerisable monomer, said initiator system comprising a compound of the formula I as defined above,
with the proviso that the composition does not contain a light-absorbing dye.

25 The polymerisable composition may suitably be a two-part composition in which at least one free-radically polymerisable monomer component is provided in one part and the initiator compound of formula I is provided in the other part. Alternatively the composition could be a one-part composition with suitable stabilisation and activation
30 systems such as a moisture-latent acid or oxygen-latent acid. In a further alternative, the initiator compound of formula I could be provided as a primer which is applied to a substrate separate from the polymerisable monomer component.

 The polymerisable monomer or monomers may suitably be one or more
35 (meth)acrylic monomers.

5 In one aspect the invention provides a two-part polymerisable adhesive composition for bonding a low surface energy substrate to a similar or different substrate, which includes:

10 part A) an effective amount of a polymerisation initiator comprising a compound of the formula I as defined above, and a carrier which is inert to the compound of formula I;

 part B) at least one (meth)acrylate monomer, optionally with a toughener, acidic monomer, filler or thickener.

15 Part B may suitably be a (meth)acrylic component. The terms (meth)acrylic and (meth)acrylate are used synonymously herein with regard to the monomer and monomer-containing component. The terms (meth)acrylic and (meth)acrylate include acrylic, methacrylic, acrylate and methacrylate.

20 No cationic dyes, visible light or ultraviolet radical polymerisation initiators or hexaaryldiimidazole are required in the adhesive compositions of the invention

 The adhesive compositions disclosed herein are useful for bonding low surface energy substrates e.g. those having a surface energy of less than 45mJ/m^2 , more
25 particularly polyolefins including polyethylene and polypropylene, acrylonitrile-butadiene-styrene and polytetrafluoroethylene, or relatively low surface energy substrates such as polycarbonate, to similar substrates, to each other, or to different substrates including metals, other plastics and glass.

30 Furthermore the invention provides a method for bonding a low surface energy substrate to a similar or different substrate, wherein the method comprises applying an adhesive composition as defined above to at least one of the substrates, bringing the substrates together and allowing the composition to cure. The curing step does not
35 involve photopolymerisation. In one aspect, the invention provides a method as defined above for bonding polyolefin substrates.

5 In particular the invention provides a method for bonding a low surface energy substrate to a similar or different substrate, wherein the method comprises mixing parts A and B of a two part adhesive composition immediately prior to use in order to initiate polymerisation, applying the mixed adhesive composition to at least one of the substrates, bringing the substrates together and allowing the composition to cure by
10 completion of the polymerisation initiated on mixing of the two parts A and B

Detailed Description of the Invention

 According to one aspect of the invention M is an alkali metal ion such as lithium,
15 sodium, potassium, or caesium, particularly lithium, sodium or potassium, although metallic elements in the second row of the Periodic Table such as barium, magnesium or calcium may be useable, as may transition metals such as copper, iron or cobalt.

$R^1 - R^4$ may suitably be the same or different alkyl groups and each may suitably
20 be a $C_1 - C_6$ alkyl group, particularly a $C_2 - C_4$ alkyl group. Large or bulky alkyl groups are considered to be less likely to provide desirably active initiators, as will be understood by those skilled in free-radical chemistry.

 An example of a compound in which $R^1 - R^4$ are the same alkyl group is Sodium
25 tetraethylborohydride, alternatively called sodium tetraethylborate, which is commercially available from various suppliers such as Sigma-Aldrich Ireland Limited. Other suitable compounds include lithium tetraethyl borohydride, alternatively called lithium tetraethylborate, lithium phenyl triethyl borate and tetramethylammonium phenyl triethyl borate.

30 Desirably at least two, particularly all three, of R^2 , R^3 and R^4 are $C_1 - C_{10}$ alkyl. Suitably one or more of R^2 , R^3 and R^4 may be phenyl. Desirably not more than one of R^2 , R^3 and R^4 contains a phenyl group. It will be understood by those skilled in the art that a phenyl group (if present) may be substituted in the ring by one or more
35 substituents which do not affect the activity of the compound of formula I as a

5 polymerisation initiator. Such ring-substituents include C₁-C₁₀ alkyl, for example C₁-C₆ alkyl, particularly methyl.

An initiator compound which is not a solid may suitably be used in a solvent such as Tetrahydrofuran, diglyme, dibutyl ether, toluene or a hydrocarbon solvent, suitably at
10 a 1 molar concentration preferably not greater than about 1.5 molar, although the person skilled in the art will select a suitable concentration depending upon the solvent used.

The quantity of initiator compound of formula I may suitably be such as to provide 0.01% to 5% by weight, particularly 0.01% to 2% by weight, such as 0.01 to
15 0.6% by weight, of boron in the total composition. For ease in handling of an initiator compound which is not used as a solid, the initiator compound is suitably used in a solution in a concentration up to about 1.5M, such as about 1M.

The free-radically polymerisable monomer may be selected from olefinically
20 unsaturated systems such as acrylates, methacrylates, styrene, maleate esters, fumarate esters, unsaturated polyester resins, alkyd resins, thiol-ene compositions, and acrylate, methacrylate, or vinyl terminated resins including silicones and urethanes. Among suitable acrylates and methacrylates are those used in polymerisable systems such as disclosed in U.S. Patent No. 4,295,909, U.S. Patent No. 4,018,851, U.S. Patent No.
25 4,963,220 to Baccei *et. al.*, and U.S. Patent No. 4,215,209 to Ray-Chaudhuri *et. al.* or polyfunctional methacrylates silicone diacrylates and polyfunctional acrylated urethanes of the type known to be useful in formulating adhesives e.g. as disclosed in U.S. Patent No. 4,092,376 to Douek *et. al.*) or a thiol-ene (e.g. as disclosed in U.S. Patent Nos. 3,661,744, 3,898,349, 4,008,341 or 4,808,638). The contents of the above-mentioned
30 patents are incorporated herein by reference.

Suitable monomers include monofunctional acrylate and methacrylate esters and substituted derivatives thereof such as hydroxy, amide, cyano, chloro, and silane derivatives. Such monomers include tetrahydrofurfuryl (meth)acrylate, methyl
35 (meth)acrylate, ethyl (meth)acrylate, isobornyl methacrylate, hydroxyethyl methacrylate, hydroxypropyl (meth)acrylate, butyl acrylate, n-octyl acrylate, 2-ethylhexyl

5 (meth)acrylate, decylmethacrylate, dodecyl methacrylate, cyclohexyl methacrylate, *tert.*-butyl methacrylate, acrylamide, gamma-methacryloxypropyl trimethoxysilane, 2-cyanoethyl acrylate, 3-cyanopropyl acrylate, tetrahydrofurfuryl chloroacrylate, and glycidyl (meth)acrylate.

10 Blends of two or more monomers, particularly two or more (meth)acrylate monomers, may desirably be used, the choice of monomers in the blend being determined by the end use application of the compositions, as known to those skilled in the art.

The addition of an acid (which term includes a latent acid) in the monomer
15 component (Part B) is desirable. For certain substrates and/or certain polymerisation speeds, the presence of an acid may be required. In other cases, acidic residues, for example in the monomers, may be sufficient. Alternatively, or in addition, the initiator compound of formula I may react with another compound in the composition (particularly in Part B of a two-part composition), thus freeing the alkylborane to initiate
20 polymerisation of the polymerisable composition. In the case of a 2-part composition, the reaction takes place after mixing of the two parts, one containing the initiator compound of formula I and the other containing the compound reactive therewith.

The acid when added may suitably be a weak acid. Lewis acids may be used (see
25 U.S Patent No. 5,539,070 to Zharov et al., the contents of which are incorporated herein by reference). The pKa of the weak acid normally is no lower than about 0.5 with the desirable limit being about 0.9. The upper limit normally is about 13, or less, such as 11.5. However, carboxylic acids which have a pKa of up to about 8, such as 6 or 7, are particularly suitable.

30

The carboxylic acids may contain one or more carboxyl groups, suitably 1 to 4, and more preferably 1 to 2, carboxyl groups. Suitable aliphatic carboxylic acids ordinarily include C₁₋₁₈ chains, such as C₁₋₁₀ monocarboxylic acids.

35 Suitable acids may be monobasic or polybasic. Typical but not limiting examples of suitable acids are formic acid, acetic acid, propionic acid, maleic acid, malic acid,

5 fumaric acid, acrylic acid and copolymers thereof, methacrylic acid and copolymers thereof, pyruvic acid, itaconic acid, nadic acid, benzoic acid, phthalic acids, cinnamic acid, trichloroacetic acid and saccharin. It is particularly suitable to use an acidic monomer which can itself be polymerised, so that it is bound into the cured polymer composition, for example a part-ester of a polyfunctional acid wherein the ester group
10 contains a free-radically polymerisable component, particularly a (meth)acrylic half-ester of a difunctional acid such as maleic, fumaric or succinic acid e.g. 2-(meth)acryloyloxyethyl maleate, 2-(meth)acryloyloxyethyl fumarate or 2-(meth)acryloyloxyethyl succinate. The effective amount of the acid (or the acid residue of an acidic monomer or residue resulting from preparation of a monomer) is suitably within the
15 range from about 0.1 to about 20%, particularly from about 0.1 to about 10%, such as from about 0.5 to about 5%, by weight based on the weight of the polymerisable composition. The amount of an acidic monomer is suitably within the range from about 0.1% to about 25%, such as about 0.5% to about 15%, by weight based on the weight of the polymerisable composition.

20

The acid may be present as a latent acid, particularly a masked carboxylic acid compound hydrolyzable on contact with moisture, such as an acid anhydride, as described in EP-A-0 356 875 and US 5,268, 436, the contents of which are incorporated herein by reference. A latent acid may be used in Part B of a two-part composition, in
25 which the acid is released on mixing the two parts, or in a one-part composition.

The presence of air or oxygen is desirable at the time of initiation of polymerisation e.g. when the two parts of a two-part composition are mixed.

30 The initiator compound of formula I is desirably used with a carrier which is non-reactive with the initiator compound. Most suitably, the carrier should be liquid, should be capable of supporting and carrying the initiator compound, should be moisture-free, non-reactive with a base and not susceptible to free-radical polymerisation. The carrier may suitably be a solvent for the initiator compound.

35

5 It is important that the initiator compound and carrier should not react together or start to cross-link, causing a change in viscosity, before polymerisation of the total polymerisable composition is initiated. Suitable carriers include aziridine-functional materials which are described as diluents in PCT Publication No. WO 99/64528, which in turn refers to PCT Publication No., WO 98/17694, equivalent to US Patent No.
10 5,935,711, the contents of all of which are incorporated herein by reference. When used, the initiator compound of formula 1 is carried by (e.g., dissolved in or diluted by) an aziridine-functional material or a blend of two or more different aziridine-functional materials in the initiator component. Generally, the aziridine-functional material should not be reactive toward the initiator compound and functions as an extender for the
15 initiator. Also advantageously, the aziridine-functional material may generally increase the spontaneous combustion temperature of the initiator component.

An "aziridine-functional material" refers to an organic compound having at least

one aziridine ring or group, $\text{---N} \begin{array}{c} \diagup \\ \diagdown \end{array}$, the carbon atom(s) of which may optionally be
20 substituted by C₁ - C₁₀ alkyl groups, particularly C₁ - C₃ alkyl groups.

Suitable aziridine-functional materials are described in WO 98/17694 (U.S. Patent No. 5,935,711). Polydifunctional aziridines such as trimethylolpropane tris(3-(2-methylaziridino) propionate are particularly suitable. The aziridine-functional material
25 may also act as a cross-linking agent in the polymerisable composition, e.g. by reaction with an acid monomer or polymeric acid which may suitably be present in the composition as described above.

The aziridine-functional material should be generally soluble in monomers
30 included in the polymerisable composition, such that the parts of the two-part composition can be readily mixed. By "soluble" is meant that no evidence of gross phase separation at room temperature (i.e., about 22°C to about 25°C.) is visible to the unaided eye. Similarly, the initiator compound of formula 1 should also desirably be soluble in the aziridine-functional material, although slightly warming a mixture of the
35 initiator compound and the aziridine-functional material may be helpful in forming a

5 solution of the two at room temperature (i.e., about 22⁰C . to about 25⁰C.).

Accordingly, preferably, if used, the aziridine-functional material is a liquid at or near room temperature (i.e., within about 10⁰C of room temperature) or forms a liquid solution with the initiator compound at or near room temperature.

10 Other suitable carriers include liquid polyethers, liquid polyethers capped with non-reactive groups being groups which are not susceptible to free-radical polymerisation such as epoxies, liquid polyesters, polyisoprene or polybutadiene. A thickened solvent could also be used as a carrier. Polytetrahydrofuran could be used as both solvent and carrier. The quantity of carrier may suitably be in the range from about
15 5% to about 50% by weight, for example 5% to 25% by weight, particularly 5% to 10% by weight, of the total composition. It is an advantage of the present invention that a wider range of carriers can be used than with an amine-containing initiator system, e.g. an epoxy which could react with the amine.

20 The initiator compound of formula I and the carrier, optionally with a thickener or filler, are usually contained in Part A - the initiator component - of a two-part composition. If desired, Part A may also contain a complexing agent or sequestering agent, e.g. a calixarene or a polyether or polythioether, e.g. a crown ether or thiocrown ether respectively, with affinity for the metal in the initiator compound.

25

The monomer containing component - Part B of a two-part composition - may suitably include a toughener to improve the impact resistance and peel resistance of the bond while maintaining adhesive strength. Suitable tougheners include elastomeric materials such as polybutadiene rubbers, polyisoprene (e.g. available under the trade
30 name Kratan), acrylonitrile-butadiene-styrene (e.g. available under the trade name Hycaror or as core-shell polymers under the trade name Blendex), or polystyrenes. For bonding polyolefins it is desirable to use a core-shell polymer. The use of core-shell polymers in (meth)acrylate-based compositions is described, for example, in US Patents Nos. 4,536,546 and 4,942,201 Briggs et al. assigned to Illinois Tool Works. Core shell
35 polymers are suitably graft copolymer resins (e.g. acrylonitrile-butadiene-styrene graft copolymers or others described in the above-mentioned patents of Briggs et al.) in the

5 form of particles that comprise rubber or rubber - like cores or networks that are surrounded by relatively hard shells. In addition to improving the impact resistance of the bond, core-shell polymers can also impart enhanced spreading and flow properties to the composition (see WO 99/64528). These enhanced properties include a reduced tendency for the composition to leave an undesirable "string" upon dispensing from a
10 syringe-type applicator, or sap or slump after having been applied to a vertical surface. The quantity of toughener may suitably be in the range from about 1% to about 40% by weight, particularly about 5% to about 25% by weight, of the total composition.

The composition may optionally further comprise oxidising agents, reducing
15 agents, thickeners, fillers, non-reactive colourants and pigments, metal salts (particularly transition metal salts) and free radical polymerisation stabilisers. The optional additives are used in an amount that does not significantly adversely affect the polymerisation process or the desired properties of polymerisation products made thereby. Ingredients for a photopolymerisation system are not required and may be excluded.

20

Suitable reducing agents may be, but are not limited to, acetylphenylhydrazine, tetramethylthiourea or thiocaprolactam. Suitable oxidising agents may be, but are not limited to, peroxides and hydroperoxides.

25 Polymeric thickeners may be present in the compositions in a minor amount, up to about 50%, and may be thickeners such as a polymer or prepolymer of low or high molecular weight. Suitable polymeric thickeners are a commercially available methacrylate polymer sold by E.I. du Pont de Nemours and Company, under the trademark Elvacite, as well as styrene-methyl methacrylate co-polymers and
30 polybisphenol A maleate or propoxylated bisphenol-A-fumarate polyester (sold under the trademark Atlac). It is also possible to add inert filling materials such as finely divided silica, fumed silica (treated or untreated), montmorillonite, clay, bentonite and the like. The use of micronized silica would result in a paste-like thixotropic composition.

35 It is an advantage of the present invention that a broader range of thickeners can be used than with an initiator system containing amine. Additionally, it is conventional to

5 include in adhesive formulations certain "inert" fillers such as wood flour, glass fibres and hollow glass spheres, cotton linters, mica, alumina, silica and the like to modify viscosity, improve impact resistance and for other purposes such as spacing to provide a minimum bond thickness in the case of hollow glass spheres, e.g. at least 100 micrometres. Such fillers could be incorporated in the formulations of the present invention. The quantity of
10 filler is suitably from about 0.5% to about 20%, for example about 1.0% to about 5.0%, by weight of the composition. Small percentages of silane monomers could also be added to increase moisture resistance, as well as to enhance bonding of an adhesive to glass and similar surfaces. Other substances such as dyes, fire retarders, stabilizers such as quinones and hydroquinones, thixotropes, plasticizers, antioxidants, and the like may also
15 be included, although such additives may often be furnished in the principal ingredients, making their separate introduction unnecessary.

It is a particular advantage of the invention that polyolefin materials can be used as fillers in the composition. Polyolefin powders such as polyethylene powder or
20 polypropylene powder are relatively inexpensive and in a composition which readily bonds to a polyolefin the filler becomes securely adhered into the cured composition. Polyethylene or polypropylene powders can be used with particle sizes in the range from 0.01mm to 1mm, particularly 0.02mm to 0.3mm, allowing a good control of the gap between substrates (i.e. the depth of adhesive). Particularly suitable polyethylene
25 powders are commercially available under the trade name Microthene. Polyethylene flock and polyolefin chopped fibre can also be used as fillers. The amount of polyolefin filler may suitably be 0.5% to about 20%, particularly 1.0% to about 10%, by weight of the composition.

30

Compositions of the present invention may be used as adhesives, sealants, surface coatings, moulding resins and composite matrices, for example with "fleece" or "padding" materials of glass fibre, carbon fibre, metal fibre, polyethylene or polypropylene fibre or foams, or any combination of them, in which bonding to a low
35 surface energy polymer is required.

5 The compositions may be used in an un-polymerised state, in which case polymerisation occurs in situ, or they may be used in a part-polymerised state, in which case polymerisation is completed in situ.

10 The components of a two-part composition may suitably be mixed immediately prior to use in a manner known to those skilled in the art.

15 The compositions of the invention are suited for use with conventional, commercially available dispensing equipment for two-part adhesives, for example a dual syringe applicator and a static mixer nozzle. In general the compositions are suitable for curing at room temperature, i.e. 20-25⁰C without added heat or other energy input although heat input may be desirable in some instances, for example to accelerate cure.

20 The compositions of the present invention may suitably comprise about 0.01% to about 5% by weight of the initiator, about 5% to about 50% by weight of the carrier (if present), about 0.1% to about 20% by weight of the acid (if present), about 5% to about 85% by weight of the polymerisable monomer(s) and about 1% to about 40% by weight of the toughner (if present).

25 The compositions of the invention may suitably consist essentially of the ingredients defined in the preceding sentence, together with conventional ingredients such as fillers, thickeners or stabilizers, making up the total composition as 100%.

30 In a two-part composition, the parts may suitably be provided in a weight ratio in the range from 1:10 to 1:1 of initiator Component A to monomer-containing Component B, for example from 1:10 to 1:2, or from 1:10 to 1:4.

Examples

35

5 The following examples will illustrate the invention. In the following examples the sodium tetraethyl borate and the trimethylolpropane tris(3-(2-methylaziridino) propionate used are commercially available from Sigma-Aldrich Ireland Limited of Tallaght, Dublin 24, Ireland. The core-shell tougheners used are commercially available from GE Speciality Chemicals via Blagden Chemical Specialities Limited, London
10 WC1X 8NJ, England under the tradenames Blendex 336 and Blendex 360. The fumed silica used is commercially available under the trade name Aerosil R972 from Degussa via Philips Duphar (Ireland) Limited, Dublin, Ireland.

 In the examples the mixed adhesive composition is prepared using a MIXPAC
15 System 50 1:10 volume ratio dual syringe applicator and a 17 stage static mixer nozzle, both commercially available from METIX (UK) Limited of Kettering NN16 8PX, England.

 The tests on polypropylene substrates were carried out on filled polypropylene
20 (i.e. polypropylene PP-HWST supplied by Simona U.K. (Limited) of Stafford, England) unless otherwise indicated.

 In carrying out the tests, no tendency to catch fire was observed during the handling of the initiator compounds

25
Example 1.

Initiator Component (Part A)

30 Sodium tetraethyl borate (1g) was mixed with trimethylolpropane tris(3-(2-methylaziridino) propionate thickened with 5% by weight of fumed silica available commercially under the trade name Aerosil R972 from Degussa (25g) and dissolved by stirring for approximately two hours.

35 Adhesive Component (Part B)

5 A slurry comprising a core-shell toughner (100g), available commercially under the tradename Blendex 360 from GE Speciality Chemicals, tetrahydrofurfuryl methacrylate (249.5g), 2-ethylhexyl methacrylate (83.2g), 2-acryloyloxyethyl maleate (67.3g) and glass spheres available commercially from Aldrich was stirred with a high shear mixer for several hours until a homogeneous dispersion was obtained.

10

Adhesive

The initiator component A (5g) and adhesive component B (45g) were packaged respectively into the two syringes of a MIXPAC System 50 1:10 volume ratio 50ml
15 dual syringe applicator having a 1:10 volume ratio between the syringes holding the components A and B respectively. The two components were mixed by the simultaneous extrusion through a 17 stage static mixer nozzle. The mixed adhesive composition was tested on a range of substrates as follows:

20 Samples of the adhesive were spread onto an untreated test-piece (4 x 1 inches) - 101.6 x 25.4mm) to form a film of approximately 0.1 mm in depth. Following which a second test-piece was brought against the adhesive to form an overlap adhesive joint with 0.25 inch (6.3mm) overlap. A clamp was applied to the overlap area and the adhesive joint allowed to cure overnight, approximately 24 hours, at room temperature.
25 The bond strengths for bonds assembled using the above procedure were tested on a Instron tester according to ASTM- D1002 and are presented in the table below.

Substrates	Shear Strengths MPa
Polyethylene/Polyethylene	2.9
Polypropylene/Polypropylene	3.0
Mild Steel/Polyethylene	4.6
Mild Steel/Polypropylene	5.0
Mild Steel/Mild Steel	13

5

Example 2

Initiator Component (Part A)

10 Lithium phenyl triethyl borate was prepared ¹ by reacting 10mls triethyl borane (1 Molar in THF) in 30 mls of N-Hexane with 5.6 mls of phenyl lithium (1.8M in cyclohexane/ether) added dropwise over a ten minute period under a nitrogen atmosphere at -85°C. to -90°C. The resulting solution was stirred mechanically for 15 minutes at -85°C. to -90°C and allowed to return to room temperature and stirred for a

15 further hour. The solvents were removed and trimethylolpropane tris(3-(2-methylaziridino)) propionate thickened with 5% by weight of fumed silica Aerosil R972 manufactured by Degussa (3g).

1. J. Polymer Science Part A Polym.Chem. 1996,34,13 p.

20

Adhesive Component (Part B)

The adhesive component was prepared as in Example 1.

25 Adhesive

A mixed adhesive composition was prepared as in Example 1. The mixed adhesive composition was tested on a range of substrates as outlined in Example 1. The bond strengths are presented in the table below.

5

Substrates	Shear Strengths MPa
Polyethylene/Polyethylene	3.6
Polypropylene/Polypropylene	2.3
Mild Steel/Polyethylene	3.4
Mild Steel/Polypropylene	2.8
Mild Steel/Mild Steel	9.0

Example 3 (Comparative)

Initiator Component (Part A)

10

An organic borate photoinitiator CGI 1584 from Ciba, Basle, Switzerland, (0.2g) was added to trimethylolpropane tris(3-(2-methylaziridino))propionate (5g) and stirred until it dissolved.

15 Adhesive Component (Part B)

A slurry comprising a core-shell toughener (100g), available commercially under the tradename Blendex 336 from GE Specialty Chemicals, tetrahydrofurfuryl methacrylate (249.5g), 2-ethylhexyl methacrylate (83.2g) and 2-acroyloyloxyethyl maleate (67.3g) was
20 stirred with a high shear mixer for several hours until a homogeneous dispersion was obtained.

5

Adhesive

The mixed adhesive composition was prepared as in Example 1. The mixed adhesive composition was tested on a range of substrates as outlined in Example 1. The bond strengths are presented in the table below.

10

Substrates	Shear Strengths MPa
Polyethylene / Polyethylene	0
Polypropylene/Polypropylene	0
Mild Steel/ Polyethylene	0
Mild Steel/ Polypropylene	0
Mild Steel / Mild Steel	0

A similar experiment was carried out with the Ciba Photoinitiator CGI 813, tetra methyl ammonium borate, again giving the same result i.e. no bond strengths on either polyolefins or mild steel.

15

Example 4

Initiator Component (Part A)

Tetra methyl ammonium phenyl triethyl borate (0.5g) prepared ¹ as outlined in the literature was added to trimethylolpropane tris(3-(2-methylaziridino))propionate thickened with 5% by weight of fumed silica Aerosil R972 manufactured by Degussa (4.5g).

20

1. J. Polymer Science Part A Polym. Chem. 1996,34,13 p

25

Adhesive Component (Part B)

25

5 A slurry comprising a core-shell toughener (100g), available commercially under the tradename Blendex 360 from GE Specialty Chemicals, tetrahydrofurfuryl methacrylate (249.5g), 2-ethylhexyl methacrylate (83.2g) and 2-acryloyloxyethyl maleate (67.3g) was stirred with a high shear mixer for several hours until a homogeneous dispersion was obtained.

10

Adhesive

The mixed adhesive composition was prepared as in Example 1. The mixed adhesive composition was tested on a range of substrates as outlined in Example 1. The bond strengths are presented in the table below.

Substrates	Shear Strengths
	MPa
Polyethylene / Polyethylene	2.3
Polypropylene/Polypropylene	2.6
Mild Steel/ Polyethylene	3.0
Mild Steel/ Polypropylene	3.0
Mild Steel / Mild Steel	8.0

Example 5

20 Initiator Component (Part A)

The initiator component is prepared as outlined in Example 1.

Adhesive Component (Part B)

25

A slurry having the ingredients of Adhesive Component B of Example 1 together with a micronised polyethylene powder (50g) commercially available under the tradename Microthene FN500 distributed by National Chemical Company, Ireland, is

- 5 stirred with a high shear mixer for several hours until a homogeneous dispersion is obtained.


Adhesive

- 10 A mixed adhesive composition is prepared as outlined in Example 1.

5

CLAIMS

1. Use of a compound of the formula I



10

wherein R^1 is $\text{C}_1 - \text{C}_{10}$ alkyl,

15

R^2 , R^3 and R^4 , which may be the same or different, are $\text{C}_1 - \text{C}_{10}$ alkyl or $\text{C}_3 - \text{C}_{10}$ cycloalkyl, phenyl, or phenyl-substituted $\text{C}_1 - \text{C}_{10}$ alkyl or $\text{C}_3 - \text{C}_{10}$ cycloalkyl, provided that any two of $\text{R}^1 - \text{R}^4$ may optionally be part of a carbocyclic ring, and

M^{\oplus} is a metal ion, or a quaternary ammonium cation,

as an initiator of polymerisation in an adhesive composition for bonding a low surface energy substrate.


20

2. Use according to Claim 1 wherein the initiator compound is of formula I in which M^{\oplus} is a metal ion.

25

3. Use according to claim 2 wherein the initiator compound is of formula I in which M^{\oplus} is an alkali metal ion.

4. Use according to Claim 1 wherein the initiator compound is a quaternary ammonium cation of the formula II.



30

- 5 wherein R^5 - R^8 , which may be the same or different, are C_1 - C_{10} alkyl, C_1 - C_{10} alkenyl, C_3 - C_{10} cycloalkyl, aryl, C_1 - C_{10} alkylaryl, aryl C_1 - C_{10} alkyl or aryl C_1 - C_{10} cycloalkyl, provided that any two of R^5 - R^8 may be part of an optionally unsaturated carbocyclic ring.
- 10 5. Use according to any of the preceding claims wherein the initiator compound is of formula I in which each of R^1 - R^4 is the same C_1 - C_{10} alkyl group.
6. Use according to any of the preceding claims wherein the initiator compound is of formula I in which each of R^1 - R^4 is the same C_2 - C_4 alkyl group.
- 15 7. Use according to Claim 3 wherein the alkali metal salt is selected from the group consisting of Sodium tetraethylborate and Lithium tetraethylborate.
8. Use according to any of claims 1-3 wherein the initiator compound is of formula I in which three of R^1 - R^4 are the same C_1 - C_{10} alkyl group and one of R^1 - R^4 is phenyl or
- 20 phenyl-substituted C_1 - C_{10} alkyl.
9. Use according to any of claims 1-3 wherein the initiator compound is of formula I in which three of R^1 - R^4 are the same C_2 - C_4 alkyl group and one of R^1 - R^4 is phenyl.
- 25 10. Use according to claim 8 wherein the initiator compound is selected from the group consisting of lithium phenyl triethyl borate and sodium phenyl triethyl borate.
11. A polymerisable adhesive composition for bonding a low surface energy substrate to a similar or different substrate, comprising:
- 30 a) at least one free-radically polymerisable monomer component, and
- b) an effective amount of an initiator system for initiating polymerisation of the free-radically polymerisable monomer, said initiator system comprising a compound of the formula I as defined in Claim 1.

5 12. A composition according to claim 10 which is a two-part composition in which the free-radically polymerisable monomer component is provided in one part and the initiator compound of the formula I is provided in the other part.

13. A two-part polymerisable adhesive composition according to Claim 10
10 comprising:

part A) an effective amount of a polymerisation initiator comprising a compound of the formula I as defined above, and a carrier which is inert to the compound of formula I;

15 part B) at least one (meth)acrylate monomer, optionally with a toughener, acidic monomer, filler or thickener.


14. A composition according to any of Claims 10-12, wherein the initiator compound is of formula I in which each of R^1 - R^4 is a C_2 - C_6 alkyl group.

20 15. A composition according to any of Claims 10-12, wherein the initiator compound is of formula I in which each of R^1 - R^4 is a C_2 - C_4 alkyl group.

16. A composition according to any of Claims 10-15, wherein the initiator compound is of formula I in which M^+ is an alkali metal ion.

25

17. A composition according to any of claims 10-15 wherein the initiator compound is of formula I in which M^+ is a quaternary ammonium cation of the formula II:



30 wherein R^5 - R^8 , which may be the same or different, are C_1 - C_{10} alkyl, C_1 - C_{10} alkenyl, C_3 - C_{10} cycloalkyl, aryl, C_1 - C_{10} alkylaryl, aryl C_1 - C_{10} alkyl or aryl C_1 - C_{10} cycloalkyl, provided that any two of R^5 - R^8 may be part of an optionally unsaturated carbocyclic ring.

- 5 18. A composition according to claim 16 wherein the alkali metal salt is selected from Sodium tetraethylborate and Lithium tetraethylborate.
19. A composition according to any of claims 10-13, 15 or 16 wherein the initiator compound is of formula I in which three of R^1-R^4 are the same C_1-C_{10} alkyl group and
10 one of R^1-R^4 is phenyl or phenyl-substituted C_1-C_{10} alkyl.
20. A composition according to any of claims 10-13, 15 or 16 wherein the initiator compound is of formula I in which three of R^1-R^4 are the same C_2-C_4 alkyl group and one of R^1-R^4 is phenyl.
- 15 21. A composition according to claim 19 wherein the initiator compound is selected from the group consisting of lithium phenyl triethyl borate and sodium phenyl triethyl borate.
- 20 22. A composition according to any of Claims 10-20, further comprising a polyolefin filler.
23. A composition according to any of Claims 10-21, wherein the free-radically polymerisable monomer component comprises a (meth)acrylic monomer.
- 25 24. A composition according to Claim 22, wherein the free-radically polymerisable monomer component comprises at least two (meth)acrylic monomers.
- 25 25. A composition according to any of claims 10-23, wherein the quantity of the
30 initiator compound of formula I is such as to provide 0.01% to 5% by weight, particularly 0.01% to 2% by weight, such as 0.01% to 0.6% by weight, of boron in the total composition.
- 35 26. A composition according to any of claims 10-24 which includes an acidic monomer which is free-radically polymerisable.

- 5 27. A composition according to any of claims 10-25 which includes an aziridine-functional material as a carrier for the initiator compound of formula I.
28. A method for bonding a low surface energy substrate, such as a polyolefin substrate, to a similar or different substrate, wherein the method comprises applying a
10 composition according to any of Claims 10-26 to at least one of the substrates, bringing the substrates together with the composition between them and allowing the composition to cure.
29. A method for bonding a low surface energy substrate to a similar or different
15 substrate, wherein the method comprises mixing parts A and B of a two part adhesive composition according to claim 12 immediately prior to use in order to initiate polymerisation, applying the mixed adhesive composition to at least one of the substrates, bringing the substrates together and allowing the composition to cure by completion of the polymerisation initiated on mixing of the two parts A and B.
20
30. A cured adhesive composition comprising the polymerisation product of a composition according to any of Claims 10-26..
31. A bonded article comprising two substrates bonded by the polymerisation
25 product of a composition according to any of Claims 10-26..
32. A bond formed between two substrates by the polymerisation product of a composition according to any of Claims 10-26.
- 30 33. A polymerisable composition, which includes
- a) at least one free-radically polymerisable monomer component,
b) an effective amount of an initiator system for initiating polymerisation of the free-radically polymerisable monomer, said initiator system comprising a compound of the
35 formula I as defined in Claim 1, and

5 c) an effective amount of a compound that is reactive with the compound of the formula I to free an organoborane from the compound of formula I and thus to initiate polymerisation of the at least one free-radically polymerisable monomer.

34. A system capable of initiating the polymerisation of a (meth)acrylic monomer, the
10 system comprising.

- a) a compound of the formula I as defined in Claim 1; and
- b) an effective amount of a compound that is reactive with the compound of the formula I to free an organoborane from the compound of the formula I.

15

35. A polymerisable acrylic composition comprising:

- a) a (meth)acrylate component comprising at least one (meth)acrylic monomer,
- b) an effective amount of a compound of the formula I as defined in Claim 1; and
- 20 c) an effective amount of a compound that is reactive with the compound of formula I to free an organoborane from the compound of the formula I and thus to initiate polymerisation of the at least one (meth)acrylic monomer.

36. A composite article comprising a first substrate and a second substrate bonded to
25 the first substrate by an acrylic adhesive, wherein the acrylic adhesive comprises the polymerisation product of a polymerisable acrylic composition that comprised:

- a) a (meth)acrylic component comprising at least one (meth)acrylic monomer,
- b) an effective amount of a compound of the formula I as defined in Claim 1, and
- 30 c) an effective amount of a compound that is reactive with the compound of the formula I to free an organoborane from the compound of the formula I and thus to initiate polymerisation of the at least one (meth)acrylic monomer.

37. A method of bonding a low surface energy polymer to a substrate, the method
35 comprising the steps of:


- 5 i) providing a low surface energy polymer;
ii) providing a substrate;
iii) providing an adhesive composition comprising:
- 10 a) a (meth)acrylic component comprising at least one (meth)acrylic monomer;
b) an effective amount of a compound of the formula I as defined in Claim 1;
and
c) an effective amount of the compound that is reactive with the compound of the formula I to free an organoborane from the compound of the formula I and thus to initiate polymerisation of the at least one
- 15 (meth)acrylic monomer;
- (iv) applying the adhesive composition to either the low surface energy polymer or the substrate;
v) joining the low surface energy polymer and the substrate with the adhesive
- 20 composition therebetween; and
(vi) permitting the adhesive composition to cure to adhesively bond the low surface energy polymer and the substrate.

AMENDED CLAIMS

[received by the International Bureau on 8 March 2002 (08.03.02);
original claims 4, 12-17 and 19-32 amended;
remaining claims unchanged (7 pages)]

1. Use of a compound of the formula I

5



wherein R¹ is C₁ - C₁₀ alkyl,

10 R², R³ and R⁴, which may be the same or different, are C₁ - C₁₀ alkyl or C₃ - C₁₀ cycloalkyl, phenyl, or phenyl-substituted C₁ - C₁₀ alkyl or C₃ - C₁₀ cycloalkyl, provided that any two of R¹ - R⁴ may optionally be part of a carbocyclic ring, and

M⁺ is a metal ion, or a quaternary ammonium cation,


15 as an initiator of polymerisation in an adhesive composition for bonding a low surface energy substrate.

2. Use according to Claim 1 wherein the initiator compound is of formula I in which M⁺ is a metal ion.

20

3. Use according to claim 2 wherein the initiator compound is of formula I in which M⁺ is an alkali metal ion.

4. Use according to Claim 1 wherein the initiator compound is of formula I in
25 which M⁺ is a quaternary ammonium cation of the formula II.



wherein R^5 - R^8 , which may be the same or different, are C_1 - C_{10} alkyl, C_1 - C_{10} alkenyl, C_3 - C_{10} cycloalkyl, aryl, C_1 - C_{10} alkylaryl, aryl C_1 - C_{10} alkyl or aryl C_1 - C_{10} cycloalkyl, provided that any two of R^5 - R^8 may be part of an optionally unsaturated
5 carbocyclic ring.

5. Use according to any of the preceding claims wherein the initiator compound is of formula I in which each of R^1 - R^4 is the same C_1 - C_{10} alkyl group.
- 10 6. Use according to any of the preceding claims wherein the initiator compound is of formula I in which each of R^1 - R^4 is the same C_2 - C_4 alkyl group.
7. Use according to Claim 3 wherein the alkali metal salt is selected from the group consisting of Sodium tetraethylborate and Lithium tetraethylborate.
- 15 8. Use according to any of claims 1-3 wherein the initiator compound is of formula I in which three of R^1 - R^4 are the same C_1 - C_{10} alkyl group and one of R^1 - R^4 is phenyl or phenyl-substituted C_1 - C_{10} alkyl.
- 20 9. Use according to any of claims 1-3 wherein the initiator compound is of formula I in which three of R^1 - R^4 are the same C_2 - C_4 alkyl group and one of R^1 - R^4 is phenyl.
10. Use according to claim 8 wherein the initiator compound is selected from the group consisting of lithium phenyl triethyl borate and sodium phenyl triethyl borate.
- 25 11. A polymerisable adhesive composition for bonding a low surface energy substrate to a similar or different substrate, comprising:
- a) at least one free-radically polymerisable monomer component, and
 - b) an effective amount of an initiator system for initiating polymerisation of the
- 30 free-radically polymerisable monomer, said initiator system comprising a compound of the formula I as defined in Claim 1.

12. A composition according to claim 11 which is a two-part composition in which the free-radically polymerisable monomer component is provided in one part and the initiator compound of the formula I is provided in the other part.

5

13. A two-part polymerisable adhesive composition according to Claim 11 comprising:

part A) an effective amount of a polymerisation initiator comprising a compound of the formula I as defined above, and a carrier which is inert to the compound of formula I;

10

part B) at least one (meth)acrylate monomer, optionally with a toughener, acidic monomer, filler or thickener.

14. A composition according to any of Claims 11-13, wherein the initiator compound is of formula I in which each of R¹-R⁴ is a C₂-C₆ alkyl group.

15


15. A composition according to any of Claims 11-13, wherein the initiator compound is of formula I in which each of R¹-R⁴ is a C₂-C₄ alkyl group.

20

16. A composition according to any of Claims 11-15, wherein the initiator compound is of formula I in which M⁺ is an alkali metal ion.

17. A composition according to any of claims 11-15 wherein the initiator compound is of formula I in which M⁺ is a quaternary ammonium cation of the formula II:

25



wherein R⁵-R⁸, which may be the same or different, are C₁-C₁₀ alkyl, C₁-C₁₀ alkenyl, C₃-C₁₀ cycloalkyl, aryl, C₁-C₁₀alkylaryl, arylC₁-C₁₀alkyl or arylC₁-C₁₀

- cycloalkyl, provided that any two of R⁵-R⁸ may be part of an optionally unsaturated carbocyclic ring.
- 5 18. A composition according to claim 16 wherein the alkali metal salt is selected from Sodium tetraethylborate and Lithium tetraethylborate.
19. A composition according to any of claims 11-13, 16 or 17 wherein the initiator compound is of formula I in which three of R¹-R⁴ are the same C₁-C₁₀ alkyl group and
10 one of R¹-R⁴ is phenyl or phenyl-substituted C₁-C₁₀ alkyl.
20. A composition according to any of claims 11-13, 16 or 17 wherein the initiator compound is of formula 1 in which three of R¹-R⁴ are the same C₂-C₄ alkyl group and one of R¹-R⁴ is phenyl.
- 15 21. A composition according to claim 20 wherein the initiator compound is selected from the group consisting of lithium phenyl triethyl borate and sodium phenyl triethyl borate.
- 20 22. A composition according to any of Claims 11-21, further comprising a polyolefin filler.
23. A composition according to any of Claims 11 - 22 wherein the free-radically polymerisable monomer component comprises a (meth)acrylic monomer.
- 25 24. A composition according to Claim 23 wherein the free-radically polymerisable monomer component comprises at least two (meth)acrylic monomers.
- 25 25. A composition according to any of claims 11 - 24, wherein the quantity of the
30 initiator compound of formula I is such as to provide 0.01% to 5% by weight,

particularly 0.01% to 2% by weight, such as 0.01% to 0.6% by weight, of boron in the total composition.

5 26. A composition according to any of claims 11 - 25 which includes an acidic monomer which is free-radically polymerisable.

27. A composition according to any of claims 11 - 26 which includes an aziridine-functional material as a carrier for the initiator compound of formula I.

10

28. A method for bonding a low surface energy substrate, such as a polyolefin substrate, to a similar or different substrate, wherein the method comprises applying a composition according to any of Claims 11 -27 to at least one of the substrates, bringing the substrates together with the composition between them and allowing the
15 composition to cure.

29. A method for bonding a low surface energy substrate to a similar or different substrate, wherein the method comprises mixing parts A and B of a two part adhesive composition according to claim 13 immediately prior to use in order to initiate
20 polymerisation, applying the mixed adhesive composition to at least one of the substrates, bringing the substrates together and allowing the composition to cure by completion of the polymerisation initiated on mixing of the two parts A and B.

30. A cured adhesive composition comprising the polymerisation product of a
25 composition according to any of Claims 11 - 27.

31. A bonded article comprising two substrates bonded by the polymerisation product of a composition according to any of Claims 11 - 27..

30 32. A bond formed between two substrates by the polymerisation product of a composition according to any of Claims 11 - 27.

33. A polymerisable composition, which includes
- a) at least one free-radically polymerisable monomer component,
 - 5 b) an effective amount of an initiator system for initiating polymerisation of the free-radically polymerisable monomer, said initiator system comprising a compound of the formula I as defined in Claim 1, and
 - c) an effective amount of a compound that is reactive with the compound of the formula I to free an organoborane from the compound of formula I and thus to initiate
10 polymerisation of the at least one free-radically polymerisable monomer.
34. A system capable of initiating the polymerisation of a (meth)acrylic monomer, the system comprising.
- 15 a) a compound of the formula I as defined in Claim 1; and
 - b) an effective amount of a compound that is reactive with the compound of the formula I to free an organoborane from the compound of the formula I.
35. A polymerisable acrylic composition comprising:
- 20
- a) a (meth)acrylate component comprising at least one (meth)acrylic monomer,
 - b) an effective amount of a compound of the formula I as defined in Claim 1; and
 - c) an effective amount of a compound that is reactive with the compound of formula I to free an organoborane from the compound of the formula I and thus to
25 initiate polymerisation of the at least one (meth)acrylic monomer.
36. A composite article comprising a first substrate and a second substrate bonded to the first substrate by an acrylic adhesive, wherein the acrylic adhesive comprises the
30 polymerisation product of a polymerisable acrylic composition that comprised:
- a) a (meth)acrylic component comprising at least one (meth)acrylic monomer,

- b) an effective amount of a compound of the formula I as defined in Claim 1, and
- c) an effective amount of a compound that is reactive with the compound of the formula I to free an organoborane from the compound of the formula I and thus to
5 initiate polymerisation of the at least one (meth)acrylic monomer.

37. A method of bonding a low surface energy polymer to a substrate, the method comprising the steps of:

- 10 i) providing a low surface energy polymer;
- ii) providing a substrate;
- iii) providing an adhesive composition comprising:
 - a) a (meth)acrylic component comprising at least one (meth)acrylic monomer;
 - 15 b) an effective amount of a compound of the formula I as defined in Claim 1;
and
 - c) an effective amount of the compound that is reactive with the compound of the formula I to free an organoborane from the compound of the formula I and thus to initiate polymerisation of the at least one
20 (meth)acrylic monomer;
- (iv) applying the adhesive composition to either the low surface energy polymer or the substrate;
- v) joining the low surface energy polymer and the substrate with the adhesive
25 composition therebetween; and
- (vi) permitting the adhesive composition to cure to adhesively bond the low surface energy polymer and the substrate.

30 *rety0424*

INTERNATIONAL SEARCH REPORT

Int: Application No

PCT/IE 01/00133

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C09J4/00 C08F220/18 C08F4/52

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C09J C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X,P	PATENT ABSTRACTS OF JAPAN vol. 2000, no. 14, 5 March 2001 (2001-03-05) & JP 2000 327683 A (FUJI PHOTO FILM CO. LTD.), 28 November 2000 (2000-11-28) abstract see also WPI abstract n° 2001-260214	1, 13, 33
A	EP 0 078 995 A (HENKEL KGAA) 18 May 1983 (1983-05-18) claim 3	1, 11, 13, 33, 36
A	WO 97 17383 A (MINNESOTA MINING & MFG) 15 May 1997 (1997-05-15) claims	1, 11, 12, 28, 29, 33, 36, 37

 Further documents are listed in the continuation of box C. Patent family members are listed in annex.

° Special categories of cited documents :

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

& document member of the same patent family

Date of the actual completion of the international search

23 January 2002

Date of mailing of the international search report

31/01/2002

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Bettels, B

INTERNATIONAL SEARCH REPORT

ation on patent family members

International Application No

PCT/IE 01/00133

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
JP 2000327683	A	28-11-2000	NONE	
EP 0078995	A	18-05-1983	DE 3143945 A1	11-05-1983
			AT 12789 T	15-05-1985
			AT 33035 T	15-04-1988
			DE 3263159 D1	23-05-1985
			DE 3278243 D1	21-04-1988
			EP 0078994 A1	18-05-1983
			EP 0078995 A1	18-05-1983
			JP 1681718 C	31-07-1992
			JP 3044111 B	04-07-1991
			JP 58084802 A	21-05-1983
			JP 1691473 C	27-08-1992
			JP 3054683 B	21-08-1991
			JP 58084803 A	21-05-1983
WO 9717383	A	15-05-1997	AU 7250596 A	29-05-1997
			BR 9611590 A	06-04-1999
			CA 2236939 A1	15-05-1997
			CN 1201467 A	09-12-1998
			DE 69613387 D1	19-07-2001
			EP 0859801 A1	26-08-1998
			JP 2000500172 T	11-01-2000
			WO 9717383 A1	15-05-1997
			US 6027813 A	22-02-2000
			US 5883208 A	16-03-1999