




US 20140276406A1

(19) **United States**(12) **Patent Application Publication**
Campbell et al.(10) **Pub. No.: US 2014/0276406 A1**(43) **Pub. Date: Sep. 18, 2014**(54) **CONFORMABLE BALLOON DEVICES AND METHODS**(71) Applicant: **W. L. Gore & Associates, Inc.**, Newark, DE (US)(72) Inventors: **Carey V. Campbell**, Flagstaff, AZ (US);
Matthew E. Maulding, Flagstaff, AZ (US); **Benjamin M. Trapp**, Flagstaff, AZ (US)(73) Assignee: **W. L. Gore & Associates, Inc.**, Newark, DE (US)(21) Appl. No.: **14/209,711**(22) Filed: **Mar. 13, 2014****Related U.S. Application Data**

(60) Provisional application No. 61/786,022, filed on Mar. 14, 2013.

Publication Classification(51) **Int. Cl.**
A61M 25/10 (2006.01)(52) **U.S. Cl.**CPC **A61M 25/104** (2013.01); **A61M 2025/105**
(2013.01); **A61M 2025/1075** (2013.01); **A61M**
2025/1086 (2013.01)
USPC **604/103.02**; 604/103.08(57) **ABSTRACT**

The present disclosure is directed toward a semi-compliant to non-compliant, conformable balloon useful in medical applications. Conformable balloons of the present disclosure exhibit a low or insignificant straightening force when in a curved configuration and at inflation pressures greater than 4 atm. Balloons of the present disclosure are constructed of material that can compress along an inner length when the balloon is in a curved configuration. In further embodiments, balloons of the present disclosure can be constructed of material that sufficiently elongates along an outer arc when the balloon is in a curved configuration. As a result, medical balloons, in accordance with the present disclosure, when inflated in a curved configuration, exhibit kink-free configurations and do not cause a significant degree of vessel straightening.






FIG. 1a




FIG. 1b




FIG. 1c




FIG. 1d




FIG. 1e




FIG. 2a




FIG. 2b




FIG. 3a




FIG. 3b




FIG. 4




FIG. 5




FIG. 6a




FIG. 6b




FIG. 6c




FIG. 7a




FIG. 7b




FIG. 7c

Balloon	Circumferential		Mean Circ Stiffness (gf/mm/mm)	Longitudinal		Mean Long Stiffness (gf/mm/mm)	Stiffness Balance Ratio (af/mm/mm)	Mean Long Load at Elongation (kgf)
	Sample	Stiffness (gf/mm/mm)		Max Load (kgf)	Stiffness (gf/mm/mm)			
Creagh	1	457.8	429.7	2.68	320.2	374.5	1.1	2.98
	2	450.3		3.12	394.5			
	3	363.1		3.15	408.8			
Fox	1	248.0	241.4	2.59	218.0	199.0	1.2	2.23
	2	253.6		1.71	181.8			
	3	222.6		2.39	197.0			
Workhorse	1	853.9	1002.4	1.11	514.1	536.8	1.9	1.27
	2	1067.0		1.07	498.6			
	3	1086.2		1.64	597.8			
Hi TD MTS	1	351.8	380.1	0.46	28.5	23.4	16.2	0.38
	2	409.8		0.35	21.5			
	3	378.6		0.32	20.4			
Med TD MTS	1	437.8	425.1	0.22	13.4	17.5	24.3	0.30
	2	383.2		0.37	21.1			
	3	454.3		0.32	18.0			
Lo TD MTS	1	270.9	329.6	0.15	6.7	9.9	33.4	0.18
	2	285.8		0.19	9.8			
	3	431.9		0.21	13.2			

FIG. 8




FIG. 9b




FIG. 9d




FIG. 9a




FIG. 9c




FIG. 10




FIG. 11a




FIG. 11b




FIG. 11c




FIG. 11d

Sample	Straightening Force (N) at Pressure											
	5 atm	6 atm	7 atm	8 atm	9 atm	10 atm	12 atm	13 atm	15 atm	16 atm	17 atm	25 atm
Conq 8mm	—	15.01	—	18.24	—	—	—	—	—	31.75	—	45.04
Work 8mm	—	14.46	—	—	—	19.11	20.94	—	—	22.87	—	—
Fox 3mm	—	1.91	—	—	—	2.27	—	2.8	—	—	3.36	—
Fox 5mm	—	—	—	—	5	—	—	6.5	—	—	7.8	—
Fox 8mm	—	6.49	—	—	9.42	—	12.73	—	15.98	—	—	—
Fox 12mm	9.7	12.5	15.4	18.7	—	—	—	—	—	—	—	—
Ex 7-3mm	—	1.85	—	—	—	2.24	—	2.44	—	—	2.58	—
Ex 8-5mm	—	2.2	—	—	2.7	—	—	2.8	—	—	3.2	—
Ex 9-8mm	—	4	—	—	—	—	4.9	—	—	3.88	—	—
Ex 10-12mm	5.1	6.2	7.5	7.8	—	—	—	—	—	—	—	—

FIG. 12




FIG. 13a




FIG. 13b




FIG. 13c




FIG. 13d




FIG. 14a




FIG. 14b

CONFORMABLE BALLOON DEVICES AND METHODS

FIELD

[0001] The present disclosure generally relates to medical balloons, and more particularly semi-compliant to non-compliant medical balloons that are conformable to a curved vessel.

BACKGROUND

[0002] There are two main types of mechanical stresses present during a typical inflation of an elongated balloon. Hydraulic loading on a generally cylindrical balloon wall results in hoop stress and longitudinal stress. The result of the inflation loading depends on the type of material from which the balloon walls are constructed. In simplified terms, for a compliant balloon, the load will result in the balloon adapting to the shape of surrounding constraints. For example, in a body vessel, the balloon will inflate up to contact with the vessel wall(s) and then continue to lengthen down the length of the vessel as more inflation medium is introduced into the balloon. For non-compliant balloons, the shape is defined by the configuration of the balloon walls as manufactured rather than surrounding constraints, and as inflation medium is introduced, the pressure increases while the volume remains relatively constant. When a generally cylindrical non-compliant balloon is inflated in a curved vessel, the tendency is to maintain the molded balloon shape, usually a straight shape, and thus stress the vessel walls.

[0003] Percutaneous transluminal angioplasty (PTA) balloons, which are semi-compliant to non-compliant balloons, are designed to operate at pressures between 5 to 30 atmospheres ("atm") and do not readily conform to a curved configuration, in particular tortuous anatomies, e.g., curved body vessels. More precisely, medical angioplasty balloons when inflated in a curved configuration tend toward a straight configuration as the balloon is inflated to angioplasty pressures. This tendency to straighten is characterized herein in terms of a straightening force. As one might expect, such balloons, when extended along the vessel curvature, are impeded from straightening by the surrounding vessel. As a result, the balloon can cause unwanted straightening of, and damage to, the vessel, and/or the angioplasty balloon can kink. These balloons do not typically conform to the surrounding constraints, particularly when the surrounding constraints involve certain amounts of curvature.

[0004] Medical balloons capable of operating at angioplasty pressures yet having a low or insignificant straightening force when in a curved configuration can be useful in many applications.

SUMMARY

[0005] In accordance with one aspect of the disclosure, a medical balloon can comprise a balloon wall material defining a chamber wherein a portion of the balloon wall along an inner arc undergoes at least 5% compressive strain when inflated in a curved configuration requiring 20% strain; wherein said medical balloon is semi-compliant to non-compliant.

[0006] In accordance with another aspect of the disclosure, a medical balloon having a length along a longitudinal axis can comprise a balloon wall material having a porous microstructure, wherein the balloon wall material comprises a cir-

cumferential stiffness and a longitudinal stiffness and wherein the circumferential stiffness is at least 5 times greater than the longitudinal stiffness. In various embodiments, the circumferential stiffness can be at least 8 times greater, 10 times greater, 15 times greater, 25 times greater, or 50 times greater than the longitudinal stiffness.

[0007] In accordance with another aspect of the disclosure, a method of making a medical balloon can comprise wrapping an anisotropic, porous film about a mandrel having a diameter slightly greater than a nominal diameter at an angle greater than 75 degrees with respect to a longitudinal axis to form a tubular precursor, wherein the tubular precursor has a longitudinal stiffness that is at least 5 times less than a circumferential stiffness; and securing the tubular precursor about a compliant bladder to form a balloon cover. During manufacture, the medical balloon may be inflated to the nominal diameter and then radially compacted to a delivery profile, wherein, upon radial compaction, the balloon cover forms a plurality of randomly oriented folds that are much shorter than the length of the balloon, e.g., less than 20% of the balloon length.

[0008] In accordance with another aspect of the disclosure, a medical balloon can comprise a balloon comprising a polymeric material and having a nominal diameter between 3 mm to 8 mm and a nominal inflation pressure at or below 10 atm, where the balloon exhibits less than a 25% increase in mean straightening force when inflated from a pressure of 10 atm to 16 atm while in a curved conformation requiring 16% total strain. In addition, other diameter balloons are also contemplated. For example, a medical balloon can comprise a balloon comprising a polymeric material and having a nominal diameter between 9 mm to 12 mm and a nominal pressure at or below 6 atm, where the balloon exhibits less than a 3N increase in mean straightening force when inflated from a pressure of 5 atm to 8 atm while in a curved conformation requiring 16% total strain. Also, a medical balloon can comprise a balloon comprising a polymeric material and having a nominal diameter between 13 mm to 14 mm and a nominal inflation pressure at or below 6 atm, where the balloon exhibits less than a 4N increase in mean straightening force when inflated from a pressure of 6 atm to 8 atm while in a curved conformation requiring 16% total strain.

[0009] In accordance with another aspect of the disclosure, a medical balloon can comprise a balloon comprising a polymeric material and having a nominal diameter between 3 mm to 8 mm and a working pressure range that spans a nominal inflation pressure to a rated burst pressure, where the balloon exhibits less than a 25% increase in mean straightening force when inflated across the working pressure range while in a curved conformation requiring 16% total strain, and where the nominal inflation pressure is at least 4 atm. In addition, other diameter balloons are also contemplated. For example, a medical balloon can comprise a balloon comprising a polymeric material and having a nominal diameter between about 9 mm to about 12 mm and a working pressure range that spans a nominal inflation pressure to a rated burst pressure, where the balloon exhibits less than a 3N increase in mean straightening force when inflated across the working pressure range while in a curved conformation requiring 16% total strain, and where the nominal inflation pressure is at least 4 atm. Also, a medical balloon can comprise a balloon comprising a polymeric material, and having a nominal diameter having the nominal diameter between about 13 mm to about 14 mm and a working pressure range spans a nominal inflation pres-

sure to a rated burst pressure, where the balloon exhibits less than a 5N increase in mean straightening force when inflated across the working pressure range while in a curved conformation requiring 16% total strain, and where the nominal inflation pressure is at least 4 atm.

[0010] In accordance with another aspect of the disclosure, a medical balloon can comprise a balloon comprising a polymeric material and being inflatable to a rated burst pressure, the balloon having a nominal diameter of 3 mm to 12 mm where at the rated burst pressure, the balloon exhibits a straightening force as a function of balloon diameter (d) of less than $0.86(\text{Diameter})+0.20$ when in a curved conformation requiring 16% total strain, where the rated burst pressure is at least 4 atm.

[0011] In accordance with another aspect of the disclosure, a medical balloon can comprise a balloon comprising a polymeric material that can become plastically deformed upon inflation of the balloon to a pressure within the working pressure range such that when inflated in a curved configuration having a bend radius and requiring 16% strain, the balloon upon re-inflation, without any surrounding constraints and to a pressure within the working pressure range, comprises a curved configuration having a bend radius that is less than 200% larger than the initial bend radius. Said balloon is semi-compliant to compliant.

[0012] The various aspects of the present disclosure can comprise a variety of additional or alternative features in any combination. In various embodiments, the balloon wall material can remain kink-free when inflated in said curved configuration. Said medical balloon can be semi-compliant to non-compliant. The balloon wall material can comprise a porous microstructure, such as one comprising a node and fibril microstructure and/or be fibrillated. The porous microstructure can be expanded polytetrafluoroethylene. In various embodiments, a portion of the balloon wall material along an inner arc undergoes at least 5% compressive strain when inflated in a curved configuration requiring 20% total strain. In various embodiments, the curved configuration can be such that the portion of the balloon wall material along the inner arc undergoes compressive strain that is at least 30% of the total strain. Similarly, in various embodiments, the curved configuration can require 25% total strain and the portion of the balloon wall material along the inner arc undergoes at least 10% compressive strain. In various embodiments, the working length of the balloon lengthens less than 10% during inflation to at least an angioplasty pressure. In various embodiments, the balloon wall material can remain kink-free when the ratio of a balloon diameter within a working length to a bend radius is at least 1:3. In various embodiments, the medical balloon can further comprise a compliant bladder, such as an elastomeric bladder. The nominal inflation pressures of the conformable balloon in a curved configuration can be greater than 4 atm, greater than 8 atm, greater than 12 atm, greater than 16 atm, greater than 20 atm, or more and remain kink-free. In various embodiments, the balloon wall material comprises a circumferential stiffness greater than 200 gf/mm/mm. In various embodiments, the balloon wall material comprises a circumferential stiffness and a longitudinal stiffness and wherein the circumferential stiffness is at least 5 times greater than the longitudinal stiffness. For example, the longitudinal stiffness can be less than 30 gf/mm/mm for a medical balloon having a 4 mm diameter. In various embodiments, the microstructure of the balloon wall material can be oriented at an angle greater than 80 degrees relative to

the longitudinal axis when inflated to the nominal diameter. In various embodiments, the balloon wall material can comprise a membrane wherein the membrane has a balance ratio of at least 10:1. In various embodiments, the balloon wall material can be adapted to perfuse. In various embodiments, the balloon can form varied surface by way of a template having at least one aperture and overlying at least a portion of the balloon wherein the balloon wall material protrudes through the aperture in an inflated configuration. In various embodiments, the outer surface of the medical balloon can be coated with a therapeutic agent and/or utilized for the deployment or touching up of an endoprosthetic device. For example, in various embodiments, the medical balloon can comprise a stent or stent graft disposed about the balloon in a delivery configuration.

BRIEF DESCRIPTION OF THE DRAWINGS

[0013] The features and advantages of the present disclosure will become more apparent from the detailed description set forth below when taken in conjunction with the drawings, wherein:

[0014] FIG. 1a illustrates a medical balloon embodiment in accordance with a present disclosure, inflated in a curved configuration.

[0015] FIG. 1b illustrates a medical balloon embodiment in accordance with a present disclosure, inflated in a straight configuration.

[0016] FIG. 1c illustrates a schematic view of the cross-section of a medical balloon embodiment in accordance with a present disclosure.

[0017] FIG. 1d illustrates a medical balloon embodiment in accordance with a present disclosure, inflated in a curved configuration and having a therapeutic agent coated thereon.

[0018] FIG. 1e illustrates a medical balloon embodiment in accordance with a present disclosure, inflated in a curved configuration and having a medical device disposed about said medical balloon.

[0019] FIG. 2a illustrates a perfusable, a medical balloon embodiment in accordance with a present disclosure.

[0020] FIG. 2b illustrates a schematic view of the cross-section of a perfusable, medical balloon embodiment in accordance with the present disclosure.

[0021] FIG. 3a illustrates a medical balloon embodiment in accordance with a present disclosure adapted to form protrusions on the outer surface.

[0022] FIG. 3b illustrates a schematic view of the cross-section of a medical balloon embodiment in accordance with a present disclosure adapted to form protrusions on the outer surface.

[0023] FIG. 4 illustrates a method of making a medical balloon embodiment in accordance with a present disclosure.

[0024] FIG. 5 illustrates a method of using a medical balloon embodiment in accordance with a present disclosure.

[0025] FIGS. 6a-6c depict images of a nylon balloon in a bent configuration as described in Example 3.

[0026] FIGS. 7a-7c depict images of a medical balloon embodiment in accordance with a present disclosure in a bent configuration as described in Example 3.

[0027] FIG. 8 is a table of data showing balance ratios of the balloon wall materials of both commercially-available PTA balloon devices and various balloon embodiments in accordance with the present disclosure as described in Example 5.

[0028] FIGS. 9a-9d are reproduction sketches of fluoroscopy images of various balloon devices as set forth in

Example 6 inflated in a curved vessel. The animal model and vessel location within the animal model (i.e., where the balloon was inflated) were the same for FIGS. 9a and 9d and for FIGS. 9b and 9c. As such, the relative amount of vessel deformation (or straightening) can be inferred from the shape of the balloon and the catheter. The conformable balloons of FIGS. 9a and 9b exhibit a more curved shape and minimal, if not any, vessel straightening. In addition, the shoulders on the conformable balloons of FIGS. 9a and 9b are not deformed, and the guidewire is generally centered between the shoulders at both ends of the balloon. This is indicative of less stress at the ends as compared to the balloons of FIGS. 9c and 9d.

[0029] FIG. 10 is a schematic curve as described in Example 3.

[0030] FIGS. 11a-11d illustrate the setup of the Instron 3-point bend fixture for a 3 mm, a 5 mm, an 8 mm, and a 12 mm balloon, respectively.

[0031] FIG. 12 is a table of data showing the straightening force measurements taken of various balloons in a 3-point bend fixture as described in Example 11.

[0032] FIG. 13a is a plot showing the straightening force as a function of pressure of a 3 mm nominal diameter balloon made in accordance with the present disclosure compared to a Abbott "FoxCross" 3 mm balloon as described in Example 11.

[0033] FIG. 13b is a plot showing the straightening force as a function of pressure of a 5 mm nominal diameter balloon made in accordance with the present disclosure compared to a Abbott "FoxCross" 5 mm balloon as described in Example 11.

[0034] FIG. 13c is a plot showing the straightening force as a function of pressure of a 8 mm nominal diameter balloon made in accordance with the present disclosure compared to other 8 mm PTA balloons, namely, the Bard "Conquest" balloon; the Abbott "FoxCross" balloon; and the AngioDynamics "Workhorse" balloon as described in Example 11.

[0035] FIG. 13d is a plot showing the straightening force as a function of pressure of a 12 mm nominal diameter balloon made in accordance with the present disclosure compared to a Abbott "FoxCross" 12 mm balloon as described in Example 11.

[0036] FIG. 14a is a graph plotting the straightening force at the rated burst pressure for a 3, 5, 8, and 12 mm conformable balloon and the threshold trend lines, and FIG. 14b shows the straightening force at the rated burst pressure for the 3 mm conformable balloon and the lower end point of the threshold trend lines.

DETAILED DESCRIPTION OF THE ILLUSTRATED EMBODIMENTS

[0037] Persons skilled in the art will readily appreciate that various aspects of the present disclosure can be realized by any number of methods and apparatuses configured to perform the intended functions. Stated differently, other methods and apparatuses can be incorporated herein to perform the intended functions. It should also be noted that the accompanying drawing figures referred to herein are not all drawn to scale, but may be exaggerated to illustrate various aspects of the present disclosure, and in that regard, the drawing figures should not be construed as limiting. Finally, although the present disclosure may be described in connection with various principles and beliefs, the present disclosure should not be bound by theory.

[0038] As used herein, "straightening force" means the amount of force exerted by the balloon on to a constraint as the balloon attempts to return to a straight state. One technique for measuring the amount of straightening force is set forth in Example 11, where the constraint is a 3-point bend fixture.

[0039] As used herein, "strain" means the deformation of a material caused by applying an external force to it.

[0040] As used herein, "compressive strain" means an amount of material deformation caused by applying a compressive force to a material, i.e., negative strain. Compressive strain can be understood as in-plane compression as distinguished from macro buckling or folding of a material.

[0041] As used herein, "tensile strain" means an amount of material deformation caused by applying a tensile force to a material.

[0042] As used herein, "nominal diameter" means the approximate diameter of the balloon at the nominal inflation pressure. Beyond this state, pressure increases (e.g., up to the rated burst pressure) result in less than a 20% increase in diameter, less than a 15% increase in diameter, or less than a 10% increase in diameter.

[0043] As used herein, "angioplasty pressure" means the minimum pressure required to perform a PTA procedure for a balloon of a certain size. This value is dependent on the size of the balloon, and can be within the working pressure range between the nominal inflation pressure to the rated burst pressure, the nominal inflation pressure being the minimum pressure at which the balloon reaches nominal diameter and rated burst pressure being the upper limit of a pressure range for a medical balloon provided by the manufacturer.

[0044] As used herein, "balance ratio" means ratio of machine direction matrix tensile strength to transverse direction matrix tensile strength. Where the matrix tensile strengths in the machine and transverse direction are not substantially equal, a material can be said to be "anisotropic."

[0045] As used herein, "stiffness" is a measure of the change in load over an increase or decrease in tested length. Stiffness differs from modulus as it is not normalized for cross sectional area or for gauge length. Modulus is change in stress over change in strain.

[0046] As used herein, a "semi-compliant to non-compliant" balloon is one that has less than about 20% diametric growth (e.g., less than a 20% increase in the balloon diameter relative to the nominal diameter) when inflated from the nominal inflation pressure to the rated burst pressure. Balloons of the present disclosure are semi-compliant to non-compliant, and after reaching the nominal inflation pressure, can exhibit less 20% diametric growth, less than 15% diametric growth, or less than 10% diametric growth.

[0047] As used herein, "medical device" means any medical device capable of being implanted and/or deployed within a body lumen or cavity. In various embodiments, a medical device can comprise an endovascular medical device such as a stent, a stent-graft, graft, heart valve, heart valve frame or pre-stent, occluder, sensor, marker, closure device, filter, embolic protection device, anchor, drug delivery device, cardiac or neurostimulation lead, gastrointestinal sleeves, and the like.

[0048] As used herein, "kink" means a fold, pleat, wrinkle, or similar deformed condition.

[0049] As used herein, "mean straightening force" means the mean force measured over the time span that the balloon was held at a specific pressure.

[0050] Lastly, the preposition “between,” when used to define a range of values (e.g., between x and y) means that the range includes the end points (e.g., x and y) of the given range and the values between the end points.

[0051] The present disclosure is directed towards a semi-compliant to non-compliant, conformable balloon useful for medical applications. Conformable balloons of the present disclosure exhibit a low or insignificant straightening force when in a curved configuration and at inflation pressures greater than 4 atm. Balloons of the present disclosure are constructed of material(s) that can compress along an inner arc length when the balloon is in a curved configuration. In further embodiments, balloons of the present disclosure can be constructed of material that sufficiently elongates along an outer arc length when the balloon is in a curved configuration. As a result, medical balloons, in accordance with the present disclosure, can conform to the surrounding curved anatomy. When inflated in a curved configuration, these conformable medical balloons exhibit kink-free inflation and do not cause a significant degree of straightening of body anatomies or “tortuous paths” (e.g., blood vessels), if any at all, at inflation pressures greater than 4 atm.

[0052] In addition, the balloon embodiments of the present disclosure can provide substantially uniform vessel contact (“apposition”) along their working lengths or intermediate sections. By contrast, if a kink occurs, there will not be uniform vessel contact along the working length. The described embodiments can also provide generally uniform pressure along their working lengths to the entire circumference of a curved anatomy. By contrast, if a kink occurs, there will not be uniform pressure along the working length. Uniform contact and uniform pressures on a curved vessel, for example, can facilitate a more efficient delivery of a therapeutic agent for such embodiments coated with a therapeutic agent. Similarly, uniform contact and uniform pressures on a curved vessel, for example, can facilitate improved device deployment for such embodiments having a deployable device mounted thereon.

[0053] The balloon embodiments of the present disclosure can comprise a fluid-tight, compliant bladder so that the balloon does not perfuse. Alternatively, described embodiments can be bladderless and constructed to perfuse at a desired threshold pressure or diameter.

[0054] The balloon embodiments of the present disclosure can be part of a balloon assembly adapted to form a protruding topography on the balloon surface. A template having at least one aperture can be located about an underlying conformable balloon. The template is constructed not to circumferentially or longitudinally distend to the same extent as the underlying balloon, thus, at least one surface protrusion would form. Said constructs can be fluid tight or configured to perfuse as well.

[0055] According to the present disclosure, with reference to FIGS. 1a-1c, a medical balloon 100 comprises a balloon wall 110 defining a chamber 106 wherein a portion of the balloon wall 110 along an inner arc 111 undergoes at least 5% compressive strain when inflated in a curved configuration that requires 20% total strain. As the balloon 100 can be semi-compliant to non-compliant, it is capable of inflation pressures within the range of at least about 4 atm to about 30 atm or more and has less than about 20% diametric growth from the nominal inflation pressure to the rated burst pressure. For example, a working pressure range can be between about 5 atm to about 9 atm, about 9 atm to about 20 atm, or any

range within either of these ranges. The medical balloon 100 remains kink-free when inflated to an angioplasty pressure in the specified curved configuration. The balloon 100 of the present disclosure when inflated to at least the angioplasty pressure is capable of retaining a kink-free at curved configuration requiring total strain amounts higher than 20%.

[0056] The range of curvature wherein a kink-free inflation can be maintained depends on the dimension of the balloon. In various embodiments, the medical balloon can have a kink-free, curved configuration such that the bend radius is at least three times greater than the balloon diameter as measured within a working length of the balloon 100, e.g., the nominal diameter. In various embodiments, the medical balloon 100 can have a curved configuration such that the ratio of bend radius to balloon diameter is about 2:1; about 3:1; about 4:1; about 5:1; about 6:1; about 7:1; about 8:1; about 9:1; about 10:1; about 11:1; about 12:1; about 13:1; or about 14:1 or more.

[0057] The balloon wall 110 comprises a material layer that is compressible, elongatable, or a combination of the two, along the length of the balloon 100. Stated differently, the balloon wall 110 can undergo compressive strain along the portion of the wall 110 defining the inner arc 111 and/or tensile strain along the portion of the balloon wall defining the outer arc 112 when inflated in a curved configuration. In various embodiments, the relative amount of compressive strain can be between about 25% to about 100% of the total strain. Accordingly, when inflated in a curved configuration, the balloon wall 110 can adapt to the changes in length along the portion of the working length of the balloon defining an inner arc 111 and outer arc 112.

[0058] In various embodiments, the balloon wall 110 is capable of undergoing at least 5% compressive strain or at least 10% compressive strain, e.g., along the section or sections of the balloon wall 110 that extend along the inner arc 111 of the balloon in a curved conformation. For example, the balloon wall 110 comprises a porous material that facilitates compressive strain along a lengthwise section. Such section of balloon wall 110 can be at least a 5 mm lengthwise section extending along inner arc 111, such as the 1 cm lengthwise section measured in Example 3 to determine compressive strain. While not wishing to be bound by a particular theory, it is believed that compression is facilitated by the void spaces of the porous material that allow for the material bulk to compress and thus reduce the volume of the void spaces.

[0059] In various embodiments, a porous material can comprise an expanded polymeric film. In addition, the pores of at least a portion of the porous material can be devoid of any material that can impede compression; e.g., the porous material comprises a plurality of compressible voids. For example, the porous material can comprise a node and fibril microstructure that is free of any imbibed material. In addition, the architecture of porous microstructure can be substantially fibrillated (e.g., a non-woven web having a microstructure of substantially only fibrils, some fused at crossover points or with smaller nodal dimensions). Large nodes or large densified regions may have an impact on the extent of compressibility or compressive stiffness.

[0060] In various embodiments, the porous material comprises expanded polytetrafluoroethylene (ePTFE), expanded polyethylene, woven and non-woven fabrics or films, and the like. Non-limiting examples of expandable fluoropolymers include, but are not limited to, expanded PTFE, expanded modified PTFE, and expanded copolymers of PTFE. Patents

have been filed on expandable blends of PTFE, expandable modified PTFE, and expanded copolymers of PTFE, such as, for example, U.S. Pat. No. 5,708,044 to Branca; U.S. Pat. No. 6,541,589 to Baillie; U.S. Pat. No. 7,531,611 to Sabol et al.; U.S. patent application Ser. No. 11/906,877 to Ford; and U.S. patent application Ser. No. 12/410,050 to Xu et al.

[0061] While in some embodiments the porous material is free of any imbibed materials, in various other embodiments, the porous material can comprise light imbibing and/or sectional imbibing that facilitates balloon compaction or retraction upon deflation but does not significantly impact the ability to undergo compressive strain and/or tensile strain. Such imbibed materials can comprise an elastomer, such as a polyurethane (such as an aromatic polyurethane like Techthane), a thermoplastic fluoroelastomer copolymer of tetrafluoroethylene/perfluoromethylvinylether (TFE/PMVE) as taught in U.S. Pat. No. 7,049,380 and U.S. Pat. No. 8,048,440, both to Chang et al., silicone, FKM designated fluoroelastomers according to ASTM D1418 (e.g., Viton by DuPont), and/or silicone rubbers. The weight ratio of porous material to imbibed elastomer in the balloon wall **110** can be at least 1:3, 1:2, 2:3, 1:1, 3:2, 2:1, 3:1, 4:1, 5:1, 6:1, 7:1, 8:1, 9:1, 10:1, 15:1, 18:1, 19:1, 20:1, or any ratio or range therebetween. In some embodiments, the weight ratio of porous material to imbibed elastomer can be between 2:3 and 3:2. In various embodiments, the balloon wall **110** can be formed from wrapped layers wherein a certain percentage of layers comprise an imbibed porous material. For example, the balloon wall **110** can comprise wrapped layers of porous material, wherein up to 50%, up to 30%, up to 20%, up to 15%, up to 10%, up to 5%, or up to 2% of the wrapped layers are imbibed with an elastomer. In some embodiments, 5% to 30% of the wrapped layers are imbibed with an elastomer. Alternatively or in addition thereto, in various embodiments, a discrete circumferential section of the porous material of balloon wall **110** can be imbibed with an elastomer.

[0062] In different or the same embodiments, the material layer can be anisotropic, oriented such that the balloon wall is weaker in the longitudinal direction than the radial direction. The longitudinal stiffness is sufficiently low to provide for some elongation (tensile strain) on the outer arc **112**. The preferred amount of longitudinal stiffness can vary with the dimensions (width and length) of the balloon. For example, an 8 mm diameter balloon can have a longitudinal stiffness less than 70 gf/mm/mm, or a 4 mm diameter balloon can have a longitudinal stiffness less than 30 gf/mm/mm. In general, the longitudinal stiffness (also referred to herein as “tensile stiffness”) of the anisotropic layer will be sufficiently low so that the balloon does not significantly reorient toward a straight configuration when inflated in a curved configuration at angioplasty pressures greater than 4 atm or more.

[0063] While a low longitudinal stiffness facilitates tensile strain along the outer arc **112**, in various embodiments, there can be a lower limit to the amount of longitudinal stiffness. Again, the lower limit can depend on the dimensions of the balloon **100**. Tensile strain along the outer arc **112** can result in the working length **101** of the balloon **100** lengthening to some degree. While reduced longitudinal stiffness in the balloon wall **110** can contribute to a lower straightening force, being too low can result in excessive lengthening. Excessive lengthening can in many applications be undesirable, and the extent of lengthening should be controlled for a desired pressure. By appropriately selecting the longitudinal stiffness, the working length **101** of the balloon **100**, in accordance with the

present disclosure, can lengthen less than 10% during inflation to an angioplasty pressure.

[0064] In addition, in various embodiments, the balloon wall **110** can more readily compress along the inner arc **111** than distend along the outer arc **112**. In other words, the material layer can comprise a compressive stiffness less than the tensile stiffness.

[0065] The total strain can be calculated by the method described in Example 4. By way of example, an 8 mm balloon in a 32 mm bend radius requires about 11% to 25% total strain to have a low or insignificant straightening force and/or remain kink-free. The precise value is dependant on the manner in which material layer responds to being stressed when in a curved conformation. A material layer can exhibit equal amounts of compressive and tensile strain amounting to 22.2% total strain (11.1% on the inner radius and 11.1% on the outer radius); all compressive strain resulting in 20% total strain; all tensile strain resulting in 25% total strain; or any strain amount there between.

[0066] In accordance with the present disclosure, the circumferential stiffness of the balloon wall **110** is sufficiently high to facilitate control of the maximum diameter at the rated burst pressure. In accordance with various embodiments, the balloon wall **110** can comprise a circumferential stiffness of at least 200 gf/mm/mm for 8 mm balloons and 100 gf/mm/mm for 4 mm balloons. In various embodiments, the balloon wall **110** comprises a circumferential stiffness and a longitudinal stiffness and wherein the circumferential stiffness is at least 5 times greater than the longitudinal stiffness. In various embodiments, the balance ratio of the material layer can be 3:1 up to 100:1, e.g., at least 10:1. A sufficiently high circumferential stiffness may also facilitate at least partially a preferential failure mode at the ends of the balloon **100**, typically at its seals **104** and/or **105**.

[0067] To construct the material layer in the desired orientation, the material of the balloon wall **110** can comprise an oriented anisotropic film. Orientation refers to the general direction of the microstructure features, e.g., the fibrils. In various embodiments, the wall **110** comprises a material that is helically oriented at a high angle. For example, the material of wall **110** can have a fibril orientation of at least 75 degrees relative to the longitudinal axis of balloon **100**; and in further embodiments, the material of wall **110** can have a fibril orientation of between 80 degrees to 86 degrees. In this instance, the anisotropic film being wrapped at a high angle comprises a high strength in the direction that is oriented at the high wrap angle (in other words, the higher strength of the balloon wall **110** is generally oriented around the circumference and the weaker direction is generally oriented along the length of the balloon).

[0068] In accordance with the present disclosure, the material of balloon wall **110** can become plastically deformed upon inflation to a pressure within the working pressure range such that when inflated in a curved configuration defined by a bend radius and requiring 16% strain, the balloon **100** upon re-inflation, without any surrounding constraints and again to a pressure within the working pressure range, will have a curved configuration that comprises a bend radius that is less than 200% larger than the initial bend radius or less than 150% larger than the initial bend radius. In addition, upon re-inflation, the diameter of the balloon will remain within the semi-compliant to non-compliant range.

[0069] The described medical balloon can have any appropriate dimension for the clinical application and can be gen-

erally cylindrical along the working length **101**. The working length **101** of the balloon **100** can be about 10 mm to about 150 mm or more. Similarly, the diameter of the balloon **100** can be about 2 mm to about 30 mm or more. By way of example, a balloon **100** can have a 4 mm diameter and a 30 mm working length, or alternatively, an 8 mm diameter and about a 60 mm working length. Of course, the balloon **100** of the present disclosure can be constructed at any dimensions appropriate for the specific use.

[0070] The described medical balloon **100** mounted on an elongate member **150**, such as a catheter or a hypotube, can have good trackability through the vasculature. In various embodiments, the described medical balloon **100** can be concentrically crushed to a profile for delivery as opposed to being longitudinally pleated and folded thus having random, numerous, and relatively smaller folds and creases. While not wishing to be bound by any particular theory, it is believed that the longitudinal pleats result in added longitudinal rigidity to the corresponding section of the elongate member **150**, whereas random folds in a variety of directions contribute less to the longitudinal rigidity.

[0071] The described medical balloon **100** can be used for a number of applications traditionally performed by other semi-compliant to non-compliant balloons. Medical balloon **100** can be used to perform a PTA procedure, deploy or seat a medical device, deliver a drug, deliver RF energy, and/or in any other procedure that would benefit from its properties. When used to deploy, seat, touch-up, or otherwise position medical devices, the described balloon can be used in conjunction with any such devices, such as balloon expandable or self-expanding stents or stent grafts, or other endoluminal devices.

[0072] By way of example, with reference to FIG. 1*d*, the balloon **100** in accordance with the present disclosure can be coated with a therapeutic agent **160**. In further embodiments, a retractable sheath (not shown) can be located about the balloon **100** to prevent or minimize release of said therapeutic agent **160** until the balloon **100** is at the desired treatment site.

[0073] A “therapeutic agent,” as used herein, is an agent that can a bioactive response or be detectable by an analytical device. Such agents include, but are not limited to, radiopaque compounds, cilostazol, everolimus, dicumarol, zotarolimus, carvedilol, anti-thrombotic agents such as heparin, heparin derivatives, urokinase, and dextrophenylalanine proline arginine chloromethylketone; anti-inflammatory agents such as dexamethasone, prednisolone, corticosterone, budesonide, estrogen, sulfasalazine and mesalamine, sirolimus and everolimus (and related analogs), anti-neoplastic/antiproliferative/anti-mirotic agents such as major taxane domain-binding drugs, such as paclitaxel and analogues thereof, epothilone, discodermolide, docetaxel, paclitaxel protein-bound particles such as ABRAXANE® (ABRAXANE is a registered trademark of ABRAXIS BIOSCIENCE, LLC), paclitaxel complexed with an appropriate cyclodextrin (or cyclodextrin like molecule), rapamycin and analogues thereof, rapamycin (or rapamycin analogs) complexed with an appropriate cyclodextrin (or cyclodextrin like molecule), 1713-estradiol, 1713-estradiol complexed with an appropriate cyclodextrin, dicumarol, dicumarol complexed with an appropriate cyclodextrin, 13-lapachone and analogues thereof, 5-fluorouracil, cisplatin, vinblastine, vincristine, epothilones, endostatin, angiostatin, angiopeptin, monoclonal antibodies capable of blocking smooth muscle cell proliferation, and thymidine kinase inhibitors; anesthetic

agents such as lidocaine, bupivacaine and ropivacaine; anti-coagulants such as D-Phe-Pro-Arg chloromethyl ketone, an RGD peptide-containing compound, AZX100 a cell peptide that mimics HSP20 (Capstone Therapeutics Corp., USA), heparin, hirudin, antithrombin compounds, platelet receptor antagonists, anti-thrombin antibodies, anti-platelet receptor antibodies, aspirin, prostaglandin inhibitors, platelet inhibitors and tick antiplatelet peptides; vascular cell growth promoters such as growth factors, transcriptional activators, and translational promoters; vascular cell growth inhibitors such as growth factor inhibitors, growth factor receptor antagonists, transcriptional repressors, translational repressors, replication inhibitors, inhibitory antibodies, antibodies directed against growth factors, bifunctional molecules consisting of a growth factor and a cytotoxin, bifunctional molecules consisting of an antibody and a cytotoxin; protein kinase and tyrosine kinase inhibitors (e.g., tyrphostins, genistein, quinoxalines); prostacyclin analogs; cholesterol-lowering agents; angiopoietins; antimicrobial agents such as triclosan, cephalosporins, aminoglycosides and nitrofurantoin; cytotoxic agents, cytostatic agents and cell proliferation affectors; vasodilating agents; agents that interfere with endogenous vasoactive mechanisms; inhibitors of leukocyte recruitment, such as monoclonal antibodies; cytokines; hormones or a combination thereof. In one embodiment, said therapeutic agent is a hydrophilic agent. In another embodiment, said therapeutic agent is a hydrophobic agent. In another embodiment, said therapeutic agent is paclitaxel.

[0074] By way of second example, with reference to FIG. 1*e*, balloon **100** in accordance with the present disclosure can comprise medical device **170** disposed about balloon **100**. Balloon **100** can be used to expand or touch up medical device **170**. As shown, medical device **170** is a stent, and more particularly a segmented stent, e.g., a stent comprising a plurality of discrete annular stent members. As previously mentioned, the stent can be balloon-expandable or self-expanding.

[0075] In various embodiments, again with reference to FIGS. 1*a* to 1*c*, the medical balloon **100** comprises a generally cylindrical form that is secured to the elongate member **150** at its proximal and distal ends. The balloon **100** has a body portion **101** across the intermediate section, which is also referred to as the working length. This section is the section of the balloon **100** that reaches the nominal diameter in the inflated state. The balloon proximal shoulder **102** and distal shoulder **103** are the sections of the balloon **100** lying between the proximal seal **104** and distal seal **105** and the body portion **101**. In various embodiments, the shoulders **102**, **103** are not conical in shape but are more akin to a rounded corner of a square. In various other embodiments, the shoulders **102**, **103** comprise a conical shape or conical stepped shoulders. For example, shoulder **102**, **103** of material layer can comprise a non-distensible material that gives the shoulders a conical shape or a stepped conical shape. Radiopaque markers or other detectable marker mechanisms can be used to indicate the working length **101** of the balloon **100**. The markers can be located on the underlying elongate member **150** or within or on the balloon wall **110**.

[0076] In various embodiments, the balloon **100** can further comprise a compliant bladder **120**, such as an elastomeric bladder to facilitate a fluid tight device. In various embodiments, the compliant bladder **120** can be detached from wall **110** along at least a portion of the length including the working length **101** and shoulders **102** and **103** or the entire length.

In other embodiments, the compliant bladder **120** is attached to the wall **110** along at least a portion of said length or the entire length. The compliant bladder **120** can be an inner layer about which the material layer is situated. The compliant bladder can possess properties that do not consequentially impact the balloon inflating kink-free in a curved configuration.

[0077] In various embodiments, with reference to FIGS. **2a** to **2b**, the balloon **100** does not have a compliant bladder and thus is capable of perfusion. For example, balloons **100** are disclosed that expand to a nominal diameter and perfuse in response to an internal pressure exceeding a threshold pressure. In such a manner, in various embodiments, the balloon **100** can be inflated to a first pressure sufficient for the balloon **100** to reach the nominal diameter. Then, at a desired time, the internal pressure can be increased from the first pressure, causing perfusion of the inflation fluid **240** through the balloon wall **110** without a significant increase in balloon diameter. Stated another way, balloons, in accordance with various embodiments, have a water entry pressure (“WEP”) and/or bubble point tailored to be at or above that which is required for inflation to a fixed diameter. For example, in various embodiments, the balloon **100** can inflate to a nominal diameter at a pressure below the WEP and/or bubble point and then additional internal pressure can be exerted to reach or exceed the WEP and/or bubble point. Thus, expansion and perfusion can be independently controllable. In various embodiments, the inflation fluid can comprise a therapeutic fluid **240**.

[0078] In various embodiments, with reference to FIGS. **3a** to **3b**, the balloon **100** can further comprise a template **330** having at least one aperture **331** and overlying at least a portion of the balloon wall **110** wherein the balloon wall **110** protrudes through the aperture **331** in an inflated configuration, producing protrusion **332**. The template **330** can similarly be anisotropic, except the template **330** comprises the same or a slightly higher amount of longitudinal stiffness and/or a circumferential stiffness greater than that of the balloon wall **110**. As such, the template **330** will expand and/or elongate at a lower rate per increase in internal pressure, thereby resulting in the underlying balloon **100** to protrude through the aperture(s) **331**. Alternatively or in addition thereto, the template **330** can have a “nominal diameter” that is less than the underlying balloon **100**. The difference between the nominal diameters being the approximate height of a protrusion **332**. For example, the template **330** can be similarly formed from a wrapped film as described herein; however, the film is wrapped to form a tubular precursor at a diameter less than the diameter at which the tubular precursor of balloon **100** can be formed. The apertures **331** can be formed in the template **330** in any suitable manner, e.g., laser cutting the tubular precursor.

[0079] Aperture **331** can comprise an opening or weakened site in the template **330**. In this regard, an opening can be a hole, cut, or any other discontinuous section of the template **330**. For example, a hole could be formed by puncturing template **330**. Alternatively, aperture **331** can comprise an area of template **330** where a portion of the template material has been removed or otherwise weakened such that the weakened portion at least partially deforms or detaches in response to inflation of balloon **100** and permits distension beyond the first inflated state. Apertures **331** can be formed by any suitable means, including cutting, stamping, laser cutting, perforating, and/or punching/puncturing and/or the like. In various embodiments, the template **330** can comprise a net like struc-

ture. The template **330** can comprise apertures **331** that vary in size or are the same size. In addition, decreasing the size the apertures can allow for a “coarser” balloon surface.

[0080] With reference to FIG. **4**, a method of making a medical balloon in accordance with the present disclosure can comprise wrapping a film about a mandrel at an angle at least about 75 degrees with respect to a longitudinal axis and up to about 88 degrees to form a tubular precursor (**400**). The wrapped film can be bonded and then removed as a tubular precursor from said mandrel. Once formed, tension to the length of the tubular precursor can be applied to reduce its diameter (**401**). In various embodiments, at least a portion of the tubular precursor can then be longitudinally compressed to reduce its length (**402**). The precursor can then be placed on an elongate member having a lumen wherein the precursor is in fluid communication with the lumen of the elongate member and secured thereto (**403**). The tubular precursor can optionally be secured over a balloon catheter comprising a compliant bladder.

[0081] A pre-conditioning inflation can be performed by inflating the balloon to a nominal diameter (**404**). The inflation can be performed within a concentric tubular form having an inner diameter approximately equal to the nominal diameter of the balloon. The balloon and the balloon cover can be radially compacted to a delivery profile (**405**). The radial compaction of the balloon cover forms random creases and folds in random directions.

[0082] With reference to FIG. **5a** method of using a medical balloon in accordance with the present disclosure can comprise placing a balloon as described herein in a vessel wherein the working length of the balloon extends along a curve of the vessel (**500**). The curvature of the vessel would cause at least 20% total strain to the balloon wall and the balloon wall along an inner arc would have at least 5% compressive strain upon inflation. Once in position, the balloon can be inflated (**501**) to at least 4 atm, at least 8 atm, at least 16 atm, at least 20 atm, or more, or any range or value therebetween. In various embodiments, inflating the balloon causes substantially uniform pressure to be applied to the surrounding vessel along the curve of the vessel (**502**). In various embodiments, inflating the balloon causes substantially uniform contact to the surrounding vessel wall along the curve of the vessel (**503**).

Example 1

Precursor Material

[0083] An expanded PTFE membrane—that is amorphously locked and generally made in accordance with U.S. Pat. No. 5,476,589 to Bacino which is hereby incorporated by reference in its entirety—had the following properties: Bubble point is approximately 138 kPa, thickness is approximately 6.3 μm , mass per area is approximately 3 g/m², matrix tensile strength in the strongest direction is approximately 907 mPa, matrix tensile strength in the direction orthogonal to the strongest direction is approximately 17.2 mPa. The precursor material was cut into a tape, wherein the strongest direction is along the length of the tape.

Example 2

Constructing Medical Balloon Comprising a Nominal Diameter of 8 Mm in Accordance with the Present Disclosure

[0084] A tubular precursor was formed as follows: The precursor material from Example 1 having a 1.25 in slit width

was helically wrapped about an 8.5 mm mandrel at approximately 85 degrees relative to the longitudinal axis of the mandrel. The wraps were repeated on a bias in the opposite direction to complete a total of four passes over a length of 100 mm. This tubular precursor was then thermally treated in an oven at 380° C. for 11 minutes and then removed from the oven. The tubular precursor was removed from the mandrel and axially stretched to decrease its diameter to about 1.8 mm. The tubular precursor was then placed on a mandrel having an outer diameter of about 1.8 mm and cut to 108 mm. The tube assembly was then axially compressed to about 72% of its original length.

[0085] A compliant polyurethane balloon catheter was obtained with a generally cylindrical balloon having a diameter of 5 mm and length of 60 mm (Bavaria Medizin Technologie GmbH (BMT), Oberpfaffenhofen, Germany). The tubular precursor was slid over the balloon assembly (with the balloon in its collapsed state). The ends of the tubular precursor were secured to the catheter using LOCTITE® adhesive 4981 (Henkel Corporation, Düsseldorf, Germany) applied to an approximately 6 mm wide ePTFE tape as it was wrapped 15 times about the ends and the catheter body. The balloon was then inflated to an approximate 8 mm diameter at 16 atmospheres. With inflation medium in the balloon and the inflation valve open, the tubular precursor, now a balloon cover, and compliant bladder were then radially compacted at 689 kPa to about the catheter.

Example 3

Compressive and Tensile Strain Test Method and Results

[0086] Test method: First, a 0.9 mm PTFE coated stainless steel mandrel was inserted through the lumen of the balloon catheter to be tested. The balloon was inflated to nominal inflation pressure. The inflation valve was closed. The exterior surface of the working length of the balloon was measured and marked around its circumference at 10 mm intervals. The inflation valve was then opened and the balloon allowed to deflate. The mandrel was removed and replaced with a 0.035" guidewire (AMPLATZ SUPER STIFF® Guidewire, Boston Scientific, Natick, Mass., USA), ensuring that the flexible section of the guidewire was beneath the balloon portion of the catheter.

[0087] The balloon to be tested was then inserted into an 8 mm ID×12 mm OD polyurethane tubing (Part number 50315K281, McMaster-Carr, Santa Fe Springs, Calif., USA). The area in which the balloon was to be positioned within the tube was lubricated with a light coat of release compound (Release Compound 7, Dow-Corning, Elizabethtown, Ky.). The polyurethane tubing was bent around a 60 mm diameter rod while holding the tubing tight against the outside circumference so that the balloon was centered in the bent section of the tubing as shown in FIGS. 6a-6c and 7a-7c. The balloon was inflated within the tube to its rated burst pressure. A flexible ruler was bent around the rod adjacent the tube and the spacing of the marks on the balloon on the inside arc of the bend were measured, as shown in FIGS. 6c and 7c. The flexible ruler was similarly used to measure the marks across the outside arc of the balloon, as shown in FIGS. 6b and 7b. The measurements obtained are provided in Table 1.

TABLE 1

Balloon	Balloon Pressures	Distance between marks on the outside arc	Distance between marks on the inside arc	Compressive Strain on inside arc	Tensile Strain on outside arc
8 mm × 62 mm standard BMT PTA balloon (Nylon, Lot 130327)	16 atm	12.25 mm (See FIG. 6b)	10 mm (See FIG. 6c)	0%	22.5%
8 mm × 60 mm balloon prepared in accordance with Example 2)	16 atm	10.5 mm (See FIG. 7b)	8.5 mm (See FIG. 7c)	15%	5%

[0088] Compressive strain was detected on the balloon made in accordance with Example 2, while none was detected on the BMT PTA balloon (Bavaria Medizin Technologie GmbH (BMT), Oberpfaffenhofen, Germany).

Example 4

Method for Calculating Theoretical Compressive and Tensile Strain

[0089] In order to obtain perspective on the strain values observed in Example 3, the theoretical strain values required to maintain a neutral axis can be compared to the observed values. The theoretical compressive and tensile strain values can be calculated based on the following. FIG. 10 is a schematic of the test setup described in Example 3. Tubing 1000 is shown in a bent configuration. Neutral axis "NA" lies co-radially with tubing 1000. When a balloon having a catheter aligned co-radially is inserted into the tube 1000, the center axis of the balloon will match this neutral axis. The working length of the balloon will have an arc length aligned along the neutral axis. The angle θ is calculated according to this formula:

$$\theta = S/r$$

[0090] where S is the arc length, r is the radius, and theta is the angle in radians.

[0091] Using this approach, θ equals 1.56 radians if a balloon having a working length of 50 mm is inserted into the test apparatus and the bend has a radius of 32 mm (includes the wall thickness of tubing 1000).

[0092] To solve for the arc radius on the inside length of the balloon S_i (under compression) and the outside length of the balloon S_o (under tension) the following relationship is used:

$$S_i/r_1 = \theta = S_o/r_2$$

[0093] For a balloon having a diameter of 8 mm and a 50 mm working length with a bend radius of 32 mm, assuming equal amounts of compressive and tensile strain, the inside arc length S_i is calculated by the following: $32 \times 50 / (32 + 4) = S_i = 44.44$ mm. For the same balloon and radius, the outer arc length S_o is calculated by the following: $(32 + 8) \times 50 / (32 + 4) = S_o = 55.56$ mm. Therefore, S_o is 11.1% longer than the working length of the balloon along the neutral axis and S_i is 11.1% shorter than the working length of the balloon along the neutral axis.

[0094] Through a similar calculation, assuming all compressive strain, the total strain would be 20%, and when

assuming all tensile strain, the total strain would be 25%. The 25% total strain on the outer arc is close to that which was observed for the PTA Nylon balloon test in Example 3 at 22.5%.

Example 5

Method of Determining the Longitudinal and Circumferential Stiffness of a Balloon Wall and Test Results

[0095] Test Method: The balloon to be tested was inflated by placing a 100 mm section of drawn ePTFE tubing over a pleated and folded balloon (8 mm×60 mm) to form a cover. Movement of the cover was limited during inflation by ensuring cover material was clamped in a vice that was supporting/clamping the catheter. The balloon was inflated and the mid-balloon diameter was recorded with a laser micrometer. Once a diameter of 8 mm was achieved, the balloon was deflated. The cover is removed from the balloon.

[0096] Next, for each longitudinal sample the cones of the balloon were cut so that the sample was 50 mm long. The cuts were located in the flat working length of the balloon and resulted in square edges. Each sample was longitudinally slit with scissors to form a sheet and then trimmed to create a sample that was 50 mm long×20 mm wide. An INSTRON® tensile tester was set up with smooth grips, and the jaw pressure was set to 552 kPa. The rate was set to 10 mm/min with a gauge length of 10 mm. Prior to loading the sample in the INSTRON® device, the width was taken in the middle of the sample length. The gauge length of the specimen during the testing was 10 mm. The test was set to run for 1 mm of crosshead displacement (~10% strain). The resulting slope (i.e., force over change in length) was divided by the specimen width to obtain the stiffness, as this response is not normalized per specimen thickness or % strain. The slope was calculated in the region that matches the balloon tested “longitudinal” compliance. For example, if a balloon had a 3% longitudinal compliance (i.e., the percent of balloon lengthening when inflated from the nominal inflation pressure to the rated burst pressure), the slope would be determined within the 3% strain region.

[0097] For each circumferential sample, after inflating the balloon as described above, the cones of the balloon were cut within the flat working length of the balloon but maximizing the sample length and resulting in square edges. The sample was further cut to form 2 annular samples, each with a length of 10 mm. The INSTRON® device was set with a circumferential fixture. The rate was set to 10 mm/min and the gauge length was set so that the fixtures were almost in contact with each other. The test was set to run for 1 mm of crosshead displacement (~8% strain). This resulting slope (i.e., force over change in length) was divided by the specimen width and multiplied by 2 to account for the hoop specimen to determine stiffness, as this response was not normalized per specimen thickness or % strain. The slope was calculated in the region that matches the balloon tested compliance. For example, if a balloon had a 3% circumferential compliance (i.e., the percent of circumferential diametric growth of the balloon when inflated from the nominal inflation pressure to the rated burst pressure), the slope would be determined within the 3% strain region.

[0098] The above tests were performed on the following balloons: High Pressure PTA Catheter, Creagh Medical Ltd, Galway, Ireland; “Fox” Balloon Catheter, p/n 12760-06,

Abbott Vascular, Santa Clara, Calif., USA; “Workhorse” P/N 16500432; PTA Balloon Catheter, AngioDynamics, Latham, N.Y.; 3 conformable balloons prepared in accordance with Example 2 with precursor materials as indicated below. The results are shown in FIG. 8.

[0099] Lo MD: An expanded ePTFE membrane—that is amorphously locked and generally made in accordance with U.S. Pat. No. 5,476,589 to Bacino which is hereby incorporated by reference in its entirety—had the following properties: Bubble point is approximately 138 kPa, thickness is approximately 6.3 μm, mass per area is approximately 3 g/m², matrix tensile strength in the strongest direction is approximately 917 mPa, matrix tensile strength in the direction orthogonal to the strongest direction is approximately 17.2 mPa. The precursor material was cut into a tape of 2.5 cm width, wherein the strongest direction is along the length of the tape.

[0100] Med MD: An expanded ePTFE membrane—that is amorphously locked and generally made in accordance with U.S. Pat. No. 5,476,589 to Bacino which is hereby incorporated by reference in its entirety—had the following properties: Bubble point is approximately 138 kPa, thickness is approximately 6.3 μm, mass per area is approximately 3 g/m², matrix tensile strength in the strongest direction is approximately 834 mPa, matrix tensile strength in the direction orthogonal to the strongest direction is approximately 36.5 mPa. The precursor material was cut into a tape of 2.5 cm width, wherein the strongest direction is along the length of the tape.

[0101] Hi MD: An expanded ePTFE membrane—that is amorphously locked and generally made in accordance with U.S. Pat. No. 5,476,589 to Bacino which is hereby incorporated by reference in its entirety—had the following properties: Bubble point is approximately 138 kPa, thickness is approximately 6.3 μm, mass per area is approximately 3 g/m², matrix tensile strength in the strongest direction is approximately 758 mPa, matrix tensile strength in the direction orthogonal to the strongest direction is approximately 67.6 mPa. The precursor material was cut into a tape of 2.5 cm width, wherein the strongest direction is along the length of the tape.

Example 6

In Vivo Inflation of a Medical Balloon within a Curved Vasculature

[0102] The following balloons were each inflated in the bifurcated iliac of a canine model and the images were taken at the indicated pressures. As shown in FIG. 9d, a Conquest balloon (P/N CQ-7586, Bard Medical, Tempe, Ariz.) was inflated to 10 atm and exhibited a kink in the working length and vessel straightening. The balloon could not be inflated to the rated burst pressure because the observed degree of vessel straightening. As shown in FIG. 9c, a semi-compliant balloon was inflated to 8 atm and exhibits vessel straightening. The balloon could not be inflated to the rated burst pressure because the observed degree of vessel straightening. As shown in FIGS. 9a and 9b, the conformable balloon prepared in accordance with Example 2 exhibited kink-free inflation and improved conformance to the curved vessel at both 10 atm and at 18 atm.

Example 7

Constructing Medical Balloon Comprising a
Nominal Diameter of 3 Mm in Accordance with the
Present Disclosure

[0103] A tubular precursor was formed as follows: The precursor material from Example 1 at a 0.5 inch slit width was helically wrapped about an 3.25 mm mandrel at 76 degrees relative to the longitudinal axis of the mandrel. The wraps were repeated on a bias in the opposite direction to complete a total of six passes. This tubular precursor was then thermally treated in an oven at 380° C. for 5 minutes and then removed from the oven. The tubular precursor was removed from the mandrel and axially stretched to decrease its diameter to about 1.8 mm. The tubular precursor was then placed on a mandrel having an outer diameter of about 1.8 mm and cut to 87 mm. The balloon working length portion of the tube assembly was then axially compressed to about 90% of its original length.

[0104] A compliant polyurethane balloon catheter was obtained with a generally cylindrical balloon having a diameter approximately 5 mm and length of 60 mm (Bavaria Medizin Technologie GmbH (BMT), Oberpfaffenhofen, Germany). The tubular precursor was slid over the balloon assembly (with the balloon in its collapsed state). The ends of the tubular precursor were secured to the catheter using LOCTITE® adhesive 4981 (Henkel Corporation, Düsseldorf, Germany) applied to an approximately 6 mm wide ePTFE tape as it was wrapped 15 times about the ends and the catheter body. The balloon was then inflated to an approximate 3 mm diameter at approximately 10 atmospheres. With inflation medium in the balloon and the inflation valve open, the tubular precursor, now a balloon cover, and compliant bladder were then radially compacted at approximately 689 kPa to about the catheter.

Example 8

Constructing Medical Balloon Comprising a
Nominal Diameter of 5 Mm in Accordance with the
Present Disclosure

[0105] A tubular precursor was formed as follows: The precursor material from Example 1 having a 1 inch slit width was helically wrapped about an 5.2 mm mandrel at 81 degrees relative to the longitudinal axis of the mandrel. The wraps were repeated on a bias in the opposite direction to complete a total of four passes. This tubular precursor was then thermally treated in an oven at 380° C. for 7 minutes and then removed from the oven. The tubular precursor was removed from the mandrel and axially stretched to decrease its diameter to about 1.8 mm. The tubular precursor was then placed on a mandrel having an outer diameter of about 1.8 mm and cut to 108 mm. The balloon working length portion of the tube assembly was then axially compressed to about 80% of its original length.

[0106] A compliant polyurethane balloon catheter was obtained with a generally cylindrical balloon having a diameter of 5 mm and length of 60 mm (Bavaria Medizin Technologie GmbH (BMT), Oberpfaffenhofen, Germany). The tubular precursor was slid over the balloon assembly (with the balloon in its collapsed state). The ends of the tubular precursor were secured to the catheter using LOCTITE® adhesive 4981 (Henkel Corporation, Düsseldorf, Germany) applied to

an approximately 6 mm wide ePTFE tape as it was wrapped 15 times about the ends and the catheter body. The balloon was then inflated to an approximate 5 mm diameter at approximately 12 atmospheres. With inflation medium in the balloon and the inflation valve open, the tubular precursor, now a balloon cover, and compliant bladder were then radially compacted at approximately 689 kPa to about the catheter.

Example 9

Constructing Medical Balloon Comprising a
Nominal Diameter of 8 Mm in Accordance with the
Present Disclosure

[0107] A tubular precursor was formed as follows: The precursor material from Example 1 having a 1.25 inch slit width was helically wrapped about an 8.5 mm mandrel at approximately 85 degrees relative to the longitudinal axis of the mandrel. The wraps were repeated on a bias in the opposite direction to complete a total of four passes. This tubular precursor was then thermally treated in an oven at 380° C. for 11 minutes and then removed from the oven. The tubular precursor was removed from the mandrel and axially stretched to decrease its diameter to about 1.8 mm. The tubular precursor was then placed on a mandrel having an outer diameter of about 1.8 mm and cut to 135 mm. The balloon working length portion of the tube assembly was then axially compressed to about 70% of its original length.

[0108] A compliant polyurethane balloon catheter was obtained with a generally cylindrical balloon having a diameter of 5 mm and length of 60 mm (Bavaria Medizin Technologie GmbH (BMT), Oberpfaffenhofen, Germany). The tubular precursor was slid over the balloon assembly (with the balloon in its collapsed state). The ends of the tubular precursor were secured to the catheter using LOCTITE® adhesive 4981 (Henkel Corporation, Düsseldorf, Germany) applied to an approximately 6 mm wide ePTFE tape as it was wrapped 15 times about the ends and the catheter body. The balloon was then inflated to an approximate 8 mm diameter at 16 atmospheres. With inflation medium in the balloon and the inflation valve open, the tubular precursor, now a balloon cover, and compliant bladder were then radially compacted at 689 kPa to about the catheter.

Example 10

Constructing Medical Balloon Comprising a
Nominal Diameter of Approximately 12 Mm in
Accordance with the Present Disclosure

[0109] A tubular precursor was formed as follows: The precursor material from Example 1 having a 1.25 inch slit width was helically wrapped about a 13 mm mandrel at 86 degrees relative to the longitudinal axis of the mandrel. The wraps were repeated on a bias in the opposite direction to complete a total of six passes. This tubular precursor was then thermally treated in an oven at 380° C. for 17 minutes and then removed from the oven. The tubular precursor was removed from the mandrel and axially stretched to decrease its diameter to about 1.8 mm. The tubular precursor was then placed on a mandrel having an outer diameter of about 1.8 mm and cut to 185 mm. The balloon working length portion of the tube assembly was then axially compressed to about 55% of its original length.

[0110] A compliant polyurethane balloon catheter was obtained with a generally cylindrical balloon having a diameter of 5 mm and length of 60 mm (Bavaria Medizin Technologie GmbH (BMT), Oberpfaffenhofen, Germany). The tubular precursor was slid over the balloon assembly (with the balloon in its collapsed state). The ends of the tubular precursor were secured to the catheter using LOCTITE® adhesive 4981 (Henkel Corporation, Düsseldorf, Germany) applied to an approximately 6 mm wide ePTFE tape as it was wrapped 15 times about the ends and the catheter body. The balloon was then inflated to an approximate 12 mm diameter at approximately 5 atmospheres. With inflation medium in the balloon and the inflation valve open, the tubular precursor, now a balloon cover, and compliant bladder were then radially compacted at 689 kPa to about the catheter.

Example 11

Comparison Study of Straightening Force of Medical Balloons as Measured in 3-Point Bend Fixture

[0111] Test Method: In order to measure the straightening force, an Instron® 3-point bend fixture with an Instron® 100N load cell was set up, such that the balloon to be tested would have a bend radius that would achieve a 16% theoretical strain (according the equation described in Example 4) at the nominal inflation pressure. The setup of the Instron® 3-point bend fixture is shown in FIGS. 11a to 11d for the 3 mm, 5 mm, 8 mm, and 12 mm balloon, respectively. The dimensions shown in FIGS. 11a to 11d are in millimeters.

[0112] Prior to testing, each balloon was conditioned by submersing in a 37° C. water bath for 2 minutes. Once conditioned, a guidewire (Amplatz, 0.035" Super Stiff) was inserted into to catheter of the balloon such that the "floppy" end was aligned with the balloon portion. A pressure gauge and inflator was connected to the catheter. The sample was inserted into the 3-point bend fixture in a curved conformation approximate the appropriate bend radius. Each balloon was inflated to pressures spanning the working pressure range and as shown in the table of data provided in FIG. 12. Each balloon was held at each pressure for 10 seconds except for the rated burst pressure, which was held for 30 seconds. The force was measured continuously throughout the entire test with mean force for each pressure provided in FIG. 12. The working pressure range for the 3 mm balloon of Example 7 was 10 atm to 17 atm. The working pressure range for the 5 mm balloon of Example 8 was 9 atm to 17 atm. The working pressure range for the 8 mm balloon of Example 9 was 6 atm to 16 atm. The working pressure range for the 12 mm balloon of Example 10 was 5 atm to 8 atm.

[0113] The above test was performed on the following balloons: "Conquest" Balloon Catheter, P/N CQ-7586, Bard Medical, Tempe, Ariz.; "FoxCross" Balloon Catheter, P/N 10324-80 (3 mm), 10326-60 (5 mm), 10329-60 (8 mm), 10332-60 (12 mm), Abbott Vascular, Santa Clara, Calif., USA; "Workhorse" P/N 16500432; PTA Balloon Catheter, AngioDynamics, Latham, N.Y.; and 4 balloons prepared in accordance with Examples 7-10.

[0114] Plots of the balloons tested are provided in FIGS. 13a-13d. As shown in each of these figures, the observed rate of change of the straightening force per unit of pressure is much lower for each of the conformable balloons (prepared in accordance with Examples 7-10) as compared to the Abbott FoxCross having the same diameter. As shown in FIG. 13c, in particular, the conformable balloon prepared in accordance

with Example 9 demonstrated the lowest rate of change of the straightening force per unit of pressure as compared to other PTA balloons sold by Bard, Abbott, and Angiodynamics.

[0115] This example demonstrates that medical balloons—made in accordance with the present disclosure and having a nominal diameter between about 3 mm to about 8 mm and a nominal inflation pressure at or below 10 atm—exhibit less than a 13% increase in mean straightening force when inflated from a pressure of 10 atm to 14 atm while in a curved conformation requiring 16% total strain. In addition, such balloons exhibit a mean straightening force of less than 5 N when inflated up to a pressure of 17 atm while in a curved conformation requiring 16% total strain. Specifically, under such conditions, the 5 mm diameter balloon exhibited a mean straightening force of less than 4N, and the 8 mm diameter balloon exhibited less than 5N.

[0116] Similarly, medical balloons—made in accordance with the present disclosure and having a nominal diameter between about 9 mm to about 12 mm and a nominal pressure at or below 6 atm—exhibit less than a 3N increase in mean straightening force when inflated from a pressure of 5 atm to 8 atm while in a curved conformation requiring 16% total strain. In addition, such balloons exhibit a mean straightening force of less than 8 N when inflated up to a pressure of 8 atm while in a curved conformation requiring 16% total strain.

[0117] Moreover, it can be inferred from this example, that a medical balloon—made in accordance with the present disclosure and having a nominal diameter between about 13 mm to about 14 mm and a nominal inflation pressure at or below 6 atm—exhibits less than about 3.5N increase in mean straightening force when inflated from a pressure of 6 atm to 8 atm while in a curved conformation requiring approximately 16% total strain. In addition, such balloons can exhibit a mean straightening force of less than 11 N when inflated up to 8 atm while in a curved conformation requiring 16% total strain.

[0118] FIG. 14a is a graph plotting the straightening force at the rated burst pressure for the 3, 5, 8, and 12 mm conformable balloon. Based on this data, predictive trend lines of a maximum straightening force at the rated burst pressure for balloons ranging from 3-12 mm are plotted. A conformable balloon of the present disclosure within about 3 to about 12 mm in diameter will have a straightening force at the rated burst pressure that can be less than $0.86(\text{Diameter}) + 0.20$; less than $0.74(\text{Diameter}) + 0.49$; or even less than $0.66(\text{Diameter}) + 0.64$. The trend line formulas are based on the following increases (see Table 2) to the observed 3 mm straightening force at rated (2.575 N) and the observed 12 mm straightening force at rated (7.8 N).

TABLE 2

Trend line formula	% increase at 3 mm	% increase at 12 mm
$0.86(\text{Diameter}) + 0.20$	8	35
$0.74(\text{Diameter}) + 0.49$	5	20
$0.66(\text{Diameter}) + 0.64$	2	10

[0119] Numerous characteristics and advantages have been set forth in the preceding description, including various alternatives together with details of the structure and function of the devices and/or methods. The disclosure is intended as illustrative only and as such is not intended to be exhaustive. For example, embodiments of the present disclosure are described in the context of medical applications but can also

be useful in non-medical applications. It will be evident to those skilled in the art that various modifications may be made, especially in matters of structure, materials, elements, components, shape, size, and arrangement of parts including combinations within the principles of the invention, to the full extent indicated by the broad, general meaning of the terms in which the appended claims are expressed. To the extent that these various modifications do not depart from the spirit and scope of the appended claims, they are intended to be encompassed therein.

1. A medical balloon having a working length and comprising a balloon wall defining a chamber,

wherein the balloon wall is configured such that, when the medical balloon is inflated in a curved configuration requiring 20% total strain, the medical balloon, along a portion of the working length, defines an inner arc and an outer arc and a portion of balloon wall extending along the inner arc undergoes at least 5% compressive strain and

wherein said medical balloon is semi-compliant to non-compliant.

2. The medical balloon of claim 1, wherein the balloon wall is configured to remain kink-free when inflated in the curved configuration.

3. The medical balloon of claim 1, wherein the portion of the balloon wall extending along the inner arc has a length of at least 5 mm or a length of at least 1 cm.

4. (canceled)

5. The medical balloon of claim 1, wherein the balloon wall material comprises a porous microstructure.

6. (canceled)

7. The medical balloon of claim 5, wherein the porous microstructure is highly fibrillated.

8. The medical balloon of claim 5, wherein the porous microstructure is expanded polytetrafluoroethylene.

9. (canceled)

10. The medical balloon of claim 1, wherein the portion of balloon wall extending along the inner arc undergoes at least 10% compressive strain.

11. The medical balloon of claim 1, wherein the curved configuration requires 25% total strain and the portion of balloon wall extending along the inner arc undergoes at least 10% compressive strain.

12. The medical balloon of claim 1, wherein the working length of the balloon lengthens less than 10% during inflation to at least an angioplasty pressure.

13. The medical balloon of claim 1, wherein the balloon wall material is configured to remain kink-free when a ratio of a balloon diameter within the working length to a bend radius is at least 1:3.

14. The medical balloon of claim 1, further comprising a compliant bladder.

15. (canceled)

16. The medical balloon of claim 1, wherein the medical balloon is inflatable to a pressure greater than 4 atm or greater than 8 atm.

17. (canceled)

18. The medical balloon of claim 1, wherein the balloon wall material comprises a circumferential stiffness greater than 200 gf/mm/mm.

19. The medical balloon of claim 1, wherein the balloon wall material comprises a circumferential stiffness and a longitudinal stiffness and wherein the circumferential stiffness is at least 5 times greater than the longitudinal stiffness.

20. The medical balloon of claim 19, wherein the longitudinal stiffness is less than 70 gf/mm/mm for the medical balloon having an 8 mm diameter or the longitudinal stiffness is less than 30 gf/mm/mm for the medical balloon having a 4 mm diameter.

21. (canceled)

22. The medical balloon of claim 1, wherein the balloon wall material comprises a helically wrapped film at an angle greater than 80 degrees relative to the longitudinal axis and wherein the helically wrapped film comprises a balance ratio of at least 10:1.

23.-26. (canceled)

27. The medical balloon of claim 1, further comprising an endovascular medical device disposed about the balloon or a therapeutic agent coated on an outer surface of the medical balloon.

28. (canceled)

29. A medical balloon having a length along a longitudinal axis comprising

a polymeric balloon wall material,

wherein the balloon wall material comprises a circumferential stiffness and a longitudinal stiffness and

wherein the circumferential stiffness is at least 5 times greater than the longitudinal stiffness.

30. The balloon of claim 29, wherein the circumferential stiffness is at least 8 times greater than the longitudinal stiffness or at least 10 times greater than the longitudinal stiffness.

31. (canceled)

32. The medical balloon of claim 29, wherein the balloon wall material remains kink-free when inflated in the curved configuration.

33. The medical balloon of claim 29, wherein the balloon wall material comprises a material with a porous microstructure.

34. (canceled)

35. The medical balloon of claim 33, wherein the porous microstructure is highly fibrillated.

36. The medical balloon of claim 33, wherein the porous microstructure is expanded polytetrafluoroethylene.

37.-39. (canceled)

40. The medical balloon of claim 29, wherein a working length of the balloon lengthens less than 10% during inflation to at least an angioplasty pressure.

41. The medical balloon of claim 29, wherein the balloon wall material is configured to remain kink free when a ratio of a balloon diameter within a working length to a bend radius is at least 1:3.

42. The medical balloon of claim 29, further comprising a compliant bladder.

43. (canceled)

44. The medical balloon of claim 29, wherein the medical balloon is inflatable to a pressure greater than 4 atm or greater than 8 atm.

45. (canceled)

46. The medical balloon of claim 29, wherein the balloon wall material comprises a circumferential stiffness greater than 200 gf/mm/mm.

47. The medical balloon of claim 29, wherein the longitudinal stiffness is less than 70 gf/mm/mm for the medical balloon having an 8 mm diameter.

48. The medical balloon of claim 29, wherein the longitudinal stiffness is less than 30 gf/mm/mm for the medical balloon having a 4 mm diameter.

49. The medical balloon of claim **29**, wherein the balloon wall material comprises a helically wrapped film at an angle greater than 80 degrees relative to the longitudinal axis and wherein the helically wrapped film comprises a balance ratio of at least 10:1.

50.-76. (canceled)

77. The medical balloon of claim **1**, wherein the balloon wall comprises a material having a porous microstructure, wherein at least a portion of the porous microstructure comprises a plurality of voids defined by the porous microstructure.

78.-214. (canceled)

* * * * *