

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number:

0 361 684 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication of patent specification: **13.10.93** (51) Int. Cl.⁵: **D01D 5/11, D01F 6/04**

(21) Application number: **89308701.5**

(22) Date of filing: **29.08.89**

(54) **Halocarbons for flash-spinning polymeric plexifilaments.**

(30) Priority: **30.08.88 US 238442**
18.07.89 US 379291

(43) Date of publication of application:
04.04.90 Bulletin 90/14

(45) Publication of the grant of the patent:
13.10.93 Bulletin 93/41

(84) Designated Contracting States:
DE FR GB IT LU NL

(56) References cited:
US-A- 3 081 519
US-A- 3 227 794
US-A- 4 528 300

RESEARCH DISCLOSURE, no. 146, June 1976,
pages 13,14, no. 14623;
"Hydrogen-containing chlorofluorocarbons"

CHEMICAL & ENGINEERING NEWS, 8th Feb-
ruary 1988, pages 17-20, The New Yorker
Magazine Inc.; P.S. ZURER: "Search intensi-
fies for alternatives to ozone-depleting
halocarbons"

(73) Proprietor: **E.I. DU PONT DE NEMOURS AND**
COMPANY
1007 Market Street
Wilmington Delaware 19898(US)

(72) Inventor: **Shin, Hyunkook**
134 Hitching Post Drive
Wilmington, Delaware 19803(US)

(74) Representative: **Jones, Alan John et al**
CARPMAELS & RANSFORD
43 Bloomsbury Square
London, WC1A 2RA (GB)

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid (Art. 99(1) European patent convention).

EP 0 361 684 B1

Description

This invention relates to flash-spinning polymeric film-fibril strands. More particularly, the invention concerns an improvement in such a process which permits flash-spinning of the strands from liquids which, if released to the atmosphere, would not detrimentally affect the earth's ozone.

Description of the Prior Art

Blades and White, United States Patent 3,081,519, describes a flash-spinning process for producing plexifilamentary film-fibril strands from fiber-forming polymers. A solution of the polymer in a liquid, which is a non-solvent for the polymer at or below its normal boiling point, is extruded at a temperature above the normal boiling point of the liquid and at autogenous or higher pressure into a medium of lower temperature and substantially lower pressure. This flash-spinning causes the liquid to vaporize and thereby cool the exudate which forms a plexifilamentary film-fibril strand of the polymer. Preferred polymers include crystalline polyhydrocarbons such as polyethylene and polypropylene.

According to Blades and White, a suitable liquid for the flash spinning (a) has a boiling point that is at least 25 °C below the melting point of the polymer, (b) is substantially unreactive with the polymer at the extrusion temperature; (c) should be a solvent for the polymer under the pressure and temperature set forth in the patent (i.e., these extrusion temperatures and pressures are respectively in the ranges of 165 to 225 °C and 545 to 1490 psia - 3757 to 10273 kPa); (d) should dissolve less than 1% of the polymer at or below its normal boiling point; and should form a solution that will undergo rapid phase separation upon extrusion to form a polymer phase that contains insufficient solvent to plasticize the polymer. Depending on the particular polymer employed, the following liquids are useful in the flash-spinning process: aromatic hydrocarbons such as benzene, toluene, etc.; aliphatic hydrocarbons such as butane, pentane, hexane, heptane, octane, and their isomers and homologs; alicyclic hydrocarbons such as cyclohexane; unsaturated hydrocarbons; halogenated hydrocarbons such as methylene chloride, carbon tetrachloride, chloroform, ethyl chloride, methyl chloride; alcohols; esters; ethers; ketones; nitriles; amides; fluorocarbons; sulfur dioxide; carbon disulfide; nitromethane; water; and mixtures of the above liquids. The patent also diagrammatically illustrates certain principles helpful in establishing optimum spinning conditions to obtain plexifilamentary strands. Blades and White states that the flash-spinning solution additionally may contain a dissolved gas, such as nitrogen, carbon dioxide, helium, hydrogen, methane, propane, butane, ethylene, propylene, butene, etc. Preferred for improving plexifilament fibrillation are the less soluble gasses, i.e., those that are dissolved to a less than 7% concentration in the polymer solution under the spinning conditions. Common additives, such as antioxidants, UV stabilizers, dyes, pigments and the like also can be added to the solution prior to extrusion.

Anderson and Romano, United States Patent 3,227,794, discloses a diagram similar to that of Blades and White for selecting conditions for spinning plexifilamentary strands. A graph is presented of spinning temperature versus spinning pressure for solutions of 10 to 16 weight percent of linear polyethylene in trichlorofluoromethane. This patent also describes in detail the preparation of a solution of 14 weight percent high density linear polyethylene in trichlorofluoromethane at a temperature of about 185 °C and a pressure of about 1640 psig (11407 kPa) which is then flash-spun from a let-down chamber at a temperature of 185 °C and a pressure of 1050 psig (7339 kPa). Very similar temperatures, pressures and concentrations have been employed in commercial flash-spinning of polyethylene into plexifilamentary film-fibril strands, which were then converted into sheet structures.

Although trichlorofluoromethane has been a very useful solvent for flash-spinning plexifilamentary film-fibril strands of polyethylene, and has been the solvent used in commercial manufacture of polyethylene plexifilamentary strands, the escape of such a halocarbon into the atmosphere has been implicated as a serious source of depletion of the earth's ozone. A general discussion of the ozone-depletion problem is presented, for example, by P.S. Zurer, "Search Intensifies for Alternatives to Ozone-Depleting Halocarbons", Chemical & Engineering News, pages 17-20 (February 8, 1988).

A convenient test to determine whether a given solvent would be suitable for flash-spinning a given polymer is disclosed by Woodell, United States Patent 3,655,498. This test has been used extensively by the world's largest manufacturer of flash-spun polyethylene products to determine the suitability of alternatives to the trichlorofluoromethane solvent for preparing plexifilamentary strands. In the test, a mixture of the polymer plus the amount of solvent calculated to give about a 10 weight percent solution, is sealed in a thick-walled glass tube (the mixture occupies about one-third to one-half the tube volume) and the mixture is heated at autogenous pressure. Test temperatures usually range from about 100 °C to just below the critical temperature of the liquid being tested. Woodell states that if a single-phase, flowable solution is not

formed in the tube at any temperature below the solvent critical temperature, T_c , (or the polymer degradation temperature, whichever is lower) the solvent power is too low. At the other extreme, if a single phase solution is formed at some temperature below T_c , but that solution cannot be converted to two liquid phases on being heated to a higher temperature (still below T_c), the solvent power is too high. Solvents
 5 whose inherent solvent power fails to fall within these extremes may be made suitable by dilution with either a non-solvent or a good-solvent additive, as appropriate. After choosing a suitable solvent or solvent mixture, the single-phase and two-liquid-phase boundary behavior of the solvent or mixture can be determined as a function of temperature and pressure at different polymer concentrations, as described by Anderson and Romano, mentioned above.

10 An object of this invention is to provide an improved process for flash-spinning plexifilamentary film-fibril strands of fiber-forming polyolefin, wherein the solvent should not be a depletion hazard to the earth's ozone.

SUMMARY OF THE INVENTION

15 The present invention provides an improved process for flash-spinning plexifilamentary film-fibril strands wherein polyethylene is dissolved in a halocarbon spin liquid to form a spin solution containing 10 to 20 percent of polyethylene by weight of the solution at a temperature in the range of 130 to 210 °C and a pressure that is greater than 3000 psi (20685 kPa) which solution is flash-spun into a region of substantially
 20 lower temperature and pressure, the improvement comprising the halocarbon being selected from 1,1-dichloro-2,2,2-trifluoroethane and 1,2-dichloro-1,2,2-trifluoroethane.

The present invention provides an improved process for flash-spinning plexifilamentary film-fibril strands wherein polyethylene is dissolved in a halocarbon spin liquid to form a spin solution containing 10 to 20 percent of polyethylene by weight of the solution at a temperature in the range of 130 to 210 °C and a
 25 pressure that is greater than 1,800 psi (12411 kPa) which solution is flash-spun into a region of substantially lower temperature and pressure, the improvement comprising the halocarbon being selected from 1,1-dichloro-2,2-difluoroethane and 1,2-dichloro-1,1-difluoroethane.

The present invention provides an improved process for flash-spinning plexifilamentary film-fibril strands wherein polyethylene is dissolved in a halocarbon spin liquid to form a spin solution containing 10 to 20 percent of polyethylene by weight of the solution at a temperature in the range of 130 to 210 °C and a
 30 pressure that is greater than 2,000 psi (13790 kPa) which solution is flash-spun into a region of substantially lower temperature and pressure, the improvement comprising the halocarbon being 1,1-dichloro-1-fluoroethane.

The present invention provides an improved process for flash-spinning plexifilamentary film-fibril strands wherein polypropylene is dissolved in a halocarbon spin liquid to form a spin solution containing 10 to 20 percent of polypropylene by weight of the solution at a temperature in the range of 130 to 210 °C and a
 35 pressure that is greater than 1,500 psi (10343 kPa) which solution is flash-spun into a region of substantially lower temperature and pressure, the improvement comprising the halocarbon being selected from

1,1-dichloro-2,2,2-trifluoroethane,
 40 1,2-dichloro-1,2,2-trifluoroethane,
 1,1-dichloro-2,2-difluoroethane,
 1,2-dichloro-1,1-difluoroethane and
 1,1-dichloro-1-fluoroethane.

The present invention provides an improved process for flash-spinning plexifilamentary film-fibril strands wherein a fiber-forming polyolefin is dissolved in a halocarbon spin liquid at a temperature in the range of 130 to 210 °C and a pressure that is greater than 1000 psi (6895 kPa) wherein the spin liquid further
 45 contains a co-solvent, either a hydrocarbon which amounts to 2 to 25 percent of the total weight of spin liquid or methylene chloride which amounts to 5 to 50 percent of the total weight of spin liquid, to form a spin solution containing 10 to 20 percent of fiber-forming polyolefin by weight of the solution and then is
 50 flash-spun into a region of substantially lower temperature and pressure, the improvement comprising the halocarbon being selected from

1,1-dichloro-2,2,2-trifluoroethane,
 1,2-dichloro-1,2,2-trifluoroethane,
 1,1-dichloro-2,2-difluoroethane,
 55 1,2-dichloro-1,1-difluoroethane and
 1,1-dichloro-1-fluoroethane.

The present invention provides a novel solution consisting essentially of 10 to 20 weight percent of a fiber-forming polyolefin and 90 to 80 weight percent of a liquid containing a halocarbon selected from

1,1-dichloro-2,2,2-trifluoroethane,
 1,2-dichloro-1,2,2-trifluoroethane,
 1,1-dichloro-2,2-difluoroethane,
 1,2-dichloro-1,1-difluoroethane and
 1,1-dichloro-1-fluoroethane.

The present invention provides a novel solution consisting essentially of 10 to 20 weight percent of a fiber-forming polyolefin and 90 to 80 weight percent of a halocarbon liquid selected from

1,1-dichloro-2,2,2-trifluoroethane,
 1,2-dichloro-1,2,2-trifluoroethane,
 1,1-dichloro-2,2-difluoroethane,
 1,2-dichloro-1,1-difluoroethane and
 1,1-dichloro-1-fluoroethane.

DETAILED DESCRIPTION OF PREFERRED EMBODIMENTS

The term "polyolefin" as used herein, is intended to mean any of a series of largely saturated open chain polymeric hydrocarbons composed only of carbon and hydrogen. Typical polyolefins include, but are not limited to, polyethylene, polypropylene and polymethylpentene. Conveniently, polyethylene and polypropylene are the preferred polyolefins for use in the process of the present invention.

"Polyethylene" as used herein is intended to embrace not only homopolymers of ethylene, but also copolymers wherein at least 85% of the recurring units are ethylene units. The preferred polyethylene is a homopolymeric linear polyethylene which has an upper limit of melting range of about 130 to 135 °C, a density in the range of 0.94 to 0.98 g/cm³ and a melt index (as defined by ASTM D-1238-57T, Condition E) of 0.1 to 6.0.

The term "polypropylene" is intended to embrace not only homopolymers of propylene but also copolymers wherein at least 85% of the recurring units are propylene units.

The term "plexifilamentary film-fibril strands" as used herein, means a strand which is characterized as a three-dimensional integral network of a multitude of thin, ribbon-like, film-fibril elements of random length and of less than about 4 microns average thickness, generally coextensively aligned with the longitudinal axis of the strand. The film-fibril elements intermittently unite and separate at irregular intervals in various places through the length, width and thickness of the strand to form the three-dimensional network. Such strands are described in further detail by Blades and White, United States Patent 3,081,519 and by Anderson and Romano, United States Patent 3,227,794.

The present invention provides an improvement in the known process for producing plexifilamentary film-fibril strands of fiber-forming polyolefins from a halocarbon spin solution that contains 10 to 20 weight percent of the fiber-forming polyolefin. A fiber-forming polyolefin, e.g. linear polyethylene, is dissolved in a spin liquid that includes a halocarbon to form a spin solution containing 10 to 20 percent of the linear polyethylene by weight of the solution and then is flash-spun at a temperature in the range of 130 to 210 °C and a pressure that is greater than the autogenous pressure of the spin liquid into a region of substantially lower temperature and pressure.

The key improvement of the present invention requires the halocarbon to be selected from

1,1-dichloro-2,2,2-trifluoroethane ("HC-123")
 1,2-dichloro-1,2,2-trifluoroethane ("HC-123a")
 1,1-dichloro-2,2-difluoroethane (HC-132a")
 1,2-dichloro-1,1-difluoroethane ("HC-132b") and
 1,1-dichloro-1-fluoroethane ("HC-141b").

The parenthetic designation is used herein as an abbreviation for the chemical formula of the halocarbon. The following table lists the known normal atmospheric boiling points (Tbp), critical temperatures (Tcr) and critical pressures (Pcr) for the selected halocarbons and for some prior art solvents. In the column labeled "Solubility", the Table also lists whether a 10% polyethylene solution can be formed in the halocarbon at temperatures between 130 and about 225 °C under autogenous pressures.

	Tbp, °C	Tcr, °C	Pcr, psia*	Solubility
HC-123	28.7	185	550	no
HC-123a	28			no
HC-132a	60	238		no
HC-132b	46.8	220	570	no
HC-141b	32	210	673	no
Trichlorofluoromethane	23.8	198.0	639.5	yes
Methylenechloride	39.9	237.0	894.7	yes
Hexane	68.9	234.4	436.5	yes
Cyclohexane	80.7	280.4	590.2	yes

* 1 psia = 6.895 kPa

Note that the five suitable halocarbons listed above represent a very particular and small group of halocarbons that are suitable for use in the present invention. There are hundreds of halocarbons to select from. The conventional method of screening liquids (i.e., by means of the autogenous pressure polyethylene solubility test, described above) is inadequate as the halocarbons discovered to be useful for the present invention do not dissolve the polyethylene at autogenous pressures, in contrast to the prior art solvents shown above that would have been selected for further study because they do form solutions with the polyethylene at autogenous pressure. Furthermore, in contrast to the flash spinning fluids of the past, none of the halocarbons of the present invention form a single phase solution with polyethylene at the required concentrations and temperatures at a pressure of less than 1,500 psia (10345 kPa). These halocarbons do, of course, have certain characteristics that are also possessed by the known fiber-forming polyolefin flash-spinning liquids. For example, these halocarbons also are substantially unreactive with the polymer at the extrusion temperature. These halocarbons are solvents for the fiber-forming polyolefin under certain conditions, dissolve less than 1% of the polymer at or below their normal boiling points and form solutions that undergo rapid phase separation upon extrusion to form a polymer phase that contains insufficient solvent to plasticize the polymer.

In addition to the above-stated characteristics, halocarbons suitable for use in the process and solutions of the present invention (1) have boiling points in the range of 0 to 80 °C, (2) are incompletely fluorinated and/or chlorinated, (3) have low flammability, (4) have adequate heat of vaporization to permit rapid cooling of the plexifilament when it is formed upon flash spinning, (5) have adequate thermal and hydrolytic stability for use in the flash spinning process, (6) have a sufficiently high electrostatic breakdown potential in the gaseous state so that they can be used in conventional spunbonded processes for forming sheets of the plexifilament (e.g., Steuber, United States Patent 3,169,899) without exhibiting excessive decomposition of the halocarbon and (7) cannot form a single phase 10 weight percent solution of polyethylene in the liquid at temperatures in the range of 130 to 225 °C at any pressure less than 1,500 psia (10345 kPa). Specifically, with HC-123 and HC-123a, such solutions of polyethylene can be formed in the halocarbon liquid only at pressures greater than 3,000 psi (20685 kPa); with HC-132a and HC-132b, such solutions of polyethylene can be formed in the halocarbon liquid only at pressures greater than 1,800 psi (12411 kPa) and with HC-141b, such solutions of polyethylene can be formed in the halocarbon liquid only at pressures greater than 2,000 psi (13790 kPa). Such solutions of polypropylene can be formed in the halocarbon spin liquids of this invention only at pressures greater than 1,500 psi (10343 kPa).

Satisfactory solutions of polymer and halocarbon can be formed at pressures greater than 1,000 psi (6895 kPa), only when co-solvents of high solvent power are present in the halocarbon spin liquid.

The combination of halocarbon characteristics have been discovered to be met substantially by only the five halocarbons, listed above. To function similarly to any of these five halocarbons, another halocarbon would also have to meet substantially all of these characteristics in order to be suitable for flash-spinning high quality, plexifilamentary film-fibril strands of fiber-forming polyolefin.

Even among the five halocarbons suitable for use in the process of the invention, care must be taken with these halocarbons to avoid certain disadvantageous characteristics which may be present. For example, excessive heating times are avoided with HC-123a, HC-132a, HC-132b and HC-141b to minimize decomposition that can arise from dehydrohalogenation or hydrolysis of the halocarbon. Care must also be taken with HC-132b, because there have been some indications that this chemical may be a male-animal-reproductive toxin. Because of its relative freedom from all of these stability and toxicity problems, HC-123 is the preferred halocarbon for use in the process of the invention.

In forming a solution of fiber-forming polyolefin in the halocarbon liquids of the invention, a mixture of the fiber-forming polyolefin and halocarbon are raised to a temperature in the range of 130 to 210 °C. If polyethylene is the polyolefin; the mixture is under a pressure of greater than 2,000 psi (13790 kPa) if the halocarbon is HC-141b, greater than 3,000 psi (20685 kPa) if the halocarbon is HC-123 or HC-123a and greater than 1,800 psi (12411 kPa) if the halocarbon is HC-132a or HC-132b. If polypropylene is used, the pressure is greater than 1,500 psi (10345 kPa) regardless of the halocarbon chosen. The mixtures described above are held under the required pressure until a solution of the fiber-forming polyolefin is formed in the liquid. Usually, maximum pressures of less than 10,000 psi (68950 kPa) are satisfactory. After the fiber-forming polyolefin has dissolved, the pressure may be reduced somewhat and the mixture is then flash spun to form the desired high quality plexifilamentary strand structure.

The concentration of fiber-forming polyolefin in the spin liquid usually is in the range of 10-20 percent, based on the total weight of the liquid and the fiber-forming polyolefin.

The spin solution preferably consists of halocarbon liquid and fiber-forming polyolefin, but if lower pressures are desired for solution preparation and spinning, the spin solution can contain a second liquid, or co-solvent, for the fiber-forming polyolefin. When the co-solvent, is a hydrocarbon solvent, such as cyclohexane, toluene, chlorobenzene, hexane, pentane, 3-methyl pentane and the like, the concentration of the co-solvent in the mixture of halocarbon and co-solvent generally amounts to 2 to 25 weight percent and preferably less than 15 weight percent to minimize potential flammability problems. However, when methylene chloride is employed as the co-solvent, concentrations of the methylene chloride in the halocarbon/co-solvent mixture (i.e., free of fiber-forming polyolefin) generally amounts to 5 to 50 weight percent.

Conventional flash-spinning additives can be incorporated into the spin mixtures by known techniques. These additives can function as ultraviolet-light stabilizers, antioxidants, fillers, dyes, and the like.

The various characteristics and properties mentioned in the preceding discussion and in the examples below were determined by the following procedures.

Test Methods

Solubility of the polyethylene and polypropylene under autogenous conditions were measured by the convenient sealed-tube test of Woodell, United States Patent 3,655,498, that was also described in the next to last paragraph of the "Description of the Prior Art" section of this document.

The quality of the plexifilamentary film-fibril strands produced in the examples were rated subjectively. A rating of "5" indicates that the strand had better fibrillation than is usually achieved in the commercial production of spunbonded sheet made from such flash-spun polyethylene strands. A rating of "4" indicates that the product was as good as commercially flash-spun strands. A rating of "3" indicates that the strands were not quite as good as the commercially flash-spun strands. A "2" indicates a very poorly fibrillated, inadequate strand. A "1" indicates no strand formation. A rating of "3" is the minimum considered satisfactory for use in the process of the present invention. The commercial strand product is produced from solutions of about 12.5% linear polyethylene in tichlorofluoromethane substantially as set forth in Lee, United States patent 4,554,207, column 4, line 63, through column 5, line 10, which disclosure is hereby incorporated by reference.

The surface area of the plexifilamentary film-fibril strand product is another measure of the degree and fineness of fibrillation of the flash-spun product. Surface area is measured by the BET nitrogen absorption method of S. Brunauer, P.H. Emmett and E. Teller, J. Am. Chem Soc., V. 60 p 309-319 (1938) and is reported as m²/g.

Tenacity of the flash-spun strand is determined with an Instron tensile-testing machine. The strands are conditioned and tested at 21.1 °C (70 °F) and 65% relative humidity.

The denier of the strand is determined from the weight of a 15 cm sample length of strand. The sample is then twisted to 10 turns per inch and mounted in the jaws of the Instron Tester. A 1-inch (25.4 mm) gauge length and an elongation rate of 60% per minute are used. The tenacity at break is recorded in grams per denier (gpd).

The invention is illustrated in the Examples which follow with a batch process in equipment of relatively small size. Such batch processes can be scaled-up and converted to continuous flash-spinning processes that can be performed, for example, in the type of equipment disclosed by Anderson and Romano, United States Patent 3,227,794. In the Examples and Tables, processes of the invention are identified with Arabic numerals. Processes identified with uppercase letters are comparison processes that are outside the invention.

EXAMPLES

For each of Examples 1-25 and Comparisons A and B, a high density linear polyethylene of 0.76 Melt Index was flash-spun into satisfactory plexifilamentary film-fibril strands in accordance with the invention (except for Example 7, in which a low density linear polyethylene of 26 Melt Index was used).

Two types of apparatus were used to prepare the mixture of halocarbon and fiber-forming polyolefin and perform the flash-spinning. The apparatus designated "I" was employed Examples 1, 5 and 16. The apparatus designated "II" was utilized for all other Examples and for the Comparisons.

Apparatus "I" is a high pressure apparatus comprising a cylindrical vessel of 50 cm³ volume, fitted at one end with a cylindrical piston which is adapted to apply pressure to the contents of the vessel. The other end of the vessel is fitted with a spinneret assembly having an orifice of 0.030-inch (0.76 mm) diameter and 0.060-inch (1.5 mm) length and a quick-acting means for opening and closing the orifice. Means are included for measuring the pressure and temperature inside the vessel. In operation, the vessel is charged with fiber-forming polyolefin and halocarbon. A high pressure (e.g., 4,500 psi - 31028 kPa) is applied to the charge. The contents are heated at the desired temperature (e.g., 140 °C) for about an hour to effect the formation of a solution which is then "mixed" by cycling the pressure about ten times. The pressure is then reduced to that desired for spinning and the spinneret orifice valve opened. The resultant flash-spun product is then collected.

Apparatus "II" comprises a pair of high pressure cylindrical vessels, each fitted with a piston for applying pressure. The vessels are each similar to the cylindrical vessel of apparatus "I", but rather than having an orifice assembly in each vessel, the two are connected to each other with a transfer line. The transfer line contains a series of fine mesh screens intended for mixing the contents of the apparatus by forcing the contents through the transfer line from one cylinder to the other. A spinneret assembly having an orifice of 0.030-inch (0.76 mm) diameter is connected to the transfer lines with quick acting means for opening and closing the orifice. Means are included for measuring the pressure and temperature inside the vessel. In operation, the apparatus is charged with fiber-forming polyolefin and halocarbon and a high pressure is applied to the charge. The contents then are heated at the desired temperature for about an hour and a half during which time a differential pressure of about 50 psi (345 kPa) is alternately established between the two cylinders to repeatedly force the contents through the transfer line from one cylinder to the other to provide mixing and effect formation of a solution. The pressure desired for spinning is then set and the spinneret orifice opened. The resultant flash-spun product is then collected.

All Examples and Comparisons were performed in a similar fashion, depending on the apparatus used, under the specific conditions and with the particular ingredients shown in the following summary tables. The tables also record characteristics of the strands produced by the flash-spinning.

In Table I, Examples 1-7 illustrate the use of different halocarbons suitable for the process and solutions of the invention. Comparisons A and B show the use of some of the same halocarbons but under conditions that do not permit production of satisfactory strand.

Table I

<u>Example No.</u>	<u>1</u>	<u>2</u>	<u>A</u>	<u>3</u>	<u>B</u>
Apparatus	I	II	II	II	II
Polyethylene					
Conc, wt %	14.4	12	12	12	12
Solvent: HC	123	123	123	132b	132b
Mixing					
Temp, °C	140	140	170	140	140
Press, psig ²	4500-3800	5700	2900	2000	1500
Spinning					
Temp, °C	170	140	170	180	200
Press, psig ²	2500	3200-4200	2900	2000	1500
Strand Product					
Denier ³	776	1003	ns*	476	ns
Tenacity, gpd ⁴	3.25	2.91	ns	3.03	ns
Quality	4	4	1	4.5	1

TABLE I (CONT.)

<u>Example No.</u>	<u>4</u>	<u>5</u>	<u>6</u>	<u>7</u>
Apparatus	II	I	II	II
Polyethylene				
Conc, wt %	12	11.4	12	12
Solvent: HC	141b	123a	132a	132b
Mixing				
Temp, °C	140	140	140	140
Press, psig ²	2500	4200	2500	2500
Spinning				
Temp, °C	170	170	200	180
Press, psig ²	2500	2500	2500	2500
Strand Product				
Denier ³	598	nm**	nm	nm
Tenacity, gpd ⁴	2.8	nm	nm	nm
Quality	4	3	4	3

In Table II, Examples 8-25 illustrate the use of various co-solvents with the halocarbons.

Table II

5

10

15

20

25

30

35

40

45

50

55

<u>Example No.</u>	<u>8</u>	<u>9</u>	<u>10</u>	<u>11</u>
Apparatus	II	II	II	II
Polyethylene				
Conc, wt %	12	12	12	12
Solvent: HC	123	123	123	132b
Co-solvent	CH ₂ Cl ₂	CH ₂ Cl ₂	CH ₂ Cl ₂	3-methyl pentane
wt %	25	33	50	7
Mixing				
Temp, °C	140	140	140	140
Press, psig ²	2500	1800	2500	2500
Spinning				
Temp, °C	170	160	170	200
Press, psig ²	2500	1800	2500	2500
Strand Product				
Denier ³	577	566	686	nm
Tenacity, gpd ⁴	2.74	2.58	2.43	nm
Surface Area,	37.8	49.6	63.1	nm
m ² /g	4.5	4.5	4	4.5

TABLE II (CONT.)

<u>Example No.</u>	<u>12</u>	<u>13</u>	<u>14</u>	<u>15</u>
Apparatus	II	II	II	II
Polyethylene				
Conc, wt %	12	12	12	12
Solvent: HC	123	123	123	123
Co-solvent	C ₆ H ₁₂	C ₆ H ₁₂	toluene	toluene
wt %	13.3	16.7	6.7	13.3
Mixing				
Temp, °C	140	140	140	140
Press, psig ²	2800	2500	2600	2000
Spinning				
Temp, °C	170	170	170	160
Press, psig ²	2900	2500	2900	2000
Strand Product				
Denier ³	564	612	642	877
Tenacity, gpd ⁴	2.3	1.96	2.41	1.70
Quality	5	5	4.5	4.5
Surface Area, m ² /g	34.9	28.0	15.9	25.6

TABLE II (CONT.)

<u>Example No.</u>	<u>16</u>	<u>17</u>	<u>18</u>
Apparatus	I	II	II
Polyethylene			
Conc, wt %	11.4	12	12
Solvent: HC	123	123	123
Co-solvent	pentane	hexane	chlorobenzene
wt %	13.1	20	6.7
Mixing			
Temp, °C	140	140	140
Press, psig ²	4200-3700	2700	2600
Spinning			
Temp, °C	170	170	170
Press, psig ²	3000	2900	2800
Strand Product			
Quality	4	5	4

TABLE II (CONT.)

5	<u>Example No.</u>	<u>19</u>	<u>20</u>	<u>21</u>
	Apparatus	II	II	II
	Polyethylene			
10	Conc, wt %	12	12	15
	Solvent: HC	123	123	123
15	Co-solvent	CH ₂ Cl ₂	CH ₂ Cl ₂	CH ₂ Cl ₂
	wt %	5	10	10
	Mixing			
20	Temp, °C	140	140	140
	Press, psig ²	5500	5500	5500
	Spinning			
25	Temp, °C	170	160	170
	Press, psig ²	~4700	~4700	~4000
30	Strand Product			
	Denier ³	527	374	596
	Tenacity, gpd ⁴	4.61	2.93	4.22
35	Surface Area,			
	m ² /g	34.2	36.4	52.9
40	Quality	4	5	4

45

50

55

TABLE II (CONT.)

Example No.	<u>22</u>	<u>23</u>	<u>24</u>	<u>25</u>
Apparatus	II	II	II	II
Polyethylene				
Conc, wt %	12	12	12	12
Solvent: HC	123	123	123	123
Co-solvent	CH ₂ Cl ₂	CH ₂ Cl ₂	C ₆ H ₁₂	toluene
wt %	32.5	40	5	5
Mixing				
Temp, °C	140	140	140	140
Press, psig ²	1800	1800	~5000	4000
Spinning				
Temp, °C	170	200	170	170
Press, psig ²	1575	1575	~5000	~3650
Strand Product				
Denier ³	486.8	399.2	707	549
Tenacity, gpd ⁴	2.67	2.43	1.79	2.94
Surface Area,				
m ² /g	29.7	36.2	34.9	30.5
Quality	5	4.5	4	4

*"ns" means no strand formed

**"nm" means no measurement was made

+ C₆H₁₂ is cyclohexane

In Table III, Example 26 shows that well fibrillated plexifilaments can be obtained from other types of polyolefins using this invention. The apparatus and methodology used in this example were the same as the examples in Table II except polyethylene was substituted with isotactic polypropylene with a Melt Flow Rate of 0.4, available commercially under the tradename "Profax 6823" by Hercules, Inc. Wilmington, De. In addition, higher mixing temperature was used to compensate for the higher melting point of the polymer. The conditions used and the properties of the resultant fiber are summarized in Table III. The polymer mix contained 3.6 wt% based on polymer of Irganox^R 1010 (Trademark of Ciba-Geigy Corp. for a high-molecular weight hindered polyphenol) as an antioxidant.

Table III

5	<u>Example No.</u>	<u>26</u>
	Apparatus	II
	Polypropylene	
10	Conc, wt %	16
	Solvent: HC	123
	Mixing	
15	Temp, °C	180
	Press, psi ¹	1800
20	Spinning	
	Temp, °C	180
	Press, psi ¹	1800
25	TABLE III (CONT.)	
	<u>Example No.</u>	<u>26</u>
30	Strand Product	
	Denier ³	483
	Tenacity, gpd ⁴	1.23
35	Quality	4

In Tables I, II and III

1. To convert psi to kPa multiply by 6.9
2. To convert psig to kPa add 14.4 and multiply by 6.9
3. To convert denier to d tex multiply by 1.1
4. To convert gpd to gp tex divide by 0.11

Claims

1. A process for flash-spinning plexifilamentary film-fibril strands wherein polyethylene is dissolved in a halocarbon spin liquid to form a spin solution containing 10 to 20 percent of polyethylene by weight of the solution at a temperature in the range of 130 to 210°C and a superatmospheric pressure which solution is flash-spun into a region of substantially lower temperature and pressure, wherein for a superatmospheric pressure that is greater than 3000 psi (20685 kPa) the halocarbon is selected from 1,1-dichloro-2,2,2-trifluoroethane and

1,2-dichloro-1,2,2-trifluoroethane;

for a superatmospheric pressure that is greater than 1,800 psi (1241 kpa) the halocarbon is selected from 1,1-dichloro-2,2-difluoroethane and 1,2-dichloro-1,1-difluoroethane; and for a superatmospheric pressure that is greater than 2,000 psi (13790 kpa) the halocarbon is 1,1-dichloro-1-fluoroethane.

2. A process for flash-spinning plexifilamentary film-fibril strands wherein polypropylene is dissolved in a halocarbon spin liquid to form a spin solution containing 10 to 20 percent of polypropylene by weight of the solution at a temperature in the range of 130 to 210 °C and a pressure that is greater than 1,500 psi (10343 kPa) which solution is flash-spun into a region of substantially lower temperature and pressure, wherein the halocarbon is selected from

1,1-dichloro-2,2,2-trifluoroethane,
1,2-dichloro-1,2,2-trifluoroethane,
1,1-dichloro-2,2-difluoroethane,
1,2-dichloro-1,1-difluoroethane and
1,1-dichloro-1-fluoroethane.

3. A process for flash-spinning plexifilamentary film-fibril strands wherein a fibre-forming polyolefin is dissolved in a halocarbon spin liquid at a temperature in the range of 130 to 210 °C and a pressure that is greater than 1000 psi (6895 kpa) wherein the spin liquid contains a co-solvent to form a spin solution containing 10 to 20 percent of fibre-forming polyolefin by weight of the solution and then is flash-spun into a region of substantially lower temperature and pressure, wherein said co-solvent is either a hydrocarbon amounting to 2 to 25 percent of the total weight of the spin liquid or is methylene chloride amounting to 5 to 50 percent of the total weight of the spin liquid and wherein the halocarbon is selected from

1,1-dichloro-2,2,2-trifluoroethane,
1,2-dichloro-1,2,2-trifluoroethane,
1,1-dichloro-2,2-difluoroethane,
1,2-dichloro-1,1-difluoroethane and
1,1-dichloro-1-fluoroethane.

4. A process in accordance with claim 3 wherein the co-solvent is selected from 3-methyl pentane, cyclohexane, toluene, pentane, hexane and chlorobenzene.

5. A process in accordance with claim 4 wherein the co-solvent amounts to no more than 15 percent of the total weight of the spin liquid.

6. A process in accordance with claim 1, 2, 3, 4 or 5, wherein the halocarbon is 1,1-dichloro-2,2,2-trifluoroethane.

7. A process in accordance with claims 3, 4 or 5 wherein the polyolefin is polyethylene.

8. A process in accordance with claims 3, 4 or 5 wherein the polyolefin is polypropylene.

9. A solution consisting essentially of 10 to 20 weight percent of a fibre-forming polyolefin and 90 to 80 weight percent of a liquid comprising a halocarbon selected from

1,1-dichloro-2,2,2-trifluoroethane,
1,2-dichloro-1,2,2-trifluoroethane,
1,1-dichloro-2,2-difluoroethane,
1,2-dichloro-1,1-difluoroethane and
1,1-dichloro-1-fluoroethane.

10. A solution in accordance with claim 9 wherein the liquid contains a hydrocarbon co-solvent amounting to 2 to 25 percent of the total weight of the halocarbon and co-solvent.

11. A solution in accordance with claim 9 wherein the liquid also contains methylene chloride as a co-solvent amounting to 5 to 50 percent of the weight of the halocarbon and methylene chloride.

12. A solution in accordance with any one of claims 9 to 11 wherein the halocarbon is 1,1-dichloro-2,2,2-trifluoroethane.

13. A solution in accordance with any one of claims 9 to 12 wherein the polyolefin is polyethylene.

14. A solution in accordance with any one of claims 9 to 12 wherein the polyolefin is polypropylene.

Patentansprüche

1. Verfahren zum Flashspinnen von plexifilamentären Filmfibrillen-Strängen, bei dem Polyethylen in einer Halogen-Kohlenwasserstoff-Spinnflüssigkeit aufgelöst wird, um eine Spinnlösung zu bilden, die bei einer Temperatur im Bereich von 130 bis 210 °C und einem super-atmosphärischen Druck 10 bis 20 % des Polyethylen, bezogen auf das Gewicht der Lösung, enthält, wobei die Lösung flashgesponnen wird in einen Bereich von im wesentlichen niedrigerer Temperatur und einem niedrigeren Druck, bei dem für einen superatmosphärischen Druck, der größer ist als 3 000 psi (20 685 kPa), der halogenierte Kohlenwasserstoff ausgewählt wird aus

1,1-Dichlor-2,2,2-trifluorethan und
1,2-Dichlor-1,2,2-trifluorethan;

für einen super-atmosphärischen Druck, der größer ist als 1 800 psi (1 241 kPa), der halogenierte Kohlenwasserstoff ausgewählt wird aus 1,1-Dichlor-2,2-difluorethan und 1,2-Dichlor-1,1-difluorethan; und für einen super-atmosphärischen Druck, der größer ist als 2 000 psi (13 790 kPa), der halogenierte Kohlenwasserstoff 1,1-Dichlor-1-fluorethan darstellt.

2. Verfahren zum Flashspinnen von plexifilamentären Filmfibrillen-Strängen, bei dem Polypropylen in einer Halogen-Kohlenwasserstoff-Spinnflüssigkeit aufgelöst wird, um eine Spinnlösung zu bilden, die bei einer Temperatur im Bereich von 130 bis 210 °C und einem Druck, der größer ist als 1 500 psi (10 343 kPa) 10 bis 20 % Polypropylen, bezogen auf das Gewicht der Lösung, enthält, wobei die Lösung flashgesponnen wird in einen Bereich vom im wesentlichen niedrigerer Temperatur und niedrigerem Druck, bei dem der halogenierte Kohlenwasserstoff ausgewählt wird aus

1,1-Dichlor-2,2,2-trifluorethan,
1,2-Dichlor-1,2,2-trifluorethan,
1,1-Dichlor-2,2-difluorethan,
1,2-Dichlor-1,1-difluorethan und
1,1-Dichlor-1-fluorethan.

3. Verfahren zum Flashspinnen von plexifilamentären Filmfibrillen-Strängen, bei dem ein faserbildendes Polyolefin bei einer Temperatur im Bereich von 130 bis 210 °C und einem Druck, der größer ist als 1 000 psi (6 895 kPa) in einer Halogen-Kohlenwasserstoff-Spinnflüssigkeit aufgelöst wird, bei dem die Spinnflüssigkeit ein Co-Lösungsmittel enthält, um eine Spinnlösung zu bilden, die 10 bis 20 % eines faserbildenden Polyolefin, bezogen auf das Gewicht der Lösung, enthält, und die dann in eine Umgebung von im wesentlichen niedrigerer Temperatur und niedrigerem Druck flashgesponnen wird, bei dem das genannte Co-Lösungsmittel entweder ein halogenerter Kohlenwasserstoff in einer Konzentration von 2 bis 25 % des gesamten Gewichts der Spinnflüssigkeit oder Methylen-chlorid in einer Konzentration von 5 bis 50 % des Gesamtgewichts der Spinnflüssigkeit ist, und bei dem der halogenierte Kohlenwasserstoff ausgewählt wird aus

1,1-Dichlor-2,2,2-trifluorethan,
1,2-Dichlor-1,2,2-trifluorethan,
1,1-Dichlor-2,2-difluorethan,
1,2-Dichlor-1,1-difluorethan und
1,1-Dichlor-1-fluorethan.

4. Verfahren nach Anspruch 3, bei dem das Co-Lösungsmittel ausgewählt wird aus 3-Methylpentan, Cyclohexan, Toluol, Pentan, Hexan und Chlorbenzol.

5. Verfahren nach Anspruch 4, bei dem das Co-Lösungsmittel nicht mehr als 15 % des Gesamtgewichts der Spinnflüssigkeit beträgt.

6. Verfahren nach Anspruch 1, 2, 3, 4 oder 5, bei dem der halogenierte Kohlenwasserstoff 1,1-Dichlor-2,2,2-trifluorethan ist.

7. Verfahren nach den Ansprüchen 3, 4 oder 5, bei dem das Polyolefin Polyethylen ist.

8. Verfahren nach den Ansprüchen 3, 4 oder 5, bei dem das Polyolefin Polypropylen ist.

9. Lösung, bestehend im wesentlichen aus 10 bis 20 Gew.-% eines faserbildenden Polyolefin und 90 bis 80 Gew.-% einer Flüssigkeit, umfassend einen halogenierten Kohlenwasserstoff, ausgewählt aus

1,1-Dichlor-2,2,2-trifluorethan,
1,2-Dichlor-1,2,2-trifluorethan,
1,1-Dichlor-2,2-difluorethan,
1,2-Dichlor-1,1-difluorethan und
1,1-Dichlor-1-fluorethan.

10. Lösung nach Anspruch 9, in der die Flüssigkeit einen Kohlenwasserstoff als Co-Lösungsmittel in einer Konzentration von 2 bis 25 % des Gesamtgewichts des halogenierten Kohlenwasserstoffs und des Co-Lösungsmittels enthält.

11. Lösung nach Anspruch 9, bei der die Flüssigkeit auch Methylenchlorid als Co-Lösungsmittel in einer Menge von 5 bis 50 Gew.-% des Halogenkohlenwasserstoffs und Methylenchlorid enthält.

12. Lösung, nach einem der Ansprüche 9 bis 11, bei der der halogenierte Kohlenwasserstoff 1,1-Dichlor-2,2,2-trifluorethan ist.

13. Lösung nach einem der Ansprüche 9 bis 12, bei der das Polyolefin Polyethylen ist.

14. Lösung nach einem der Ansprüche 9 bis 12, bei der das Polyolefin Polypropylen ist.

Revendications

1. Un procédé pour le filage-éclair de faisceaux de fibrilles pelliculaires plexifilamentaires dans lequel du polyéthylène est dissous dans un liquide à filer du type hydrocarbure halogéné pour constituer une solution à filer contenant 10 à 20 pour cent de polyéthylène par rapport au poids de la solution à une température de l'ordre de 130 à 210° C et une pression superatmosphérique, cette solution étant soumise à un filage-éclair dans une région de température et de pression considérablement inférieures, dans lequel pour une pression superatmosphérique supérieure à 20685 kPa l'hydrocarbure halogéné est choisi parmi

le 1,1-dichloro-2,2,2-trifluoroéthane et

le 1,2-dichloro-1,2,2-trifluoroéthane ;

pour une pression superatmosphérique supérieure à 12410 kPa, l'hydrocarbure halogéné est choisi parmi le 1,1-dichloro-2,2-difluoroéthane et le 1,2-dichloro-1,1-difluoroéthane ; et pour une pression superatmosphérique supérieure à 13790 kPa, l'hydrocarbure halogéné est du 1,1-dichloro-1-fluoroéthane.

2. Un procédé pour le filage-éclair de faisceaux de fibrilles pelliculaires plexifilamentaires dans lequel du polyéthylène est dissous dans un liquide à filer du type hydrocarbure halogéné pour constituer une solution à filer contenant 10 à 20 pour cent de polypropylène par rapport au poids de la solution à une température de l'ordre de 130 à 210° C et une pression supérieure à 10343 kPa, cette solution étant soumise à un filage-éclair dans une région de température et de pression considérablement inférieures, dans lequel l'hydrocarbure halogéné est choisi parmi

le 1,1-dichloro-2,2,2-trifluoroéthane,

le 1,2-dichloro-1,2,2-trifluoroéthane,

le 1,1-dichloro-2,2-difluoroéthane,

le 1,2-dichloro-1,1-difluoroéthane et

le 1,1-dichloro-1-fluoroéthane.

3. Un procédé pour le filage-éclair de faisceaux de fibrilles pelliculaire plexifilamentaires dans lequel une polyoléfine fibrogène est dissoute dans un liquide à filer du type hydrocarbure halogéné à une température de l'ordre de 130 à 210° C et à une pression supérieure à 6895 kpa, dans lequel le liquide à filer contient un cosolvant pour constituer une solution à filer contenant 10 à 20 pour cent de polyoléfine fibrogène par rapport au poids de la solution, et est ensuite soumise à un filage-éclair dans une région de température et de pression considérablement inférieures, dans lequel ledit cosolvant est soit un hydrocarbure représentant 2 à 25 pour cent du poids total du liquide à filer soit du chlorure de méthylène représentant 5 à 50 pour cent du poids total du liquide à filer et dans lequel l'hydrocarbure halogéné est choisi parmi
 - le 1,1-dichloro-2,2,2-trifluoroéthane,
 - le 1,2-dichloro-1,2,2-trifluoroéthane,
 - le 1,1-dichloro-2,2-difluoroéthane,
 - le 1,2-dichloro-1,1-difluoroéthane et
 - le 1,1-dichloro-1-fluoroéthane.
4. Un procédé selon la revendication 3 dans lequel le cosolvant est choisi parmi le 3-méthyl-pentane, le cyclohexane, le toluène, le pentane, l'hexane et le chlorobenzène.
5. Un procédé selon la revendication 4 dans lequel le cosolvant ne représente pas plus de 15 pour cent du poids total du liquide à filer.
6. Un procédé selon les revendications 1, 2, 3, 4 ou 5, dans lequel l'hydrocarbure halogéné est du 1,1-dichloro-2,2,2-trifluoroéthane.
7. Un procédé selon les revendications 3, 4 ou 5, dans lequel la polyoléfine est du polyéthylène.
8. Un procédé selon les revendications 3, 4 ou 5, dans lequel la polyoléfine est du polypropylène.
9. Une solution comportant essentiellement 10 à 20 pour cent en poids d'une polyoléfine fibrogène et 80 à 90 pour cent en poids d'un liquide comprenant un hydrocarbure halogéné choisi parmi
 - le 1,1-dichloro-2,2,2-trifluoroéthane,
 - le 1,2-dichloro-1,2,2-trifluoroéthane,
 - le 1,1-dichloro-2,2-difluoroéthane,
 - le 1,2-dichloro-1,1-difluoroéthane et
 - le 1,1-dichloro-1-fluoroéthane.
10. Une solution selon la revendication 9 dans laquelle le liquide contient un cosolvant hydrocarbure représentant 2 à 25 pour cent du poids total de l'hydrocarbure halogéné et du cosolvant.
11. Une solution selon la revendication 9 dans laquelle le liquide contient aussi du chlorure de méthylène comme cosolvant représentant 5 à 50 pour cent du poids de l'hydrocarbure halogéné et du chlorure de méthylène.
12. Une solution selon l'une quelconque des revendications 9 à 11 dans laquelle l'hydrocarbure halogéné est du 1,1-dichloro-2,2,2-trifluoroéthane.
13. Une solution selon l'une quelconque des revendications 9 à 12 dans laquelle la polyoléfine est du polyéthylène.
14. Une solution selon l'une quelconque des revendications 9 à 12 dans laquelle la polyoléfine est du polypropylène.