



US010290726B2

(12) **United States Patent**
Gu et al.

(10) **Patent No.:** **US 10,290,726 B2**
(45) **Date of Patent:** **May 14, 2019**

(54) **LATERAL INSULATED GATE BIPOLAR TRANSISTOR**

(71) Applicant: **CSMC TECHNOLOGIES FAB2 CO., LTD.**, Jiangsu (CN)

(72) Inventors: **Yan Gu**, Jiangsu (CN); **Wei Su**, Jiangsu (CN); **Sen Zhang**, Jiangsu (CN)

(73) Assignee: **CSMC TECHNOLOGIES FAB2 CO., LTD.**, Jiangsu (CN)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **15/548,290**

(22) PCT Filed: **Jan. 28, 2016**

(86) PCT No.: **PCT/CN2016/072435**

§ 371 (c)(1),

(2) Date: **Aug. 2, 2017**

(87) PCT Pub. No.: **WO2016/124093**

PCT Pub. Date: **Aug. 11, 2016**

(65) **Prior Publication Data**

US 2018/0012980 A1 Jan. 11, 2018

(30) **Foreign Application Priority Data**

Feb. 2, 2015 (CN) 2015 1 0054601

(51) **Int. Cl.**

H01L 29/10 (2006.01)

H01L 29/40 (2006.01)

(Continued)

(52) **U.S. Cl.**

CPC **H01L 29/7394** (2013.01); **H01L 29/1037**

(2013.01); **H01L 29/1095** (2013.01);

(Continued)

(58) **Field of Classification Search**

CPC H01L 29/7394; H01L 29/1037; H01L 29/1095; H01L 29/402; H01L 29/4236;

H01L 29/735

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,227,653 A 7/1993 Sin et al.

5,773,852 A 6/1998 Han et al.

(Continued)

FOREIGN PATENT DOCUMENTS

CN 101419981 A 4/2009

CN 102832240 A 12/2012

(Continued)


Primary Examiner — Mark W Tornow

(74) *Attorney, Agent, or Firm* — Muncy, Geissler, Olds & Lowe, P.C.

(57) **ABSTRACT**

A lateral insulated gate bipolar transistor, comprising: a substrate (100), having a first conductivity type; an insulating layer (200), formed on the substrate (100); an epitaxial layer (300), having a second conductivity type and formed on the insulating layer (200); a field oxide layer (400), formed on the epitaxial layer (300); a first well (500), having the first conductivity type; a plurality of gate trench structures (600); second source doped regions (720), having the second conductivity type; first source doped regions (710), having the first conductivity type; a second well (800), having the second conductivity type; a first drain doped region (910), having the first conductivity type and formed on a surface layer of the second well (800); gate lead-out ends (10); a source lead-out end (20); a drain lead-out end (30).

11 Claims, 3 Drawing Sheets



- (51) **Int. Cl.**
H01L 29/423 (2006.01)
H01L 29/735 (2006.01)
H01L 29/739 (2006.01)

- (52) **U.S. Cl.**
CPC *H01L 29/402* (2013.01); *H01L 29/4236*
(2013.01); *H01L 29/735* (2013.01)

(56) **References Cited**

U.S. PATENT DOCUMENTS

2008/0265278 A1* 10/2008 Hara G09G 3/296
257/141
2009/0194785 A1 8/2009 Lu et al.
2011/0291157 A1* 12/2011 Takahashi H01L 29/0696
257/144
2013/0153956 A1* 6/2013 Shi H01L 21/743
257/140
2016/0111415 A1* 4/2016 Basler H01L 29/7397
257/140

FOREIGN PATENT DOCUMENTS

CN 103413824 A 11/2013
CN 104040720 A 9/2014
KR 99015523 A 3/1999

* cited by examiner




FIG. 3




FIG. 4




FIG. 5

1

LATERAL INSULATED GATE BIPOLAR TRANSISTOR

FIELD OF THE INVENTION

The present disclosure relates to the field of semiconductor devices, and more particularly relates to a lateral insulated gate bipolar transistor (LIGBT).

BACKGROUND OF THE INVENTION

Lateral insulated gate bipolar transistor is a transistor that combines the advantages of MOS and bipolar transistors, and it is widely applied to an output stage of a power output drive circuit. Meanwhile, Silicon-on-Insulator (SOI) technology is widely used in manufacturing of power integrated circuit due to its ideal dielectric isolation performance. The SOI-LIGBT device is a LIGBT device based on SOI technology.

In a conventional SOI-LIGBT device, the conductive channel of the device is in a lateral direction, the electron hole current can only drift to the other end through the lateral direction, and the injection of carriers is concentrated on the surface. Therefore, such a single device has a very small working current during conduction. In order to obtain a higher working current, a plurality of cells are required to be added in parallel, which, however lead to a large area of the device, at the same time lead to increase of saturation conduction voltage drop of the device, such that the switching characteristics of the device is also weakened.

SUMMARY OF THE INVENTION

Accordingly, it is necessary to provide a lateral insulated gate bipolar transistor which exhibits the advantages of large working current, small device area, and low conduction voltage drop.

A lateral insulated gate bipolar transistor includes:

- a substrate of a first conductivity type;
- an insulating layer formed on the substrate;
- an epitaxial layer of a second conductivity type formed on the insulating layer;
- an field oxide layer formed on the epitaxial layer;
- a first well of the first conductivity type formed on the epitaxial layer and positioned on a side of the field oxide layer;
- a plurality of gate trench structures embedded in the first well and spaced apart from each other, a bottom of each gate trench structure extends to the epitaxial layer; each gate trench structure comprises a trench and conductive material filled in the trench, an inner sidewall of the trench is provided with a gate insulating layer;
- a second source doped region of the second conductivity type formed on a surface of the first well and on both sides of each gate trench structure;
- a first source doped region of the first conductivity type formed on a surface of the first well and on a side of the second source doped region away from the gate trench structure;
- a second well of the second conductivity type formed on the epitaxial layer and positioned on a side of the field oxide layer away from the first well;
- a first drain doped region of the first conductivity type formed on a surface of the second well;
- a gate lead-out terminal electrically coupled to the conductive material;

2

a source lead-out terminal electrically coupled to the second source doped region and the first source doped region; and

a drain lead-out terminal electrically coupled to the first drain doped region.

According to the aforementioned lateral insulated gate bipolar transistor, one or more gate trench structure are added to the source structure of a single cell, and a gate lead-out terminal is led out from the gate trench structure to serve as the gate, such that when a certain voltage is applied to the gate electrode, the gate insulating layer on both sides of the trench and the first well form an inversion layer, i.e., a conductive channel. When a voltage is applied to the drain structure (the first drain doped region), there is a current flowing in the conductive channel. If there are N gate trench structures, then there will be 2N conductive channels flowed by the current, such that the current density in the single cell structure is significantly increased compared with that of the conventional single channel SOI-LIGBT, thus increasing the overall current density of the single device in a multi-cell structure. Accordingly, under the same working current, the greater working current of the single cell structure can enable the device to have a smaller size and lower conduction voltage drop. And under the same device area, the aforementioned lateral insulated gate bipolar transistor can have a greater working current.

BRIEF DESCRIPTION OF THE DRAWINGS

To illustrate the technical solutions according to the embodiments of the present invention or in the prior art more clearly, the accompanying drawings for describing the embodiments or the prior art are introduced briefly in the following. Apparently, the accompanying drawings in the following description are only some embodiments of the present invention, and persons of ordinary skill in the art can derive other drawings from the accompanying drawings without creative efforts.

FIG. 1 is a schematic view of a lateral insulated gate bipolar transistor according to a first embodiment;

FIG. 2 is an enlarged view of the gate trench structure of FIG. 1;

FIG. 3 is a schematic view of a lateral insulated gate bipolar transistor according to a second embodiment;

FIG. 4 is a schematic view of a lateral insulated gate bipolar transistor according to a third embodiment;

FIG. 5 is a schematic view of a lateral insulated gate bipolar transistor according to a fourth embodiment.

DETAILED DESCRIPTION OF THE EMBODIMENTS

Embodiments of the invention are described more fully hereinafter with reference to the accompanying drawings. The various embodiments of the invention may, however, be embodied in many different forms and should not be construed as limited to the embodiments set forth herein. Rather, these embodiments are provided so that this disclosure will be thorough and complete, and will fully convey the scope of the invention to those skilled in the art.

Unless otherwise defined, all terms (including technical and scientific terms) used herein have the same meaning as commonly understood by one of ordinary skill in the art to which this invention belongs. It will be further understood that terms, such as those defined in commonly used dictionaries, should be interpreted as having a meaning that is consistent with their meaning in the context of the relevant

art and will not be interpreted in an idealized or overly formal sense unless expressly so defined herein. The term “and/or” as used herein includes any and all combinations of one or more of the associated listed items.

The terms used in the field of semiconductor have the same meaning as commonly understood by persons of ordinary skill in the art. For example, regarding P-type and N-type impurities, in order to distinguish the doping concentration, the P+ type represents the P-type with heavy doping concentration, the P-type represents the P-type with doping concentration, the P- type represents the P-type with light doping concentration, the N+ type represents the N-type with heavy doping concentration, the N-type represents the N-type with doping concentration, and the N- type represents the N-type with light doping concentration.

Embodiments of the invention are described more fully hereinafter with reference to the accompanying drawings. In the following description, the first conductivity type is P-type and the second conductivity type is N-type.

The First Embodiment

FIG. 1 is a schematic view of a lateral insulated gate bipolar transistor according to a first embodiment.

The lateral insulated gate bipolar transistor according to the first embodiment includes: a substrate **100** of a first conductivity type, an insulating layer **200**, an epitaxial layer **300** of a second conductivity type, an field oxide layer **400**, a first well **500** of the first conductivity type, gate trench structures **600**, a first source doped region **710** of the first conductivity type, a second source doped region **720** of the second conductivity type, a second well **800** of the second conductivity type, a first drain doped region **910** of the first conductivity type, a gate lead-out terminal **10**, a source lead-out terminal **20**, and a drain lead-out terminal **30**.

The substrate **100** is made of silicon, silicon carbide, gallium arsenide, indium phosphide or germanium silicon. The substrate is a P+ type substrate (P-sub).

The insulating layer **200** is formed on the substrate **100**. The insulating layer is made of silicon oxide, such as silicon dioxide. The insulating layer **200** is functionally a buried oxygen layer. The substrate **100** has little effect on the device due to the blocking effect of the insulating layer **200**, such that the substrate **100** can be heavily doped (P+).

The epitaxial layer **300** is formed on the insulating layer **200**. The epitaxial layer **300** is an N-type epitaxial layer. The epitaxial layer **300** serves as a drift region and has an conductivity type opposite to that of the substrate **100**. The epitaxial layer **300** is made of silicon, silicon carbide, gallium arsenide, indium phosphide or germanium silicon.

The field oxide layer **400** is formed on the epitaxial layer **300**. The field oxide layer **400** is made of silicon oxide, such as silicon dioxide. The field oxide layer **400** is mainly configured to separate a source structure and a drain structure.

The first well **500** is formed on the epitaxial layer **300** and is positioned on a side of the field oxide layer **400**. The first well **500** is a P- type well. As a buffer region for the source structure, the first well has some effects on device conduction hole injection and withstand voltage.

The plurality of gate trench structures **600** are embedded in the first well **500** and spaced apart from each other. A bottom of each gate trench structure **600** extends to the epitaxial layer **300**. Each gate trench structure **600** includes a trench **610** and conductive material **620** filled in the trench, an inner sidewall of the trench **610** is provided with a gate insulating layer **630**. The conductive material **620** is poly-

silicon. The gate insulating layer **630** is made of silicon oxide, such as silicon dioxide. The gate lead-out terminal **10** is electrically coupled to the conductive material **620** in the trench **610**. The gate lead-out terminal **10** is a gate contact electrode.

FIG. 2 is an enlarged view of the gate trench structure.

Since the gate is embedded in the first well **500** in the form of a trench, when a certain voltage is applied to the gate electrode (gate lead-out terminal **10**), the gate insulating layer **630** on both sides of the trench **610** and the first well **500** form an inversion layer, i.e., a conductive channel. When a voltage is applied to the drain structure (the first drain doped region **910**), there is a current flowing in the conductive channel. If there are N gate trench structures **600**, then there will be 2N conductive channels flowed by the current, such that the current density in the single cell structure is significantly increased compared with that of the conventional single channel SOI-LIGBT, thus increasing the overall current density of the single device in a multi-cell structure. Accordingly, under the same working current, the greater working current of the single cell structure can enable the device to have a smaller size and lower conduction voltage drop. And under the same device area, the aforementioned lateral insulated gate bipolar transistor can have a greater working current.

The second source doped region **720** is formed on a surface of the first well **500** and on both sides of each gate trench structure **600**. The second source doped region **720** is an N+ type source doped region and is wrapped by the first well **500**.

The first source doped region **710** is formed on a surface of the first well **500** and on a side of the second source doped region **720** away from the gate trench structure **600**. The first source doped region is a P+ type source doped region and is also wrapped by the first well **500**. In other words, the second source doped region **720** and the first source doped region **710** are successively arranged on each side of the gate trench structure **600**.

The source lead-out terminal **20** is electrically coupled to the second source doped region **720** and the first source doped region **710**. The source lead-out terminal **20** is a source contact electrode.

The second well **800** is formed on the epitaxial layer **300** and is positioned on a side of the field oxide layer **400** away from the first well **500**. The second well is an N-type well, which has a middle doping concentration. The first well **500** and the second well **800** are located on opposite sides of the field oxide layer **400**.

The first drain doped region **910** is formed on the surface of the second well **800**. The first drain doped region **910** is a P+ type drain doped region and is wrapped by the second well **800**.

The drain lead-out terminal **30** is electrically coupled to the first drain doped region **910**. The drain lead-out terminal **30** is a drain contact electrode.

The gate lead-out terminal **10**, the source lead-out terminal **20**, and the drain lead-out terminal **30** are usually made of conductive materials, such as copper, aluminum, aluminum-silicon alloy, titanium, titanium nitride, tungsten, polysilicon, metal silicide and the like. The gate lead-out terminal **10**, the source lead-out terminal **20**, and the drain lead-out terminal **30** can be formed by physical/chemical vapor deposition.

The used raw material is a sandwich structure with the buried oxide layer (insulating layer **200**) as the middle layer, i.e., SOI structure. The raw material can also be a two-layered material having the insulating substrate (substrate

5

100) and a top-layer monocrystalline silicon (the epitaxial layer 300). There is a longitudinal PNP transistor below the drain of the lateral insulated gate bipolar transistor, the PNP transistor is composed by a drain terminal high-doped P-region (the first drain doped region 910), a top-layer silicon N-type embedding region (the second well 800) and a substrate P-type embedding region (substrate 100). When the device is switched on, the PNP transistor is easily to be turned on, which results in that the drain current flows through the transistor to the substrate and thus resulting failure. Therefore, when fabricating device using SOI structure, only the top-layer silicon (the epitaxial layer 300) is used as the device fabrication layer, on which the source, drain, channel region and the like is formed, and the substrate (substrate 100) serves only as a support. In this structure, the buried oxide layer is electrically isolated from the substrate, thus eliminating the formation of the longitudinal PNP transistor from the source. In addition, a dielectric isolation structure is provided between the devices, then a completely isolation of the entire device is achieved.

In the raw materials, the top-layer silicon (the epitaxial layer 300) requires a certain thickness, e.g. greater than a depth of the gate trench structures 600, such that there is enough distance between the gate trench structures 600 and the buried oxide layer (insulating layer 200), and the flow path of electron becomes wider, the on-state resistance becomes smaller in the conducting state, and the distribution of the electric field becomes more uniform in the reverse withstand voltage.

The Second Embodiment

FIG. 3 is a schematic view of a lateral insulated gate bipolar transistor according to the second embodiment.

The lateral insulated gate bipolar transistor of the second embodiment is similar to that of the first embodiment, and differs in that: the lateral insulated gate bipolar transistor of the second embodiment further includes a second drain doped region 920. The second drain doped region 920 is an N⁺-type drain doped region, which is formed on the surface of the second well 800. The second drain doped region 920 is sandwiched between the field oxide layer 400 and the first drain doped region 910. The drain lead-out terminal 30 is electrically coupled to the second drain doped region 920.

The second well 800 is firstly shorted with the drain structure and then led out, which has some advantages that, when the device is switched off, the drift region (the epitaxial layer 300) will generate a conductance modulation effect in the conducting state, the stored carriers can flow out directly from the drain via the second drain doped region 920 of the drain structure. Meanwhile, the attenuation process also occurs under the composite effect, thus the problems of large off-tail current and long turn-off time caused by small sub-memory effect of the parasitic PNP transistor in the device are effectively addressed, and the turn-off time is effectively reduced.

The Third Embodiment

The lateral insulated gate bipolar transistor of the third embodiment is substantially the same as the first embodiment, and differs in that it further includes a conductive member 40. The conductive member 40 is formed on a side of the field oxide layer 400 adjacent to the second well 800. The drain lead-out terminal 30 is electrically coupled to the conductive member 40. The conductive member 40 can be made of polysilicon.

6

When the device is under a reverse voltage, the conductive member 40 has the same potential as the drain structure, such that the potential of the oxide layer structure 400 has a substantially linear change from the drain structure to the source structure. The electric field distribution in the drift region (the epitaxial layer 300) also has a linear change, which can assist the drift region to be depleted, and the rate of reverse depletion can be kept uniform. When the concentration of the drift region becomes slightly higher, no local electric field lines are generated which results in the peak electric field. Accordingly, the concentration of the drift region can be slightly increased to reduce the conduction voltage drop, without changing breakdown voltage and breakdown point.

The Fourth Embodiment

FIG. 5 is a schematic view of a lateral insulated gate bipolar transistor according to a fourth embodiment.

The lateral insulated gate bipolar transistor of the fourth embodiment is substantially the same as the first embodiment, and differs in that it further includes an embedded region 730 of the first conductivity type. The embedded region 730 is a P-type doped region and has a middle doping concentration. The embedded region 730 is formed between the first source doped region 710 and the first well 500. In other words, the first source doped region 710 is wrapped by the embedded region 730, such that the first source doped region 710 is isolated from the first well 500.

When the device is a conduction state, there is a parasitic NPN transistor generated below the source structure. When the condition that the base minority carrier of the transistor can cross is met, the transistor will be turned on, this will cause the device to fail during the turning on stage. The P-type doped region added below the first source doped region 710 can increase the concentration of the base region of the NPN transistor, the life of the minority carrier is reduced and cannot travel to the emitter, thus it can effectively avoid the phenomenon of turning on of the source parasitic transistor.

According to the aforementioned lateral insulated gate bipolar transistor, one or more gate trench structure are added to the source structure of a single cell, and a gate lead-out terminal is led out from the gate trench structure to serve as the gate, such that when a certain voltage is applied to the gate electrode, the gate insulating layer on both sides of the trench and the first well form an inversion layer, i.e., a conductive channel. When a voltage is applied to the drain structure (the first drain doped region), there is a current flowing in the conductive channel. If there are N gate trench structures, then there will be 2N conductive channels flowed by the current, such that the current density in the single cell structure is significantly increased compared with that of the conventional single channel SOI-LIGBT, thus increasing the overall current density of the single device in a multi-cell structure. Accordingly, under the same working current, the greater working current of the single cell structure can enable the device to have a smaller size and lower conduction voltage drop. And under the same device area, the aforementioned lateral insulated gate bipolar transistor can have a greater working current.

The foregoing descriptions are merely specific embodiments of the present invention, but are not intended to limit the protection scope of the present invention. Any variation or replacement readily figured out by a person skilled in the art within the technical scope disclosed in the present invention shall all fall within the protection scope of the

present invention. Therefore, the protection scope of the present invention shall be subject to the protection scope of the appended claims.

What is claimed is:

1. A lateral insulated gate bipolar transistor, comprising:
 - a substrate of a first conductivity type;
 - an insulating layer formed on the substrate;
 - an epitaxial layer of a second conductivity type formed on the insulating layer;
 - a field oxide layer formed on the epitaxial layer;
 - a first well of the first conductivity type formed on the epitaxial layer and positioned on a side of the field oxide layer;
 - a plurality of gate trench structures embedded in the first well and spaced apart from each other, a bottom of each of the plurality of gate trench structures extending to the epitaxial layer, and said each of the plurality of gate trench structures comprising a trench and conductive material filled in the trench, an inner sidewall of the trench being provided with a gate insulating layer;
 - a second source doped region of the second conductivity type formed on a surface of the first well and on both sides of each gate trench structure;
 - a first source doped region of the first conductivity type formed on a surface of the first well and on a side of the second source doped region away from the gate trench structure, the first source doped region being more heavily doped than the first well;
 - a second well of the second conductivity type formed on the epitaxial layer and positioned on a side of the field oxide layer away from the first well;
 - a first drain doped region of the first conductivity type formed on a surface of the second well;
 - a gate lead-out terminal electrically coupled to the conductive material;
 - a source lead-out terminal electrically coupled to the second source doped region and the first source doped region;
 - a drain lead-out terminal electrically coupled to the first drain doped region; and
 - a conductive member formed on a side of the field oxide adjacent to the second well and contacting the field oxide, wherein the drain lead-out terminal is electrically coupled to the conductive member.
2. The lateral insulated gate bipolar transistor according to claim 1, wherein the first conductivity type is P-type, and the second conductivity type is N-type.

3. The lateral insulated gate bipolar transistor according to claim 1, wherein
 - the substrate is a P+-type substrate, the epitaxial layer is an N--type epitaxial layer,
 - the first well is a P--type well, the second source doped region is an N+-type source doped region,
 - the first source doped region is a P+-type source doped region,
 - the second well is an N-well, and
 - the first drain doped region is a P+-type drain doped region.
4. The lateral insulated gate bipolar transistor according to claim 1, further comprising a second drain doped region of the second conductivity type, wherein
 - the second drain doped region is an N+-type drain doped region,
 - the second drain doped region is formed on the surface of the second well and is sandwiched between the field oxide layer and the first drain doped region, and
 - the drain lead-out terminal is electrically coupled to the second drain doped region.
5. The lateral insulated gate bipolar transistor according to claim 1, further comprising an embedded region of the first conductivity type formed between the first source doped region and the first well, thereby isolating the first source doped region from the first well.
6. The lateral insulated gate bipolar transistor according to claim 1, wherein the substrate and the epitaxial layer are made of silicon, silicon carbide, gallium arsenide, indium phosphide or germanium silicon.
7. The lateral insulated gate bipolar transistor according to claim 1, wherein the insulating layer, the field oxide layer, and the gate insulating layer are made of silicon oxide.
8. The lateral insulated gate bipolar transistor according to claim 1, wherein the conductive material is polysilicon.
9. The lateral insulated gate bipolar transistor according to claim 1, wherein the gate lead-out terminal is a gate contact electrode, and the source lead-out terminal is a source contact electrode.
10. The lateral insulated gate bipolar transistor according to claim 1, wherein both of the gate insulating layer and the first well form an inversion layer.
11. The lateral insulated gate bipolar transistor according to claim 1, wherein the gate lead-out terminal, the source lead-out terminal, and the drain lead-out terminal are made of copper, aluminum, aluminum-silicon alloy, titanium, titanium nitride, tungsten, polysilicon or metal silicide.

* * * * *