



(86) Date de dépôt PCT/PCT Filing Date: 2010/10/07
 (87) Date publication PCT/PCT Publication Date: 2011/04/14
 (45) Date de délivrance/Issue Date: 2016/11/22
 (85) Entrée phase nationale/National Entry: 2012/03/08
 (86) N° demande PCT/PCT Application No.: EP 2010/064964
 (87) N° publication PCT/PCT Publication No.: 2011/042484
 (30) Priorité/Priority: 2009/10/08 (ITMI2009A001719)

(51) Cl.Int./Int.Cl. *C25B 11/04* (2006.01)
 (72) Inventeurs/Inventors:
 ANTOZZI, ANTONIO LORENZO, IT;
 BRICHESE, MARIANNA, IT;
 CALDERARA, ALICE, IT
 (73) Propriétaire/Owner:
 INDUSTRIE DE NORA S.P.A., IT
 (74) Agent: MACRAE & CO.

(54) Titre : CATHODE POUR PROCEDES ELECTROLYTIQUES
 (54) Title: CATHODE FOR ELECTROLYTIC PROCESSES

(57) **Abrégé/Abstract:**

A cathode for electrolytic processes, particularly suitable for hydrogen evolution in chloralkali electrolysis consists of a metal substrate provided with a catalytic coating made of two layers containing palladium, rare earths (such as praseodymium) and a noble component selected between platinum and ruthenium. The rare earth percent amount by weight is lower in the outer layer than in the inner layer.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
14 April 2011 (14.04.2011)

(10) International Publication Number
WO 2011/042484 A1

(51) International Patent Classification:
C25B 11/04 (2006.01)

(21) International Application Number:
PCT/EP2010/064964

(22) International Filing Date:
7 October 2010 (07.10.2010)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
MI2009A001719 8 October 2009 (08.10.2009) IT

(71) Applicant (for all designated States except US): **INDUSTRIE DE NORA S.P.A.** [IT/IT]; Via Bistolfi 35, I-20134 Milano (IT).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **ANTOZZI, Antonio Lorenzo** [IT/IT]; Via Sant'Ambrogio, 20, I-23807 Merate (IT). **BRICHESE, Marianna** [IT/IT]; Via della Sachetta, 3, I-30021 Caorle (IT). **CALDERARA, Alice** [IT/IT]; Via della Vittoria, I-26020 Agnadello (IT).

(74) Agent: **REITSTÖTTER KINZEBACH**; Sternwartstr. 4, 81679 München (DE).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) Title: CATHODE FOR ELECTROLYTIC PROCESSES

(57) Abstract: A cathode for electrolytic processes, particularly suitable for hydrogen evolution in chloralkali electrolysis consists of a metal substrate provided with a catalytic coating made of two layers containing palladium, rare earths (such as praseodymium) and a noble component selected between platinum and ruthenium. The rare earth percent amount by weight is lower in the outer layer than in the inner layer.



WO 2011/042484 A1

CATHODE FOR ELECTROLYTIC PROCESSES

FIELD OF THE INVENTION

5

The invention relates to an electrode for use in electrolytic processes and to a method of manufacturing thereof.

BACKGROUND OF THE INVENTION

10

The invention relates to a cathode for electrolytic processes, in particular to a cathode suitable for hydrogen evolution in an industrial electrolytic process. In the following, reference will be made to chlor-alkali electrolysis as a typical process of industrial electrolysis with cathodic hydrogen evolution, but the invention is not limited to a particular application. In the industry of electrolytic processes, competitiveness is associated with several factors, the main of which is the reduction of energy consumption, directly correlated with the operative voltage; this justifies the many efforts directed to reduce the various components of the latter, for instance ohmic drops, which depend on process parameters such as temperature, electrolyte concentration and interelectrode gap, besides anodic and cathodic overvoltage. For this reason, although some chemically resistant metallic materials deprived of catalytic activity – such as for instance carbon steels – may be used as hydrogen-evolving cathodes in various electrolytic processes, the use of electrodes activated with a catalytic coating has become more widespread with the purpose of decreasing the hydrogen cathodic overvoltage. Good results can thus be obtained by using metal substrates, for instance made of nickel, copper or steel, provided with ruthenium oxide or platinum-based catalytic coatings. Energy savings obtainable through the use of activated cathodes in fact can sometimes compensate for the costs deriving from the employment of precious metal-based catalysts. At any rate, the economic convenience of the use of activated cathodes basically depends on their operative lifetime: in order to compensate for the cost of installation of activated cathodic structures in a chlor-alkali cell it is for instance necessary to guarantee their functioning for a period of time not lower than 2 or 3 years. Nevertheless, the vast majority of noble metal-based catalytic coatings suffer great

15
20
25
30

damages following the occasional current reversals which can typically occur in case of malfunctioning of industrial plants: the passage of anodic current, even of limited duration, leads to a shifting of the potential to very high values, somehow giving rise to the dissolution of platinum or of ruthenium oxide. A partial solution of this problem was proposed in international patent application WO 2008/043766 incorporated herein in its entirety, disclosing a cathode obtained on a nickel substrate provided with a coating consisting of two distinct zones, one of which comprising palladium and optionally silver, with a protective function especially towards current reversal phenomena, and an activation zone comprising platinum and/or ruthenium, preferably mixed with a small content of rhodium, with a function of catalyst for cathodic hydrogen evolution. The increase in the tolerance to current reversal phenomena is presumably attributable to the role of palladium, which can form hydrides during the normal cathodic operation; during the reversals, hydrides would be ionised preventing the electrode potential from shifting to dangerous levels. Although the invention disclosed in WO 2008/043766 proves useful in extending the lifetime of activated cathodes in electrolysis processes, suitable performances are provided only by those formulations containing a significant amount of rhodium; in consideration of the very high price of rhodium and of the limited availability of this metal, this appears to be a strong limitation to the use of such kind of coatings.

It has therefore been evidenced the need for a new cathode composition for industrial electrolytic processes, in particular for electrolytic processes with cathodic evolution of hydrogen, characterised by a higher catalytic activity and by an equivalent or higher duration and tolerance to accidental current reversals in the usual operating conditions with respect to prior art formulations.

SUMMARY OF THE INVENTION

Various aspects of the invention are set out in the accompanying claims.

In one embodiment, a cathode for electrolytic processes consists of a metal substrate, for instance made of nickel, copper or carbon steel, provided with a catalytic coating comprising at least two layers, both containing palladium, rare earths and at least one

component selected between platinum and ruthenium, wherein the percent amount of rare earths is higher in the inner layer – indicatively above 45% by weight – and lower in the outer layer, indicatively 10 to 45% by weight. In one embodiment, the percent amount of rare earth is 45 to 55% by weight in the inner catalytic layer and 30 to 40% by weight in the outer catalytic layer. In the present description and in the claims of the instant application, the percent amount by weight of the various elements is referred to the metals, except when specified otherwise. The indicated elements may be present as such or in form of oxides or other compounds, for instance platinum and ruthenium may be present in form of metals or oxides, rare earths mainly as oxides, palladium mainly as oxide upon manufacturing the electrode and mainly as metal in operating conditions under hydrogen evolution. Inventors have surprisingly observed that the amount of rare earths inside the catalytic layer displays its protective action versus the noble component more effectively when a certain compositional gradient is established, in particular when the rare earth content is lower in the outermost layer. Without wishing the invention to be bound to a particular theory, it might be assumed that the reduced amount of rare earth in the outer layer makes the platinum or ruthenium catalytic sites more accessible to the electrolyte, without significantly altering the overall structure of the coating. In one embodiment, rare earths comprise praseodymium, even though the inventors found out how other elements of the same group, for instance cerium and lanthanum, are capable of displaying an analogous action with similar results. In one embodiment, the catalytic coating is free of rhodium; the catalytic coating formulation with a reduced amount of rare earths in the outermost layer is characterised by an extremely low hydrogen evolution cathodic overvoltage, so that the use of rhodium as catalyst becomes unnecessary. This can have the advantage of reducing the manufacturing cost of the electrode to a remarkable extent, given the tendency of the price of rhodium to remain consistently higher than those of platinum and ruthenium. In one embodiment, the palladium to noble component weight ratio is 0.5 to 2 referred to the metals; this can have the advantage of providing an adequate catalytic activity combined with a suitable protection of the catalyst from accidental current reversal phenomena. In one embodiment, the palladium content in such formulation can be partially replaced by silver, for instance with an Ag/Pd molar ratio of 0.15 to 0.25. This can have the advantage of improving the capability of palladium of absorbing hydrogen during operation and oxidising the absorbed hydrogen during the accidental current

reversals.

In one embodiment, the above described electrode is obtained by oxidative pyrolysis of precursor solutions, that is by thermal decomposition of at least two solutions
5 sequentially applied; both solutions comprise salts or other soluble compounds of palladium, of a rare earth such as praseodymium and of at least one noble metal such as platinum or ruthenium, under the condition that the last applied solution, directed to form the outermost catalytic layer, have a rare earth percent amount lower than that of the first applied solution. In one embodiment, the salts contained in the precursor
10 solutions are nitrates and their thermal decomposition is carried out at a temperature of 430-500°C in the presence of air.

Some of the most significant results obtained by the inventors are presented in the following examples, which shall not be intended as a limitation of the extent of the
15 invention.

EXAMPLE 1

A nickel 200 mesh of 100 mm x 100 mm x 0.89 mm size was subjected to a blasting
20 treatment with corundum, then etched in 20% boiling HCl for 5 minutes. The mesh was then painted with 5 coats of an aqueous solution of Pt (II) diamino dinitrate (30 g/l), Pr (III) nitrate (50 g/l) and Pd (II) nitrate (20 g/l) acidified with nitric acid, with execution of a 15 minute thermal treatment at 450°C after each coat until obtaining the deposition of 1.90 g/m² of Pt, 1.24 g/m² of Pd and 3.17 g/m² of Pr (inner catalytic layer formation). On
25 the thus obtained catalytic layer, 4 coats of a second solution were applied containing Pt (II) diamino dinitrate (30 g/l), Pr (III) nitrate (27 g/l) and Pd (II) nitrate (20 g/l) acidified with nitric acid, with execution of a 15 minute thermal treatment at 450°C after each coat until obtaining the deposition of 1.77 g/m² of Pt, 1.18 g/m² of Pd and 1.59 g/m² of Pr (outer catalytic layer formation).

30

The sample was subjected to an operating test, displaying an ohmic-corrected initial average cathodic potential of -924 mV/NHE at 3 kA/m² under hydrogen evolution in 33% NaOH, at a temperature of 90°C, corresponding to an excellent catalytic activity.

The same sample was subsequently subjected to cyclic voltammetry in the range from -1 to +0.5 V/NHE at a scan rate of 10 mV/s; the average cathodic potential variation after 25 cycles was 15 mV, corresponding to an excellent tolerance to current reversal.

5

EXAMPLE 2

A nickel 200 mesh of 100 mm x 100 mm x 0.89 mm size was subjected to a blasting treatment with corundum, then etched in 20% boiling HCl for 5 minutes. The mesh was then painted with 3 coats of an aqueous solution of Pt (II) diamino dinitrate (30 g/l), Pr (III) nitrate (50 g/l) and Pd (II) nitrate (20 g/l) acidified with nitric acid, with execution of a 15 minute thermal treatment at 460°C after each coat until obtaining the deposition of 1.14 g/m² of Pt, 0.76 g/m² of Pd and 1.90 g/m² of Pr (inner catalytic layer formation). On the thus obtained catalytic layer, 6 coats of a second solution were applied containing Pt (II) diamino dinitrate (23.4 g/l), Pr (III) nitrate (27 g/l) and Pd (II) nitrate (20 g/l) acidified with nitric acid, with execution of a 15 minute thermal treatment at 460°C after each coat until obtaining the deposition of 1.74 g/m² of Pt, 1.49 g/m² of Pd and 2.01 g/m² of Pr (outer catalytic layer formation).

The sample was subjected to an operating test, displaying an ohmic-corrected initial average cathodic potential of -926 mV/NHE at 3 kA/m² under hydrogen evolution in 33% NaOH, at a temperature of 90°C, corresponding to an excellent catalytic activity.

The same sample was subsequently subjected to cyclic voltammetry in the range from -1 to +0.5 V/NHE at a scan rate of 10 mV/s; the average cathodic potential variation after 25 cycles was 28 mV, corresponding to a still acceptable tolerance to current reversal albeit a bit lower than the electrode of example 1; this was attributed to the fact that the percent amount of rare earth in the inner catalytic layer (65%) is a little higher than the value later identified as optimum (45-55%).

30

EXAMPLE 3

A nickel 200 mesh of 100 mm x 100 mm x 0.89 mm size was subjected to a blasting treatment with corundum, then etched in 20% boiling HCl for 5 minutes. The mesh was then painted with 5 coats of an aqueous solution of Ru (III) nitrosyl nitrate (30 g/l), Pr (III) nitrate (50 g/l), Pd (II) nitrate (16 g/l) and AgNO₃ (4 g/l) acidified with nitric acid, with execution of a 15 minute thermal treatment at 430°C after each coat until obtaining the deposition of 1.90 g/m² of Ru, 1.01 g/m² of Pd, 0.25 g/m² of Ag and 3.17 g/m² of Pr (inner catalytic layer formation). On the thus obtained catalytic layer, 6 coats of a second solution were applied containing Ru (III) nitrosyl nitrate (30 g/l), Pr (III) nitrate (27 g/l), Pd (II) nitrate (16 g/l) and AgNO₃ (4 g/l) acidified with nitric acid, with execution of a 15 minute thermal treatment at 430°C after each coat until obtaining the deposition of 2.28 g/m² of Ru, 1.22 g/m² of Pd, 0.30 g/m² of Ag and 2.05 g/m² of Pr (outer catalytic layer formation).

The sample was subjected to an operating test, displaying an ohmic-corrected initial average cathodic potential of -925 mV/NHE at 3 kA/m² under hydrogen evolution in 33% NaOH, at a temperature of 90°C, corresponding to an excellent catalytic activity.

The same sample was subsequently subjected to cyclic voltammetry in the range from -1 to +0.5 V/NHE at a scan rate of 10 mV/s; the average cathodic potential variation after 25 cycles was 12 mV, corresponding to an excellent tolerance to current reversal.

EXAMPLE 4

A nickel 200 mesh of 100 mmx 100 mm x 0.89 mm size was subjected to a blasting treatment with corundum, then etched in 20% boiling HCl for 5 minutes. The mesh was then painted with 5 coats of an aqueous solution of Pt (II) diamino dinitrate (30 g/l), La (III) nitrate (50 g/l) and Pd (II) nitrate (20 g/l) acidified with nitric acid, with execution of a 15 minute thermal treatment at 450°C after each coat until obtaining the deposition of 1.90 g/m² of Pt, 1.24 g/m² of Pd and 3.17 g/m² of La (inner catalytic layer formation). On the thus obtained catalytic layer, 3 coats of a second solution were applied containing Pt (II) diamino dinitrate (30 g/l), La (III) nitrate (32 g/l) and Pd (II) nitrate (20 g/l) acidified with nitric acid, with execution of a 15 minute thermal treatment at 450°C after each

coat until obtaining the deposition of 1.14 g/m² of Pt, 0.76 g/m² of Pd and 1.22 g/m² of La (outer catalytic layer formation).

The sample was subjected to an operating test, displaying an ohmic-corrected initial average cathodic potential of -928 mV/NHE at 3 kA/m² under hydrogen evolution in 33% NaOH, at a temperature of 90°C, corresponding to an excellent catalytic activity.

The same sample was subsequently subjected to cyclic voltammetry in the range from -1 to +0.5 V/NHE at a scan rate of 10 mV/s; the average cathodic potential variation after 25 cycles was 22 mV, corresponding to an excellent tolerance to current reversal.

COUNTEREXAMPLE 1

A nickel 200 mesh of 100 mm x 100 mm x 0.89 mm size was subjected to a blasting treatment with corundum, then etched in 20% boiling HCl for 5 minutes. The mesh was then painted with 7 coats of an aqueous solution of Pt (II) diamino dinitrate (30 g/l), Pr (III) nitrate (50 g/l), Rh (III) chloride (4 g/l) and Pd (II) nitrate (20 g/l) acidified with nitric acid, with execution of a 15 minute thermal treatment at 450°C after each coat until obtaining the deposition of 2.66 g/m² of Pt, 1.77 g/m² of Pd, 0.44 g/m² of Rh and 4.43 g/m² of Pr (formation of a catalytic layer in accordance with WO 2008/043766).

The sample was subjected to an operating test, displaying an ohmic-corrected initial average cathodic potential of -930 mV/NHE at 3 kA/m² under hydrogen evolution in 33% NaOH, at a temperature of 90°C, corresponding to a good catalytic activity, albeit lower than that of the previous examples notwithstanding the presence of rhodium.

The same sample was subsequently subjected to cyclic voltammetry in the range from -1 to +0.5 V/NHE at a scan rate of 10 mV/s; the average cathodic potential variation after 25 cycles was 13 mV, corresponding to an excellent tolerance to current reversal.

COUNTEREXAMPLE 2

A nickel 200 mesh of 100 mm x 100 mm x 0.89 mm size was subjected to a blasting treatment with corundum, then etched in 20% boiling HCl for 5 minutes. The mesh was then painted with 7 coats of an aqueous solution of Pt (II) diamino dinitrate (30 g/l), Pr (III) nitrate (50 g/l) and Pd (II) nitrate (20 g/l) acidified with nitric acid, with execution of a
5 15 minute thermal treatment at 460°C after each coat until obtaining the deposition of 2.80 g/m² of Pt, 1.84 g/m² of Pd and 4.70 g/m² of Pr (catalytic layer formation).

The sample was subjected to an operating test, displaying an ohmic-corrected initial average cathodic potential of -936 mV/NHE at 3 kA/m² under hydrogen evolution in 33%
10 NaOH, at a temperature of 90°C, corresponding to an average-to-good catalytic activity, lower than that of Counterexample 1 likely due to the absence of rhodium in the catalytic formulation.

The same sample was subsequently subjected to cyclic voltammetry in the range from -
15 1 to +0.5 V/NHE at a scan rate of 10 mV/s; the average cathodic potential variation after 25 cycles was 80 mV, corresponding to a poor tolerance to current reversal.

COUNTEREXAMPLE 3

20 A nickel 200 mesh of 100 mm x 100 mm x 0.89 mm size was subjected to a blasting treatment with corundum, then etched in 20% boiling HCl for 5 minutes. The mesh was then painted with 6 coats of an aqueous solution of Pt (II) diamino dinitrate (30 g/l), Pr (III) nitrate (28 g/l) and Pd (II) nitrate (20 g/l) acidified with nitric acid, with execution of a
25 15 minute thermal treatment at 480°C after each coat until obtaining the deposition of 2.36 g/m² of Pt, 1.57 g/m² of Pd and 2.20 g/m² of Pr (catalytic layer formation).

The sample was subjected to an operating test, displaying an ohmic-corrected initial average cathodic potential of -937 mV/NHE at 3 kA/m² under hydrogen evolution in 33%
30 NaOH, at a temperature of 90°C, corresponding to an average-to-good catalytic activity, as in Counterexample 2.

The same sample was subsequently subjected to cyclic voltammetry in the range from -
1 to +0.5 V/NHE at a scan rate of 10 mV/s; the average cathodic potential variation after

25 cycles was 34 mV, corresponding to a tolerance to current reversal better than in Counterexample 2 – most probably due to the different noble metal to rare earth ratio in the activation – but still unsatisfactory.

- 5 The previous description is not intended to limit the invention, which may be used according to different embodiments without departing from the scopes thereof, and whose extent is univocally defined by the appended claims.

10 Throughout the description and claims of the present application, the term "comprise" and variations thereof such as "comprising" and "comprises" are not intended to exclude the presence of other elements or additives.

15 The discussion of documents, acts, materials, devices, articles and the like is included in this specification solely for the purpose of providing a context for the present invention. It is not suggested or represented that any or all of these matters formed part of the prior art base or were common general knowledge in the field relevant to the present invention before the priority date of each claim of this application.

CLAIMS:

1. A cathode for electrolytic processes consisting of a metal substrate provided with a multilayer catalytic coating comprising at least one internal catalytic layer and one external catalytic layer, both the at least one internal catalytic layer and the external catalytic layer containing palladium, at least one rare earth and at least one noble component selected from the group consisting of platinum and ruthenium, wherein said external catalytic layer has a rare earth content of 10 to 45% by weight and said at least one internal catalytic layer has a rare earth content higher than that of said external catalytic layer.
2. The cathode according to claim 1 wherein said external catalytic layer has a rare earth content of 30 to 40% by weight and said at least one internal catalytic layer has a rare earth content of 45 to 55% by weight.
3. The cathode according to claim 1 or 2 wherein said at least one rare earth is praseodymium.
4. The cathode according to any one of claims 1 to 3 wherein said catalytic coating is rhodium-free.
5. The cathode according to any one of claims 1 to 4 wherein said catalytic coating contains silver.
6. The cathode according to claim 5 wherein the weight ratio of the sum of palladium and silver to said noble component is 0.5 to 2 referred to the elements.

7. A method for the manufacturing of a cathode according to any one of claims 1 to 4 comprising the multicoat thermal decomposition of a first precursor solution containing at least one salt of Pd, at least one salt of Pr and at least one salt of a noble metal selected between Pt and Ru, followed by the multicoat thermal decomposition of a second precursor solution containing at least one salt of Pd, at least one salt of Pr and at least one salt of a noble metal selected between Pt and Ru, wherein said second precursor solution has a percentage content of Pr with respect to the overall sum of metals lower than the percentage content of Pr in said first precursor solution.
8. The method according to claim 7 wherein said salts of Pd, Pr, Pt and Ru are nitrates and said thermal decomposition is carried out at a temperature of 430 to 500°C.
9. A cell for the electrolysis of an alkali chloride brine including at least one cathode according to any one of claims 1 to 6.