

(19) **DANMARK**

(10) **DK/EP 2176183 T3**



Patent- og
Varemærkestyrelsen

(12) **Oversættelse af
europæisk patentskrift**

-
- (51) Int.Cl.: **C 03 C 25/32 (2018.01)** **D 06 M 15/03 (2006.01)** **E 04 B 1/78 (2006.01)**
- (45) Oversættelsen bekendtgjort den: **2020-04-20**
- (80) Dato for Den Europæiske Patentmyndigheds bekendtgørelse om meddelelse af patentet: **2020-03-04**
- (86) Europæisk ansøgning nr.: **08786793.3**
- (86) Europæisk indleveringsdag: **2008-08-01**
- (87) Den europæiske ansøgnings publiceringsdag: **2010-04-21**
- (86) International ansøgning nr.: **EP2008060178**
- (87) Internationalt publikationsnr.: **WO2009019232**
- (30) Prioritet: **2007-08-03 GB 0715100** **2008-04-29 GB 0807777**
2008-06-06 GB 0810297
- (84) Designerede stater: **AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MT NL NO PL PT RO SE SI SK TR**
- (73) Patenthaver: **Knauf Insulation SPRL, Rue de Maestricht 95, 4600 Visé, Belgien**
- (72) Opfinder: **HAMPSON, Carl, Knauf Insulation, PO Box 10, Stafford Road, St Helens Merseyside WA10 3NS, Storbritannien**
MUELLER, Gert, Knauf INSulation, One Knauf Drive, Shelbyville, Indiana 46176, USA
APPLEY, Charles, Knauf Insulation, One Knauf Drive, Shelbyville, Indiana 46176, USA
- (74) Fuldmægtig i Danmark: **Plougmann Vingtoft A/S, Strandvejen 70, 2900 Hellerup, Danmark**
- (54) Benævnelse: **MINERALULDISOLERING**
- (56) Fremdragne publikationer:
EP-A- 0 044 614
EP-A- 1 698 598
WO-A-2007/024020
US-A- 5 977 232
US-A1- 2007 027 283

DESCRIPTION

[0001] This invention relates to the manufacture of mineral wool insulation, for example glass wool or stone wool insulation, and to mineral wool insulation products.

[0002] WO 2007/014236 and US 2007/027283 A1 disclose manufacture of mineral wool insulation products using binders which comprise Maillard reactants. One particular binder disclosed is based on a triammonium citrate - dextrose system derived from mixing dextrose monohydrate, anhydrous citric acid, water and aqueous ammonia. One of the many advantages of this binder system is that it is formaldehyde free. EP0044614A discloses glass fabrics given enhanced weld splash resistance. WO 2007/024020A discloses aqueous binder for inorganic fibers and thermal and/or acoustical insulation material using the same. US 5977232A discloses formaldehyde-free, accelerated cure, aqueous composition for bonding glass fiber heat-resistant nonwovens.

[0003] One aspect of the present invention provides a method of manufacturing a mineral fibre thermal insulation product in accordance with claim 1. The dependent claims define alternative and/or preferred embodiments.

[0004] Binder solutions used in accordance with the present invention may be "substantially formaldehyde free", that is to say that they liberate less than 5 ppm formaldehyde as a result of drying and/or curing (or appropriate tests simulating drying and/or curing). Such binder solutions are preferably "formaldehyde free", that is to say they liberate less than 1 ppm formaldehyde in such conditions.

Insulation materials in accordance with the invention which incorporate binders may be "substantially formaldehyde free", that is to say that they comprise less than 5 ppm or less than detectable limits of free formaldehyde and/or consist of materials which together comprise less than these amounts of free formaldehyde and/or release levels of formaldehyde in standardised tests adapted to simulate their ordinary use which allows them to be classified as having no or undetectable levels of formaldehyde release. Preferably, such products release less than $10\mu\text{g}/\text{m}^3$, more preferably less than $5\mu\text{g}/\text{m}^3$ of formaldehyde during the period of 24-48 hours from the start of testing in accordance with ISO 16000.

[0005] It has been found that insulation materials made according to the present invention may have at least equivalent and indeed improved properties compared to, for example, products made using the tri-ammonium citrate - dextrose system of WO 2007/014236. WO 2007/014236 teaches binder systems based, inter alia, on a combination of a carbohydrate (for example a reducing sugar), ammonia and a carboxylic acid and suggests that a Maillard type reaction may form the basis of the curing chemistry. It would have been thought that the nature of the acid used would have a significant effect upon the properties of the cured binder, particularly if the acid precursor and/or a derivative therefrom is incorporated into the structure of the cured binder. It is thus surprising that an acid precursor derivable from an inorganic salt should provide a suitable acid precursor in an otherwise apparently similar binder system.

[0006] Use of an acid precursor derivable from an inorganic salt may have significant advantages in terms of cost, availability and ease of handling. A particular advantage can be achieved by use of one or more inorganic ammonium salts, for example, an ammonium sulphate, an ammonium phosphate or an ammonium carbonate. An ammonium salt may provide the or part of the acid precursor and/or the or part of the source of nitrogen and/or the or part of a pH control system. An ammonium nitrate may also work; however, ammonium nitrate may oxidise aldehyde groups of the carbohydrate (for example in the case of dextrose) and/or require precautions to avoid explosions.

[0007] An ammonium sulphate is particularly advantageous but ammonium phosphate may be used in addition to or instead of this. Ammonium phosphate may be mono ammonium phosphate, di ammonium phosphate or tri ammonium phosphate; it may be an ammonium hydrogen phosphate. An ammonium carbonate, alone or in combination with the other materials disclosed herein, may also provide good results. The ammonium carbonate may be an ammonium bicarbonate.

[0008] The acid precursor, particularly when this consists essentially of inorganic ammonium salt(s), may make up

- at least 5%, preferably at least 7%, more preferably at least 9% by dry weight of the uncured binder solution; and/or
- less than 20%, preferably less than 18%, more preferably less than 16% by dry weight of the uncured binder solution.

[0009] The acid may comprise: a sulphuric acid, a phosphoric acid, a nitric acid or a weak acid.

[0010] The binder may comprise between 5%-25%, preferably 10% to 20 %, more preferably 15% to 20% by dry weight of acid precursor (particularly where this is an inorganic ammonium salt) to carbohydrate (particularly when this is a sugar).

[0011] Where the binder comprises both an acid precursor derivable from an inorganic salt and an organic acid with the carbohydrate (particularly where this is a sugar), these may be present in the following amounts by dry weight with respect to the carbohydrate:

	Preferred	More preferred	Most preferred
acid precursor derivable from an inorganic salt	At least 2.5%	At least 5%	
organic acid	At least 2.5%	At least 5%	
Combination of organic acid and acid precursor derivable from an inorganic salt	5-25%	10-20%	15-20%

[0012] Where an organic acid is used, this is preferably derived from an ammonium salt. For example, an ammonium citrate, particularly tri-ammonium citrate may be used as a source of citric acid.

[0013] Prior art phenol formaldehyde binder systems for mineral wool insulation have been used with the addition of about 2% by weight ammonium sulphate as a curing agent. However, the chemistry of such phenol formaldehyde binder systems is not comparable to the binder systems of the present invention which are not based on phenol and/or formaldehyde and/or on other phenolics.

[0014] A carbohydrate may be used in the binder solution rather than specifically a reducing sugar and may comprise a monosaccharide, for example in its aldose or ketose form. Preferably, the carbohydrate comprises a sugar, more preferably a reducing sugar or a reactant that yields a reducing sugar in situ under thermal curing condition; it may comprise glucose (ie dextrose). The carbohydrate may comprise a carbohydrate having a reducing aldehyde. It is believed that the use of a reducing sugar and particularly dextrose gives particularly good results for the manufacture of mineral wool insulation products. The dextrose need not be 100% pure but use of a material having a dextrose equivalent value of at least 0.85, preferably at least 0.9 and more preferably at least 0.95 is thought to be advantageous. The dextrose equivalent value DE can be thought of as i) a measure of de-polymerization and is roughly: $DE = 100/dp$ where dp stands for degree of polymerization or ii) the total amount of reducing sugars calculated as D-glucose (dextrose) on a dry basis.

[0015] Preferably, the binder solution and/or the binder is free or substantially free of starch; the presence of substantial quantities of starch is thought to increase the curing time and/or reduce the strength of the cured binder. The binder solution and/or the binder may be free or substantially free of proteins.

[0016] Industrial, non-food grade dextrose may be used as the reducing sugar; products such as Sirodex331 which is a 75% solids sugar solution obtainable from Tate and Lyle with a DE value of 94.5 may be used.

[0017] Particularly in the case where the reducing sugar consists essentially of dextrose and the acid precursor consists essentially of an ammonium salt, for example an ammonium sulphate, the ratio by dry weight of the amount of reducing sugar/ the amount of acid precursor may be greater than or equal to 2.5 and/or less than or equal to 13.

[0018] The source of nitrogen may be an amine or an amine reactant; it may be derivable from the same source as the acid precursor, for example, from an inorganic ammonium salt. It is preferably ammonia in solution.

[0019] Precursors for and/or reactants which give the materials referred to may be used.

[0020] In one embodiment, the binder is derived essentially from a reducing sugar and an inorganic ammonium salt in aqueous solution.

[0021] In another embodiment, the binder may also comprise an organic acid, particularly a carboxylic acid; this may be a polycarboxylic acid, particularly a bi-carboxylic acid or tri-carboxylic acid, preferably citric acid; it is preferably monomeric. The combination of an organic acid (or a precursor a salt or an anhydride thereof) with an acid precursor derivable from an inorganic salt may present various advantages. Firstly, such a combination may reduce the risk of punking (which has been observed with such binders based solely on organic acids) whilst providing acceptable strength. Punking is a term of art in the mineral fibre insulation area which generally denotes a comparatively rapid oxidation of a binder with a concomitant generation of heat in a finished and generally packaged insulation product. Punking generally causes generation of fumes and discolouring of the insulation material. It may be associated with exothermic reactions which increase the temperatures through the thickness of the insulation material; this may destroy the integrity of the insulation product and/or present a fire hazard. Alternatively or additionally, the combination of an organic acid (or a precursor, a salt or an anhydride thereof) with an acid precursor derivable from an inorganic salt may moderate acid conditions occurring during curing and thus reduce the risk or tendency of such conditions to cause significant damage to the material being bound. Such a combination may be particularly advantageous as a binder for stone wool insulation whose fibres may be more susceptible to potential damage by acid than, for example, glass wool insulation.

[0022] In a further embodiment, the binder is derived essentially from: a carbohydrate; an inorganic ammonium salt; and an organic acid and/or organic acid precursor; in aqueous solution.

[0023] The term "consist or consisting essentially of" is intended to limit the scope of a claim to the specified materials or steps and those that do not materially affect the basic and novel characteristic(s) of the claimed invention.

[0024] Binders which comprise or consist essentially of the components described herein may include additives, for example, additives selected from: silanes, mineral oils, coupling agents, silicones or siloxanes (particularly for water repellency), silicon containing compounds, surfactants, hydrophilic additives, hydrophobic additives, waxes, substances useful for controlling the pH (e.g. ammonium hydroxide) and ammonia. Ammonium hydroxide when used, and indeed other additives, may provide the and/or an additional source of nitrogen. Preferably, the total quantity of additives (excluding ammonia) is less than 5 % by weight (excluding the weight of water present), more preferably less than 3% or less than 2% by weight.

[0025] It is preferred to include a silane as an additive. The binder and/or binder solution may comprise at least 0.1 % and/or less than 1% of a silane by dry weight. The silane may be amino substituted; it may be a silyl ether and it is believed that its presence may significantly improve the long term strength of the binder, particularly after weathering.

[0026] Preferences for the pH of the binder are:

	Preferred	More preferred	Most preferred
pH of binder	≥ 7	≥ 8	≥ 9

at least in the state in which the binder is applied to a material to be bound and/or recovered in a waste water recuperation system. Such a neutral or alkaline pH of the binder may alleviate problems of corrosion of manufacturing equipment which have been encountered with some essentially acidic prior art binder systems. Such prior art binders include binders consisting essentially of polyacrylic acids or polymer polycarboxylic acids. One particular advantage of the present invention is thus the use of a binder system that can operate in such neutral or alkaline conditions. When cured, the binder may become acidic during the curing process. However, equipment corrosion considerations are less significant in this case due to the minimal contact between the manufacturing equipment and the binder when in this state. The pH of the binder may be less than or equal to 13, preferably less than or equal to 12, 11 or 10. A preferred pH may be in the range of 7.5 to 9.5, particularly 8 to 9.

[0027] It is preferred to arrange the pH of the binder solution at an appropriate level to prevent precipitation of its constituents and particularly to ensure that the acid precursor derivable from an inorganic salt remains in solution. This is particularly the case where ammonium phosphate provides the acid precursor. Better dry and/or weathered strengths and/or more homogeneous products may be achieved by using homogeneous binder solutions comprising ammonium salt acid precursors which are free from precipitates, particularly when ammonium phosphate is used and the binder solution is free from phosphate precipitates.

[0028] The binder composition may be provided in the form of an aqueous solution; it may contain free ammonia or excess ammonia in solution. A neutral or alkaline pH of the binder may be generated by an excess of alkaline groups compared with acid groups present in the binder solution, for example, due partially or substantially to the presence of ammonia in the solution. Additional ammonia may be added to the binder solution, for example 0.2% - 1% by weight, or indeed more; this may help to keep a wash water system used in the manufacture of mineral wool insulation alkaline over the long term.

[0029] When binder solution is sprayed on to hot mineral wool fibres just after they have been formed, the residual heat of the mineral wool fibres may cause a significant portion of any water in the binder solution to evaporate. Consequently, the mineral wool fibres which are then collected to form a batt may have binder present on them in the form of a sticky, viscous or tacky liquid. This may facilitate bonding between individual fibres via the binder.

[0030] One of the many advantages of this binder system is that it is sprayed onto the mineral wool fibers in a substantially unreacted state. The ability to spray the binder solution onto the mineral wool fibers in a substantially unreacted state may alleviate problems associated with pre-reacting the binder components in solution which have been encountered with some prior art binder systems in which the components are pre-reacted. Such prior art binders include binders consisting essentially of pre-reacted polymers or resins which are applied to the

materials to be bound. With substantially unreacted binder present on the mineral wool fibers in the form of a sticky, viscous or tacky liquid, the reaction between the binder components may occur in a substantially dry state. One may describe the reaction as a bulk polymerization because it is occurring without the benefit of a solvent. A particular advantage of the present invention is thus the use of a binder system that can polymerise in a substantially dry state or through a bulk polymerisation.

[0031] The mineral fibres may be formed by internal or external spinning. They may have a temperature in the range 20 °C to 200 °C, generally 30 °C to 100 °C or 150 °C, when sprayed with the binder solution. The quantity of binder solution sprayed may be used with or without additional water sprays to assist in cooling the mineral fibres to a desired temperature between their formation and their collection to form a batt.

A particular advantage of using ammonia in solution to control the pH of the binder solution applied to the mineral fibres is that at least part of the ammonia of binder solution that sticks to the fibres may flash off due to the residual heat of the mineral wool fibres. Consequently, the binder solution that coats the fibres may have a lower pH than the binder solution sprayed.

[0032] The binder may be curable; it may be cured, for example in a curing oven; it may form a thermoset binder. In its cured form, the binder may: comprise melanoidins; and/or be thermoset; and/or be water insoluble or substantially water insoluble. The binder solution may be substantially colourless or white to off-white; upon curing, the binder may take on a dark colour, particularly a dark brown colour. The cured product may be dark in colour, particularly dark brown in colour. The binder may be free of proteins; it may be free of cellulosic feedstock. One of the many advantages of this binder system is that the extent of curing can be determined by the colour. Substantially dehydrated binder appears white or off-white. Progressively cured to a greater extent, the binder appears progressively darker in colour (a darker shade of brown). When applied to mineral fibers, the extent to which the mineral wool insulation has cured can be determined by its colour.

[0033] When applied to the mineral fibres and/or prior to passing through the curing oven, the binder may be free or substantially free of melanoidins and/or other reaction products derived from curing. Curing of the binder may produce glucosylamine, particularly as an intermediate product. Consequently, a cured or particularly a partially cured product may comprise glucosylamine.

[0034] The reaction of the binder upon curing may be essentially a Maillard type reaction as described for example in US Patent Application 20070027283 or WO2007/14236. The binder may comprise polymerisation products of a mixture that comprises a reducing sugar and a material selected from the group consisting of ammonium sulphate, ammonium phosphate, ammonium nitrate and ammonium carbonate.

[0035] The binder solution may be formulated by combining:

- A carbohydrate, preferably a reducing sugar;

- An acid precursor derivable from an inorganic salt, preferably an ammonium sulphate or ammonium phosphate;
- A source of nitrogen; and
- water.

The formulation may comprise optional or additional ammonia provided in the form of an aqueous ammonia solution. The water may comprise wash water.

[0036] Forming the binder solution from a carbohydrate and an acid precursor comprising an inorganic ammonium salt provides one particular advantageous preparation method. This may be achieved in a simple mixing chamber which may be open and/or at atmospheric pressure. The carbohydrate and/or the acid precursor may be added in powder or liquid form. The preparation is preferably carried out at room temperature. Preferably it is not necessary to supply heat to prepare the binder solution; nevertheless, the binder solution may be heated during its preparation, for example to a temperature with the range 20°C to 80°C, particularly where this facilitates dissolving and/or mixing of its ingredients.

[0037] The binder solution may comprise:

- at least 5% 10%, 15% or 18% solids and/or
- less than 50%, 40% or 20% solids

particularly determined as bake out solids by weight after drying at 140 °C for 2 hours.

[0038] The binder solution and/or the binder are preferably organic.

The mineral fibre insulation may be shaped and/or dimensioned and/or moulded with the aid of the binder.

The binder solution, particularly when applied to the mineral fibres, may have a viscosity appropriate for application by spraying or pouring. Its viscosity at 20°C may be:

- Less than about 1.5 Pa.s, preferably less than about 1×10^{-2} Pa.s; and/or
- Greater than about 2×10^{-4} Pa.s, preferably greater than about 5×10^{-4} Pa.s

[0039] Curing of the binder may occur in a curing oven, for example using forced hot air circulation; it may occur in a press. Curing may comprise a dehydration of the binder; it may comprise a polymerisation. Curing may comprise a bulk polymerisation reaction. Curing may be carried out for duration of 20 minutes or less, preferably 10 minutes or less. Curing of the binder preferably occurs when the binder solution (from which water may have been evaporated) is in contact with the mineral fibres; it may occur at substantially atmospheric pressure. The curing may be a substantially dry curing, that is to say by application of dry heat and/or substantially dry or heated atmospheric air rather than using steam or heated water vapour.

[0040] The curing temperature and time may be selected as a function of the product density and/or thickness. The curing oven in such cases may have a plurality of heating zones having temperatures within the range 200 °C to 350 °C (typically 230°C to 300 °C). A thin, low density product (12 kg/m³ or less) may be cured by passing through the curing oven in as little as 20 seconds; a thick, high density product (80 kg/m³ or more) may require a passage of 15 minutes or more in the curing oven. The product may reach a temperature in the range 180 °C - 220 °C during the curing process.

[0041] The cured binder may comprise greater than 2% and/or less than 8% nitrogen by mass as determined by elemental analysis.

[0042] The binder in its uncured state may comprise the following levels of sulphates, phosphates carbonates and/or nitrates by dry weight:

- Greater than 2.5%, 3% or 5%; and/or
- Less than 25%, 22%, or 20%

[0043] Finished materials manufactured using binder systems according to the present invention may have residual levels of sulphates, phosphates, carbonates and/or nitrates derived notably from the inorganic salt serving as the acid precursor. Such species may be present in the following quantities:

- Greater than 500, 750, 1000 or 1500 mg/kg ; and/or
- Less than 5000, 4000 or 3000 mg/kg .

[0044] The presence of such species may be assessed in a leach test and provide an indication in the final product of the binder system used.

[0045] The quantity of binder in the finished product may be:

- Greater than: 1%, 2%, 2.5%, 3%, 3.5% or 4%; and/or
- Less than: 20%, 15%, 10 % or 8%

measured by dry weight of the finished product.

[0046] The mineral wool insulation may have one or more of the following parting strengths:

Ordinary Parting Strength of

- At least 120 g/g, preferably at least 150 g/g; and/or
- Less than 400 g/g

Weathered Parting Strength of

- At least 120 g/g, preferably at least 150 g/g; and/or
- Less than 400 g/g

% loss between Ordinary and Weathered Parting Strength of

- Less than 10%, preferably less than 5%

[0047] The mineral wool insulation may have one or more of the following characteristics:

- A density greater than 5, 8 or 10 kg/m³;
- A density less than 200, 180 or 150 kg/m³
- Comprise glass wool fibres and have a density greater than 5, 8 or 10 kg/m³ and/or less than 80, 60 or 50 kg/m³;
- Comprise stone wool fibres and have a density greater than 15, 20 or 25 kg/m³ and/or less than 220, 200 or 180 kg/m³;
- A thermal conductivity λ of less than 0.05 W/mK and/or greater than 0.02 W/mK
- Comprise less than 99% by weight and/or more than 80% by weight mineral fibres.
- A thickness of greater than 10 mm, 15mm or 20 mm and/or less than 400mm, 350 mm or 300 mm.

[0048] Embodiments of the invention will now be described by way of example with reference to Fig 1 which is a plan view of a test sample.

Shell bone testing:

[0049] Binders were prepared as aqueous solutions by

- combining the ingredients of a desired binder formulation in an open, unheated reaction vessel
- adding distilled water
- subsequently adding a silane solution
- agitating during addition of liquids and afterwards for several minutes to achieve complete dissolution of solids

such that the binder solution contained approximately 45% dissolved solids as a percentage of total weight of solution. A 2-g sample of this solution, upon thermal curing at about 200 °C to 210 °C for 8 minutes, would yield 30% solids (the weight loss being attributed to dehydration during thermoset binder formation).

[0050] An evaluation of dry and "weathered" tensile strength of glass bead-containing shell bones provided an indication of the likely tensile strength and the likely durability of fibreglass insulation or other materials prepared with that particular binder. Predicted durability is based on the ratio of a shell bone's weathered tensile strength to its dry tensile strength.

[0051] To prepare the shell bones, an electric mixer was used for about two minutes to mix approximately 75 g of binder with 727.5g of glass beads (equivalent to Quality Ballotini Impact Beads, Spec. AD, US Sieve 70-140, 106-212 micron-#7, from Potters Industries, Inc.). Any clumps from the sides of the mixer whisk and from the sides and bottom of the mixing bowl were mixed in manually using a spatula about half way through the mixing and also at the end of the mixing.

[0052] The prepared glass beads/binder mixture was added to the mould cavities of a shell bone mould (Dietert Foundry Testing Equipment; Heated Shell Curing Accessory, Model 366) which had been pre-heated to about 218 °C (425°F). The surface of the mixture in each cavity was flattened out, while scraping off the excess mixture to give a uniform surface area to the shell bone. Any inconsistencies or gaps that existed in any of the cavities were filled in with additional glass beads/binder mixture and then flattened out. The top platen was quickly placed onto the bottom platen (to avoid producing shell bones with two differentially cured layers). The cured shell bones were removed after seven minutes, cooled to room temperature on a wire rack, labelled and placed individually in plastic storage bags. If shell bones could not be tested on the day they were prepared, the shell bone-containing plastic bags were placed in a dessiccator unit. During curing the temperature of the bottom platen ranged from about 204 °C to about 221 °C (about 400°F to about 430°F), while the temperature of the top platen ranged from about 227 °C to about 243 °C (about 440°F to about 470 °F).

[0053] Procedure for testing breaking strength:

- Equipment: 5500 R Instron machine
- Immediately prior to testing, each shell bone was removed from its plastic bag and its weight and thickness recorded.

[0054] Weathering Procedure for Shell Bones:

- 16 hours weathering in a pre-heated humidity chamber (65 °C , 95% relative humidity)
- upon removal shell bones were sealed in individual plastic storage bags and taken immediately for testing.

Procedure for measuring gel time:

[0055] A small amount of binder (2.0ml) is added to the centre of a hot plate set to 150°C and a stop watch is started .The binder is worked with a spatula until it is possible to draw the sample into a long string. The time taken from the addition of the binder to the string formation is the gel time.

[0056] Binder formulations tested - inorganic acid precursors compared with citric acid:

Test ref:	Binder formulation (by dry weight)
A	85% DMH + 15% CA + 4.8% NH ₄ OH + 0.3% ISIO200
B	90% DMH + 10% AmSO ₄ + 4.8% NH ₄ OH + 0.3% ISIO200
C	85% DMH + 15% AmSO ₄ + 4.8% NH ₄ OH + 0.3% ISIO200
D	80% DMH + 20% AmSO ₄ + 4.8% NH ₄ OH + 0.3% ISIO200
E	90% DMH + 10% AmPO ₄ + 4.8% NH ₄ OH + 0.3% ISIO200
F	85% DMH + 15% AmPO ₄ + 4.8% NH ₄ OH + 0.3% ISIO200
G	80% DMH + 20% AmPO ₄ + 4.8% NH ₄ OH + 0.3% ISIO200

[0057] Binder formulations tested - combined inorganic acid precursor and citric acid compared with citric acid alone and inorganic acid precursor alone:

Test ref:	Binder formulation (by dry weight)
H	85% DMH + 15% CA + 4.8% NH ₄ OH + 0.3% ISIO200
I	85% DMH + 10% CA + 5% AmSO ₄ + 4.8% NH ₄ OH + 0.3% ISIO200
J	85% DMH + 5% CA + 10% AmSO ₄ + 4.8% NH ₄ OH + 0.3% ISIO200
K	85% DMH + 15% AmSO ₄ + 4.8% NH ₄ OH + 0.3% ISIO200

Key:

[0058]

DMH=Dextrose monohydrate

CA= citric acid

NH₄OH= ammonium hydroxide

ISIO200= silane

AmSO₄= ammonium sulphate

AmPO₄= ammonium phosphate

[0059] Test results - inorganic acid precursors compared with citric acid:

Test ref	Dry breaking strength (MN/m ²)	Weathered breaking strength (MN/m ²)	Loss in breaking strength from weathering/ %	Gel time of binder solution (s)	pH of binder solution just before mixing with beads
A	1,455	1,567	-7,70	343	9,54
B	1,271	0,895	29,57	280	10,28
C	1,550	0,856	44,79	362	10,24
D	1,877	1,156	38,39	327	10,13
E	1,499	1,069	28,68	356	10,18
F	1,281	0,848	33,82	334	9,99
G	1,123	0,801	28,74	287	9,73

[0060] Test results - combined inorganic acid precursor and citric acid compared with citric acid alone and inorganic acid precursor alone:

Test ref	Dry breaking strength (MN/m ²)	Weathered breaking strength (MN/m ²)	Loss in breaking strength from weathering/ %	Gel time of binder solution (s)	pH of binder solution just before mixing with beads
H	1.69	1.50	11.32	363	9.39
I	1.50	1.18	21.37	341	9.71
J	1.21	1.05	13.19	375	9.99
K	1.47	1.02	30.33	376	9.97

[0061] Results from tests carried out together (test A to G were carried out in one session and tests H to K carried out during another session) provide a useful indication of results relative to other results obtained during the same test session. It may not be reliable to compare tests results from different test sessions.

First Comparative testing on insulation product:

[0062] Comparative testing of binder systems on a mineral fibre insulation product gave the following results:

Binder tested	Description	Formulation
PF1	Comparative example - standard phenol formaldehyde binder	Resin, Urea, Lignin, Ammonia, Silane

Binder tested	Description	Formulation
AC1	Comparative example - ammonium citrate based binder	Dextrose 85% Citric Acid 15% Ammonia 4.8% Silane 0.3%
Ex1	Example 1 of the present invention	Dextrose 85% Ammonium Sulphate 15% Ammonia 4.8% Silane 0.3%
Product used for test:	glass wool fibre insulation product, nominal density 16 kg/m ³ , nominal thickness 75mm, nominal width 455mm	

[0063] Binder content of test product LOI (Loss on ignition) %weight:

Binder	Mean LOI
PF1	6,22%
AC1	6,91%
Ex1	6,78%

[0064] Drape test (mean average in mm measured after the periods specified):

Binder	Day 1	Week 1	Week 3	Week 6
PF1	55	68	60	71
AC1	83	99	80	72
Ex1	66	76	66	75

[0065] Thickness (mean average in mm measured after the periods specified in accordance with British Standard BS EN 823:1995)

Binder	Day 1	Week 1	Week 3	Week 6
PF1	76,4	75,1	75,1	75,2
AC1	75,3	73,6	72,5	74
Ex1	76	76,7	74,9	74,3

[0066] Density (mean average in kg/m³ measured after the periods specified)

Binder	Day 1	Week 1	Week 3	Week 6
PF1	16,44	16,7	16,35	16,44
AC1	16,68	16,41	16,33	16,48
Ex1	16,5	16,9	16,5	16,5

[0067] Quantity of sulphates present mg/kg

Binder	Sample 1	Sample 2
AC1	240	240
Ex1	2000	2200

[0068] Parting strength (g/g)

Binder	Ordinary	Weathered	%loss
PF1	248	107	56.85
AC1	230	199	13.47
Ex1	196	189	3.57

Test procedures:**Binder content LOI (Loss on ignition)**

[0069] A weighed sample of wool plus binder is placed in a muffle furnace set to 550°C. After a set time the wool is removed from the furnace, placed in a desiccator to cool and re-weighed. The weight loss is expressed as a percentage of the original sample weight and is known as the binder content or Loss On Ignition (LOI).

Drape test

[0070] A single batt (or slab) is placed across two poles (each 500mm long, 20mm diameter) set into a wall 1 metre apart. The degree of sag in the centre of the batt is recorded. This is repeated for all of the batts in a pack and for several packs. Packs are measured at set points over a period of time to determine the long term effects of compression on the batts.

Density: measured for the samples subjected to the drape test

Quantity of sulphates present: leaching test for granular wastes in water with eluate analysis according to British standard BS EN 12457-2 at L/S10

Parting Strength

[0071] The parting strength is expressed in grams/gram being the total breaking load of six test specimens divided by their total weight.

[0072] The test is carried out on mineral fibre mats as received for testing (Ordinary Parting Strength) and after an accelerated weathering test as explained below (Weathered Parting Strength).

[0073] A first set of six samples of the form and dimensions shown in Fig 1 are cut from the mineral fibre mat to be tested. The dimensions are:

r: radius 12.7mm;

DC: distance between centres 44.5mm;

a: 25.4 mm;

b: 121 mm.

[0074] The long axis of the samples should be parallel to the conveyor direction and the samples should be taken across the full width of the mineral mat. A second set of six samples is then taken in the same way.

[0075] The total weight of the first group of six samples W1 in grams is recorded.

[0076] The total weight of the second group of six samples W2 in grams is recorded; these samples are then placed in a preheated autoclave and conditioned on a wire mesh shelf away from the bottom of the chamber under wet steam at 35kN/m² for one hour. They are then removed, dried in an oven at 100°C for five minutes and tested immediately for parting strength.

[0077] To test the parting strength, each sample is mounted in turn on the jaws of a 5500 Instron tensile strength machine and the maximum breaking load in grams or Newtons is recorded. If the breaking load is measured in Newtons it is converted to grams by multiplying it by 101.9. Six results in grams are obtained for each set of samples: G1 G2 G3 G4 G5 and G6 for the first set of samples and G7 G8 G9 G10 G11 and G12 for the second set of samples.

[0078] The Ordinary Parting Strength is calculated from the first set of samples using the formula Ordinary Parting Strength = (G1+G2+G3+G4+G5+G6)/W1.

[0079] The Weathered Parting Strength is calculated from the second set of samples using the formula Weathered Parting Strength = (G7+G8+G9+G10+G11+G12)/W2.

[0080] Second comparative testing on insulation product:

Product used for test:	glass wool fibre insulation product, nominal density 7.2 kg/m ³ , nominal thickness 159 mm
------------------------	---

[0081] SAMPLES: The following samples of fibreglass batts were tested:

Example	Binder Description	Target binder content (LOI) for product
PF2	standard phenol formaldehyde binder of Resin, Urea, Ammonia, Silane	4.5%
2.1	Dextrose 85% Ammonium Sulphate 15% Silane 0.3% (10.6% solids in binder solution)	4.5%
2.2	Dextrose 85% Ammonium Sulphate 15% Silane 0.3% Norjohn oil (11.4% solids in binder solution)	4.5%
2.3	Dextrose 85% Ammonium Sulphate 15% Silane 0.3%, 2.4%NH ₃ (10.6% solids in binder solution)	4.5%
2.4	Dextrose 85% Ammonium Sulphate 15% Silane 0.3% , 2.4%NH ₃ (10.6% solids in binder solution)	6.0%

Results

[0082]

	PF2	2.1	2.2	2.3	2.4
Recovery	158mm	157 mm	163 mm	160 mm	166 mm
Recovery. % nominal	99.4 %	99.0 %	102.8 %	100.6 %	104.8 %
Parting Strength (ASTM C-686)	190.8 g/g	131.7 g/g	146.7 g/g	159.9 g/g	143.9 g/g
Parting strength after weathering (ASTM C-686 following conditioning for 7 days at 90 °F, 90% relative humidity)	145.9 g/g	100.0 g/g	110.3 g/g	124.9 g/g	114.3 g/g

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all

liability in this regard.

Patent documents cited in the description

- WO2007014236A [0002] [0005] [0005]
- US2007027283A1 [0002]
- EP0044614A [0002]
- WO2007024020A [0002]
- US5977232A [0002]
- US20070027283A [0034]
- WO200714236A [0034]

Patentkrav

1. Fremgangsmåde til fremstilling af et mineralfiber-varmeisoleringsprodukt omfattende de fortløbende trin:

- at danne mineralfibre fra en smeltet mineralblanding;
- 5 • at sprøjte en i alt væsentligt formaldehydfri bindemiddelopløsning på mineralfibrene, hvilken bindemiddelopløsning omfatter: et reducerende sukker, en syre-prækursor der kan afledes fra et uorganisk salt og en nitrogenkilde; i hvilken syre-prækursoren af bindemiddelopløsningen der kan afledes fra et uorganisk salt omfatter et ammoniumsalt; og i hvilken
- 10 det uorganiske ammoniumsalt udgør mellem 5 % og 25 % tørvægt af bindemiddelopløsningen;
- at indsamle mineralfibre til hvilke bindemiddelopløsningen er blevet påført for at danne en måtte af mineralfibre; og
- at hærde måtten omfattende mineralfibre og bindemidlet ved at
- 15 passere måtten igennem en hærkningsovn for således at tilvejebringe en måtte af mineralfibre holdt sammen af et i alt væsentligt vandopløseligt, hærdet bindemiddel.

2. Fremgangsmåde til fremstilling af et mineralfiber-varmeisoleringsprodukt ifølge krav 1, i hvilken vaskevand sprøjtes på mineralfibrene mellem deres dannelse og deres indsamling for at danne en måtte, hvor mindst en del af vaskevandet er blevet sprøjtet på mineralfibre og efterfølgende returneret til et vaskevandssystem for at blive genanvendt som vaskevand.

25 **3.** Fremgangsmåde til fremstilling af et mineralfiber-varmeisoleringsprodukt ifølge krav 1, i hvilken bindemiddelopløsningen sprøjtes på mineralfibrene når mineralfibrene er ved en temperatur på mellem 30 °C og 150 °C.

30 **4.** Fremgangsmåde til fremstilling af et mineralfiber-varmeisoleringsprodukt ifølge et hvilket som helst foregående krav, i hvilken hærkning af bindemidlet udføres ved at passere måtten igennem mindst en zone af en hærkningsovn ved en

temperatur indenfor området 230 °C - 300 °C med en ovn-opholdstid i området 30 sekunder til 20 minutter.

5. Fremgangsmåde til fremstilling af et mineralfiber-varmeisoleringsprodukt ifølge et hvilket som helst foregående krav, i hvilken bindemiddelopløsningen har en pH større end 7 når sprøjtet på mineralfibrene.

6. Fremgangsmåde til fremstilling af et mineralfiber-varmeisoleringsprodukt ifølge et hvilket som helst foregående krav, i hvilken fremgangsmåden omfatter mindst 10 en af de følgende egenskaber:

6.1 i hvilken syre-prækursoren der kan afledes fra et uorganisk salt af bindemiddelopløsningen omfatter en species valgt fra gruppen bestående af sulfater, fosfater, nitrater og karbonater.

6.2 i hvilken det reducerende sukker af bindemiddelopløsningen har en dextrose ækvivalent værdi på mindst 0,85.

6.3 i hvilken det reducerende sukker af bindemiddelopløsningen består i alt væsentligt af dextrose.

7. Fremgangsmåde til fremstilling af et mineralfiber-varmeisoleringsprodukt ifølge et hvilket som helst foregående krav, i hvilken bindemiddelopløsningen er valgt fra:

a) en bindemiddelopløsning, som omfatter en silicium-indeholdende forbindelse; og

b) en bindemiddelopløsning, som omfatter mellem 0,1 % og 1 % af et silan eller silicium-indeholdende koblingsmiddel beregnet som opløste bindemiddelfaststoffer.

8. Fremgangsmåde til fremstilling af et mineralfiber-varmeisoleringsprodukt ifølge et hvilket som helst foregående krav, i hvilken bindemiddelopløsningen omfatter et materiale valgt fra listen bestående af en polycarboxylsyre, et salt af en polycarboxylsyre, et anhydrid af en polycarboxylsyre.

9. Fremgangsmåde til fremstilling af et mineralfiber-varmeisoleringsprodukt ifølge et hvilket som helst af kravene 1 til 8, i hvilken bindemiddelopløsningen er valgt fra:

5 a) en bindemiddelopløsning, som består i alt væsentligt af en vandig opløsning af: et reducerende sukker; mindst én syre-prækursor der kan afledes fra et ammoniumsalt valgt fra listen bestående af ammoniumsulfatsalte, ammoniumfosfatsalte, og ammoniumkarbonatsalte; og, eventuelt, overskydende ammoniak;

10 b) en bindemiddelopløsning, som består i alt væsentligt af en vandig opløsning af: et reducerende sukker; mindst én syre-prækursor der kan afledes fra et ammoniumsalt valgt fra listen bestående af ammoniumsulfatsalte og ammoniumfosfatsalte; og, eventuelt, overskydende ammoniak, hvor bindemiddelopløsningen har en pH, der, i sine anvendelsesbetingelser, forhindrer bundfældning af sulfater eller
15 fosfater; og

c) en bindemiddelopløsning, som består i alt væsentligt af en vandig opløsning af: et reducerende sukker; en syre-prækursor der kan afledes fra et ammoniumsalt; en carboxylsyre eller en prækursor deraf; og, eventuelt, overskydende ammoniak.

20

10. Fremgangsmåde til fremstilling af et mineralfiber-varmeisoleringsprodukt ifølge et hvilket som helst foregående krav, i hvilken bindemiddelopløsningen når sprøjtet på mineralfibrene omfatter mindst 5 % faststoffer.

25 **11.** Fremgangsmåde til fremstilling af et mineralfiber-varmeisoleringsprodukt ifølge et hvilket som helst foregående krav, i hvilken bindemiddelopløsningen når sprøjtet på mineralfibrene omfatter mindre end 50 % faststoffer.

12. Fremgangsmåde til fremstilling af et mineralfiber-varmeisoleringsprodukt
30 ifølge et hvilket som helst foregående krav, i hvilken forholdet af tørvægt af reducerende sukker til uorganisk syre-prækursor udtrykt som (tørvægt af reducerende sukker / tørvægt af uorganisk syre-prækursor) er i området 2,5 til 13.

- 13.** Fremgangsmåde til fremstilling af et mineralfiber-varmeisoleringsprodukt ifølge et hvilket som helst foregående krav, i hvilken varmeisoleringsproduktet har en varmeledningsevne λ i området 0,02 W/mK til 0,05 W/mK.
- 5 **14.** Fremgangsmåde til fremstilling af et mineralfiber-varmeisoleringsprodukt ifølge et hvilket som helst foregående krav, i hvilken varmeisoleringsproduktet omfatter glasuldsfibre og har en densitet i området fra 8 til 50 kg/m³.
- 15.** Fremgangsmåde til fremstilling af et mineralfiber-varmeisoleringsprodukt
10 ifølge et hvilket som helst af kravene 1 til 13, i hvilken varmeisoleringsproduktet omfatter stenuldsfibre og har en densitet i området fra 25 til 180 kg/m³.

DRAWINGS

Fig 1

