



- (51) **International Patent Classification:**
C07C 319/14 (2006.01) C07C 323/52 (2006.01)
- (21) **International Application Number:**
PCT/EP2016/059661
- (22) **International Filing Date:**
29 April 2016 (29.04.2016)
- (25) **Filing Language:** English
- (26) **Publication Language:** English
- (30) **Priority Data:**
PA 2015 00265 30 April 2015 (30.04.2015) DK
- (71) **Applicant:** HALDOR TOPSØE A/S [DK/DK]; Haldor Topsøes Allé 1, 2800 Kgs. Lyngby (DK).
- (72) **Inventors:** SADABA ZUBIRI, Irantzu; Dirch Passers Allé 11, 4th, 2000 Frederiksberg (DK). TAARNING, Esben; Smallegade 24, 3th, 2000 Frederiksberg (DK). TZOULAKI, Despina; Romsøgade 8, 2100 Copenhagen (DK).
- (74) **Agent:** HALDOR TOPSØE A/S; Haldor Topsøes Allé 1, 2800 Kgs. Lyngby (DK).
- (81) **Designated States** (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY,

BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

- (84) **Designated States** (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:


- as to the identity of the inventor (Rule 4.17(i))
- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii))
- of inventorship (Rule 4.17(iv))

Published:

- with international search report (Art. 21(3))

(54) **Title:** A PROCESS FOR THE PREPARATION OF METHIONINE ALPHA-HYDROXY ANALOGUES FROM SUGARS AND DERIVATIVES THEREOF

Fig. 1



(57) **Abstract:** A process for the preparation of methionine α -hydroxy analogue and derivatives thereof comprising contacting one or more sugars or derivatives thereof with a metallo-silicate composition in the presence of a compound comprising sulphur and a solvent.

**Title: A process for the Preparation of methionine
alpha-hydroxy analogues from sugars and derivatives thereof.**

Description:

5

A process for the preparation of methionine α -hydroxy analogue and derivatives thereof from sugars in the presence of zeotype compounds.

10 Background:

Carbohydrates represent the largest fraction of biomass and various strategies for their efficient use as a feedstock for the preparation of commercial chemicals are being established. Biomass is of particular interest due to its potential for supplementing, and ultimately replacing, petroleum as a feedstock for such purposes. Carbohydrates obtainable from biomass comprise C2 to C6 sugars and are of particular interest industrially as they are a potential source of highly functionalised short chain carbon compounds.

This invention is directed towards the preparation of methionine α -hydroxy analogue and derivatives thereof from sugars in the presence of zeotype compounds. Methionine α -hydroxy analogue is 2-hydroxy-4-(methylthio) butanoic acid. Methionine α -hydroxy analogue and derivatives thereof may be used as a food/nutritional supplement in animal feed compositions/formulations.

30 It is known that C2-C6 sugars may be converted to methyl lactate and methyl vinylglycolate (MVG) in the presence of zeotype materials such as Sn-BEA. EP 2 184 270 B1 and Science (2010) 328, pp 602 - 605 report average yields of methyl lac-

tate of 64%, 43% and 44% at 160 °C, in the presence of Sn-BEA and methanol from sucrose, glucose and fructose, respectively. Methyl vinylglycolate (MVG) is the major by-product with a reported yield of 3-11%. MVG may be produced in yields of up to 56% from the C4 sugar D-erythrose.

WO 98/32735 discloses a process for the preparation of methionine α -hydroxy analogue methyl ester, 2-hydroxy-4-(methylthio) butanoic acid methyl ester, , in an 85% yield via a free radical addition of methylthiol to a non-conjugated olefinic substrate, i.e. methyl vinylglycolate (MVG). Although high yielding, radical reactions have the potential to form region-isomeric by-products.

WO 98/32735 also discloses an alternative, multi-step, commercially feasible process for preparing methionine α -hydroxy analogue, 2-hydroxy-4-(methylthio)butanoic acid. The process comprises a Michael addition of methyl mercaptan to acrolein (a conjugated olefinic substrate) in the presence of an organic amine catalyst to produce 3-(methylthio)propanal, followed by nitrile addition and hydrolysis to the acid. Although the process is industrially feasible, the use of toxic and expensive reagents such as HCN and acrolein should be avoided.


ChemCatChem (2013) 5, pp 569-575 discloses the conversion of tetroses (C4 sugars) to MVG and MMHB under homogenous catalytic conditions. MMHB is selectively produced from erythrose (C4 sugar) in the presence of a homogenous tin chloride catalyst.

Accordingly, it is desirable to provide an alternative process for the preparation of methionine α -hydroxy analogue and derivatives thereof. In particular, it is desirable to provide a process that is industrially feasible, it is therefore desirable that the process is high yielding, direct and selective. It is desirable that the process is carried out under conditions that are industrially feasible, with reagents or catalysts that enable ease of production and reduced toxic waste, such as the use of heterogeneous catalysts that may be regenerated. Additionally, the provision of a process wherein the substrates are derived from renewable sources such as C2-C6 sugars, is desirable. In particular because the sugar substrates are much less toxic and much cheaper than, for example acrolein and the HCN reagent, consequently the use of sugar substrates significantly lowers the costs of production.

Disclosure of the Invention


It has surprisingly been found that a methionine α -hydroxy analogue and derivatives thereof is obtainable by contacting one or more sugars with a metallo-silicate composition in the presence of a compound comprising sulphur and a solvent.

The methionine α -hydroxy analogue and derivatives thereof may be represented by the formula



wherein R is selected from the group consisting of H, C₁-C₈ alkyl or alkaline or alkaline-earth metals; and R' is selected from the group consisting of H and methyl.

The methionine α -hydroxy analogue and derivatives thereof may alternatively be represented as follows:



5 It has surprisingly been found that a high yield of the methionine α -hydroxy analogue and derivatives thereof is obtainable according to the process of the present invention.

10 The compound comprising sulphur is preferably a compound of the formula RSR' , wherein R and R' are selected from the group consisting of H, C₁-C₅ alkyl or alkaline or alkaline-earth metals. The compound comprising sulphur is preferably selected from the group consisting of C₁-C₅ alkyl thiol, C₁-C₅ alkyl thiol salts, dimethylmercaptan, dimethyl disulphide and
15 hydrogen sulphide. C₁-C₅ alkyl thiol is in the present context meant to refer to mono- and di-substituted thiols with a substituent comprising a straight or branched chain saturated aliphatic alkyl group comprising one, two, three, four or five carbons. C₁-C₅ alkyl thiol is in the present context
20 meant to refer to an alkyl thiol selected from the group consisting of methane thiol, ethane thiol, straight or branched chain propane thiol, straight or branched chain butane thiol and straight or branched chain pentane thiol.

25 C₁-C₅ alkyl thiol salt is in the present context meant to refer to the alkali or alkaline earth metal salt of a C₁-C₅ alkyl thiol. Specifically, C₁-C₅ alkyl thiol salt is in the present context meant to refer to a C₁-C₅ alkyl thiol in the salt form wherein the cation is selected from the group con-

sisting of sodium, potassium, lithium, magnesium and calcium. Specifically, C₁-C₅ alkyl thiol salt is in the present context meant to refer to a C₁-C₅ alkyl thiol selected from one or more of the group consisting of NaSCH₃, KSCCH₃, Ca(SCH₃)₂ and Mg(SCH₃)₂.

Hydrogen sulphide can be used as sulphur compound to produce 2-hydroxy-4-mercapto-butanoic acid or esters thereof, which can be further converted to the methionine α -hydroxy analogues by reaction with methanol. Alternatively, hydrogen sulphide can be used to form a C₁-C₅ alkyl thiol in the presence of the sugar, an alcohol and an acidic catalyst, as described in Roberts, J. S. 2000. Thiols, Kirk-Othmer Encyclopedia of Chemical Technology.

15

The methionine α -hydroxy analogue and derivatives thereof are selected from the group consisting of 2-hydroxy-4-(C₁₋₅ alkylthio)butanoic acid, salts and esters thereof. C₁₋₅ alkylthio corresponds to the C₁₋₅ alkyl thio compound comprising sulphur present in the process. Preferably, the methionine α -hydroxy analogue and derivatives thereof are selected from the group consisting of 2-hydroxy-4-(methylthio)butanoic acid, salts and esters thereof. Preferably, the methionine α -hydroxy analogue and derivatives thereof are selected from the group consisting of 2-hydroxy-4-(methylthio)butanoic acid, alkali and alkaline earth metal salts and C₁₋₈ alkyl esters thereof. Preferably, the methionine α -hydroxy analogue and derivatives thereof are selected from the group consisting of 2-hydroxy-4-(methylthio)butanoic acid, alkali and alkaline earth metal salts and C₁₋₈ alkyl esters thereof.

30

C₁₋₈ alkyl esters is in the present context meant to refer to esters comprising the alkyl group selected from the group consisting of methyl, ethyl, propyl, butyl, isopropyl, isobutyl, pentyl, hexyl, heptyl, octyl and 2-ethylhexyl. Alkali and alkaline earth metal salts mean salts of the acid wherein the salt cation is selected from the group I and group II metals.

In one embodiment of the invention the methionine α -hydroxy analogue and derivatives thereof is 2-hydroxy-4-(methylthio)butanoic acid.

In a another embodiment of the invention the methionine α -hydroxy analogue and derivatives thereof is selected from the group consisting of 2-hydroxy-4-(methylthio)butanoic acid methyl ester, 2-hydroxy-4-(methylthio)butanoic acid ethyl ester, 2-hydroxy-4-(methylthio)butanoic acid propyl ester, 2-hydroxy-4-(methylthio)butanoic acid butyl ester, 2-hydroxy-4-(methylthio)butanoic acid isopropyl ester, 2-hydroxy-4-(methylthio)butanoic acid pentyl ester, 2-hydroxy-4-(methylthio)butanoic acid hexyl ester, 2-hydroxy-4-(methylthio)butanoic acid heptyl ester, 2-hydroxy-4-(methylthio)butanoic acid octyl ester and 2-hydroxy-4-(methylthio)butanoic acid 2-ethylhexyl ester.

25

The one or more sugars or derivatives thereof are selected from the group consisting of C2-C6 sugars or derivatives thereof. C2-C6 sugars or derivatives thereof is in the present context meant to refer to carbohydrates commonly found in biomass selected from the group consisting of glucose, fructose, galactose, mannose, sucrose, xylose, erythrose, erythrulose, threose, glycolaldehyde and 2-hydroxy- γ -

30

butyrolactone. The one or more sugars or derivatives thereof may be used in solution or it may be a sugar syrup. Such a solution and syrup may be referred to as a sugar composition. The sugar composition may contain the solvent. Accordingly, the one or more sugars and derivatives thereof may be mixed with the solvent and/or the compound comprising sulphur. before it is contacted with the metallo-silicate composition. It may be referred to as a reaction mixture.

The process is preferably a one step process wherein the methionine α -hydroxy analogue and derivatives thereof are obtainable directly from the sugar substrate by contacting one or more sugars with a metallo-silicate composition in the presence of a compound comprising sulphur and a solvent.

In a further embodiment of the invention the sugars can be used in the presence of other C₁-C₃ oxygenates such as, acetol, pyruvaldehyde, formaldehyde and glyoxal. Glycolaldehyde (C₂ sugar) can be produced together with minor amounts of other C₁-C₃ oxygenates by hydrous thermolysis of sugars according to the procedure described in US 7,094,932 B2 and PCT/EP2014/053587.

The methionine α -hydroxy analogue and derivatives thereof are also obtainable by subjecting the one or more sugars or derivatives thereof to a pyrolysis step to obtain a pyrolysis product and subsequently contacting the pyrolysis product with the metallo-silicate composition in the presence of the compound comprising sulphur and the solvent.

Metallo-silicate composition refers to one or more solid materials comprising silicon oxide and metal and/or metal oxide

components, wherein the metal and/or metal oxide components are incorporated into and/or grafted onto the surface of the silicon oxide structure (i.e. the silicon oxide structure comprises M-O-Si bonds). The silicon oxide structure is also known as a silicate. Metallo-silicate compositions may be crystalline or non-crystalline. Non-crystalline metallo-silicates include ordered mesoporous amorphous or other mesoporous amorphous forms. The metallo-silicate composition is selected from one or more of the group consisting of zeotype materials and ordered mesoporous amorphous silicates.

Preferably the active metal of the metal and/or metal oxide component is selected from one or more of the group consisting of Ge, Sn, Pb, Ti, Zr and Hf. The genus of zeotype materials encompasses the zeolite material genus. Preferably the zeotype material has a framework structure selected from the group consisting of BEA, MFI, FAU, MOR and FER. Preferably the ordered mesoporous amorphous silicate has a structure selected from the group consisting of MCM-41 and SBA-15. In a preferred embodiment, the metallo-silicate composition is a zeotype material. More preferably the metallo-silicate composition is a zeotype material and is selected from the group consisting of Sn-BEA, Sn-MFI, Sn-FAU, Sn-MCM-41 and Sn-SBA-15.

The solvent is preferably selected from one or more of the group consisting of methanol, ethanol, 1-propanol, 1-butanol, 2-propanol, 2-butanol, DMSO and water.

WO 2015/024875 discloses that in certain conditions, the presence of a metal ion in the reaction solution is beneficial to the yield. WO 2015/024875 provides experimental de-

tails describing the origin and addition of the metal ion to the process either via the catalyst itself or independently of the catalyst.

5 A further embodiment of the present invention is a basic reaction solution. The basic solution may be obtainable by the addition of one or more basic components. The basic component may be selected from one or more of the reagents selected from a metal salt and a basic polymer resin. Basic polymer
10 resin may be for example a basic amberlyst resin.

The metal salt comprises a metal ion. Preferably the metal ion is selected from the group consisting of potassium, sodium, lithium, rubidium and caesium. Preferably the metal salt
15 is a salt of an alkaline earth metal or alkali metal and anion is selected from the group consisting of carbonate, nitrate, acetate, lactate, chloride, bromide and hydroxide. Even more preferably the metal ion originates from one or more salts of the alkaline earth metal or alkali metal and is
20 selected from the group consisting of K_2CO_3 , KNO_3 , KCl , potassium acetate (CH_3CO_2K), potassium lactate ($CH_3CH(OH)CO_2K$), Na_2CO_3 , Li_2CO_3 and Rb_2CO_3 .

The reaction vessel/solution that is used in the process is
25 heated to a temperature of less than 250 °C. Preferably the vessel is heated to from 50 °C to 180 °C, from 60 °C to 170 °C, from 80 °C to 150 °C; more preferably from 60 °C to 140 °C.

30 According to the process of the present invention the inventors have surprisingly found that the yield of the methionine α -hydroxy analogue and derivatives thereof is greater than

than the yield of MVG. If a C4 saccharide is the substrate, the yield of MVG is less than 5%, 4%, 3%, 2%, 1%.

Also, the inventors have surprisingly found that the yield of
5 the methionine α -hydroxy analogue and derivatives thereof prepared according to the process of the present invention is greater than 15%.

The process for the preparation of methionine α -hydroxy ana-
10 logue and derivatives thereof may be carried out in a batch scale reaction or a continuous flow reaction.

The one or more sugars or derivatives thereof are contacted with the metallo-silicate composition in the presence of the
15 compound comprising sulphur and the solvent in a reactor. Sugars or derivatives thereof are gradually converted into the methionine α -hydroxy analogue and derivatives thereof. Preferably the reactor is stirred such as by a mixer or by the flow through the reactor. The conversion is preferably
20 carried out under heating and for a period of time sufficient to achieve a high conversion of the sugars and derivatives thereof. Preferably for a period of from 10 minutes to 12 hours, more preferred of from 20 to 300 minutes. The methio-
nine α -hydroxy analogue and derivatives thereof may be re-
25 covered as it is or it may be purified such as by distillation.

Products obtained from bio materials such as sugars, will have a significantly higher content of ^{14}C carbon than the same products obtained from petrochemical sources. Previous-
30 ly, methionine and its derivatives for use as nutritional supplements have been obtained from fossil fuels.

Accordingly a product is provided according to the present invention, which is obtainable by the process for the preparation of a methionine α -hydroxy analogue and derivatives thereof from sugars described above. Such a product is characteristic by having a ^{14}C content above 0.5 parts per trillion of the total carbon content. The methionine α -hydroxy analogue and derivatives thereof may be 2-hydroxy-4-(methylthio)butanoic acid, salts and esters thereof and at least 70% of the initial carbon may be recovered in that form.

Legends to the Figures

Figure 1. Yield of methyl ester of methionine α -hydroxy analogue (2-hydroxy-4-(methylthio)butanoic acid methyl ester) with Sn-Beta as catalyst using glycolaldehyde as sugar in continuous flow reaction. Feed composition: 9 g/L glycolaldehyde in methanol as solvent, 10.7 wt% of water, 0.9 g/L methanethiol.

Figure 2. Yield of methyl ester of methionine α -hydroxy analogue (2-hydroxy-4-(methylthio)butanoic acid methyl ester) with Sn-Beta as catalyst using glycolaldehyde in the presence of $\text{C}_1\text{-C}_3$ oxygenate compounds in continuous flow reaction. Feed composition: 10.9 g/L glycolaldehyde in methanol as solvent, 8 wt% of water, 0.7 g/L methanethiol.

Examples

Preparation of catalyst

Sn-BEA (Si/Sn = 125) is prepared according to a modification of the procedure described in US 4,933,161. Commercial zeolite Beta (Zeolyst, Si/Al 12.5, ammonium form) is calcined (550°C for 6 h) to obtain the H form (de-aluminated form) and treated with 10 grams of concentrated nitric acid (Sigma-Aldrich, 65%) per gram of zeolite beta powder for 12 h at 80°C. The resulting solid is filtered, washed with ample water and calcined (550°C for 6 h) to obtain the de-aluminated Beta. This solid is impregnated by incipient wetness methodology with a Sn/Si ratio of 125. For this purpose, tin (II) chloride (0.128 g, Sigma-Aldrich, 98%) is dissolved in water (5.75 mL) and added to the de-aluminated Beta (5 g). After the impregnation process, the samples are dried 12 h at 110 °C and calcined again (550°C for 6 h)

Example 1: Catalytic reaction in batch reaction

A stainless steel pressure vessel (40 cc, Swagelok) is charged with 15.0 g of methanol (Sigma-Aldrich, >99.8%), 0.450 g of sucrose (Fluka, >99.0%) and 0.150 g of catalyst. The reactor is then filled with 75 mL of methanethiol at 1.7 bar, pressurized at 11 bar with N₂ and closed. The reactor is heated in an oil bath at 170 °C under stirring (700 rpm). The reaction is continued for the desired time and after this period, the reaction is quenched by submerging the vessel in cold water. Samples from the reaction vessel are filtered and analysed by HPLC (Agilent 1200, Biorad Aminex HPX-87H column at 65 °C, 0.05 M H₂SO₄, 0.6 ml min⁻¹) to quantify unconverted hexoses and dihydroxyacetone (DHA), glyceraldehyde (GLA); and GC (Agilent 7890 with a Phenomenex Solgelwax column) was used to quantify: methyl lactate (ML), methyl vinylglycolate (MVG, methyl 2-hydroxy-3-butenate), glycolaldehyde dimethylacetal

(GADMA) and MHA (Methionine α -hydroxy analogue and derivatives thereof).

The methionine α -hydroxy analogue esters prepared according to Example 1 may be reacted in a basic aqueous solution, such as aqueous NaOH or KOH or an acidic aqueous solution, such as aqueous HCl, or solid acid catalyst to produce the salts and the acid derivatives of the methionine α -hydroxy analogue ester.

Table 1: Conversion of sugars to methionine α -hydroxy analogue and derivatives thereof in the Presence of a Metallo-silicate composition and sulfur compound. MHA means methionine α -hydroxy analogue and derivatives thereof. In the case of solvents A, B and C, MHA means 2-hydroxy-4-(methylthio)butanoic acid methyl ester. In the case of H₂O as solvent, MHA means 2-hydroxy-4-(methylthio)butanoic acid. In the case of IPA, MHA means 2-hydroxy-4-(methylthio)butanoic acid isopropyl ester. In the case of ethanol, MHA means 2-hydroxy-4-(methylthio)butanoic acid ethyl ester.

Ex	Sugar	Catalyst	Sol-vent	CH ₃ SH / mL	MHA Yield	MVG Yield	Conver-sion	Temp	Time
1	Erythrulose	Sn-BEA	A	25	20.7	0	68.1	60	16
2	Erythrulose	Sn-BEA	A	25	6.8	0	43.8	60	4
3	Erythrulose	Sn-BEA	A	50	3.5	0	14.0	60	4
4	Erythrulose	Sn-BEA	A	25	24.3	0	77.7	100	4
5	Erythrulose	Sn-BEA	A	25	11.4	0	86.6	60	4
6	Erythrulose	Sn-BEA	A	25	12.7	17.4	93.8	170	16
7	Erythrulose	Sn-MFI	A	25	29.1	0	81.3	100	4
8	Erythrulose	Sn-FAU	A	25	0	0	54.0	100	4
9	Erythrulose	Sn-MOR	A	25	0	-	97.2	100	4
10	Erythrulose	Sn-BEA	IPA	25	0	0	66.7	100	4
11	Erythrulose	Sn-BEA	EtOH	25	15.6	0	68.7	100	4
12	Erythrulose	Sn-BEA	H ₂ O	25	0	0	0	80	4
13	Erythrulose	Sn-BEA	A	25	21.2	0	76.6	140	4
14	Erythrulose	Sn-BEA	A	50	19.7	8.3	85.7	170	4
15	Erythrulose	Sn-BEA	A	25	6.7	0	27.4	60	4
16	Erythrulose	Sn-BEA	A	25	14.8	0	84.6	170	4
17	Erythrulose	Sn-BEA	B	25	23.7	0	73.0	100	4
18	Erythrulose	Sn-BEA	C	25	22.1	0	76.9	100	4
19	Glucose	Sn-BEA	A	25	3.6	<<1	0	160	3
20	Glucose	Sn-BEA	A	25	8.3	0	100	160	4
21	Glucose	Sn-BEA	A	25	5.0	5.8	96.8	170	16
22	GA	Sn-BEA	A	25	12.7	0	44.3	120	4
23	GA	Sn-BEA	A	25	17.4	0	41.9	120	16
24	GA	Sn-BEA	A	25	14.9	5.4	30.7	140	16
25	GA	Sn-BEA	A	10	7.5	0	48.0	60	4
26	GA	Sn-BEA	A	25	5.0	0	8.4	60	4
27	GA	Sn-BEA	A	25	17.7	4	28.9	60	3
28	GA	Sn-BEA	H ₂ O	25	0	0	51.3	80	4

Ex	Sugar	Catalyst	Sol-vent	CH3SH / mL	MHA Yield	MVG Yield	Conver-sion	Temp	Time
29	GA	Sn-BEA	A	25	0	0	39.4	60	4
30	GA	Sn-BEA	A	25	0	0	52.3	60	4
31	GA	Sn-BEA	A	10	0	0	51.1	60	4
32	GA	Sn-BEA	B	25	0	0	46.5	60	4
33	GA	Sn-BEA	C	25	5.0	0	88.9	120	4
34	GA	Sn-BEA	A	25	8.3	0	62.1	120	4
35	Sucrose	Sn-BEA	A	25	2.0	4.2	96	170	16
36	Sucrose	Sn-BEA	A	25	0.9	0	72.8	160	3
37	MVG	Sn-BEA	A	25	0		0	100	4
38	MVG	Sn-BEA	A	25	0		100	100	4
39	MVG	Sn-BEA	A	25	0.2		12.7	170	16
40	Erythrose	Sn-BEA	A	25	0	0	0	60	4
41	Erythrose	Sn-BEA	A	25	20.0	0	80.0	100	4
42	Erythrose	Sn-BEA	A	25	19.3	0	94.0	170	4
43	GA	Sn-BEA	A	25	14.5	0	73.0	100	16
44	GA	Sn-BEA & Amberlyst	A	25	15.4	0	90.1	100	16
45	Glucose	Sn-BEA	A	85	8.3	-	79.4	120	4
46	Erythrulose	Sn-BEA	A	85	17.0	-	81.8	120	4

Solvent A: MeOH+0.13mmol K₂CO₃

Solvent B: MeOH+0.06mmol K₂CO₃

Solvent C: MeOH+0.3mmol K₂CO₃

5

GA = glycolaldehyde

10

As observed in Table 1, C4 and C2 sugars (erythrulose and glycolaldehyde) provided the highest yields of methionine α -hydroxy analogue and derivatives thereof. Methanol and ethanol provided similar yields of the corresponding esters.

Example 2: Catalytic reaction in continuous flow reaction

5 Compositions comprising glycolaldehyde in the presence of C₁-C₃ oxygenate compounds may be prepared by pyrolysis of biomass or C₅-C₆ sugars such as glucose, sucrose, fructose or xylose. Exemplary pyrolysis reactions are provided in US 7,094,932 B2 and PCT/EP2014/053587.

10 A composition comprising glycolaldehyde or C₁-C₃ oxygenate compounds with 814 g/L glycolaldehyde was dissolved in methanol (Sigma-Aldrich, 99.9%) at room temperature to reach a concentration of 10.9 g/l. Additionally, methanethiol (Sigma, 1.7 bar) and if necessary water, were added to the feed solution. Catalyst Sn-Beta (Si:Sn 125) prepared according to the above preparation was fractionized (0.25 g, 300-600 µm.) and loaded into a stainless steel 0.25 inch reactor. Glass wool was used to hold the catalyst in place. The reactor was introduced into an oven and the temperature of the reactor increased to 160 °C. When the temperature was over 140°C, the pump was started with a flow of 0.05 ml/min.

25 As observed from figures 1 and 2, stable yields of 2-hydroxy-4-(methylthio)butanoic acid methyl ester (over 30%) were obtained from glycolaldehyde in water and methanol using Sn-Beta as catalyst. The presence of other C₁-C₃ oxygenates (Figure 2) did not affect the reaction of production of the methionine α -hydroxy analogue methyl ester.

30 Embodiments

The present invention may also be described according to the following embodiments:

Embodiment 1. A process for the preparation of methio-
nine α -hydroxy analogues comprising contacting one or
more sugars or derivatives thereof with a metallo-
silicate composition in the presence of a compound com-
prising sulphur and a solvent.

5

Embodiment 2. The process according to embodiment 1,
wherein the compound comprising sulphur is selected from
the group consisting of C₁-C₅ alkyl thiol, C₁-C₅ alkyl
thiol salt, dimethylmercaptan, dimethyl disulphide and
hydrogen sulphide.

10

Embodiment 3. The process according to any one of em-
bodiments 1 and 2, wherein the compound comprising sul-
phur is selected from the group consisting of methane
thiol, dimethylmercaptan, dimethyl disulphide and hydro-
gen sulphide.

15

Embodiment 4. A process according to any one of embodi-
ments 1 to 3, wherein the one or more sugars or deriva-
tives thereof is selected from the group consisting of
glucose, fructose, galactose, mannose, sucrose, xylose,
erythrose, erythrulose, threose, glycolaldehyde and 2-
hydroxy- γ -butyrolactone.

20

Embodiment 5. A process according to any one of embodi-
ments 1 to 3, wherein the one or more sugars or deriva-
tives thereof are derivatives obtained by subjecting one
or more sugars selected from the group consisting of
glucose, fructose, galactose, mannose, sucrose, xylose,
erythrose, erythrulose, threose; to a pyrolysis step to
obtain a pyrolysis product and subsequently contacting
the pyrolysis product with the metallo-silicate composi-
tion in the presence of the compound comprising sulphur
and the solvent

25

30

Embodiment 6. The process according to any one of embodiments 1 to 5, wherein the metallo-silicate composition is a zeotype material.

5 Embodiment 7. The process according to embodiment 6, wherein the zeotype material is one or more materials selected from the group consisting of Sn-BEA, Sn-MFI, Sn-FAU, Sn-MCM-41 and Sn-SBA-15.

10 Embodiment 8. The process according to any one of embodiments 1 to 7, wherein the solvent is selected from one or more of the group consisting of methanol, ethanol, 1-propanol, 1-butanol, 2-propanol, 2-butanol, DMSO and water.

15 Embodiment 9. The process according to any one of embodiments 1 to 8, wherein the methionine α -hydroxy analogues is selected from the group consisting of 2-hydroxy-4-(methylthio)butanoic acid, salts and esters thereof.

20 Embodiment 10. The process according to any one of embodiments 1 to 9, wherein the methionine α -hydroxy analogues is selected from the group consisting of 2-hydroxy-4-(methylthio)butanoic acid, 2-hydroxy-4-(methylthio)butanoic acid methyl ester and 2-hydroxy-4-(methylthio)butanoic acid ethyl ester

25 Embodiment 11. The process according to any one of embodiments 1 to 10, wherein the temperature of the process is less than 200°C, preferably within the range of from 50 to 200°C.

30 Embodiment 12. The process according to any one of embodiments 1 to 11, wherein the reaction solution comprises one or more basic components selected from the group consisting of a metal salt and a polymer resin.

Embodiment 13. The process according to any one of embodiments 1 to 12, wherein the yield of the methionine α -hydroxy analogues is greater than methyl vinylglycolate (MVG).

5 Embodiment 14. The process according to any one of embodiments 1 to 13, wherein the yield of the methionine α -hydroxy analogues is greater than 15%.

Embodiment 15. The process according to any one of embodiments 1 to 14, wherein the process is a continuous
10 process.

Embodiment 16. The process according to any one of embodiments 1 to 15, wherein the methionine α -hydroxy analogues are purified by distillation.

Embodiment 17. The process according to embodiment 9,
15 wherein the 2-hydroxy-4-(methylthio)butanoic esters are hydrolysed.

Embodiment 18. Use of 2-hydroxy-4-(methylthio)butanoic acid, salts and esters thereof prepared by the process of claims 9 to 17 for a nutritional supplement.

Claims:

1. A process for the preparation of a methionine α -hydroxy
analogue and derivatives thereof of the formula:



wherein R is selected from the group consisting of H,
C₁-C₈ alkyl, alkaline or alkaline-earth metals; and R'
is selected from the group consisting of H and methyl;
and wherein

the process comprises a step of contacting one or more
sugars or derivatives thereof with a metallo-silicate
composition in the presence of a compound comprising
sulphur and a solvent.

2. A process according to claim 1, wherein the compound
comprising sulphur is selected from the group consisting
of C₁-C₅ alkyl thiol, C₁-C₅ alkyl thiol salt, dimethyl-
mercaptan, dimethyl disulphide and hydrogen sulphide.

3. A process according to claim 2, wherein the compound
comprising sulphur is selected from the group consisting
of methane thiol, methanethiolate alkaline salts, dime-
thylmercaptan, dimethyl disulphide, and hydrogen sul-
phide.

4. A process according to any one of claims 1 to 3, wherein
the one or more sugars or derivatives thereof is select-
ed from the group consisting of glucose, fructose, ga-
lactose, mannose, sucrose, xylose, erythrose, erythru-

lose, threose, glycolaldehyde, methyl vinyl glycolate, vinyl glycolic acid and 2-hydroxy- γ -butyrolactone.

- 5 5. A process according to any one of claims 1 to 3, wherein the one or more sugars or derivatives thereof are derivatives obtained by subjecting one or more sugars selected from the group consisting of glucose, fructose, galactose, mannose, sucrose, xylose, erythrose, erythrose, threose; to a pyrolysis step to obtain a pyrolysis product and subsequently contacting the pyrolysis product with the metallo-silicate composition in the presence of the compound comprising sulphur and the solvent.
- 10 6. The process according to any one of claims 1 to 5, wherein the metallo-silicate composition is a zeotype material.
- 15 7. The process according to claim 6, wherein the zeotype material is one or more materials selected from the group consisting of Sn-BEA, Sn-MFI, Sn-FAU, Sn-MCM-41 and Sn-SBA-15.
- 20 8. The process according to any one of claims 1 to 7, wherein the solvent is selected from one or more of the group consisting of methanol, ethanol, 1-propanol, 1-butanol, 2-propanol, 2-butanol, DMSO and water.
- 25 9. The process according to any one of claims 1 to 8, wherein the methionine α -hydroxy analogue and derivatives thereof are selected from the group consisting of 2-hydroxy-4-(methylthio)butanoic acid, salts and esters thereof.
- 30

10. The process according to any one of claims 1 to 9,
wherein the methionine α -hydroxy analogue and deriva-
tives thereof are selected from the group consisting of
2-hydroxy-4-(methylthio)butanoic acid, 2-hydroxy-4-
5 (methylthio)butanoic acid methyl ester and 2-hydroxy-4-
(methylthio)butanoic acid ethyl ester.

11. The process according to any one of claims 1 to 10,
wherein the one or more sugars or derivatives thereof
10 are contacted with the metallo-silicate composition in
the presence of the compound comprising sulphur and the
solvent under heating.

12. The process according to claim 11, wherein the heating
15 temperature is between 50 and 200°C, preferably of be-
tween 80 and 120 °C.

13. The process according to any one of claims 11 to 12,
wherein the heating is continued for a period of from 10
20 minutes to 12 hours, preferably of from 20 to 300
minutes.

14. The process according to any one of claims 1 to 13,
wherein the one or more sugars or derivatives thereof
25 are contacted with the metallo-silicate composition in
the presence of the compound comprising sulphur and the
solvent and in the presence of one or more basic compo-
nents selected from the group consisting of a metal salt
and a polymer resin.

15. The process according to any one of claims 1 to 14,
wherein the yield of the methionine α -hydroxy analogue

and derivatives thereof are greater than the yield of methyl vinylglycolate (MVG).

16. The process according to any one of claims 1 to 15,
5 wherein the yield of the methionine α -hydroxy analogue and derivatives thereof is greater than 15%.

17. The process according to any one of claims 1 to 16,
10 wherein the process is a continuous process.

18. The process according to claim 17, wherein the weight hourly space velocity is between 0.005 and 10 h⁻¹, preferably between 0.1 and 1 h⁻¹.

15 19. The process according to any one of claims 1 to 18, wherein the methionine α -hydroxy analogue and derivatives thereof are recovered.

20 20. The process according to any one of claims 1 to 19, wherein the methionine α -hydroxy analogue and derivatives thereof are recovered by purification.

21. The process according to any one of claims 1 to 20,
25 wherein the methionine α -hydroxy analogue and derivatives thereof are purified by distillation.

22. The process according to claim 9, wherein the 2-hydroxy-4-(methylthio)butanoic esters are hydrolysed.

30 23. A 2-hydroxy-4-(methylthio)butanoic acid, salts and esters thereof obtainable by the process according to any one of claims 1 to 22, characterized in that the ¹⁴C

content is above 0.5 parts per trillion of the total carbon content.

5 24. A 2-hydroxy-4-(methylthio)butanoic acid, salts and esters thereof, characterized in that the ^{14}C content is above 0.5 parts per trillion of the total carbon content.

10 25. Use of 2-hydroxy-4-(methylthio)butanoic acid, salts and esters thereof prepared by the process according to any one of claims 9 to 22 or the product according to claim 23 or 24 for a nutritional supplement.

Fig. 1





Fig.2



INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2016/059661

A. CLASSIFICATION OF SUBJECT MATTER
INV. C07C319/14 C07C323/52
ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
C07C A23L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPO-Internal, WPI Data, CHEM ABS Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2011/229626 A1 (DEVAUX JEAN-FRANCOIS [FR] ET AL) 22 September 2011 (2011-09-22)	23-25
A	paragraph [0002] - paragraph [0014] paragraph [0052] - paragraph [0072]; claims; example 3	1-22
A	----- EP 2 184 270 A1 (TOPSOE HALDOR AS [DK]) 12 May 2010 (2010-05-12) cited in the application claims; examples	1-25
A	----- WO 98/32735 A1 (NOVOUS INTERNATIONAL INC [US]) 30 July 1998 (1998-07-30) cited in the application claims; examples	1-22
E	----- WO 2016/083137 A1 (HALDOR TOPSÖE AS [DK]) 2 June 2016 (2016-06-02) claims; examples	1-25



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

29 June 2016

Date of mailing of the international search report

06/07/2016

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040,
Fax: (+31-70) 340-3016

Authorized officer

Zervas, Brigitte

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP2016/059661

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 2011229626	A1	22-09-2011	BR PI0922066 A2 15-12-2015
		CN 102282119 A 14-12-2011	
		EP 2361239 A2 31-08-2011	
		FR 2938535 A1 21-05-2010	
		JP 2012509304 A 19-04-2012	
		SG 171773 A1 28-07-2011	
		US 2011229626 A1 22-09-2011	
		WO 2010058129 A2 27-05-2010	
EP 2184270	A1	12-05-2010	AU 2009235999 A1 27-05-2010
		BR PI0904364 A2 15-03-2011	
		CA 2684852 A1 11-05-2010	
		CN 101898955 A 01-12-2010	
		DK 2184270 T3 15-04-2013	
		EP 2184270 A1 12-05-2010	
		ES 2401537 T3 22-04-2013	
		US 2010121096 A1 13-05-2010	
WO 9832735	A1	30-07-1998	CN 1244192 A 09-02-2000
		DE 69812911 D1 08-05-2003	
		DE 69812911 T2 06-11-2003	
		EP 0961769 A1 08-12-1999	
		ES 2196538 T3 16-12-2003	
		US 5973200 A 26-10-1999	
		WO 9832735 A1 30-07-1998	
WO 2016083137	A1	02-06-2016	NONE