



US007172752B2

(12) **United States Patent**  
**Watanabe et al.**

(10) **Patent No.:** **US 7,172,752 B2**  
(45) **Date of Patent:** **Feb. 6, 2007**

(54) **COMBINATION PARTICLES FOR THE  
TREATMENT OF ASTHMA**

(75) Inventors: **Wiwik Watanabe**, Sunnyvale, CA  
(US); **Esko Kauppinen**, Helsinki (FI);  
**Petri Ahonen**, Koivjärvi (FI); **David**  
**Brown**, Helsinki (FI); **Esa Muttonen**,  
Espoo (FI)

(73) Assignee: **Orion Corporation**, Espoo (FI)

(\*) Notice: Subject to any disclaimer, the term of this  
patent is extended or adjusted under 35  
U.S.C. 154(b) by 328 days.

(21) Appl. No.: **10/398,381**

(22) PCT Filed: **Oct. 5, 2001**

(86) PCT No.: **PCT/FI01/00864**

§ 371 (c)(1),  
(2), (4) Date: **Aug. 14, 2003**

(87) PCT Pub. No.: **WO02/28378**

PCT Pub. Date: **Apr. 11, 2002**

(65) **Prior Publication Data**

US 2004/0052732 A1 Mar. 18, 2004

(30) **Foreign Application Priority Data**

Oct. 6, 2000 (FI) ..... 20002216

(51) **Int. Cl.**

**A61K 9/14** (2006.01)

**A61K 9/12** (2006.01)

**A61K 31/56** (2006.01)

(52) **U.S. Cl.** ..... **424/46**; 424/45; 424/489;  
514/171; 514/174; 514/826

(58) **Field of Classification Search** ..... 424/45,  
424/46, 489, 490; 514/630, 171, 174, 826  
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

4,590,206 A 5/1986 Forrester et al.

4,999,182 A 3/1991 Baumard et al.  
5,637,620 A \* 6/1997 Trofast et al. .... 514/630  
5,674,860 A \* 10/1997 Carling et al. .... 514/171  
5,972,919 A \* 10/1999 Carling et al. .... 514/171  
6,030,604 A 2/2000 Trofast  
6,051,257 A 4/2000 Kodas et al.  
6,287,540 B1 \* 9/2001 Trofast ..... 424/46  
2004/0028619 A1 2/2004 Watanabe  
2004/0096516 A1 \* 5/2004 Musa et al. .... 424/490

#### FOREIGN PATENT DOCUMENTS

EP 0357005 A1 3/1990  
EP 416950 A1 3/1991  
EP 416951 A1 3/1991  
WO WO 93/11743 6/1993  
WO WO 97/36574 10/1997  
WO WO 98/41193 9/1998  
WO WO 00/48587 8/2000  
WO WO 01/49263 7/2001

#### OTHER PUBLICATIONS

D. Bouros et al., "Formoterol and beclomethasone versus higher  
dose beclomethasone as maintenance therapy in adult asthma," Eur  
Respir J, vol. 14, pp. 627-632, 1999.

\* cited by examiner

*Primary Examiner*—Johann Richter

*Assistant Examiner*—Mina Haghighatian

(74) *Attorney, Agent, or Firm*—Finnegan, Henderson,  
Farabow, Garrett & Dunner, LLP

(57) **ABSTRACT**

Inhalation particles incorporating, in an individual particle,  
a combination of a  $\beta$ hd 2-agonist and a glucocorticosteroid  
in a predetermined and constant ratio, a process for the  
preparation thereof and pharmaceutical compositions com-  
prising the inhalation particles. The particles have a narrow  
particle size distribution and are preferably in the form of  
spherical crystalline particles with a rough surface. The  
particles are particularly useful in the treatment of asthma  
and other respiratory disorders.

**26 Claims, 7 Drawing Sheets**




Fig. 1a




Fig. 1b




Fig. 1c




Fig. 2




Fig. 3a




Fig. 3b




Fig. 4




Fig. 5




Fig. 6



1

## COMBINATION PARTICLES FOR THE TREATMENT OF ASTHMA

This application is a U.S. national stage filing of PCT International Application No. PCT/FI01/00864, filed on Oct. 5, 2001. This application also claims the benefit of priority under 35 U.S.C. § 119(a) to Finnish patent application no. 20002216, filed on Oct. 6, 2000.

### FIELD OF THE INVENTION

The present invention relates to inhalation particles and inhalation compositions suitable for pulmonary drug delivery and to methods for the preparation thereof. In particular, the present invention relates to inhalation particles incorporating a combination of two or more different active ingredients. The inhalation particles of the invention are particularly useful in the treatment of asthma and other respiratory disorders.

### BACKGROUND OF THE INVENTION

Inhalation has become the primary route of administration in the treatment of asthma. This is because, besides providing direct access to the lungs, medication delivered through the respiratory tract provides rapid and predictable onset of action and requires lower dosages compared to the oral route. Typical delivery systems for inhalable drugs are the pressurized metered-dose inhaler (pMDI) comprising a suspension of fine drug particles in a propellant gas, and the dry powder inhaler (DPI) comprising fine drug particles as dry powder typically admixed with coarser excipient such as lactose.

There have been recent advances in the treatment of asthma resulting from the recognition that asthma is a chronic inflammatory disease. Current asthma drugs can be classified into two classes, namely anti-inflammatory agents and bronchodilators. Anti-inflammatory drugs do not relieve asthma symptoms once they occur, rather they are used to control the inflammation. One of the drawbacks of anti-inflammatory drugs is that their onset of action is relatively slow. Therefore, patients often do not recognise any immediate therapeutic effects and tend to stop the medication. This could cause the inflammation uncontrollable. On the other hand, bronchodilators are effective to relieve acute asthma symptoms. They have a potent bronchodilating activity and rapid onset of action.

A particularly advantageous group of anti-inflammatory agents is anti-inflammatory glucocorticosteroids, such as beclomethasone and budesonide.

A particularly advantageous group of bronchodilators is  $\beta_2$ -agonists. The short-acting inhaled  $\beta_2$ -agonists e.g. salbutamol and terbutaline, are important for an immediate symptomatic asthma relieve, while long-acting  $\beta_2$ -agonists, e.g. salmeterol, formoterol and procaterol, are important for the treatment of moderate and severe asthma. However, there are currently debates on the safety of a regular use of  $\beta_2$ -agonists as well as efficiency of long-acting  $\beta_2$ -agonists. Also, the short-acting nature of the drug requires more frequent drug administrations, which tend to cause patient compliance problem.

To overcome these problems, inhalation compositions comprising a combination of a bronchodilator agent and an anti-inflammatory glucocorticosteroid, have been proposed as described e.g. in patent publications EP 0416950, EP 0416951, WO 93/11773 and WO 98/15280. Such combinations include salmeterol with beclomethasone dipropionate,

2

salmeterol with fluticasone propionate, and formoterol with budesonide. These patent publications disclose a method of mixing mechanically the two drug powders and optionally the carrier material in a certain proportion and placing the resulting inhalation powder into an inhaler device. When these combinations are used in dry powder inhalers, the consistency of drug proportion in each dose cannot be easily controlled. The ratio of drugs in each dose significantly depends on the forces existing in each drug, between the drugs, between the drug and carrier material, and between the drug and the dry powder container of the inhaler device. It is well acknowledged that the current powder manufacturing methods, especially the conventional methods, produce dry powder that is highly charged and therefore very cohesive. Hence, it is not easy to maintain the ratio of the drugs in each dose constant. The inconsistency of the dose could cause serious problems especially when a very potent drug is delivered in a much higher amount than expected.

A method for the preparation of inhalation particles by spray-drying a solution of one or several drugs has been disclosed in U.S. Pat. No. 4,590,206. However, particles incorporating a combination of a  $\beta_2$ -agonist and a glucocorticosteroid have not been disclosed. Furthermore the size and the morphology of the particles obtained are not optimal for pulmonary delivery by inhalation.

The object of the invention is to provide a composition that is better adapted than products of the prior art, for delivery of a drug combination into the lungs.

### SUMMARY OF THE INVENTION

It has been found that it is possible to prepare inhalation particles incorporating, in an individual particle, a combination of a  $\beta_2$ -agonist and a glucocorticosteroid, in a predetermined and constant ratio, the particles being especially suitable to be administered by inhalation. The mean mass aerodynamic diameter of the particles is typically between about 0.5–10  $\mu\text{m}$ , more typically between about 1–5  $\mu\text{m}$ . The aerodynamic particle size distribution of said particles is typically between about 0.5–10  $\mu\text{m}$ , more typically between about 1–5  $\mu\text{m}$ .

The predetermined and constant molar ratio of the  $\beta_2$ -agonist to the glucocorticosteroid in a particle of the invention may be from about 3:1 to about 1:3000, preferably from about 1:1 to about 1:1000. It has been found that particularly advantageous are particles, wherein the molar ratio of the  $\beta_2$ -agonist to the glucocorticosteroid is from about 1:5 to about 1:100, especially from about 1:10 to about 1:60.

The particles provide more controlled delivery of the combination of a  $\beta_2$ -agonist and a glucocorticosteroid by inhalation, since it is now possible to keep the ratio of the drugs in each dose constant. The particles exhibit good dispersibility and stability. The particles also have a narrow aerodynamic particle size distribution which is especially suitable for the preparation of compositions for dry powder inhalers. Moreover, their preparation by aerosol flow reactor method is simple and can be easily scaled-up to higher production rates.

In another aspect the present invention provides an inhalation composition comprising particles incorporating, in an individual particle, a combination of a  $\beta_2$ -agonist and a glucocorticosteroid. The particles may be formulated into an inhalation composition together with one or more pharmaceutically acceptable additives, diluents or carriers. Preferably, the composition is provided in the form of dry inhalation powder

In still another aspect the present invention provides a method for preparing particles incorporating a combination of a  $\beta_2$ -agonist and a glucocorticosteroid, comprising the steps of:

- providing liquid feed stock comprising a  $\beta_2$ -agonist and a glucocorticosteroid in a predetermined ratio;
- atomising said liquid feed stock to create droplets;
- suspending said droplets in a carrier gas;
- passing said carrier gas and droplets suspended therein through a heated tube flow reactor under predetermined residence time and temperature history; and collecting the particles produced,

#### BRIEF DESCRIPTION OF THE DRAWINGS

FIGS. 1a, 1b and 1c are schematic diagrams showing parts of the apparatus used in the method of the invention.

FIG. 2 is a schematic diagram of the electrostatic precipitator.

FIGS. 3a and 3b show the normalised and cumulative mass size distribution of the drug combination particles of the invention.

FIG. 4 shows the XRD pattern of the combination powder of the invention.

FIG. 5 shows moisture absorption profile of the combination powder of the invention when exposed in different humidity levels.

FIG. 6 depicts a scanning electron microscopy image of the combination powder of the invention.

#### DETAILED DESCRIPTION OF THE INVENTION

Various combinations of a  $\beta_2$ -agonist and a glucocorticosteroid can be used in preparing particles of the invention. Particularly preferred are combinations, which are typically used in the pulmonary delivery by inhalation in the treatment of asthma and other respiratory diseases. Examples of  $\beta_2$ -agonists include salbutamol, formoterol, formoterol, procaterol, salmeterol, clenbuterol and the like and their salts and hydrates. Examples of anti-inflammatory glucocorticosteroids include beclomethasone, budesonide, fluticasone, mometasone, betamethasone, triamcinolone, flunisonide and the like and their salts and hydrates. Typical combinations include formoterol fumarate with beclomethasone dipropionate, salbutamol with beclomethasone dipropionate, formoterol fumarate with budesonide, salmeterol with fluticasone propionate, and salmeterol with beclomethasone dipropionate.

The molar ratio of the  $\beta_2$ -agonist to the glucocorticosteroid in a particle of the invention may be selected from a broad range. For example, it may be from about 3:1 to about 1:3000, preferably from about 1:1 to about 1:1000. It has been found that particularly advantageous are particles, wherein the molar ratio of the  $\beta_2$ -agonist to the glucocorticosteroid is from about 1:5 to about 1:100, especially from about 1:10 to about 1:60.

The mean mass aerodynamic diameter of the particles is generally between about 0.5–10  $\mu\text{m}$ , preferably between about 1–5  $\mu\text{m}$ . Particularly it is preferred that more than 98% of the mass is in particles having a diameter of 5  $\mu\text{m}$  or less, and less than about 5% of the mass being in particles having a diameter of 0.5  $\mu\text{m}$  or less. It is particularly preferred that the aerodynamic particle size distribution of said particles is between about 0.5–10  $\mu\text{m}$ , more preferably between about 1–5  $\mu\text{m}$ .

It has been found that it is particularly advantageous if the particles are in crystalline form, since this reduces the tendency of moisture adsorption and increases the stability. It is especially preferred, that the relative degree of crystallinity of an active ingredient is 90% or higher, more preferably 95% or higher, most preferably 99% or higher.

It is also desired that the inhalation particles are essentially spherical in form. The spherical form reduces the contact areas between particles and thereby improves aerosolization and deagglomeration of the particles upon inhalation. The surface of the spherical particles is preferably rough. Rough surface is advantageous since it increases the effective separation distance of the particles, and thus improves aerosolization and deagglomeration properties of the particles.

If desired, various additives known in the art may be additionally incorporated in the particles together with the active ingredients. Such additives include e.g. diluents, carriers and stabilizers and the like. Examples of suitable solid diluents or carriers comprise lactose, dextran, mannitol and glucose, lactose being preferred. Also such additives incorporated in the particle are preferably in the crystalline form. It is particularly preferred that at least about 90 w-% of the total weight of the particle is in crystalline form. However in order to reduce the amount of material other than the active ingredients potentially reaching the lungs, it is preferred that the active ingredients constitute at least 90 w-%, preferably at least 95 w-%, more preferably at least 99 w-%, of the total weight of particles. Most preferably the particles are free from other material than the active ingredients.

The particles of the invention may be formulated into an inhalation composition together with one or more pharmaceutically acceptable additives, diluents or carriers. Examples of suitable solid diluents or carriers comprise lactose, dextran, mannitol and glucose, lactose being preferred. Examples of aerosol carriers include non-chlorofluorocarbon-based carriers such as HFA (hydrofluoroalkane). The use of aqueous carriers is also possible. Typical additives include solubilizers, stabilizers, flavouring agents, coloring agents and preserving agents.

The particles of the invention are preferably administered in the form of a dry powder composition. The particles can be used for pulmonary drug delivery by inhalation as such, e.g. they can be filled directly into capsules, cartridges, blister packs or reservoirs of dry powder inhalers. However, if desired the particles may be adapted to form loose agglomerates of several individual particles, said agglomerates breaking into individual particles upon dispersion into the inhaled air stream. The particles may also be combined with pharmaceutically acceptable carrier materials or excipients typically used in dry inhalation powders. Such carriers may be used simply as bulking agents or to improve the dispersibility of the powder. For example, the particles may be used in admixture with carrier particles, e.g. lactose, having larger particle size than the active ingredients, typically in the range of 5 to 100  $\mu\text{m}$ . If the composition contains a carrier, the total amount of the active ingredients is typically about 0.1–50% (w/w), preferably about 1–10% (w/w), based on total weight of the composition. Such compositions can be prepared by methods known in the art.

The particles of the invention can be also administered in the form of pressurized metered dose inhalation suspension, where the particles are suspended in pressurized aerosol carrier and delivered using pressurized metered dose inhaler (pMDI).

The particles of the present invention are preferably prepared by using an aerosol flow reactor method (aerosol synthesis method). It is a one-step continuous process, which can directly produce desirable particle size range. The method has been used to produce various materials, e.g. ceramic powder (U.S. Pat. No. 5,061,682) or zirconia powder (U.S. Pat. No. 4,999,182), at high operation temperatures. However, the method has not been used to produce pharmaceutical materials, which requires a significantly lower-temperature operation (less than 300° C.).

Other methods commonly used in the preparation of inhalation particles for pulmonary drug delivery may also be suitable in the preparation of particles of the invention. Such methods include, but are not limited to, precipitation, crystallization, spray-drying, supercritical fluid technologies such as rapid expansion of supercritical solutions (RESS), supercritical antisolvent method (SAS), gas antisolvent method (GAS) and solution enhanced dispersion by supercritical fluids (SEDS), which are all well known methods for one skilled in the art. However, the aerosol flow reactor method is the preferred method.

The aerosol flow reactor method comprises generally the following steps: (a) providing liquid feed stock comprising a  $\beta_2$ -agonist and a glucocorticosteroid in a predetermined ratio, (b) atomising said liquid feed stock to create droplets, (c) suspending said droplets in a carrier gas, (d) passing said carrier gas and droplets suspended therein through a heated tube flow reactor under predetermined residence time and temperature history, and (e) collecting the particles produced.

The above method differs significantly from the conventional spray-drying process. In spray-drying hot gas is used as a source of heat to evaporate the solvent. The spray-drying chamber is only used as a place for the heat transfer to occur, the chamber itself is not heated. The temperature of the gas is changing across the chamber as heat transfer occurs between the cold feed and the hot gas. Furthermore, the evaporation is so rapid that it is not easy to properly control the temperature history and the residence time of each droplet and product particle. The crystallization can not be easily controlled either, and therefore the particles formed are commonly amorphous.

In the present method the droplets are already suspended in the carrier gas before they are fed into the tubular flow reactor, which is placed in an oven set at a constant temperature. The carrier gas flows evenly in the tubular reactor with a constant rate, uniform temperature field and non-circulating flow. Therefore, the temperature history and the residence time of each droplet and product particle can be properly controlled and excellent uniformity of the particles can be ensured. Accordingly, the method provides better control of the droplet size distribution, and thus the particle size distribution such that particles with optimal aerodynamic particle size distribution typically between about 1–5  $\mu\text{m}$  can be obtained. Furthermore, in contrast to spray drying, the method allows essentially complete crystallization of the particles. Thus, the method is able to produce consistent and controlled particle properties, including particle size and size distribution, shape, crystallinity, polymorphic phase, surface roughness and chemical purity.

The liquid feed stock of step (a) may be prepared by mixing each active ingredient with a suitable liquid solution, e.g. solvent. The two liquid feed stocks are then mixed to form a solution, suspension, dispersion, gel, emulsion, slurry or the like, and is preferably homogenous to ensure uniform distribution of the components in the mixture. It is also

possible to mix the active ingredients directly in one liquid feed stock. The liquid feed stock in the form of a solution is preferred.

Various solvents may be employed in the preparation of the liquid feed stock, including but not limited to, water, hydrocarbons, halogenated hydrocarbons, alcohols, ketones and the like. Examples of suitable solvents include water, hexane, perfluorohexane, ethanol, methanol, acetone, chloroform, methylene chloride and combinations thereof.

In case the liquid feed stock is a solution, the active ingredients should be sufficiently soluble in the solvent of the solution so as to obtain, from the atomized droplets of the liquid feed stock, uniform particles with the desired particle size, size distribution and drug ratio. The total solids dissolved may be present in wide range of concentrations, typically from about 0.1% to about 10% by weight, for example from about 1% to about 5% by weight. A liquid feed stock containing relatively low concentration of solids results in particles having relatively small diameter. The finding of suitable liquid feed stock concentrations for each active agents/solvent combinations is considered to be a routine to one skilled in the art. Usually, the liquid feed stock concentration is firstly chosen at its maximum solubility so as to obtain the largest particle size with the atomizer and atomizer conditions used. From the results, the liquid feed stock concentration required to obtain the desired particle size range with the atomizer and the atomizer conditions used can be approximated.

The liquid feed stock is atomized to create droplets in a suitable atomizer, which are well known in the art, such as a spray nozzle (e.g. a two fluid nozzle), an ultrasonic or air assisted nebuliser or a spinning disc, an ultrasonic nebulizer being preferred. Examples of the devices used in this process include ultrasonic generators sold under trademarks Omron NE-U12 and RBI Pyrosol 7901. While there are no special restrictions placed on the atomisers used in the process, it is recommended to use an atomiser, which can produce uniform droplets of constant composition and in a specific size range. Such devices are suitable to produce dry powders of controlled composition and with particle size range suitable for dry powder inhalation.

The droplets of the liquid feed stock are suspended in a carrier gas before passing through a heated tube flow reactor. The carrier gas must be inert with respect to the drug molecules and the solvent. It is recommended to use nitrogen gas or other inert gases. The temperature of the carrier gas is typically ambient. To maintain a uniform solution concentration in the droplets in the suspending phase, it is preferred to bubble the carrier gas through a bottle containing the same solvent as the liquid feed stock before entering the atomizer.

Because the droplets are already suspended in the carrier gas when fed into the reactor (i.e. the droplet generation and flow reactor are separated), the temperature history and residence time of each droplet and product particle can be better controlled than in the conventional spray-drying method. Therefore, excellent uniformity of the resulted particles and narrow particle size distribution can be ensured.

The droplets suspended in the carrier gas are passed through a tubular flow reactor, which is maintained at a constant temperature. The temperature and the flow rate of the carrier gas are adjusted to evaporate the solvent and to allow the crystallisation process to complete. The particles formed are then collected using an electrostatic precipitator, a cyclone, a planar filter (e.g. nylon) or other particle collecting devices.

It is preferred that the aerosol flow reactor conditions are selected such that crystalline spherical particles of homogeneous constituents having a narrow particle size distribution and rough surfaces are formed. Suitable mean mass aerodynamic diameter of the particles is between 0.5–10  $\mu\text{m}$ , preferably between 1–5  $\mu\text{m}$ . The aerodynamic particle size distribution between about 0.5–10  $\mu\text{m}$ , especially between about 1–5  $\mu\text{m}$ , is preferred.

Generally, the particles obtained from the heated tube flow reactor are in a crystalline form. It is especially preferred, that the relative degree of crystallinity of an active ingredient is 90% or higher, more preferably 95% or higher, most preferably 99% or higher. Preferably the aerosol flow reactor conditions are selected such that all active ingredients in the particle are in a crystalline form. The relative degree of crystallinity can be determined based on the x-ray powder diffraction patterns. The value of the relative degree of crystallinity can be estimated by a known method of broadening of the diffraction maxima (FWHM-values).

The aerosol flow reactor method generally produces particles which are essentially spherical, i.e. the spherical form is consistent and apparent when examined under the scanning electron microscope.

The surface of the obtained spherical particles is generally rough, i.e. the roughness is consistent over the entire surface of the particle and apparent when examined under the scanning electron microscope and the ratio of the maximum and minimum diameter of the particle is generally between 1.001–1.5, preferably between 1.002–1.2, more preferably between 1.01–1.1.

If desired, various additives known in the art may be additionally incorporated in the particles together with the active ingredients. Such additives include e.g. diluents, carriers and stabilizers and the like. In such case the additives are included in the liquid feed stock of the process together with the active ingredients. However, it is preferred that the active ingredients constitute at least 90 w-%, preferably at least 95 w-%, more preferably at least 99 w-%, of the total weight of particles. Most preferably the particles are free from other material than the active ingredients.

The particle size may be controlled to any expected particle size ranges by selection of the atomizer and concentration of the liquid feed stock. It is also possible to employ a droplet size modification apparatus (e.g. impactor or virtual impactor), or using size selective collection of particles, e.g. a cyclone) upstream and/or downstream of the flow reactor. Normally, however, this is not needed.

For the tubular flow reactor, while there are no particular restrictions, it is recommended to use a vertical, rather than horizontal configuration in order to minimise buoyancy effects and related losses due to recirculating flow. A laminar flow is preferred. To ensure uniform temperature and flow fields in the hot zone of the reactor, CFD (Computational Fluid Dynamics) calculations have shown that it is preferable that the aerosol flows against gravity. Flow in any other direction tends to produce undesirable reactor conditions. The reactor tube is preferably placed inside an oven to maintain a uniform reactor wall temperature during the process. The oven can be of any kind, which has sufficient temperature control (i.e.  $\pm 1^\circ\text{C}$ . or less) at low temperatures (less than  $300^\circ\text{C}$ .). The temperature of the oven is set such that the materials being processed do not decompose. Typically the selected oven temperature is within the range of about  $30$  to  $300^\circ\text{C}$ ., more typically between about  $70$  to  $200^\circ\text{C}$ . For the combination of beclomethasone dipropionate and formoterol fumarate, for example, since the melting point of beclomethasone dipropionate is about  $210^\circ\text{C}$ .

and the melting point of formoterol fumarate is about  $138^\circ\text{C}$ ., the range of oven temperature used for the combination particle production may vary between  $30$  to  $110^\circ\text{C}$ ., preferably between  $70$  to  $100^\circ\text{C}$ .

While there are no particular restrictions placed on the particle collection, it is recommended to use a system, which can be heated to prevent the re-condensation process. Electrostatic precipitators, cyclones and/or filters can be used for this purpose. Accordingly, the particle collection system and the line from the flow reactor outlet to the particle collection system are preferably heated to a temperature above the boiling point of the solution to prevent the recondensation process to occur. However, the temperature should not be too high so as to cause material degradation. For example, for the combination of beclomethasone dipropionate and formoterol fumarate dissolved in ethanol, the temperature of the collection system and the line may be kept constant at a temperature between  $80$  to  $100^\circ\text{C}$ ., preferably between  $80$  and  $90^\circ\text{C}$ . To further prevent the re-condensation process to occur, dry carrier gas may be flown to the particle collection system. The carrier gas is preferably heated at a temperature between  $80$  to  $90^\circ\text{C}$ .

The particles obtained incorporate, in an individual particle, a combination of a  $\beta_2$ -agonist and a glucocorticosteroid. An individual particle means here an unagglomerated particle.

Such individual (unagglomerated) particles are well suited for pulmonary drug delivery by inhalation as such, or they may be mixed with suitable carrier materials.

The invention is further illustrated by the following experiments, which are not meant to limit the scope of the invention.

#### Experiments

All compositions produced according to the present invention fulfill the strict specification for content and purity required for pharmaceutical products.

#### EXAMPLE 1

##### 40 Preparation of Inhalation Particles Incorporating a Combination of Formoterol Fumarate and Beclomethasone Dipropionate

##### Preparation of the Liquid Feed Stock

Beclomethasone dipropionate is an anti-inflammatory glucocorticosteroid, which is practically insoluble in water, freely soluble in acetone and in chloroform, and sparingly soluble in alcohol. Thus, the solvent could be acetone, chloroform, methanol, ethanol, or other alcohols. In the current experiments, ethanol was used as a solvent, not only because ethanol is cheap and readily available but it is also recommended for use in production of pharmaceutical agents because it is non-toxic.

The beclomethasone dipropionate liquid feed stock was prepared by dissolving 1 gram of beclomethasone dipropionate powder in 40 ml of ethanol (99.5%) at room temperature.

Formoterol fumarate is a  $\beta_2$ -agonist bronchodilator, which is freely soluble in glacial acetic acid, soluble in methanol, sparingly soluble in ethanol. Thus, the solvent could be glacial acetic acid, methanol or ethanol. In the current experiments, ethanol was used as a solvent, not only because ethanol is cheap and readily available but it is also harmless and recommended for use in production of pharmaceuticals.

The formoterol fumarate liquid feed stock was prepared by dissolving 1 gram of formoterol fumarate powder in 613 ml of ethanol (99.5%) at room temperature.

The two liquid feed stocks were then mixed in such a way that the ratio between beclomethasone dipropionate and formoterol fumarate in the mixture is 200:6 (weight basis), which was considered to be a suitable drug ratio for the treatment of asthma.

#### Aerosol Synthesis

FIG. 1a shows the experimental set-up of the particle synthesis, and FIG. 1b and 1c show optional configurations used for particle analysis. The liquid feed stock described above was atomised using an ultrasonic atomizer (2), sold under trademark RBI Pyrosol 7901. The resulted droplets, which were suspended into a carrier gas, were then passed through a heated tube flow reactor (4). Nitrogen gas was used as a carrier gas, with a constant flow rate of 1.5 l/min. To maintain a uniform solution concentration in the atomizer, the carrier gas was bubbled through ethanol in a saturation bottle (1) before entering the atomizer. A vertical tube, which was inserted into an oven (3), was used to dry up the droplets. The oven used was a WTB Binder EDIFED 400, which has temperature variations of  $\pm 1$  and  $\pm 2^\circ$  C. for temperature at 70 and 110 $^\circ$  C., respectively. The tube was made of stainless steel, with an inner diameter and a heated length of 30 and 800 mm, respectively. The oven temperature was set at 100 $^\circ$  C. The minimum particle residence time in the heated zone under the selected process conditions was approximately 12 seconds. From the CFD calculation, it is shown that temperature field is uniform and the velocity is fully developed and non-circulating in the heated zone.

The resulted particles were then collected using an electrostatic precipitator (ESP) (5) connected to a high voltage generator (6). A carrier gas, preferably nitrogen gas, may be flown to the ESP to further prevent the recondensation process to occur. The exhaust gas was led from ESP via a dripping bottle (7) to exit (9). FIG. 2 shows the schematic diagram of ESP having inlet (16) and exit for exhaust gas (19). The ESP was made of a tubular stainless steel collection plate (20) with inside diameter and length of 10 and 50 cm, respectively. A 0.05 mm diameter tungsten wire was placed on the center axis of the collection plate and a high voltage (18) of 16 kV was applied between the wire and the plate. The high electric field formed a corona discharge (17) on the wire and charged the gas molecules. The gas ions were then formed. These ions migrated across the space between the wire and the plate under the influence of the applied electric field. During the migration, the ions collided with the aerosol particles, which thus acquired charge. The charged particles then migrated toward the grounded surface electrode. When the particles struck the grounded plate, they lost their charges and adhered to the plate surface via surface forces. Therefore, the particles collected were not charged. Dry nitrogen gas with a flow rate of 22.5 l/min was flowed into the ESP and temperature in the ESP and in the line from tubular tube outlet to the ESP were maintained at a constant temperature of 85 $^\circ$  C., to avoid condensation of organic vapours and moisture to occur. Condensation particle counter (CPC) model 3022, shown as (8) in FIG. 1a, was used to determine efficiency of the ESP. Particles collected were then removed from the plate surface of ESP by scraping, and then placed in a tight glass bottle to avoid moisture penetration or other contamination.

#### Characterisation

##### i. Particle Size Analysis

Referring now to FIG. 1b, the particle size distribution was measured by an electrical low pressure impactor (12) (ELPI) connected to a vacuum (13). The particles exiting the tubular tube were passed into a diluter (10), with a dilution ratio of 1:10, before entering the ELPI. Exhaust gas exit (11)

was arranged in the diluter. To minimize temperature gradient, and thus to reduce the moisture condensation, the diluter, the line to the diluter and the gas line into the diluter were layered with heating elements, which were kept at a temperature higher than that of the solution dew point. FIGS. 3a and 3b show normalised and cumulative mass size distributions of beclomethasone dipropionate/formoterol fumarate particles, respectively, measured gravimetrically. It is shown that a narrow size distribution within the range of aerodynamic particle size of interest, i.e. at around 1–5  $\mu$ m, was obtained.

##### ii. Particle Crystallinity

Crystallinity of the sample was studied by X-ray powder diffraction (Diffractometer D500, Siemens GmbH, Karlsruhe, Germany). A copper target X-ray (wavelength 0.1541 nm) tube was operated with the power of 40 kV $\times$ 40 mA.

For x-ray powder diffraction analysis, 500 mg of the powder was mounted to a cylindrical sample stage which has a diameter of 20 mm and height of approximately 2 mm.

The relative degree crystallinity of the powder was also determined based on the x-ray powder diffraction patterns shown in FIG. 4, wherein "A" means typical beclomethasone dipropionate, "B" means typical formoterol fumarate and "C" means the (200:6) combination of beclomethasone dipropionate (BDP) and formoterol fumarate. It is noticed that the diffraction pattern of the combination of beclomethasone dipropionate (BDP) and formoterol fumarate resembles very much to the diffraction pattern of pure BDP. Hence, formoterol fumarate may be partly or totally in amorphous state. For BDP, it can be seen that the maximum intensities were sharp and well above background intensities, which indicates that the BDP in the powder was well crystallised. The determined relative degree of crystallinity for BDP was 100%. The estimation was based on the broadening of the diffraction maxima (FWHM-values) positioned at 11.3 $^\circ$  and 18.4 $^\circ$ .

##### iii. Powder Stability

The ratio of BDP to formoterol fumarate in the powder is 200:6 (formoterol fumarate is about 2.9% w/w). As shown from the XRD pattern, formoterol fumarate in the powder may be in amorphous state. Despite of the small formoterol concentration in the powder, it was desirable to conduct stability tests to ensure that the powder remains stable in various conditions. The stability tests were carried out by observing moisture adsorption profiles of the powder when exposed to different relative humidity levels. From FIG. 5, it can be seen that the combination powder of the invention is stable when exposed to different humidity levels, with a maximum weight increase of 0.02% when exposed to 80% relative humidity level for 24 h.

##### iv. Particle Shape and Surface Structure

Referring now to FIG. 1c, individual particles were collected on the surface of a holey carbon film TEM grid (14) connected to a vacuum (15) after particle collection. The morphology of the particles were then imaged using a field emission low voltage scanning electron microscope (FE-SEM) operated at 2 kV acceleration voltage. FIG. 6 is a scanning electron microscope image of the powder (magnification  $\times 27000$ ). It is shown that the particles are spherical with rough surfaces and diameter of about 2–3  $\mu$ m.

##### v. Chemical Analysis

The product purity was analysed using Hewlett Packard HP 1090 Liquid Chromatograph equipped with diode array detector. The column used is Hewlett-Packard Hypersil ODS, 5  $\mu$ m, 100 $\times$ 2.1 mm.

## 11

To analyse formoterol fumarate, the powder was dissolved into 25 ml of a mixture of water-methanol (25:75). The sample was then analysed using the high performance liquid chromatograph with diode array detector (wavelengths 200 nm and 214 nm), and the quantitative analyses were carried out using external standard method with four standard concentrations. Eluents used were 0.01M ammonium dihydrogen phosphate ( $\text{NH}_3$  is added to obtain pH 8) (solvent A) and acetonitrile (solvent B) with gradient elution of 40% B for 2 minutes followed by 100% B in 5 minutes. The flow rate and injection volume used were 0.4 ml/min and 5  $\mu\text{l}$ , respectively, and the oven temperature was set to 40° C.

To analyse beclomethasone dipropionate, the powder was dissolved into 25 ml of a mixture of water-methanol (25:75) and then diluted (1:50) using water-methanol (25:75). Samples were then analysed with the high performance liquid chromatograph using diode array detector (wavelength 241 nm) and quantitative analyses were carried using external standard method (four different standard concentrations). Eluents used were water (solvent A) and acetonitrile (solvent B) with gradient elution of 65% B for 2 minutes followed by 100% B in 5 minutes. The flow rate and injection volume used were 0.4 ml/min and 8  $\mu\text{l}$ , respectively, and the oven temperature was set to 40° C.

The analysis results show beclomethasone dipropionate 97.1% and formoterol fumarate 2.9%, the same as concentration of solution precursor.

## EXAMPLE 2

## Dry Inhalation Powder

	Per dose
Formoterol fumarate	6 $\mu\text{g}$
Beclomethasone dipropionate	200 $\mu\text{g}$
Lactose monohydrate Ph. Eur.	8 mg

Particles of Example 1 and part of lactose is added into a blender. The powder mixture is mixed until it is homogenous. The mixture is sieved to reduce the number of particle clusters present. Thereafter the rest of lactose is added and the powder is again mixed until it is homogenous. Powder is poured into a supply chamber of the multi-dose powder inhaler Easyhaler (Orion Corporation trademark) for a supply of 200 doses.

The invention claimed is:

1. Inhalation particles incorporating, in an unagglomerated individual particle, a combination of a  $\beta_2$ -agonist and a glucocorticosteroid in a predetermined and constant ratio.

2. Inhalation particles according to claim 1, wherein the mean mass aerodynamic diameter of said particles is about 1–5  $\mu\text{m}$ .

3. Inhalation particles according to claim 1, wherein the aerodynamic particle size distribution of said particles is about 0.5–10  $\mu\text{m}$ .

4. Inhalation particles according to claim 1, wherein the predetermined and constant ratio of the  $\beta_2$ -agonist to the glucocorticosteroid is from about 3:1 to about 1:3000.

5. Inhalation particles according to claim 4, wherein the predetermined and constant ratio of the  $\beta_2$ -agonist to the glucocorticosteroid is from about 1:5 to about 1:1000.

6. Inhalation particles according to claim 1, wherein the particles are spherical.

## 12

7. Inhalation particles according to claim 1, wherein the particles are crystalline.

8. Inhalation particles according to claim 1, wherein the particles have a rough surface.

9. Inhalation particles according to claim 1, wherein the particles are uncharged.

10. Inhalation particles according to claim 1, incorporating a combination of formoterol fumarate and beclomethasone dipropionate.

11. An inhalation composition comprising particles incorporating, in an unagglomerated individual particle, a combination of a  $\beta_2$ -agonist and a glucocorticosteroid and in a predetermined and constant ratio.

12. An inhalation composition according to claim 11 additionally comprising one or more pharmaceutically acceptable additives, diluents or carriers.

13. An inhalation composition according to claim 11 in the form of dry inhalation powder.

14. An inhalation composition according to claim 11 in the form of pressurized metered dose inhalation suspension.

15. An inhaler device comprising an inhalation composition according to claim 11.

16. A method for preparing particles incorporating, in an unagglomerated individual particle, a combination of a  $\beta_2$ -agonist and a glucocorticosteroid, comprising the steps of:

providing liquid feed stock comprising a  $\beta_2$ -agonist and a glucocorticosteroid in a predetermined ratio;

atomising said liquid feed stock to create droplets;

suspending said droplets in a carrier gas;

passing said carrier gas and droplets suspended therein through a heated tube flow reactor under predetermined residence time and temperature history; and

collecting the particles produced.

17. A method of claim 16 wherein the liquid feed stock, comprising a  $\beta_2$ -agonist and a glucocorticosteroid in a predetermined ratio, is in the form of a solution.

18. A method according to claim 16, wherein the carrier gas is selected from nitrogen gas or other inert gas.

19. A method according to claim 16, wherein the particles are collected using a particle collection selected from an electrostatic precipitator, a cyclone or a filter.

20. A method according to claim 19, wherein the particle collection system is heated to a temperature above the boiling point temperature of the solution to prevent condensation.

21. A method according to claim 16, wherein the liquid feed stock comprises formoterol fumarate and beclomethasone dipropionate as active ingredients.

22. A method according to claim 18, wherein the liquid feed stock comprises ethanol as a solvent.

23. Inhalation particles according to claim 1, wherein the aerodynamic particle size distribution of said particles is about 1–5  $\mu\text{m}$ .

24. Inhalation particles according to claim 1, wherein the predetermined and constant ratio of the  $\beta_2$ -agonist to the glucocorticosteroid is from about 1:1 to about 1:1000.

25. Inhalation particles according to claim 4, wherein the predetermined and constant ratio of the  $\beta_2$ -agonist to the glucocorticosteroid is from about 1:10 to about 1:60.

26. Inhalation particles according to claim 1, wherein at least about 90 w-% of the total weight of the particles is in crystalline form.