

Office de la Propriété Intellectuelle du Canada

Un organisme d'Industrie Canada Canadian
Intellectual Property
Office

An agency of Industry Canada

CA 2510522 A1 2005/12/28

(21) 2 510 522

(12) DEMANDE DE BREVET CANADIEN CANADIAN PATENT APPLICATION (13) A1

(22) Date de dépôt/Filing Date: 2005/06/22

(41) Mise à la disp. pub./Open to Public Insp.: 2005/12/28

(30) Priorité/Priority: 2004/06/28 (10/876,575) US

(51) Cl.Int.⁷/Int.Cl.⁷ G03G 9/08

(71) Demandeur/Applicant: XEROX CORPORATION, US

(72) Inventeurs/Inventors:

MOFFAT, KAREN A., CA;
VANBESIEN, DARYL W., CA;
AGUR, ENNO E., CA;
LIU, CHU-HENG, US;
SANDERS, DAVID J., CA


(74) Agent: SIM & MCBURNEY

(54) Titre: TONER A AGREGATION D'EMULSION A ENRICHISSEMENT DE LUSTRE ET LIBERATION DE TONER (54) Title: EMULSION AGGREGATION TONER HAVING GLOSS ENHANCEMENT AND TONER RELEASE

(57) Abrégé/Abstract:

A toner including particles of a resin, an optional colorant, and a crystalline wax, where the crystalline wax is selected from aliphatic polar amide functionalized waxes, carboxylic acid-terminated polyethylene waxes, aliphatic waxes consisting of esters of hydroxylated unsaturated fatty acids, high acid waxes, and mixtures thereof, is prepared by an emulsion aggregation process.





42

ABSTRACT OF THE DISCLOSURE

A toner including particles of a resin, an optional colorant, and a crystalline wax, where the crystalline wax is selected from aliphatic polar amide functionalized waxes, carboxylic acid-terminated polyethylene waxes, aliphatic waxes consisting of esters of hydroxylated unsaturated fatty acids, high acid waxes, and mixtures thereof, is prepared by an emulsion aggregation process.

1

EMULSION AGGREGATION TONER HAVING GLOSS ENHANCEMENT AND TONER RELEASE

BACKGROUND OF THE INVENTION

1. Field of Invention

5

10

15

20

25

This invention relates to toners and developers containing the toners for use in forming and developing images of good quality and gloss, and in particular to toners having novel wax components to provide the desired print quality and high gloss.

2. Description of Related Art

Emulsion aggregation toners are excellent toners to use in forming print and/or xerographic images in that the toners can be made to have uniform sizes and in that the toners are environmentally friendly. U.S. patents describing emulsion aggregation toners include, for example, U.S. Patents Nos. 5,370,963, 5,418,108, 5,290,654, 5,278,020, 5,308,734, 5,344,738, 5,403,693, 5,364,729, 5,346,797, 5,348,832, 5,405,728, 5,366,841, 5,496,676, 5,527,658, 5,585,215, 5,650,255, 5,650,256, 5,501,935, 5,723,253, 5,744,520, 5,763,133, 5,766,818, 5,747,215, 5,827,633, 5,853,944, 5,804,349, 5,840,462, and 5,869,215.

Two main types of emulsion aggregation toners are known. First is an emulsion aggregation process that forms acrylate based, e.g., styrene acrylate, toner particles. See, for example, U.S. Patent No. 6,120,967, incorporated herein by reference in its entirety, as one example of such a process. Second is an emulsion aggregation process that forms polyester, e.g., sodio sulfonated polyester. See, for example, U.S. Patent No. 5,916,725, incorporated herein by reference in its entirety, as one example of such a process.

Emulsion aggregation techniques typically involve the formation of an emulsion latex of the resin particles, which particles have a small size of from, for example, about 5 to about 500 nanometers in diameter, by heating the resin, optionally with solvent if needed, in water, or by making a latex in water using an emulsion polymerization. A colorant dispersion, for example of a pigment dispersed in water, optionally also with additional resin, is separately formed. The colorant dispersion is added to the emulsion latex mixture, and an aggregating agent or complexing agent is

then added to form aggregated toner particles. The aggregated toner particles are heated to enable coalescence/fusing, thereby achieving aggregated, fused toner particles.

U.S. Patent No. 5,462,828 describes a toner composition that includes a styrene/n-butyl acrylate copolymer resin having a number average molecular weight of less than about 5,000, a weight average molecular weight of from about 10,000 to about 40,000 and a molecular weight distribution of greater than 6 that provides excellent gloss and high fix properties at a low fusing temperature.

What is still desired is a styrene acrylate type emulsion aggregation toner that can achieve excellent print quality, particularly gloss, for all colors.

10

15

20

25

30

SUMMARY OF THE INVENTION

The present invention comprises a toner having a specified wax that enable the toner to achieve the objects of the invention, mainly to achieve a toner exhibiting excellent gloss properties.

In embodiments, the present invention provides a toner comprising particles of a resin, an optional colorant, and a crystalline wax, wherein the crystalline wax is selected from the group consisting of aliphatic polar amide functionalized waxes, carboxylic acid-terminated polyethylene waxes, aliphatic waxes consisting of esters of hydroxylated unsaturated fatty acids, high acid waxes, and mixtures thereof, and wherein said toner particles are prepared by an emulsion aggregation process.

In embodiments, the present invention also provides methods for making such toners.

BRIEF DESCRIPTION OF THE DRAWINGS

A more complete understanding of the present invention can be obtained by reference to the accompanying drawings wherein:

Figure 1 illustrates an embodiment of a high pressure wax homogenization process.

Figure 2 is a graph relating 75 degree gloss (ggu) to external heat roll (EHR) temperature for various toner compositions described in Example 1.

Figure 3 is a graph relating 75 degree gloss to fusing temperature for various toner compositions described in Example 1.

Figure 4 is a graph relating 75 degree gloss (ggu) to external heat roll (EHR) temperature for various toner compositions described in Example 2.

Figure 5 is a graph relating 75 degree gloss to fusing temperature for various toner compositions described in Example 2.

Figure 6 is a graph relating 75 degree gloss (ggu) to external heat roll (EHR) temperature for various toner compositions described in Example 3.

Figure 7 is a graph relating 75 degree gloss to fusing temperature for various toner compositions described in Example 3.

Figure 8 is a graph relating 75 degree gloss (ggu) to external heat roll (EHR) temperature for various toner compositions described in Example 4.

Figures 9a and 9b are graphs relating 75 degree gloss to fusing temperature for various toner compositions described in Example 4.

15

10

DETAILED DESCRIPTION OF EXEMPLARY EMBODIMENTS

The toner of the invention is comprised of toner particles comprised of at least a latex emulsion polymer resin and a colorant dispersion. The toner particles preferably also include at least a wax dispersion, a coagulant and a colloidal silica.

20

25

30

Illustrative examples of specific latex for resin, polymer or polymers selected for the toner of the present invention include, for example, poly(styrene-alkyl acrylate), poly(styrene-1,3-diene), poly(styrene-alkyl methacrylate), poly(styrene-alkyl acrylate-acrylic acid), poly(styrene-1,3-diene-acrylic acid), poly(styrene-alkyl methacrylate-acrylic acid), poly(alkyl methacrylate-alkyl acrylate), poly(alkyl methacrylate-aryl acrylate), poly(aryl methacrylate-alkyl acrylate), poly(alkyl methacrylate-acrylic acid), poly(styrene-alkyl acrylate-acrylonitrile-acrylic acid), poly(styrene-1,3-diene-acrylonitrile-acrylic acid), poly(alkyl acrylate-acrylonitrile-acrylic acid), poly(styrene-butadiene), poly(methylstyrene-butadiene), poly(methyl methacrylate-butadiene), poly(ethyl methacrylate-butadiene), poly(propyl methacrylate-butadiene), poly(butyl methacrylate-butadiene), poly(ethyl acrylate-butadiene), poly(propyl acrylate-butadiene), poly(butyl acrylate-butadiene), poly(styrene-isoprene), poly(methylstyrene-isoprene),

poly(methyl methacrylate-isoprene), poly(ethyl methacrylate-isoprene), poly(propyl methacrylate-isoprene), poly(butyl methacrylate-isoprene), poly(methyl acrylate-isoprene), poly(ethyl acrylate-isoprene), poly(propyl acrylate-isoprene), and poly(butyl acrylate-isoprene); poly(styrene-propyl acrylate), poly(styrene-butyl acrylate), poly(styrene-butadiene-acrylic acid), poly(styrene-butadiene-acrylic acid), poly(styrene-butyl acrylate-acrylic acid), and other similar polymers or other similar known polymers.

5

10

15

20

25

30

As the latex emulsion polymer of the invention toner, preferably a styrene-alkyl acrylate is used. More preferably, the styrene-alkyl acrylate is a styrene/n-butyl acrylate copolymer resin, and most preferably, a styrene-butyl acrylate beta-carboxyethyl acrylate polymer.

The latex polymer is preferably present in an amount of from about 70 to about 95% by weight of the toner particles (i.e., toner particles exclusive of external additives) on a solids basis, preferably from about 75 to about 85% by weight of the toner.

The monomers used in making the selected polymer are not limited, and the monomers utilized may include any one or more of, for example, styrene, acrylates such as methacrylates, butylacrylates, β -carboxy ethyl acrylate (β -CEA), etc., butadiene, isoprene, acrylic acid, methacrylic acid, itaconic acid, acrylonitrile, benzenes such as divinylbenzene, etc., and the like. Known chain transfer agents, for example dodecanethiol or carbon tetrabromide, can be utilized to control the molecular weight properties of the polymer. Any suitable method for forming the latex polymer from the monomers may be used without restriction.

Various suitable colorants can be employed in toners of the present invention, including suitable colored pigments, dyes, and mixtures thereof, including carbon black, such as REGAL 330 carbon black, acetylene black, lamp black, aniline black, Chrome Yellow, Zinc Yellow, SICOFAST Yellow, SUNBRITE Yellow, LUNA Yellow, NOVAPERM Yellow, Chrome Orange, BAYPLAST Orange, Cadmium Red, LITHOL Scarlet, HOSTAPERM Red, FANAL PINK, HOSTAPERM Pink, LUPRETON Pink, LITHOL Red, RHODAMINE Lake B, Brilliant Carmine,

HELIOGEN Blue, HOSTAPERM Blue, NEOPAN Blue, PV Fast Blue, CINQUASSI Green, HOSTAPERM Green, titanium dioxide, cobalt, nickel, iron powder, SICOPUR 4068 FF, and iron oxides such as MAPICO Black (Columbia) NP608 and NP604 (Northern Pigment), BAYFERROX 8610 (Bayer), M08699 (Mobay), TMB-100 (Magnox), mixtures thereof and the like.

The colorant, preferably carbon black, cyan, magenta and/or yellow colorant, is incorporated in an amount sufficient to impart the desired color to the toner. In general, pigment or dye is employed in an amount ranging from about 2% to about 35% by weight of the toner particles on a solids basis, preferably from about 5% to about 25% by weight and more preferably from about 5 to about 15% by weight.

10

15

20

25

30

Of course, as the colorants for each color are different, the amount of colorant present in each type of color toner typically is different. For example, in preferred embodiments of the present invention, a cyan toner may include about 3 to about 11% by weight of colorant (preferably Pigment Blue 15:3 from SUN), a magenta toner may include about 3 7 to about 15% by weight of colorant (preferably Pigment Red 122, Pigment Red 185, Pigment Red 238 and/or mixtures thereof), a yellow toner may include about 3 to about 10% by weight of colorant (preferably Pigment Yellow 74), and a black toner may include about 3 to about 10% by weight of colorant (preferably carbon black).

In addition to the latex polymer binder and the colorant, the toners of the invention also contain a wax dispersion. The wax is added to the toner formulation in order to aid toner release from the fuser roll, particularly in low oil or oil-less fuser designs. For emulsion/aggregation (E/A) toners, for example styrene-acrylate E/A toners, it has been conventional to add linear polyethylene waxes such as the POLYWAX® line of waxes available from Baker Petrolite to the toner composition. POLYWAX® 725 has been a particularly preferred wax for use with styrene-acrylate E/A toners.

However, in order to provide improved toner compositions, such as exhibiting improved gloss or print properties, compositional improvements are required. The present inventors have discovered that the use of other wax materials, in place of conventional wax materials, provides these improved results.

In embodiments of the present invention, a wax dispersion including one or more crystalline waxes is used as the wax component. By "crystalline polymeric waxes" it is meant that a wax material contains an ordered array of polymer chains within a polymer matrix which can be characterized by a crystalline melting point transition temperature; Tm. The crystalline melting temperature is the melting temperature of the crystalline domains of a polymer sample. This is in contrast to the glass transition temperature, Tg which characterizes the temperature at which polymer chains begin to flow for the amphorous regions within a polymer. Preferably, in embodiments of the present invention, the toner composition as a whole, or at least the wax component thereof, does not contain an unmodified polyethylene wax (e.g., a non-carboxylic acid-terminated polyethylene wax), and particularly does not contain a crystalline polyethylene wax, other than a carboxylic acid-terminated polyethylene wax. Thus, in embodiments, the toner composition as a whole, or at least the wax component thereof, is substantially free or preferably completely free of any unmodified polyethylene wax, or at least of any crystalline polyethylene wax other than a carboxylic acid-terminated polyethylene wax.

10

15

20

25

30

Preferred crystalline polymeric waxes include one or more materials selected from the group of aliphatic polar amide functionalized waxes, carboxylic acid-terminated polyethylene waxes, aliphatic waxes consisting of esters of hydroxylated unsaturated fatty acids, high acid waxes, and mixtures thereof. By "high acid waxes" it is meant a wax material that has a high acid content.

Suitable examples of crystalline aliphatic polar amide functionalized waxes include, but are not limited to, stearamides, lauramides, palmitamides, behenamides, oleamides, erucamides, recinoleamides, mixtures thereof, and the like. Specific examples of suitable crystalline aliphatic polar amide functionalized waxes include, but are not limited to, stearyl stearamide, behenyl behenamide, stearyl behenamide, behenyl stearamide, oleyl oleamide, oleyl stearamide, stearyl oleamide, stearyl erucamide, oleyl palmitamide; methylol amide such as methylol stearamide or methylol behenamide, mixtures thereof, and the like. For example, a particularly suitable crystalline aliphatic polar amide functionalized wax is the stearyl stearamide wax KEMAMIDE® S-180, available from Witco, USA. Other types of nitrogen containing functional group waxes suitable for use in the present invention include

amines, imides and quaternary amines, such as those available as JONCRYL® waxes from Johnson Diversey Inc.

Suitable examples of carboxylic acid-terminated polyethylene waxes include, but are not limited to, mixtures of carbon chains with the structure CH_3 -(CH_2)_{n-2}-COOH, where there is a mixture of chain lengths, n, where the average chain length, is preferably in the range of about 16 to about 50, and linear low molecular weight polyethylene, of similar average chain length. Suitable examples of such waxes include, but are not limited to, UNICID® 550 with n approximately equal to 40, and UNICID® 700 with n approximately equal to 50. For example, a particularly suitable crystalline carboxylic acid-terminated polyethylene wax is UNICID® 550, available from Baker Petrolite, USA. UNICID® 550 consists of 80% carboxylic acid functionality with the remainder a linear, low molecular weight polyethylene of a similar chain length, and an acid value of 72 mg KOH/gram and melting point of about 101°C. Other suitable waxes have a structure CH₃-(CH₂)_n-COOH, such as hexadecanoic or palmitic acid with n=16, heptadecanoic or margaric or daturic acid with n=17, octadecanoic or stearic acid with n=18:0, eicosanoic or arachidic acid with n=20, docosanoic or behenic acid with n=22, tetracosanoic or lignoceric acid with n=24, hexacosanoic or cerotic acid with n=26, heptacosanoic or carboceric acid with n=27, octacosanoic or montanic acid with n=28, triacontanoic or melissic acid with n=30, dotriacontanoic or lacceroic acid with n=32, tritriacontanoic or ceromelissic or psyllic acid, with n=33, tetratriacontanoic or geddic acid with n=34, pentatriacontanoic or ceroplastic acid with n=35.

10

15

20

25

30

Suitable examples of crystalline aliphatic waxes consisting of esters of hydroxylated unsaturated fatty acids, are those having a carbon chain length of from about 8 or less to about 20 or more or about 30 or more, more preferably from about 10 to about 16. For the crystalline aliphatic waxes consisting of esters of hydroxylated unsaturated fatty acids, any suitable chain length can be employed, so long as the functionality remains present and effective. In one particular embodiment, for example, the crystalline aliphatic waxes consisting of esters of hydroxylated unsaturated fatty acids have a chain length of preferably from about 10 to about 16. Especially preferred are those having a carbon chain length of approximately 12 units, such as from about 11 to about 13. Examples of such waxes include, but are not

limited to, carnauba wax and the like. For example, a particularly suitable crystalline aliphatic waxes consisting of esters of hydroxylated unsaturated fatty acids is RC-160 carnauba wax, available from Toa Kasei, Japan.

Suitable examples of high acid waxes are acid waxes having a high acid content of, for example, greater than about 50% acid functionalized. Preferred high acid waxes are linear long chain aliphatic high acid waxes where a long chain is a chain with 16 or more CH₂ units. Linear, saturated, aliphatic waxes, preferably having an end-functionalized carboxylic acid, are particularly preferred. Also preferred are high acid waxes with acid content of greater than about 50 mg KOH/g. In embodiments, the high acid wax is preferably a montan wax, n-octacosanoic acid, CH₃(CH₂)₂₆-COOH, about 100% acid functionalized. Examples of such suitable montan waxes include, but are not limited to, LICOWAX® S, manufactured by Clariant, GmbH (Germany) with an acid value of 127 to 160 mg KOH/g, LICOWAX® SW with acid value of 115-135, LICOWAX® UL with an acid value of 100-115 mg KOH/g and LICOWAX® X101 with acid value 130-150. Other suitable high acid waxes include partly esterified montanic acid waxes, where some of the acid termination have been esterified, such as LICOWAX® U with an acid value of 72-92 mg KOH/g. Such high acid waxes are preferred, because it has been found that they provide adequate charge stability to the toner composition, since most emulsion/aggregation toner compositions have a high acid content (due to their constituent resin materials) and thus a resultant negative charge.

10

15

20

25

30

To incorporate the wax into the toner, it is preferable for the wax to be in the form of an aqueous emulsion or dispersion of solid wax in water, where the solid wax particle size is usually in the range of from about 100 to about 500 nm.

The toners may contain from, for example, about 3 to about 15% by weight of the toner, on a dry basis, of the wax. Preferably, the toners contain from about 5 to about 15% by weight of the wax.

In addition, the toners of the invention may also optionally contain a coagulant and a flow agent such as colloidal silica. Suitable optional coagulants include any coagulant known or used in the art, including the well known coagulants polyaluminum chloride (PAC) and/or polyaluminum sulfosilicate (PASS). A preferred coagulant is polyaluminum chloride. The coagulant is present in the toner

particles, exclusive of external additives and on a dry weight basis, in amounts of from 0 to about 3% by weight of the toner particles, preferably from about greater than 0 to about 2% by weight of the toner particles. The flow agent, if present, may be any colloidal silica such as SNOWTEX OL colloidal silica, SNOWTEX OS colloidal silica, and/or mixtures thereof. The colloidal silica is present in the toner particles, exclusive of external additives and on a dry weight basis, in amounts of from 0 to about 15% by weight of the toner particles, preferably from about greater than 0 to about 10% by weight of the toner particles.

The toner may also include additional known positive or negative charge additives in effective suitable amounts of, for example, from about 0.1 to about 5 weight percent of the toner, such as quaternary ammonium compounds inclusive of alkyl pyridinium halides, bisulfates, organic sulfate and sulfonate compositions such as disclosed in U.S. Patent No. 4,338,390, cetyl pyridinium tetrafluoroborates, distearyl dimethyl ammonium methyl sulfate, aluminum salts or complexes, and the like.

10

15

20

25

30

Also, in preparing the toner by the emulsion aggregation procedure, one or more surfactants may be used in the process. Suitable surfactants include anionic, cationic and nonionic surfactants.

Anionic surfactants include sodium dodecylsulfate (SDS), sodium dodecyl benzene sulfonate, sodium dodecylnaphthalene sulfate, dialkyl benzenealkyl, sulfates and sulfonates, abitic acid, and the NEOGEN brand of anionic surfactants. An example of a preferred anionic surfactant is NEOGEN RK available from Daiichi Kogyo Seiyaku Co. Ltd., or TAYCA POWER BN2060 from Tayca Corporation (Japan), which consists primarily of branched sodium dodecyl benzene sulphonate.

Examples of cationic surfactants include dialkyl benzene alkyl ammonium chloride, lauryl trimethyl ammonium chloride, alkylbenzyl methyl ammonium chloride, alkyl benzyl dimethyl ammonium bromide, benzalkonium chloride, cetyl pyridinium bromide, C₁₂, C₁₅, C₁₇ trimethyl ammonium bromides, halide salts of quaternized polyoxyethylalkylamines, dodecyl benzyl triethyl ammonium chloride, MIRAPOL and ALKAQUAT available from Alkaril Chemical Company, SANISOL (benzalkonium chloride), available from Kao Chemicals, and the like. An example of

a preferred cationic surfactant is SANISOL B-50 available from Kao Corp., which consists primarily of benzyl dimethyl alkonium chloride.

5

10

15

20

25

30

Examples of nonionic surfactants include polyvinyl alcohol, polyacrylic acid, methalose, methyl cellulose, ethyl cellulose, propyl cellulose, hydroxy ethyl cellulose, carboxy methyl cellulose, polyoxyethylene cetyl ether, polyoxyethylene lauryl ether, polyoxyethylene octyl ether, polyoxyethylene octylphenyl ether, polyoxyethylene oleyl ether, polyoxyethylene sorbitan monolaurate, polyoxyethylene stearyl ether, polyoxyethylene nonylphenyl ether, dialkylphenoxy poly(ethyleneoxy) ethanol, available from Rhone-Poulenc Inc. as IGEPAL CA-210, IGEPAL CA-520, IGEPAL CA-720, IGEPAL CO-890, IGEPAL CO-720, IGEPAL CO-290, IGEPAL CA-210, ANTAROX 890 and ANTAROX 897. An example of a preferred nonionic surfactant is ANTAROX 897 available from Rhone-Poulenc Inc., which consists primarily of alkyl phenol ethoxylate.

Any suitable emulsion aggregation procedure may be used in forming the emulsion aggregation toner particles without restriction. These procedures typically include the basic process steps of at least aggregating an emulsion containing binder, one or more colorants, optionally one or more surfactants, optionally a wax emulsion, optionally a coagulant and one or more additional optional additives to form aggregates, subsequently coalescing or fusing the aggregates, and then recovering, optionally washing and optionally drying the obtained emulsion aggregation toner particles.

An example emulsion/aggregation/coalescing process preferably includes forming a mixture of latex binder, colorant dispersion, wax emulsion, optional coagulant and deionized water in a vessel. The mixture is then stirred using a homogenizer until homogenized and then transferred to a reactor where the homogenized mixture is heated to a temperature of, for example, about 50°C and held at such temperature for a period of time to permit aggregation of toner particles to the desired size. Once the desired size of aggregated toner particles is achieved, the pH of the mixture is adjusted in order to inhibit further toner aggregation. The toner particles are further heated to a temperature of, for example, about 90°C and the pH lowered in order to enable the particles to coalesce and spherodize. The heater is then turned off and the reactor mixture allowed to cool to room temperature, at which point

the aggregated and coalesced toner particles are recovered and optionally washed and dried.

Most preferably, following coalescence and aggregation, the particles are wet sieved through an orifice of a desired size in order to remove particles of too large a size, washed and treated to a desired pH, and then dried to a moisture content of, for example, less than 1% by weight.

5

10

15

20

25

30

The toner particles of the invention are preferably made to have the following physical properties when no external additives are present on the toner particles.

The toner particles preferably have a surface area, as measured by the well known BET method, of about 1.3 to about 6.5 m²/g. More preferably, for cyan, yellow and black toner particles, the BET surface area is less than 2 m²/g, preferably from about 1.4 to about 1.8 m²/g, and for magenta toner, from about 1.4 to about 6.3 m²/g.

It is also desirable to control the toner particle size and limit the amount of both fine and coarse toner particles in the toner. In a preferred embodiment, the toner particles have a very narrow particle size distribution with a lower number ratio geometric standard deviation (GSD) of approximately 1.15 to approximately 1.30, more preferably approximately less than 1.25. The toner particles of the invention also preferably have a size such that the upper geometric standard deviation (GSD) by volume is in the range of from about 1.15 to about 1.30, preferably from about 1.18 to about 1.24, more preferably less than 1.25. These GSD values for the toner particles of the invention indicate that the toner particles are made to have a very narrow particle size distribution.

Shape factor is also an important control process parameter associated with the toner being able to achieve optimal machine performance. The toner particles of the invention preferably have a shape factor of about 105 to about 170, more preferably about 110 to about 160, SF1*a. Scanning electron microscopy (SEM) and Image Analysis (IA) is used to determine the shape factor of the toners. The average particle shapes are quantified by employing the following shape factor (SF1*a) formula: SF1*a = $100\pi d^2/(4A)$, where A is the area of the particle and d is its major axis. A perfectly circular or spherical particle has a shape factor of exactly 100. The shape factor SF1*a increases as the shape becomes more irregular or elongated in shape with

a higher surface area. In addition to measuring shape factor SF, another metric to measure particle circularity is being used on a regular basis. This is a faster method to quantify the particle shape. The instrument used is an FPIA-2100 manufactured by Sysmex. For a completely circular sphere the circularity would be 1.000. The toner particles of the invention have circularity of about 0.920 to 0.990 and preferably from about 0.940 to about 0.975.

5

10

15

20

25

30

In addition to the foregoing, the toner particles of the present invention also have the following rheological and flow properties. First, the toner particles preferably have the following molecular weight values, each as determined by gel permeation chromatography (GPC) as known in the art. The binder of the toner particles preferably has a weight average molecular weight, Mw of from about 15,000 daltons to about 90,000 daltons.

Overall, the toner particles of the invention preferably have a weight average molecular weight (Mw) in the range of about 17,000 to about 60,000 daltons, a number average molecular weight (Mn) of about 9,000 to about 18,000 daltons, and a MWD of about 2.1 to about 10. MWD is a ratio of the Mw to Mn of the toner particles, and is a measure of the polydispersity, or width, of the polymer molecular weight distribution. For cyan and yellow toners, the toner particles preferably exhibit a weight average molecular weight (Mw) of about 22,000 to about 38,000 daltons, a number average molecular weight (Mn) of about 9,000 to about 13,000 daltons, and a MWD of about 2.2 to about 10. For black and magenta, the toner particles preferably exhibit a weight average molecular weight (Mw) of about 22,000 to about 38,000 daltons, a number average molecular weight (Mm) of about 9,000 to about 13,000 daltons, a number average molecular weight (Mn) of about 9,000 to about 13,000 daltons, and a MWD of about 2.2 to about 10.

Further, the toners of the present invention preferably have a specified relationship between the molecular weight of the latex binder and the molecular weight of the toner particles obtained following the emulsion aggregation procedure. As understood in the art, the binder undergoes crosslinking during processing, and the extent of crosslinking can be controlled during the process. The relationship can best be seen with respect to the molecular peak values for the binder. Molecular peak is the value that represents the highest peak of the weight average molecular weight. In the present invention, the binder preferably has a molecular peak (Mp) in the range of

from about 22,000 to about 30,000 daltons, preferably from about 22,500 to about 29,000 daltons. The toner particles prepared from such binder also exhibit a high molecular peak, for example of about 23,000 to about 32,000 daltons, preferably about 23,500 to about 31,500 daltons, indicating that the molecular peak is driven by the properties of the binder rather than another component such as the colorant.

5

10

15

20

25

30

Another property of the toners of the present invention is the cohesivity of the particles prior to inclusion of any external additives. The greater the cohesivity, the less the toner particles are able to flow. The cohesivity of the toner particles, prior to inclusion of any external additives, may be from, for example, about 55 to about 98% for all colors of the toner. Cohesivity was measured by placing a known mass of toner, two grams, on top of a set of three screens, for example with screen meshes of 53 microns, 45 microns, and 38 microns in order from top to bottom, and vibrating the screens and toner for a fixed time at a fixed vibration amplitude, for example for 90 seconds at a 1 millimeter vibration amplitude. A device to perform this measurement is a Hosokawa Powders Tester, available from Micron Powders Systems. The toner cohesion value is related to the amount of toner remaining on each of the screens at the end of the time, and is calculated by the formula: % cohesion = 50*A+30*B+10*C, where A, B and C are respectively the weight of the toner remaining on the 53 microns, 45 microns, and 38 microns screens, respectively. A cohesion value of 100% corresponds to all of the toner remaining on the top screen at the end of the vibration step and a cohesion value of zero corresponds to all of the toner passing through all three screens, that is, no toner remaining on any of the three screens at the end of the vibration step. The higher the cohesion value, the lesser the flowability of the toner.

Finally, the toner particles preferably have a bulk density of from about 0.22 to about 0.34 g/cc and a compressibility of from about 33 to about 51.

The toner particles of the invention are preferably blended with external additives following formation. Any suitable surface additives may be used in the present invention. Most preferred in the present invention are one or more of SiO₂, metal oxides such as, for example, TiO₂ and aluminum oxide, and a lubricating agent such as, for example, a metal salt of a fatty acid (e.g., zinc stearate (ZnSt), calcium stearate) or long chain alcohols such as UNILIN 700, as external surface additives. In

general, silica is applied to the toner surface for toner flow, tribo enhancement, admix control, improved development and transfer stability and higher toner blocking temperature. TiO₂ is applied for improved relative humidity (RH) stability, tribo control and improved development and transfer stability. Zinc stearate is preferably also used as an external additive for the toners of the invention, the zinc stearate providing lubricating properties. Zinc stearate provides developer conductivity and tribo enhancement, both due to its lubricating nature. In addition, zinc stearate enables higher toner charge and charge stability by increasing the number of contacts between toner and carrier particles. Calcium stearate and magnesium stearate provide similar functions. Most preferred is a commercially available zinc stearate known as Zinc Stearate L, obtained from Ferro Corporation. The external surface additives can be used with or without a coating.

Most preferably, the toners contain from, for example, about 0.1 to about 5 weight percent titania, about 0.1 to about 8 weight percent silica and about 0.1 to about 4 weight percent zinc stearate.

10

15

20

25

30

The toner particles of the invention can optionally be formulated into a developer composition by mixing the toner particles with carrier particles. Illustrative examples of carrier particles that can be selected for mixing with the toner composition prepared in accordance with the present invention include those particles that are capable of triboelectrically obtaining a charge of opposite polarity to that of the toner particles. Accordingly, in one embodiment the carrier particles may be selected so as to be of a negative polarity in order that the toner particles that are positively charged will adhere to and surround the carrier particles. Illustrative examples of such carrier particles include iron, iron alloys steel, nickel, iron ferrites, including ferrites that incorporate strontium, magnesium, manganese, copper, zinc, and the like, magnetites, and the like. Additionally, there can be selected as carrier particles nickel berry carriers as disclosed in U.S. Patent No. 3,847,604, the entire disclosure of which is totally incorporated herein by reference, comprised of nodular carrier beads of nickel, characterized by surfaces of reoccurring recesses and protrusions thereby providing particles with a relatively large external area. Other carriers are disclosed in U.S. Patents Nos. 4,937,166 and 4,935,326, the disclosures of which are totally incorporated herein by reference.

The selected carrier particles can be used with or without a coating, the coating generally being comprised of acrylic and methacrylic polymers, such as methyl methacrylate, acrylic and methacrylic copolymers with fluoropolymers or with monoalkyl or dialklyamines, fluoropolymers, polyolefins, polystrenes such as polyvinylidene fluoride resins, terpolymers of styrene, methyl methacrylate, and a silane, such as triethoxy silane, tetrafluoroethylenes, other known coatings and the like.

The carrier particles can be mixed with the toner particles in various suitable combinations. The toner concentration is usually about 2% to about 10% by weight of toner and about 90% to about 98% by weight of carrier. However, one skilled in the art will recognize that different toner and carrier percentages may be used to achieve a developer composition with desired characteristics.

Toners of the present invention can be used in known electrostatographic imaging methods. Thus for example, the toners or developers of the invention can be charged, e.g., triboelectrically, and applied to an oppositely charged latent image on an imaging member such as a photoreceptor or ionographic receiver. The resultant toner image can then be transferred, either directly or via an intermediate transport member, to a support such as paper or a transparency sheet. The toner image can then be fused to the support by application of heat and/or pressure, for example with a heated fuser roll.

It is envisioned that the toners of the present invention may be used in any suitable procedure for forming an image with a toner, including in applications other than xerographic applications.

Specific embodiments of the invention will now be described in detail. These Examples are intended to be illustrative, and the invention is not limited to the materials, conditions, or process parameters set forth in these embodiments. All parts and percentages are by weight unless otherwise indicated.

EXAMPLES

30 Comparative Example 1:

10

15

20

25

A conventional styrene/n-butyl acrylate emulsion/aggregation toner containing 9% by weight polyethylene wax (POLYWAX® 725) is prepared as follows.

Step 1: Preparation of Latex Emulsion A. A latex emulsion comprised of polymer particles generated from the semi-continuous emulsion polymerization of styrene, n-butyl acrylate and beta carboxy ethyl acrylate (β-CEA) is prepared as follows. This reaction formulation is prepared in a 2 liter Buchi reactor, which can be readily scaled-up to a 100 gallon scale or larger by adjusting the quantities of materials accordingly.

10

15

20

25

30

A surfactant solution consisting of 0.9 grams Dowfax 2A1 (anionic emulsifier) and 514 grams de-ionized water is prepared by mixing for 10 minutes in a stainless steel holding tank. The holding tank is then purged with nitrogen for 5 minutes before transferring into the reactor. The reactor is then continuously purged with nitrogen while being stirred at 300 RPM. The reactor is then heated up to 76°C at a controlled rate and held constant. In a separate container, 8.1 grams of ammonium persulfate initiator is dissolved in 45 grams of de-ionized water. Also in a second separate container, the monomer emulsion is prepared in the following manner. 426.6 grams of styrene, 113.4 grams of n-butyl acrylate and 16.2 grams of β-CEA, 11.3 grams of 1dodecanethiol, 1.89 grams of ADOD, 10.59 grams of Dowfax (anionic surfactant), and 257 grams of deionized water are mixed to form an emulsion. The ratio of styrene monomer to n-butyl acrylate monomer by weight is 79 to 21 percent. One percent of the above emulsion is then slowly fed into the reactor containing the aqueous surfactant phase at 76°C to form the "seeds" while being purged with nitrogen. The initiator solution is then slowly charged into the reactor and after 20 minutes the rest of the emulsion is continuously fed in using metering pumps. Once all the monomer emulsion is charged into the main reactor, the temperature is held at 76°C for an additional 2 hours to complete the reaction. Full cooling is then applied and the reactor temperature is reduced to 35°C. The product is collected into a holding tank after filtration through a 1 micron filter bag. After drying a portion of the latex the molecular properties are measured to be Mw = 24,751, Mn = 8,245 and the onset Tg is 51.46°C. The average particle size of the latex as measured by Disc Centrifuge is 203 nanometers and residual monomer as measured by GC as < 50 ppm for styrene and < 100 ppm for n-butyl acrylate. This latex is used to prepare emulsion/aggregation toner particles as described below.

Step 2: Preparation of toner particles from Latex Emulsion A containing 9% POLYWAX® 725. Into a 4 liter glass reactor equipped with an overhead stirrer and heating mantle is dispersed 639.9 grams of the above Latex Emulsion A having a 41.76 percent solids content, 135.53 grams of POLYWAX® 725 dispersion having a solids content of 30.63 percent, 92.6 grams of a Blue Pigment PB15:3 dispersion having a solids content of 26.49 percent into 1462.9 grams of water with high shear stirring by means of a polytron. To this mixture is added 54 grams of a coagulant solution consisting of 10 weight percent poly(aluminium chloride), PAC and 90 wt. % 0.02M HNO₃ solution. The PAC solution is added drop-wise at low rpm and as the viscosity of the pigmented latex mixture increases the rpm of the polytron probe also increases to 5,000 rpm for a period of 2 minutes. This produces a flocculation or heterocoagulation of gelled particles consisting of nanometer sized latex particles, 9% wax and 5% pigment for the core of the particles. The pigmented latex/wax slurry is heated at a controlled rate of 0.5 C/minute up to approximately 52°C and held at this temperature or slightly higher to grow the particles to approximately 5.0 microns. Once the average particle size of 5.0 microns is achieved, 308.9 grams of the Latex Emulsion A is then introduced into the reactor while stirring. After an additional 30 minutes to 1 hour the particle size measured is 5.7 microns with a GSD of 1.20. The pH of the resulting mixture is then adjusted from 2.0 to 7.0 with aqueous base solution of 4 percent sodium hydroxide and allowed to stir for an additional 15 minutes. Subsequently, the resulting mixture is heated to 93°C at 1.0°C per minute and the particle size measured is 5.98 microns with a GSD by volume of 1.22 and GSD by number of 1.22. The pH is then reduced to 5.5 using a 2.5 percent Nitric acid solution. The resultant mixture is then allowed to coalesce for 2 hrs at a temperature of 93°C. The morphology of the particles is smooth and "potato" shape. The final particle size after cooling but before washing is 5.98 microns with a GSD by volume of 1.21. The particles are washed 6 times, where the 1st wash is conducted at pH of 10 at 63°C, followed by 3 washes with deionized water at room temperature, one wash carried out at a pH of 4.0 at 40°C, and finally the last wash with deionized water at room temperature. The final average particle size of the dried particles is 5.77

10

15

20

25

30

microns with $GSD_v = 1.21$ and $GSD_n = 1.25$. The glass transition temperature of this sample is measured by DSC and found to have Tg(onset) = 49.4°C.

The particles are dried blended with a standard additive package consisting of silicon dioxide RY50 from Nippon Aerosil, titanium dioxide JMT2000 from Tayca, silicon dioxide X-24 from Shin-Etsu, EA latex particles of 1-5 micron size and shape factor of 134 and UNILIN® wax particles from Baker-Petrolite to produce a free flowing toner. Then 805 grams of developer is prepared at 5% toner concentration by weight using 76.5 grams of this toner and 773.5 grams of 35 micron Xerox DocuColor 2240 carrier. The developer is conditioned overnight in A-zone and C-zone. The developer is evaluated in a Sfida Mark 3 belt fuser 2.1 RAM system operating at a print speed of 60 PPM and fusing speed of 80 PPM.

Comparative Example 2:

10

15

25

30

Similarly, the aggregation/coalescence process of Comparative Example 1 is scaled up to a 20-gallon scale using this Latex Emulsion A. Two 20-gallon aggregation/coalescence runs for cyan toner particles are performed producing 15 kilograms of dried toner particles. This sample is of similar fusing performance as the toner particles of Comparative Example 1.

20 Comparative Example 3:

A conventional styrene/n-butyl acrylate emulsion/aggregation toner containing 9% by weight polyethylene wax (POLYWAX® 725) is prepared as follows.

Step 1: A second latex emulsion (denoted Latex Emulsion B) comprised of polymer particles generated from the semi-continuous emulsion polymerization of styrene, n-butyl acrylate and β -carboxy ethyl acrylate (β -CEA) is prepared as follows. This reaction formulation is prepared in a 2 liter Buchi reactor, which can be readily scaled-up to a 100 gallon scale or larger by adjusting the quantities of materials accordingly.

A surfactant solution consisting of 0.8 grams Dowfax 2A1 (anionic emulsifier) and 514 grams de-ionized water is prepared by mixing for 10 minutes in a stainless steel holding tank. The holding tank is then purged with nitrogen for 5 minutes before transferring into the reactor. The reactor is then continuously purged with nitrogen

while being stirred at 300 RPM. The reactor is then heated up to 76°C at a controlled rate and held constant. In a separate container, 8.1 grams of ammonium persulfate initiator is dissolved in 45 grams of de-ionized water. Also in a second separate container, the monomer emulsion is prepared in the following manner. 442.8 grams of styrene, 97.2 grams of n-butyl acrylate and 16.2 grams of \beta-CEA, 11.88 grams of 1dodecanethiol, 1.89 grams of ADOD, 10.69 grams of Dowfax (anionic surfactant), and 257 grams of deionized water are mixed to form an emulsion. The ratio of styrene monomer to n-butyl acrylate monomer by weight is 82 to 18 percent. One percent of the above emulsion is then slowly fed into the reactor containing the aqueous surfactant phase at 76°C to form the "seeds" while being purged with nitrogen. The initiator solution is then slowly charged into the reactor and after 20 minutes the rest of the emulsion is continuously fed in using metering pumps. Once all the monomer emulsion is charged into the main reactor, the temperature is held at 76°C for an additional 2 hours to complete the reaction. Full cooling is then applied and the reactor temperature is reduced to 35°C. The product is collected into a holding tank after filtration through a 1 micron filter bag. After drying a portion of the latex the molecular properties are measured to be Mw = 19271, Mn = 8106 and the onset Tg is 53.24°C. The average particle size of the latex as measured by Disc Centrifuge is 238 nanometers and residual monomer as measured by GC as < 50 ppm for styrene and < 100 ppm for n-butyl acrylate. This latex is used to prepare emulsion/aggregation toner particles as described below.

10

15

20

25

30

Step 2: Preparation of emulsion/aggregation toner particles from Latex Emulsion B containing 9% POLYWAX® 725. Into a 4 liter glass reactor equipped with an overhead stirrer and heating mantle is dispersed 637.3 grams of the above Latex Emulsion B having a 41.93 percent solids content, 135.35 grams of POLYWAX® 725 dispersion having a solids content of 30.67 percent, 100.9 grams of a Blue Pigment PB15:3 dispersion having a solids content of 24.30 percent into 1457.3 grams of water with high shear stirring by means of a polytron. To this mixture is added 54 grams of a coagulant solution consisting of 10 weight percent poly(aluminiumchloride) (PAC) and 90 wt. % 0.02M HNO₃ solution. The PAC solution is added drop-wise at low rpm and as the viscosity of the pigmented latex

5

10

15

20

25

30

mixture increases the rpm of the polytron probe also increases to 5,000 rpm for a period of 2 minutes. This produces a flocculation or heterocoagulation of gelled particles consisting of nanometer sized latex particles, 9% wax and 5% pigment for the core of the particles. The pigmented latex/wax slurry is heated at a controlled rate of 0.5°C/minute up to approximately 52°C and held at this temperature or slightly higher to grow the particles to approximately 5.0 microns. Once the average particle size of 5.0 microns is achieved, 307.7 grams of the latex EA12-79 is then introduced into the reactor while stirring. After an additional 30 minutes to 1 hour the particle size measured is 5.7 microns with a GSD of 1.20. The pH of the resulting mixture is then adjusted from 2.0 to 7.0 with aqueous base solution of 4 percent sodium hydroxide and allowed to stir for an additional 15 minutes. Subsequently, the resulting mixture is heated to 93°C at 1.0°C per minute and the particle size measured is 5.98 microns with a GSD by volume of 1.22 and GSD by number of 1.22. The pH is then reduced to 5.5 using a 2.5 percent Nitric acid solution. The resultant mixture is then allowed to coalesce for 2 hrs at a temperature of 93°C. The morphology of the particles is smooth and "potato" shape. The final particle size after cooling but before washing is 5.98 microns with a GSD by volume of 1.21. The particles are washed 6 times, where the 1st wash is conducted at pH of 10 at 63°C, followed by 3 washes with deionized water at room temperature, one wash carried out at a pH of 4.0 at 40°C, and finally the last wash with deionized water at room temperature. The final average particle size of the dried particles is 5.98 microns with $GSD_v = 1.22$ and $GSD_n = 1.22$. The glass transition temperature of this sample is measured by DSC and found to have Tg(onset) = 49.8°C.

The particles are dried blended with the above-described standard additive package to produce a free flowing toner. Then 805 grams of developer is prepared using 76.5 grams of this toner and 773.5 grams of 35 micron Xerox DocuColor 2240 carrier. The developer is conditioned overnight in A-zone and C-zone. The developer is evaluated in a belt fuser system operating at a print speed of 60 PPM and fusing speed of 80 PPM.

The image gloss fusing results of the toner particles; containing optimized high gloss Latex Emulsion B, obtained on the Sfida Mark 3 60/80PPM bench fixture

and on the Imari-MF FBNF (DocuColor 2240) fixture are described below. This data is compared to that of the toner particles of Example 1; containing a lower gloss Latex Emulsion A, at the same weight percent of KEMAMIDE® S-180 wax instead of POLYWAX® 725.

5

10

15

20

25

30

Example 1:

Preparation of emulsion/aggregation toner containing 9% KEMAMIDE® S-180.

Step 1: Preparation of KEMAMIDE® S-180 Wax Emulsion. A wax emulsion containing KEMAMIDE® S-180 stearyl stearamide wax (Witco, USA) and Neogen RK anionic surfactant (Daiichi Kogyo Seiyaku Co. Ltd., Japan), is prepared using a high pressure homogenizer. The surfactant-to-wax ratio in the emulsion is 2.5 pph. The sample descriptions are as follows:

A stable aqueous wax emulsion containing stearyl stearamide wax particles and one or more anionic stabilizers in water are produced using a high pressure homogenization process. The wax content of said emulsion is in the range from about 10 to about 50 per cent by weight. The wax particles have an average diameter of in the range from about 100 to about 500 nm as measured with a Microtrac UPA150 particle size analyzer, and have a peak melting point in the range from about 70 to about 120°C as measured by DSC. A particularly useful stearyl stearamide wax in said emulsion is KEMAMIDE® S-180 stearyl stearamide wax from Witco (USA) having a peak melting point of about 95°C as measured by DSC. An example of a particularly useful anionic surfactant is Neogen RK (Daiichi Kogyo Seiyaku Co. Ltd., Japan) which consists primarily of branched sodium dodecyl benzenene sulphonate. The amount of surfactant or stabilizer needed to stabilize the wax emulsion depends very much on the wax and surfactant structures. A typical amount of Neogen RK needed to produce a stable wax emulsion is about 2.5 parts per hundred (pph) surfactant-to-wax ratio.

An exemplary process to fabricate said wax emulsion is illustrated in Figure 1 and is described as follows. The equipment includes a homogenizer 10, such as a Gaulin 15MR homogenizer (APV Homogenizer Group, Wilmington, MA) and a

suitable reactor 20, such as a 1 US gal stainless steel jacketed reactor with steam heating and water cooling capability. A crystalline stearyl stearamide wax (usually in powder form), surfactant or stabilizer (usually in the form of a dilute aqueous solution) and deionized water are mixed together in the reactor. The mixture is stirred and heated to a temperature higher than the peak melting point of the wax to melt the wax. Typically, the desired temperature is 10°C or more higher than the peak melting point of the wax. A higher temperature usually results in a smaller wax particle size in the product. For the present stearyl stearamide wax, which has a peak melting point of about 95°C, the mixture is heated to a temperature in the range from about 115 to about 125°C, and more specifically about 120°C. In order to heat the mixture to above 100°C, a sealed reactor and circulation system is used, which can operate at above atmospheric pressure. Once the desired temperature is achieved, the mixture is pumped through the homogenizer. The homogenizer has two valves in series - a primary valve that operates at high pressure up to 8,000 psi during homogenization and a secondary valve that operates at lower pressures up to about 1,000 psi. Initially, the homogenizer is operated in pre-emulsification mode where the primary valve is fully open and the secondary valve is partially closed to generate a pressure drop of about 800 to about 1,000 psi. The wax mixture is pre-emulsified for a desired period of time, up to 8 theoretical passes (time for one theoretical pass is defined by the mixture volume divided by the volumetric flow rate through the homogenizer). For a 4 liter mixture pumped at 1 liter per minute, one theoretical pass takes about 4 minutes. 30 minutes of pre-emulsification in this case is equivalent to about 7.5 theoretical passes. After pre-emulsification, the primary valve is partially closed to increase the homogenizer pressure to a desired pressure in the range from about 3,000 psi to about 8,000 psi. Emulsification is carried out for a number of theoretical passes ranging from about 5 to about 15 passes. Operating at a higher pressure for a longer time results in a smaller wax particle size in the product. For the present emulsion, the homogenizer pressure is about 1,000 psi for 30 minutes (pre-emulsification) and about 8,000 psi for 60 minutes (emulsification). After completion of emulsification, the homogenizer is stopped and the wax emulsion in the reactor is cooled to ambient room temperature, discharged into a product container and filtered through a filter bag

10

15

20

25

30

(typically having about 1 to about 50 micron pore size). Pore size of the polyester filter bag in the present example is about 5 microns.

The wax emulsion of the present example is described in Table 1.

Table 1
Wax emulsion of Example 1 based on KEMAMIDE® S-180 stearyl stearamide.

Sample	Solids Content (%)	Wax Content (%)	d _{3,50} (nm)	d _{3,90} (nm)
Stearyl stearamide wax	19.15	18.68	188	292

10

15

20

25

Step 2: Preparation of styrene/n-butyl acrylate emulsion/aggregation toner containing 9% KEMAMIDE® S-180. Into a 4 liter glass reactor equipped with an overhead stirrer and heating mantle is dispersed 626.4 grams of the above Latex Emulsion A having a 41.76 percent solids content, 216.78 grams of KEMAMIDE® S-180 wax dispersion having a solids content of 19.15 percent, 100.9 grams of a Blue Pigment PB15:3 dispersion having a solids content of 24.3 percent into 1381.6 grams of water with high shear stirring by means of a polytron. To this mixture is added 54 grams of a coagulant solution consisting of 10 weight percent poly(aluminiumchloride) (PAC) and 90 wt. % 0.02M HNO₃ solution. The PAC solution is added drop-wise at low rpm and as the viscosity of the pigmented latex mixture increases the rpm of the polytron probe also increases to 5,000 rpm for a period of 2 minutes. This produces a flocculation or heterocoagulation of gelled particles consisting of nanometer sized latex particles, 9% wax and 5% pigment for the core of the particles. The pigmented latex/wax slurry is heated at a controlled rate of 0.5°C/minute up to approximately 47°C and held at this temperature for 75 minutes producing particles of approximately 5.0 microns and GSD by volume = 1.21. Once the average particle size of 5.0 microns is achieved, 308.9 grams of the Latex Emulsion A is then introduced into the reactor while stirring to produce a shell around the pigmented wax core. After an additional 30 minutes the particle size measured is 5.7 microns with a GSD by volume = 1.20. The pH of the resulting mixture is then adjusted from 2.0 to 7.0 with aqueous base solution of 4 percent sodium hydroxide

and allowed to stir for an additional 15 minutes to freeze the particle size. Subsequently, the resulting mixture is heated to 93°C at 1.0°C per minute and the particle size measured is 5.86 microns with a GSD of 1.22. The pH is then reduced to 5.5 using a 2.5 percent Nitric acid solution. The resultant mixture is then allowed to coalesce for 5 hrs at a temperature of 93°C. The morphology of the particles is smooth and "potato" shape. The final particle size after cooling but before washing is 6.1 microns with a GSDv of 1.22. The particles are washed 6 times, where the 1st wash is conducted at pH of 10 at 63°C, followed by 3 washes with deionized water at room temperature, one wash carried out at a pH of 4.0 at 40°C, and finally the last wash with deionized water at room temperature. The final average particle size of the dried particles is 5.91 microns with $GSD_v = 1.22$ and $GSD_n = 1.22$. Two batches (450 gram scale) are combined together to give an overall yield of 792 grams (90 percent) yield. The glass transition temperature of this toner is 45.8°C as measured by DSC and the melt point of the crystalline KEMAMIDE wax in the toner is very sharp at 92.6°C.

10

15

20

25

30

For the evaluation of the toner particles in the 80/80PPM fixture the particles are dried blended with the above-described standard additive package to produce a free flowing toner. Then 805 grams of developer is prepared at 5% toner concentration by weight using 76.5 grams of this toner and 773.5 grams of 35 micron Xerox DocuColor 2240 carrier. The developer is conditioned overnight in A-zone and C-zone. Table 2 below and Figure 2 show the image gloss of the toner particles of this Example 1 compared to the toner particles of Comparative Example 2, i.e., toners containing the same latex obtained on the Sfida Mark 3 80/80PPM 2.1 belt fuser bench fixture. All gloss data is measured at a 75 degree angle. A peak gloss for toner particles of Comparative Example 2 of 90 ggu is obtained at an external heat roll (EHR) temperature of 220°C. The equivalent 90 ggu image gloss for the toner particles of Example 1 made using the same latex is achieved at a lower external heat roll temperature of only 210°C, which is a 10°C reduction in fusing temperature. A conventional polyester control toner obtains 90 ggu image gloss at an external heat roll temperature of 200°C, which is 10°C lower than the toner of Example 1. The best high gloss toner using POLYWAX® 725 is for toner particles of Comparative

Example 3, which contains the optimized high gloss latex of Latex Emulsion B achieved a 90 ggu image gloss at an external heat roll temperature of only 197°C, which is 17°C lower than the toner particles of Example 1. If this high gloss latex Latex Emulsion B is used with KEMAMIDE® S-180 wax to make another toner, then the fused image gloss of that toner would be expected to be better than the results provided by the toner particles of Comparative Example 3.

Table 2
Temperature Required to Achieve Gloss 90 for Different Toners

10

15

20

25

	EHR Temp@Gloss 90	Difference from Example 1
Example 1	210	-
Comp. Example 3	197	-13
Control	200	-10
Comp. Example 2	220	+10

The toner particles of Example 1 are also evaluated on the oil-less Free Belt Nip Fuser system, which is the fusing system for the Imari-MF 22PPM color printer. Presented in Table 3 below and in Figure 3 is the image gloss of the toner particles of Example 1 compared to two other toners, the toner particles of Comparative Example 1 and a low gloss control toner, on Lustro Gloss coated paper, as fused on the Free Belt Nip Fuser fixture. All gloss data is measured at a 75 degree angle. The low gloss control toner is an example of a commercial toner that is used in the Xerox DocuColor 2240 product. It contains 9% POLYWAX® 725 wax, and is made from a styrene/nbutyl acrylate latex with Mw=33K and Tg=51°C. The toner particles of Comparative Example 1 are made in a similar fashion with 9% POLYWAX ®725 wax, and made with a higher gloss styrene/n-butyl acrylate EP latex with Mw=24.7K and Tg=51.5°C. The increase in gloss is due to the reduction in Mw from the low gloss toner to the toner particles of Comparative Example 1. On LG paper the fusing temperature required to reach gloss = 60gu is lowered by about 28°C, by lowering the latex Mw from 33,200 daltons to 24,700 daltons. It can be seen that the use of 9% of KEMAMIDE® S-180 in the toner particles of Example 1 instead of POLYWAX®

725 in the toner particles of Comparative Example 1 produces a further reduction of about 8°C in the Gloss 60 fusing temperature on LG paper.

Table 3
Temperature Required to Achieve Gloss 60 for Different Toners

	HR Temp@Gloss 60	Difference from Example 1
Example 1	147	-
Comparative		
Example 1	155	+8
Low gloss		
control	183	+36

Example 2:

10

15

20

25

Preparation of emulsion/aggregation toner containing 9% UNICID® 550.

Step 1: Preparation of UNICID® 550 Wax Emulsion. A wax emulsion, containing crystalline carboxylic acid terminated UNICID® 550 polyethylene wax (Baker Petrolite, USA) and Neogen RK anionic surfactant (Daiichi Kogyo Seiyaku Co. Ltd., Japan), is prepared in a high pressure homogenizer, as described in Example 1 above. The surfactant-to-wax ratio in the emulsion is 2.5 pph.

A stable aqueous wax emulsion containing crystalline carboxylic acid terminated polyethylene wax particles and one or more anionic stabilizers in water are produced using a high pressure homogenization process. The wax content of said emulsion is in the range from about 10 to about 50 per cent by weight. The wax particles have an average diameter of in the range from about 100 to about 500 nm as measured with a Microtrac UPA150 particle size analyzer, and have a peak melting point in the range from about 70 to about 120°C as measured by DSC. A particularly useful carboxylic acid terminated polyethylene wax in said emulsion is UNICID[®] 550 wax from Baker Petrolite (USA) having a peak melting point of about 100°C as measured by DSC. An example of a particularly useful anionic surfactant is Neogen RK (Daiichi Kogyo Seiyaku Co. Ltd., Japan) which consists primarily of branched sodium dodecyl benzenene sulphonate. The amount of surfactant or stabilizer needed

A typical amount of Neogen RK needed to produce a stable wax emulsion is about 2.5 parts per hundred (pph) surfactant-to-wax ratio. The wax emulsion of the present example is described in Table 4.

Table 4
Wax emulsion based on UNICID® 550 carboxylic acid terminated polyethylene wax.

Sample	Solids Content (%)	Wax Content (%)	d _{3,50} (nm)	d _{3,90} (nm)
Example 2	19.15	18.68	223	315

10

15

20

25

30

Step 2: Preparation of styrene/n-butyl acrylate emulsion/aggregation toner containing 9% UNICID® 550 montan wax. Into a 4 liter glass reactor equipped with an overhead stirrer and heating mantle is dispersed 626.4 grams of the above Latex Emulsion A having a 42.66 percent solids content, 216.78 grams of UNICID® 550 wax dispersion having a solids content of 19.15 percent, 143.2 grams of a Blue Pigment PB15:3 dispersion having a solids content of 17.13 percent into 1344.5 grams of water with high shear stirring by means of a polytron. To this mixture is added 54 grams of a coagulant solution consisting of 10 weight percent poly(aluminiumchloride) (PAC) and 90 wt. % 0.02M HNO₃ solution. The PAC solution is added drop-wise at low rpm and as the viscosity of the pigmented latex mixture increases the rpm of the polytron probe also increases to 5,000 rpm for a period of 2 minutes. This produces a flocculation or heterocoagulation of gelled particles consisting of nanometer sized latex particles, 9% wax and 5% pigment for the core of the particles. The pigmented latex/wax slurry is heated at a controlled rate of 0.5°C/minute up to approximately 47°C and held at this temperature for 75 minutes producing particles of approximately 5.0 microns and GSD by volume = 1.21. Once the average particle size of 5.0 microns is achieved, 302.4 grams of the Latex Emulsion A is then introduced into the reactor while stirring to produce a shell around the pigmented wax core. After an additional 30 minutes the particle size measured is 5.7 microns with a GSD by volume = 1.21. The pH of the resulting mixture is then adjusted from 2.0 to 7.0 with aqueous base solution of 4 percent sodium hydroxide and allowed to stir for an additional 15 minutes to freeze the particle size. Subsequently, the resulting mixture is heated to 93°C at 1.0°C per minute and the

particle size measured is 6.05 microns with a GSD of 1.20. The pH is then reduced to 5.5 using a 2.5 percent Nitric acid solution. The resultant mixture is then allowed to coalesce for 5 hrs at a temperature of 93°C. The morphology of the particles is smooth and "potato" shape. The final particle size after cooling but before washing is 6.05 microns with a GSDv of 1.20. The particles are washed 6 times, where the 1st wash is conducted at pH of 10 at 63°C, followed by 3 washes with deionized water at room temperature, one wash carried out at a pH of 4.0 at 40°C, and finally the last wash with deionized water at room temperature. The final average particle size of the dried particles is 6.06 microns with $GSD_v = 1.20$ and $GSD_n = 1.22$. Two batches (450 gram scale) are combined together to give an overall yield of 791 grams (88 percent) yield. The glass transition temperature of this toner is 45.6°C as measured by DSC.

10

15

20

25

30

For the evaluation of the toner particles of Example 2 in the Sfida 80/80PPM fixture the particles are dried blended with the above-described standard additive package to produce a free flowing toner. Then 805 grams of developer is prepared at 5% toner concentration by weight using 76.5 grams of this toner and 773.5 grams of 35 micron Xerox DocuColor 2240 carrier. The developer is conditioned overnight in A-zone and C-zone. As shown in Table 5 below and Figure 4 is the image gloss of the toner particles of Comparative Example 2 compared to the toner particles of Example 2 obtained on the Sfida Mark 3 80/80PPM 2.1 belt fuser bench fixture. All gloss data is measured at a 75 degree angle. A peak gloss for the toner particles of Comparative Example 2 of 90 ggu is obtained at an external heat roll (EHR) temperature of 220°C. The equivalent 90 ggu image gloss for the toner particles of Example 2 made using the same latex is achieved at a much lower external heat roll temperature of only 190°C, which is a 30°C reduction in fusing temperature. A typical conventional polyester control toner obtains 90 ggu image gloss at an external heat roll temperature of 200°C, which is 10°C higher than the toner particles of Example 2. The best high gloss latex using POLYWAX® 725 in the toner particles of Comparative Example 3 achieves a 90 ggu image gloss at an external heat roll temperature of 197°C, which is 7°C higher than the toner particles of Example 2. If this high gloss latex Latex Emulsion B is used with the crystalline UNICID®550 wax to make another toner then the fused image gloss of that toner is expected to be better than the toner particles of Comparative Example 3 and the toner particles of Example 2.

Table 5
Temperature Required to Achieve Gloss 90 for Different Toners

	EHR Temp@Gloss 90	Difference from Example 2
Example 2	190	-
Comp. Example 2	197	+7
Control	200	+10
Comp. Example 2	220	+30

The toner particles of Example 2 is also evaluated on the oil-less Free Belt Nip Fuser system which is the fusing system for the Imari-MF color printer. Presented in Table 6 below and Figure 5 is the image gloss of the toner particles of Example 2 compared to two other toners, the toner particles of Comparative Example 1, and a conventional low gloss toner, on Lustro Gloss coated paper as fused on the Free Belt Nip Fuser fixture. All gloss data is measured at a 75 degree angle. The low gloss toner contains 9% POLYWAX® 725 wax, and is made from a styrene/n-butyl acrylate latex with Mw = 33,000 daltons and Tg=51 $^{\circ}$ C. The toner particles of Comparative Example 1 are made in a similar fashion with 9% POLYWAX® 725 wax, but with a higher gloss styrene/n-butyl acrylate EP latex with Mw = 24,700 daltons and Tg = 51.5°C. The increase in gloss is due to the reduction in Mw from the low gloss toner to the toner particles of Comparative Example 1. On LG paper the fusing temperature required to reach gloss = 50gu is lowered by about 22°C, by lowering the latex Mw from 33,200 to 24,700 daltons. It can be seen that the use of the toner particles of Example 2 with 9% of UNICID® 550 produces a further reduction of about 8°C in the Gloss 50 fusing temperature on LG paper.

10

15

20

30

Table 6
Temperature Required to Achieve Gloss 60 for Different Toners

	HR Temp@Gloss 50	Difference from Example 2
Example 2	140	
Comp. Example 1	148	+8
Low gloss		
toner	170	+30

5 Example 3:

10

15

20

25

Preparation of emulsion/aggregation toner containing 9% carnauba wax.

Step 1: Preparation of carnauba wax emulsion. A wax emulsion containing RC-160 carnauba wax (Toa Kasei Co. Ltd., Japan) and Neogen RK anionic surfactant (Daiichi Kogyo Seiyaku Co. Ltd., Japan), is prepared using a high pressure homogenizer. The surfactant-to-wax ratio in the emulsion was 2.5 pph. The sample descriptions are as follows: A stable aqueous wax emulsion containing carnauba wax particles and one or more anionic stabilizers in water are produced using a high pressure homogenization process. The wax content of said emulsion is in the range from about 10 to about 50 per cent by weight. The wax particles have an average diameter of in the range from about 100 to about 500 nm as measured with a Microtrac UPA150 particle size analyzer, and have a peak melting point in the range from about 60 to about 100°C as measured by DSC. A particularly useful carnauba wax in said emulsion is RC-160 carnauba wax from Toa Kasei Co. Ltd. (Japan) having a peak melting point of about 84°C as measured by DSC. An example of a particularly useful anionic surfactant is Neogen RK (Daiichi Kogyo Seiyaku Co. Ltd., Japan), which consists primarily of branched sodium dodecyl benzenene sulphonate. The amount of surfactant or stabilizer needed to stabilize the wax emulsion depends very much on the wax and surfactant structures. A typical amount of Neogen RK needed to produce a stable wax emulsion is about 2.5 parts per hundred (pph) surfactant-to-wax ratio. The wax emulsion of the present example is described in Table 7.

31 Table 7 Wax emulsion of Example 3 based on RC-160 carnauba wax.

Sample	Solids Content (%)	Wax Content (%)	d _{3,50} (nm)	d _{3,90} (nm)
Example 3	18.28	17.83	287	467

Step 2: Preparation of styrene/n-butyl acrylate emulsion/aggregation toner containing 9% RC-160 carnauba wax. Into a 4 liter glass reactor equipped with an overhead stirrer and heating mantle is dispersed 626.4 grams of the above Latex Emulsion A having a 42.66 percent solids content, 227.34 grams of RC-160 carnauba wax dispersion having a solids content of 18.28 percent, 143.2 grams of a Blue Pigment PB15:3 dispersion Lot Number WS1824 having a solids content of 17.13 percent into 1334.0 grams of water with high shear stirring by means of a polytron. To this mixture is added 54 grams of a coagulant solution consisting of 10 weight percent poly(aluminiumchloride) (PAC) and 90 wt.% 0.02M HNO₃ solution. The PAC solution is added drop-wise at low rpm and as the viscosity of the pigmented latex mixture increases the rpm of the polytron probe also increases to 5,000 rpm for a period of 2 minutes. This produces a flocculation or heterocoagulation of gelled particles consisting of nanometer sized latex particles, 9% wax and 5% pigment for the core of the particles. The pigmented latex/wax slurry is heated at a controlled rate of 0.5°C/minute up to approximately 47°C and held at this temperature for 75 minutes producing particles of approximately 5.0 microns and GSD by volume = 1.21. Once the average particle size of 5.0 microns is achieved, 302.4 grams of the Latex Emulsion A is then introduced into the reactor while stirring to produce a shell around the pigmented wax core. After an additional 30 minutes the particle size measured is 5.7 microns with a GSD by volume = 1.20. The pH of the resulting mixture is then adjusted from 2.0 to 7.0 with aqueous base solution of 4 percent sodium hydroxide and allowed to stir for an additional 15 minutes to freeze the particle size. Subsequently, the resulting mixture is heated to 93°C at 1.0°C per minute and the particle size measured is 5.86 microns with a GSD of 1.22. The pH is then reduced to 5.5 using a 2.5 percent Nitric acid solution. The resultant mixture is then allowed to coalesce for 5 hrs at a temperature of 93°C. The morphology of the particles is smooth and "potato" shape. The final particle size after cooling but before washing is

10

20

30

5.98 microns with a GSDv of 1.21. The particles are washed 6 times, where the 1st wash is conducted at pH of 10 at 63°C, followed by 3 washes with deionized water at room temperature, one wash carried out at a pH of 4.0 at 40°C, and finally the last wash with deionized water at room temperature. The final average particle size of the dried particles is 6.06 microns with $GSD_v = 1.20$ and $GSD_n = 1.25$. Two batches (450 gram scale) are combined together to give an overall yield of 794 grams (90 percent) yield. The glass transition temperature of this toner is 43.4°C as measured by DSC and the sharp crystalline wax melting point is 84.12°C.

10

15

20

25

30

For the evaluation of the toner particles of Example 3 in the Sfida 80/80PPM fixture the particles are dried blended with the above-described standard additive package to produce a free flowing toner. Then 805 grams of developer is prepared at 5% toner concentration by weight using 76.5 grams of this toner and 773.5 grams of 35 micron Xerox DocuColor 2240 carrier. The developer is conditioned overnight in A-zone and C-zone. As shown in Table 8 below and Figure 6 is the image gloss of the toner particles of Comparative Example 2 compared to the toner particles of Example 3 obtained on the Sfida Mark 3 80/80PPM 2.1 belt fuser bench fixture. All gloss data is measured at a 75 degree angle. A peak gloss for the toner particles of Comparative Example 2 of 90 ggu is obtained at an external heat roll (EHR) temperature of 220°C. The equivalent 90 ggu image gloss for the toner particles of Example 3 made using the same latex is achieved at a much lower external heat roll temperature of only 200°C, which is a 20°C reduction in fusing temperature. This toner with the crystalline carnauba wax reaches a gloss 90 at the same temperature that the typical conventional polyester control toner does. The typical conventional polyester control toner obtains 90 ggu image gloss at an external heat roll temperature of 200°C, which is equal to that of the toner particles of Example 3. The best high gloss latex toner using POLYWAX® 725 is for the toner particles of Comparative Example 3 toner which contains the optimized high gloss latex Latex Emulsion B achieved a 90 ggu image gloss at an external heat roll temperature of 197°C, which is only 3°C lower than the toner particles of Example 3. If this high gloss latex Latex Emulsion B is used with the crystalline RC-160 carnauba wax to make another toner then the fused

image gloss of that toner is expected to be better than the toner particles of Comparative Example 3.

Table 8
Temperature Required to Achieve Gloss 90 for Different Toners

10

15

20

25

	EHR Temp@Gloss 90	Difference from Example 3
Example 3	200	
Comp.		
Example 3	197	-3
Control	200	_
Comp.		
Comp. Example 2	220	+20

The toner particles of Example 3 are also evaluated on the oil-less Free Belt Nip Fuser system which is the fusing system for the Imari-MF 22PPM color printer. Presented in Table 9 below and Figure 7 is the image gloss of the toner particles of Example 3 compared to two other toners, the toner particles of Comparative Example 1 and a conventional low gloss toner, on Lustro Gloss coated paper, as fused on the Free Belt Nip Fuser fixture. All gloss data was measured at a 75 degree angle. The emulsion aggregation low gloss toner contains 9% POLYWAX® 725 wax, and is made from a styrene/n-butyl acrylate latex with Mw = 33,000 daltons and Tg = 51°C. The toner particles of Comparative Example 1 are made in a similar fashion with 9% POLYWAX® 725 wax, and made with a higher gloss S/n-BA EP latex with Mw = 24,700 daltons and Tg = 51.5°C. The increase in gloss is due to the reduction in Mw from the low gloss toner to the toner particles of Comparative Example 1. On LG paper the fusing temperature required to reach gloss = 60gu is lowered by about 28°C, by lowering the latex Mw from 33,200 to 24,700 daltons. It can be seen that the use of 9% of carnauba RC-160 in the toner particles of Example 3 instead of POLYWAX® 725 in the toner particles of Comparative Example 1 produces a further reduction of about 12°C in the Gloss 60 fusing temperature on LG paper.

Table 9
Temperature Required to Achieve Gloss 60 for Different Toners

	HR Temp@Gloss 60	Difference from Example 3
Example 3	143	-
Comp. Example 1	155	+12
Low gloss toner	183	+40

)

Example 4:

Table 10.

Preparation of emulsion/aggregation toner containing 9% LICOWAX® S montan wax

Step 1: Preparation of LICOWAX® S wax emulsion. A wax emulsion 10 containing LICOWAX® S montan wax (Clariant Corp., USA) and Neogen RK anionic surfactant (Daiichi Kogyo Seiyaku Co. Ltd., Japan), is prepared using a high pressure homogenizer. The surfactant-to-wax ratio in the emulsion was 2.5 pph. The sample descriptions are as follows: A stable aqueous wax emulsion containing high acid montan wax particles and one or more anionic stabilizers in water are produced 15 using a high pressure homogenization process. The wax content of said emulsion is in the range from about 10 to about 50 per cent by weight. The wax particles have an average diameter of in the range from about 100 to about 500 nm as measured with a Microtrac UPA150 particle size analyzer, and have a peak melting point in the range from about 70 to about 120°C as measured by DSC. A particularly useful high acid 20 montan wax in said emulsion is LICOWAX®S wax from Clariant Corp. (USA) having a peak melting point of about 82°C as measured by DSC. An example of a particularly useful anionic surfactant is Neogen RK (Daiichi Kogyo Seiyaku Co. Ltd., Japan), which consists primarily of branched sodium dodecyl benzenene sulphonate. 25 The amount of surfactant or stabilizer needed to stabilize the wax emulsion depends very much on the wax and surfactant structures. A typical amount of Neogen RK needed to produce a stable wax emulsion is about 2.5 parts per hundred (pph) surfactant-to-wax ratio. The wax emulsion of the present example is described in

Table 10
Wax emulsion of Example 4 based on LICOWAX® S.

Sample	Solids Content (%)	Wax Content	d _{3,50} (nm)	d _{3,90} (nm)
		(%)		
Example 4	18.96	18.50	182	271

5

10

15

20

30

Step 2: Preparation of styrene/n-butyl acrylate emulsion/aggregation toner containing 9% LICOWAX® S montan wax. Into a 4 liter glass reactor equipped with an overhead stirrer and heating mantle is dispersed 626.4 grams of the above latex Latex Emulsion A having a 42.66 percent solids content, 218.95 grams of LICOWAX® S montan wax dispersion having a solids content of 18.96 percent, 143.2 grams of a Blue Pigment PB15:3 dispersion having a solids content of 17.13 percent into 1342.4 grams of water with high shear stirring by means of a polytron. To this mixture is added 54 grams of a coagulant solution consisting of 10 weight percent poly(aluminiumchloride) (PAC) and 90 wt. % 0.02M HNO₃ solution. The PAC solution is added drop-wise at low rpm and as the viscosity of the pigmented latex mixture increases the rpm of the polytron probe also increases to 5,000 rpm for a period of 2 minutes. This produces a flocculation or heterocoagulation of gelled particles consisting of nanometer sized latex particles, 9% wax and 5% pigment for the core of the particles. The pigmented latex/wax slurry is heated at a controlled rate of 0.5 C/minute up to approximately 47°C and held at this temperature for 75 minutes producing particles of approximately 5.0 microns and GSD by volume = 1.21. Once the average particle size of 5.0 microns is achieved, 302.4 grams of the Latex Emulsion A is then introduced into the reactor while stirring to produce a shell around the pigmented wax core. After an additional 30 minutes the particle size measured is 5.7 microns with a GSD by volume = 1.21. The pH of the resulting mixture is then adjusted from 2.0 to 7.0 with aqueous base solution of 4 percent sodium hydroxide and allowed to stir for an additional 15 minutes to freeze the particle size. Subsequently, the resulting mixture is heated to 93°C at 1.0°C per minute and the particle size measured is 5.84 microns with a GSD of 1.22. The pH is then reduced to 5.5 using a 2.5 percent Nitric acid solution. The resultant mixture is then allowed to

coalesce for 5 hrs at a temperature of 93°C. The morphology of the particles is smooth and "potato" shape. The final particle size after cooling but before washing is 5.98 microns with a GSDv of 1.21. The particles are washed 6 times, where the 1st wash is conducted at pH of 10 at 63°C, followed by 3 washes with deionized water at room temperature, one wash carried out at a pH of 4.0 at 40°C, and finally the last wash with deionized water at room temperature. The final average particle size of the dried particles is 5.98 microns with $GSD_v = 1.21$ and $GSD_n = 1.37$. Two batches (450 gram scale) are combined together to give an overall yield of 808 grams (90 percent) yield. The glass transition temperature of this toner is 43.7°C as measured by DSC.

For the evaluation of the toner particles of Example 4 in the Sfida 80/80PPM fixture the particles are dried blended with the above-described standard additive package to produce a free flowing toner. Then 805 grams of developer is prepared at

15

25

5% toner concentration by weight using 76.5 grams of this toner and 773.5 grams of

35 micron Xerox DocuColor 2240 carrier. The developer is conditioned overnight in

A-zone and C-zone. As shown in Table 11 below and Figure 8 is the image gloss of

the toner particles of Comparative Example 2 compared to the toner particles of Example 4 obtained on the Sfida Mark 3 80/80PPM 2.1 belt fuser bench fixture. All

gloss data is measured at a 75 degree angle. A peak gloss for the toner particles of

Comparative Example 2 of 90 ggu is obtained at an external heat roll (EHR)

temperature of 220°C. The equivalent 90 ggu image gloss for the toner particles of

Example 4 made using the same latex is achieved at a much lower external heat roll

temperature of only 170°C, which is a 50°C reduction in fusing temperature. A

typical conventional polyester control toner obtains 90 ggu image gloss at an external

heat roll temperature of 200°C, which is 30°C higher than the toner particles of

Example 4. The best high gloss latex using POLYWAX® 725 in the toner particles

of Comparative Example 3 toner achieves a 90 ggu image gloss at an external heat roll

temperature of 197°C, which is 27°C higher than the toner particles of Example 4.

	EHR Temp@Gloss 90	Difference from Example 4
Example 4	170	
Comp.		
Example 3	197	+27
Control	200	+30
Comp.		
Comp. Example 2	220	+50

The toner particles of Example 4 are also evaluated on the oil-less Free Belt

5

10

15

20

25

Nip Fuser system which is the fusing system for the Imari-MF 22PPM color printer. Presented in Figure 9 is the image gloss of the toner particles of Example 4 compared to two other toners, the toner particles of Comparative Example 3, and a conventional low gloss toner, on both coated paper (Lustro Gloss) and uncoated paper (Color Expressions), as fused on the Free Belt Nip Fuser fixture. All gloss data is measured at a 75 degree angle. The low gloss toner contains 9% POLYWAX® 725 wax, and is made from a styrene/n-butyl acrylate latex with Mw=33,000 daltons and Tg=51°C. The toner particles of Comparative Example 3 is made in a similar fashion with 9% POLYWAX® 725 wax, and made with a high gloss styrene/n-butyl acrylate EP latex with Mw=19,200 daltons and Tg=53.2°C. The increase in gloss is due to the reduction in Mw from the low gloss toner to the toner particles of Comparative Example 3. On LG paper the fusing temperature required to reach gloss = 60gu is lowered by about 30° C, and on CX paper, the temperature required to reach gloss = 40gu is also lowered by about 30°C, by lowering the latex Mw from 33,200 to 19,200 daltons. It can be seen that the use of the toner particles of Example 4 with 9% of LICOWAX® S produces a further reduction of about 15°C in the Gloss 60 fusing temperature on LG paper, and a further reduction of about 20°C in the Gloss 40 temperature on CX paper. The toner particles of Comparative Example 3, made from a latex with Mw=19,200 daltons, is known to have higher gloss than the toner particles of Comparative Example 1 and the toner particles of Comparative Example 2 made from a latex with Mw=24,700 daltons. Therefore, if the image gloss of the toner particles of Example 4 were compared directly to that of the toner particles of

Comparative Examples 1 or 2, as fused on the FBNF, the reduction in Gloss temperatures due to the substitution of 9% LICOWAX® S for 9% POLYWAX® 725 would be even larger than those relative to the toner particles of Comparative Example 3.

While this invention has been described in conjunction with various exemplary embodiments, it is to be understood that many alternatives, modifications and variations would be apparent to those skilled in the art. Accordingly, Applicants intend to embrace all such alternatives, modifications and variations that follow in the spirit and scope of this invention.

WHAT IS CLAIMED IS:

5

15

1. A toner comprising particles of a resin, an optional colorant, and a crystalline wax,

wherein the crystalline wax is selected from the group consisting of aliphatic polar amide functionalized waxes, carboxylic acid-terminated polyethylene waxes, aliphatic waxes consisting of esters of hydroxylated unsaturated fatty acids, high acid waxes, and mixtures thereof, and

wherein said toner particles are prepared by an emulsion aggregation process.

- 2. A toner according to claim 1, wherein the crystalline wax comprises an aliphatic polar amide functionalized wax.
 - 3. A toner according to claim 2, wherein the crystalline wax comprises a stearyl stearamide.
 - 4. A toner according to claim 1, wherein the crystalline wax comprises a carboxylic acid-terminated polyethylene wax.
 - 5. A toner according to claim 4, wherein the crystalline wax has at least an 80% carboxylic acid functionality.
 - 6. A toner according to claim 1, wherein the crystalline wax comprises an aliphatic wax consisting of esters of hydroxylated unsaturated fatty acids.
- 7. A toner according to claim 6, wherein the crystalline wax has a carbon chain length of from about 8 to about 20.
 - 8. A toner according to claim 6, wherein the crystalline wax is a carnauba wax.
- 9. A toner according to claim 1, wherein the crystalline wax comprises a high acid wax.
 - 10. A toner according to claim 9, wherein the crystalline wax is a montanic wax.
 - 11. A toner according to claim 9, wherein the crystalline wax has an acid value of from about 127 to about 160 mg KOH/g.
- 12. A toner according to claim 1, wherein the crystalline wax comprises a mixture of waxes.

13. A toner according to claim 1, wherein the emulsion aggregation process comprises:

shearing a first ionic surfactant with a wax emulsion comprising said crystalline wax, and a latex mixture comprising (a) a counterionic surfactant with a charge polarity of opposite sign to that of said first ionic surfactant, (b) a nonionic surfactant, and (c) a resin, thereby causing flocculation or heterocoagulation of formed particles of resin to form electrostatically bound aggregates;

heating the electrostatically bound aggregates to form aggregates of at least about 1 micron in average particle diameter.

14. A toner according to claim 1, wherein the emulsion aggregation process comprises:

10

15

20

25

30

preparing a colorant dispersion in a solvent, which dispersion comprises a colorant and a first ionic surfactant;

shearing the colorant dispersion with a wax emulsion comprising said crystalline wax, and a latex mixture comprising (a) a counterionic surfactant with a charge polarity of opposite sign to that of said first ionic surfactant, (b) a nonionic surfactant, and (c) a resin, thereby causing flocculation or heterocoagulation of formed particles of colorant and resin to form electrostatically bound aggregates; and

heating the electrostatically bound aggregates to form aggregates of at least about 1 micron in average particle diameter.

15. A toner according to claim 1, wherein the emulsion aggregation process comprises:

shearing an ionic surfactant with a wax emulsion comprising said crystalline wax, and a latex mixture comprising (a) a flocculating agent, (b) a nonionic surfactant, and (c) a resin, thereby causing flocculation or heterocoagulation of formed particles of colorant and resin to form electrostatically bound aggregates;

heating the electrostatically bound aggregates to form aggregates of at least about 1 micron in average particle diameter.

16. A toner according to claim 1, wherein the emulsion aggregation process comprises:

preparing a colorant dispersion in a solvent, which dispersion comprises a colorant and an ionic surfactant;

shearing the colorant dispersion with a wax dispersion comprising said crystalline wax, and a latex mixture comprising (a) a flocculating agent, (b) a nonionic surfactant, and (c) a resin, thereby causing flocculation or heterocoagulation of formed particles of colorant and resin to form electrostatically bound aggregates; and

heating the electrostatically bound aggregates to form aggregates of at least about 1 micron in average particle diameter.

17. A toner according to claim 1, wherein the emulsion aggregation process comprises:

preparing a colloidal solution comprising a resin, said crystalline wax and an optional colorant, and

adding to the colloidal solution an aqueous solution containing a coalescence agent comprising an ionic metal salt to form toner particles.

10

15

20

25

18. A toner according to claim 1, wherein the emulsion aggregation process comprises:

providing a resin latex dispersion of a resin in an aqueous ionic surfactant solution;


providing a pigment dispersion in water of a pigment dispersed in water, an optional dispersant, and an optional an surfactant;


providing a wax dispersion comprising said crystalline wax;
blending the resin latex dispersion shear with the pigment dispersion,
and the wax dispersion under high shear to form a resin-pigment-wax blend;


heating the sheared blend at temperatures below a glass transition temperature (Tg) of the resin while continuously stirring to form aggregate particles;


heating the aggregate particles at temperatures above the Tg of the resin followed by reduction of the pH to form coalesced particles of a toner composition; and


optionally separating and drying the toner composition.























FIG. 9A




FIG. 9B